

DESCRIPTION

MICROCRYSTALLINE GLASS, MICROCRYSTALLINE GLASS PRODUCT AND MANUFACTURING METHOD THEREOF

Technical Field

5 The present invention relates to microcrystalline glass, microcrystalline glass product and manufacturing method thereof, and in particular, to microcrystalline glass, microcrystalline glass product with excellent mechanical and optical properties and suitable for electronic devices or display devices, and manufacturing methods thereof.

Background

10 Microcrystalline glass is a material that precipitates crystals in glass through thermal treatment. It has better mechanical properties than conventional glass and forms crystallites in the glass. Its bending resistance, wear resistance, drop resistance and other properties have significant advantages over conventional glass. On the other hand, the microcrystalline glass can also be chemically strengthened to further improve the mechanical properties.

15 Based on the advantages above, at present, microcrystalline glass or glass products obtained after treating the microcrystalline glass are applied to display devices or electronic devices with higher requirements such as drop resistance, compression resistance, and scratch resistance, especially to front and back covers of portable electronic devices (e.g., mobile phones, watches, PAD, etc.).

20 With the development of science and technology, the electronic devices or the display devices have higher requirements on optical properties of glass materials used therein. The optical properties refer to the properties of the materials in absorption, reflection and refraction of light, including transmittance, haze, $|B|$ value and refractive index, etc. However, the microcrystalline glass currently available in the market have problems such as
25 poor chemical strengthening performance, high haze, and large $|B|$ value, and are thus difficult to be applied to display devices or electronic devices with higher requirements.

Therefore, developing a microcrystalline glass and a microcrystalline glass product with excellent mechanical and optical properties and suitable for display devices or electronic devices has become a pursuit of scientific and technical personnel.

Summary

5 The technical problem to be solved by the present invention is to provide a microcrystalline glass product with excellent mechanical and optical properties.

The technical solution adopted by the present invention for solving the technical problem is as follows:

(1) A microcrystalline glass product, including the following components in percentage
10 by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; and Y_2O_3 : greater than 0 but less than or equal to 8%.

(2) The microcrystalline glass product according to (1) further includes the following components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or BaO : 0-5%; and/or CaO : 0-5%; and/or TiO_2 :
15 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(3) The microcrystalline glass product includes the following components: SiO_2 , Al_2O_3 , Li_2O , ZrO_2 , P_2O_5 , and Y_2O_3 . A crystal phase of the microcrystalline glass product includes
20 lithium monosilicate. The lithium monosilicate has a higher weight percentage than other crystal phases.

(4) The microcrystalline glass product includes the following components: SiO_2 , Al_2O_3 , Li_2O , ZrO_2 , and P_2O_5 . An average light $|B|$ value of the microcrystalline glass product with a thickness of 1 mm or less at 400-800 nm is 0.6 or less.

25 (5) The microcrystalline glass product includes a lithium monosilicate crystal phase. A

drop ball test height of the microcrystalline glass product is 1300 mm or more.

(6) The microcrystalline glass product according to any one of (3) to (5) includes the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; and Y_2O_3 : greater than 0 but less than or equal to 8%.

5 (7) The microcrystalline glass product according to any one of (3) to (6) further includes the following components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or BaO : 0-5%; and/or CaO : 0-5%; and/or TiO_2 : 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or
10 more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(8) The microcrystalline glass product includes the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; Y_2O_3 : greater than 0 but less than or equal to 8%; K_2O : 0-5%; MgO : 0-2%; ZnO : 0-2%; Na_2O : 0-6%; SrO : 0-5%; BaO : 0-5%; CaO : 0-5%; TiO_2 : 0-5%; B_2O_3 : 0-5%; Ln_2O_3 : 0-5%; and a
15 clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(9) The microcrystalline glass product according to any one of (1) to (8), where the content of each component satisfies more than one of the following five situations:

- 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is greater than 0;
- 20 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 2.5-50.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.16-0.9;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 6.0 or less;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is greater than 0 but less than or equal to 0.15.

(10) The microcrystalline glass product according to any one of (1) to (9) includes the

following components in percentage by weight: SiO_2 : 50-65%; and/or Al_2O_3 : 8-15%; and/or Li_2O : 13-22%; and/or ZrO_2 : 6-12%; and/or P_2O_5 : 3.5-9%; and/or K_2O : 0-4%; and/or MgO : 0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%; and/or Y_2O_3 : 1-7%; and/or SrO : 0-3%; and/or BaO : 0-3%; and/or CaO : 0-3%; and/or TiO_2 : 0-3%; and/or B_2O_3 : 0-3%; and/or Ln_2O_3 : 0-4%;
5 and/or a clarifying agent: 0-1%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(11) The microcrystalline glass product according to any one of (1) to (10), where the content of each component satisfies more than one of the following five situations:

- 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.1-1.0;
- 10 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 3.0-40.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

(12) The microcrystalline glass product according to any one of (1) to (11) includes the
15 following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent: 0-0.5%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is
20 one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(13) The microcrystalline glass product according to any one of (1) to (12), where the content of each component satisfies more than one of the following five situations:

- 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.03-0.09.

(14) The microcrystalline glass product according to any one of (1) to (13) excludes SrO ;
5 and/or excludes BaO ; and/or excludes CaO ; and/or excludes ZnO ; and/or excludes PbO ;
and/or excludes As_2O_3 ; and/or excludes TiO_2 ; and/or excludes B_2O_3 ; and/or excludes Ln_2O_3 ;
and/or excludes F ; and/or excludes Ta_2O_5 .

(15) The microcrystalline glass product according to any one of (1) to (14), where a
crystal phase of the microcrystalline glass product includes lithium monosilicate and/or
10 lithium phosphate.

(16) The microcrystalline glass product according to any one of (1) to (15), where the
crystal phase of the microcrystalline glass product mainly includes lithium monosilicate, the
lithium monosilicate has a higher weight percentage than other crystal phases, and the lithium
monosilicate accounts for 10-63.5% of the microcrystalline glass product, and preferably
15 15-55%.

(17) The microcrystalline glass product according to any one of (1) to (16), where the
microcrystalline glass product includes a lithium phosphate crystal phase, and the lithium
phosphate crystal phase accounts for 3-15% of the microcrystalline glass product, and
preferably 5-12%.

20 (18) The microcrystalline glass product according to any one of (1) to (17), where a
surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa
or more, and more preferably 700 MPa or more.

(19) The microcrystalline glass product according to any one of (1) to (18), where a
four-point bending strength of the microcrystalline glass product is 600 MPa or more,
25 preferably 650 MPa or more, and more preferably 700 MPa or more.

(20) The microcrystalline glass product according to any one of (1) to (19), where an ion-exchange layer depth of the microcrystalline glass product is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more.

5 (21) The microcrystalline glass product according to any one of (1) to (20), where a drop ball test height of the microcrystalline glass product is 1300 mm or more, preferably 1400 mm or more, and more preferably 1500 mm or more.

(22) The microcrystalline glass product according to any one of (1) to (21), where fracture toughness of the microcrystalline glass product is 1 $\text{MPa}\cdot\text{m}^{1/2}$ or more, preferably 1.1 $\text{Mpa}\cdot\text{m}^{1/2}$ or more, and more preferably 1.2 $\text{Mpa}\cdot\text{m}^{1/2}$ or more.

10 (23) The microcrystalline glass product according to any one of (1) to (22), where Vickers hardness of the microcrystalline glass product is 700 kgf/mm^2 or more, preferably 720 kgf/mm^2 or more, and more preferably 730 kgf/mm^2 or more.

(24) The microcrystalline glass product according to any one of (1) to (23), where a crystallinity of the microcrystalline glass product is 50% or more, preferably 60% or more,
15 and more preferably 70% or more.

(25) The microcrystalline glass product according to any one of (1) to (24), where a grain size of the microcrystalline glass product is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

(26) The microcrystalline glass product according to any one of (1) to (15), where a haze
20 of the microcrystalline glass product with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less.

(27) The microcrystalline glass product according to any one of (1) to (26), where average transmittance of the microcrystalline glass product with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more.

25 (28) The microcrystalline glass product according to any one of (1) to (27), where

transmittance of the microcrystalline glass product with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more.

(29) The microcrystalline glass product according to any one of (1) to (28), where an average light | B | value of the microcrystalline glass product with the thickness of 1 mm
5 or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

(30) The microcrystalline glass product according to any one of (26) to (29), where the thickness of the microcrystalline glass product is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

10 (31) The microcrystalline glass product according to any one of (1) to (7), where the microcrystalline glass product includes a colorant.

(32) The microcrystalline glass product according to (31), where the colorant includes the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃:
15 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

(33) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: NiO: 0.1-4%; and/or Ni₂O₃: 0.1-4%; and/or CoO: 0.05-2%; and/or Co₂O₃: 0.05-2%; and/or Fe₂O₃: 0.2-7%; and/or MnO₂: 0.1-4%; and/or Er₂O₃: 0.4-8%; and/or Nd₂O₃: 0.4-8%; and/or Cu₂O: 0.5-4%; and/or
20 Pr₂O₃: 0.4-8%; and/or CeO₂: 0.5-4%.

(34) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%; and/or CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%; and/or Fe₂O₃: 0.2-5%; and/or MnO₂: 0.1-3%; and/or Er₂O₃: 0.4-6%; and/or Nd₂O₃: 0.4-6%; and/or Cu₂O: 0.5-3%;
25 and/or Pr₂O₃: 0.4-6%; and/or CeO₂: 0.5-3%.

(35) The microcrystalline glass product according to either (31) or (32), where the

colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%.

(36) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: CoO: 0.05-1.8%;
5 and/or Co₂O₃: 0.05-1.8%.

(37) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: Cu₂O: 0.5-3%; and /or CeO₂: 0.5-3%.

(38) The microcrystalline glass product according to either (31) or (32), where the
10 colorant includes the following components in percentage by weight: Fe₂O₃: 0.2-5%, and CoO: 0.05-0.3%; or Fe₂O₃: 0.2-5%, and Co₂O₃: 0.05-0.3%; or Fe₂O₃: 0.2-5%, CoO: 0.05-0.3%, and NiO: 0.1-1%; or Fe₂O₃: 0.2-5%, Co₂O₃: 0.05-0.3%, and NiO: 0.1-1%.

(39) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: Pr₂O₃: 0.4-6%; or
15 Fe₂O₃: 0.2-5%; or MnO₂: 0.1-3%; or Er₂O₃: 0.4-6%; or Nd₂O₃: 0.4-6%.

(40) The microcrystalline glass product according to either (31) or (32), where the colorant includes the following components in percentage by weight: Er₂O₃: 0.4-6%, Nd₂O₃: 0.4-4%, and MnO₂: 0.1-2%.

The present invention further provides a microcrystalline glass with excellent mechanical
20 and optical properties.

The technical solution adopted by the present invention for solving the technical problem is as follows:

(41) A microcrystalline glass, including the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃:
25 greater than 0 but less than or equal to 8%.

(42) The microcrystalline glass according to (41) further includes the following components in percentage by weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or BaO: 0-5%; and/or TiO₂: 0-5%; and/or CaO: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, where Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

(43) The microcrystalline glass includes the following components: SiO₂, Al₂O₃, Li₂O, ZrO₂, P₂O₅, and Y₂O₃. A crystal phase of the microcrystalline glass includes lithium monosilicate. The lithium monosilicate has a higher weight percentage than other crystal phases.

(44) The microcrystalline glass includes the following components: SiO₂, Al₂O₃, Li₂O, ZrO₂, and P₂O₅. An average light | B | value of the microcrystalline glass with a thickness of 1 mm or less at 400-800 nm is 0.6 or less.

(45) The microcrystalline glass includes a lithium monosilicate crystal phase. A body drop height of the microcrystalline glass is 1000 mm or more.

(46) The microcrystalline glass according to any one of (43) to (45) includes the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃: greater than 0 but less than or equal to 8%.

(47) The microcrystalline glass according to any one of (43) to (46) further includes the following components in percentage by weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or BaO: 0-5%; and/or CaO: 0-5%; and/or TiO₂: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, where Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

(48) The microcrystalline glass includes the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; Y₂O₃:

greater than 0 but less than or equal to 8%; K₂O: 0-5%; MgO: 0-2%; ZnO: 0-2%; Na₂O: 0-6%; SrO: 0-5%; BaO: 0-5%; CaO: 0-5%; TiO₂: 0-5%; B₂O₃: 0-5%; Ln₂O₃: 0-5%; and a clarifying agent: 0-2%, where Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

5 (49) The microcrystalline glass according to any one of (41) to (48), where the components are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

1) Y₂O₃/ZrO₂ is greater than 0;

2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 2.5-50.0;

10 3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.16-0.9;

4) Na₂O/Y₂O₃ is 6.0 or less;

5) Y₂O₃/(Al₂O₃+SiO₂) is greater than 0 but less than or equal to 0.15.

15 (50) The microcrystalline glass according to any one of (41) to (49) includes the following components in percentage by weight: SiO₂: 50-65%; and/or Al₂O₃: 8-15%; and/or Li₂O: 13-22%; and/or ZrO₂: 6-12%; and/or P₂O₅: 3.5-9%; and/or K₂O: 0-4%; and/or MgO: 0-1%; and/or ZnO: 0-1%; and/or Na₂O: 1-5%; and/or Y₂O₃: 1-7%; and/or SrO: 0-3%; and/or TiO₂: 0-3%; and/or BaO: 0-3%; and/or CaO: 0-3%; and/or B₂O₃: 0-3%; and/or Ln₂O₃: 0-4%; and/or a clarifying agent: 0-1%, where Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

20 (51) The microcrystalline glass according to any one of (41) to (50), where the components are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

1) Y₂O₃/ZrO₂ is 0.1-1.0;

2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 3.0-40.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

(52) The microcrystalline glass according to any one of (41) to (51) includes the
5 following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or
 Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 :
2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%;
and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent:
0-0.5%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is
10 one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(53) The microcrystalline glass according to any one of (41) to (52), where the
components are expressed in percentage by weight, and the content of each component
satisfies more than one of the following five situations:

1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;

15 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.03-0.09.

(54) The microcrystalline glass according to any one of (41) to (53) excludes SrO ; and/or
20 excludes BaO ; and/or excludes CaO ; and/or excludes ZnO ; and/or excludes PbO ; and/or
excludes As_2O_3 ; and/or excludes TiO_2 ; and/or excludes B_2O_3 ; and/or excludes Ln_2O_3 ; and/or
excludes F; and/or excludes Ta_2O_5 .

(55) The microcrystalline glass according to any one of (41) to (54), where a crystal
phase of the microcrystalline glass includes lithium monosilicate and/or lithium phosphate.

(56) The microcrystalline glass according to any one of (41) to (55), where the crystal phase of the microcrystalline glass mainly includes lithium monosilicate, the lithium monosilicate has a higher weight percentage than other crystal phases, and the lithium monosilicate accounts for 10-63.5% of the microcrystalline glass, and preferably 15-55%.

5 (57) The microcrystalline glass according to any one of (41) to (56), where the microcrystalline glass includes a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% of the microcrystalline glass, and preferably 5-12%.

(58) The microcrystalline glass according to any one of (41) to (57), where a crystallinity of the microcrystalline glass is 50% or more, preferably 60% or more, and more preferably
10 70% or more.

(59) The microcrystalline glass according to any one of (41) to (58), where a grain size of the microcrystalline glass is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

(60) The microcrystalline glass according to any one of (41) to (59), where a coefficient
15 of thermal expansion of the microcrystalline glass is $75-95 \times 10^{-7}/K$.

(61) The microcrystalline glass according to any one of (41) to (60), where a refractive index of the microcrystalline glass is 1.5700-1.5800.

(62) The microcrystalline glass according to any one of (41) to (61), where a body drop height of the microcrystalline glass is 1000 mm or more, preferably 1100 mm or more, and
20 more preferably 1200 mm or more.

(63) The microcrystalline glass according to any one of (41) to (62), where Vickers hardness of the microcrystalline glass is 650 kgf/mm² or more, preferably 680 kgf/mm² or more, and more preferably 700 kgf/mm² or more.

(64) The microcrystalline glass according to any one of (41) to (63), where a haze of the
25 microcrystalline glass with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or

less, and more preferably 0.1% or less.

(65) The microcrystalline glass according to any one of (41) to (64), where average transmittance of the microcrystalline glass with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more.

5 (66) The microcrystalline glass according to any one of (41) to (65), where transmittance of the microcrystalline glass with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more.

(67) The microcrystalline glass according to any one of (41) to (66), where an average light |B| value of the microcrystalline glass with the thickness of 1 mm or less at
10 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

(68) The microcrystalline glass according to any one of (64) to (67), where the thickness of the microcrystalline glass is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

(69) The microcrystalline glass according to any one of (41) to (47), where the
15 microcrystalline glass includes a colorant.

(70) The microcrystalline glass according to (69), where the colorant includes the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

20 (71) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: NiO: 0.1-4%; and/or Ni₂O₃: 0.1-4%; and/or CoO: 0.05-2%; and/or Co₂O₃: 0.05-2%; and/or Fe₂O₃: 0.2-7%; and/or MnO₂: 0.1-4%; and/or Er₂O₃: 0.4-8%; and/or Nd₂O₃: 0.4-8%; and/or Cu₂O: 0.5-4%; and/or Pr₂O₃: 0.4-8%; and/or CeO₂: 0.5-4%.

25 (72) The microcrystalline glass according to either (69) or (70), where the colorant

includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%; and/or CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%; and/or Fe₂O₃: 0.2-5%; and/or MnO₂: 0.1-3%; and/or Er₂O₃: 0.4-6%; and/or Nd₂O₃: 0.4-6%; and/or Cu₂O: 0.5-3%; and/or Pr₂O₃: 0.4-6%; and/or CeO₂: 0.5-3%.

5 (73) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%.

 (74) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: CoO: 0.05-1.8%; and/or Co₂O₃:
10 0.05-1.8%.

 (75) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: Cu₂O: 0.5-3%; and /or CeO₂: 0.5-3%.

 (76) The microcrystalline glass according to either (69) or (70), where the colorant
15 includes the following components in percentage by weight: Fe₂O₃: 0.2-5%, and CoO: 0.05-0.3%; or Fe₂O₃: 0.2-5%, and Co₂O₃: 0.05-0.3%; or Fe₂O₃: 0.2-5%, CoO: 0.05-0.3%, and NiO: 0.1-1%; or Fe₂O₃: 0.2-5%, Co₂O₃: 0.05-0.3%, and NiO: 0.1-1%.

 (77) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: Pr₂O₃: 0.4-6%; or Fe₂O₃:
20 0.2-5%; or MnO₂: 0.1-3%; or Er₂O₃: 0.4-6%; or Nd₂O₃: 0.4-6%.

 (78) The microcrystalline glass according to either (69) or (70), where the colorant includes the following components in percentage by weight: Er₂O₃: 0.4-6%, Nd₂O₃: 0.4-4%, and MnO₂: 0.1-2%.

The present invention further provides matrix glass.

25 The technical solution adopted by the present invention for solving the technical problem

is as follows:

(79) Matrix glass, including the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; and Y_2O_3 : greater than 0 but less than or equal to 8%.

5 (80) The matrix glass according to (79) further includes the following components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or BaO : 0-5%; and/or CaO : 0-5%; and/or TiO_2 : 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 ,
10 SnO , CeO_2 , F, Cl, and Br.

(81) The matrix glass includes the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; Y_2O_3 : greater than 0 but less than or equal to 8%; K_2O : 0-5%; MgO : 0-2%; ZnO : 0-2%; Na_2O : 0-6%; SrO : 0-5%; BaO : 0-5%; CaO : 0-5%; TiO_2 : 0-5%; B_2O_3 : 0-5%; Ln_2O_3 : 0-5%; and a clarifying agent:
15 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(82) The matrix glass according to any one of (79) to (81), where the components are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 20 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is greater than 0;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 2.5-50.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.16-0.9;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 6.0 or less;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is greater than 0 but less than or equal to 0.15.

(83) The matrix glass according to any one of (79) to (82) includes the following components in percentage by weight: SiO_2 : 50-65%; and/or Al_2O_3 : 8-15%; and/or Li_2O : 13-22%; and/or ZrO_2 : 6-12%; and/or P_2O_5 : 3.5-9%; and/or K_2O : 0-4%; and/or MgO : 0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%; and/or Y_2O_3 : 1-7%; and/or SrO : 0-3%; and/or TiO_2 : 0-3%; and/or BaO : 0-3%; and/or CaO : 0-3%; and/or B_2O_3 : 0-3%; and/or Ln_2O_3 : 0-4%; and/or a clarifying agent: 0-1%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

(84) The matrix glass according to any one of (79) to (83), where the components are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.1-1.0;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 3.0-40.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

(85) The matrix glass according to any one of (79) to (84) includes the following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent: 0-0.5%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

(86) The matrix glass according to any one of (79) to (85), where the components are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.03-0.09.

(87) The matrix glass according to any one of (79) to (86) excludes SrO ; and/or excludes BaO ; and/or excludes CaO ; and/or excludes ZnO ; and/or excludes PbO ; and/or excludes As_2O_3 ; and/or excludes TiO_2 ; and/or excludes B_2O_3 ; and/or excludes Ln_2O_3 ; and/or excludes F ; and/or excludes Ta_2O_5 .

- (88) The matrix glass according to any one of (79) to (87), where a coefficient of thermal expansion of the matrix glass is $50 \times 10^{-7}/\text{K}$ - $70 \times 10^{-7}/\text{K}$.

(89) The matrix glass according to any one of (79) to (88), where a refractive index of the matrix glass is 1.5600-1.5700.

- (90) The matrix glass according to any one of (79) to (80), where the matrix glass includes a colorant.

(91) The matrix glass according to (90), where the colorant includes the following components in percentage by weight: NiO : 0-4%; and/or Ni_2O_3 : 0-4%; and/or CoO : 0-2%; and/or Co_2O_3 : 0-2%; and/or Fe_2O_3 : 0-7%; and/or MnO_2 : 0-4%; and/or Er_2O_3 : 0-8%; and/or Nd_2O_3 : 0-8%; and/or Cu_2O : 0-4%; and/or Pr_2O_3 : 0-8%; and/or CeO_2 : 0-4%.

- (92) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: NiO : 0.1-4%; and/or Ni_2O_3 : 0.1-4%; and/or CoO : 0.05-2%; and/or Co_2O_3 : 0.05-2%; and/or Fe_2O_3 : 0.2-7%; and/or MnO_2 : 0.1-4%; and/or Er_2O_3 : 0.4-8%; and/or Nd_2O_3 : 0.4-8%; and/or Cu_2O : 0.5-4%; and/or Pr_2O_3 : 0.4-8%; and/or CeO_2 : 0.5-4%.

(93) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%; and/or CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%; and/or Fe₂O₃: 0.2-5%; and/or MnO₂: 0.1-3%; and/or Er₂O₃: 0.4-6%; and/or Nd₂O₃: 0.4-6%; and/or Cu₂O: 0.5-3%; and/or Pr₂O₃: 0.4-6%;
5 and/or CeO₂: 0.5-3%.

(94) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%.

(95) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%.

10 (96) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: Cu₂O: 0.5-3%; and /or CeO₂: 0.5-3%.

(97) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: Fe₂O₃: 0.2-5%, and CoO: 0.05-0.3%; or Fe₂O₃: 0.2-5%, and Co₂O₃: 0.05-0.3%; or Fe₂O₃: 0.2-5%, CoO: 0.05-0.3%, and NiO: 0.1-1%;
15 or Fe₂O₃: 0.2-5%, Co₂O₃: 0.05-0.3%, and NiO: 0.1-1%.

(98) The matrix glass according to either (90) or (91), where the colorant includes the following components in percentage by weight: Pr₂O₃: 0.4-6%; or Fe₂O₃: 0.2-5%; or MnO₂: 0.1-3%; or Er₂O₃: 0.4-6%; or Nd₂O₃: 0.4-6%.

(99) The matrix glass according to either (90) or (91), where the colorant includes the
20 following components in percentage by weight: Er₂O₃: 0.4-6%, Nd₂O₃: 0.4-4%, and MnO₂: 0.1-2%.

The present invention further provides a glass cover plate.

(100) The glass cover plate includes the microcrystalline glass product according to any one of (1) to (40), and/or the microcrystalline glass according to any one of (41) to (78),
25 and/or the matrix glass according to any one of (79) to (99).

The present invention further provides a glass component.

(101) The glass component includes the microcrystalline glass product according to any one of (1) to (40), and/or the microcrystalline glass according to any one of (41) to (78), and/or the matrix glass according to any one of (79) to (99).

5 The present invention further provides a display device.

(102) The display device includes the microcrystalline glass product according to any one of (1) to (40), and/or the microcrystalline glass according to any one of (41) to (78), and/or the matrix glass according to any one of (79) to (99), and/or the glass cover plate according to (100), and/or the glass component according to (101).

10 The present invention further provides an electronic device.

(103) The electronic device includes the microcrystalline glass product according to any one of (1) to (40), and/or the microcrystalline glass according to any one of (41) to (78), and/or the matrix glass according to any one of (79) to (99), and/or the glass cover plate according to (100), and/or the glass component according to (101).

15 The present invention further provides a method for manufacturing a microcrystalline glass product.

(104) The method for manufacturing a microcrystalline glass product includes the following steps:

forming matrix glass, the matrix glass including the following components in percentage
20 by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃: greater than 0 but less than or equal to 8%; and

forming the matrix glass into a microcrystalline glass through a crystallization process, and then forming the microcrystalline glass into a microcrystalline glass product through a chemical strengthening process.

(105) The method for manufacturing a microcrystalline glass product according to (104), where the matrix glass further includes the following components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or TiO_2 : 0-5%; and/or BaO : 0-5%; and/or CaO : 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

(106) The method for manufacturing a microcrystalline glass product includes the following steps:

forming matrix glass, the matrix glass including the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; Y_2O_3 : greater than 0 but less than or equal to 8%; K_2O : 0-5%; MgO : 0-2%; ZnO : 0-2%; Na_2O : 0-6%; SrO : 0-5%; TiO_2 : 0-5%; BaO : 0-5%; CaO : 0-5%; B_2O_3 : 0-5%; Ln_2O_3 : 0-5%; and a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br ; and

forming the matrix glass into a microcrystalline glass through a crystallization process, and then forming the microcrystalline glass into a microcrystalline glass product through a chemical strengthening process.

(107) The method for manufacturing a microcrystalline glass product according to any one of (104) to (106), where the components of the matrix glass are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 1) Y_2O_3/ZrO_2 is greater than 0;
- 2) $(Li_2O+ZrO_2+P_2O_5)/Y_2O_3$ is 2.5-50.0;
- 3) $Al_2O_3/(Li_2O+ZrO_2+P_2O_5)$ is 0.16-0.9;
- 4) Na_2O/Y_2O_3 is 6.0 or less;

5) $Y_2O_3/(Al_2O_3+SiO_2)$ is greater than 0 but less than or equal to 0.15.

(108) The method for manufacturing a microcrystalline glass product according to any one of (104) to (107), where the matrix glass includes the following components in percentage by weight: SiO_2 : 50-65%; and/or Al_2O_3 : 8-15%; and/or Li_2O : 13-22%; and/or ZrO_2 : 6-12%; and/or P_2O_5 : 3.5-9%; and/or K_2O : 0-4%; and/or MgO : 0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%; and/or Y_2O_3 : 1-7%; and/or SrO : 0-3%; and/or TiO_2 : 0-3%; and/or BaO : 0-3%; and/or CaO : 0-3%; and/or B_2O_3 : 0-3%; and/or Ln_2O_3 : 0-4%; and/or a clarifying agent: 0-1%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

(109) The method for manufacturing a microcrystalline glass product according to any one of (104) to (108), where the components of the matrix glass are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 1) Y_2O_3/ZrO_2 is 0.1-1.0;
- 2) $(Li_2O+ZrO_2+P_2O_5)/Y_2O_3$ is 3.0-40.0;
- 3) $Al_2O_3/(Li_2O+ZrO_2+P_2O_5)$ is 0.18-0.6;
- 4) Na_2O/Y_2O_3 is 0.1-5.0;
- 5) $Y_2O_3/(Al_2O_3+SiO_2)$ is 0.01-0.12.

(110) The method for manufacturing a microcrystalline glass product according to any one of (104) to (109), where the matrix glass includes the following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent: 0-0.5%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO ,

CeO₂, F, Cl, and Br.

(111) The method for manufacturing a microcrystalline glass product according to any one of (104) to (110), where the components of the matrix glass are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 1) Y₂O₃/ZrO₂ is 0.2-0.6;
- 2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 4.0-21.0;
- 3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.19-0.5;
- 4) Na₂O/Y₂O₃ is 0.3-2.0;
- 5) Y₂O₃/(Al₂O₃+SiO₂) is 0.03-0.09.

(112) The method for manufacturing a microcrystalline glass product according to any one of (104) to (111), where the matrix glass excludes SrO; and/or excludes BaO; and/or excludes CaO; and/or excludes ZnO; and/or excludes PbO; and/or excludes As₂O₃; and/or excludes TiO₂; and/or excludes B₂O₃; and/or excludes Ln₂O₃; and/or excludes F; and/or excludes Ta₂O₅.

(113) The method for manufacturing a microcrystalline glass product according to either (104) or (105), where the matrix glass includes a colorant.

(114) The method for manufacturing a microcrystalline glass product according to (113), where the colorant includes the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

(115) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by

weight: NiO: 0.1-4%; and/or Ni₂O₃: 0.1-4%; and/or CoO: 0.05-2%; and/or Co₂O₃: 0.05-2%; and/or Fe₂O₃: 0.2-7%; and/or MnO₂: 0.1-4%; and/or Er₂O₃: 0.4-8%; and/or Nd₂O₃: 0.4-8%; and/or Cu₂O: 0.5-4%; and/or Pr₂O₃: 0.4-8%; and/or CeO₂: 0.5-4%.

(116) The method for manufacturing a microcrystalline glass product according to either
5 (113) or (114), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%; and/or CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%; and/or Fe₂O₃: 0.2-5%; and/or MnO₂: 0.1-3%; and/or Er₂O₃: 0.4-6%; and/or Nd₂O₃: 0.4-6%; and/or Cu₂O: 0.5-3%; and/or Pr₂O₃: 0.4-6%; and/or CeO₂: 0.5-3%.

(117) The method for manufacturing a microcrystalline glass product according to either
10 (113) or (114), where the colorant includes the following components in percentage by weight: NiO: 0.1-3%; and/or Ni₂O₃: 0.1-3%.

(118) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by weight: CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%.

15 (119) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by weight: Cu₂O: 0.5-3%; and/or CeO₂: 0.5-3%.

(120) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by
20 weight: Fe₂O₃: 0.2-5%, and CoO: 0.05-0.3%; or Fe₂O₃: 0.2-5%, and Co₂O₃: 0.05-0.3%; or Fe₂O₃: 0.2-5%, CoO: 0.05-0.3%, and NiO: 0.1-1%; or Fe₂O₃: 0.2-5%, Co₂O₃: 0.05-0.3%, and NiO: 0.1-1%.

(121) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by
25 weight: Pr₂O₃: 0.4-6%; or Fe₂O₃: 0.2-5%; or MnO₂: 0.1-3%; or Er₂O₃: 0.4-6%; or Nd₂O₃: 0.4-6%.

(122) The method for manufacturing a microcrystalline glass product according to either (113) or (114), where the colorant includes the following components in percentage by weight: Er_2O_3 : 0.4-6%, Nd_2O_3 : 0.4-4%, and MnO_2 : 0.1-2%.

5 (123) The method for manufacturing a microcrystalline glass product according to any one of (104) to (122), where the crystallization process includes the following steps: increasing a temperature to a prescribed crystallization treatment temperature; after reaching the crystallization treatment temperature, maintaining the temperature for a certain period of time; and then cooling down. The crystallization treatment temperature is 600°C to 750°C, and preferably 650°C to 700°C. The holding time at the crystallization treatment temperature
10 is 0-8 hours, and preferably 1-6 hours.

(124) The method for manufacturing a microcrystalline glass product according to any one of (104) to (122), where the crystallization process includes the following steps: performing a nucleation process at a first temperature, and then performing a crystal growth process at a second temperature higher than the nucleation process temperature.

15 (125) The method for manufacturing a microcrystalline glass product according to (124), where the crystallization process includes the following steps: the first temperature is 470-630°C, the second temperature is 650-750°C, the holding time at the first temperature is 0-24 hours, and preferably 2-15 hours, and the holding time at the second temperature is 0-10 hours, and preferably 0.5-6 hours.

20 (126) The method for manufacturing a microcrystalline glass product according to any one of (104) to (125), where the chemical strengthening process includes: immersing the microcrystalline glass in a salt bath of molten Na salt at a temperature of 430°C to 470°C for 6-20 hours, a preferred temperature range being 435°C to 460°C, and a preferred time range being 8-13 hours; and/or immersing the microcrystalline glass in a salt bath of molten K salt
25 at the temperature of 400°C to 450°C for 1-8 hours, a preferred time range being 2-4 hours.

(127) The method for manufacturing a microcrystalline glass product according to any one of (104) to (126), where a crystal phase of the microcrystalline glass product includes

lithium monosilicate and/or lithium phosphate.

(128) The method for manufacturing a microcrystalline glass product according to any one of (104) to (127), where the crystal phase of the microcrystalline glass product mainly includes lithium monosilicate, the lithium monosilicate has a higher weight percentage than
5 other crystal phases, and the lithium monosilicate accounts for 10-63.5% of the microcrystalline glass product, and preferably 15-55%.

(129) The method for manufacturing a microcrystalline glass product according to any one of (104) to (128), where the microcrystalline glass product includes a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% of the
10 microcrystalline glass product, and preferably 5-12%.

(130) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where a surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more.

(131) The method for manufacturing a microcrystalline glass product according to any
15 one of (104) to (112), where a four-point bending strength of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more.

(132) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where an ion-exchange layer depth of the microcrystalline glass
20 product is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more.

(133) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where a drop ball test height of the microcrystalline glass product is 1300 mm or more, preferably 1400 mm or more, and more preferably 1500 mm or more.

(134) The method for manufacturing a microcrystalline glass product according to any
25 one of (104) to (112), where fracture toughness of the microcrystalline glass product is 1 $\text{MPa}\cdot\text{m}^{1/2}$ or more, preferably 1.1 $\text{Mpa}\cdot\text{m}^{1/2}$ or more, and more preferably 1.2 $\text{Mpa}\cdot\text{m}^{1/2}$ or

more.

(135) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where Vickers hardness of the microcrystalline glass product is 700 kgf/mm² or more, preferably 720 kgf/mm² or more, and more preferably 730 kgf/mm² or more.

(136) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where a crystallinity of the microcrystalline glass product is 50% or more, preferably 60% or more, and more preferably 70% or more.

(137) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where a grain size of the microcrystalline glass product is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

(138) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where a haze of the microcrystalline glass product with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less.

(139) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where average transmittance of the microcrystalline glass product with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more.

(140) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where transmittance of the microcrystalline glass product with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more.

(141) The method for manufacturing a microcrystalline glass product according to any one of (104) to (112), where an average light | B | value of the microcrystalline glass product with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

(142) The method for manufacturing a microcrystalline glass product according to any

one of (138) to (141), where the thickness of the microcrystalline glass product is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

The present invention further provides a method for manufacturing a microcrystalline glass.

(143) The method for manufacturing microcrystalline glass includes the following steps:

forming matrix glass, the matrix glass including the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; and Y_2O_3 : greater than 0 but less than or equal to 8%; and

forming the matrix glass into a microcrystalline glass through a crystallization process.

(144) The method for manufacturing a microcrystalline glass according to (143), where the matrix glass further includes the following components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or TiO_2 : 0-5%; and/or BaO : 0-5%; and/or CaO : 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(145) The method for manufacturing a microcrystalline glass includes the following steps:

forming matrix glass, the matrix glass including the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; Y_2O_3 : greater than 0 but less than or equal to 8%; K_2O : 0-5%; MgO : 0-2%; ZnO : 0-2%; Na_2O : 0-6%; SrO : 0-5%; TiO_2 : 0-5%; BaO : 0-5%; CaO : 0-5%; B_2O_3 : 0-5%; Ln_2O_3 : 0-5%; and a clarifying agent: 0-2%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br; and

forming the matrix glass to a microcrystalline glass through a crystallization process.

(146) The method for manufacturing a microcrystalline glass according to any one of (143) to (145), where the components of the matrix glass are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

- 5 1) Y_2O_3/ZrO_2 is greater than 0;
- 2) $(Li_2O+ZrO_2+P_2O_5)/Y_2O_3$ is 2.5-50.0;
- 3) $Al_2O_3/(Li_2O+ZrO_2+P_2O_5)$ is 0.16-0.9;
- 4) Na_2O/Y_2O_3 is 6.0 or less;
- 5) $Y_2O_3/(Al_2O_3+SiO_2)$ is greater than 0 but less than or equal to 0.15.

10 (147) The method for manufacturing a microcrystalline glass according to any one of (143) to (146), where the matrix glass includes the following components in percentage by weight: SiO_2 : 50-65%; and/or Al_2O_3 : 8-15%; and/or Li_2O : 13-22%; and/or ZrO_2 : 6-12%; and/or P_2O_5 : 3.5-9%; and/or K_2O : 0-4%; and/or MgO : 0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%; and/or Y_2O_3 : 1-7%; and/or SrO : 0-3%; and/or TiO_2 : 0-3%; and/or BaO : 0-3%;
15 and/or CaO : 0-3%; and/or B_2O_3 : 0-3%; and/or Ln_2O_3 : 0-4%; and/or a clarifying agent: 0-1%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

 (148) The method for manufacturing a microcrystalline glass according to any one of (143) to (147), where the components of the matrix glass are expressed in percentage by
20 weight, and the content of each component satisfies more than one of the following five situations:

- 1) Y_2O_3/ZrO_2 is 0.1-1.0;
- 2) $(Li_2O+ZrO_2+P_2O_5)/Y_2O_3$ is 3.0-40.0;
- 3) $Al_2O_3/(Li_2O+ZrO_2+P_2O_5)$ is 0.18-0.6;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

(149) The method for manufacturing a microcrystalline glass according to any one of (143) to (148), where the matrix glass includes the following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent: 0-0.5%, where Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

(150) The method for manufacturing a microcrystalline glass according to any one of (143) to (149), where the components of the matrix glass are expressed in percentage by weight, and the content of each component satisfies more than one of the following five situations:

1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;

2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.03-0.09.

(151) The method for manufacturing a microcrystalline glass according to any one of (143) to (150), where the matrix glass excludes SrO ; and/or excludes BaO ; and/or excludes CaO ; and/or excludes ZnO ; and/or excludes PbO ; and/or excludes As_2O_3 ; and/or excludes TiO_2 ; and/or excludes B_2O_3 ; and/or excludes Ln_2O_3 ; and/or excludes F; and/or excludes Ta_2O_5 .

(152) The method for manufacturing a microcrystalline glass according to either (143) or (144), where the matrix glass includes a colorant.

(153) The method for manufacturing a microcrystalline glass according to (152), where the colorant includes the following components in percentage by weight: NiO: 0-4%; and/or
5 Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

(154) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: NiO:
10 0.1-4%; and/or Ni₂O₃: 0.1-4%; and/or CoO: 0.05-2%; and/or Co₂O₃: 0.05-2%; and/or Fe₂O₃: 0.2-7%; and/or MnO₂: 0.1-4%; and/or Er₂O₃: 0.4-8%; and/or Nd₂O₃: 0.4-8%; and/or Cu₂O: 0.5-4%; and/or Pr₂O₃: 0.4-8%; and/or CeO₂: 0.5-4%.

(155) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: NiO:
15 0.1-3%; and/or Ni₂O₃: 0.1-3%; and/or CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%; and/or Fe₂O₃: 0.2-5%; and/or MnO₂: 0.1-3%; and/or Er₂O₃: 0.4-6%; and/or Nd₂O₃: 0.4-6%; and/or Cu₂O: 0.5-3%; and/or Pr₂O₃: 0.4-6%; and/or CeO₂: 0.5-3%.

(156) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: NiO:
20 0.1-3%; and/or Ni₂O₃: 0.1-3%.

(157) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: CoO: 0.05-1.8%; and/or Co₂O₃: 0.05-1.8%.

(158) The method for manufacturing a microcrystalline glass according to either (152) or
25 (153), where the colorant includes the following components in percentage by weight: Cu₂O: 0.5-3%; and /or CeO₂: 0.5-3%.

(159) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: Fe_2O_3 : 0.2-5%, and CoO : 0.05-0.3%; or Fe_2O_3 : 0.2-5%, and Co_2O_3 : 0.05-0.3%; or Fe_2O_3 : 0.2-5%, CoO : 0.05-0.3%, and NiO : 0.1-1%; or Fe_2O_3 : 0.2-5%, Co_2O_3 : 0.05-0.3%, and NiO : 0.1-1%.

5 (160) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: Pr_2O_3 : 0.4-6%; or Fe_2O_3 : 0.2-5%; or MnO_2 : 0.1-3%; or Er_2O_3 : 0.4-6%; or Nd_2O_3 : 0.4-6%.

(161) The method for manufacturing a microcrystalline glass according to either (152) or (153), where the colorant includes the following components in percentage by weight: Er_2O_3 :
10 0.4-6%, Nd_2O_3 : 0.4-4%, and MnO_2 : 0.1-2%.

(162) The method for manufacturing a microcrystalline glass according to any one of (143) to (161), where the crystallization process includes the following steps: increasing a temperature to a prescribed crystallization treatment temperature; after reaching the crystallization treatment temperature, maintaining the temperature for a certain period of
15 time; and then cooling down. The crystallization treatment temperature is 600°C to 750°C, and preferably 650°C to 700°C. The holding time at the crystallization treatment temperature is 0-8 hours, and preferably 1-6 hours.

(163) The method for manufacturing a microcrystalline glass according to any one of (143) to (161), where the crystallization process includes the following steps: performing a
20 nucleation process at a first temperature, and then performing a crystal growth process at a second temperature higher than the nucleation process temperature.

(164) The method for manufacturing a microcrystalline glass according to (163), where the crystallization process includes the following steps: the first temperature is 470-630°C, the second temperature is 650-750°C, the holding time at the first temperature is 0-24 hours,
25 and preferably 2-15 hours, and the holding time at the second temperature is 0-10 hours, and preferably 0.5-6 hours.

(165) The method for manufacturing a microcrystalline glass according to any one of (143) to (164), where a crystal phase of the microcrystalline glass includes lithium monosilicate and/or lithium phosphate.

5 (166) The method for manufacturing a microcrystalline glass according to any one of (143) to (165), where the crystal phase of the microcrystalline glass mainly includes lithium monosilicate, the lithium monosilicate has a higher weight percentage than other crystal phases, and the lithium monosilicate accounts for 10-63.5% of the microcrystalline glass, and preferably 15-55%.

10 (167) The method for manufacturing a microcrystalline glass according to any one of (143) to (166), where the microcrystalline glass includes a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% of the microcrystalline glass, and preferably 5-12%.

(168) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where a crystallinity of the microcrystalline glass is 50% or more, preferably
15 60% or more, and more preferably 70% or more.

(169) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where a grain size of the microcrystalline glass is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less; and/or a coefficient of thermal expansion is $75-95 \times 10^{-7}/K$.

20 (170) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where a refractive index of the microcrystalline glass is 1.5700-1.5800.

(171) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where a body drop height of the microcrystalline glass is 1000 mm or more, preferably 1100 mm or more, and more preferably 1200 mm or more.

25 (172) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where Vickers hardness of the microcrystalline glass is 650 kgf/mm² or more,

preferably 680 kgf/mm² or more, and more preferably 700 kgf/mm² or more.

(173) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where a haze of the microcrystalline glass with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less.

5 (174) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where average transmittance of the microcrystalline glass with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more.

(175) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where transmittance of the microcrystalline glass with the thickness of 1 mm
10 or less at the wavelength of 550 nm is 91% or more.

(176) The method for manufacturing a microcrystalline glass according to any one of (143) to (151), where an average light | B | value of the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

15 (177) The method for manufacturing a microcrystalline glass according to any one of (173) to (176), where the thickness of the microcrystalline glass is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

The present invention has the following beneficial effects: through reasonable
20 component design, the microcrystalline glass and the microcrystalline glass product obtained in the present invention have excellent mechanical and optical properties and are suitable for electronic devices or display devices.

Detailed Description

The microcrystalline glass and the microcrystalline glass product of the present invention
25 are materials with a crystal phase and a glass phase, which are different from amorphous

solids. The crystal phases of the microcrystalline glass and the microcrystalline glass product can be distinguished by peak angles appearing in an X-ray diffraction pattern of X-ray diffraction analysis and/or measured by TEMEDX.

After repeated tests and studies, the inventor of the present invention obtains the
5 microcrystalline glass or the microcrystalline glass product of the present invention at a lower cost by specifying the content and content ratios of specific components constituting the microcrystalline glass or the microcrystalline glass product to specific values and allowing the specific components to precipitate specific crystal phases.

The range of each component (ingredient) of the matrix glass, the microcrystalline glass,
10 and the microcrystalline glass product of the present invention are described below. In the description, if there is no special illustration, the content of each component is expressed in percentage by weight (wt%) relative to the total amount of the matrix glass, or the microcrystalline glass, or the microcrystalline glass product of an oxide-converted composition. Here, the "oxide-converted composition" means that the oxides, composite
15 salts, hydroxides, etc. used as raw materials for the constituent components of the matrix glass, the microcrystalline glass or the microcrystalline glass of the present invention are decomposed and converted into oxides when melted, the total amount of the oxide material is regarded as 100%. In addition, when only referred to as glass in the description, it is the matrix glass before crystallization, the matrix glass is called a microcrystalline glass after
20 crystallization, and the microcrystalline glass product refers to a chemically strengthened microcrystalline glass.

Unless otherwise indicated under specific circumstances, the numerical ranges listed herein include upper and lower limits, and "or more" and "or less" include endpoint values, as well as all integers and fractions within the ranges, and are not limited to the specific values
25 listed in the limited ranges. As used herein, the term "about" means that the formula, parameters, and other quantities and features are not, and need not to be accurate, and can be approximated and/or larger or lower if necessary, which reflects tolerances, conversion factors, measurement errors, etc. As used herein, "and/or" is inclusive, for example, "A;

and/or B" means that there is only A, or only B, or both A and B.

In the microcrystalline glass and the microcrystalline glass product in the present invention, a crystal phase includes lithium monosilicate and/or lithium phosphate.

In some embodiments of the present invention, the crystal phase of the microcrystalline glass or the microcrystalline glass product mainly includes a lithium monosilicate crystal phase, the lithium monosilicate crystal phase has a higher weight percentage than other crystal phases, and the lithium monosilicate accounts for 10-63.5% of the microcrystalline glass or the microcrystalline glass product, and in some embodiments, the weight percentage range is 15-55%.

In some embodiments of the present invention, the crystal phase of the microcrystalline glass or the microcrystalline glass product includes a lithium phosphate crystal phase, and the weight percentage range of the crystal phase in the microcrystalline glass or the microcrystalline glass product is 3-15%, and in some embodiments, the weight percentage range is 5-12%.

SiO₂ is an essential component of the glass of the present invention. It is one of the main components forming crystals after thermal treatment. If the content of SiO₂ is 45% or less, it is more difficult to form crystals in the glass. Therefore, the lower limit of the content of SiO₂ is 45%, preferably 50%, and further preferably 53%. If the content of SiO₂ is 70% or more, it is unfavorable for glass formation and affects the haze and | B | value of the microcrystalline glass and the microcrystalline glass product. Therefore, the upper limit of the content of SiO₂ is 70%, preferably 65%, and more preferably 63%. In some embodiments, about 45%, 46%, 47%, 48%, 49%, 50%, 51%, 52%, 53%, 54%, 55%, 56%, 57%, 58%, 59%, 60%, 61%, 62%, 63%, 64%, 65%, 66%, 67%, 68%, 69%, 70% of SiO₂ may be included.

Al₂O₃ can be used as a glass network structure, which is conducive to glass formation, reduces the glass crystallization temperature, and is conducive to glass crystallization. Al₂O₃ is one of the components forming microcrystalline glass crystals, which is conducive to

chemical strengthening of the microcrystalline glass and increases the ion-exchange layer depth of the microcrystalline glass product, but if its content is less than 8%, the effect above is poor. Therefore, the lower limit of the content of Al_2O_3 is 8%. On the other hand, if the content of Al_2O_3 exceeds 18%, it affects the size of fragments after the chemical strengthening of the microcrystalline glass. Therefore, the upper limit of the content of Al_2O_3 is 18%, preferably 15%, and more preferably 12%. In some embodiments, about 8%, 8.5%, 9%, 9.5%, 10%, 10.5%, 11%, 11.5%, 12%, 12.5%, 13%, 13.5%, 14%, 14.5%, 15%, 15.5%, 16%, 16.5%, 17%, 17.5%, 18% of Al_2O_3 may be included.

Li_2O can promote the melting of glass and reduce the melting temperature. It is a main component for forming crystals, and is also the main component that replaces sodium and potassium ions in the chemical strengthening process, which can increase the surface stress of the chemically strengthened microcrystalline glass product and improve the drop ball height of the microcrystalline glass product. However, if the content of Li_2O is less than 10%, the crystal phase of the formed lithium monosilicate is poor, which affects the drop height and fragment size of the microcrystalline glass product. Therefore, the lower limit of the content of Li_2O is 10%, preferably 13%, and further preferably 14%. On the other hand, if there is too much Li_2O , the glass is prone to phase separation during crystallization, which affects the transmittance of the microcrystalline glass and the microcrystalline glass product. Therefore, the upper limit of the content of Li_2O is 25%, preferably 22%, and further preferably 21%. In some embodiments, about 10%, 10.5%, 11%, 11.5%, 12%, 12.5%, 13%, 13.5%, 14%, 14.5%, 15%, 15.5%, 16%, 16.5%, 17%, 17.5%, 18%, 18.5%, 19%, 19.5%, 20%, 20.5%, 21%, 21.5%, 22%, 22.5%, 23%, 23.5%, 24%, 24.5%, 25% Li_2O may be included.

Na_2O is an optional component, which can reduce the melting temperature of the glass and is conducive to the adjustment of the chemical strengthening process of the glass or microcrystalline glass. Therefore, the lower limit of the content of Na_2O in the present invention is preferably 1%, and more preferably 1.5%. On the other hand, if the glass contains too much Na_2O , it promotes the phase separation of the glass, resulting in a decrease in the transmittance of the microcrystalline glass and the microcrystalline glass product after

crystallization. Therefore, the upper limit of the content of Na_2O is 6%, preferably 5%, and further preferably 4%. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1%, 1.5%, 2%, 2.5%, 3%, 3.5%, 4%, 4.5%, 5%, 5.5%, and 6% of Na_2O may be included.

K_2O is conducive to glass formation and reduces the viscosity of the glass, but if the glass contains too much K_2O , it may easily lead to a decrease in the chemical stability and hardness of the glass. Therefore, the upper limit of the content of K_2O is 5%, preferably 4%, and further preferably 2%. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of K_2O may be included.

P_2O_5 can form a crystal nucleus in the glass crystallization process, promote the formation of crystals, and increase the crystallinity of the microcrystalline glass or the microcrystalline glass product, and is conducive to chemical strengthening, increasing the hardness, drop ball height and bending strength of the microcrystalline glass product. The lower limit of the content of P_2O_5 is 2%, preferably 3.5%, and more preferably 4%. However, if there is too much P_2O_5 , it may easily lead to phase separation of the glass and reduce the chemical stability of the glass. Therefore, the upper limit of the content of P_2O_5 is 10%, preferably 9%, and further preferably 8%. In some embodiments, about 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, 5.0%, 5.5%, 6.0%, 6.5%, 7.0%, 7.5%, 8.0%, 8.5%, 9.0%, 9.5%, and 10% of P_2O_5 may be included.

ZrO_2 and P_2O_5 can dissolve each other, reduce the phase separation of P_2O_5 during glass formation, increase the crystallization temperature of the glass during crystallization, ensure the integrity of the lithium monosilicate crystal phase in the microcrystalline glass and the microcrystalline glass product, and reduce the haze and the $|B|$ value of the microcrystalline glass and the microcrystalline glass product, and improve the drop resistance of the microcrystalline glass product. Therefore, the lower limit of the content of ZrO_2 is 5%, preferably 6%, and more preferably 7%. On the other hand, if there is too much ZrO_2 , glass melting is difficult. Therefore, the upper limit of the content of ZrO_2 is 15%, and preferably 12%. In some embodiments, about 5.0%, 5.5%, 6.0%, 6.5%, 7.0%, 7.5%, 8.0%, 8.5%, 9.0%, 9.5%, 10.0%, 10.5%, 11.0%, 11.5%, 12%, 12.5%, 13.0%, 13.5%, 14.0%, 14.5%, and 15.0%

of ZrO_2 may be included.

Y_2O_3 can promote the melting of ZrO_2 , reduce the smelting difficulty of glass, reduce the phase separation in the glass, reduce the haze and $|B|$ value of the microcrystalline glass and the microcrystalline glass product. The lower limit of the content of Y_2O_3 is greater than 0%, preferably 1%, and further preferably 2%. On the other hand, if the content of Y_2O_3 is too large, it is difficult to form crystals during glass crystallization, and the crystallinity of the microcrystalline glass and the microcrystalline glass product decreases. Therefore, the upper limit of the content of Y_2O_3 is 8%, preferably 7%, and further preferably 6%. In some embodiments, about greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, 5.0%, 5.5%, 6.0%, 6.5%, 7.0%, 7.5%, and 8.0% of Y_2O_3 may be included.

After a large number of experimental studies of the inventor, it is found that in some embodiments, the relative content of Y_2O_3 and ZrO_2 has an important influence on the haze and $|B|$ value of the microcrystalline glass and the microcrystalline glass product, especially making $\text{Y}_2\text{O}_3/\text{ZrO}_2$ greater than 0, which can reduce the haze and $|B|$ value of the microcrystalline glass and the microcrystalline glass product, and improve the video photography and still photography effects of terminal products. Therefore, preferably, $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is greater than 0, more preferably, $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.1-1.0, and further preferably, $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6. In some embodiments, the value of $\text{Y}_2\text{O}_3/\text{ZrO}_2$ may be greater than 0, 0.05, 0.1, 0.15, 0.2, 0.25, 0.3, 0.35, 0.4, 0.45, 0.5, 0.55, 0.6, 0.65, 0.7, 0.75, 0.8, 0.85, 0.9, 0.95, and 1.0.

In some embodiments of the present invention, making $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ in the range of 2.5-50.0 can make grains of the matrix glass refined during the crystallization process, so that the microcrystalline glass and the microcrystalline glass product can obtain smaller grains, reducing the haze of the microcrystalline glass and the microcrystalline glass product. Therefore, preferably, $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 2.5-50.0, more preferably, $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 3.0-40.0, and further preferably $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0. In some embodiments, the value of $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ may be 2.5, 3.0, 4.0, 5.0, 6.0, 7.0, 8.0, 9.0, 10.0, 11.0, 12.0, 13.0, 14.0, 15.0, 16.0, 17.0, 18.0, 19.0, 20.0, 21.0,

22.0, 23.0, 24.0, 25.0, 26.0, 27.0, 28.0, 29.0, 30.0, 31.0, 32.0, 33.0, 34.0, 35.0, 36.0, 37.0, 38.0, 39.0, 40.0, 41.0, 42.0, 43.0, 44.0, 45.0, 46.0, 47.0, 48.0, 49.0, and 50.0.

In the process of a large number of experimental studies, the inventor found that by controlling a ratio $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ of Al_2O_3 to the total content $\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5$ of P_2O_5 , Li_2O , and ZrO_2 is within the range of 0.16 to 0.9, the microcrystalline glass product can withstand the ball impact of 1300 mm or more, and more preferably, $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6. Furthermore, in some embodiments, further preferably, when $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is within the range of 0.19 to 0.5, it is easier to form the lithium monosilicate crystal phase, and the microcrystalline glass product is easier to obtain excellent fracture toughness. The fracture toughness may be $1 \text{ MPa}\cdot\text{m}^{1/2}$ or more, preferably $1.1 \text{ MPa}\cdot\text{m}^{1/2}$ or more, and more preferably $1.2 \text{ MPa}\cdot\text{m}^{1/2}$ or more. Moreover, the bearing capacity of the drop ball test height is further optimized. Therefore, further preferably, $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5. In some embodiments, $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ may be 0.16, 0.17, 0.18, 0.19, 0.2, 0.21, 0.22, 0.23, 0.24, 0.25, 0.26, 0.27, 0.28, 0.29, 0.30, 0.31, 0.32, 0.33, 0.34, 0.35, 0.36, 0.37, 0.38, 0.39, 0.40, 0.41, 0.42, 0.43, 0.44, 0.45, 0.46, 0.47, 0.48, 0.49, 0.50, 0.55, 0.60, 0.65, 0.70, 0.75, 0.80, 0.85, and 0.90.

After a large number of experimental studies by the inventor, it is found that the relative content of Na_2O and Y_2O_3 has an important impact on the surface stress and the ion-exchange layer depth of the microcrystalline glass product, especially when $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 6.0 or less, the surface stress and the ion-exchange layer depth of the microcrystalline glass product may be improved, and more preferably, $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0. In some embodiments, further preferably, $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0, which can also improve the fragment size of the microcrystalline glass product. In some embodiments, the surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more. The ion-exchange layer depth of the microcrystalline glass product is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more. In some embodiments, the value of $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ may be 0, greater than 0, 0.1, 0.2, 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.1, 1.2, 1.3, 1.4, 1.5, 1.6, 1.7, 1.8, 1.9, 2.0, 2.3, 2.5, 2.7, 3.0, 3.3, 3.5,

3.7, 4.0, 4.3, 4.5, 4.7, 5.0, 5.3, 5.5, 5.7, and 6.0.

In some embodiments of the present invention, when a content ratio $Y_2O_3/(Al_2O_3+SiO_2)$ of Y_2O_3 to the total content ($Al_2O_3+SiO_2$) of Al_2O_3 and SiO_2 is controlled to be greater than 0 but less than or equal to 0.15, the crystallization of glass can be optimized, so that the microcrystalline glass and the microcrystalline glass product have an appropriate crystallinity, and thus the microcrystalline glass and the microcrystalline glass product have excellent properties. Preferably, $Y_2O_3/(Al_2O_3+SiO_2)$ is 0.01-0.12, and more preferably 0.03-0.09. The drop ball test height of the microcrystalline glass and the microcrystalline glass product becomes larger. In some embodiments, the drop ball test height of the microcrystalline glass product is preferably 1300 mm or more, more preferably 1400 mm or more, and further preferably 1500 mm or more. In some embodiments, the value of $Y_2O_3/(Al_2O_3+SiO_2)$ may be greater than 0, 0.01, 0.02, 0.03, 0.04, 0.05, 0.06, 0.07, 0.08, 0.09, 0.1, 0.11, 0.12, 0.13, 0.14, and 0.15.

B_2O_3 can improve a network structure of glass, optimize the chemical strengthening properties of the glass and the microcrystalline glass, and increase the drop ball height of the microcrystalline glass product. When the content of B_2O_3 exceeds 5%, it is not conducive to glass formation and is easy to crystallize during formation. Therefore, the upper limit of the content of B_2O_3 is 5%, preferably 3%, and more preferably 2%. Further preferably, B_2O_3 is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of B_2O_3 may be included.

ZnO can reduce the smelting difficulty of glass. However, when the content of ZnO is high, it may promote the low-temperature crystallization of glass, reduce the crystallinity and transmittance of the microcrystalline glass and the microcrystalline glass product, and increase the haze of the microcrystalline glass and the microcrystalline glass product. Therefore, the upper limit of the content of ZnO is 2%, preferably 1%. Further preferably, ZnO is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, and 2.0% of ZnO may be included.

MgO can reduce the smelting difficulty of glass, and is conducive to increase the drop ball height of the microcrystalline glass and the microcrystalline glass product. However, it is easy to promote the low-temperature crystallization of the glass and reduce the crystallinity and transmittance of the microcrystalline glass and the microcrystalline glass product.

5 Therefore, the upper limit of the content of MgO is 2%, and preferably 1%. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, and 2.0% of MgO may be included.

SrO is an optional component that improves the low-temperature melting property of glass and suppresses crystallization during glass formation. When the content is too much, it may affect the glass formation, and it is easy to crystallize during formation. Therefore, the

10 range of the SrO content in the present invention is 0 to 5%, preferably 0 to 3%, and more preferably 0 to 1%. Further preferably, SrO is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of SrO may be included.

BaO is an optional component that facilitates improving the glass formation properties of glass. When the content is too large, it is unfavorable for glass formation. Therefore, the range of the BaO content in the present invention is 0 to 5%, preferably 0 to 3%, and more preferably 0 to 1%. Further preferably, BaO is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of

15 BaO may be included.

20

CaO can increase the hardness of glass, and when the content is too much, the glass is easy to be milky when it is formed. Therefore, the range of the CaO content in the present invention is 0 to 5%, preferably 0 to 3%, and more preferably 0 to 1%. Further preferably, CaO is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%,

25 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of CaO may be included.

TiO₂ is an optional component that facilitates reducing the melting temperature of the matrix glass and improving the chemical stability. 5% or less of TiO₂ contained in the present

invention can make the crystallization process of the matrix glass easier to control, preferably 3% or less, and more preferably 1% or less. In some embodiments, further preferably, TiO_2 is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.3%, 0.5%, 1%, 1.5%, 2%, 2.5%, 3%, 3.5%, 4%, 4.5%, and 5% of TiO_2 may be included.

5 Ln_2O_3 (Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3) is an optional component that improves the hardness and chemical stability of the microcrystalline glass and suppresses glass formation and crystallization. Too much content may affect the chemical strengthening property of the glass and reduce the strength of the microcrystalline glass product. Therefore, the range of the Ln_2O_3 content in the present invention is 0 to 5%, preferably 0 to 4%, and
10 more preferably 0 to 3%. Further preferably, Ln_2O_3 is excluded. In some embodiments, about 0%, greater than 0%, 0.1%, 0.5%, 1.0%, 1.5%, 2.0%, 2.5%, 3.0%, 3.5%, 4.0%, 4.5%, and 5.0% of Ln_2O_3 may be included.

In some embodiments, the glass, the microcrystalline glass or the microcrystalline glass product may further include 0-2% of a clarifying agent to improve the defoaming ability of
15 the glass, the microcrystalline glass or the microcrystalline glass product. The clarifying agent includes, but is not limited to, one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br. Preferably, Sb_2O_3 is used as the clarifying agent. When the clarifying agents are present alone or in combination, the upper limit of the content of the clarifying agent is preferably 1%, and more preferably 0.5%. In some embodiments, the content of one or more of the
20 clarifying agents is 0%, 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, and 2.0%.

In order to obtain the desired mechanical properties, optical properties, production properties, chemical strengthening properties and other excellent properties of the glass, the microcrystalline glass or the microcrystalline glass product of the present invention, in some
25 embodiments of the present invention, preferably, F is excluded, and/or Ta_2O_5 is excluded.

PbO and As_2O_3 are toxic substances, and even a small amount of addition does not satisfy the requirements of environmental protection. Therefore, the present invention

preferably does not include PbO and As₂O₃ in some embodiments.

In some embodiments of the present invention, by containing a colorant, a colored matrix glass, microcrystalline glass or microcrystalline glass product may be prepared, and the matrix glass, the microcrystalline glass or the microcrystalline glass product may exhibit
5 different colors. The colorant includes the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₅: 0-8%; and/or CeO₂: 0-4%. The weight percentage of the colorant and its function are detailed as follows:

10 The brown or green matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses NiO, Ni₂O₃ or Pr₂O₅ as the colorant. NiO and Ni₂O₃ are colorants, used for preparing brown or green matrix glass, microcrystalline glass or microcrystalline glass product. The two components can be used alone or in combination, and the respective contents are generally 4% or less, and preferably 3% or less. If the content
15 exceeds 4%, the colorant cannot be dissolved well in the matrix glass, the microcrystalline glass or the microcrystalline glass product, and the lower limit of the content of the colorant is 0.1% or more, and if the content is less than 0.1%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product is not obvious. In some embodiments, about 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%,
20 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of NiO or Ni₂O₃ may be included. In mixed use, the total amount of NiO and Ni₂O₃ is generally 4% or less, and the lower limit of the total amount is 0.1% or more. In some embodiments, about 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%,
25 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of NiO and Ni₂O₃ may be included. Pr₂O₅ is used as the colorant for the green matrix glass, microcrystalline glass or microcrystalline glass product, and is used alone, and

the content is generally 8% or less, and preferably 6% or less. The lower limit of the content of Pr_2O_5 is 0.4% or more, and if the content is lower than 0.4%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product is not obvious. In some embodiments, about 0.4%, 0.6%, 0.8%, 1.0%, 1.2%, 1.4%, 1.6%, 1.8%, 2.0%, 2.2%, 2.4%,
5 2.6%, 2.8%, 3.0%, 3.2%, 3.4%, 3.6%, 3.8%, 4.0%, 4.2%, 4.4%, 4.6%, 4.8%, 5.0%, 5.2%, 5.4%, 5.6%, 5.8%, 6.0%, 6.2%, 6.4%, 6.6%, 6.8%, 7.0%, 7.2%, 7.4%, 7.6%, 7.8%, and 8.0% of Pr_2O_5 may be included.

The blue matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses CoO or Co_2O_3 as the colorant. The two colorants can be used
10 alone or in combination, and the respective contents are generally 2% or less, and preferably 1.8% or less. If the content exceeds 2%, the colorants cannot be dissolved well in the matrix glass, the microcrystalline glass or the microcrystalline glass product. The lower limit of the content of the colorants is 0.05% or more, and if the content is less than 0.05%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product is not
15 obvious. In some embodiments, about 0.05%, 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, and 2.0% of CoO or Co_2O_3 may be included. In mixed use, the total amount of CoO and Co_2O_3 does not exceed 2%, and the lower limit of the total amount is 0.05% or more. In some embodiments, about 0.05%, 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%,
20 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0% of CoO and Co_2O_3 may be included.

The yellow matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses Cu_2O or CeO_2 as the colorant, and the two colorants are used alone or in combination, and the lower limit of the respective content is 0.5% or more, and if the content is less than 0.5%, the color of the matrix glass, the microcrystalline
25 glass or the microcrystalline glass product is not obvious. Cu_2O used alone is 4% or less, preferably 3% or less. If the content exceeds 4%, the matrix glass may easily crystallize. In some embodiments, about 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%,

2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of Cu_2O may be included. The content of CeO_2 used alone is generally 4% or less, and preferably 3% or less. If the content exceeds 4%, the glossiness of the matrix glass, the microcrystalline glass or the microcrystalline glass product may be poor. In some embodiments, about 0.5%,
5 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of CeO_2 may be included. Moreover, adding a small amount of CeO_2 to the glass has a defoaming effect, and CeO_2 can also be used as a clarifying agent in the glass. If two colorants are used in combination, the total amount is
10 generally 4% or less, and the lower limit of the total amount is 0.5% or more. In some embodiments, about 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of CeO_2 and Cu_2O may be included.

15 The black or smoky gray matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses Fe_2O_3 alone as the colorant; or uses a mixture of Fe_2O_3 and CoO as the colorant; or uses a mixture of Fe_2O_3 and Co_2O_3 as the colorant; or uses a mixture of Fe_2O_3 , CoO and NiO as the colorant; or uses a mixture of Fe_2O_3 , Co_2O_3 and NiO as the colorant. The colorant for preparing the black and smoky gray matrix glass,
20 microcrystalline glass or microcrystalline glass product is mainly colored with Fe_2O_3 , the content is 7% or less, preferably 5% or less, and the lower limit of the content is 0.2% or more. In some embodiments, about 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%,
25 3.9%, 4.0%, 4.5%, 5.0%, 5.5%, 6.0%, 6.5%, and 7.0% of Fe_2O_3 may be included. CoO and Co_2O_3 absorb visible light, which can deepen the coloring degree of the matrix glass, the microcrystalline glass or the microcrystalline glass products. Generally, when mixed with Fe_2O_3 , the respective content is 0.6% or less, and the lower limit is 0.2% or more. In some embodiments, about 0.2%, 0.3%, 0.4%, 0.5%, and 0.6% of CoO and/or Co_2O_3 may be

included. NiO absorbs visible light and can deepen the coloring degree of the matrix glass, the microcrystalline glass or the microcrystalline glass products. Generally, in mixed use, the content is 1% or less, and the lower limit of the total amount is 0.2% or more. In some embodiments, about 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, and 1.0% of NiO
5 may be included.

The purple matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses MnO_2 as the colorant, the content of which is generally 4% or less, preferably 3% or less, and the lower limit of the content is 0.1% or more, and if the content is less than 0.1%, the color of the matrix glass, the microcrystalline
10 glass or the microcrystalline glass product is not obvious. In some embodiments, about 0.1%, 0.2%, 0.3%, 0.4%, 0.5%, 0.6%, 0.7%, 0.8%, 0.9%, 1.0%, 1.1%, 1.2%, 1.3%, 1.4%, 1.5%, 1.6%, 1.7%, 1.8%, 1.9%, 2.0%, 2.1%, 2.2%, 2.3%, 2.4%, 2.5%, 2.6%, 2.7%, 2.8%, 2.9%, 3.0%, 3.1%, 3.2%, 3.3%, 3.4%, 3.5%, 3.6%, 3.7%, 3.8%, 3.9%, and 4.0% of MnO_2 may be included.

15 The pink matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses Er_2O_3 as the colorant, the content of which is generally 8% or less, and preferably 6% or less. Due to the low coloring efficiency of the rare earth element Er_2O_3 , when the content used exceeds 8%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product cannot be further deepened, but the cost is
20 increased. The lower limit of its content is 0.4% or more, and if the content less than 0.4%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product is not obvious. In some embodiments, about 0.4%, 0.6%, 0.8%, 1.0%, 1.2%, 1.4%, 1.6%, 1.8%, 2.0%, 2.2%, 2.4%, 2.6%, 2.8%, 3.0%, 3.2%, 3.4%, 3.6%, 3.8%, 4.0%, 4.2%, 4.4%, 4.6%, 4.8%, 5.0%, 5.2%, 5.4%, 5.6%, 5.8%, 6.0%, 6.2%, 6.4%, 6.6%, 6.8%, 7.0%, 7.2%,
25 7.4%, 7.6%, 7.8%, and 8.0% of Er_2O_3 may be included.

The purple-red matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses Nd_2O_3 as the colorant, the content of which is generally 8% or less, and preferably 6% or less. Due to the low coloring efficiency of the rare

earth element Nd_2O_3 , when the content used exceeds 8%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass product cannot be further deepened, but the cost is increased. The lower limit of its content is 0.4% or more, and if the content is less than 0.4%, the color of the matrix glass, the microcrystalline glass or the microcrystalline glass products is not obvious. In some embodiments, about 0.4%, 0.6%, 0.8%, 1.0%, 1.2%, 1.4%, 1.6%, 1.8%, 2.0%, 2.2%, 2.4%, 2.6%, 2.8%, 3.0%, 3.2%, 3.4%, 3.6%, 3.8%, 4.0%, 4.2%, 4.4%, 4.6%, 4.8%, 5.0%, 5.2%, 5.4%, 5.6%, 5.8%, 6.0%, 6.2%, 6.4%, 6.6%, 6.8%, 7.0%, 7.2%, 7.4%, 7.6%, 7.8%, and 8.0% of Nd_2O_3 may be included.

The red matrix glass, microcrystalline glass or microcrystalline glass product prepared by the present invention uses a mixed colorant of Er_2O_3 , Nd_2O_3 , and MnO_2 . Er ions in the glass absorb at 400-500 nm, Mn ions mainly absorb at 500 nm, and Nd ions has strong absorption mainly at 580 nm. The mixture of the three substances can prepare the red matrix glass, microcrystalline glass or microcrystalline glass product. Because Er_2O_3 and Nd_2O_3 are of rare earth coloring, the coloring ability is relatively weak. The usage amount of Er_2O_3 is within 6%. The usage amount of Nd_2O_3 is within 4%, and the coloring ability of MnO_2 is strong, and the usage amount of MnO_2 is within 2%. The lower limit of the total amount of mixed colorants used is 0.9% or more.

As used herein, "exclude" and "0%" means that the compound, molecule or element is not intentionally added as a raw material to the matrix glass, the microcrystalline glass or the microcrystalline glass product of the present invention. However, the raw materials and/or equipment for producing the matrix glass, the microcrystalline glass or the microcrystalline glass product may contain some impurities or components that are not intentionally added, which may be contained in small or trace amounts in the final matrix glass, microcrystalline glass or microcrystalline glass product. This situation is also within the protection scope of the present invention patent.

In some embodiments of the present invention, the crystal phase in the microcrystalline glass and the microcrystalline glass product contains lithium monosilicate crystals, which provides high strength for the microcrystalline glass and the microcrystalline glass product of

the present invention. The fracture toughness of the microcrystalline glass and the microcrystalline glass product becomes higher. The drop ball test height and four-point bending strength of the microcrystalline glass and the microcrystalline glass product become larger. The microcrystalline glass of the present invention has excellent chemical
5 strengthening properties, and can also be chemically strengthened to obtain additional mechanical strength. Through reasonable component design, the microcrystalline glass and the microcrystalline glass product of the present invention can obtain suitable grain sizes, so that the microcrystalline glass and the microcrystalline glass product of the present invention have high strength. The microcrystalline glass and the microcrystalline glass product of the
10 present invention have good crystallinity, so that the microcrystalline glass and the microcrystalline glass product of the present invention have excellent mechanical properties. The crystallinity herein refers to the degree of crystal integrity. The arrangement of particles inside the completely crystallized crystal is relatively regular, the diffraction lines are strong, sharp and symmetrical, and the half-height width of the diffraction peak is close to the width
15 measured by an instrument. There are defects such as dislocations in crystals with poor crystallinity, which makes the peak shape of the diffraction line wide and diffuse. The poorer the crystallinity is, the weaker the diffraction ability is and the wider the diffraction peak is, until they disappear into the background. In some embodiments, the crystallinity of the microcrystalline glass product or the microcrystalline glass is 50% or more, preferably 60%
20 or more, and more preferably 70% or more.

The grain size and type in the microcrystalline glass or the microcrystalline glass product of the present invention may affect the haze and transmittance of the microcrystalline glass or the microcrystalline glass product. The smaller the grain is, the higher the transmittance is. The smaller the haze is, the higher the transmittance is. In some embodiments, the haze of the
25 microcrystalline glass product or the microcrystalline glass with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less. In some embodiments, the grain size of the microcrystalline glass product or the microcrystalline glass is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

In some embodiments, the crystal phase content and refractive index in the microcrystalline glass or the microcrystalline glass product of the present invention affect the $|B|$ value of the microcrystalline glass or the microcrystalline glass product. It is observed that the microcrystalline glass or the microcrystalline glass product in the visible
5 light range is bluish or yellowish, which affects the optical properties of the product. It is marked with the $|B|$ value in the LAB (chromaticity value of the substance color). The microcrystalline glass or the microcrystalline glass product exhibits a low $|B|$ value in the visible light range. In some embodiments, the average light $|B|$ value of the microcrystalline glass or the microcrystalline glass product with a thickness of 1 mm or less
10 at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

In some embodiments, the microcrystalline glass or the microcrystalline glass product of the present invention exhibits high transparency in the visible light range (that is, the microcrystalline glass or the microcrystalline glass product is transparent). The microcrystalline glass or the microcrystalline glass product exhibits high transmittance in the
15 visible light range. In some embodiments, average light transmittance of the microcrystalline glass product or the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is preferably 89% or more. In some preferred embodiments, the light transmittance of the microcrystalline glass product or the microcrystalline glass with the thickness of 1 mm or less at 550 nm is preferably 91% or more.

20 In some embodiments, antimicrobial components may be added to the matrix glass, the microcrystalline glass or the microcrystalline glass product. The microcrystalline glass or the microcrystalline glass product described herein can be used in applications such as kitchen or catering countertops, which are likely to be exposed to harmful bacteria. The antimicrobial components that can be added to the matrix glass, the microcrystalline glass or the
25 microcrystalline glass product include, but are not limited to, Ag, AgO, Cu, CuO, Cu₂O, etc. In some embodiments, the separate or combined content of the antimicrobial components is 2% or less, and preferably 1% or less.

The matrix glass, the microcrystalline glass and the microcrystalline glass product of the

present invention can be produced and manufactured by the following methods:

generation of the matrix glass: uniformly mixing the raw materials according to a component ratio, putting the homogeneous mixture into a platinum or quartz crucible, and according to the melting difficulty of the glass components, melting in an electric furnace or
5 a gas furnace at a temperature ranging from 1250°C to 1650°C for 5-24 hours, stirring to make it uniform, cooling the mixture to an appropriate temperature and pouring into a mold, and then slowly cooling down.

The matrix glass of the present invention can be molded by a well-known method.

The matrix glass of the present invention undergoes crystallization treatment through a
10 crystallization process after molding or molding processing, so that crystals are uniformly precipitated inside the glass. The crystallization treatment may be performed in one stage or in two stages, and the crystallization treatment is preferably performed in two stages. The nucleation process is performed at a first temperature, and then a crystal growth process is performed at a second temperature higher than the nucleation process temperature. The
15 crystallization treatment performed at the first temperature is referred to as a first crystallization treatment, and the crystallization treatment performed at the second temperature is referred to as a second crystallization treatment.

To obtain the desired physical properties of the microcrystalline glass, the preferred crystallization process is:

20 The crystallization process is performed in one stage, and the nucleation process and the crystal growth process can be continuously performed. That is, the temperature is raised to a predetermined crystallization treatment temperature, and after reaching the crystallization treatment temperature, the temperature is maintained for a certain period of time, and then the temperature is lowered. The crystallization treatment temperature is preferably 600°C to
25 750°C, and in order to precipitate the desired crystal phase, it is more preferably 650°C to 700°C. The holding time at the crystallization treatment temperature is preferably 0-8 hours, and more preferably 1-6 hours.

When the crystallization treatment is performed in two stages as described above, the first temperature is preferably 470°C to 630°C, and the second temperature is preferably 650°C to 750°C. The holding time at the first temperature is preferably 0-24 hours, and more preferably 2-15 hours. The holding time at the second temperature is preferably 0-10 hours,
5 and more preferably 0.5-6 hours.

The holding time of 0 hour means that the temperature drops or increases less than 1 minute after reaching its temperature.

In some embodiments, the matrix glass or the microcrystalline glass described herein can be manufactured into a molded body by various processes, the molded body includes, but is
10 not limited to, a sheet. The process includes, but is not limited to, slit drawing, floating, rolling, and other sheet forming processes known in the art. Alternatively, the matrix glass or the microcrystalline glass can be formed by a floating method or a rolling method known in the art.

The matrix glass or the microcrystalline glass of the present invention can be used for
15 manufacturing the glass molded body of the sheet through methods such as grinding or polishing, but the method of manufacturing the glass molded body is not limited to these methods.

The matrix glass or the microcrystalline glass of the present invention may be prepared into various shapes by hot bending or pressing methods at a certain temperature, and is not
20 limited to these methods.

The matrix glass, the microcrystalline glass and the microcrystalline glass product of the present invention may have any thickness that is reasonably useful.

The microcrystalline glass of the present invention can not only improve the mechanical properties by precipitation of crystals, but also obtain higher strength by forming a
25 compressive stress layer, thereby preparing the microcrystalline glass product.

In some embodiments, the matrix glass or the microcrystalline glass may be processed

into a sheet, and/or shaped (such as perforated, hot-bending, etc.), polished and/or swept after shaping, and then chemically strengthened by a chemical strengthening process.

The chemical strengthening described in the present invention is an ion-exchange method. The matrix glass and the microcrystalline glass of the present invention may be ion-exchanged by a method known in the art. In the ion-exchange process, the smaller metal ions in the matrix glass or the microcrystalline glass are replaced or "exchanged" by larger metal ions of the same valence close to the matrix glass or the microcrystalline glass. The smaller ions are replaced with larger ions to build up compressive stress in the matrix glass or the microcrystalline glass to form a compressive stress layer.

10 In some embodiments, the metal ion is a monovalent alkali metal ion (e.g., Na^+ , K^+ , Rb^+ , Cs^+ , etc.), and the ion exchange is performed by immersing the matrix glass or the microcrystalline glass in a salt bath containing at least one molten salt of larger metal ions. The larger metal ions are used for replacing the smaller metal ions in the matrix glass. Alternatively, other monovalent metal ions such as Ag^+ , Tl^+ , and Cu^+ can also be used for
15 exchanging monovalent ions. One or more ion-exchange processes for chemically strengthening the matrix glass or the microcrystalline glass may include, but are not limited to: immersing it in a single salt bath, or immersing it in a plurality of salt baths with the same or different compositions. There are washing and/or annealing steps between immersion.

In some embodiments, the matrix glass or the microcrystalline glass can be ion-exchanged by immersing in a salt bath of molten Na salt (such as NaNO_3) at a
20 temperature of about 430°C to 470°C for about 6-20 hours. Preferably, the temperature range is 435°C to 460°C . Preferably, the time range is 8-13 hours. In this embodiment, Na ions replace some of Li ions in the matrix glass or the microcrystalline glass, thereby forming a surface compression layer and exhibiting high mechanical properties. In some embodiments,
25 the matrix glass or the microcrystalline glass can be ion-exchanged by immersing in a salt bath of molten K salt (such as KNO_3) at a temperature of about 400°C to 450°C for 1-8 hours. Preferably, the time range is 2-4 hours.

In some embodiments, there is an ion implantation method in which ions are implanted into the surface layer of the matrix glass or the microcrystalline glass, and a thermal strengthening method in which the matrix glass or the microcrystalline glass is heated and then rapidly cooled.

- 5 The performance indexes of the microcrystalline glass and/or the microcrystalline glass product and/or the matrix glass of the present invention are tested by the following methods:

[Haze]

A haze tester EEL57D is used for preparing a sample of 1 mm or less, and the test is carried out with GB2410-80 as the standard.

- 10 [Grain size]

An SEM scanning electron microscope is used for measurement. The microcrystalline glass is subjected to surface treatment in HF acid, and then metal spraying is performed on the surface of the microcrystalline glass, and surface scanning is performed under the SEM scanning electron microscope to determine the grain size.

- 15 [Light transmittance]

The light transmittance described herein is the external transmittance, sometimes referred to as the transmittance.

- 20 The sample is processed to 1 mm or less and then parallel polishing of opposite surfaces is performed, and the average light transmittance of 400-800 nm is measured with a Hitachi U-41000 spectrophotometer.

The sample is processed to 1 mm or less and then parallel polishing of opposite surfaces is performed, and the average light transmittance of 550 nm is measured with the Hitachi U-41000 spectrophotometer.

[Crystallinity]

XRD diffraction peaks are compared with database patterns. The crystallinity is obtained by calculating the proportion of the crystal phase diffraction intensity in the overall pattern intensity, and is internally calibrated by using pure quartz crystals.

[Surface stress] and [ion-exchange layer depth]

5 The surface stress is measured using a glass surface stress meter FSM-6000LEUV.

The ion-exchange layer depth is measured using a glass surface stress meter SLP-2000.

As measurement conditions, a refractive index of the sample is 1.54 and an optical elastic constant is 25.3 [(nm/cm)/Mpa] for calculation.

[Drop ball test height]

10 A 150×57×0.55 mm microcrystalline glass product sample is placed on a glass bearing fixture, and a 132 g steel ball drops from a predetermined height, the maximum drop ball test height that the sample can withstand the impact without breaking. Specifically, the test is carried out from the drop ball test height of 800 mm, and the height is changed sequentially through 850 mm, 900 mm, 950 mm, 1000 mm and above without breaking. For the examples
15 with the "drop ball test height", the microcrystalline glass product is used as a test object. The test data recorded as 1000 mm in the examples indicates that even if the steel ball drops from a height of 1000 mm, the microcrystalline glass product does not break and withstands the impact. In the present invention, the drop ball test height is sometimes referred to as the drop ball height.

20 [Body drop height]

A 150×57×0.55 mm microcrystalline glass product sample is placed on a glass bearing fixture, and a 32 g steel ball drops from a predetermined height, the maximum drop ball test height that the sample can withstand the impact without breaking. Specifically, the test is carried out from the drop ball test height of 500mm, and the height is changed sequentially
25 through 550mm, 600mm, 650mm, 700mm and above without breaking. For the examples

with the "body drop height", the microcrystalline glass is used as a test object. The test data recorded as 1000 mm in the examples indicates that even if the steel ball drops from a height of 1000 mm, the microcrystalline glass does not break and withstands the impact.

[Fracture toughness]

5 The method of directly measuring the size of an indentation propagation crack is used, the sample size is 2 mm×4 mm×20 mm, after chamfering, grinding and polishing, and after the sample preparation is completed, a Vickers hardness indenter is used for applying a force of 49 N to the sample and maintain it for 30s. After the indentation is made, the fracture strength is measured by a three-point bending method.

10 [Four-point bending strength]

A microcomputer-controlled electronic universal testing machine CMT6502 is used, and the sample size is the thickness of 1 mm or less, and the test is carried out according to ASTM C 158-2002.

15 The thickness of the sample is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

[Vickers hardness]

20 It is expressed by dividing the load (N) when a diamond quadrangular pyramid indenter with an opposite surface angle of 136° is pressed into a pyramid-shaped depression on the test surface, by the surface area (mm²) calculated by the length of the depression. The test load is 100 (N) and the holding time is 15 (seconds). In the present invention, the Vickers hardness is sometimes referred to as hardness for short.

[| B | value]

25 Minolta CM-700d is used for B value detection. The matched long tube and short tube for calibration are used for performing zero calibration and whiteboard calibration of

instrument, respectively. After calibration, the long tube is used for performing an air test to determine the stability and calibration reliability of the instrument ($B \leq 0.05$). After the instrument is calibrated, the product is placed on the zero-position long tube for testing.

The $|B|$ value is an absolute value of the B value.

5 [Coefficient of thermal expansion]

The coefficient of thermal expansion ($\alpha_{20\text{ }^{\circ}\text{C}-120\text{ }^{\circ}\text{C}}$) is tested according to the GB/T7962.16-2010 test method.

[Refractive index]

The refractive index (nd) is tested according to the GB/T7962.1-2010 method.

10 The microcrystalline glass product of the present invention has the following properties.

1) In some embodiments, the surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more.

2) In some embodiments, the four-point bending strength of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more.
15 more.

3) In some embodiments, the ion-exchange layer depth of the microcrystalline glass product is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more.

4) In some embodiments, the drop ball test height of the microcrystalline glass product is 1300 mm or more, preferably 1400 mm or more, and more preferably 1500 mm or more.

20 5) In some embodiments, the fracture toughness of the microcrystalline glass product is 1 $\text{MPa}\cdot\text{m}^{1/2}$ or more, preferably 1.1 $\text{MPa}\cdot\text{m}^{1/2}$ or more, and more preferably 1.2 $\text{MPa}\cdot\text{m}^{1/2}$ or more.

6) In some embodiments, the Vickers hardness (H_v) of the microcrystalline glass product

is 700 kgf/mm² or more, preferably 720 kgf/mm² or more, and more preferably 730 kgf/mm² or more.

7) In some embodiments, the crystallinity of the microcrystalline glass product is 50% or more, preferably 60% or more, and more preferably 70% or more.

5 8) In some embodiments, the grain size of the microcrystalline glass product is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

9) In some embodiments, the haze of the microcrystalline glass product with the thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further
10 preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

10) In some embodiments, the average transmittance of the microcrystalline glass product with the thickness of 1 mm or less at 400-800 nm is 89% or more. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more
15 further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

11) In some embodiments, the transmittance of the microcrystalline glass product with the thickness of 1 mm or less at 550 nm is 91% or more. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

20 12) In some embodiments, the average light | B | value of the microcrystalline glass product with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

25 The microcrystalline glass of the present invention has the following properties.

1) In some embodiments, the crystallinity of the microcrystalline glass is 50% or more, preferably 60% or more, and more preferably 70% or more.

2) In some embodiments, the grain size of the microcrystalline glass is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

5 3) In some embodiments, the haze of the microcrystalline glass with the thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

10 4) In some embodiments, the average transmittance of the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is 89% or more. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

15 5) In some embodiments, the transmittance of the microcrystalline glass with the thickness of 1 mm or less at 550 nm is 91% or more. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

6) In some embodiments, the body drop height of the microcrystalline glass is 1000 mm or more, preferably 1100 mm or more, and more preferably 1200 mm or more.

20 7) In some embodiments, the average light | B | value of the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less. The thickness is preferably 0.2-1 mm, more preferably 0.3-0.9 mm, further preferably 0.5-0.8 mm, and more further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

25 8) In some embodiments, the Vickers hardness (H_v) of the microcrystalline glass is 650 kgf/mm² or more, preferably 680 kgf/mm² or more, and more preferably 700 kgf/mm² or more.

9) In some embodiments, the coefficient of thermal expansion ($\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$) of the microcrystalline glass is $75-95 \times 10^{-7}/\text{K}$.

10) In some embodiments, the refractive index (n_d) of the microcrystalline glass is 1.5700-1.5800.

5 The matrix glass of the present invention has the following properties.

1) In some embodiments, the coefficient of thermal expansion ($\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$) of the matrix glass is $50 \times 10^{-7}/\text{K}$ - $70 \times 10^{-7}/\text{K}$.

2) In some embodiments, the refractive index (n_d) of the matrix glass is 1.5600-1.5700.

10 The microcrystalline glass, the microcrystalline glass product and the matrix glass of the present invention can be widely manufactured into glass cover plates or glass components due to the excellent properties above. Moreover, the microcrystalline glass, the microcrystalline glass product and the matrix glass of the present invention are applied to electronic devices or display devices, such as mobile phones, watches, computers, touch screens, etc., for manufacturing protective glass of mobile phones, smart phones, tablets, 15 notebook computers, PDAs, televisions, personal computers, MTA machines or industrial displays, or for manufacturing touch screens, protective windows, car windows, train windows, aviation machinery windows, touch screen protective glass, or for manufacturing hard disk substrates or solar cell substrates, or for manufacturing white household appliances, such as for manufacturing refrigerator parts or kitchenware.

20 Examples

To further clearly describe and illustrate the technical solutions of the present invention, the following non-limiting examples are provided. The examples of the present invention have gone through many efforts to ensure the accuracy of the values (e.g., quantity, temperature, etc.), but some errors and deviations are necessarily considered. The 25 composition itself is given in weight% based on the oxide and has been standardized to 100%.

<Example of matrix glass>

This example adopts the above-mentioned method for manufacturing a matrix glass to obtain the matrix glass having the components as shown in Tables 1-4. In addition, the characteristics of the matrix glass are measured by the test method described in the present invention, and the measurement results are shown in Tables 1-4.

Table 1

Component (wt%)	1#	2#	3#	4#	5#	6#	7#	8#	9#
SiO ₂	53	54	55	56	57	58	59	60	61
Al ₂ O ₃	11.5	11	10	11	11	8	8	8	9
Li ₂ O	13	13.5	15	14.5	15	16	18	13	13
Na ₂ O	1	1	2	1	2	1	1	1	3
P ₂ O ₅	4	4	4	4	5	6	4	5	4
ZrO ₂	10	11	8.5	8	7	8	7	10	7
Y ₂ O ₃	6	5	4	3	3	3	3	3	3
K ₂ O	1	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	2	0	0	0	0	0
ZnO	0	0	0	0	0	0	0	0	0
MgO	0	0	1	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0.5	0.5	0.5	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.6	0.5	0.5	0.4	0.4	0.4	0.4	0.3	0.4
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	4.5	5.7	6.9	8.8	9.0	10.0	9.7	9.3	8.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.43	0.39	0.36	0.42	0.41	0.27	0.28	0.29	0.38
Na ₂ O/Y ₂ O ₃	0.2	0.2	0.5	0.3	0.7	0.3	0.3	0.3	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.09	0.08	0.06	0.04	0.04	0.05	0.04	0.04	0.04
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$ ($\times 10^{-7}/\text{K}$)	62	65	65	63	63	68	68	65	68
n _d	1.5629	1.5615	1.5601	1.5659	1.5633	1.5619	1.5689	1.5642	1.5677

Table 2

Component (wt%)	10#	11#	12#	13#	14#	15#	16#	17#	18#
SiO ₂	62	63	53	53	50	51	52	64	65
Al ₂ O ₃	8	8	12	9	15	8	14	8	8

Li ₂ O	14.5	13	20	15	13	22	15	13	13
Na ₂ O	1	1	1	1	0	1	4	0	0
P ₂ O ₅	4	5	4	7	9	4	4	4	4
ZrO ₂	7	7	7	12	6	12	8	7	8
Y ₂ O ₃	3	3	3	3	7	2	3	1	1
K ₂ O	0	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	3	0
ZnO	0	0	0	0	0	0	0	0	1
MgO	0	0	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.4	0.4	0.3	1.2	0.2	0.4	0.1	0.1
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	8.5	8.3	10.3	11.3	4.0	19.0	9.0	24.0	25.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.31	0.32	0.39	0.26	0.54	0.21	0.52	0.33	0.32
Na ₂ O/Y ₂ O ₃	0.3	0.3	0.3	0.3	0.0	0.5	1.3	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.05	0.05	0.11	0.03	0.05	0.01	0.01
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}} (\times 10^{-7}/\text{K})$	69	69	68	65	60	58	59	62	70
n _d	1.5601	1.5622	1.5610	1.5612	1.5611	1.5610	1.5608	1.5602	1.5626

Table 3

Component (wt%)	19#	20#	21#	22#	23#	24#	25#	26#	27#
SiO ₂	54	55	55	45	46	47	48	49	66
Al ₂ O ₃	8	8	8	10	17	16	10	10	8
Li ₂ O	15	15	15	25	18	18	24	23	10
Na ₂ O	0	4	2	0	0	0	0	0	0
P ₂ O ₅	4	4	4	4	4	4	4	4	4
ZrO ₂	9	9	9	8	9	9	9	9	9
Y ₂ O ₃	4	3	3	8	3	3	3	3	3
K ₂ O	4	0	2	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	0	0
ZnO	0	0	0	0	0	0	2	0	0
MgO	0	0	0	0	0	0	0	2	0
SrO	2	0	0	0	3	0	0	0	0
BaO	0	2	0	0	0	3	0	0	0
TiO ₂	0	0	2	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0

Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.3	0.3	1.0	0.3	0.3	0.3	0.3	0.3
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	7.0	9.3	9.3	4.6	10.3	10.3	12.3	12.0	7.7
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.29	0.29	0.29	0.27	0.55	0.52	0.27	0.28	0.35
Na ₂ O/Y ₂ O ₃	0.0	1.3	0.7	0.0	0.0	0.0	0.0	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.06	0.05	0.05	0.15	0.05	0.05	0.05	0.05	0.04
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$ ($\times 10^{-7}/\text{K}$)	62	70	70	53	52	52	65	64	63
n _d	1.5650	1.5625	1.5608	1.5632	1.5667	1.5611	1.5632	1.5688	1.5655

Table 4

Component (wt%)	28#	29#	30#	31#	32#	33#	34#
SiO ₂	67	68	69	70	49	50	55
Al ₂ O ₃	8	8	8	8	10	10	8
Li ₂ O	10	10	10	10	12	15	15
Na ₂ O	1	0	0	0	2	6	2
P ₂ O ₅	2	2	2	2	4	4	4
ZrO ₂	9	9	8	7	15	9	9
Y ₂ O ₃	3	3	3	3	8	1	2
K ₂ O	0	0	0	0	0	0	5
B ₂ O ₃	0	0	0	0	0	5	0
ZnO	0	0	0	0	0	0	0
MgO	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0
Sb ₂ O ₃	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.3	0.3	0.4	0.4	0.5	0.1	0.2
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	7.0	7.0	6.7	6.3	3.9	28.0	14.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.38	0.38	0.40	0.42	0.32	0.36	0.29
Na ₂ O/Y ₂ O ₃	0.3	0.0	0.0	0.0	0.3	6.0	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.04	0.04	0.14	0.02	0.03
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$ ($\times 10^{-7}/\text{K}$)	68	69	70	65	65	65	65
n _d	1.5666	1.5689	1.5634	1.5641	1.5625	1.5618	1.5625

<Example of microcrystalline glass>

This example adopts the above-mentioned method for manufacturing a microcrystalline glass to obtain the microcrystalline glass having the components as shown in Tables 5-8. In addition, the characteristics of each microcrystalline glass are measured by the test method described in the present invention, and the measurement results are shown in Tables 5-8.

5 Table 5

Component (wt%)	1#	2#	3#	4#	5#	6#	7#	8#	9#
SiO ₂	53	54	55	56	57	58	59	60	61
Al ₂ O ₃	11.5	11	10	11	11	8	8	8	9
Li ₂ O	13	13.5	15	14.5	15	16	18	13	13
Na ₂ O	1	1	2	1	2	1	1	1	3
P ₂ O ₅	4	4	4	4	5	6	4	5	4
ZrO ₂	10	11	8.5	8	7	8	7	10	7
Y ₂ O ₃	6	5	4	3	3	3	3	3	3
K ₂ O	1	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	2	0	0	0	0	0
ZnO	0	0	0	0	0	0	0	0	0
MgO	0	0	1	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0.5	0.5	0.5	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.6	0.5	0.5	0.4	0.4	0.4	0.4	0.3	0.4
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	4.5	5.7	6.9	8.8	9.0	10.0	9.7	9.3	8.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.43	0.39	0.36	0.42	0.41	0.27	0.28	0.29	0.38
Na ₂ O/Y ₂ O ₃	0.2	0.2	0.5	0.3	0.7	0.3	0.3	0.3	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.09	0.08	0.06	0.04	0.04	0.05	0.04	0.04	0.04
Crystal phase	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate
Crystallinity (%)	80	84	90	80	82	88	75	74	73
Grain size (nm)	25	25	30	25	25	25	25	30	25
Haze at the thickness of 1 mm (%)	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09
B value at the thickness of 1 mm	0.45	0.45	0.4	0.45	0.4	0.45	0.4	0.42	0.47
H _v (kgf/mm ²)	706	703	710	711	706	707	701	703	705

Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92
Body drop height (mm)	1200	1200	1200	1200	1250	1200	1200	1200	1300
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$ ($\times 10^{-7}/\text{K}$)	92	93	90	92	95	92	98	92	88
n_d	1.5789	1.5734	1.5711	1.5725	1.5718	1.5788	1.5755	1.5766	1.5778

Table 6

Component (wt%)	10#	11#	12#	13#	14#	15#	16#	17#	18#
SiO ₂	62	63	53	53	50	51	52	64	65
Al ₂ O ₃	8	8	12	9	15	8	14	8	8
Li ₂ O	14.5	13	20	15	13	22	15	13	13
Na ₂ O	1	1	1	1	0	1	4	0	0
P ₂ O ₅	4	5	4	7	9	4	4	4	4
ZrO ₂	7	7	7	12	6	12	8	7	8
Y ₂ O ₃	3	3	3	3	7	2	3	1	1
K ₂ O	0	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	3	0
ZnO	0	0	0	0	0	0	0	0	1
MgO	0	0	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.4	0.4	0.3	1.2	0.2	0.4	0.1	0.1
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	8.5	8.3	10.3	11.3	4.0	19.0	9.0	24.0	25.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.31	0.32	0.39	0.26	0.54	0.21	0.52	0.33	0.32
Na ₂ O/Y ₂ O ₃	0.3	0.3	0.3	0.3	0.0	0.5	1.3	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.05	0.05	0.11	0.03	0.05	0.01	0.01
Crystal phase	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate

				and lithium phosph ate	and lithium phosph ate				
Crystallinity (%)	77	76	85	89	67	68	65	61	62
Grain size (nm)	25	25	30	25	35	35	35	40	40
Haze at the thickness of 1 mm (%)	0.09	0.09	0.09	0.09	0.11	0.11	0.12	0.14	0.14
B value at the thickness of 1 mm	0.4	0.45	0.4	0.48	0.54	0.54	0.48	0.54	0.54
H _v (kgf/mm ²)	708	709	703	702	695	685	680	692	684
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92
Body drop height (mm)	1200	1200	1350	1200	1100	1100	1100	1100	1100
$\alpha_{20^{\circ}\text{C}-120^{\circ}\text{C}}$ ($\times 10^{-7}/\text{K}$)	92	86	89	85	93	95	80	83	85
n _d	1.5705	1.5725	1.5709	1.5778	1.5708	1.5702	1.5726	1.575	1.5725

Table 7

Component (wt%)	19#	20#	21#	22#	23#	24#	25#	26#	27#
SiO ₂	54	55	55	45	46	47	48	49	66
Al ₂ O ₃	8	8	8	10	17	16	10	10	8
Li ₂ O	15	15	15	25	18	18	24	23	10
Na ₂ O	0	4	2	0	0	0	0	0	0
P ₂ O ₅	4	4	4	4	4	4	4	4	4
ZrO ₂	9	9	9	8	9	9	9	9	9
Y ₂ O ₃	4	3	3	8	3	3	3	3	3
K ₂ O	4	0	2	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	0	0
ZnO	0	0	0	0	0	0	2	0	0
MgO	0	0	0	0	0	0	0	2	0
SrO	2	0	0	0	3	0	0	0	0
BaO	0	2	0	0	0	3	0	0	0
TiO ₂	0	0	2	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0

Sb ₂ O ₃	0	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.3	0.3	1.0	0.3	0.3	0.3	0.3	0.3
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/ Y ₂ O ₃	7.0	9.3	9.3	4.6	10.3	10.3	12.3	12.0	7.7
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ + P ₂ O ₅)	0.29	0.29	0.29	0.27	0.55	0.52	0.27	0.28	0.35
Na ₂ O/Y ₂ O ₃	0.0	1.3	0.7	0.0	0.0	0.0	0.0	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.06	0.05	0.05	0.15	0.05	0.05	0.05	0.05	0.04
Crystal phase	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate and lithium phosphate	Lithium monosilicate and lithium phosphate	Lithium monosilicate and lithium phosphate	Lithium monosilicate and lithium phosphate	Lithium monosilicate and lithium phosphate	Lithium monosilicate
Crystallinity (%)	68	69	68	55	56	57	58	59	54
Grain size (nm)	35	35	35	35	35	35	35	35	35
Haze at the thickness of 1 mm (%)	0.12	0.12	0.12	0.11	0.09	0.09	0.1	0.1	0.09
B value at the thickness of 1 mm	0.48	0.48	0.48	0.58	0.48	0.48	0.48	0.48	0.48
H _v (kgf/mm ²)	695	698	690	675	674	665	668	673	663
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92
Body drop height (mm)	1100	1100	1100	1000	1000	1000	1000	1000	1000
α _{20℃-120℃} (×10 ⁻⁷ /K)	86	88	85	75	76	77	77	83	85
n _d	1.5710	1.5712	1.5705	1.5715	1.5706	1.5759	1.5733	1.5719	1.5789

Table 8

Component (wt%)	28#	29#	30#	31#	32#	33#	34#
SiO ₂	67	68	69	70	49	50	55
Al ₂ O ₃	8	8	8	8	10	10	8
Li ₂ O	10	10	10	10	12	15	15
Na ₂ O	1	0	0	0	2	6	2
P ₂ O ₅	2	2	2	2	4	4	4

ZrO ₂	9	9	8	7	15	9	9
Y ₂ O ₃	3	3	3	3	8	1	2
K ₂ O	0	0	0	0	0	0	5
B ₂ O ₃	0	0	0	0	0	5	0
ZnO	0	0	0	0	0	0	0
MgO	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0
Sb ₂ O ₃	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.3	0.3	0.4	0.4	0.5	0.1	0.2
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	7.0	7.0	6.7	6.3	3.9	28.0	14.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.38	0.38	0.40	0.42	0.32	0.36	0.29
Na ₂ O/Y ₂ O ₃	0.3	0.0	0.0	0.0	0.3	6.0	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.04	0.04	0.14	0.02	0.03
Crystal phase	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate	Lithium monosilicate
Crystallinity (%)	53	55	55	51	55	58	59
Grain size (nm)	35	35	35	35	35	40	35
Haze at the thickness of 1 mm (%)	0.09	0.09	0.09	0.09	0.14	0.14	0.1
B value at the thickness of 1 mm	0.48	0.48	0.48	0.50	0.48	0.48	0.48
H _v (kgf/mm ²)	653	654	663	668	685	686	689
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92
Body drop height (mm)	1000	1000	1000	1000	1000	1000	1000
α _{20℃-120℃} (×10 ⁻⁷ /K)	86	88	82	86	88	89	88
n _d	1.5742	1.5779	1.5732	1.5767	1.5711	1.5732	1.5711

<Example of microcrystalline glass product>

This example adopts the above-mentioned method for manufacturing a microcrystalline

glass product to obtain the microcrystalline glass product having the components as shown in Tables 9-12. In addition, the characteristics of each microcrystalline glass product are measured by the test method described in the present invention, and the measurement results are shown in Tables 9-12.

5 Table 9

Component (wt%)	1#	2#	3#	4#	5#	6#	7#	8#	9#
SiO ₂	53	54	55	56	57	58	59	60	61
Al ₂ O ₃	11.5	11	10	11	11	8	8	8	9
Li ₂ O	13	13.5	15	14.5	15	16	18	13	13
Na ₂ O	1	1	2	1	2	1	1	1	3
P ₂ O ₅	4	4	4	4	5	6	4	5	4
ZrO ₂	10	11	8.5	8	7	8	7	10	7
Y ₂ O ₃	6	5	4	3	3	3	3	3	3
K ₂ O	1	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	2	0	0	0	0	0
ZnO	0	0	0	0	0	0	0	0	0
MgO	0	0	1	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0.5	0.5	0.5	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.6	0.5	0.5	0.4	0.4	0.4	0.4	0.3	0.4
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	4.5	5.7	6.9	8.8	9.0	10.0	9.7	9.3	8.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.43	0.39	0.36	0.42	0.41	0.27	0.28	0.29	0.38
Na ₂ O/Y ₂ O ₃	0.2	0.2	0.5	0.3	0.7	0.3	0.3	0.3	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.09	0.08	0.06	0.04	0.04	0.05	0.04	0.04	0.04
Surface stress (MPa)	775	805	778	776	786	769	780	856	780
Ion-exchange layer depth (μm)	28	26	26	48	49	45	45	45	46
Four-point bending (MPa)	775	758	736	755	843	855	795	810	862
Drop ball test height (mm)	1600	1500	1600	1600	1600	1600	1600	1600	1500
Fracture toughness (MPa•m ^{1/2})	1.3	1.4	1.3	1.3	1.5	1.4	1.3	1.3	1.3
H _v (kgf/mm ²)	766	763	770	771	766	767	761	763	765
Crystallinity (%)	80	84	90	80	82	88	75	74	73
Grain size (nm)	25	25	30	25	25	25	25	30	25
Haze at the thickness of 1	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09	0.09

mm (%)									
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92

Table 10

Component (wt%)	10#	11#	12#	13#	14#	15#	16#	17#	18#
SiO ₂	62	63	53	53	50	51	52	64	65
Al ₂ O ₃	8	8	12	9	15	8	14	8	8
Li ₂ O	14.5	13	20	15	13	22	15	13	13
Na ₂ O	1	1	1	1	0	1	4	0	0
P ₂ O ₅	4	5	4	7	9	4	4	4	4
ZrO ₂	7	7	7	12	6	12	8	7	8
Y ₂ O ₃	3	3	3	3	7	2	3	1	1
K ₂ O	0	0	0	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	3	0
ZnO	0	0	0	0	0	0	0	0	1
MgO	0	0	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0.5	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.4	0.4	0.3	1.2	0.2	0.4	0.1	0.1
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	8.5	8.3	10.3	11.3	4.0	19.0	9.0	24.0	25.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.31	0.32	0.39	0.26	0.54	0.21	0.52	0.33	0.32
Na ₂ O/Y ₂ O ₃	0.3	0.3	0.3	0.3	0.0	0.5	1.3	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.05	0.05	0.11	0.03	0.05	0.01	0.01
Surface stress (MPa)	785	790	765	773	655	659	688	656	688
Ion-exchange layer depth (μm)	45	45	55	46	28	40	45	35	35
Four-point bending (MPa)	835	799	745	776	704	669	691	633	688
Drop ball test height (mm)	1600	1600	1700	1600	1400	1400	1400	1400	1400
Fracture toughness (MPa•m ^{1/2})	1.5	1.3	1.4	1.3	1.1	1.2	1.2	1.2	1.2
H _v (kgf/mm ²)	768	769	763	762	703	708	711	713	724
Crystallinity (%)	77	76	85	89	67	68	65	61	62

Grain size (nm)	25	25	30	25	35	35	35	40	40
Haze at the thickness of 1 mm (%)	0.09	0.09	0.09	0.09	0.11	0.11	0.12	0.14	0.14
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92

Table 11

Component (wt%)	19#	20#	21#	22#	23#	24#	25#	26#	27#
SiO ₂	54	55	55	45	46	47	48	49	66
Al ₂ O ₃	8	8	8	10	17	16	10	10	8
Li ₂ O	15	15	15	25	18	18	24	23	10
Na ₂ O	0	4	2	0	0	0	0	0	0
P ₂ O ₅	4	4	4	4	4	4	4	4	4
ZrO ₂	9	9	9	8	9	9	9	9	9
Y ₂ O ₃	4	3	3	8	3	3	3	3	3
K ₂ O	4	0	2	0	0	0	0	0	0
B ₂ O ₃	0	0	0	0	0	0	0	0	0
ZnO	0	0	0	0	0	0	2	0	0
MgO	0	0	0	0	0	0	0	2	0
SrO	2	0	0	0	3	0	0	0	0
BaO	0	2	0	0	0	3	0	0	0
TiO ₂	0	0	2	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0	0	0
Sb ₂ O ₃	0	0	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.4	0.3	0.3	1.0	0.3	0.3	0.3	0.3	0.3
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	7.0	9.3	9.3	4.6	10.3	10.3	12.3	12.0	7.7
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.29	0.29	0.29	0.27	0.55	0.52	0.27	0.28	0.35
Na ₂ O/Y ₂ O ₃	0.0	1.3	0.7	0.0	0.0	0.0	0.0	0.0	0.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.06	0.05	0.05	0.15	0.05	0.05	0.05	0.05	0.04
Surface stress (MPa)	673	697	656	638	635	635	648	649	625
Ion-exchange layer depth (μm)	35	35	35	25	35	35	35	35	30
Four-point bending (MPa)	698	668	695	658	678	635	645	655	635
Drop ball test height (mm)	1400	1400	1300	1300	1600	1600	1700	1600	1600
Fracture toughness (MPa•m ^{1/2})	1.2	1.2	1.2	1.1	1.1	1.2	1.2	1.2	1.2

H _v (kgf/mm ²)	706	720	721	713	714	716	711	705	704
Crystallinity (%)	68	69	68	55	56	57	58	59	54
Grain size (nm)	35	35	35	35	35	35	35	35	35
Haze at the thickness of 1 mm (%)	0.12	0.12	0.12	0.11	0.09	0.09	0.1	0.1	0.09
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92	92	92

Table 12

Component (wt%)	28#	29#	30#	31#	32#	33#	34#
SiO ₂	67	68	69	70	49	50	55
Al ₂ O ₃	8	8	8	8	10	10	8
Li ₂ O	10	10	10	10	12	15	15
Na ₂ O	1	0	0	0	2	6	2
P ₂ O ₅	2	2	2	2	4	4	4
ZrO ₂	9	9	8	7	15	9	9
Y ₂ O ₃	3	3	3	3	8	1	2
K ₂ O	0	0	0	0	0	0	5
B ₂ O ₃	0	0	0	0	0	5	0
ZnO	0	0	0	0	0	0	0
MgO	0	0	0	0	0	0	0
SrO	0	0	0	0	0	0	0
BaO	0	0	0	0	0	0	0
TiO ₂	0	0	0	0	0	0	0
CaO	0	0	0	0	0	0	0
La ₂ O ₃	0	0	0	0	0	0	0
Gd ₂ O ₃	0	0	0	0	0	0	0
Yb ₂ O ₃	0	0	0	0	0	0	0
Sb ₂ O ₃	0	0	0	0	0	0	0
In total	100	100	100	100	100	100	100
Y ₂ O ₃ /ZrO ₂	0.3	0.3	0.4	0.4	0.5	0.1	0.2
(Li ₂ O+ZrO ₂ +P ₂ O ₅)/Y ₂ O ₃	7.0	7.0	6.7	6.3	3.9	28.0	14.0
Al ₂ O ₃ /(Li ₂ O+ZrO ₂ +P ₂ O ₅)	0.38	0.38	0.40	0.42	0.32	0.36	0.29
Na ₂ O/Y ₂ O ₃	0.3	0.0	0.0	0.0	0.3	6.0	1.0
Y ₂ O ₃ /(Al ₂ O ₃ +SiO ₂)	0.04	0.04	0.04	0.04	0.14	0.02	0.03
Surface stress (MPa)	612	638	648	635	645	601	645
Ion-exchange layer depth (μm)	45	30	30	30	45	45	35
Four-point bending (MPa)	648	651	645	638	679	625	612
Drop ball test height (mm)	1600	1700	1600	1700	1300	1400	1500

Fracture toughness (MPa•m ^{1/2})	1.2	1.2	1.2	1.2	1.2	1.2	1.2
H _v (kgf/mm ²)	713	712	709	705	701	711	701
Crystallinity (%)	53	55	55	51	55	58	59
Grain size (nm)	35	35	35	35	35	40	35
Haze at the thickness of 1 mm (%)	0.09	0.09	0.09	0.09	0.14	0.14	0.1
Average light transmittance at the thickness of 1 mm at 400-800 nm (%)	90	90	90	90	90	90	90
Light transmittance at the thickness of 1 mm at the wavelength of 550 nm (%)	92	92	92	92	92	92	92

5

10

15

CLAIMS

What is claimed is:

1. A microcrystalline glass product, comprising the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and
5 Y₂O₃: greater than 0 but less than or equal to 8%.

2. The microcrystalline glass product according to claim 1, further comprising the following components in percentage by weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or BaO: 0-5%; and/or CaO: 0-5%; and/or
10 TiO₂: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

3. The microcrystalline glass product according to claim 1 or 2, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

15 1) Y₂O₃/ZrO₂ is greater than 0;

2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 2.5-50.0;

3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.16-0.9;

4) Na₂O/Y₂O₃ is 6.0 or less;

5) Y₂O₃/(Al₂O₃+SiO₂) is greater than 0 but less than or equal to 0.15.

20 4. The microcrystalline glass product according to claim 1 or 2, comprising the following components in percentage by weight: SiO₂: 50-65%; and/or Al₂O₃: 8-15%; and/or Li₂O: 13-22%; and/or ZrO₂: 6-12%; and/or P₂O₅: 3.5-9%; and/or K₂O: 0-4%; and/or MgO: 0-1%; and/or ZnO: 0-1%; and/or Na₂O: 1-5%; and/or Y₂O₃: 1-7%; and/or SrO: 0-3%; and/or BaO: 0-3%; and/or CaO: 0-3%; and/or TiO₂: 0-3%; and/or B₂O₃: 0-3%; and/or Ln₂O₃: 0-4%;
25 and/or a clarifying agent: 0-1%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃,

and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

5. The microcrystalline glass product according to claim 1 or 2, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

- 5 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.1-1.0;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 3.0-40.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;
- 5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

- 10 6. The microcrystalline glass product according to claim 1 or 2, comprising the following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent:
- 15 0-0.5%, wherein Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

7. The microcrystalline glass product according to claim 1 or 2, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

- 20 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;
- 2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;
- 3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;
- 4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;

5) $Y_2O_3/(Al_2O_3+SiO_2)$ is 0.03-0.09.

8. The microcrystalline glass product according to claim 1 or 2, wherein the components exclude SrO; and/or exclude BaO; and/or exclude CaO; and/or exclude ZnO; and/or exclude PbO; and/or excludes As_2O_3 ; and/or exclude TiO_2 ; and/or exclude B_2O_3 ; and/or exclude
5 Ln_2O_3 ; and/or exclude F; and/or exclude Ta_2O_5 .

9. The microcrystalline glass product according to claim 1 or 2, wherein a crystal phase of the microcrystalline glass product comprises lithium monosilicate and/or lithium phosphate.

10. The microcrystalline glass product according to claim 1 or 2, wherein a crystal phase
10 of the microcrystalline glass product mainly comprises lithium monosilicate; lithium monosilicate has a higher weight percentage than other crystal phases, and lithium monosilicate accounts for 10-63.5% by weight of the microcrystalline glass product, and preferably 15-55%.

11. The microcrystalline glass product according to claim 1 or 2, wherein the
15 microcrystalline glass product comprises a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% by weight of the microcrystalline glass product, and preferably 5-12%.

12. The microcrystalline glass product according to claim 1 or 2, wherein a surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 MPa or more,
20 and more preferably 700 MPa or more; and/or a four-point bending strength is 600 MPa or more, preferably 650 MPa or more, and more preferably 700 MPa or more; and/or an ion-exchange layer depth is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more; and/or a drop ball test height is 1300 mm or more, preferably 1400 mm or more, and more preferably 1500 mm or more; and/or a fracture toughness is 1 $MPa \cdot m^{1/2}$ or
25 more, preferably 1.1 $MPa \cdot m^{1/2}$ or more, and more preferably 1.2 $MPa \cdot m^{1/2}$ or more; and/or a Vickers hardness is 700 kgf/mm^2 or more, preferably 720 kgf/mm^2 or more, and more preferably 730 kgf/mm^2 or more.

13. The microcrystalline glass product according to claim 1 or 2, wherein a crystallinity of the microcrystalline glass product is 50% or more, preferably 60% or more, and more preferably 70% or more; and/or a crystal grain size is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

5 14. The microcrystalline glass product according to claim 1 or 2, wherein a haze of the microcrystalline glass product with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less; and/or an average transmittance of the microcrystalline glass product with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more; and/or a transmittance of the microcrystalline glass product with the
10 thickness of 1 mm or less at the wavelength of 550 nm is 91% or more; and/or an average light | B | value of the microcrystalline glass product with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

15 15. The microcrystalline glass product according to claim 14, wherein the thickness of the microcrystalline glass product is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

16. The microcrystalline glass product according to claim 1 or 2, wherein the microcrystalline glass product includes a colorant.

17. The microcrystalline glass product according to claim 16, wherein the colorant comprises the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃:
20 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

18. Microcrystalline glass, comprising the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃:
25 greater than 0 but less than or equal to 8%.

19. The microcrystalline glass according to claim 18, further comprising the following

components in percentage by weight: K_2O : 0-5%; and/or MgO : 0-2%; and/or ZnO : 0-2%; and/or Na_2O : 0-6%; and/or SrO : 0-5%; and/or BaO : 0-5%; and/or TiO_2 : 0-5%; and/or CaO : 0-5%; and/or B_2O_3 : 0-5%; and/or Ln_2O_3 : 0-5%; and/or a clarifying agent: 0-2%, wherein Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of
5 Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

20. The microcrystalline glass according to claim 18 or 19, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

- 1) Y_2O_3/ZrO_2 is greater than 0;
- 10 2) $(Li_2O+ZrO_2+P_2O_5)/Y_2O_3$ is 2.5-50.0;
- 3) $Al_2O_3/(Li_2O+ZrO_2+P_2O_5)$ is 0.16-0.9;
- 4) Na_2O/Y_2O_3 is 6.0 or less;
- 5) $Y_2O_3/(Al_2O_3+SiO_2)$ is greater than 0 but less than or equal to 0.15.

21. The microcrystalline glass according to claim 18 or 19, comprising the following
15 components in percentage by weight: SiO_2 : 50-65%; and/or Al_2O_3 : 8-15%; and/or Li_2O : 13-22%; and/or ZrO_2 : 6-12%; and/or P_2O_5 : 3.5-9%; and/or K_2O : 0-4%; and/or MgO : 0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%; and/or Y_2O_3 : 1-7%; and/or SrO : 0-3%; and/or TiO_2 : 0-3%; and/or BaO : 0-3%; and/or CaO : 0-3%; and/or B_2O_3 : 0-3%; and/or Ln_2O_3 : 0-4%; and/or a clarifying agent: 0-1%, wherein Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 ,
20 and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

22. The microcrystalline glass according to claim 18 or 19, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

- 1) Y_2O_3/ZrO_2 is 0.1-1.0;

2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 3.0-40.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.18-0.6;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.1-5.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.01-0.12.

5 23. The microcrystalline glass according to claim 18 or 19, comprising the following components in percentage by weight: SiO_2 : 53-63%; and/or Al_2O_3 : 8-12%; and/or Li_2O : 14-21%; and/or ZrO_2 : 7-12%; and/or P_2O_5 : 4-8%; and/or K_2O : 0-2%; and/or Y_2O_3 : 2-6%; and/or B_2O_3 : 0-2%; and/or Na_2O : 1.5-4%; and/or SrO : 0-1%; and/or TiO_2 : 0-1%; and/or BaO : 0-1%; and/or CaO : 0-1%; and/or Ln_2O_3 : 0-3%; and/or a clarifying agent: 0-0.5%, wherein
10 Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F , Cl , and Br .

24. The microcrystalline glass according to claim 18 or 19, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

15 1) $\text{Y}_2\text{O}_3/\text{ZrO}_2$ is 0.2-0.6;

2) $(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)/\text{Y}_2\text{O}_3$ is 4.0-21.0;

3) $\text{Al}_2\text{O}_3/(\text{Li}_2\text{O}+\text{ZrO}_2+\text{P}_2\text{O}_5)$ is 0.19-0.5;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 0.3-2.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is 0.03-0.09.

20 25. The microcrystalline glass according to claim 18 or 19, wherein the components exclude SrO ; and/or exclude BaO ; and/or exclude CaO ; and/or exclude ZnO ; and/or exclude PbO ; and/or exclude As_2O_3 ; and/or exclude TiO_2 ; and/or exclude B_2O_3 ; and/or exclude Ln_2O_3 ; and/or exclude F ; and/or exclude Ta_2O_5 .

26. The microcrystalline glass according to claim 18 or 19, wherein a crystal phase of the microcrystalline glass comprises lithium monosilicate and/or lithium phosphate.

27. The microcrystalline glass according to claim 18 or 19, wherein a crystal phase of the microcrystalline glass mainly comprises lithium monosilicate; lithium monosilicate has a
5 higher weight percentage than other crystal phases, and lithium monosilicate accounts for 10-63.5% by weight of the microcrystalline glass, and preferably 15-55%.

28. The microcrystalline glass according to claim 18 or 19, wherein the microcrystalline glass comprises a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% by weight of the microcrystalline glass, and preferably 5-12%.

10 29. The microcrystalline glass according to claim 18 or 19, wherein a crystallinity of the microcrystalline glass is 50% or more, preferably 60% or more, and more preferably 70% or more; and/or a crystalgrain size is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less; and/or a coefficient of thermal expansion is $75-95 \times 10^{-7}/K$; and/or a refractive index is 1.5700-1.5800.

15 30. The microcrystalline glass according to claim 18 or 19, wherein a body drop height of the microcrystalline glass is 1000 mm or more, preferably 1100 mm or more, and more preferably 1200 mm or more; and/or a Vickers hardness is 650 kgf/mm² or more, preferably 680 kgf/mm² or more, and more preferably 700 kgf/mm² or more.

20 31. The microcrystalline glass according to claim 18 or 19, wherein a haze of the microcrystalline glass with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less; and/or an average transmittance of the microcrystalline glass with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more; and/or a transmittance of the microcrystalline glass with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more; and/or an average light | B | value of
25 the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

32. The microcrystalline glass according to claim 31, wherein the thickness of the microcrystalline glass is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

33. The microcrystalline glass according to claim 18 or 19, wherein the microcrystalline glass includes a colorant.

34. The microcrystalline glass according to claim 33, wherein the colorant comprises the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

35. Matrix glass, comprising the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃: greater than 0 but less than or equal to 8%.

36. The matrix glass according to claim 35, further comprising the following components in percentage by weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or BaO: 0-5%; and/or CaO: 0-5%; and/or TiO₂: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

37. The matrix glass according to claim 35 or 36, wherein the components are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

1) Y₂O₃/ZrO₂ is greater than 0, preferably 0.1-1.0, and more preferably 0.2-0.6;

2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 2.5-50.0, preferably 3.0-40.0, and more preferably 4.0-21.0;

3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.16-0.9, preferably 0.18-0.6, and more preferably

0.19-0.5;

4) $\text{Na}_2\text{O}/\text{Y}_2\text{O}_3$ is 6.0 or less, preferably 0.1-5.0, and more preferably 0.3-2.0;

5) $\text{Y}_2\text{O}_3/(\text{Al}_2\text{O}_3+\text{SiO}_2)$ is greater than 0 but less than or equal to 0.15, preferably 0.01-0.12, and more preferably 0.03-0.09.

5 38. The matrix glass according to claim 35 or 36, comprising the following components
in percentage by weight: SiO_2 : 50-65%, preferably 53-63%; and/or Al_2O_3 : 8-15%, preferably
8-12%; and/or Li_2O : 13-22%, preferably 14-21%; and/or ZrO_2 : 6-12%, preferably 7-12%;
and/or P_2O_5 : 3.5-9%, preferably 4-8%; and/or K_2O : 0-4%, preferably 0-2%; and/or MgO :
0-1%; and/or ZnO : 0-1%; and/or Na_2O : 1-5%, preferably 1.5-4%; and/or Y_2O_3 : 1-7%,
10 preferably 2-6%; and/or SrO : 0-3%, preferably 0-1%; and/or BaO : 0-3%, preferably 0-1%;
and/or TiO_2 : 0-3%, preferably 0-1%; and/or CaO : 0-3%, preferably 0-1%; and/or B_2O_3 :
0-3%, preferably 0-2%; and/or Ln_2O_3 : 0-4%, preferably 0-3%; and/or a clarifying agent:
0-1%, preferably 0-0.5%, wherein Ln_2O_3 is one or more of La_2O_3 , Gd_2O_3 , and Yb_2O_3 , and the
clarifying agent is one or more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

15 39. The matrix glass according to claim 35 or 36, wherein the components exclude SrO ;
and/or exclude BaO ; and/or exclude CaO ; and/or exclude ZnO ; and/or exclude PbO ; and/or
exclude As_2O_3 ; and/or exclude TiO_2 ; and/or exclude B_2O_3 ; and/or exclude Ln_2O_3 ; and/or
exclude F; and/or exclude Ta_2O_5 .

20 40. The matrix glass according to claim 35 or 36, wherein a coefficient of thermal
expansion of the microcrystalline glass is $50-70 \times 10^{-7}/\text{K}$; and/or a refractive index is
1.5600-1.5700.

41. The matrix glass according to claim 35 or 36, wherein the matrix glass includes a
colorant.

25 42. The matrix glass according to claim 41, wherein the colorant comprises the
following components in percentage by weight: NiO : 0-4%; and/or Ni_2O_3 : 0-4%; and/or
 CoO : 0-2%; and/or Co_2O_3 : 0-2%; and/or Fe_2O_3 : 0-7%; and/or MnO_2 : 0-4%; and/or Er_2O_3 :

0-8%; and/or Nd_2O_3 : 0-8%; and/or Cu_2O : 0-4%; and/or Pr_2O_3 : 0-8%; and/or CeO_2 : 0-4%.

43. A glass cover plate, comprising the microcrystalline glass product according to any one of claims 1 to 17, and/or the microcrystalline glass according to any one of claims 18 to 34, and/or the matrix glass according to any one of claims 35 to 42.

5 44. A glass component, comprising the microcrystalline glass product according to any one of claims 1 to 17, and/or the microcrystalline glass according to any one of claims 18 to 34, and/or the matrix glass according to any one of claims 35 to 42.

45. A display device, comprising the microcrystalline glass product according to any one of claims 1 to 17, and/or the microcrystalline glass according to any one of claims 18 to 34, and/or the matrix glass according to any one of claims 35 to 42, and/or the glass cover plate according to claim 43, and/or the glass component according to claim 44.

10

46. An electronic device, comprising the microcrystalline glass product according to any one of claims 1 to 17, and/or the microcrystalline glass according to any one of claims 18 to 34, and/or the matrix glass according to any one of claims 35 to 42, and/or the glass cover plate according to claim 43, and/or the glass component according to claim 44.

15

47. A method for manufacturing a microcrystalline glass product, the method including the following steps:

forming matrix glass, the matrix glass including the following components in percentage by weight: SiO_2 : 45-70%; Al_2O_3 : 8-18%; Li_2O : 10-25%; ZrO_2 : 5-15%; P_2O_5 : 2-10%; and Y_2O_3 : greater than 0 but less than or equal to 8%; and

20

forming the matrix glass into a microcrystalline glass through a crystallization process, and then forming the microcrystalline glass into a microcrystalline glass product through a chemical strengthening process.

48. The method for manufacturing a microcrystalline glass product according to claim 47, wherein the matrix glass further includes the following components in percentage by

25

weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or TiO₂: 0-5%; and/or BaO: 0-5%; and/or CaO: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

49. The method for manufacturing a microcrystalline glass product according to claim 47 or 48, wherein the components of the matrix glass are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

- 1) Y₂O₃/ZrO₂ is greater than 0, preferably 0.1-1.0, and more preferably 0.2-0.6;
- 2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 2.5-50.0, preferably 3.0-40.0, and more preferably 4.0-21.0;
- 3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.16-0.9, preferably 0.18-0.6, and more preferably 0.19-0.5;
- 4) Na₂O/Y₂O₃ is 6.0 or less, preferably 0.1-5.0, and more preferably 0.3-2.0;
- 5) Y₂O₃/(Al₂O₃+SiO₂) is greater than 0 but less than or equal to 0.15, preferably 0.01-0.12, and more preferably 0.03-0.09.

50. The method for manufacturing a microcrystalline glass product according to claim 47 or 48, wherein the matrix glass includes the following components in percentage by weight: SiO₂: 50-65%, preferably 53-63%; and/or Al₂O₃: 8-15%, preferably 8-12%; and/or Li₂O: 13-22%, preferably 14-21%; and/or ZrO₂: 6-12%, preferably 7-12%; and/or P₂O₅: 3.5-9%, preferably 4-8%; and/or K₂O: 0-4%, preferably 0-2%; and/or MgO: 0-1%; and/or ZnO: 0-1%; and/or Na₂O: 1-5%, preferably 1.5-4%; and/or Y₂O₃: 1-7%, preferably 2-6%; and/or SrO: 0-3%, preferably 0-1%; and/or BaO: 0-3%, preferably 0-1%; and/or TiO₂: 0-3%, preferably 0-1%; and/or CaO: 0-3%, preferably 0-1%; and/or B₂O₃: 0-3%, preferably 0-2%; and/or Ln₂O₃: 0-4%, preferably 0-3%; and/or a clarifying agent: 0-1%, preferably 0-0.5%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or

more of Sb_2O_3 , SnO_2 , SnO , CeO_2 , F, Cl, and Br.

51. The method for manufacturing a microcrystalline glass product according to claim 47 or 48, wherein the matrix glass excludes SrO ; and/or excludes BaO ; and/or excludes CaO ; and/or excludes ZnO ; and/or excludes PbO ; and/or excludes As_2O_3 ; and/or excludes TiO_2 ; and/or excludes B_2O_3 ; and/or excludes Ln_2O_3 ; and/or excludes F; and/or excludes Ta_2O_5 .

52. The method for manufacturing a microcrystalline glass product according to claim 47 or 48, wherein the matrix glass includes a colorant, and the colorant comprises the following components in percentage by weight: NiO : 0-4%; and/or Ni_2O_3 : 0-4%; and/or CoO : 0-2%; and/or Co_2O_3 : 0-2%; and/or Fe_2O_3 : 0-7%; and/or MnO_2 : 0-4%; and/or Er_2O_3 : 0-8%; and/or Nd_2O_3 : 0-8%; and/or Cu_2O : 0-4%; and/or Pr_2O_3 : 0-8%; and/or CeO_2 : 0-4%.

53. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein the crystallization process comprises the following steps: increasing the temperature to a prescribed crystallization treatment temperature, after reaching the crystallization treatment temperature, maintaining the temperature for a certain period of time, and then cooling down, wherein the crystallization treatment temperature is 600-750°C, and preferably 650°C to 700°C, and the holding time at the crystallization treatment temperature is 0-8 hours, and preferably 1-6 hours.

54. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein the crystallization process comprises the following steps: performing a nucleation process at a first temperature, and then performing a crystal growth process at a second temperature higher than the nucleation process temperature.

55. The method for manufacturing the microcrystalline glass product according to claim 54, wherein crystallization process comprises the following steps: the first temperature is 470-630°C, the second temperature is 650-750°C; the holding time at the first temperature is 0-24 hours, and preferably 2-15 hours; the holding time at the second temperature is 0-10 hours, and preferably 0.5-6 hours.

56. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein the chemical strengthening process comprises: immersing the microcrystalline glass in a salt bath of molten Na salt at a temperature of 430°C to 470°C for 6-20 hours, and a preferred temperature range being 435°C to 460°C, a preferred time range being 8-13 hours; and/or immersing the microcrystalline glass in a salt bath of molten K salt at the temperature of 400°C to 450°C for 1-8 hours, and a preferred time range being 2-4 hours.

57. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein a crystal phase of the microcrystalline glass product comprises lithium monosilicate and/or lithium phosphate.

58. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein a crystal phase of the microcrystalline glass product mainly comprises lithium monosilicate; lithium monosilicate has a higher weight percentage than other crystal phases, and lithium monosilicate accounts for 10-63.5% by weight of the microcrystalline glass product, and preferably 15-55%.

59. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein the microcrystalline glass product comprises a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% by weight of the microcrystalline glass product, and preferably 5-12%.

60. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein a surface stress of the microcrystalline glass product is 600 MPa or more, preferably 650 Mpa or more, and more preferably 700 Mpa or more; and/or a four-point bending strength is 600 Mpa or more, preferably 650 Mpa or more, and more preferably 700 Mpa or more; and/or an ion-exchange layer depth is 20 μm or more, preferably 30 μm or more, and more preferably 40 μm or more; and/or a drop ball test height is 1300 mm or more, preferably 1400 mm or more, and more preferably 1500 mm or more; and/or a fracture toughness is 1 $\text{Mpa}\cdot\text{m}^{1/2}$ or more, preferably 1.1 $\text{Mpa}\cdot\text{m}^{1/2}$ or more, and more preferably 1.2

Mpa·m^{1/2} or more; and/or a Vickers hardness is 700 kgf/mm² or more, preferably 720 kgf/mm² or more, and more preferably 730 kgf/mm² or more; and/or a crystallinity is 50% or more, preferably 60% or more, and more preferably 70% or more; and/or a crystal grain size is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less.

5 61. The method for manufacturing the microcrystalline glass product according to claim 47 or 48, wherein a haze of the microcrystalline glass product with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less; and/or an average transmittance of the microcrystalline glass product with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more; and/or a transmittance of the
10 microcrystalline glass product with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more; and/or an average light | B | value of the microcrystalline glass product with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

 62. The method for manufacturing the microcrystalline glass product according to claim
15 47 or 48, wherein the thickness of the microcrystalline glass product is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

 63. A method for manufacturing microcrystalline glass, the method including the following steps:

20 forming matrix glass, the matrix glass including the following components in percentage by weight: SiO₂: 45-70%; Al₂O₃: 8-18%; Li₂O: 10-25%; ZrO₂: 5-15%; P₂O₅: 2-10%; and Y₂O₃: greater than 0 but less than or equal to 8%; and

 forming the matrix glass into microcrystalline glass through a crystallization process.

 64. The method for manufacturing microcrystalline glass according to claim 63, wherein
25 the matrix glass further includes the following components in percentage by weight: K₂O: 0-5%; and/or MgO: 0-2%; and/or ZnO: 0-2%; and/or Na₂O: 0-6%; and/or SrO: 0-5%; and/or

BaO: 0-5%; and/or TiO₂: 0-5%; and/or CaO: 0-5%; and/or B₂O₃: 0-5%; and/or Ln₂O₃: 0-5%; and/or a clarifying agent: 0-2%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃, SnO₂, SnO, CeO₂, F, Cl, and Br.

65. The method for manufacturing microcrystalline glass according to claim 63 or 64,
5 wherein the components of the matrix glass are expressed in percentage by weight, and a content of each component satisfies more than one of the following five situations:

1) Y₂O₃/ZrO₂ is greater than 0, preferably 0.1-1.0, and more preferably 0.2-0.6;

2) (Li₂O+ZrO₂+P₂O₅)/Y₂O₃ is 2.5-50.0, preferably 3.0-40.0, and more preferably
4.0-21.0;

10 3) Al₂O₃/(Li₂O+ZrO₂+P₂O₅) is 0.16-0.9, preferably 0.18-0.6, and more preferably 0.19-0.5;

4) Na₂O/Y₂O₃ is 6.0 or less, preferably 0.1-5.0, and more preferably 0.3-2.0;

5) Y₂O₃/(Al₂O₃+SiO₂) is greater than 0 but less than or equal to 0.15, preferably 0.01-0.12, and more preferably 0.03-0.09.

15 66. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein the matrix glass includes the following components in percentage by weight: SiO₂: 50-65%, preferably 53-63%; and/or Al₂O₃: 8-15%, preferably 8-12%; and/or Li₂O: 13-22%, preferably 14-21%; and/or ZrO₂: 6-12%, preferably 7-12%; and/or P₂O₅: 3.5-9%, preferably 4-8%; and/or K₂O: 0-4%, preferably 0-2%; and/or MgO: 0-1%; and/or ZnO: 0-1%; and/or
20 Na₂O: 1-5%, preferably 1.5-4%; and/or Y₂O₃: 1-7%, preferably 2-6%; and/or SrO: 0-3%, preferably 0-1%; and/or BaO: 0-3%, preferably 0-1%; and/or CaO: 0-3%, preferably 0-1%; and/or TiO₂: 0-3%, preferably 0-1%; and/or B₂O₃: 0-3%, preferably 0-2%; and/or Ln₂O₃: 0-4%, preferably 0-3%; and/or a clarifying agent: 0-1%, preferably 0-0.5%, wherein Ln₂O₃ is one or more of La₂O₃, Gd₂O₃, and Yb₂O₃, and the clarifying agent is one or more of Sb₂O₃,
25 SnO₂, SnO, CeO₂, F, Cl, and Br.

67. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein the matrix glass excludes SrO; and/or excludes BaO; and/or excludes CaO; and/or excludes ZnO; and/or excludes PbO; and/or excludes As₂O₃; and/or excludes TiO₂; and/or excludes B₂O₃; and/or excludes Ln₂O₃; and/or excludes F; and/or excludes Ta₂O₅.

5 68. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein the matrix glass includes a colorant, and the colorant comprises the following components in percentage by weight: NiO: 0-4%; and/or Ni₂O₃: 0-4%; and/or CoO: 0-2%; and/or Co₂O₃: 0-2%; and/or Fe₂O₃: 0-7%; and/or MnO₂: 0-4%; and/or Er₂O₃: 0-8%; and/or Nd₂O₃: 0-8%; and/or Cu₂O: 0-4%; and/or Pr₂O₃: 0-8%; and/or CeO₂: 0-4%.

10 69. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein the crystallization process comprises the following steps: increasing the temperature to a prescribed crystallization treatment temperature, after reaching the crystallization treatment temperature, maintaining the temperature for a certain period of time, and then cooling down, wherein the crystallization treatment temperature is 600-750°C, and preferably
15 650°C to 700°C, and the holding time at the crystallization treatment temperature is 0-8 hours, and preferably 1-6 hours.

70. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein crystallization process comprises the following steps: performing a nucleation process at a first temperature, and then performing a crystal growth process at a second
20 temperature higher than the nucleation process temperature.

71. The method for manufacturing microcrystalline glass according to claim 70, wherein crystallization process comprises the following steps: the first temperature is 470-630°C, the second temperature is 650-750°C; the holding time at the first temperature is 0-24 hours, and preferably 2-15 hours; the holding time at the second temperature is 0-10 hours, and
25 preferably 0.5-6 hours.

72. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein a crystal phase of the microcrystalline glass product comprises lithium monosilicate

and/or lithium phosphate.

73. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein a crystal phase of the microcrystalline glass mainly comprises lithium monosilicate; lithium monosilicate has a higher weight percentage than other crystal phases, and lithium
5 monosilicate accounts for 10-63.5% by weight of the microcrystalline glass, and preferably 15-55%.

74. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein the microcrystalline glass comprises a lithium phosphate crystal phase, and the lithium phosphate crystal phase accounts for 3-15% by weight of the microcrystalline glass,
10 and preferably 5-12%.

75. The method for manufacturing microcrystalline glass according to claim 63 or 64, wherein a crystallinity of the microcrystalline glass is 50% or more, preferably 60% or more, and more preferably 70% or more; and/or a crystal grain size is 50 nm or less, preferably 40 nm or less, and more preferably 30 nm or less; and/or a coefficient of thermal expansion is
15 $75-95 \times 10^{-7}/K$; and/or a refractive index is 1.5700-1.5800; and/or a drop ball test height is 1000 mm or more, preferably 1100 mm or more, and more preferably 1200 mm or more; and/or a Vickers hardness is 650 kgf/mm² or more, preferably 680 kgf/mm² or more, and more preferably 700 kgf/mm² or more.

76. The method for manufacturing microcrystalline glass according to claim 63 or 64,,
20 wherein a haze of the microcrystalline glass with a thickness of 1 mm or less is 0.15% or less, preferably 0.12% or less, and more preferably 0.1% or less; and/or an average transmittance of the microcrystalline glass with the thickness of 1 mm or less at a wavelength of 400-800 nm is 89% or more; and/or a transmittance of the microcrystalline glass with the thickness of 1 mm or less at the wavelength of 550 nm is 91% or more; and/or an average light | B |
25 value of the microcrystalline glass with the thickness of 1 mm or less at 400-800 nm is 0.6 or less, preferably 0.55 or less, and more preferably 0.5 or less.

77. The method for manufacturing microcrystalline glass according to claim 76, wherein

the thickness of the microcrystalline glass is 0.2-1 mm, preferably 0.3-0.9 mm, more preferably 0.5-0.8 mm, and further preferably 0.55 mm or 0.6 mm or 0.68 mm or 0.72 mm or 0.75 mm.

5

10

15

20

25

30

35

40