

ANIONIC VINYL/DICARBOXYLIC ACID POLYMERS AND USES THEREOF

5

RELATED APPLICATION

This is a continuation-in-part of application Serial No. 09/562,519 filed May 1, 2000.

BACKGROUND OF THE INVENTION

Field of the Invention

10 The present invention is broadly concerned with novel anionic substantially biodegradable and substantially water soluble polymers and derivatives thereof which have significant utility in agricultural applications, especially plant nutrition and related areas. More particularly, the invention is concerned with such polymers, as well as methods of synthesis and use thereof, wherein the preferred polymers have significant levels of anionic groups.

15 Additionally, the preferred polymers also include significant levels of alcohol groups. The most preferred polymers of the instant invention include recurring polymeric subunits made up of vinylic (e.g., vinyl acetate or vinyl alcohol) and dicarboxylic (e.g., maleic acid, itaconic acid, anhydrides, and other derivatives thereof) moieties. The polymers may be complexed onto ions and/or mixed with or coated with phosphate-based fertilizers to provide improved plant nutrition

20 products.

Description of the Prior Art

 Lignosulfonates, polyacrylates, polyaspartates and related compounds have become known to the art of agriculture as materials that facilitate nutrient absorption. All of them suffer

25 from significant disadvantages, which decrease their utility in comparison to the art discussed herein and limit performance.

 Lignosulfonates are a byproduct of paper pulping; they are derived from highly variable sources. They are subject to large, unpredictable variations in color, physical properties, and performance in application areas of interest for this invention.

30 Polyacrylates and polymers containing appreciable levels thereof can be prepared with good control over their composition and performance. They are stable to pH variations.

-2-

However, polyacrylates have just one carboxylate per repeat unit and they suffer from a very significant limitation in use, namely that they are not biodegradable. As a result, their utility for addressing the problems remedied by the instant invention is low.

5 Polyaspartates are biodegradable, but are very expensive, and are not stable outside a relatively small pH range of about 7 to about 10. They usually have very high color, and incorporate amide groups, which causes difficulties in formulating them. Additionally, polyaspartates have just one carboxylate per repeat unit and are therefore not a part of the present invention.

10 *Russian Journal of Applied Chemistry*, 24(5):485-489 (1951) teaches the preparation of maleic anhydride-vinyl acetate copolymers in benzene and acetone with benzoyl peroxide initiators. It further discloses the addition of above copolymers to water, wherein the polymer gradually self-hydrolyzes to a complex mixture containing units of maleic acid, vinyl alcohol, vinyl acetate, lactones, free acetic acid, and other species. Deficiencies of this teaching include undesirable presence of lactone, which decreases number of dicarboxylic groups. In addition,
15 no use for polymers is taught or suggested.

U.S. Patents Nos. 3,268,491 and 3,887,480 teach preparation of maleic acid-vinyl acetate copolymers in water-based solutions using redox-based initiators in a certain pH range. The approaches described in these patents are highly problematic. Only redox-type initiators are claimed to be useful. A fixed pH range restricts the practice. Only a narrow range of copolymers
20 composed exclusively from the monomers of maleic acid and vinyl acetate are taught. The process of U.S. Patent No. 3,268,491 is deemed to be non-commercial by U.S. Patent No. 3,887,480 which described improved processes but uses over 17% by weight of redox initiator; such processes are very wasteful, have high environmental impact, and are not cost effective.

U.S. Patents No. 5,191,048 and 5,264,510 teach copolymerization of acrylic acid, maleic
25 acid, and vinyl acetate with subsequent hydrolysis by base. Again, several important deficiencies are evident. Among these are the exclusive use of base hydrolysis and preferred embodiments of invention incorporating monocarboxylic acids. Only terpolymers are disclosed. Furthermore, the intended uses of the compositions are very restricted and in no way teach, suggest or imply utility of the enumerated and contemplated compositions for the purposes of the present
30 invention.

-3-

It will thus be seen that the prior art fails to disclose or provide polymers which can be synthesized using a variety of monomers and techniques in order to yield end products which are substantially biodegradable, substantially water soluble, and have wide applicability for agricultural uses.


5

SUMMARY OF THE INVENTION

The present invention overcomes the problems outlined above and provides a new class of anionic polymers having a variety of uses, e.g., for enhancing takeup of nutrient by plants or for mixture with conventional phosphate-based fertilizers to provide an improved fertilizer product. Advantageously, the polymers are biodegradable, in that they degrade to environmentally innocuous compounds within a relatively short time (up to about 1 year) after being in intimate contact with soil. That is to say that the degradation products are compounds such as CO₂ and H₂O or the degradation products are absorbed as food or nutrients by soil microorganisms and plants. Similarly, derivatives of the polymers and/or salts of the polymers (e.g. ammonium salt forms of the polymer) also degrade within a relatively short time, during which significant fractions of the weight of the polymer are believed to be metabolized by soil organisms.

Broadly speaking, the anionic polymers of the invention include recurring polymeric subunits made up of at least two different moieties individually and respectively taken from the group consisting of what have been denominated for ease of reference as A, B and C moieties. Thus, exemplary polymeric subunits may be AB, BA, AC, CA, ABC, BAC, CAB, or any other combination of A moieties with B and C moieties. Moreover, in a given polymer different polymeric subunits may include different types or forms of moieties, e.g., in an AB recurring polymeric unit polymer, the B moiety may be different in different units.


In detail, moiety A is of the general formula




30

4.


moiety B is of the general formula



or




and moiety C is of the general formula




-5-

or



or




wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups (formate (C_0), acetate (C_1), propionate (C_2), butyrate (C_3), etc. up to C_{30}), $R'\text{CO}_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, V, Cr, Si, B, Co, Mo, and Ca; R_8 and R_9 are individually and respectively selected from the group

-6-

consisting of nothing (i.e., the groups are non-existent), CH_2 , C_2H_4 , and C_3H_6 , at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.

As can be appreciated, the polymers of the invention can have different sequences of recurring polymeric subunits as defined above (for example, a polymer comprising A, B and C subunits may include the one form of A moiety, all three forms of B moiety and all three forms of C moiety). In the case of the polymer made up of A and B moieties, R_1 - R_4 are respectively and individually selected from the group consisting of H, OH and C_1 - C_4 straight and branched chain alkyl groups, R_5 and R_6 are individually and respectively selected from the group consisting of the alkali metals.

The most preferred polymers of the invention are made up of recurring polymeric subunits formed of A and B moieties, wherein R_5 and R_6 are individually and respectively selected from the group consisting of H, Na, K, and NH_4 and specifically wherein R_1 , R_3 and R_4 are each H, R_2 is OH, and R_5 and R_6 are individually and respectively selected from the group consisting of H, Na, K, and NH_4 , depending upon the specific application desired for the polymer. These preferred polymers have the generalized formula



wherein R_5 and R_6 are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and C_1 - C_4 alkyl ammonium groups (and most preferably, H, Na, K and NH_4 depending upon the application), and n ranges from about 1-10000 and more preferably from about 1-5000.

For purposes of the present invention, it is preferred to use dicarboxylic acids, precursors and derivatives thereof for the practice of the invention. For example, terpolymers containing mono and dicarboxylic acids with vinyl esters and vinyl alcohol are contemplated, however,

-7-

polymers incorporating dicarboxylic acids were unexpectedly found to be significantly more useful for the purposes of this invention. This finding was in contrast to the conventional teachings that mixtures of mono and dicarboxylates were superior in applications previously suggested for mono-carboxylate polymers. Thus, the use of dicarboxylic acid derived polymers
5 for agricultural applications is unprecedented and produced unexpected results. It is understood that when dicarboxylic acids are mentioned herein, various precursors and derivatives of such are contemplated and well within the scope of the present invention. Put another way, copolymers of the present invention are made up of monomers bearing at least two carboxylic groups or precursors and/or derivatives thereof. The polymers of the invention may have a wide
10 variety of molecular weights, ranging for example from 500-5,000,000, more preferably from about 1,500-20,000, depending chiefly upon the desired end use.

In many applications, and especially for agricultural uses, the polymers of the invention may be mixed with or complexed with a metal or non-metal ion, and especially ions selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca.
15 Alternatively, polymers containing, mixed with or complexed with such elements may be formulated using a wide variety of methods that are well known in the art of fertilizer formation. Examples of such alternative methods include, forming an aqueous solution containing molybdate and the sodium salt of polymers in accordance with the invention, forming an aqueous solution which contains a zinc complex of polymers in accordance with the present invention and
20 sodium molybdate, and combinations of such methods. In these examples, the presence of the polymer in soil adjacent growing plants would be expected to enhance the availability of these elements to these growing plants. In the case of Si and B, the element would merely be mixed with the polymer rather than having a coordinate metal complex formation. However, in these cases, the availability of these ions would be increased for uptake by growing plants and will be
25 termed "complexed" for purposes of this application.

The polymers hereof (with or without complexed ions) may be used directly as plant growth enhancers. For example, such polymers may be dispersed in a liquid aqueous medium and applied foliarly to plant leaves or applied to the earth adjacent growing plants. It has been found that the polymers increase the plant's uptake of both polymer-borne metal nutrients and
30 ambient non-polymer nutrients found in adjacent soil. In such uses, plant growth-enhancing amounts of compositions comprising the above-defined polymers are employed, either in liquid

-8-

dispersions or in dried, granular form. Thus, application of polymer alone results in improved plant growth characteristics, presumably by increasing the availability of naturally occurring ambient nutrients. Typically, the polymers are applied at a level of from about 0.001 to about 100 lbs. polymer per acre of growing plants, and more preferably from about 0.005 to about 50
5 lbs. polymer per acre, and still more preferably from about 0.01 to about 2 lbs.

In other preferred uses, the polymers may be used to form composite products where the polymers are in intimate contact with fertilizer products including but not limited to phosphate-based fertilizers such as monoammonium phosphate (MAP), diammonium phosphate (DAP), any one of a number of well known N-P-K fertilizer products, and/or fertilizers containing nitrogen
10 materials such as ammonia (anhydrous or aqueous), ammonium nitrate, ammonium sulfate, urea, ammonium phosphates, sodium nitrate, calcium nitrate, potassium nitrate, nitrate of soda, urea formaldehyde, metal (e.g. zinc, iron) ammonium phosphates; phosphorous materials such as calcium phosphates (normal phosphate and super phosphate), ammonium phosphate, ammoniated super phosphate, phosphoric acid, superphosphoric acid, basic slag, rock phosphate,
15 colloidal phosphate, bone phosphate; potassium materials such as potassium chloride, potassium sulfate, potassium nitrate, potassium phosphate, potassium hydroxide, potassium carbonate; calcium materials, such as calcium sulfate, calcium carbonate, calcium nitrate; magnesium materials, such as magnesium carbonate, magnesium oxide, magnesium sulfate, magnesium hydroxide; sulfur materials such as ammonium sulfate, sulfates of other fertilizers discussed
20 herein, ammonium thiosulfate, elemental sulfur (either alone or included with or coated on other fertilizers); micronutrients such as Zn, Mn, Cu, Fe, and other micronutrients discussed herein; oxides, sulfates, chlorides, and chelates of such micronutrients (e.g., zinc oxide, zinc sulfate and zinc chloride); such chelates sequestered onto other carriers such as EDTA; boron materials such as boric acid, sodium borate or calcium borate; and molybdenum materials such as sodium
25 molybdate. As known in the art, these fertilizer products can exist as dry powders/granules or as water solutions. It has also been discovered that the polymers of the invention, when used as a coating on solid fertilizer products such as those mentioned herein, significantly increases the abrasion resistance of the fertilizer. In such uses, the polymers are typically applied at a level of from about 0.005-15% by weight, and more preferably from about 0.25-3% by weight, based
30 upon the weight of the fertilizer taken as 100%.

In such contexts, the polymers may be co-ground with the fertilizer products, applied as a surface coating to the fertilizer products, or otherwise thoroughly mixed with the fertilizer products. Preferably, in such combined fertilizer/polymer compositions, the fertilizer is in the form of particles having an average diameter of from about powder size (less than 0.001 cm) to about 10 cm, more preferably from about 0.1 cm to about 2 cm, and still more preferably from about 0.15 cm to about 0.3 cm. The polymer is present in such combined products at a level of from about 0.001 g to about 20 g polymer per 100 g phosphate-based fertilizer, more preferably from about 0.1 g to about 10 g polymer per 100 g phosphate-based fertilizer, and still more preferably from about 0.5 g to about 2 g polymer per 100 g phosphate-based fertilizer. Again, the polymeric fraction of such combined products may include the polymers defined above, or such polymers complexed with the aforementioned ions. In the case of the combined fertilizer/polymer products, the combined product is applied at a level so that the polymer fraction is applied at a level of from about 0.001 to about 20 lbs. polymer per acre of growing plants, more preferably from about 0.01 to about 10 lbs polymer per acre of growing plants, and still more preferably from about 0.5 to about 2 lbs polymer per acre of growing plants. The combined products can likewise be applied as liquid dispersions or as dry granulated products, at the discretion of the user. When polymers in accordance with the present invention are used as a coating, the polymer comprises at least about 0.01% by weight of the coated fertilizer product, more preferably the polymer comprises at least about 5% by weight of the coated fertilizer product, and most preferably comprises at least about 10% by weight of the coated fertilizer product.

Additionally, use of polymers in accordance with the present invention increases the availability of phosphorus and other common fertilizer ingredients and decreases nitrogen volatilization, thereby rendering ambient levels of such plant nutrient available for uptake by growing plants. In such cases, the polymer can be applied as a coating to fertilizer products prior to their introduction into the soil. In turn, plants grown in soil containing such polymers exhibit enhanced growth characteristics.

Another alternative use of polymers in accordance with the present invention includes using the polymer as a seed coating. In such cases, the polymer comprises at least about 0.01% by weight of the coated seed, and more preferably comprises at least about 5% by weight of the coated seed, and still more preferably comprises at least about 10% by weight of the coated seed.

-10-

In general, the polymers of the invention are made by free radical polymerization serving to convert selected monomers into the desired polymers with recurring polymeric subunits. Such polymers may be further modified to impart particular structures and/or properties. A variety of techniques can be used for generating free radicals, such as addition of peroxides, hydroperoxides, azo initiators, percarbonate, per-acid, charge transfer complexes, irradiation (e.g., UV, electron beam, X-ray, gamma-radiation and other ionizing radiation types), and combinations of these techniques. Of course, an extensive variety of methods and techniques are well known in the art of polymer chemistry for initiating free-radical polymerizations. Those enumerated herein are but some of the more frequently used methods and techniques. Any suitable technique for performing free-radical polymerization is likely to be useful for the purposes of practicing the present invention

The polymerization reactions are carried out in a compatible solvent system, namely a system which does not unduly interfere with the desired polymerization, using essentially any desired monomer concentrations. A number of suitable aqueous or non-aqueous solvent systems can be employed, such as ketones, alcohols, esters, ethers, aromatic solvents, water and mixtures thereof. Water alone and the lower (C_1 - C_4) ketones and alcohols are especially preferred, and these may be mixed with water if desired. In most instances, the polymerization reactions are carried out with the substantial exclusion of oxygen, and most usually under an inert gas such as nitrogen or argon. There is no particular criticality in the type of equipment used in the synthesis of the polymers, i.e., stirred tank reactors, continuous stirred tank reactors, plug flow reactors, tube reactors and any combination of the foregoing arranged in series may be employed. A wide range of suitable reaction arrangements are well known to the art of polymerization.

In general, the initial polymerization step is carried out at a temperature of from about 0°C to about 120°C (more preferably from about 30°C to about 95°C for a period of from about 0.25 hours to about 24 hours and even more preferably from about 0.25 hours to about 5 hours. Usually, the reaction is carried out with continuous stirring.

After the initial polymerization, the products are recovered and hydrolyzed so as to replace at least certain of the ester-containing groups on the polymer with alcohol groups, thereby providing the polymers defined previously. Generally, the hydrolyzing step involves the addition of an acid or base to the polymerized product in the presence of water. Polymers comprising monomers with vinyl ester groups (polymers formed at least in part


-11-

from A moieties) need to have sufficient base added to neutralize all of the carboxylic acid groups and form a substantial number of alcohol groups from the precursor vinyl ester groups. Thereafter, the completed polymer may be recovered as a liquid dispersion or dried to a solid form. It is important to note that both acid and base hydrolysis are useful in practicing the present invention so that under appropriate conditions, sufficient acid must be added in order to form a substantial number of alcohol groups. Additionally, in many cases it is preferred to react the hydrolyzed polymer with an ion such as Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, and Ca to form a coordinate metal complex. Techniques for making metal-containing polymer compounds are well known to those skilled in the art. In some of these techniques, a metal's oxide, hydroxide, carbonate, salt, or other similar compound may be reacted with the polymer in acid form. These techniques also include reacting a finely divided free metal with a solution of an acid form of a polymer described or suggested herein. Additionally, the structures of complexes or salts of polymers with metals in general, and transition metals in particular, can be highly variable and difficult to precisely define. Thus, the depictions used herein are for illustrative purposes only and it is contemplated that desired metals or mixtures of such are bonded to the polymer backbone by chemical bonds. Alternatively, the metal may be bonded to other atoms in addition to those shown. For example, in the case of the structure shown herein for the second reactant, there may be additional atoms or functional groups bonded to the Y. These atoms include, but are not limited to, oxygen, sulfur, halogens, etc. and potential functional groups include (but are not limited to) sulfate, hydroxide, etc. It is understood by those skilled in the art of coordination compound chemistry that a broad range of structures may be formed depending upon the preparation protocol, the identity of the metal, the metal's oxidation state, the starting materials, etc. Alternatively, acid hydrolysis may be performed followed by a reaction to form a complex with a previously enumerated metal. In yet another alternative method, the polymer may be isolated and subsequently formulated in such a way that the hydrolysis reaction occurs *in situ*, in the soil or during mixture with a fertilizing composition. In this alternative method, unhydrolyzed polymer is added to soil or fertilizer compositions of appropriately low or high pH such that when contacted by water, a microenvironment of low or high pH is produced. It is within this microenvironment that hydrolysis occurs and alcohol groups are formed. In the case of Si and B ions, the polymer


-12-

is merely mixed with these ions and does not form a coordinate complex. However, the availability of these ions to growing plants is increased.


In more detail, the preferred method for polymer synthesis comprises the steps of providing a reaction mixture comprising at least two different reactants selected from the group consisting of first, second, and third reactants. The first reactant is of the general formula




the second reactant is of the general formula



or




or




-13-

and the third reactant is of the general formula




10

or



20

or



30

With reference to the above formulae, R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl

-14-

or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups (formate (C_0), acetate (C_1), propionate (C_2), butyrate (C_3), etc. up to C_{30}), $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively
5 selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing (i.e., the
10 groups are non-existent), CH_2 , C_2H_4 , and C_3H_6 , at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.

15 Selected monomers and reactants are dispersed in a suitable solvent system and placed in a reactor. The polymerization reaction is then carried out to obtain an initial polymerized product having the described recurring polymeric subunits. Thereupon, the initial polymer product is hydrolyzed to the alcohol form. Put another way, the general reaction proceeds by dissolving monomers (e.g., maleic anhydride and vinyl acetate) in a
20 solvent (e.g., acetone). The amount of monomers incorporated can be either equimolar or non-equimolar. A free radical initiator is then introduced and copolymerization takes place in solution. After the reaction is complete and substantially all monomer has been reacted, the resulting solution is a maleic anhydride-vinyl acetate copolymer. Of course, if all monomers have not undergone polymerization, the resulting solution will contain a small
25 portion of monomers which do not affect later use of the polymer. The solution is concentrated and subjected to hydrolysis (either *in situ* or by performing a hydrolysis reaction during manufacture) with a sufficient amount of base (e.g., NaOH) in the presence of water. This base neutralizes a substantial majority of the carboxylic acid groups and converts a substantial majority of the polymer's acetate groups into alcohol groups. The
30 anhydride groups are converted to carboxylic acid sodium salt groups arranged in groups of

-15-

two on the backbone of the polymer. The resulting copolymer is then isolated by conventional methods such as precipitation.

Again, it is important to note that the aforementioned methods and procedures are merely preferred methods of practicing the present invention and those skilled in the art understand that a large number of variations and broadly analogous procedures can be carried out using the teachings contained herein. For example, acid hydrolysis can also be used followed optionally by formation of various derivatives or the hydrolysis may be carried out naturally in soil under sufficient moisture and pH conditions. The acid hydrolysis isolates the polymers of the present invention in a substantially acid form which renders them highly versatile and useful. These polymers may be used as is (in the acid form) or further reacted with various materials to make salts and/or complexes. Furthermore, complexes or salts with various metals may be formed by reacting the acid form with various oxides, hydroxides, carbonates, and free metals under suitable conditions. Such reactions are well known in the art and include (but are not limited to) various techniques of reagent mixing, monomer and/or solvent feed, etc. One possible technique would be gradual or stepwise addition of an initiator to a reaction in progress. Other potential techniques include the addition of chain transfer agents, free radical initiator activators, molecular weight moderators/control agents, use of multiple initiators, initiator quenchers, inhibitors, etc. Of course, this list is not comprehensive but merely serves to demonstrate that there are a wide variety of techniques available to those skilled in the art and that all such techniques are embraced by the present invention.

Another alternative method involves taking an aqueous solution of, for example, caustic and stirring it in a suitable container. Next, an acetone reaction mixture containing, for example, acetone and a copolymer of maleic anhydride with vinyl acetate is added to the caustic solution. Throughout this addition, the polymer going into the caustic solution will experience a high pH and have the acetate groups hydrolyzed to the alcohol form. In acid-base titrations such as this, at the point where one reagent is just exhausted, a very sharp pH change usually takes place with minimal addition of the second reagent. Therefore, in this reaction, just enough acetone-polymer reaction solution is added to bring the apparent pH of the now final polymer product-acetone-water mixture to about 7. At this time, the mixture is subjected to reduced pressure distillation to remove acetone. The result is an

-16-

aqueous solution at a neutral pH that contains the desired polymer. From this solution, it may be isolated by a variety of ways, including but not limited to precipitation, spray drying, simple drying, and etc. The only side effect of a reaction of this type is that a small fraction of the polymer is going to contain acetate groups which are not hydrolyzed to alcohol.

5 The foregoing description is useful in instances where polymers in accordance with the present invention, upon dissolution in water, give a solution that is alkaline. In many cases, this alkalinity is not a problem as the solution pH can be adjusted to neutral or acidic with a suitable mineral or organic acid. However, the formulation of this powder into some liquid formulations containing metals is problematic. High-pH solutions of metal salts tend
10 to form insoluble metal hydroxides that precipitate and/or exhibit other behaviors that are undesirable from the point of view of formulation ease and convenience, as well as nutrient availability. One way to remedy this problem, other than as described in the preceding paragraph, is to add a mineral or organic acid to the aqueous solution of polymer salt in order to bring the pH close to neutral.

15

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The following examples set forth techniques for the synthesis of polymers in accordance with the invention, and various uses thereof. It is to be understood that these examples are provided by way of illustration only and nothing therein should be taken as a
20 limitation upon the overall scope of the invention.


EXAMPLE 1

Acetone (111ml), maleic anhydride (20g), vinyl acetate monomer (19ml), and the radical source initiator di-tertbutyl peroxide (2.4ml) were stirred together under inert gas
25 (such as nitrogen or argon) in a reactor. The reactor provided included a suitably sized glass spherical flask equipped with a magnetic stirrer, an inert gas inlet, a contents temperature measurement device in contact with the contents of the flask, and a removable reflux condenser. This combination of materials was heated in a hot water bath with stirring at an internal temperature of about 70°C for five hours. At that point, the contents of the flask
30 were evaporated (by removing the condenser with continued heating) to a thick oil, and 100ml of water was added. Then, 18g of granular sodium hydroxide (NaOH) was added to


-17-

the above dispersion. The resulting mixture was heated again to about 100°C and allowed to reflux for about two hours. The mixture was then allowed to evaporate by removal of the condenser to a slightly viscous mass. This mass was precipitated by adding the evaporated mixture to about 0.5 liters of ethanol while stirring was continued. The solids were recovered and then dried. The resulting product was a white-colored powder. These reactions proceeded as follows:

-18-



+




5



Radical Source Initiator
(di-tertbutyl peroxide)
70-80° C

10




15



NaOH
H₂O

20



25

EXAMPLE 2

This reaction was carried out similarly to that of Example 1. However, in this case the following quantities of ingredients were used: acetone (50ml), maleic anhydride (44g), vinyl acetate monomer (42ml), and di-tertbutyl peroxide (8.3ml). This mixture was heated in a hot water bath with stirring at an internal temperature of about 70°C for five hours. The contents of the reactor flask were then evaporated to a thick oil and 100ml of water was added. Next, 57g granular NaOH was added. This mixture was heated again to about

-19-

100°C and allowed to reflux for about one hour. After refluxing, the mixture evaporated to a slightly viscous mass. This mass was precipitated by adding it, with stirring to 0.9 liters of ethanol. The solids were then recovered and dried. The resulting product was a tan-colored powder.

5

EXAMPLE 3

This reaction was also carried out as in Example 1. However, the following quantities of ingredients were used: acetone (273.0ml), maleic anhydride (49g), vinyl acetate monomer (46ml), and di-tertbutyl peroxide (5.9ml). This mixture was heated in a hot water bath with stirring at an internal temperature of about 70°C for five hours. The contents of the flask were then evaporated into a thick oil (once again by removing the condenser), and 250ml of water was added. Following the water addition, 63g of granular NaOH was added. The resulting mixture was heated to about 100°C again, and allowed to reflux for about one hour. This mixture was then evaporated to a slightly viscous mass. The mass was precipitated with stirring into about 2 liters of ethanol. Solids were recovered and dried and the product was a very bright white powder.

10

15

EXAMPLE 4

In this example, copper was complexed with the polymer isolated in Example 1. Five grams of the Example 1 polymer was mixed with 50g (dry weight) of ion exchange resin (strong acid macro reticular, 4.9 meq/gram dry) which had been soaked in water until the mixture was fluid. The acid form of the polymer was then washed out with several aliquots of water. The resultant water-polymer mixture was then mixed with 6g of CuSO₄ pentahydrate. The aqueous solution containing the copper complex was then evaporated to dryness and the material was collected.

20

25

EXAMPLE 5

One gram of the polymer prepared and isolated in Example 1 was dissolved into 20ml of room temperature water. 1.3g sodium bisulfate was added to this dispersion with stirring. While stirring was continued, 0.5g of ferric sulfate (Fe₂(SO₄)₃) tetrahydrate was added slowly with stirring. This product was isolated by evaporating the water from the

30

-20-

solution to dryness. Thereafter, the isolated dry material was collected. The resultant product was an iron complex of the polymer of Example 1.

EXAMPLE 6

5 In this example, 1g of the polymer prepared and isolated in Example 1 was added to 20ml of room temperature water. Sulfuric acid (98%) was added to the dispersion with stirring, until the pH dropped to about 2. 1.5g of manganese dichloride tetrahydrate was added slowly to the dispersion with vigorous stirring. The material (a manganese complex of the Example 1 polymer) was then evaporated to dryness and the material was collected.

10

EXAMPLE 7

 Five grams of the polymer prepared and isolated in Example 1 was dissolved in 100ml of water. Sulfuric acid (98%) was added until the pH dropped to about 2. 7g of zinc sulfate heptahydrate was added slowly with vigorous stirring to the dispersion. The
15 resulting solution had the product (a zinc complex of the Example 1 polymer) isolated by evaporating the water to dryness and was collected thereafter.

EXAMPLE 8

 Water (30g), and maleic anhydride (20g) is put into the reactor with stirring under
20 inert gas, such as nitrogen or argon. During this time, the anhydride is converted to the acid form. Di-tertbutyl peroxide (2.4ml) is added to the flask. The resulting mixture is heated and refluxed until the reflux head temperature gradually rises to about 100°C. At this point, vinyl acetate monomer (19ml) is gradually added to the reaction at about the same rate that it is consumed. The reaction is carried out until substantially all monomer is consumed.
25 The product of this synthesis is then hydrolyzed as in Example 1. This example demonstrates that the preferred polymerization may be carried out in an aqueous medium.

EXAMPLE 9

 The product of the reaction described in Example 8 is refluxed overnight at about
30 100°C and then subjected to a short-path distillation under inert atmosphere in order to remove the acetic acid hydrolysis product. Due to the high temperature and high product

-21-

concentration, lactone formation is minimized, and the fraction of dicarboxylic acid functional groups that are available is maximized. The desired product is isolated by spray-drying the aqueous solution to give a white amorphous powder.

5

EXAMPLE 10

This example is similar to that described in Example 8; however, water is replaced with a 1:1 (w/w) mixture of water and ethanol. 20g of maleic anhydride is added to this mixture. Next, di-tertbutyl peroxide (2.4ml) is added to the reactor and the resulting mixture is heated to reflux until the reflux head temperature rises to about 100°C. Vinyl acetate monomer is then gradually added to the reaction at about the same rate it is consumed. Once again, 19ml of vinyl acetate monomer is used. The reaction is carried out until substantially all of the monomer is consumed. The resulting product is then refluxed overnight and subjected to a short-path distillation under inert atmosphere in order to remove the acetic acid hydrolysis product. Once again, due to the high temperature and high product concentration, lactone formation is minimized and the fraction of dicarboxylic acid functional groups is maximized. The desired product is then isolated by spray-drying the aqueous solution to give a white amorphous powder.

10

15

EXAMPLE 11

This Example demonstrates that the polymerization may be carried out using UV free radical initiation instead of peroxide. Water (30g) and maleic anhydride (20g) is mixed in the reactor under inert gas. A 10 watt lamp emitting UV radiation at the 190-210 nm wavelength range is immersed in the reaction vessel. The mixture is heated to reflux until the reflux head temperature gradually rises to about 100°C, at which point 19ml of vinyl acetate monomer is gradually added to the reaction at about the same rate as it is consumed. The reaction is carried out until substantially all of the monomer is consumed. Once synthesis (copolymerization) is substantially complete, the resultant product is hydrolyzed as in Example 1.

20

25

30

-22-

EXAMPLE 12

In this example, polymerization is carried out using UV free radical initiation in a mixture of organic solvent and water. The experiment is carried out as in Example 11, but water is replaced with a 1:1 (w/w) mixture of water and ethanol. The isolation and hydrolysis procedures are substantially the same as those used in Examples 8 and 9.

EXAMPLE 13

In this example, the procedure of Example 8 is carried out except that 1ml of hydrogen peroxide (30% w/w) is used instead of di-tertbutyl peroxide.


EXAMPLE 14

This example demonstrates acid hydrolysis in an aqueous medium. To the product of the reaction described in Example 8, 0.2g 98% of sulfuric acid is added and the mixture is refluxed overnight at about 100°C. Next, the mixture is subjected to a short-path distillation under inert gas to remove the acetic acid hydrolysis product. Due to the acidity, high temperature and high product concentration, lactone formation is minimized, and the fraction of dicarboxylic acid functional groups is maximized. The product is isolated by spray drying the aqueous solution to give a white amorphous powder.


EXAMPLE 15

An aqueous solution composed of 40g water, 11.6g maleic acid and 8.1g zinc oxide is formed. The oxide slowly reacts and dissolves to give zinc maleate derivative solution. This is used as a monomer source in a polymerization such as that described in Example 8 where equimolar amounts of maleate and vinyl acetate were used. After that, a hydrolysis is performed using the procedures described in Example 14. The reaction proceeded as follows:


-23-



Radical Source Initiator
(di-tertbutyl peroxide)
70-80° C



H₂SO₄
H₂O




30

-24-

EXAMPLE 16


An aqueous solution composed of 40g water, 11.6g maleic acid, and 11.5g manganese carbonate is prepared. The carbonate slowly reacts and dissolves to give manganese maleate derivative solution. This manganese maleate solution is used as a monomer source in a polymerization such as that described in Example 8, wherein
5 equimolar amounts of maleate and vinyl acetate were used. After that, a hydrolysis is performed using the procedures described in Example 14. The reaction proceeded as follows:



-25-

EXAMPLE 17

An aqueous solution composed of 40g water, 11.g maleic acid, and 5.6g very fine iron dust is formed. The metal slowly reacts and dissolves to give iron maleate derivative solution. This solution is used as a monomer source in a polymerization reaction such as that described in Example 8, wherein equimolar amounts of maleate and vinyl acetate were used. After that, a hydrolysis is performed using the procedures described in Example 14. This reaction proceeded as follows:



-26-

EXAMPLE 18

A continuous reactor is provided including an in-line motionless tube mixer, pumps, thermostatted tubes, and associated valves, fittings, and controls. Maleic anhydride (50% w/w in acetone), vinyl acetate and di-tertbutyl peroxide are pumped into the in-line tube mixer and then into the thermostatted tube. The mixture's residence time in the tube is about 3 hours. The tube temperature is about 70°C. The flow rates are: maleic anhydride solution - 100g/min; vinyl acetate - 43g/min; and di-tertbutyl peroxide - 3g/min. Hydrolysis is performed using the procedures described in Example 14.

EXAMPLE 19

Aqueous dispersions containing 10, 50 and 100 ppm of the copper, manganese and zinc copolymers formed in Examples 4, 6 and 7 were applied to the foliage of plum, maple and sweetgum trees, respectively, in order to obtain substantially uniform foliage coverage. Prior to this application, the trees visually exhibited characteristic deficiency symptoms for each of the three micronutrients. This treatment alleviated the visual symptoms of the micronutrient deficiency in about 7-10 days.

EXAMPLE 20

Bluegrass was treated with aqueous dispersions of the iron copolymer from Example 5 (20, 50 and 100 ppm concentrations of iron copolymer) and compared to an untreated control which received no iron copolymer. These foliar iron treatments were applied at three different times as pretreatments before bluegrass was harvested. Photos of the plants were taken two weeks after the last treatment. The results (Table 1) clearly show that the bluegrass responded to the iron copolymer application. The total harvest weights for each of the three iron copolymer bluegrass test groups were at least twice that of the control bluegrass. As the amount of copolymer applied increased, harvest weight also increased.

-27-

TABLE 1

Bluegrass Response to Varying Concentrations of Fe Copolymer

Harvest	Harvest Wts (g)			
	Fe Copolymer Concentration Applied			
	0 ppm	25 ppm	50 ppm	100 ppm
1	0.3	1.6	1.8	2.1
2	1.8	2.9	2.1	2.0
3	1.4	2.5	3.6	3.9
Total	3.5	7.0	7.5	8.0

EXAMPLE 21

In this example, the effect of iron copolymer treatment on *Lisintus* was determined. The iron copolymer of Example 5 was used for this experiment. The first control group of plants received no iron copolymer treatment, the second group was foliarly treated with an aqueous dispersion containing 50 ppm of the iron copolymer on three different occasions before harvest, and the third group was similarly treated with an aqueous dispersion containing 100 ppm iron copolymer three times before harvest. The *Lisintus* was harvested and analyzed (by digestion followed by atomic absorption spectroscopy) for iron concentration, and by SPAD meter to determine photosynthetically active chlorophyll levels. The results of this experiment are given in Table 2 which shows that application of iron copolymer resulted in a higher iron concentration in the *Lisintus* leaves. However, the amount of iron copolymer applied to the *Lisintus* did not have an appreciable effect on ultimate iron concentration (i.e. SPAD meter readings between *Lisintus* treated with 50 ppm iron copolymer and 100 ppm iron copolymer did not differ significantly). Therefore, the most efficient treatment may occur at levels below 50 ppm.

-28-

TABLE 2

Iron Concentration and SPAD Meter Readings of Lisintus Leaves
Treated with Foliar Applications of Iron Copolymer

Treatment	Fe Uptake (ppm)	SPAD Meter Readings
Control	146	29.5
50 ppm	276	63.7
100 ppm	309	64.1

EXAMPLE 22

In this experiment, different amounts of the copolymer formed in Example 1 were used in conjunction with phosphate fertilizer in soil, in order to test the effect of using the polymer with the fertilizer. In particular, the test was conducted on ryegrass grown in growth bags. The growth bags contained soil, water and a conventional, commercially available 8-14-9 N PK liquid fertilizer. One growth bag (the control) had no copolymer added. One bag labeled .5X was treated with a fertilizer mixture containing 25 ppm of the copolymer (the copolymer was added to the liquid fertilizer prior to addition thereof to the growth bags). The bag labeled 1X was treated with a liquid fertilizer mixture containing 50 ppm of copolymer. The fertilizer solution in the growth bags were replenished uniformly on an as-needed basis. After the grass was harvested, it was dried and weighed. Results of this experiment are given in Table 3 which shows no response to the .5X copolymer application. The 1X copolymer application resulted in a 25% increase in dry weight.

TABLE 3

Effects of Copolymer with Liquid Fertilizer on Resulting Plant Growth

Treatment	Average Shoot Weight
1X Copolymer and Liquid Fertilizer	33.0
.5X Copolymer and Liquid Fertilizer	25.0
Control - Liquid Fertilizer Only	24.9

-29-

EXAMPLE 23

In this test, the copolymer from Example 1 was tested with phosphate fertilizers in high phosphate-fixing soils in corn growth tests. The test was designed to determine the effect of the copolymer on the plant availability of phosphate based fertilizer in the soil. For this experiment, monoammonium phosphate (MAP) was tested although it is understood that similar results would occur with any phosphate based fertilizer.

Two soils were utilized in the study, an acid soil (pH 4.5-4.7) from Sedgewick County, KS and a calcareous soil (pH 8.0-8.3) from the vicinity of Tribune, KS. The acid soil is high in available P but owing to the high exchangeable Al and Fe content of the soil, P availability is limited. The calcareous soil was lower in available P.

Containers (flats) approximately 75 cm x 40 cm were used for the study. These flats held approximately 8 kg of soil filled to a depth of approximately of 7.5 cm, and allows planting in rows with band placement of the fertilizer material, beside the row or in seed contact if desired. Multiple rows within each container were used as replications. The containers served as individual treatment for each crop and were rotated to eliminate any possible variables of light and/or temperature.

Corn was used as the test crop. The seeds were planted in rows, thinned to a constant population per row. Only a single variety of corn was used for each crop. Corn was taken to approximately the 6-leaf stage before the whole plant was harvested for dry weight and plant composition analysis. In the corn test, four plants per row per replication were used, thinned back from ten plants.

Conventional Cargill MAP fertilizer was used, with the fertilizer being coated with the copolymer product of Example 1 at rates of 1 g copolymer/100 g MAP (P1X) and 2 g copolymer/100 g MAP (P2X). The MAP particles were sized prior to copolymer application to insure that the individual particles were of approximately the same size. In all instances, a single rate of application of 20 ppm phosphorus calculated as P_2O_5 was employed. In addition, a no-phosphorus control was also included in the study for each crop on each soil. Other nutrients were supplied at constant rates.

The fertilizer-copolymer MAP product was applied in a banded fashion with a constant number of phosphate material particles utilized per row (63 particles per each 10 inch row section). This procedure placed the experimental products close to the rows for

-30-

maximum availability in the phosphate-fixing conditions, and allowed comparison of the effect of the copolymer with each phosphorus fertilizer.

After harvesting, the plants were tested for dry weight, phosphorus concentration and phosphorus uptake. SAS was utilized to analyze variance of the data.

5

TABLE 4

Phosphorus Materials Evaluation - Corn

Material	Dry Wt. (g)	P. Concentration (%)	P Uptake
Control	5.18	0.827	43.2
P1X	8.90	0.996	88.7
P2X	9.55	1.043	99.6
LSD ₀₅	2.47	0.177	31.8

10

15

EXAMPLE 24

In this test, the effects of polymers on nitrogen volatilization was tested. A urea was sized by screening to a uniform size and was treated to form a 5% by weight coating of a polymer in accordance with the present invention. The coating was prepared by solubilizing 5 grams of polymer in 3 ml of water. The mixture was then added uniformly to 95 g of urea. To the mixture, 7 g of clay was added which dried the mixture and provided a clay coating. The mixture was then applied to soil for comparison. There were two polymers tested, one which was 50% calcium and 50% hydrogen saturated and the other which was 100% calcium saturated. Each of these polymer mixtures were compared to an untreated urea. Soil samples were taken and cumulative nitrogen losses were determined after 16 days.

20

25

As shown in Table 5, coating the urea with clay or a polymer and clay combination greatly reduced nitrogen volatilization. Untreated urea lost 37.4% of its total nitrogen. The polymers, calcium/hydrogen mixtures and calcium alone, lost only 20.6% and 19.5% respectively. Unexpectedly, the polymer combination significantly reduced nitrogen volatilization.

30

-31-

TABLE 5

Ammonia Loss as a Percentage of Total Nitrogen Applied

Treatment	Replicate 1	Replicate 2	Replicate 3	Average
Urea	33.3	41.3	37.7	37.4
Urea/Clay/5% Polymer 50% H, 50% Ca saturated	19.0	19.3	23.7	20.6
Urea/Clay/5% Polymer 100% Ca saturated	17.1	21.7	19.5	19.5

EXAMPLE 25

This experiment determined the effects of polymers in accordance with the invention on phosphorus fertilizer availability. An acid soil (pH 4.7) and a calcareous soil (pH 7.8) treated as in Example 23 were collected. These soils were chosen for their P fixing characteristics, preformed by Fe and Al in the acid soil and Ca in the calcareous soil. All treatments involved four replication. Soil samples were collected from the area of banded P beside the corn row after the plants had been harvested. The phosphorus material was MAP (although it is understood that all fertilizers should have similar results) with and without an experimental coating of 1.0% on the exterior of the MAP particles. The coating was prepared using the procedures described above in Example 24. Phosphorus rates were 5, 10 and 20 ppm P205 banded beside the seed (1 inch to the side, 1 inch below) of corn in flats containing 7 kilograms of soil. Composited cores from each treatment were processed and analyzed using conventional testing procedures. A single weak acid extractant (Bray P-1) was utilized for both the acid and calcareous soils. The P fertilizer had been in contact with the soil for approximately 5 weeks at the time of sampling.

Results of this experiment are given below in Table 6. Coating MAP with the experimental product produced consistently higher soil test P values indicating that the extractability of the P was increased. Therefore, normal soil P fixation had not progressed as rapidly in the presence of the polymer. The results from the acid soil displayed more differentiation than those of the calcareous soil, perhaps due to the tendency of the weak Bray

-32-

extractant to react with free calcium carbonate in the calcareous soil. Plant growth data also demonstrated similar indications of greater P availability.

Thus, polymers in accordance with the present invention have significant effects on P availability from ammonium phosphate fertilizers. Furthermore, these polymers may be of substantial value in improving P use efficiency from applied fertilizers on both acid and calcareous soils with P fixation capacities.

TABLE 6
Polymer Effects on Soil Test P

10	Treatment	Soil Bray-1 P Concentrations ppm P
	No P Control, Acid Soil	76
	5 ppm P205, MAP Control, Acid Soil	121
	10 ppm P205, MAP Control, Acid Soil	117
	20 ppm P205, MAP Control, Acid Soil	151
15	5 ppm P205, MAP Experimental, Acid Soil	195
	10 ppm P205, MAP Experimental, Acid Soil	190
	20 ppm P205, MAP Experimental, Acid Soil	220
	LSD 0.10, Acid Soil	26
	No P Control, Calcareous Soil	76
20	5 ppm P205, MAP Control, Calcareous Soil	96
	10 ppm P205, MAP Control, Calcareous Soil	110
	20 ppm P205, MAP Control, Calcareous Soil	156
	5 ppm P205, MAP Experimental, Calcareous Soil	164
	10 ppm P205, MAP Experimental, Calcareous Soil	159
25	20 ppm P205, MAP Experimental, Calcareous Soil	102
	LSD 0.10 Calcareous Soil	38

EXAMPLE 26

In this example, a representative polymer in accordance with the invention was employed as a coating on granular fertilizer, in order to determine the effect of the polymer on increasing the abrasion resistance of the fertilizer. Abrasion resistance is the resistance to the formation of dust and fines as a result of granule-to-granule and granule-to-granule equipment contact. Increasing abrasion resistance reduces material losses from handling, storage and during application, and also decreases pollution and consequent need for pollution control equipment.

In each case, conventional granular MAP fertilizer was used, and tests were run with no coating, a commercially available dust control coating (ARR-MAZ KGA500) and a sodium-saturated polymer in accordance with Example 1 (40% solids). The fertilizer samples were prepared by first screening the fertilizer over 3.35 and 1.00 mm sieves to obtain a 100 cm³ portion. Individual 20 g samples of the screened fertilizer were then coated by mixing the ARR-MAX-KGA500 and polymer of the invention at the levels set forth in Table 7 below. After coating and drying, the samples were placed in respective 100 ml rectangular polyurethane bottles, along with 10 stainless steel 7.9 mm diameter balls. All sample bottles were taped together into one block and shaken for five minutes. At the end of the shaking, the balls were removed manually, and the bottle contents examined. Fines were separated manually and weighed, and the percentage of dust after the shaking test was calculated. Table 7 sets forth the results of this experiment.

Table 7


Fertilizer Type	Coating	Coating Level (% w/w, as is)	% Dust After Shaking
Granular MAP	None	N/A	0.43
Granular MAP	AAR-MAZ-KGA500	0.52	0.29
Granular MAP	Polymer	0.5	None
Granular MAP	Polymer	1.0	None
Granular MAP	Polymer	1.5	None

-34-


These results demonstrated that the polymers of the invention are highly useful as coatings for solid fertilizer products in order to enhance the abrasion resistance of the products.

We claim:


1. A polymer comprising recurring dicarboxylic polymeric subunits each made up of at least two different moieties individually and respectively taken from the group consisting of A, B, and C moieties, or recurring C moieties, wherein moiety A is of the general formula




moiety B is of the general formula




or




or




and moiety C is of the general formula



or



or



wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.

2. The polymer of claim 1, wherein said recurring polymeric subunits are made up of A and B moieties, wherein R_1 , R_3 and R_4 are each H, R_2 is OH, R_5 and R_6 are Na.

3. The polymer of claim 1, wherein R_1 - R_4 are respectively and individually selected from the group consisting of H, OH and C_1 - C_4 straight and branched chain alkyl groups, R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of the alkali metals, NH_4 and H.

4. The polymer of claim 1, said polymer being complexed with an ion.

5. The polymer of claim 4, said ion being selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca.

6. A fertilizer product comprising particles of a fertilizer in intimate contact with a polymer as defined in claim 1.


7. The fertilizer product of claim 6, said fertilizer being selected from the group consisting of phosphate-based fertilizers, fertilizers containing nitrogen, phosphorous, potassium

calcium, magnesium, sulfur, boron, or molybdenum materials, fertilizers containing micronutrients, and oxides, sulfates, chlorides, and chelates of such micronutrients.



8. The fertilizer product of claim 6, said polymer and fertilizer being co-ground together.
9. The fertilizer product of claim 6, said polymer being applied to the surface of said fertilizer.
10. The fertilizer product of claim 6, said fertilizer being in the form of particles having an average diameter from about powder size to about 10 cm.
11. The fertilizer product of claim 6, said polymer being present in said fertilizer product at a level of from about 0.001 g to about 20 g polymer per 100 g fertilizer.
12. The fertilizer product of claim 6, said polymer being complexed with an ion.
13. The fertilizer product of claim 12, said ion being selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca.
14. A method of enhancing the growth of plants comprising the step of applying to said plants or the earth adjacent said plants a growth-enhancing amount of a composition comprising the polymer of claim 1.
15. The method of claim 14, said polymer being applied at a level of from about 0.001 lbs. to about 100 lbs. polymer per acre of said growing plants.
16. The method of claim 14, said polymer being in liquid dispersion.
17. The method of claim 14, said polymer being in granular form.
18. The method of claim 14, said polymer being in intimate mixture with a fertilizer.
19. The method of claim 18, said fertilizer being selected from the group consisting of phosphate-based fertilizers, fertilizers containing nitrogen, phosphorous, potassium calcium, magnesium, sulfur, boron, or molybdenum materials, fertilizers containing micronutrients, and oxides, sulfates, chlorides, and chelates of such micronutrients.
20. The method of claim 18, said polymer and fertilizer being co-ground together.
21. The method of claim 18, said polymer being applied to the surface of said fertilizer.
22. The method of claim 18, said fertilizer being in the form of particles having an average diameter of from about powder size to about 10 cm.

23. The method of claim 18, said polymer being present in said fertilizer product at a level of from about 0.001 g to about 20 g polymer per 100 g fertilizer.
24. The method of claim 14, said polymer being complexed with an ion.
25. The polymer of claim 24, said ion being selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca.
26. A method of enhancing the growth of plants comprising the step of applying to said plants or to the earth adjacent said plants a growth-enhancing amount of a fertilizer product comprising a fertilizer in intimate contact with the polymer of claim 1.
27. The method of claim 26, said polymer being applied at a level of from about 0.001 lbs. to about 100 lbs. polymer per acre of said growing plants.
28. The method of claim 26, said fertilizer product being a liquid dispersion of said fertilizer and said polymer.
29. The method of claim 26, said fertilizer product being a granulated mixture of said fertilizer and said polymer.
30. The method of claim 26, said fertilizer being selected from the group consisting of phosphate-based fertilizers, fertilizers containing nitrogen, phosphorous, potassium calcium, magnesium, sulfur, boron, or molybdenum materials, fertilizers containing micronutrients, and oxides, sulfates, chlorides, and chelates of such micronutrients.
31. The method of claim 26, said fertilizer being in the form of particles having an average diameter of from about powder size to about 10 cm.
32. The method of claim 26, said polymer being present in said fertilizer product at a level of from about 0.001 g to about 20 g polymer per 100 g fertilizer.
33. The method of claim 26, including the step of applying said fertilizer product to the foliage of said plants.
34. The method of claim 26, including the step of applying said fertilizer product to the earth adjacent said plants.
35. The method of claim 26, said polymer being complexed with an ion.
36. The method of claim 35, said ion being selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca.


37. A method of forming a polymer comprising the steps of:
 polymerizing a reaction mixture to form a polymer having recurring
 polymeric subunits therein. said reaction mixture comprising at least two different
 reactants selected from the group consisting of first, second, and third reactants,
 wherein said first reactant is of the general formula




said second reactant is of the general formula




or




and said third reactant is of the general formula



or



or



wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , said polymer having at least one of said R_1 , R_2 , R_3 and R_4 being OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.

38. The method of claim 37, said first reactant being vinyl acetate and said second reactant being maleic anhydride.

39. The method of claim 37, said polymerization step being carried out by generating free radicals in said reaction mixture.

40. The method of claim 39, said free radical generation step comprising the step of adding a peroxide to said reaction mixture.

41. The method of claim 39, said free radical generation step comprising the step of subjecting said reaction mixture to UV light.

42. The method of claim 37, said reaction mixture being formed in a solvent selected from the group consisting of water and acetone.


43. The method of claim 37, said polymerization step being carried out at a temperature of from about $0^\circ C$ to about $120^\circ C$ for a period of from about 0.25 hours to about 24 hours.

44. The method of claim 37, said polymerization step being carried out under an inert gas atmosphere.

45. The method of claim 37, including the step of hydrolyzing said polymer by adding an acid or base to said polymer.

46. The method of claim 45, including the step of adding a base to said polymer.
47. The method of claim 37, including the step of drying said polymer to a solid form.
48. The method of claim 37, including the step of concentrating an aqueous solution of the polymer until the polymer precipitates out.
49. The method of claim 37, including the step of reacting said polymer with an ion to form a complex with the polymer.
50. The method of claim 49, said ion being selected from the group consisting of Fe, Zn, Cu, Mn, Mg, Mo, Co, Ni, Al, V, Cr, Si, B, or Ca ion.
51. The method of claim 45, said hydrolyzing step being carried out *in situ*.

52. A dicarboxylic acid polymer having the generalized formula



wherein R_5 and R_6 are

individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and $\text{C}_1\text{-C}_4$ alkyl ammonium groups, and n ranges from about 1-10,000.

53. The polymer of claim 52, wherein each of R_5 and R_6 is Na.
54. The polymer of claim 52, wherein each of R_5 and R_6 is ammonium.
55. The polymer of claim 52, wherein each of R_5 and R_6 is hydrogen.
56. A method of decreasing nitrogen volatilization comprising the step of coating a fertilizer product with a substantially water-soluble dicarboxylic polymer to form a coated fertilizer product.
57. The method of claim 56, said fertilizer product being selected from the group consisting of phosphate-based fertilizers, fertilizers containing nitrogen, phosphorous, potassium calcium, magnesium, sulfur, boron, or molybdenum materials, fertilizers containing micronutrients, and oxides, sulfates, chlorides, and chelates of such micronutrients.
58. The method of claim 56, said polymer being 100% saturated with calcium.
59. The method of claim 56, said polymer being 50% saturated with hydrogen and 50% saturated with calcium.
60. The method of claim 56, said polymer including the salt form thereof.
61. The method of claim 56, said polymer coating comprising at least about 0.01% by weight of said coated fertilizer product.
62. The method of claim 56, said polymer coating comprising at least about 5% by weight of said coated fertilizer product.
63. The method of claim 56, said polymer coating comprising at least about 10% by weight of said coated fertilizer product.
64. A method of increasing phosphorus availability comprising the step

of applying to the soil adjacent growing plants a fertilizer product coated with a substantially water-soluble dicarboxylic polymer.

65. The method of claim 64, said fertilizer product being applied at a rate of at least about 5 ppm.

66. The method of claim 64, said fertilizer product being applied at a rate of at least about 10 ppm.


67. The method of claim 64, said fertilizer product being applied at a rate of at least about 20 ppm.

68. A method of enhancing plant growth comprising the step of applying to the soil adjacent growing plants the dicarboxylic acid polymer of claim 1.


69. A composition for enhancing the growth of plants comprising a dicarboxylic acid polymer and a fertilizer product, said dicarboxylic acid polymer comprising the polymer of claim 1.

70. The composition of claim 69, said fertilizer being selected from the group consisting of phosphate-based fertilizers, fertilizers containing nitrogen, phosphorous, potassium calcium, magnesium, sulfur, boron, or molybdenum materials, fertilizers containing micronutrients, and oxides, sulfates, chlorides, and chelates of such micronutrients.


71. The composition of claim 69, said dicarboxylic acid polymer comprising recurring polymeric subunits each made up of at least two different moieties individually and respectively taken from the group consisting of A, B, and C moieties, or recurring C moieties, wherein moiety A is of the general formula




moiety B is of the general formula




or




or




and moiety C is of the general formula



or



or



wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups; $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.


72.

A method of forming a polymer comprising the steps of:


providing an aqueous solution of caustic;

providing a reaction mixture comprising at least two different reactants in a solvent, said reactants being selected from the group consisting of first, second, and third reactants, wherein said


first reactant is of the general formula



said second reactant is of the general formula



and said third reactant is of the general formula



wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , adding a sufficient amount of said reaction mixture to said caustic solution in order to bring the pH of the resulting reaction solution to about 7;

polymerizing said reaction mixture to form a polymer having recurring polymeric subunits therein with carboxyl-containing groups;
performing reduced pressure distillation to remove said solvent;
hydrolyzing said polymer so that at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties; and
isolating said polymer.

73. The method of claim 72, said first reactant being vinyl acetate and said second reactant being maleic anhydride.

74. The method of claim 72, said polymerization step being carried out by generating free radicals in said reaction mixture.

75. The method of claim 74, said free radical generation step comprising the step of adding a peroxide to said reaction mixture.

76. The method of claim 74, said free radical generation step comprising the step of subjecting said reaction mixture to UV light.

77. The method of claim 72, said solvent being selected from the group consisting of water and acetone.

78. The method of claim 72, said polymerization step being carried out at a temperature of from about 0°C to about 120°C for a period of from about 0.25 hours to about 24 hours.


79. The method of claim 72, said polymerization step being carried out under an inert gas atmosphere.

80. The method of claim 72, said isolation step being selected from the group consisting of precipitation, spray drying, and simple drying.


81. The method of claim 72, including the step of concentrating the aqueous solution of the polymer until the polymer precipitates out.

82. A seed product comprising seeds in intimate contact with a polymer as defined in claim 1.
83. The seed product of claim 82, said polymer being applied as a coating to said seeds.
84. The seed product of claim 82, further comprising particles of fertilizer in intimate contact with said polymer.
85. The seed product of claim 83, said polymer coating comprising at least about 0.01% by weight of said seed product.
86. The seed product of claim 83, said polymer coating comprising at least about 5% by weight of said seed product.
87. The seed product of claim 83, said polymer coating comprising at least about 10% by weight of said seed product.
88. The seed product of claim 84, said polymer being applied as a coating to said fertilizer.
89. A method of increasing the abrasion resistance of solid fertilizer comprising the step of applying to the surface of the solid fertilizer a polymer as defined in claim 1.
90. The method of claim 89, including the step of applying said polymer at a level of from about 0.005-15% by weight, based upon the weight of the fertilizer taken as 100%.

91. A polymer comprising recurring dicarboxylic polymeric subunits each made up of at least two different moieties individually and respectively taken from the group consisting of A, B, and C moieties, or recurring C moieties, wherein moiety A is of the general formula





moiety B is of the general formula




or


or




and moiety C is of the general formula



or




or




wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties, and wherein the polymer contains a number of alcohol groups.

92.


A method of forming a polymer comprising the steps of:
 polymerizing a reaction mixture to form a polymer having recurring polymeric subunits therein, said reaction mixture comprising at least two different reactants selected from the group consisting of first, second, and third reactants, wherein said first reactant is of the general formula




said second reactant is of the general formula



or





or




and said third reactant is of the general formula

or




or

wherein R_1 , R_2 and R_3 are


individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_2 , C_2H_4 , and C_3H_6 , said polymer having at least one of said R_1 , R_2 , R_3 and R_4 being OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 ,

R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties.


93. A method of forming a polymer comprising the steps of:
 providing an aqueous solution of caustic;
 providing a reaction mixture comprising at least two different reactants in a solvent, said reactants being selected from the group consisting of first, second, and third reactants, wherein said first reactant is of the general formula




said second reactant is of the general formula




or



or



and said third reactant is of the general formula



wherein R_1 , R_2 and R_7 are individually and respectively selected from the group consisting of H, OH, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl C_1 - C_{30} based ester groups, $R'CO_2$ groups, and OR' groups, wherein R' is selected from the group consisting of C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_3 and R_4 are individually and respectively selected from the group consisting of H, C_1 - C_{30} straight, branched chain and cyclic alkyl or aryl groups; R_5 , R_6 , R_{10} and R_{11} are individually and respectively selected from the group consisting of H, the alkali metals, NH_4 and the C_1 - C_4 alkyl ammonium groups, Y is selected from the group consisting of Fe, Mn, Mg, Zn, Cu, Ni, Co, Mo, V, Cr, Si, B, and Ca; R_8 and R_9 are individually and respectively selected from the group consisting of nothing, CH_3 , C_2H_5 , and C_3H_7 , adding a sufficient amount of said reaction mixture to said caustic solution in order to bring the pH of the resulting reaction solution to about 7; polymerizing said reaction mixture to form a polymer having recurring polymeric subunits therein with carboxyl-containing groups; performing reduced pressure distillation to remove said solvent; hydrolyzing said polymer so that at least one of said R_1 , R_2 , R_3 and R_4 is OH where said polymeric subunits are made up of A and B moieties, at least one of said R_1 , R_2 and R_7 is OH where said polymeric subunits are made up of A and C moieties, and at least one of said R_1 , R_2 , R_3 , R_4 and R_7 is OH where said polymeric subunits are made up of A, B and C moieties; and isolating said polymer.