

Description

The present invention relates to a process for bonding a wire to a bonding pad of a semiconductor pellet to a semiconductor device with a wire bonded in this way, and to an apparatus for forming such a bond.

When forming a semiconductor device such as an IC or LSI, it is usually necessary to bond a wire to a bonding pad forming an electrode of a semiconductor element of the device, and subsequently bonding the wire to a lead frame to establish an electrical connection. One known way of bonding the wire to the pad is ball bonding.

In ball bonding, a high voltage is applied between an electric discharge electrode and the end of a wire held by a capillary wire bonding tool. The resulting electric discharge makes spherical the end of the wire (i.e. a "ball" is formed at the end of the wire). Thereafter, the capillary is lowered to crush the ball against the pad. The press-bonding is carried out under heat thereby connecting the wire to the pad. It is also known in ball bonding to supply a reducing gas atmosphere to the space between the end of the wire and the discharge electrode, which is disposed opposing thereto.

Such a wire bonding device has been described, for example, in Japanese Patent Laid-Open No. Sho 58-169918.

When manufacturing semiconductor devices such as ICs, LSIs, transistors, etc., it is common to use gold (Au) wires of from 20 to 50 μm diameter to form the connection between an aluminium (Al) pad electrode on a silicon (Si) chip (pellet) and a lead frame. Thus, using ball bonding, a ball is formed to the end of a gold wire by means of electric discharge (or possibly by a hydrogen flame) and the ball is connected by press-bonding under heating or supersonic welding. However, because the density of semiconductor elements is high, and the size of the device is small, it is necessary to make the gold Au wire very fine. This reduces the strength of the wire, thereby causing problems of deformation or disconnection of the wire upon resin encapsulation.

Therefore, ball bonding techniques using other materials than gold have been developed.

Copper (Cu) and aluminium (Al) have been considered suitable materials for the wire, and studies have been made by various research organizations using copper (Cu) wires in view of copper's electroconductivity and strength, because copper wire does not deform nor do disconnections occur even when the wire is made finer than normal gold wires.

However, it has been found extremely difficult technically to use the copper wire since it is oxidized more easily as compared with the gold wire making it difficult to obtain a ball of a high sphericalness, also as the hardness of the ball is high.

Recently, it has been proposed that copper balls of high sphericalness be obtained by forming a ball in an inert gas containing hydrogen as disclosed in Japanese Patent Laid-Open No. Sho 58-154241. This has promoted the study of copper ball bonding. The effects of a shielding gas on ball formation are also discussed in document: "36th Electronic Components Conference", Seattle, Washington, 5th-7th May 1986, pages 312-317, IEEE, K. Atsumi et al.: "Ball bonding technique for copper wire".

Further, attempts have been made for increasing the purity of the copper wire, thereby to decrease the ball hardness (Japanese Patent Laid-Open Nos. Sho 60-124959, 59-13662 and 59-139662) and GB-A-2157607. If the ball hardness is high, there is a high probability of damage to the silicon chip forming the semiconductor pellet during ball bonding. Thus the conditions for adequate bonding are extremely limited as compared with the case of gold wire making copper wire unsuitable for the mass production. However, the ball hardness is not reduced by a large amount even if the purity of the copper is improved, and a better technique for reducing the ball hardness has been in demand.

It has been found by the present inventors that in the conventional wire bonding device as described above, the hardness of the spherical portion (ball) is increased by the method by which it is formed, increasing the risk of faulty bonding. As mentioned above, the electric discharge is conducted in a reducing gas so that the copper wire is not oxidized. In this case, since the gas supplied is not heated, the temperature of the gas is at an ambient temperature (or a temperature slightly higher than the ambient temperature due to the effect of heat in the periphery). Accordingly, if the end of the wire is melted by heating due to the electric discharge, it acts to cool the molten wire since the temperature of the blown gas is nearly at the ambient temperature. This increases impurities in the interior of the ball, reducing its crystalline properties. Furthermore, the spherical portion (ball) molten into a spherical lump is rapidly cooled by the blowing of the gas after the electric discharge.

Since the ball has a high hardness, in view of the above, it cannot be press-bonded sufficiently, so that the necessary bonding area is not obtained, or cracks result in the silicon region or oxide layers under the wire bonding pad in a semiconductor pellet (chip) thereby reducing the bondability and worsening the

reliability of the device.

In the prior art, it is the accepted wisdom that the ball should be softened by reducing the hardness of the wire itself and no consideration has been paid to the relationship between the texture and the hardness of the ball, thus failing to obtain a sufficient reduction in the hardness of the ball.

5 The present invention seeks to overcome these problems and proposes that the reducing gas is heated to a high temperature, which has been found to produce a ball of very low hardness. Therefore, it becomes possible to achieve satisfactory and reliable bonding with a greatly reduced risk of cracks developing in the semiconductor pellet.

According to the present invention, there is provided a method for fabricating a semiconductor device having a semiconductor pellet at least one bonding pad on one major surface of the pellet and at least one lead outside the pellet comprising:

- (a) placing the pellet and the at least one lead on or over a heat block at a predetermined temperature;
- (b) forming a ball on the end of a copper bonding wire, the end of the bonding wire projecting from the tip of a bonding capillary, the ball being formed by electric discharge between the end of the wire and an electrode in a non-oxidative gas atmosphere;
- 15 (c) ball bonding the wire to the bonding pad by pushing the ball against the pad with the ball projecting beyond the tip of the capillary; and
- (d) subsequently bonding the wire to the at least one lead; wherein

20 in step (b), the ball is formed in a non-oxidative gas atmosphere having an atmosphere temperature of at least 100°C but lower than the temperature at which the wire sticks to the capillary, the gas being supplied at the atmosphere temperature from a nozzle adjacent the end of the wire, and the gas atmosphere being maintained at the atmosphere temperature for a time sufficiently long for the ball to harden. to prevent the temperature of the wire being raised sufficiently to cause it to adhere to the capillary bonding tool, and so a maximum temperature of 200°C is proposed when bonding a copper wire.

25 In wire bonding of the present invention, since the sphericalization at the end of the copper wire is conducted, prior to the bonding, in a reducing gas atmosphere at high temperature, the reducing effect is increased due to the high temperature to obtain a ball of high sphericalness with a homogenous crystalline structure and a lower probability of impurities. Although the temperature of the ball decreases when the electric discharge ceases, the fact that the temperature of the atmosphere in the electric discharging space is kept at 100°C - 200°C means that the ball cools gradually. A ball at a high purity and low hardness can be obtained by avoiding impurities and by gradual cooling. Accordingly, a ball can be deformed sufficiently during bonding to the pad to obtain a predetermined bonding area, so improving the bond. Since the ball is soft and may absorb stresses when it is pressed against the bonding pad, cracks are less likely to occur in the semiconductor matrix below the wire bonding pad. Further, by controlling the temperature for the ball-forming atmosphere to about 200°C at the highest, wire bonding can be conducted satisfactorily without the risk that the ball or the wire is softened excessively, so that it adheres to the capillary wire bonding tool, which would cause clogging or contamination in the capillary.

40 It has been found that when ball bonding is carried out in the way discussed above, the ball itself has different properties from balls produced by the known techniques. Thus, the present invention further relates to a semiconductor device in which the ball bonded to the pad has these properties.

The ball has:

- (1) A hardness less than 45 when measured by using a microvickers hardness tester manufactured by Shimadzu under the condition of a 10g load.
- (2) At least one of the crystal grains at the periphery of the copper ball, just above the boundary of the bond makes an angle (θ) of less than 30° relative to the silicon (Si) chip in the junction between the copper ball and the aluminium electrode on the Si chip. This is shown in Fig. 1 of the accompanying drawings with the ball 1 being shown with crystal grains 2 which, adjacent the pad, make an angle of θ - (less than 30°) to the pad, and hence to the semiconductor chip (pellet).
- 45 (3) The average crystal grain size is less than 15 μm , after polishing the texture of the copper ball at the boundary of the copper ball bonding substantially in parallel with the pad and hence the silicon chip and observed from above by a microscope.

50 As mentioned above, the present invention also relates to a wire bonding apparatus. In a wire bonding apparatus according to the present invention, there is an electric discharge electrode, which is opposed to the end of a wire projecting from the lower end of the capillary, which electrode causes electric discharge relative to the wire. A gas supply means is provided for supplying a reducing gas at a high temperature to the portion of the wire top end opposed to the discharge electrode. The high temperature reducing gas is at a high temperature from 100 to 200°C and, preferably, from 150°C to 200°C and covers the top end of the wire. The electric discharge is conducted in such a reducing gas atmosphere at high temperature, which is

maintained at the high temperature at least till the ball formed by the electric discharge is hardened and then wire bonding is carried out.

The background of the present invention will now be discussed in greater detail, by discussing the behaviour of the structure of the ball under different production conditions.

5 When a copper wire is to be joined to an aluminium pad electrode, bonding is normally achieved by means of ultrasonic vibrations. In this case, since the ball and the electrode pad may rub each other due to the ultrasonic vibrations, oxide layers are removed from both of them to expose fresh surfaces. Then, the fresh surfaces are bonded. However, since the copper ball is extremely hard fine cracks are liable to develop to the silicon chip itself thus bringing about a problem that the range of adequate bonding conditions is extremely narrow. Further, if they are bonded, since the ball is hard, the aluminium electrode layer is forced from under the ball and the aluminium pad electrode may then become disconnected due to corrosion at its thinned portion under the ball by the intrusion of moisture after resin encapsulation of the semiconductor device.

15 In view of the above, various research organisations have proposed that the hardness of the ball be reduced by improving the purity of the copper wire and removing trace amounts of impurities such as Fe, Au, etc., that may cause hardening to the ball. Hence techniques for high purification have been studied.

However, when the purity is improved from the conventional 99.99% to 99.999%, the hardness of the copper ball is reduced until a purity of 99.999% is reached; subsequently the softening effect is not so marked as shown in Figure 3 of the accompanying drawings. Thus, simply improving the purity of the wire does not result in a sufficient reduction in the ball hardness. In Figure 3 the abscissa indicates the purity A (%) of the wire and the ordinate indicates the Vickers hardness (Hv) of the ball.

In seeking to overcome the foregoing problems, the inventors of the present invention studied the required hardness of the copper ball, the tissue of the ball capable of attaining such hardness, as well as the changes in the crystal grains of the copper ball when subjected to the ball bonding.

25 The present invention proposes to use a copper wire at a purity preferably higher than 99.999% and control the coagulation rate upon forming a ball in an inert gas atmosphere comprising a mixture of non-oxidative gas such as argon and hydrogen, thereby controlling the texture, softening the ball and preventing the defective bonding.

It has been found that, when forming a copper ball by means of short-circuit discharge relative to an electrode, the ball is rapidly coagulated since the wire is fine, e.g. several tens of micrometers and the ball diameter is also small e.g. less than 100 μm . Therefore, it has been found that the coagulated tissue of a ball becomes finer if cooling is rapid, and the hardness of the ball is increased since impurities such as oxygen and hydrogen introduced during melting of the wire cannot be released to the outside of the ball.

35 As shown in Figure 4, ball coagulation starts from the wire portion 3 and the ball periphery 4 and proceeds to the centre of the ball. Accordingly, impurities tend to accumulate at the centre and are not released to the outside. To lower the impurities, it is particularly effective if the coagulation rate of the wire 3 and the ball 5 is reduced. For that purpose, it is proposed that the wire 3 is kept heated and the ball is formed in a heated non-oxidative gas such as an inert gas. An appropriate temperature of the gas is from 100 to 200 °C and, particularly, higher than 150 °C.

40 Figure 5 of the accompanying drawings shows the change in the Vickers hardness (Hv) of the ball relative to the shield gas temperature T(°C) for the ball. As the heating temperature increases, the ball becomes more soft and if the temperature is higher than 150 °C, it is softened (about 6 to 7 Hv) as compared with the case where the temperature of the gas is at room temperature. If the inert gas is heated to a temperature higher than 200 °C, no significant change in hardness occurs above the temperature. In Figure 5, the temperature of the wire is set to 150 °C. If the temperature of the wire is set to room temperature, the Vickers hardness is increased by about 2 Hv. The temperature of the wire itself is also, preferably, from 100 to 200 °C, for example, 150 °C.

45 Figure 6 of the accompanying drawing shows the change in crack generation frequency (%) in silicon upon ball bonding relative to the Vickers hardness (Hv) of the ball. It can be seen from Figure 6 that no silicon cracks are developed if the Vickers hardness is reduced below 45.

50 Figure 7 of the accompanying drawing shows the change of the average crystal grain size Z/L of the ball relative to the temperature T(°C) of the shield gas with the dimensions Z and L being shown on the ball inset in the figure. The temperature of the copper wire near the copper ball is set to 150 °C in Figure 7. The grain size is increased as the temperature of the shield gas increases, because the coagulation rate is retarded by the use of the heated shield gas.

55 Figure 8 shows the relationship between the average crystal grain size Z/L and the Vickers hardness (Hv) of the copper ball. It can be seen that if the average crystal grain size is greater than 0.2, the hardness of the copper ball does not exceed 45 and silicon cracks do not develop upon ball bonding.

It has further been found that if a Cu ball of an average crystal grain size of greater than 0.2 is used for ball bonding, at least one of crystal grain boundary at the periphery of the ball adjacent the bond deforms plastically so as to form an angle (θ) with the face of the ball bonded to the bonding pad of less than 30° upon deformation because of the soft texture.

6 Figure 1, discussed above, shows a schematic view when applying ball bonding using a copper ball with average crystal grain size Z/L of 0.3. It can be seen that the θ is about 10°.

If a copper ball with an average grain size Z/L of less than 0.2 is used for the ball bonding, the ball is hard and insufficient plastic flow occurs, hence the angle of the crystal grain boundary with the face of the ball bonded to the bonding pad is inevitably increased. For instance, if the average crystal grain size Z/L is 0.16, the angle θ is 60° if the ball hardness is high.

Figure 2 shows the relationship between the angle θ (degree) of the crystal grain boundary relative to the bonding face in the conventional ball bonding and the silicon crack development ratio C (%). If the angle θ exceeds 30 degrees, silicon cracks are generated.

15 The temperature for the Si chip may be elevated to higher than 250°C for promoting the deformation of the ball upon ball bonding. It has been found that a ball of a greater than average crystal grain size and more soft tissue tends to cause recrystallization near the bonding boundary since fewer impurities are present in the ball as compared with a ball of smaller grain size and higher hardness.

When applying bonding by using a ball of Vickers hardness of 50, the crystal grain size of the ball is apparently decreased as compared with the case of using a ball of Vickers hardness at 42 for the bonding.

20 Figure 9 shows the relationship between the Vickers hardness B (Hv) of a ball and the average grain size after ball bonding.

In Figure 9, the crystal grain size D (μm) of a copper ball at the ball bond using a copper wire when observed from above by a microscope is shown along the ordinate as the average crystal grain size after the ball bonding. The ball tissue of a bonding wire is observed from the above within a range of a height 30 μm above the boundary of the bond where the wire is bonded to the bonding pad of the semiconductor pellet, which is polished in parallel with the surface of the semiconductor pellet.

It can be seen that the average value for the grain size is less than 15 μm in case if the Vickers hardness is less than 45. Thus defective bonding can be prevented or reduced by reducing the average crystal grain size to less than 15 μm .

30 The present invention is applicable to wire bonding of many different types of semiconductor devices. For example, the semiconductor pellet may contain an IC, or LSI device, or merely transistors. These are normally formed on a semiconductor substrate of the pellet, e.g. of silicon. Although applicable to the bonding of a wire to one bonding pad, the present invention can also be applied where wires have to be bonded to many pads of the device.

35 Embodiments of the invention will now be described, by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a schematic view illustrating the texture of the ball bonding portion in a semiconductor device according to the present invention; and has already been discussed;

40 Figure 2 is a graph showing the relationship between the angle θ formed by the crystal grain boundary of the ball bonding portion relative to the surface of an LSI chip and the crack generation ratio;

Figure 3 is a graph showing the relationship between the hardness of a copper ball and the purity of the wire;

Figure 4 is a schematic view illustrating the bonding method for a copper ball;

45 Figure 5 is a graph showing the relationship between the temperature of the shield gas and the hardness of the ball;

Figure 6 is a graph showing the relationship between the hardness of a ball and the silicon crack generation rate;

Figure 7 is a graph showing the relationship between the average crystal grain size and the temperature of the shield gas;

50 Figure 8 is a graph showing the relationship between the average crystal grain size and the Vickers hardness of a ball;

Figure 9 is a graph showing the relationship between the hardness of a ball and the crystal grain size at a ball bond;

55 Figure 10 is a front elevational view illustrating part of one embodiment of a wire bonding device according to the present invention;

Figure 11 is a schematic view illustrating the formation of a ball;

Figure 12 is a schematic view illustrating the end of a wire before the initiation of electric discharge;

Figure 13 is a schematic view showing the end of the wire made spherical by the electric discharge;

Figure 14 is a schematic view illustrating the end of the wire being positioned at a first bonding point;
 Figure 15 is a schematic view illustrating the wire being positioned at a second bonding point;
 Figure 16 is a cross sectional view illustrating a semiconductor device according to an embodiment of the present invention;
 5 Figure 17 is a front elevational view illustrating an embodiment of a wire bonding apparatus according to the present invention;
 Figure 18 is an enlarged front elevational view of a part of the apparatus of Figure 18; and
 Figure 19 is a block diagram illustrating the operation of the apparatus of Figure 18.

10 Example 1

One embodiment of the present invention will now be described with reference to Figures 10 to 16.

Figure 10 is a front elevational view showing a portion of a ball bonding type wire bonding device in one embodiment according to the present invention, Figure 11 is a schematic view illustrating the ball-formation,
 15 Figure 12 - Figure 15 are schematic views illustrating the ball-forming steps, in which Figure 12 is a schematic view illustrating the top end of a wire before starting the electric discharging, Figure 13 is a schematic view illustrating the top end of the wire sphericalized by the electric discharge, Figure 14 is a schematic view showing the state in which the top end of the wire is secured to the first bonding point
 Figure 15 is a schematic view showing the state in which the top end of the wire is secured to the second
 20 bonding point and Figure 5 is a graph showing a correlationship between the temperature for the ball-forming atmosphere and the ball hardness.

In the wire bonding device of this embodiment, as shown in Figure 10, a semiconductor pellet 102 in which a non-completed semiconductor device 101, that is, semiconductor integrated circuits such as IC or LSI or transistors such as MOSFETs or bipolar transistors are formed into a semiconductor pellet and each
 25 of leads of a lead frame 103 are electrically connected by bonding the electrode (wire bonding pad) 102a of the semiconductor pellet 102 and the leads 104 of the lead frame 103. The wire bonding device has a feeder 106 equipped with a heater block 107 capable of heating the lead frame 103. An X-Y table 108 is disposed to the outside of the feeder 106 so as to be displaceable in X-Y direction and a bonding head 109 is mounted on the X-Y table 108. A bonding arm 110 is rotatably pivoted at the base end thereof on the
 30 bonding head 109, and the bonding arm 110 is so adapted to be driven by a cam mechanism (not illustrated) such that a capillary 111 connected as a wire bonding tool to the top end thereof is moved vertically. The bonding arm 110 is connected with an ultrasonic vibration source and an ultrasonic vibration horn not illustrated so that ultrasonic vibrations are transmitted by means of the bonding arm to the capillary as the connection tool, so as to conduct bonding by means of supersonic vibrations or press bonding under
 35 heating combined with supersonic vibrations. A pair of clamp arms 112 and 113 are disposed on the upper side of the bonding arm 110 such that they are actuated by an adequate means such as solenoid plunger mechanism (not illustrated) and the respective ends of both of the clamp arms 112 and 113 are situated just above the capillary 111 to constitute a clasper 114. A copper wire 105 as a bonding wire delivered from a reel (not illustrated) is inserted by way of a guide 115 and further inserted through the capillary 11.

A discharge electrode 116 is disposed in the vicinity of and separately from the capillary 111 and the discharge electrode 116 is rotatably pivoted at the upper end thereof such that the top end displaces
 40 between the position below the capillary 111, that is, the position just beneath the top end of the wire 105 and the side position (retracting position) to the capillary 111. A power source circuit 117 is connected between the discharge electrode 116 and the clasper 114 to apply a voltage (about 1000 volt, several tens
 45 of milliamperes - several amperes) between the clasper 114, that is, the wire 105 inserted therethrough and the discharge electrode 116. In this case, the electric discharge fabrication can be carried out preferably for the ball when the top end of the wire is connected to the cathode of the power source. As a result, electric discharge arc is generated between the wire 105 and the discharge electrode 116, by which the top end of the wire 105 is melted and sphericalized by the surface tension.

While on the other hand, a plurality of tubes 118 as means for supplying a gas to the top end of the wire 105 are disposed in this wire bonding device. A plurality of tubes 118 are disposed radially such that
 50 their openings are directed to a position below the capillary 111 and opposed with each other. Further, several of the tubes 118 are disposed along the upper surface of the discharge electrode 116 so that a reducing gas may be supplied to the region on the upper surface of the discharge electrode 116. Further, a
 55 gas source 119 for the reducing gas, for example, a gas mixture of an inert gas such as a nitrogen gas and a hydrogen gas is connected to the rear end of the tube 118 and an electric heater 120 as heating means is disposed at the midway of the tube so that the gas can be heated to a predetermined temperature. As described later, the reducing gas 121 is supplied under heating to a temperature from 100° C to 200° C by

the electric heater 120. As a result, when the gas is jetted out from the top end of the tube 118, the top end of the wire is surrounded with the reducing gas at high temperature.

Description will be made specifically to the wire bonding method by such a wire bonding device and a production process for a semiconductor device.

When the lead frame 103 to which the semiconductor pellet 102 is bonded is supplied to a bonding stage on the feeder 106, the X-Y table 108 is displaced properly such that the lower end of the wire 105 held by the capillary 111 is opposed above the discharge electrode 106 as shown in Figure 12. In this state, the lower end of the wire 105 mainly composed of copper is placed in the reducing gas atmosphere formed by a gas blown out from the tubes 118 respectively as shown in Figure 11 through Figure 13. Further, the reducing gas atmosphere is formed by the reducing gas 121 heated by the electric heater 120. The temperature for the reducing gas atmosphere is kept within a range from 100°C to 200°C and, preferably, from 150°C to 200°C, which is based on the finding that if the temperature for the reducing gas high upon sphericalization of the wire top end, the top end does not involve impurities and the hardness thereof is lowered to improve the bonding property. It has, however, been also found that if the temperature is excessively high, the wire is adhered to the capillary failing to conduct wire bonding. The hardness of the ball varies depending on the temperature for ball-forming atmosphere and it has been found by the experiment made by the present inventors that the hardness changes as shown by the graph in Figure 5. That is, Figure 5 shows the temperature T(°C) for the ball-forming atmosphere, that is, shield gas on the abscissa and the Vickers hardness (Hv) of the ball on the ordinate. As can be seen from the graph, the Vickers hardness of the ball is rapidly lowered if the temperature for the reducing gas exceeds 100°C and such a hardness lowering effect is substantially saturated as the temperature exceeds 200°C. If the temperature for the shield gas is higher than 200°C, the bonding wire is adhered to the capillary (bonding tool) to cause clogging or contamination thereto, bringing about a difficult to continue the bonding operation. Accordingly, the temperature for the shield gas atmosphere upon ball-forming is desirably from 100°C to 200°C. The temperature range for the shield gas atmosphere upon ball-forming is, particularly preferably, from 150 to 200°C for forming a ball at high purity with less incorporation of impurity, obtaining a predetermined crushing amount by the press-bonding of the ball and increasing the bonding strength.

Then, when the discharge electrode 116 is brought closer to the lower end of the copper wire 105, the power source circuit 117 is closed and a voltage is applied between the lower end of the wire 105 and discharge electrode 116. As a result, a discharge arc is generated between the top end of the wire 115 and discharge electrode 116 to conduct electric discharge, by which a ball 122 is formed by melting at the top end of the copper wire 105 as shown in Figure 13. Since the ball 122 is formed under the reducing gas atmosphere (shield gas) at high temperature, a pure ball can be obtained with less incorporation of oxides. Further, since there is no oxide layers on the surface, the surface tension is exerted over the entire area of the sphere to sphericalize the ball. Further, the hardness of the ball is lower than 50 (Hv).

Then, as the bonding head 109 is displaced, the capillary 111 apart from the discharge electrode 116 and moves to the first bonding point. Since the capillary 111 descends at the first bonding point, the ball 122 at the top end of the wire 105 is crushed by the capillary 111 and then press-bonded to the electrode (wire bonding pad mainly composed of aluminum) of the pellet 102. In this instance, since the pellet 102 is heated by the heat block 107 and since the capillary 111 undergoes ultrasonic vibrations, the ball 122 is press-bonded under heating on the pad of the pellet 102 as shown in Figure 14.

The wire bonding is carried out by the press-ball bonding under heating in combination with ultrasonic vibrations. Referring more specifically the temperature, the heating temperature at the pellet bonding portion when the pellet 102 is heated by the heat block 107 is about from 330°C to 350°C. Further, in the press-bonding system under heating combined with ultrasonic vibrations, the temperature of the capillary 111 is elevated to about 130 - 140°C during operation of the capillary. The temperature of the capillary 111 in the case of the press bonding system under heating is controlled positively to 180°C ± 10°C.

After the completion of the first bonding, the capillary 111 is moved relatively in a 3-dimensional manner by means of the X-Y table 108 and the bonding head 109, transferred above a predetermined lead 104 as the second bonding point and then descended. As the capillary 111 descends and undergoes ultrasonic vibrations at the descended position, the wire 105 is press-bonded under heating onto the lead 104 also being assisted by the heating of the lead 104 from the heat block 7. The wire bonding is also conducted by the press-bonding system under heating combined with ultrasonic vibrations as in the first bonding.

After the completion of the second bonding, the clamper 114 grips the wire 105. Since the clamper 114 then uprises together with the capillary 111, the wire 105 is disconnected from the second bonding portion. Then, when the clamper 115 releases the wire 105, the capillary 111 uprises slightly. By the tail-exposing operation for the wire, the top end of the wire 105 is protruded by a length required for the formation of ball

122.

The wire bonding is completed by connecting the first bonding point on the pellet 102 and the top ends of the respective leads 104 as the second bonding point on the lead frame 103 by means of the wire 104 successively by repeating the foregoing procedures.

As shown in Figure 16, the semiconductor pellet (chip) 102 is secured by means of adhesives 123 such as silver paste (pellet-bonded) to the lead frame 103, that is, the tab 104a as the pellet mounting region of the lead frame 103 after completion of the wire bonding, and the bonding pads 102a of the semiconductor pellet 102 and the inner lead of the outer leads 104 of the lead frame 103 are connected with each other by means of the bonding wire 105.

Then, the lead frame 103 after the completion of the wire bonding is set to a transfer molding machine to apply resin encapsulation by using a mold resin thereby encapsulating the semiconductor pellet 102, etc. and conducting packaging. In the figure, 124 denotes a mold resin encapsulation body. Then, frame portions, etc. of the lead frame 103 which are no more necessary as the semiconductor device products are removed by cutting and the outer leads 104 are bent as required thereby obtaining a completed semiconductor device.

In this embodiment, a copper wire is used as the wire 105 for the wire bonding. Copper is readily oxidized and relatively hard. Accordingly, if oxide layers are formed to the surface of the wire during melting upon sphericalizing the top end of the copper wire by melting, the melting occurs not uniformly thus making the shape of the ball not suitable. Such an undesired shape of the ball makes the press bonding area not uniform to worsen the bonding reliability and causes defective press-bonding if the area of the press bonding is small. Further, if oxide layers are formed at the surface of the ball, the metal bondability of the bonding pad with aluminum is lowered. Further, if the ball is hard, the ball crushing amount upon press-bonding under heating is decreased and the shape is worsened as well. Further, if the ball is hard, it no more absorbs press-bonding force, to exert an excess force to silicon (semiconductor) material beneath the pad thereby resulting in cracks, etc., or the like to reduce the yield.

However, in this embodiment, since the ball 122 of the copper wire 105 is formed in a reducing gas atmosphere at high temperature, no oxide layers formed on the surface during melting and no impurities such oxide are involved to the inside thereof. As a result, since the top end of the copper wire 105 is melted for the inside and the entire surface, uniform surface tension is generated to form the ball 122 of high sphericallness.

In the conventional case in which the reducing gas is not heated, since the molten ball 122 is hardened by the surrounding atmosphere, the hardness is increased. While on the other hand, in this embodiment, since the ball placed in the atmosphere at 100 - 200 °C, the ball is cooling rate is moderated to reduce the hardness of the ball.

According to the embodiment as described above, the following advantageous effects can be obtained.

(1) In the wire bonding according to the present invention, upon melting to form a ball at the top end of the wire by electric discharge arc, since the top end of the wire is placed in the reducing gas atmosphere at high temperature and discharge is conducted in that state, neither the impurities are involved to the inside of the ball nor the oxide layers are formed at the surface thereof and, accordingly, a ball at high purity can be formed.

(2) Since the ball at high purity can be formed as described in (1) according to the present invention, the sphericallness of the ball is also improved.

(3) Since the sphericallness of the ball is improved as described in (2) above by the wire bonding according to the present invention, the ball is crushed uniformly and the ball press-bonded portion of the ball does not go beyond the pad.

(4) Since the sphericalized top end of the wire is put within the atmosphere at a high temperature of from 100 to 200 °C in the wire bonding according to the present invention, hardening occurs gradually to reduce the hardness of the ball.

(5) Since a ball of a low hardness and easily crushable can be formed as described in (1) and (4) above, in the wire bonding according to the present invention, the ball can be crushed as desired upon press-bonded under heating to the pad and, accordingly, an expected bonding area can be obtained to attain a wire bonding at high bonding strength.

(6) Since the hardness of the ball is not excessive in the wire bonding according to the present invention as described in (5) above, the ball absorbs the bonding force by crushing upon press-bonding under heating to the pad, thereby causing no cracking to the semiconductor placed beneath the pad.

(7) Since the bondability with the pad is satisfactory and the semiconductor device forming region, etc. beneath the pad is not injured in the wire bonding according to the present invention as described in (5) and (6) above, the bonding reliability can be improved and the yield is increased in the wire bonding

according to the present invention.

(8) While the top end of the wire is heated upon sphericalization in the wire bonding according to the present invention, since the heating does not cause adhesion of the ball to the capillary or contamination of the capillary, the wire bonding can be executed smoothly to thereby improve the productivity.

(9) A synergistic effect of providing a wire bonding technic of high yield and high wire bonding reliability can be obtained according to the present invention by the effects (1) - (8) described above.

Although the invention made by the present inventor has been described specifically referring to the embodiment, the invention is no way limited only to such an embodiment but can be modified variously within a range not departing the scope of the invention. For instance, the high temperature gas supplied to the top end of the wire is not restricted only to the reducing gas but similar effect in that embodiment can be obtained with a non-oxidative gas such as an inert gas. Further, the wire is not restricted only to those wires mainly composed of copper but those wires mainly made of aluminum, gold wire, silver wire may also be used.

Although the explanation has been made mainly to the case of applying the invention in the wire bonding technic utilizing the press-bonding under heating combined with ultrasonic vibrations, which is the background art for the present invention, the present invention is no way limited only thereto, and is also applicable to wire bonding for press-bonding system under heating.

The present invention is applicable at least to the ball bonding technics in which easily oxidizable bonding wire is connected by sphericalization.

Example 2

Description will be made to Example 2 of the present invention.

The IC applied with the ball bonding according to the present invention has such a structure in which a copper wire of 30 μm diameter is bonded at its ball portion to an aluminum alloy electrode mainly composed of aluminum, while the other end of the wire is ball-bonded to a Cu-plated lead frame on a silicon chip.

Table 1 shows the result of the reliability test conducted after resin encapsulation for the ICs described above. If cracks are resulted to silicon chips, they are developed to cause failures in the temperature cycle test. Further, if an aluminum alloy electrode goes beyond the encapsulation, corrosive disconnection to the aluminum layers is liable to occur in the PCT (pressure cooker test). No defects occur in the LSIs according to the present invention to provide satisfactory results in either of the tests.

Table 1

Reliability of Resin Encapsulated IC		
Test item	Test condition	Number of defects
Temperature cycle	-65 ° C, +150 ° C, 30 min, 2K cycle	0/200
Heat shock	-65 ° C, +150 ° C, 5 min, 500 cycle	0/200
Leaving at high temperature	150 ° C 2000 Hh	0/200
P C T	121 ° C, 2 1000 hr	0/200
Leaving at high temperature and high humidity	65 ° C, 85%RH 2000 hr	0/200
High temperature, high humidity bias	85 ° C, 85%RH 15V 2000 hr	0/200

As has been described above according to the present invention, since the occurrence of defects can be prevented upon ball bonding, it is possible to conduct highly reliable ball bonding by using a copper wire.

Example 3

In the conventional wire bonding device, since no consideration was made for the bonding property and for the safety regarding the hydrogen content in the reducing gas. Then, it has been found by the present inventors that as the hydrogen content in the reducing gas increases, the hardness of the ball formed in the reducing gas is increased to lower the bonding property and, as a result, an excess deforming force is

applied to the ball, which exerts large stresses to silicon material beneath the bonding pad of the semiconductor device thereby often causing bonding damage or cracks.

Further, in the case where hydrogen in the reducing gas used in such a wire bonding device is released to the atmosphere, and if the mixing ratio between air and hydrogen exceeds 4 % (by volume) even locally, ignition may possibly occur by the discharge sparks upon forming the ball, etc. functioning as an ignition source.

Accordingly, the principal object of this embodiment is to provide a wire bonding technic capable of providing satisfactory bondability and working safety.

In this embodiment, a wire bonding technic is proposed in which gas supply means capable of supplying a mixture containing less than 4 % (by volume) of hydrogen is supplied to the surrounding of the works.

When the reducing gas is supplied to the surrounding of the discharging portion with an aim of preventing the oxidation of a ball upon forming the ball and reducing the oxides if contained in the ball, if the hydrogen contents is excessive, the amount of hydrogen incorporated to the grain boundary of the ball (hydrogen involved to the inside of the ball upon forming the ball by discharge melting) is increased to increase the ball hardness.

However, according to the means as described above, since the hydrogen content is set to less than 4 % (by volume), which is the critical value for increasing the ball hardness, increase in the ball hardness can be prevented.

Furthermore, even in a case where the reducing gas should be released to the atmosphere, if the hydrogen content in the reducing gas is less than 4 %, the mixing ratio with air is naturally reduced to less than 4 % and there is no worry of ignition even if there is an ignition source in the vicinity thereof.

Figure 17 shows a front elevational view wire for the bonding a the example 3 of the present invention, Figure 18 is an enlarged front elevational view for a portion thereof and Figure 19 is a graph for explaining the operation thereof.

The wire bonding device in this embodiment is adapted such that the pellet 202 of a semiconductor device 201 and leads 204 of a lead frame 203 are connected electrically by bonding the bonding pads of the pellet 202 and the leads 204 of the lead frame 203 with the wire 205 respectively. Accordingly, the lead frame 203 on which the pellet 202 is mounted and the wire 205 substantially constitutes a work in this embodiment.

The wire bonding device comprises a feeder 206, which is equipped with a heat block 207 for heating the lead frame 203. An X-Y table 208 is disposed to the outside of the bonding stage on the feeder 206 so as to be displaceable to X-Y direction and a bonding head 209 is mounted on the X-Y table 208. A bonding arm 210 is rotatably pivoted at the base end thereof on the bonding head 209, and the bonding arm 210 is so adapted to be driven by a cam mechanism (not illustrated) such that a capillary 211 secured at the top end thereof is moved vertically. The bonding head 209 is connected with an ultrasonic vibration device (not shown) for putting the capillary 211 to ultrasonic vibrations by way of the bonding arm 210.

A pair of clamp arms 212 and 213 are disposed on the upper side of the bonding arm 210 such that they are actuated by an adequate means, e.g., solenoid plunger mechanisms (not illustrated) and the respective ends of both of the arms 212 and 213 are situated just above the capillary 211 to constitute a clasper 214. A copper wire 215 delivered from a reel (not illustrated) is inserted through the clasper 214 by way of a guide 215 and further inserted into the capillary 211. A discharge electrode 216 is disposed in the vicinity of and separately from the capillary 211 and the electrode 216 is rotatably pivoted at the upper end thereof such that the top end displaces between the position below the capillary 211, that is, the position just beneath the top end of the wire 105 and the side position (retracting position) to the capillary 211. A power source circuit 217 is connected between the discharge electrode 116 and the clasper 214 to cause a discharge arc between the electrode 216 and the wire 205.

The wire bonding device comprises tubes 218 for forming a gas atmosphere by supplying a gas to the periphery of a ball formed at the top end of the wire 205 and the tubes 218 as the gas supply means are attached to the discharge electrode 216 with the tube openings being directed to a position below the capillary 211. A gas supply unit 219 for supplying a reducing gas such as a gas mixture of a non-oxidative gas such as argon gas and hydrogen gas is connected to the tubes 218, and the unit 219 is controlled such that the hydrogen content in the reducing gas supplied is of about 3 %. A heater 220 as the gas heating means is inserted by way of insulation tapes to the inside of the tubes 218. The heater 220 is adapted such that it can control the reducing gas supplied from the gas supply unit 219 (hereinafter referred to as shield gas or ball-forming gas) 221 to a predetermined temperature by heating during passage through the gas between the tube 218 and the heat block 220.

While the other hand, a reducing gas supply device 223 is disposed to the bottom of the feeder 206 for

supplying the reducing gas 222 for preventing the oxidation of the lead frame 203 (hereinafter referred to as lead frame oxidation preventive gas) and the supply device 223 has blowing ports 224. A plurality of blowing ports 224 are disposed at the upper surface of the feeder 206 so that the lead frame oxidation preventive gas 222 can be blown out moderately to the periphery of the lead frame 203. A gas supply channel 225 is connected to the group of the blowing ports 224. The gas supply channel 225 is connected with a gas supply unit 226, which is constituted such that it can supply a reducing gas, for example, a gas mixture comprising a non-oxidative gas such as nitrogen and hydrogen at a predetermined flow rate. Further, the unit 226 is also controlled such that the hydrogen content in the lead frame oxidation preventive gas supplied is less than 4 % (by volume).

A cover 227 is disposed over the feeder 206 so as to substantially cover the entire lead frame 203 and cover 227 functions to hold the oxidation preventive gas 222 supplied to the periphery of the lead frame 203 as long as possible to the periphery of the lead frame 203. A window 228 is perforated to the cover 227 at the position corresponding to the bonding stage just beneath the capillary 211 in such a substantially square shape as capable of conducting the wire bonding. A lead frame retainer 229 formed substantially as a square frame is elevatably fitted to the window 228 and the retainer 229 is made vertically movable interlocking with the intermittent operation of the feeder 206 by means of an appropriate driving device such as cam mechanisms (not illustrated). That is, the retainer 229 is adapted to prevent the loose movement of the lead frame 203 by retaining the lead frame 203 above upon practicing the wire bonding.

Then, the operation of the wire bonding device having constitution as described above will be explained.

When the lead frame 203 as a work bonded with the pellet 202 is intermittently supplied by the feeder 206 and the portion of the pellet 202 to be wire-bonded is supplied to the bonding stage in the feeder 206, the lead frame retainer 229 is descended within the window 228 to retain the lead frame 203. Subsequently, the X-Y table 208 is properly moved so as to repeat the bonding operations as described later.

While on the other hand, in the capillary 211, when the discharge electrode 216 is brought closer with the lower end of the copper wire 205 and the power source circuit 207 is closed, a ball 205a is formed by melting at the top end of the copper wire 205. In this case, a reducing gas 221 controlled to about 3 % hydrogen content is supplied from the tube 218 to maintain the reducing gas atmosphere between the wire 205 and the electrode 216. Since the reducing gas 221 is put to heating control such that it is at a predetermined temperature by the heater 220 disposed to the midway in the inside of the tube 218, the gas atmosphere is kept within a predetermined temperature range to prevent the lowering of the temperature for the ball 205a formed at the top end of the wire 205. As a result, if the reducing gas 221 is blown to the molten ball 205a, the hardness of the ball 205a is not reduced.

Then, the capillary 211 is descended by the bonding head 209 to gradually press-bond the ball 205a formed at the top end of the wire 205 to the pad of the pellet 202. Since the pellet 202 is heated by the heat block 207, the ball 205a is bonded to the pad of the pellet 202 by means of the press-bonding under heating combined with ultrasonic vibrations. Then, since the hydrogen content in the gas atmosphere is kept to about 3 %, the ball 205a is kept from hardening as described later and, accordingly, can be heat-bonded with satisfactory bondability.

By the way, it has been found by the present inventor that if the hydrogen content in the ball-forming gas (shield gas) is greater, since the amount of hydrogen molecules involved into the grain boundary of the ball 205a formed by melting to the top end of the copper wire 205 is increased and the ball hardness is increased, there has been a problem that the bondability is reduced at the first bonding.

In view of the above, according to this embodiment, the hydrogen content in the ball-forming gas 221 is suppressed to about 3 % thereby reducing the amount of hydrogen involved in the grain boundary of the ball 205a formed by melting and preventing the increase in the ball hardness. As a result, since the increase of the ball hardness can effectively be prevented, coupled with the prevention of the temperature lowering caused by the blowing of the reducing gas 221 by means of preheating the reducing gas 221, bondability at the first bonding can be improved.

Figure 19 is a graph illustrating the relationship between the hydrogen content in the ball-forming gas and the hardness of the ball formed in the gas atmosphere. The abscissa indicates the hydrogen ration H (vol%) contained in the ball-forming gas, while ordinate indicates the hardness of the ball formed in the gas atmosphere at such a content by the hardness ratio R assuming the hardness of the ball "1" when it is formed in a gas with 10 % hydrogen content. The copper wire used has a purity of 99.999 % and the ball is formed into 80 μ m diameter. Further, the hardness is measured under the room temperature by using a microvickers hardness tester.

According to Figure 19, if the content of hydrogen in the ball-forming gas exceeds 3 %, the ball hardness is increased. Accordingly, the ratio of hydrogen contained in the ball-forming gas 221 is set to about 3 % in this embodiment.

After the formation of the first bonding portion, the capillary 211 is relatively moved in a three dimensional manner by means of the X-Y table 8 and the bonding head 209 and an intermediate portion of the wire 205 is urged to secure to a predetermined lead 204. Since the ultrasonic vibrations are applied to the capillary 210 and the lead 204 is heated by the heat block 7, the wire 205 is bonded on the lead 204 by the press bonding system under heating combined with ultrasonic vibrations.

After the completion of the second bonding, the clasper 214 grips the wire 205 and the clasper 214 is moved together with the capillary 211 aparting relatively from the second bonding. By the aparting movement, the wire 205 is disconnected from the second bonding portion. Then, when the clasper 24 releases the wire 205 and the capillary 211 uprises slightly, the top end of the wire 205 is protruded for a length required for forming the ball 205a and tail-exposing operation is conducted.

Subsequently, the foregoing operations are repeated by the cycle corresponding to the number of the bonding pad and the inner leads 204 in the pellet 202 to conduct required wire bonding operation. Then, when the wire bonding work has been completed for the one unit lead frame, the retainer tool 229 is moved upwardly and the lead frame 203 is sent by one pitch such that the next pellet 202 is situated to the bonding stage. Thereafter, the wire bonding operations as described above are successively conducted for the pellet 202 for each of the units.

During the bonding operation, since the lead frame oxidation preventive reducing gas 222 is always blown out from the blowing ports 224 disposed to the upper surface of the feeder 206, the lead frame 203 is immersed within the reducing atmosphere. In this case, since the reducing gas atmosphere is covered with the cover 227 laid over the feeder 206, the reducing gas 222 can effectively surround the lead frame 203 and the pellet 202. Accordingly, oxidation of the lead frame 203, etc. can surely be prevented.

In a case where the copper type lead frame is used as for the lead frame, since the copper is easily oxidizable and oxide layers are formed thickly on the bonding surface, the bondability at the second bonding is reduced. That is, if the oxide layers are formed, since the metal bondability with the wire reduced, the bondability is also worsened.

However, in the present invention, since the cover 227 covers over the feeder 206 and the frame 203 is surrounded with the reducing gas atmosphere supplied to the inside thereof, no oxide layers are formed at the surface of the oxidizable copper type lead frame if it is used and, as a result, the wire 205 can be bonded on the lead 204 with satisfactory bondability.

By the way, since the lead frame oxidation preventive reducing gas 222 contains hydrogen, if the gas escapes from the cover 227 and is brought into contact with an oxygen atmosphere, it may be ignited to cause burning in the presence of arc of the discharge electrode 226, etc. as an ignition source. The, it has been found by the present inventor that if hydrogen combustion occurs to the outside of the cover, although the oxidation for lead frame does not occur but the bonding condition varies with respect to the following points and the stability for the bondability is reduced.

(1) Since the temperature for the lead frame and the capillary becomes instable due to the change of the circumstantial temperature, the ball formation and the press-bonding operation under heating in the first and second bonding become instable.

(2) Since the extent of heat expansion varies or defective operation occurs for each of the constituent portions of the device due to the variations in the circumstantial temperature, the positional accuracy for the bonding is worsened.

(3) Since the screen of the pattern recognition device fluctuates due to the occurrence of so-called air filaments due to combustion, the pattern recognizing accuracy is reduced.

On the other hand, in the present embodiment, since the lead frame oxidation preventive gas 222 is controlled so that it contains hydrogen of less than 4 %, hydrogen combustion in the lead frame oxidation preventive gas 222 can be prevented and, as a result, the stability of the bondability can be maintained.

That is, if the oxidation preventive reducing gas 222 in the cover 227 should escape externally from the window 228 due to advance and retraction of the capillary 211, the hydrogen gas contained by less than 4 % in the reducing gas 222 does not take place combustion. Since hydrogen does not burn if the mixing ration with air is less than 4 %, combustion of hydrogen in the escaped reducing gas 222 can be prevented by controlling the hydrogen content to less than 4 % by the gas supply unit 226.

Since the combustion out of the cover 227 can thus be prevented, the generation of air filaments is suppressed and the circumstantial temperature can be kept constant and, accordingly, the ball-forming or press-bonding operation by heating, as well as positional accuracy for bonding and accuracy for pattern recognition are stabilized and, as a result, reduction in the stability of the bondability accompanying them can be prevented.

This embodiment can provide the following advantages effects.

(1) Since the amount of hydrogen evolved in the grain boundary of the ball formed by melting can be

decreased by suppressing the hydrogen content in the ball-forming gas to about 3 %, increase in the ball hardness can be prevented and the bondability in the first bonding can be improved.

(2) Since the lowering in the temperature of the ball can be prevented even if a gas is blown to the ball formed by melting, by preheating the ball-forming gas, increase in the hardness of the ball can be prevented coupled with the effect as described in (1) above.

(3) Since the combustion of the escaped reducing gas can be suppressed by setting the hydrogen content in the reducing gas supplied to the lead frame to less than 4 %, reduction in the stability for the bondability due to the change in the bonding conditions accompanying combustion can be prevented, thereby improving the bonding, thus, the quality and the reliability of the products.

(4) Since the use of then copper type wire and the lead frame can be realized by preventing the reduction of the bondability in the copper type wire and the lead frame, reduction in the cost, etc. can be promoted.

(5) Since satisfactory metal bondability can be maintained to ensure adequate bondability, by surely preventing the formation of oxide layers, it is possible to improve the quality and the reliability of the bonding, and thus, the products.

(6) Since the escape of the reducing gas can be minimized by laying the cover on the feeder and opening a window of a least minimum opening surface required for the bonding operation to the cover, the reducing gas can be formed more effectively, while the amount of gas used can be suppressed.

Although the invention made by the present inventors has been described specifically referring to the examples, the present invention is not restricted only to the examples.

For instance, the content of hydrogen in the ball-forming gas (shield gas) is not restricted to about 3% but is may be less than 3 %. Particularly, in a case where the natural oxidation of the wire is completely prevented before the ball formation, a non-oxidative gas containing no hydrogen may be used as the shield gas.

The wire used is not restricted only to the copper type but aluminum or alloy type wire may be used.

The lead frame is not restricted only to the copper type but iron-nickel lead frame, etc. may also be used.

Although the explanation has been made mainly to the case of applying the invention to the wire bonding technic utilizing the press-bonding under heating combined with the ultrasonic vibrations, which is the background art for the present invention, the present invention is no way limited only thereto, but is also applicable to wire bonding of press-bonding system under heating.

The present invention is applicable at least to the wire bonding technics in general, using reducing gas.

Claims

1. A method for fabricating a semiconductor device having a semiconductor pellet (102) at least one bonding pad (102a) on one major surface of the pellet (102) and at least one lead (103) outside the pellet (102), comprising:

(a) placing the pellet (102) and the at least one lead (103) on or over a heat block (107) at a predetermined temperature;

(b) forming a ball (112) on the end of a copper bonding wire (105), the end of the bonding wire (105) projecting from the tip of a bonding capillary (111), the ball (112) being formed by electric discharge between the end of the wire and an electrode (116) in a non-oxidative gas atmosphere;

(c) ball bonding the wire (105) to the bonding pad (102a) by pushing the ball (112) against the pad (102a) with the ball (112) projecting beyond the tip of the capillary (111); and

(d) subsequently bonding the wire (105) to the at least one lead (103);

characterised in that:

in step (b), the ball is formed in a non-oxidative gas atmosphere having an atmosphere temperature of at least 100 °C but lower than the temperature at which the wire (105) sticks to the capillary (111), the gas being supplied at the atmosphere temperature from a nozzle (118) adjacent the end of the wire, and the gas atmosphere being maintained at the atmosphere temperature for a time sufficiently long for the ball (112) to harden.

2. A method according to claim 1, wherein the wire (105) is bonded to the pad (102a) by heating in combination with ultrasonic vibration.

3. A method according to claim 1 or claim 2, wherein the atmosphere temperature is not greater than 200 °C.

decreased by suppressing the hydrogen content in the ball-forming gas to about 3 %, increase in the ball hardness can be prevented and the bondability in the first bonding can be improved.

(2) Since the lowering in the temperature of the ball can be prevented even if a gas is blown to the ball formed by melting, by preheating the ball-forming gas, increase in the hardness of the ball can be prevented coupled with the effect as described in (1) above.

(3) Since the combustion of the escaped reducing gas can be suppressed by setting the hydrogen content in the reducing gas supplied to the lead frame to less than 4 %, reduction in the stability for the bondability due to the change in the bonding conditions accompanying combustion can be prevented, thereby improving the bonding, thus, the quality and the reliability of the products.

(4) Since the use of then copper type wire and the lead frame can be realized by preventing the reduction of the bondability in the copper type wire and the lead frame, reduction in the cost, etc. can be promoted.

(5) Since satisfactory metal bondability can be maintained to ensure adequate bondability, by surely preventing the formation of oxide layers, it is possible to improve the quality and the reliability of the bonding, and thus, the products.

(6) Since the escape of the reducing gas can be minimized by laying the cover on the feeder and opening a window of a least minimum opening surface required for the bonding operation to the cover, the reducing gas can be formed more effectively, while the amount of gas used can be suppressed.

Although the invention made by the present inventors has been described specifically referring to the examples, the present invention is not restricted only to the examples.

For instance, the content of hydrogen in the ball-forming gas (shield gas) is not restricted to about 3% but is may be less than 3 %. Particularly, in a case where the natural oxidation of the wire is completely prevented before the ball formation, a non-oxidative gas containing no hydrogen may be used as the shield gas.

The wire used is not restricted only to the copper type but aluminum or alloy type wire may be used.

The lead frame is not restricted only to the copper type but iron-nickel lead frame, etc. may also be used.

Although the explanation has been made mainly to the case of applying the invention to the wire bonding technic utilizing the press-bonding under heating combined with the ultrasonic vibrations, which is the background art for the present invention, the present invention is no way limited only thereto, but is also applicable to wire bonding of press-bonding system under heating.

The present invention is applicable at least to the wire bonding technics in general, using reducing gas.

Claims

1. A method for fabricating a semiconductor device having a semiconductor pellet (102) at least one bonding pad (102a) on one major surface of the pellet (102) and at least one lead (103) outside the pellet (102), comprising:

(a) placing the pellet (102) and the at least one lead (103) on or over a heat block (107) at a predetermined temperature;

(b) forming a ball (112) on the end of a copper bonding wire (105), the end of the bonding wire (105) projecting from the tip of a bonding capillary (111), the ball (112) being formed by electric discharge between the end of the wire and an electrode (116) in a non-oxidative gas atmosphere;

(c) ball bonding the wire (105) to the bonding pad (102a) by pushing the ball (112) against the pad (102a) with the ball (112) projecting beyond the tip of the capillary (111); and

(d) subsequently bonding the wire (105) to the at least one lead (103);

characterised in that:

in step (b), the ball is formed in a non-oxidative gas atmosphere having an atmosphere temperature of at least 100 °C but lower than the temperature at which the wire (105) sticks to the capillary (111), the gas being supplied at the atmosphere temperature from a nozzle (118) adjacent the end of the wire, and the gas atmosphere being maintained at the atmosphere temperature for a time sufficiently long for the ball (112) to harden.

2. A method according to claim 1, wherein the wire (105) is bonded to the pad (102a) by heating in combination with ultrasonic vibration.

3. A method according to claim 1 or claim 2, wherein the atmosphere temperature is not greater than 200 °C.



4. A method according to any one of claims 1 to 3, wherein the atmosphere temperature is at least 150 °C.
5. A method according to any one of the preceding claims, wherein the non-oxidative gas atmosphere includes a reducing gas.
6. A method according to claim 5, wherein the reducing gas is hydrogen.
7. A method according to claim 6, wherein there is less than 10% hydrogen in the non-oxidative gas atmosphere.
8. A method according to claim 7, wherein there is less than 4% hydrogen in the non-oxidative atmosphere.
9. A method according to any one of claims 6 to 8 wherein, in addition to hydrogen, the non-oxidative gas atmosphere includes nitrogen and/or argon.
10. A method according to any one of the preceding claims wherein the electric discharge is performed with the wire (105) as an anode and the electrode (116) as a cathode.
11. A method according to any one of the preceding claims, wherein a predetermined separation is maintained between the wire (105) and the electrode (116) during the discharge.
12. A method according to any one of the preceding claims, wherein the step (d) includes transferring the capillary (111) to a position adjacent the at least one lead (103) and wedge-bending the wire (105) to the lead (103) with the capillary (111) by pushing the wire (105) against the lead (103).
13. A method according to claim 12, wherein the wire (105) is bonded to the lead (103) by heating in combination with ultrasonic vibration.
14. A method according to claim 11 or claim 12, wherein the wedge bonding occurs in a gas atmosphere adapted to prevent lead oxidation.
15. A method according to claim 14, wherein the composition of the gas atmosphere of the wedge bonding is different from the non-oxidative gas atmosphere of step (b).
16. A method according to claim 14 or claim 15 wherein the gas atmosphere of the wedge bonding contains hydrogen.
17. A method according to any one of the preceding claims, wherein the bonding pad (102a) is of aluminium.
18. A method according to any one of the preceding claims wherein the temperature of the heat block (107) is at least 200 °C.
19. A method according to any one of the preceding claims, wherein the non-oxidative gas atmosphere is supplied from a pair of nozzles (118), one on the opposite side of the wire from the other.
20. A method according to any one of the preceding claims, wherein the copper bonding wire has more than 99.999% copper by weight.

Revendications

1. Procédé de fabrication d'un dispositif à semiconducteurs possédant une puce semiconductrice (102), au moins un plot de liaison (102a) sur une surface principale de la puce (102) et au moins un conducteur (103) à l'extérieur de la puce (102), comportant les étapes consistant à :
 - (a) placer la puce (102) et le au moins un conducteur (103) sur ou au-dessus d'un bloc chauffant (107) à une température prédéterminée ;



(b) former une bille (112) sur l'extrémité d'un fil de liaison en cuivre (105), l'extrémité du fil de liaison (105) faisant saillie de l'extrémité d'un capillaire de liaison (111), la bille (112) étant formée par décharge électrique entre l'extrémité du fil et une électrode (116) sous une atmosphère de gaz non oxydant ;

(c) relier la bille du fil (105) au plot de liaison (102a) en poussant la bille (112) contre le plot (102a) avec la bille (112) faisant saillie au-delà de l'extrémité du capillaire (111) ; et

(d) relier ensuite le fil (105) à le au moins un conducteur (103) ;

caractérisé en ce que :

au cours de l'étape (b), la bille est formée sous une atmosphère de gaz non oxydant possédant une température d'au moins 100 °C mais inférieure à la température à laquelle le fil (105) adhère au capillaire (111), le gaz étant délivré à une température depuis une buse (118) adjacente à l'extrémité du fil, et l'atmosphère de gaz étant maintenue à la température pendant un temps suffisamment long permettant à la bille (112) de durcir.

2. Procédé selon la revendication 1, dans lequel le fil (105) est relié au plot (112a) par chauffage en combinaison avec une vibration ultrasonique.
3. Procédé selon la revendication 1 ou la revendication 2, dans lequel la température de l'atmosphère n'est pas supérieure à 200 °C.
4. Procédé selon l'une quelconque des revendications 1 à 3, dans lequel la température de l'atmosphère est au moins 150 °C.
5. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'atmosphère de gaz non oxydant comprend un gaz réducteur.
6. Procédé selon la revendication 5, dans lequel le gaz réducteur est de l'hydrogène.
7. Procédé selon la revendication 6, dans lequel il existe moins de 10% d'hydrogène dans l'atmosphère de gaz non oxydant.
8. Procédé selon la revendication 6, dans lequel il se trouve moins de 4% d'hydrogène dans l'atmosphère non oxydante.
9. Procédé selon l'une quelconque des revendications 6 à 8, dans lequel, en plus de l'hydrogène, l'atmosphère de gaz non oxydant comprend de l'azote et/ou de l'argon.
10. Procédé selon l'une quelconque des revendications précédentes, dans lequel la décharge électrique est amorcée avec le fil (105) jouant le rôle d'anode et l'électrode (116) celui de cathode.
11. Procédé selon l'une quelconque des revendications précédentes, dans lequel un écart prédéterminé est maintenu entre le fil (105) et l'électrode (116) durant la décharge.
12. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'étape (d) comprend un transfert du capillaire (111) jusqu'en une position adjacente à le au moins un conducteur (103) et une liaison en coin du fil (105) au conducteur (103) avec le capillaire (111) en poussant le fil (105) contre le conducteur (103).
13. Procédé selon la revendication 12, dans lequel le fil (105) est relié au conducteur (103) par chauffage en combinaison avec une vibration ultrasonique.
14. Procédé selon la revendication 11 ou la revendication 12, dans lequel la liaison en coin est effectuée sous une atmosphère gazeuse apte à empêcher une oxydation du conducteur.
15. Procédé selon la revendication 14, dans lequel la composition de l'atmosphère de gaz de la liaison en coin est différente de l'atmosphère de gaz non oxydant de l'étape (b).
16. Procédé selon la revendication 14 ou la revendication 15, dans lequel l'atmosphère gazeuse de la



liaison en coin contient de l'hydrogène.

17. Procédé selon l'une quelconque des revendications précédentes, dans lequel le plot de liaison (102a) est en aluminium.
18. Procédé selon l'une quelconque des revendications précédentes, dans lequel la température du bloc chauffant (107) est d'au moins 200 °C.
19. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'atmosphère de gaz non oxydant est délivrée à partir d'une paire de buses (118), l'une se trouvant sur le côté opposé du fil par rapport à l'autre.
20. Procédé selon l'une quelconque des revendications précédentes, dans lequel le fil de liaison en cuivre possède plus de 99,999% de cuivre en poids.

Patentansprüche

1. Verfahren zur Herstellung einer Halbleitervorrichtung mit einem Halbleiter-Pellet (102), mindestens einem Bonding-Anschluß (102a) auf einer Hauptoberfläche des Pellets (102) und mindestens einer Anschluß-Leitung (103) außerhalb des Pellets (102), umfassend:
 - (a) Platzieren des Pellets (102) und der mindestens einen Anschluß-Leitung (103) auf oder über einem Wärme-Block (107) bei vorbestimmter Temperatur,
 - (b) Bildung einer Kugel (112) am Ende eines Kupfer-Bondingdrahtes (105), das aus der Spitze einer Bonding-Kapillare (111) herausragt, wobei die Kugel (112) durch elektrische Entladung zwischen dem Drahtende und einer Elektrode (116) in einer nicht-oxidierenden Gasatmosphäre gebildet wird,
 - (c) Kugel-Bonden des Drahtes (105) an den Bonding-Anschluß (102a) durch Drücken der Kugel (112) gegen den Anschluß (102a) wobei die Kugel (112) über die Spitze der Kapillare (111) herausragt, und
 - (d) darauffolgend, Bonden des Drahtes (105) an die mindestens eine Anschluß-Leitung (103), dadurch gekennzeichnet, daß
 - in Schritt (b) die Kugel in einer nicht-oxidierenden Gasatmosphäre mit einer niedrigeren Atmosphärentemperatur als der, bei der der Draht (105) an der Kapillare (111) klebt, mindestens jedoch von 100 °C gebildet wird, wobei das Gas von einer neben dem Drahtende liegenden Düse (118) bei der Atmosphärentemperatur geliefert wird, und die Gasatmosphäre über eine zum Härten der Kugel (112) ausreichend lange Zeit auf der Atmosphärentemperatur gehalten wird.
2. Verfahren nach Anspruch 1, wobei der Draht (105) an den Anschluß (102a) durch Erhitzen zusammen mit Ultraschall-Schwingungen gebondet wird.
3. Verfahren nach Anspruch 1 oder 2, wobei die Atmosphärentemperatur nicht größer als 200 °C ist.
4. Verfahren nach einem der Ansprüche 1 bis 3, wobei die Atmosphärentemperatur mindestens 150 °C ist.
5. Verfahren nach einem der vorhergehenden Ansprüche, wobei die nicht-oxidierende Gasatmosphäre ein reduzierendes Gas beinhaltet.
6. Verfahren nach Anspruch 5, wobei das reduzierende Gas Wasserstoff ist.
7. Verfahren nach Anspruch 6, wobei sich weniger als 10% Wasserstoff in der nicht-oxidierenden Gasatmosphäre befinden.
8. Verfahren nach Anspruch 7, wobei sich weniger als 4% Wasserstoff in der nicht-oxidierenden Atmosphäre befinden.
9. Verfahren nach einem der Ansprüche 6 bis 8, wobei die nicht-oxidierende Gasatmosphäre zusätzlich zu Wasserstoff Stickstoff und/oder Argon enthält.



10. Verfahren nach einem der vorhergehenden Ansprüche, wobei die elektrische Entladung mit dem Draht (105) als Anode und der Elektrode (116) als Kathode durchgeführt wird.
- 5 11. Verfahren nach einem der vorhergehenden Ansprüche, wobei während der Entladung eine vorbestimmte Trennung zwischen dem Draht (105) und der Elektrode (116) eingehalten wird.
- 10 12. Verfahren nach einem der vorhergehenden Ansprüche, wobei Schritt (d) das Bringen der Kapillare in eine Position bei der mindestens einen Anschluß-Leitung (103) und das Klemm-Bonden des Drahtes (105) an die Anschluß-Leitung (103) mit der Kapillare (111) durch Drücken des Drahtes (105) gegen die Anschluß-Leitung (103) umfaßt.
13. Verfahren nach Anspruch 12, wobei der Draht (105) durch Erhitzen in Verbindung mit Ultraschall-Schwingungen an die Anschluß-Leitung (103) gebondet wird.
- 15 14. Verfahren nach Anspruch 11 oder 12, wobei das Klemm-Bonden in einer zur Vermeidung der Oxidation der Anschluß-Leitung angepaßten Gasatmosphäre stattfindet.
- 20 15. Verfahren nach Anspruch 14, wobei die Zusammensetzung der Gas-Atmosphäre des Klemm-Bondens von der nicht-oxidierenden Gasatmosphäre des Schrittes (b) verschieden ist.
- 25 16. Verfahren nach Anspruch 14 oder 15, wobei die Gasatmosphäre des Klemm-Bondens Wasserstoff enthält.
17. Verfahren nach einem der vorhergehenden Ansprüche, wobei der Bonding-Anschluß (102a) aus Aluminium besteht.
18. Verfahren nach einem der vorhergehenden Ansprüche, wobei die Temperatur des Wärme-Blockes (107) mindestens 200° C beträgt.
- 30 19. Verfahren nach einem der vorhergehenden Ansprüche, wobei die nicht-oxidierende Gasatmosphäre von einem Paar von an einander gegenüberliegenden Seiten des Drahtes angeordneten Düsen (118) geliefert wird.
- 35 20. Verfahren nach einem der vorhergehenden Ansprüche, wobei der Kupfer-Bondingdraht mehr als 99.999 Gew.-% Kupfer aufweist.

