

DESCRIPTION

PROCESS FOR PRODUCING ALKYLATED AROMATIC COMPOUNDS AND PROCESS
FOR PRODUCING PHENOL

5

TECHNICAL FIELD

[0001]

The present invention relates to processes for producing
alkylated aromatic compounds and processes for producing
10 phenol.

BACKGROUND ART

[0002]

The cumene process in which phenol is produced from cumene
15 as a starting material is known. The cumene process gives
by-product acetone in an equimolar amount to the phenol produced.
The by-product acetone has a wide range of applications as
solvent or organic synthesis material. However, depending on
market trends which differ at different times, the acetone
20 by-produced is in excess or the market conditions thereof are
adverse, thereby lowering economic efficiency of phenol. The
cumene is usually produced by alkylating benzene with propylene.
The propylene is manufactured by thermal cracking of naphtha.
Depending on the demand balance between propylene and ethylene

which is another product by the naphtha cracking, propylene shortage is often brought about which is a bottleneck in the production for cumene.

[0003]

5 To avoid the bottleneck, Patent Literature 1 discloses a process in which acetone by-produced in the phenol production is hydrogenated to isopropanol, the isopropanol is dehydrated to propylene, and the propylene is recycled as a material in the cumene production or the like. However, the hydrogenation
10 and the dehydration add two steps.

[0004]

 To reduce steps, Patent Literatures 2 to 4 disclose methods in which isopropanol from the hydrogenation of acetone is directly used as an alkylating agent without dehydration
15 and is reacted with benzene to give cumene. Patent Literature 4 discloses that the process involves a trickle-bed reactor, but is silent on the flow rate of gas.

Citation List

20 Patent Literature

[0005]

Patent Literature 1: JP-A-H02-174737

Patent Literature 2: JP-A-H02-231442

Patent Literature 3: JP-A-H11-35497

Patent Literature 4: JP-A-2003-523985

SUMMARY OF INVENTION

Technical Problem

5 [0006]

When an alcohol is used as an alkylating agent in the production of alkylated aromatic compounds, the reaction forms an equivalent amount of water to the alkylating agent that has reacted. As known in the art, the water poisons solid acid
10 catalysts which are the alkylation catalysts. It is therefore expected that the catalytic activity and the catalyst life are lowered compared to conventional processes using olefins as the alkylating agents. Accordingly, larger amounts of catalysts are required, and the throughput of the aromatic
15 compound (benzene) and alcohol (isopropanol) per catalyst weight, in detail the liquid weight hourly space velocity (WHSV), is lowered. To cope with these problems, the reactor size should be excessively large, increasing equipment costs.

[0007]

20 Such disadvantages should be solved in the industrial production of alkylated aromatic compounds using alcohols as alkylating agents.

[0008]

It is an object of the present invention to provide an

efficient process for producing alkylated aromatic compounds such as cumene by reacting raw materials including an aromatic compound and an alcohol in the presence of a solid acid catalyst in a compact reactor. It is another object of the invention
5 to provide a process for producing phenol which includes a step of producing cumene by the above alkylation process.

Solution to Problem

[0009]

10 The present inventors studied diligently to solve the aforementioned problems. They have then found that aromatic compounds may be alkylated with an alkylating agent alcohol such as isopropanol in a fixed-bed reactor packed with a solid acid catalyst as an alkylation catalyst with very high
15 conversion of the alkylating agent and very high cumene selectivity by passing gas through the reactor.

[0010]

In detail, the present invention is concerned with processes for producing alkylated aromatic compounds and
20 processes for producing phenol as described in (1) to (7) below.

[0011]

(1) A process for producing alkylated aromatic compounds comprising feeding raw materials including an aromatic compound and an alcohol in a gas-liquid downward concurrent

flow mode to a fixed-bed reactor packed with a solid acid catalyst thereby to produce an alkylated aromatic compound, wherein

the raw materials are fed to the reactor in a stream of
5 a gas, and

the reaction gas flow rate defined by Equation (1) below is not less than 0.05 at an entrance of a solid acid catalyst layer:

[0012]

10
$$\rho_g \cdot u_g \cdot [\rho_{air} \cdot \rho_{water} / (\rho_g \cdot \rho_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}\text{)} \cdots (1)$$

wherein ρ_g is the density of the reaction gas, ρ_l is the density of the reaction liquid, ρ_{air} is the gas density of air, ρ_{water} is the gas density of water, and u_g is the superficial velocity of the reaction gas.

15 (2) The process for producing alkylated aromatic compounds as described in (1), wherein the flow state in the reactor is in a trickle-bed zone.

[0013]

(3) The process for producing alkylated aromatic
20 compounds as described in (1) or (2), wherein the gas is at least one gas selected from the group consisting of nitrogen, hydrogen and rare gases.

[0014]

(4) The process for producing alkylated aromatic

compounds as described in any one of (1) to (3), wherein the solid acid catalyst is zeolite.

[0015]

(5) The process for producing alkylated aromatic compounds as described in (4), wherein the zeolite has a ten to twelve-membered ring structure.

[0016]

(6) The process for producing alkylated aromatic compounds as described in any one of (1) to (5), wherein the aromatic compound is benzene and the alcohol is isopropanol.

[0017]

(7) A process for producing phenol, comprising the step (a) to the step (e) described below wherein the step (d) is performed according to the process for producing alkylated aromatic compounds described in (6);

step (a): a step of oxidizing cumene into cumene hydroperoxide;

step (b): a step of acid decomposing the cumene hydroperoxide to obtain phenol and acetone;

step (c): a step of hydrogenating the acetone from the step (b) to isopropanol;

step (d): a step of reacting the isopropanol from the step (c) with benzene to synthesize cumene; and

step (e): a step of circulating the cumene from the step

(d) to the step (a).

Advantageous Effects of Invention

[0018]

5 According to the processes for producing alkylated aromatic compounds of the present invention, an alcohol such as isopropanol and an aromatic compound such as benzene (raw materials) are fed to a reactor in a stream of a gas, and thereby alkylated aromatic compounds such as cumene can be produced
10 in a higher yield than achieved heretofore with industrial and practical advantages.

[0019]

 The processes for producing phenol according to the invention have adopted the above process of producing alkylated
15 aromatic compounds, and thereby acetone that is by-produced in the phenol production can be reused.

Brief Description of Drawing

[0020]

20 Fig. 1 is a plot diagram in which flow states in Examples and Comparative Example are plotted in a diagram showing flow zones in gas-liquid downward concurrent packed layers that is described in "Shokubai Kouza (Catalyst Courses) Vol. 6, (Engineering Part 2), Shokubai Hannou Souchi to Sono Sekkei

(Catalyst reaction apparatus and its design)", Catalysts Society of Japan, Kodansha Ltd., December 1985, first impression, p. 182.

5 DESCRIPTION OF EMBODIMENTS

[0021]

In a process for producing alkylated aromatic compounds according to the invention, raw materials including an aromatic compound and an alcohol are fed in a gas-liquid downward
10 concurrent flow mode to a fixed-bed reactor packed with a solid acid catalyst thereby to produce an alkylated aromatic compound. The raw materials are fed to the reactor under a stream of a gas. The reaction gas flow rate defined by Equation (1) below is not less than 0.05 at an entrance of a solid acid catalyst
15 layer:

[0022]

$$p_g \cdot u_g \cdot [p_{air} \cdot p_{water} / (p_g \cdot p_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}\text{)} \dots (1)$$

wherein p_g is the density of the reaction gas, p_l is the density of the reaction liquid, p_{air} is the gas density of air,
20 p_{water} is the gas density of water, and u_g is the superficial velocity of the reaction gas.

The solid acid catalyst layer is a catalyst layer formed by loading the solid acid catalyst in the fixed-bed reactor.

[0023]

The reaction in the process for producing alkylated aromatic compounds according to the invention is the alkylation of an aromatic compound with an alcohol in the presence of a solid acid catalyst, and is a liquid solid two phase reaction.

5 According to the finding by the present inventors, the reaction results of the alkylation are drastically improved by feeding the raw materials to the reactor under a stream of a gas.

[0024]

Flow zones in gas-liquid downward concurrent flow mode
10 are shown in Fig. 1. The flow zone diagram is based on data obtained with an air-water system. Flow zones with other systems may be prepared in consideration of correction terms based on differing physical properties ("Shokubai Kouza (Catalyst Courses) Vol. 6, (Engineering Part 2), Shokubai
15 Hannou Souchi to Sono Sekkei (Catalyst reaction apparatus and its design)", Catalysts Society of Japan, Kodansha Ltd., December 1985, first impression, p. 182). The shaded parts in Fig. 1 indicate ranges where boundaries exist. The x-axis and y-axis in the diagram are defined as follows.

20 [0025]

x-axis: $\rho_l \cdot u_l \cdot [(\sigma_{\text{water}}/\sigma)(\rho_{\text{water}}/\rho_l)^2]^{1/3}$ ($\text{kgm}^{-2}\text{s}^{-1}$)

y-axis: $\rho_g \cdot u_g \cdot [\rho_{\text{air}} \cdot \rho_{\text{water}}/(\rho_g \cdot \rho_l)]^{1/2}$ ($\text{kgm}^{-2}\text{s}^{-1}$)

Here, ρ_l , ρ_g , ρ_{air} and ρ_{water} are the density of the reaction liquid, the density of the reaction gas, the gas

density of air and the gas density of water, respectively, σ and σ_{water} respectively indicate the surface tension of the reaction liquid and the surface tension of water, and u_l and u_g are the superficial velocity of the reaction liquid and that
5 of the reaction gas, respectively.

[0026]

In the invention, the reaction gas refers to a gas phase component in the reactor. That is, the reaction gas includes all components existing in the form of gas, in detail the gas
10 used to feed the raw materials in a gas-liquid downward concurrent flow mode, evaporated aromatic compound and alcohol, and evaporated alkylated aromatic compound and water. In the invention, the reaction liquid refers to a liquid phase component in the reactor. That is, the reaction liquid
15 includes all components existing in the form of liquid, in detail aromatic compound and alcohol fed as raw materials, gas dissolved in the liquid phase, and alkylated aromatic compound and water.

[0027]

20 In the invention, the flow state in the reactor is preferably in a trickle-bed zone (perfusate flow). In the trickle-bed zone, the liquid trickles over the outer surface of the catalyst and part thereof is attached to narrow pores in the catalyst. In either case, the liquid is scattered as

individual masses forming a dispersed phase. Meanwhile, the gas surrounds the catalyst and the liquid, forming a continuous phase.

[0028]

5 When the flow state in the reactor is in a trickle-bed zone, the concentration distribution in the system is uniform and mild operation is possible, the facility does not have to be high-pressure resistant, the physical load on the catalyst is lowered, and catalyst damage is prevented as described in
10 JP-A-H11-116523.

[0029]

In the invention, the reaction gas flow rate defined by Equation (1) below is not less than 0.05 at an entrance of the solid acid catalyst layer.

15 [0030]

$$p_g \cdot u_g \cdot [p_{air} \cdot p_{water} / (p_g \cdot p_l)]^{1/2} \quad (\text{kgm}^{-2}\text{s}^{-1}) \quad \dots (1)$$

wherein p_g is the density of the reaction gas, p_l is the density of the reaction liquid, p_{air} is the gas density of air, p_{water} is the gas density of water, and u_g is the superficial
20 velocity of the reaction gas.

Equation (1) above corresponds to the y-axis in the flow zone diagram in Fig. 1. When the reaction gas flow rate defined by Equation (1) is 0.05 or above, high cumene selectivity is achieved. The reaction gas flow rate is more preferably in the

range of 0.08 to 0.6.

[0031]

In Fig. 1, the x-axis indicates the flow rate of the reaction liquid (the liquid phase component in the reactor), represented by Equation (2) below. The reaction liquid flow rate represented by Equation (2) has been found less influential to the efficiency and results of the production of alkylated aromatic compounds by the processes according to the present invention, compared to the reaction gas flow rate expressed by Equation (1).

$$\rho_l \cdot u_l \cdot [(\sigma_{\text{water}}/\sigma) (\rho_{\text{water}}/\rho_l)^2]^{1/3} \text{ (kgm}^{-2}\text{s}^{-1}) \dots (2)$$

wherein ρ_l is the density of the reaction liquid, ρ_{water} is the gas density of water, σ is the surface tension of the reaction liquid, σ_{water} is the surface tension of water, and u_l is the superficial velocity of the reaction liquid.

As described hereinabove, it is preferable in the processes for producing alkylated aromatic compounds that the flow state in the reactor is in a trickle-bed zone. The flow rate of the reaction liquid does not adversely affect the processes of the invention as long as the flow state is in a trickle-bed zone.

[0032]

Examples of the aromatic compounds used in the processes for producing alkylated aromatic compounds include benzene and

naphthalene, with benzene being preferred. Examples of the alcohols include isopropanol and 2-butanol, with isopropanol being preferred.

[0033]

5 That is, in a preferred embodiment of the processes for producing alkylated aromatic compounds of the invention, the aromatic compound is benzene and the alcohol is isopropanol, and the alkylated aromatic compound obtained in this case is cumene.

10 [0034]

In the invention, at least one gas selected from the group consisting of nitrogen, hydrogen and rare gases is used.

[0035]

15 The solid acid catalysts used in the invention are catalysts that function as acids. Examples of the solid acid catalysts include usual solid acids such as zeolite, silica alumina, alumina, sulfate-promoted zirconia and WO_3 -promoted zirconia.

[0036]

20 In particular, the zeolites that are inorganic crystalline porous compounds composed of silicon and aluminum are suitable solid acid catalysts from the viewpoints of heat resistance and selectivity for the target alkylated aromatic compounds (such as cumene).

[0037]

For the production of cumene as the alkylated aromatic compound, a zeolite is preferably used which has a ten to twelve-membered ring structure having a pore similar in size
5 to the molecular diameter of cumene.

[0038]

Examples of the zeolites having a twelve-membered ring structure include Y-type zeolite, USY-type zeolite, mordenite type zeolite, dealuminated mordenite type zeolite, β -zeolite,
10 MCM-22-type zeolite and MCM-56-type zeolite. In particular, β -zeolite, MCM-22-type zeolite and MCM-56-type zeolite have suitable structures.

[0039]

In the zeolites, the composition ratio between silicon
15 and aluminum may be suitably in the range of 2/1 to 200/1, and in view of activity and heat stability, preferably in the range of 5/1 to 100/1. Further, isomorphously substituted zeolites may be used in which aluminum atoms in the zeolite skeleton are substituted with other metal such as Ga, Ti, Fe, Mn or B.

20 [0040]

The shape of the solid acid catalysts is not particularly limited, and the solid acid catalysts may be in the form of sphere, cylindrical column, extrudate or crushed pieces. The size of the particles of the solid acid catalysts may be selected

in the range of 0.01 mm to 100 mm depending on the size of a reactor.

[0041]

To achieve high productivity, the supply rate for the raw materials in the invention, in detail the liquid weight hourly space velocity (WHSV) relative to the catalyst weight is preferably not more than 50, more preferably not more than 20, and still more preferably not more than 10. The liquid weight hourly space velocity (WHSV) is usually not less than 1.

10 [0042]

The above supply rate ensures that cumene is produced in a high yield.

[0043]

Theoretically, the aromatic compound may be used at least in an equimolar amount relative to the alcohol. From the viewpoints of separation and recovery, the aromatic compound may be preferably used in an equimolar to ten-fold molar amount, and more preferably in an equimolar to five-fold molar amount relative to the alcohol.

20 [0044]

From the viewpoints of separation and recovery, the gas in the invention may be preferably used in an equimolar to twenty-fold molar amount, and more preferably in an equimolar to ten-fold molar amount relative to the alcohol.

[0045]

In the processes for producing alkylated aromatic compounds, the raw materials are fed to a fixed bed reactor in a gas-liquid downward concurrent flow mode. The reaction
5 temperature in the reactor is in the range of 100 to 300°C, and preferably 120 to 250°C. The reaction pressure is in the range of 0.5 to 10 MPaG, and preferably 2 to 5 MPaG.

[0046]

A process for producing phenol according to the present
10 invention includes the step (a) to the step (e) described below wherein the step (d) is performed according to the process for producing alkylated aromatic compounds described hereinabove. In the process for producing alkylated aromatic compounds which is performed as the step (d) in the phenol production process,
15 the aromatic compound is benzene and the alcohol is isopropanol.

Step (a): a step of oxidizing cumene into cumene hydroperoxide;

Step (b): a step of acid decomposing the cumene hydroperoxide to obtain phenol and acetone;

20 Step (c): a step of hydrogenating the acetone from the step (b) to isopropanol;

Step (d): a step of reacting the isopropanol from the step (c) with benzene to synthesize cumene; and

Step (e): a step of circulating the cumene from the step

(d) to the step (a).

In the process for producing phenol, phenol is formed from cumene in the steps (a) and (b), the by-product acetone is hydrogenated in the step (c) to isopropanol, the isopropanol
5 is reacted in the step (d) to form cumene, and the cumene formed in the step (d) is recycled in the step (e) back to the step (a). Accordingly, it is theoretically not necessary that acetone should be fed from the outside of the reaction system, achieving cost advantages. In practical plants, it is
10 difficult to recover 100% acetone and therefore at least an amount of acetone corresponding to the decrease is newly fed to the reaction system.

[0047]

Various modifications and improvements may be made to the
15 processes for producing phenol according to the invention.

EXAMPLES

[0048]

The present invention will be described by presenting
20 examples but the invention is not limited to such examples as long as within the scope of the invention.

[0049]

[Example 1]

A catalyst test was carried out in which cumene was

produced from isopropanol and benzene as raw materials.

[0050]

β -zeolite catalyst (pellets 1.5 mm in diameter, manufactured by TOSOH CORPORATION) weighing 2435 g was loaded
5 in a stainless steel vertical reaction tube 38.4 mm in inner diameter and 4800 mm in length. After the loading, isopropanol was supplied from the top of the reactor at 24 L/h and the catalyst was washed for 1 hour.

[0051]

10 While the reactor pressure was maintained at 3 MPaG and the preheating temperature at 175°C, benzene: 8.1 L/h, isopropanol: 0.65 L/h and hydrogen: 1900 NL/h were supplied from the top of the reactor to perform reaction. The liquid weight hourly space velocity (WHSV) under these conditions was
15 3.0. A mixture of the reaction liquid and gas that was discharged from the reactor bottom was separated in a gas-liquid separation tank, and the oil phase and the aqueous phase were separated in an oil-water separation tank. When the reaction had been continuously carried out for 12 hours, the reaction
20 liquid and the waste gas were each analyzed by gas chromatography. The gas chromatography showed that the isopropanol conversion was 100% and the cumene selectivity was high at 92.8%.

[0052]

Separately, a flow zone under the above conditions was studied. The reaction gas flow rate at the entrance of the solid acid catalyst layer (the alkylation catalyst layer) was calculated using the PSRK equation (Kagaku Kougaku Binran
5 (Chemical Engineering Handbook), revised 6th edition, edited by The Society for Chemical Engineers, Japan.) as an estimation equation which had been corrected by regressing literature data including solubility data of hydrogen in benzene and cumene (Ipatieff V., Oil Gas J. 32, 14-15, (1993) and Sokolov V., J.
10 Appl. Chem. USSR, 50(6), 1347-1349, (1977)), solubility data of benzene and cumene in water (Thompson W. H., J. Chem. Eng. Data, 9(4), 516-520, (1964) and Englin B. A., Khim. Tekhnol. Topl. Masel, 10(9), 42-46, (1965)) and benzene/water azeotropic data (Burd S. D., Proc. Am. Petrol. Inst. Ref. Div.,
15 48, 464-476, (1968)).

[0053]

Properties were estimated by inputting the above estimation equation and reaction conditions in Examples in a stationary process simulator (manufactured by Aspen Tech Japan
20 Co., Ltd.). The results are set forth in Table 1.

[0054]

In Example 1, the flow state was in a trickle-bed zone and the reaction gas flow rate was 0.280.

[0055]

$$\text{x-axis: } \rho_l \cdot u_l \cdot [(\sigma_{\text{water}}/\sigma) (\rho_{\text{water}}/\rho_l)^2]^{1/3} \text{ (kgm}^{-2}\text{s}^{-1}) = 2.263$$

$$\text{y-axis: } \rho_g \cdot u_g \cdot [\rho_{\text{air}} \cdot \rho_{\text{water}} / (\rho_g \cdot \rho_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}) = 0.280$$

[Example 2]

5 A catalyst test was carried out with the same experimental apparatus and under the same reaction conditions as in Example 1; except that the hydrogen was fed at 500 NL/h. The isopropanol conversion was 100% and the cumene selectivity was high at 86.9%.

10 [0056]

In Example 2, the flow state was in a trickle-bed zone and the reaction gas flow rate was 0.075.

[0057]

$$\text{x-axis: } \rho_l \cdot u_l \cdot [(\sigma_{\text{water}}/\sigma) (\rho_{\text{water}}/\rho_l)^2]^{1/3} \text{ (kgm}^{-2}\text{s}^{-1}) = 4.269$$

15

$$\text{y-axis: } \rho_g \cdot u_g \cdot [\rho_{\text{air}} \cdot \rho_{\text{water}} / (\rho_g \cdot \rho_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}) = 0.075$$

[Comparative Example 1]

A catalyst test was carried out with the same experimental apparatus and under the same reaction conditions as in Example 1, except that the hydrogen was fed at 190 NL/h. The isopropanol conversion was 50.5% and the cumene selectivity was low at 42.6%. Further, large amounts of by-product propane and propylene were produced.

20

[0058]

In Comparative Example 1, the flow state was in a trickle-bed zone, but the reaction gas flow rate was 0.026.

[0059]

$$\text{x-axis: } \rho_l \cdot u_l \cdot [(\sigma_{\text{water}}/\sigma) (\rho_{\text{water}}/\rho_l)^2]^{1/3} \text{ (kgm}^{-2}\text{s}^{-1}) =$$

5 4.771

$$\text{y-axis: } p_g \cdot u_g \cdot [p_{\text{air}} \cdot p_{\text{water}} / (p_g \cdot p_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}) = 0.026$$

[0060]

[Table 1]

Table 1

Properties at entrance of zeolite layer		Ex. 1		Ex. 2		Comp. Ex. 1	
		Liquid phase component	Gas phase component	Liquid phase component	Gas phase component	Liquid phase component	Gas phase component
Surface tension	dyne/cm	9.770	-	9.716	-	9.693	-
Viscosity	CP	0.143	0.017	0.143	0.016	0.142	0.016
Density	kg/m ³	615.247	27.196	607.994	28.817	604.981	29.430
Flow rate	kg/h	3.501	4.358	6.540	1.192	7.280	0.424
Superficial velocity	kg/m ² ·s	0.840	1.046	1.569	0.286	1.747	0.102
x-axis (Eq. 2)	kg/m ² ·s	2.263		4.269		4.771	
y-axis (Eq. 1)	kg/m ² ·s	0.280		0.075		0.026	

Reference Signs List

[0061]

- 1 ... perfusate flow
- 2 ... mist flow
- 5 3 ... pulsating flow
- 4 ... bubble flow

CLAIMS

1. A process for producing alkylated aromatic
5 compounds comprising feeding raw materials including an
aromatic compound and an alcohol in a gas-liquid downward
concurrent flow mode to a fixed-bed reactor packed with a solid
acid catalyst thereby to produce an alkylated aromatic compound,
wherein

10 the raw materials are fed to the reactor in a stream of
a gas, and

the reaction gas flow rate defined by Equation (1) below
is not less than 0.05 at an entrance of a solid acid catalyst
layer:

15
$$p_g \cdot u_g \cdot [p_{air} \cdot p_{water} / (p_g \cdot \rho_l)]^{1/2} \text{ (kgm}^{-2}\text{s}^{-1}) \dots (1)$$

wherein p_g is the density of the reaction gas, ρ_l is the
density of the reaction liquid, p_{air} is the gas density of air,
 p_{water} is the gas density of water, and u_g is the superficial
velocity of the reaction gas.

20 2. The process for producing alkylated aromatic
compounds according to claim 1, wherein the flow state in the
reactor is in a trickle-bed zone.

3. The process for producing alkylated aromatic compounds according to claim 1 or 2, wherein the gas is at least one gas selected from the group consisting of nitrogen, hydrogen and rare gases.

5

4. The process for producing alkylated aromatic compounds according to any one of claims 1 to 3, wherein the solid acid catalyst is zeolite.

10

5. The process for producing alkylated aromatic compounds according to claim 4, wherein the zeolite has a ten to twelve-membered ring structure.

15

6. The process for producing alkylated aromatic compounds according to any one of claims 1 to 5, wherein the aromatic compound is benzene and the alcohol is isopropanol.

20

7. A process for producing phenol, comprising the step (a) to the step (e) described below wherein the step (d) is performed according to the process for producing alkylated aromatic compounds described in claim 6;

step (a): a step of oxidizing cumene into cumene hydroperoxide;

step (b): a step of acid decomposing the cumene

hydroperoxide to obtain phenol and acetone;

step (c): a step of hydrogenating the acetone from the step (b) to isopropanol;

step (d): a step of reacting the isopropanol from the step
5 (c) with benzene to synthesize cumene; and

step (e): a step of circulating the cumene from the step (d) to the step (a).