

- 1 -

“HIGH PRESSURE DISCHARGE LAMP CONTAINING A GETTER
DEVICE”

5 The present invention relates to a high pressure discharge lamp, particularly of small dimensions, containing a getter device.

High pressure discharge lamps (also known as high intensity discharge lamps) are lamps in which the light emission is due to the electric discharge that is established in a gaseous medium comprising a noble gas (generally argon, with the possible addition of minor amounts of other noble gases) and vapors of different metals according to the kind of lamp.

10 These lamps are classified according to the means in which the discharge takes place. A first type are the sodium high pressure lamps, wherein the discharge means is a mixture of sodium and mercury vapors (obtained through vaporization of an amalgam of the two metals) and wherein, in operation, the vapors can reach pressures of about 10^5 Pascal (Pa) and temperatures higher than 800 °C; a second type are the mercury high pressure lamps (discharge in mercury vapors) wherein the vapors can reach pressures of about 10^6 Pa and temperatures of about 600-700 °C; finally, a third type of high pressure discharge lamps are metal halides lamps, wherein the discharge means is a plasma of atoms and/or ions created by the dissociation of sodium, thallium, indium, scandium or Rare Earths iodides (generally, each lamp contains at least two or more of these iodides), in addition to mercury vapors; in this case, with a lamp being turned on, pressures of 10^5 Pa can be reached in the burner and temperatures of about 700 °C in the coolest point of the lamp.

25 In Fig. 1 a generic high pressure discharge lamp, of the type wherein the electric connectors are on one side only of the lamp, is shown in a sectional view; although in the rest of the description reference is always made to this type of lamps, the invention can be also applied in the so-called “double-ended lamps”, wherein there are electric contacts on both ends of the lamp. The lamp, L, is formed of an external bulb, C, generally glass made, inside which the so-called burner, B, is provided formed of a generally spherical or cylindrical container of

30

- 2 -

quartz or translucent alumina; two electrodes E are present at two burner ends, and a noble gas added with a metal or a metal compound in vapor form (or vaporizable with the lamp turned on), V, is provided inside thereof, the mixture of noble gas and said vapor being the means in which the discharge occurs; as
5 known in the field, an end A of the bulb, and two ends Z of the burner are sealed by heat compression. The burner is kept in place by two supporting metal parts, M, through metal feedthroughs R, these latter being fixed in parts Z by sealing through heat compression these latter around said feedthroughs; the combination of the two parts M and R has also the function of electrically connecting the
10 electrodes E to the contacts P external to the lamp. The space S enclosed in the bulb can be evacuated or filled with inert gases (normally nitrogen, argon or mixtures thereof); the bulb has the purpose of mechanically protecting the burner, thermally insulating this from the outside and, above all, of keeping an optimal chemical environment outside the burner. Despite the provision of a particular
15 atmosphere in the bulb, traces of impurities are always present in the lamp, for instance as a consequence of the manufacturing operations of the lamps, coming from outgassing or decomposition of components of the lamps or due to permeation from the external atmosphere. These impurities need to be removed, as they can alter the optimal lamp operation according to various mechanisms.
20 Oxidizing gases possibly present outside the burner, due to the temperatures reached in the vicinity thereof, could damage the metal parts being present (parts M or R). Hydrogen, if present in the bulb, can easily permeate through the burner walls at the operating temperatures of these lamps, and once in the burner it has the effect of enhancing the potential difference between the electrodes E required
25 for establishing and maintaining the discharge, thereby increasing the lamp power consumption; in addition, this raise of potential difference causes a raise in the electrodes "sputtering" phenomenon, consisting in the erosion thereof due to the impact of the ions present in the discharge, with consequent formation of dark metallic deposits on the burner internal walls and decrease of the lamp brightness;
30 for these reasons, hydrogen is commonly considered the most noxious impurity in lamp bulbs.

- 3 -

To remove these impurities, it is known to insert in the bulb, outside the burner, a getter material capable of chemically fixing them. The getter materials are generally metals like titanium, zirconium, or alloys thereof with one or more transition elements, aluminum or Rare-Earths. Getter materials suitable for the use
5 in lamps are described, for example, in patents US 3,203,901 (zirconium-aluminum alloys), US 4,306,887 (zirconium-iron alloys) and US 5,961,750 (zirconium-cobalt-Rare Earths alloys). For the sorption of hydrogen, particularly at high temperatures, the use of yttrium or alloys thereof is also known, as described, for example, in patent GB 1,248,184 and in the international patent
10 application WO 03/029502. Getter materials can be inserted in the lamps in the form of devices formed of the material only (for example, a sinterized getter powders pellet), but more commonly these devices comprise a support or metallic container for the material. In Fig. 1 is shown a getter device, C, typically used in lamps, formed of a thin metal plate on which a pellet of getter material powders is
15 fixed; the drawing also shows a very common way of getter assembling to the internal structure of the lamp, in the so-called "flag" position. An example of a lamp containing a getter in the bulb is disclosed in the international patent application WO 02/089174.

However, the known mountings of getter devices inside lamp bulbs have the
20 drawback of causing a "shadow" effect, shielding the light coming from the burner for a solid angle depending on dimension of the getter device, its closeness to the burner, and its orientation with respect to the burner; this effect is undesired by lamps manufacturers, as it reduces by some percent units the overall lamp brightness. The shadow effect is a felt problem with conventional high pressure
25 discharge lamps, which have relatively large dimensions (the bulb generally has a length greater than 10 cm); it becomes much worse in high pressure discharge lamps of recent development which have sensibly reduced dimensions, for example with bulbs having an external diameter of about 2 cm or less and length of less than 7 cm (in the remaining part of the text, high pressure discharge lamps
30 with these dimensions will be referred to as miniaturized lamps). With such reduced dimensions, positioning the getter device inside the bulb presents a

- 4 -

number of problems. In first place there is a direct effect: a bulb of reduced dimensions forces to position the getter device closer to the burner compared to bigger dimension lamps, so that, with the same dimensions of the getter device, the shadow effect is increased. In second place, there is an indirect effect linked to
5 the fact that the sorption of hydrogen by getter materials is (contrary to all other common impurities), an equilibrium phenomenon: the higher is the temperature, the higher is the pressure of gaseous hydrogen in equilibrium with the getter. With miniaturized lamps, any bulb location is at relatively high temperature and as a consequence, in order to guarantee sufficiently low pressures of gaseous hydrogen
10 in the bulb, it would be necessary to increase the amount of getter material and thus the dimensions of the getter device; this increase in dimensions and the above mentioned need to place the device close to the burner concur to increase the shadow projected by the getter device.

Object of the present invention is to provide high pressure discharge lamps,
15 and particularly miniaturized ones, which solve the above mentioned problems.

According to the present invention, this object is achieved with a high pressure discharge lamp containing a getter device, characterized in that the getter device is:

- filiform, fixed to one of the metal parts supporting the burner, and in such
20 a position to be parallel to said metal part and essentially hidden to the burner by said metal part; or
- attached to at least one feedthrough for the electrical feeding of the burner; or
- in the form of a hollow filiform body filled with getter material, which
25 forms fully or in part the burner supporting metal part, extending itself between the two heads of the lamp.

The invention will be described in the following with reference to the drawings wherein:

- Figure 1 has already been illustrated in the introduction;
- 30 - Figure 2 shows in cross-section a first embodiment of lamp of the invention;

- 5 -

- Figures 3 and 4 show two possible getter devices to be used in the lamp of Fig. 2;
- Figure 5 shows in cross-section a second embodiment of lamp of the invention;
- 5 - Figure 6 shows a getter device to be used in a lamp of Fig. 5;
- Figure 7 shows in cross-section another embodiment of lamp of the invention;
- Figure 8 shows a getter device to be used in a lamp of Fig. 7;
- Figure 9 shows in cross-section another embodiment of lamp of the invention;
- 10 - Fig. 10 shows a getter device for use in a lamp of Fig. 9;
- Fig. 11 shows in cross-section a further embodiment of lamp of the invention; and
- Fig. 12 shows in cross-section a last embodiment of lamp of the invention.
- 15

A first embodiment of lamp of the invention is illustrated in Fig. 2, also with reference to Figs. 3 and 4. The lamp, 20, comprises a supporting metal part 21 on which a filiform getter device 22 is fixed. Device 22 is of a width similar to, and preferably not greater than, the cross-section of part 21, and is fixed on this part (for example, by two welding points, 23 and 23') in such a way that, when viewed along the lamp axis, its projection is essentially fully included in the supporting part 21 on which it is fixed; with this assembling, the getter device 22 results "hidden" to the burner, and does not increase the shadow effect due to part 21, which is unavoidable.

25 Getter devices suitable for the use in the lamp of Fig. 2 are shown in Figs. 3 and 4.

Device 22' (Fig. 3) is formed of a generally metallic housing 30 extended and open at the ends; inside housing 30 a getter material 31 is present in powder form; the device shown in the drawing has a false-square cross-section, but obviously other sections are also possible, such as circular, square or rectangular. The device of Fig. 3 can be obtained by passing a tube of a greater cross-section

30

- 6 -

area filled with getter powders through a series of compression rollers, according to the process described in the international patent application WO 01/67479 in the name of the applicant (even though this application refers to the production of mercury dispensers). With this process devices of type 22' with a width of about
5 0.8 mm have been produced, and it is possible to further reduce these dimensions, to at least about 0.6 mm.

Device 22'' (Fig. 4) is formed of a generally metallic housing 40, containing getter material powders 41; the housing 40 is formed of a shaped thin metal plate, thus obtaining an essentially closed cross-section (a trapezoidal cross-section is
10 shown in the drawing); between the two edges 42 and 42' of the thin plate forming the housing a slit 43 is left, which provides a further path for the access of gases towards the getter material 41 (in addition to the openings at the ends of the device). This device can be manufactured through the process described in the international patent application WO 98/53479 (in this case too the application
15 refers to the mercury dispensers production, but the process can be used for the production of getter devices in the same way); with this process devices with such a cross-section that the trapezium largest side is about 0.75 mm long and the height is about 0.6 mm have been obtained.

The housing of devices 22' and 22'' is generally made of nickel, nickel-plated iron, stainless steel; it is also possible to use niobium or tantalum which, although more expensive, have the advantage of being less susceptible to vaporization with respect to the above mentioned materials, and can thereby be more freely positioned inside the lamp, even in positions closer to the burner, without the risk of dark deposits formation on the lamp walls due to the metallic
25 vapors condensation thereon. Niobium and tantalum have also the advantage of being easily permeable to hydrogen, especially at high temperatures, so that in this case the sorption of this gas by the getter material takes place not only at the ends of the device and possibly through the slit 43, but rather through the whole surface of the device.

30 The lamp according to the second embodiment of the invention has the getter device attached to at least one and preferably both feedthroughs for the

- 7 -

electrical feeding of the burner; the use of two getter devices, one on each feedthrough, has the advantage of doubling the amount of available getter material, but in some cases one single device may be used for economical reasons.

This embodiment can be realized in two alternative ways, the first of which
5 is illustrated in Figs. 5 and 6, while the second is illustrated in Figs. 7 and 8.

The lamp according to this first alternative, 50, is shown in Fig. 5. Lamp 50 comprises a first supporting part 51, that, through feedthrough 60 sealed in burner terminal 52, electrically feeds electrode 53; and a second supporting part 51', that, through feedthrough 60' sealed in the opposite burner terminal 52', electrically
10 feeds electrode 53'. The structure of feedthrough 60 (the same as 60') is illustrated in detail in Fig. 6, and comprises a metallic wire, 61, onto which is formed a body of getter material forming getter device 62. Feedthrough 60 with
15 getter device 62 can be produced for example through the metal injection moulding technique, well known in the field of powder metallurgy, by positioning wire 61 in the mould in which the powders of getter material are poured, compressing the powders and then heating the assembly powders-wire to a temperature suitable to consolidate the structure. Alternatively, device 62 may be
20 produced by depositing (e.g., by dispensing with a brush) a suspension of particles of getter material onto wire 61, heating the assembly to a first temperature to cause evaporation of the liquid phase of the suspension, and then heating the resulting assembly to a second, higher temperature, to cause consolidation by sintering of the getter particles deposit; the suspension may be prepared with
25 powders of getter material with particle size lower than about 150 μm in a dispersing medium having an aqueous, alcoholic or hydroalcoholic base and containing less than 1% by weight of organic compounds having a boiling temperature higher than 250°C, with a ratio between the weight of getter material and the weight of dispersing medium comprised between 4:1 and 1:1, as described in US patent No. 5,882,727 in the name of the applicant.

A getter device 62 formed directly onto wire 61 is rather easy to produce,
30 but may suffer the problem that the repeated thermal cycling consequent to turning on and off the lamp could cause breaks and eventually detachment, at least

- 8 -

partial, of the getter body from the wire; this drawback can be avoided by choosing a material for getter device 62 having characteristics of thermal dilatation similar to those of the material of wire 61.

This problem may be avoided by using the second alternative way of
5 attaching the getter device to the feedthroughs, as illustrated in the lamp of Fig. 7. This lamp, 70, has supports 71 and 71', supporting feedthroughs 72 and 72' compression sealed in burner ends 73 and 73' for the electrical feeding of the electrodes in the burner. The getter device 80 (the same as 80') is shown enlarged in Fig. 8, and has the form of a hollow cylinder with a central hole 81 having a
10 diameter slightly greater than that of the wire of the feedthroughs. This device can be obtained for example through the metal injection moulding technique previously cited, or through the process described in patent US 5,908,579 in the name of the applicant. A device of type 80 can be mounted in lamp 70 simply inserting a feedthrough 72 (or 72') 81, before welding the feedthrough to one of
15 the supporting parts 71 and 71', or before the heat compression sealing of burner terminals 73 and 73' around said feedthroughs; the fact that diameter of hole 81 is greater than that of feedthrough 72 allows these two parts to expand or shrink independently from each other, each one according to its own thermal dilatation characteristics, thus avoiding the risk of breakings of body 80.

20 Both devices 62 and 80 allow to have in the lamp the necessary amount of getter material, but with a reduced external diameter, such that the getter device projection is essentially included in the width of parts 52, 52' or 73, 73', which are generally poorly transparent (especially in the common case of a burner made of alumina), thereby substantially not causing additional shadow effect.

25 Fig. 9 shows another embodiment of the lamp of the invention. Lamp 90 has the main support formed of two parts, 91 and 91', linked to each other by the getter device 100. Device 100 is shown enlarged in Fig. 10, and it is formed of a tubular housing 101 internally filled with getter material 102, except for the ends; housing 101 is made of a material which exhibits a good hydrogen permeability at
30 high temperature, niobium for example, so that the gas can pass through the housing and reach the getter material, where it is chemically fixed. The hydrogen

- 9 -

permeation through the housing can be made maximum by minimizing the housing thickness, compatibly with the mechanical resistance needs of the assembly; the minimum possible thickness can be easily identified with a limited number of experimental tests. The two ends of device 100 are not filled with
5 getter material, thus forming two seats for the insertion of the ends of parts 91 and 91' of the burner support; the fixing between device 100 and parts 91 and 91' is preferably reinforced through welding. A device of type 100 can be produced, for example, by providing a section of a niobium tube of the same diameter as the final getter device, holding this tube in vertical position by inserting in its bottom
10 aperture a support of the same diameter as the internal diameter of the tube itself and of a height equal to the part not to be filled with getter material at a first end of the completed device; by pouring getter material powders into the container formed by the housing and its lower support; and by pressing the powders in the so-formed container by a piston of a diameter equal to the inner diameter of the
15 housing; the amount of getter material will be optimized to be such that, after compression, it leaves at the second end of device 100 a second part free from the getter material itself. To avoid housing deformations due to the powders compression, it is also possible that the housing is contained into an external mould during this operation. With this embodiment, the shadow effect due to the
20 getter device is minimum, and practically negligible with respect to the effect caused by the support, which is unavoidable.

Another possible embodiment of lamp of the invention is shown in Fig. 11. In this lamp, 110, the getter device 111 performs also the function of support for the burner. This getter device may similar to the one of Figs. 3, 4 or 10, with the
25 difference that in this case the whole length of the longer support of the burner is formed of a housing filled with getter material; such a kind of getter device can be manufactured with the techniques described in the above mentioned international patent applications WO 98/53479 and WO 01/67479. In the case of a getter device produced as described in WO 01/67479, the housing material will be made of a
30 material which exhibits a good permeability to hydrogen, e.g. niobium. The end 112 of device 111 is anyway open, and represents an additional hydrogen direct

- 10 -

access channel to the getter material. In the case of a getter device produced as described in WO 98/53479, it may be produced with a material of high hydrogen permeability as well, but this is not a strict requirement in this case, because the slit 43 along the whole length of the device assures already a satisfactory rate of
5 access of hydrogen molecules to the getter material; in this second case, so, a wider choice of materials for the housing material is allowed.

Finally, it is also possible to adopt a configuration (not shown in the drawings) that is hybrid between the embodiments of Figs. 9 and 11, in which the burner support is formed of a common metal wire in its initial part (the part closer
10 to contacts P of Fig. 1), and by a getter device similar to the one of Fig. 11 for the remaining part. A particular form of realization of this last embodiment is shown in Fig. 12, and is particularly adapted for the production of lamps of smaller dimensions, that do not need that the longer support of the burner contacts the end of the bulb to assure stiffness of the structure. Lamp 120 according to this last
15 embodiment has the longer support of the burner that is made for its main part, 121, of a simple metallic wire, and for its terminal part of the getter device 122 to which, in turn, is attached feedthrough 123 for sustain and electrical feeding of the burner; feedthrough 123 will be generally fixed to device 122 by welding, while device 122, in turn, may be fixed to part 121 mechanically, for instance by
20 inserting the end portion of part 121 in a suitable bore or hollow of device 122 (the hollow may be of the kind described with reference to device 100), or as well by welding, e.g. spot welding.

The getter materials that can be used to produce devices 22, 22', 22'', 52, 70, 92 and 111 are the ones described in the introduction, and in particular zirconium-
25 aluminum alloys of patent US 3,203,901, zirconium-cobalt-Rare Earths alloys of patent US 5,961,750, yttrium and yttrium-based alloys of patent GB 1,248,184 or of international patent application WO 03/029502; it is also possible to use ZrYM alloys, where M is a metal chosen among aluminum, iron, chromium, manganese, vanadium or mixtures of these metals, described in international patent application
30 PCT/IT2005/000673 in the name of the applicant.

CLAIMS

1. High pressure discharge lamp (20, 50, 70, 90, 110, 120) comprising a bulb (C) and, within the bulb, a burner (B), supports (M) for the burner, feedthroughs (R) for feeding an electrical discharge in an atmosphere comprising a noble gas and metallic vapors in the burner, and a getter device, characterized in that the getter device is:
- filiform (22, 22', 22''), fixed to one (21) of the metal parts supporting the burner, and in such a position to be parallel to said metal part and essentially hidden to the burner by said metal part; or
 - attached to at least one feedthrough (61, 61'; 72, 72') for the electrical feeding of the burner; or
 - in the form of a hollow filiform body filled with getter material, which constitutes fully (111) or in part (100; 122) the metal part supporting the burner extending itself between the two heads of the lamp.
2. Lamp (20) according to claim 1, wherein the getter device (22') is formed of a metal housing (30) extended and open at the ends, inside which getter material in powder (31) is present.
3. Lamp (20) according to claim 1, wherein the getter device (22'') is formed of a metal housing (40) containing getter material powders (41), and formed of a thin metal plate shaped to obtain an essentially closed cross-section, with a single slit (43) between the two opposite edges (42, 42') of the thin plate.
4. Lamp (50) according to claim 1, wherein the getter device (62, 62') is in the form of a body formed of getter material onto a metallic wire (61, 61'), said wire being part of a feedthrough (60, 60') connecting an electrode (53, 53') in the burner to a support (51, 51') of the burner.
5. Lamp (70) according to claim 1, wherein the getter device (80, 80') is in the form of a hollow cylinder formed of getter material only and having a central hole (81) into which is inserted a feedthrough (72, 72') connecting an electrode in the burner to a support (71, 71') of the burner.
6. Lamp (90) according to claim 1, wherein the burner support extending

- 12 -

between the two heads of the lamp is formed of two parts (91, 91') linked to each other by a getter device (100), said device being formed of a tubular housing (101) being permeable to hydrogen internally filled with getter material (102), except for the ends, wherein the terminals of said supporting parts (91, 91') are inserted.

5 7. Lamp (110) according to claim 1, wherein the getter device (111) extends between the two heads of the lamp and also performs the function of support for the burner, and is formed of a tubular metal housing being permeable to hydrogen and filled with getter material.

10 8. Lamp (120) according to claim 1, wherein the getter device (122) forms the last portion of the longer support of the burner and is fixed on one side to a metallic part (121) and on the other side to the feedthrough (123) of an electrode in the burner.

15 9. Lamp according to claim 1, wherein the burner support is formed in its initial part by a common metal wire, and in its terminal part by a getter device formed of a tubular metal housing being permeable to hydrogen and filled with getter material.

10 10. Lamp according to one of claims 2 or 3 wherein the housings (30, 40) of said getter devices (22, 22', 22'') are made of a material chosen among nickel, nickel-plated iron, stainless steel, niobium and tantalum.

20 11. Lamp according to claim 6 wherein the housing (101) of said getter device is made of niobium or tantalum.

 12. Lamp according to claims 7 or 8 wherein the housings (30, 40, 101) of said getter devices are made of a material chosen among nickel, nickel-plated iron, stainless steel, niobium and tantalum.

25 13. Lamp according to claim 1, wherein said getter devices comprise or are made of a getter material chosen among yttrium or yttrium-based alloys, zirconium-aluminum alloys, zirconium-cobalt-Rare Earths alloys and zirconium-yttrium-M alloys, where M is a metal chosen among aluminum, iron, chromium, manganese, vanadium or mixtures of these metals.

30 14. Lamp according to claim 1, wherein said bulb has an external diameter of about 2 cm or less and length of less than 7 cm.

- 13 -

15 15. Process for the production of a getter device (22'; 111, 122) for use in a lamp of claim 2, 7 or 8, consisting in providing a metallic tube of diameter greater than the desired diameter of the getter device, filling said tube with powders of a getter material, passing the filled tube through a series of
5 compression rollers until the desired diameter for the getter device is obtained, and cutting the resulting tube in parts of the desired length.

16. Process for the production of a getter device (62) for use in a lamp of claim 4, consisting in positioning a metallic wire (61) in a mould in which powders of getter material are poured and then compressed to form a body of
10 getter material on said wire through metal injection moulding.

17. Process for the production of a getter device (62) for use in a lamp of claim 4, consisting in depositing a suspension of particles of getter material onto a metallic wire (61), heating the thus obtained assembly to a first temperature to cause evaporation of a liquid phase of the suspension, and then heating the
15 resulting assembly to a second, higher temperature, to cause consolidation by sintering of the deposit of getter material particles to form said getter device.

18. Process for the production of a getter device (80) for use in a lamp of claim 5, consisting in forming a body of consolidated particles of getter material through metal injection moulding.

20 19. Process for the production of a getter device (100) for use in a lamp of claim 6, consisting in: providing a section of a niobium tube of the same diameter as the final getter device; holding this tube in vertical position by inserting in a bottom aperture thereof a lower support of the same diameter as the internal diameter of the tube itself and of a height equal to the part not filled with the
25 getter at one end in the final device; pouring getter material powders into the container formed by the tube and said lower support; and by compressing the getter material powders in the so-formed container by a piston of a diameter equal to the inner diameter of the tube.

20. Process according to claim 19, wherein during the step of compressing
30 the getter material powders the tube is contained into an external mould of internal diameter equal to the outer diameter of the final getter device.