BUMP WITH BASIC METALLIZATION AND METHOD FOR MANUFACTURING THE BASIC METALLIZATION

This invention relates to a method for manufacturing a bump on a terminal face of a semiconductor substrate, in which the terminal face is nucleated to generate a basic metallization through electrolytic coating of the terminal face with zincate, in such a way that zinc particles electrolytically deposited on the terminal face serve as nuclei for an ensuing contact metallization autocatalytically deposited on the basic metallization. In addition, the invention relates to the structure of a bump with a basic metallization according to the preamble of claim 12.

Known in the art for preparing semiconductor substrates for a subsequent bonding is to provide the usually aluminum terminal faces of the semiconductor substrates with an elevated contact metallization, so-called "bumps". In particular when applying the contact metallization to the terminal faces through an autocatalytic deposition of metal, it has proven necessary, in order to improve the adhesion of the autocatalytically deposited metal to the terminal face, not to apply the contact metallization directly to the terminal face, but rather to provide a basic metallization between the terminal face and the contact metallization. This holds true in particular when the contact metallization consists of the autocatalytically deposited metals nickel and gold.

To improve adhesion between the autocatalytically deposited metals and the terminal face, it has proven beneficial to electrolytically coat the terminal face with zincate prior to autocatalytic deposition. The zincate or zinc in the zincate here preferably deposits at the grain boundaries of the relatively coarse-grained aluminum of the terminal face, and thereby produces a relatively coarse distribution of nuclei on the terminal face. This nucleation yields a good adhesion of a metal then autocatalytically deposited on the terminal face. However, the provided coarsely

distributed nucleation only results in a correspondingly coarse-grained structure in the autocatalytically deposited metal. This relatively coarse structure facilitates the formation of structural defects, which ends up limiting the reliability of contact metallizations formed in this way.

Known as an alternative to the electrolytic coating of the terminal faces with zincate is to subject terminal faces to electrolytic coating with palladium in preparation for a subsequent autocatalytic metal deposition. The nucleation of the terminal faces achieved as a result has a significantly refined structure with a comparatively higher number of nuclei. This also enables a correspondingly fine-grained formation of the subsequently autocatalytically deposited metal structure. The disadvantage to a palladium nucleation, however, is that the pronounced catalytic property of palladium gives it only a limited selectivity, so that intensive nucleation with palladium can result in a deposition of palladium not just on the terminal faces, but also on the entire surface of the semiconductor substrate. In addition, a palladium nucleation only enables a slight adhesion to a subsequently autocatalytically deposited metallization in particular in comparison to zincate nucleation.

The object of this invention is to propose a method for manufacturing a bump with a contact metallization on the terminal face of a semiconductor substrate that makes it possible to further improve the quality of the contact metallization.

This object is achieved by a method with the features in claim 1.

In addition to the electrolytic coating of the terminal face with zincate, the method according to the invention enables an electrolytic coating of the terminal face with palladium, in such a way that palladium particles deposited on the terminal surface along with the zinc particles serve as

This Sheet Has Been Replaced



nuclei for the contact metallization subsequently autocatalytically deposited on the terminal surface.

The combination of an electrolytic zincate coating and an electrolytic palladium coating according to the invention results in a hybrid nucleation, which yields a contact metallization that adheres well to the terminal face, and has a fine-grained structure along with a correspondingly smooth surface morphology. This produces a contact metallization with an increased reliability.

In a preferred variant of the method, the electrolytic coating of the terminal face with zincate (zincate coating) is performed in one method step, followed by the electrolytic coating of the terminal face with palladium (palladium coating) in a subsequent method step. In this variant, the subsequent palladium coating refines the nucleation structure produced by the zincate coating.

In particular having zincate coating take place at least partially after a palladium coating yields the advantageous effect that the relatively high erosion rate on the terminal face caused by the zincate coating is reduced by the comparatively low erosion rate of the palladium. This effect also has a beneficial effect on the surface morphology of the contact metallization, since an even greater surface smoothness can be achieved for the contact metallization.

One way to achieve this effect involves performing zincate coating not in a single method step, but interrupting zincate coating and interjecting a palladium coating, so that the zinc particles are at least partially removed prior to palladium coating, followed by repeated zincate coating.

Another possibility has to do with electrolytically coating the terminal face with palladium (palladium coating) in one method step, and

This Sheet Has Been Replaced

electrolytically coating the terminal face with zincate (zincate coating) in an ensuing method step.

The refinement of the nucleation structure achievable with the preceding variant and concurrent refinement of the contact metallization structure can be increased even further by at least partially removing the zinc particles after the zincate coating, and then renewing the zinc coating process.

Hybrid nucleation followed by autocatalytic metal deposition that yields a contact metallization with especially good adhesion to the terminal face given a largely uniform surface morphology for the contact metallization becomes possible if a first electrolytic coating of the terminal face with zincate (zincate coating) takes place in a first method step, the electrolytic coating of the terminal face with palladium (palladium coating) takes place in a subsequent method step, and a second zincate coating takes place in another method step.

This variant also makes it possible to even further improve the surface morphology of the contact metallization by at least partially removing the zinc particles after the first zincate coating and before the palladium coating.

If the terminal face is nucleated in a combined electrolyte comprised of zincate and palladium ions, so that the electrolytic coating of the terminal face with zincate (zincate coating) and electrolytic coating of the terminal face with palladium (palladium coating) take place in a combined method step, so that zincate coating takes place simultaneously with palladium coating due to the combined or mixed electrolyte (zincate/palladium coating), it becomes possible to achieve a well-adhering autocatalytically deposited contact metallization as well as a

flat surface morphology based on only a single method step for nucleating the terminal face.

In one advantageous modification of this method variant, at least a partial removal of the zinc particles with subsequent renewed zincate coating takes place after zincate/palladium coating.

As an alternative, it is also possible to have zincate/palladium coating be preceded by a zincate coating of the terminal face, followed by at least a partial removal of the zinc particles.

Stripping the zinc particles has proven to be particularly advantageous for at least partially removing the zinc particles.

Regardless of the method variant selected, the application of the method according to the invention as described above drawing reference to different variants results in a structure of a bump according to claim 12, which has a basic metallization according to the invention with both zinc and palladium as constituents.

In the following, preferred variants of the method according to the invention will be described in greater detail based on the drawing. Shown in:

Fig. 1 is a sectional view of a semiconductor substrate with a terminal face arranged on a silicon body, initial state;

Fig. 2 is the terminal face shown in Fig. 1 after an electrolytic coating with zincate;

Fig. 3 is the terminal face shown in Fig. 2 after an electrolytic coating with palladium;

This Sheet Has Been Replaced

Fig. 4 is the terminal face shown in Fig. 3 after an autocatalytic deposition of nickel;

Fig. 5 is a diagrammatic representation of the method for generating an elevated contact metallization on a terminal face based on a nucleation of the terminal face;

Figs. 6 – 13 are various method variants for executing the nucleation process.

Fig. 1 shows a sectional view of a semiconductor substrate 20, e.g., a wafer or a chip, with a terminal surface 21 here made out of aluminum, whose circumferential boundary area is covered by a passivation layer 22 extending over the surface of the semiconductor substrate 20. It is emphasized that the following statements regarding method variants for nucleating the terminal surface 21 are not limited to the material of the terminal face 21 that was selected here as an example, i.e., aluminum.

Fig. 2 shows the terminal face 21 after an electrolytic coating of the terminal face 21 with zincate. As evident, zinc particles or zinc grains 24 have electrolytically deposited preferably on the grain boundaries 23 of the terminal face material. Therefore, electrolytic deposition results in a relatively coarse distribution of zinc particles 24 on the terminal face 21.

Fig. 3 shows the terminal face 21 after a second electrolytic coating with palladium following the first electrolytic coating with zinc. The palladium coating results in a relatively fine distribution of palladium particles or palladium grains 25 on the intermediate surfaces 26 of the terminal surface 21 remaining free after the zincate coating. Altogether, coating the terminal faces 21 with zincate and palladium therefore yields

This Sheet Has Been Replaced



a relatively finely distributed arrangement of particles 24 and 25, which serve as deposition nuclei during a subsequent autocatalytic coating of the terminal face 21 with nickel.

As shown in Fig. 4, the nucleation structure 27 that was finely structured through the interaction of zinc particles 24 and palladium particles 25 and encompasses the grain boundaries 23 of the terminal face material in conjunction with the ensuing autocatalytic nickel deposition yields a uniform nickel coating 28 with a flat surface morphology on the terminal face 21.

As shown diagrammatically in Fig. 5, the process depicted in Figs. 1 to 4 can be supplemented by a method step preceding nucleation, which involves a preliminary treatment of the terminal face 21 to remove the oxide layer, and a method step following Ni deposition, in which the nickel coating 28 produced on the terminal face 21 is additionally provided with an Au deposit also produced by way of autocatalytic deposition. In this case, the Ni deposit combines with the Au deposit to form the contact metallization.

Additional Figs. 6 to 13 show preferred variants for nucleation via the electrolytic coating of the terminal face 21 of the semiconductor substrate 20 with zincate and palladium in diagrammatic form.

According to Fig. 6, the terminal face 21 is nucleated by first coating with zincate, then stripping the zinc grains electrolytically deposited on the terminal face 21 through zincate coating, repeating the zincate coating step and ending with a palladium coating step.

According to Fig. 7, a first nucleation step involves palladium coating, followed in a second nucleation step by zincate coating the terminal face 21.

According to Fig. 8, a first nucleation step involves a palladium coating of the terminal face 21, followed by a first zincate coating, a stripping of the zinc grains electrolytically deposited on the terminal face 21 in the first zincate coating step, and finally a second zincate coating step.

According to Fig. 9, a first nucleation step involves a zincate coating of the terminal face 21, followed by a palladium coating, and finally a second zincate coating of the terminal face 21.

According to Fig. 10, a first step for nucleating the terminal face 21 involves a first zincate coating, followed by a stripping of the zinc grains electrolytically deposited on the terminal face 21 through the first zincate coating, a palladium coating, and finally a second zincate coating of the terminal face 21.

According to Fig. 11, the terminal face 21 is nucleated in a single method step with a palladium/zincate coating by an electrolyte that has both palladium and zincate ions.

According to Fig. 12, a first method step for nucleating the terminal face 21 involves a palladium/zincate coating, followed by a stripping of the zinc grains electrolytically deposited on the terminal face 21 through palladium-zincate coating, and finally a zincate coating of the terminal face 21.

According to Fig. 13, a first method step for nucleating the terminal face 21 initially involves a zincate coating, followed by a stripping of the zinc grains electrolytically deposited on the terminal face 21 through zincate coating, and finally a palladium/zincate coating of the terminal face 21.

* C L M S *

CLAIMS

1. A method for manufacturing a bump on a terminal face of a semiconductor substrate, in which the terminal face is nucleated to generate a basic metallization through electrolytic coating of the terminal face with zincate, in such a way that zinc particles electrolytically deposited on the terminal face serve as nuclei for an ensuing contact metallization autocatalytically deposited on the basic metallization, characterized by the fact that, in addition to the electrolytic coating with zincate, an electrolytic coating of the terminal face (21) with palladium takes place, in such a way that, in addition to zinc particles (24), palladium particles (25) deposited on the terminal face (21) serve as nuclei for the contact metallization (28, 29) subsequently autocatalytically deposited on the terminal face.

2. The method according to claim 1, characterized by the fact that the electrolytic coating of the terminal face (21) with zincate (zincate coating) takes place in one method step, and the electrolytic coating of the terminal face with palladium (palladium coating) takes place in a subsequent method step.

3. The method according to claim 2, characterized by the fact that the palladium coating is preceded by at least a partial removal of the zinc particles (24) followed by renewed zincate coating.

4. The method according to claim 1, characterized by the fact that the electrolytic coating of the terminal face (21) with palladium (palladium coating) takes place in one method step, and the electrolytic coating of the terminal face (21) with zincate (zincate coating) takes place in a subsequent method step.

This Sheet Has Been Replaced

* C L M S *

5. The method according to claim 4, characterized by the fact that zincate coating is followed by an at least partial removal of the zinc particles (24) followed by renewed zincate coating.

6. The method according to claim 1, characterized by the fact that a first electrolytic coating of the terminal face (21) with zincate (zincate coating) takes place in a first method step, the electrolytic coating of the terminal face with palladium (palladium coating) takes place in a subsequent method step, and a second zincate coating takes place in another method step.

7. The method according to claim 6, characterized by the fact that at least a partial removal of the zinc particles (24) takes place after the first zincate coating and before the palladium coating.

8. The method according to claim 1, characterized by the fact that the electrolytic coating of the terminal face (21) with zincate (zincate coating) and electrolytic coating of the terminal face with palladium (palladium coating) take place in a single method step, in such a way that the zincate coating occurs simultaneously with the palladium coating via a mixed electrolyte (zincate/palladium coating).

9. The method according to claim 8, characterized by the fact that the zincate/palladium coating is followed by at least a partial removal of the zinc particles (24), followed by renewed zincate coating of the terminal face (21).

10. The method according to claim 8, characterized by the fact that the zincate/palladium coating is preceded by a zincate coating of the terminal face (21), followed by an at least partial removal of the zinc particles (24).

* C L M S *

11. The method according to one or more of the preceding claims, characterized by the fact that the at least partial removal of zinc particles (24) takes place via stripping.

12. Setup of a bump with a basic metallization situated on a terminal face of a semiconductor substrate and a contact metallization situated on the basic metallization, characterized by the fact that the basic metallization has zinc and palladium as constituents.

This Sheet Has Been Replaced