CLAIMS

1. A hollow sealing resin sheet, comprising a thermoplastic resin and an inorganic filler in a content of 70 to 90% by volume both inclusive, wherein:

in a particle diameter distribution of the inorganic filler that is measured by a laser diffraction scattering method, at least one frequency distribution peak is present in the particle diameter range of 1 to 10 μm both inclusive, and further at least one frequency distribution peak is present in the particle diameter of range more than 10 μm and not more than 100 μm; and

the inorganic filler has a BET specific surface area of 2 to 5 m^2/g both inclusive.

2. The hollow sealing resin sheet according to claim 1, which has a dynamic viscosity of 5000 to 30000 Pa·s both inclusive at 80°C before cured.

3. The hollow sealing resin sheet according to claim 1 or 2, wherein the inorganic filler is silica particles, alumina particles, or a mixture of these particles.

4. The hollow sealing resin sheet according to any one of claims 1 to 3, wherein the inorganic filler is spherical.