

IPOS COPY
9804252-6



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 28/02, 24/32 // (C04B 28/02, 24:02, 24:32, 24:38), 103:40, 103:44		A1	(11) International Publication Number: WO 98/24734
			(43) International Publication Date: 11 June 1998 (11.06.98)
(21) International Application Number: PCT/EP97/06945 (22) International Filing Date: 28 November 1997 (28.11.97) (30) Priority Data: 8/340448 6 December 1996 (06.12.96) JP (71) Applicant (for all designated States except US): MBT HOLD- ING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): MATSUO, Shigemi [JP/JP]; 786-1, Hamanogou, Chigasaki-chi, Kanagawa-ken (JP). NAGAMINE, Hidenori [JP/JP]; 2722, Hagizono, Chigasaki-chi, Kanagawa-ken (JP). OTA, Akira [JP/JP]; 1-5-42, Enzo, Chigasaki-chi, Kanagawa-ken (JP).			(81) Designated States: AU, CA, CN, DE, GB, SG, US. Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FLOWABILITY ADDITIVE			
(57) Abstract			
A cement pumpability-enhancing additive which confers good pumpability on cementitious compositions such as concrete consists essentially of (a) polyethylene glycol; (b) diethylene glycol monobutyl ether and/or a derivative thereof; (c) polysaccharide; and (d) a thickening polymer selected from the group consisting of polyacrylic acid derivatives, polyacrylic amide derivatives, cellulose ethers, polyphenyl ethers and polyalkylene glycol fatty acid esters; the weight solids proportions of (a), (b), (c), and (d) in the additive being respectively 5-55 %, 10-80 %, 1-20 % and 1-20 %. The additive is preferably used with a cement dispersing agent.			