

Description

The present invention relates to a process for preparing crystals of an MFI-type zeolite whose crystals size is uniform and controlled, and to catalysts, catalyst carriers and adsorbents comprising zeolites when produced by this process.

Zeolites, molecular sieves having a crystalline structure which is typically an aluminosilicate, find many uses as catalysts or catalyst carriers or as adsorbents. The habit and size of crystals is an important factor in the applicability of a zeolite. Generally the intrinsic quality of a zeolite is better when the crystals are small and uniform, than when the crystals are large and less uniform. Small, uniform crystals have a relatively low mass transfer resistance, and short pathways for molecules to enter and leave the zeolite structure.

As with many types of zeolite, MFI zeolites may be produced in many different crystal sizes and shapes. Indeed, within one batch of crystals there can be a significant variation in crystal habit and size. It is therefore desirable to be able to control reliably the size and size distribution of the crystals.

The present applicants have found that the use of a surprisingly small amount of seed crystals of size less than 100 nm average diameter may be used to produce accurately and reproducibly MFI-type crystals of uniform size.

Whilst the use of seed crystals when crystallising zeolites is a well known technique, previous publications recommended the use of a relatively large amount of seed. For example, EP-A-172068 describes a process in which a "complementary salt" or finely crushed crystals of a zeolite are added to the zeolite synthesis mixture. The examples suggest a weight percent of seed crystals of at least 0.8 weight percent based on the total weight of the synthesis mixture. EP-A-170486 suggests seeding a synthesis mixture with crystals of ZSM-5 or zeolite b. The examples use at least 0.66 weight percent of seed based on the total weight of the synthesis mixture. EP-A-110650 also suggests using seed crystals in zeolite synthesis. However, the examples all suggest an amount of seed of at least 0.6 weight percent based on the total weight of synthesis mixture.

GB 1567948 suggests the use of seeds in the synthesis of ZSM-5 zeolite. The amount of seed zeolite may be from 0.01 to 100 grams per 100 grams of SiO_2 . However, the alkalinity of this synthesis mixture is 0.1 to 0.4 expressed as a molar ratio of OH^-/SiO_2 and the effect of the seeds on the crystal size and uniformity is obscured in a synthesis mixture with such a high alkalinity.

The present applicants have found that if the seed crystals are sufficiently small, possibly present in the synthesis mixture in the form of a colloidal suspension, and if the synthesis mixture has a sufficiently low alkalinity then as little as 1700 ppm or less (0.17 wt% or less) of seed crystals may be used, based on the weight of the synthesis mixture.

The present invention thus provides a process for the preparation of an MFI-type zeolite comprising mixing:

- (i) a source of particulate silica in which silica particles present have an average diameter of 1 μm or less;
- (ii) seeds of an MFI zeolite having an average diameter of 100 nm or less in the form of a colloidal suspension;
- (iii) an organic structure directing agent; and
- (iv) a source of fluorine or an alkali metal;

to form an aqueous synthesis mixture, the seeds being present in an amount of 0.05 to 1700 ppm by weight of the synthesis mixture, and the synthesis mixture having an alkalinity, expressed as a molar ratio of OH^-/SiO_2 , of less than 0.1; and allowing the synthesis mixture to crystallise.

Zeolites of MFI-type include e.g. ZSM-5, and silicalite and boro-, ferro-, zinco-, gallo- or vanado-MFI structures. For example, ZSM-5 also contains aluminum or a replacement for aluminium in the structure, such as gallium or an oxide of boron or a transition metal, e.g. iron, zinc or vanadium. The synthesis mixture may therefore contain a source of alumina or alumina substitute.

ZSM-5 and silicalite should be prepared in the presence of an organic structure directing agent. A structure directing agent is a molecule which directs the formation of a given molecular sieve by the so-called "templating effect". The role of organic molecules in molecular sieve synthesis is discussed in articles published in the literature, e.g. Lok et al, Zeolites 1983, Volume 3, pages 282 to 291 and Moretti et al, Chim. Ind. (Milan) 67, No. 1-2, 21 to 34 (1985). The effect of an organic structure directing agent is that in the production of the crystalline framework the organic compound behaves like a template around which the crystalline framework grows, or which causes the crystallisation to be directed to form a particular crystalline framework. Examples of structure directing agents which may be used in the present process include tetraethyl ammonium (TEA), tetrapropyl ammonium (TPA) or tetrabutyl ammonium (TBA) com-

pounds. The lower the amount of aluminum in the synthesis mixture the more critical the choice of structure directing agent. TPA compounds are generally found to be the most appropriate.

A source of alkali metal or fluorine should also be present in the synthesis mixture. The alkali metal may be e.g. sodium, potassium or caesium. Sodium is preferred. The amount and type of alkali metal or amount of fluorine present in the synthesis mixture will be determined by the particular zeolite it is desired to produce. Suitable quantities will be known to the skilled person provided that the OH^-/SiO_2 ratio is maintained at less than 0.1. If an alkali metal is added to the mixture in the form of its hydroxide, as is common, then account should be taken of the contribution this makes to the overall OH^-/SiO_2 ratio of the mixture as discussed below.

The silica source in the synthesis mixture is present in the form of very small particles i.e. average diameter 1 μm or less, preferably less than 500 nm, more preferably less than 50 nm so that the silica is evenly distributed throughout the synthesis mixture and remains evenly distributed during the crystallisation process. This may be achieved by using a colloidal silica source. Suitable commercially available colloidal silicas include e.g. Ludox. Suitable solid silica sources include e.g. Aerosil (Degussa) in which the silica particles may typically have an average diameter of 7 nm. If the silica is present in the form of e.g. solid particles whose average diameter is much greater than 1 μm , e.g. 50 μm , the particles settle at the bottom of the synthesis mixture during crystallisation, and the resulting crystals are less uniform in size. The crystals formed at the interface of the silica and the rest of the (seed-containing) synthesis mixture are relatively small, whereas the crystals formed by silica which has not "seen" the seed crystals will be much larger.

The seed crystals used are seeds of an MFI-zeolite which have an average diameter of 100 nm or less. These may be obtained by e.g. crushing in a ball mill crystals which have a larger size to give small crystals which, to obtain most benefit from being used as seed crystals, should be of uniform size. Seed crystals can be synthesised with an average diameter of 100 nm or less using the process described in our co-pending application of even date (N.63077).

The seed crystals are present in the synthesis mixture in the form of a colloidal suspension. Again this is to ensure that the seed crystals are evenly distributed throughout the synthesis mixture and remain so throughout the crystallisation time, to encourage the formation of uniform crystals. It was observed that if the pH of the colloidal suspension is below 8 there is a tendency for the solution to decolloidalise. The particles tend to form agglomerates.

The seed crystals may be present in an amount of 0.05 to 1700 ppm by weight of the synthesis mixture. The greater the amount of crystals, the smaller will be the crystals produced. However, this effect is asymptotic; use of an amount of much greater than 1700 ppm of seed crystals does not result in a correspondingly great reduction in crystals size and the amount of seed present in the synthesis mixture begins to be significant when calculating the overall composition of the zeolite to be produced. Therefore 1700 ppm is regarded as the maximum amount of seed crystals required in practice to produce small, uniform zeolite crystals.

By simply adjusting the quantity of seed crystals the crystal size of the zeolite produced can be reproducibly varied from about 30 microns to 0.3 microns, whilst maintaining a very high degree of uniformity of the crystals. The crystals produced by the process are generally uniform in size. The variance in diameter of spherical crystals, or in length of rhomboid or similar shaped crystals e.g. coffin-shaped crystals, is typically less than 10% and can be less than 8% of the average diameter or length.

The smaller the size of the seed crystals the lower the weight percentage of seeds required to achieve the same effect in the synthesis. The size of zeolite crystals synthesised could therefore also be controlled by altering the size of the seed crystals. However, it is generally more convenient to alter the amount of seed present since this technique has been found sufficiently sensitive to be of practical use, i.e. significant changes in crystal size can be produced by only a small change in the amount of seed used.

One of the advantages of the present invention is that the amount of seed crystals used in the synthesis mixture on a weight basis is extremely low, of the order of parts per million. The composition of the seed crystals is therefore not significant when calculating the composition of the zeolite based on the ingredients of the original synthesis mixture, and the seed crystals need not be of the same composition as the desired zeolite crystals.

The synthesis mixture in the process has an alkalinity, expressed in terms of a molar ratio of OH^-/SiO_2 , of less than 0.1. When calculating this ratio, account should be taken of all sources of OH^- ion in the synthesis mixture e.g. introduced as part of an alkali metal source. The effect of any acidity (H^+ ions) must be subtracted from the total amount of OH^- before calculating the OH^-/SiO_2 molar ratio. Such H^+ ions may be introduced into the synthesis mixture e.g. in the form of aluminum sulphate.

Increasing the alkalinity to greater than 0.1 results, generally, in more nucleation in the synthesis mixture. Although this might be expected to lead to smaller crystals, the crystals are not uniform in size. To obtain small, uniform crystals it is necessary to maintain the alkalinity below 0.1 and use seed crystals.

In performing the process the source of silica particles, colloidal suspension of seeds, template source and alkali metal or fluorine source and, if present, any other ingredients may be added in any order, either sequentially or simultaneously. Preferably the synthesis mixture is stirred either whilst adding the ingredients, or after the ingredients have been added.

The mixture may be crystallised at an appropriate temperature, generally 140 to 200 °C, e.g. 150 to 185 °C and for an appropriate time, generally 65 to 150 hours, e.g. 73 to 120 hours although suitable temperatures and times are easily determined by an ordinarily skilled person. The mixture may optionally be stirred during crystallisation.

After crystallisation the crystals may be washed and dried, and optionally, calcined.

The following examples illustrate the invention:

Examples: Preparation of Colloidal Seed Suspension

Where appropriate the Manufacturers/Supplier's name and the product number are given in brackets after the name of each reagent.

Component	Ingredients	Quantity in Grams
A	Silicic acid powder (Baker 0324-5), 10% water, 99.9% purity	113.73
B	TPA OH (20% in water) (Fluka 88110),	521.07
C	NaOH (98.4%) (Baker 0402),	7.37

Component C was dissolved in B at room temperature with stirring in a one litre glass beaker. Component A was weighed into the beaker and the contents of the beaker were heated to boiling while vigorously stirring. After a few minutes into boiling a clear solution was obtained. The weight loss due to the boiling was corrected with demineralized water. The molar composition of the synthesis mixture was:



639.40 grams of this solution was poured into a 1 litre polypropylene flask, the flask was placed in a 88 °C oilbath and connected to a reflux condenser. After some 16 hours into heating the initially clear solution became slightly opaque indicating the formation of extremely small crystals. After 3 days into heating the synthesis magma was cooled to room temperature. The crystals were separated from the mother liquor by centrifuging for several hours at 3750 rpm. The crystals were washed several times with demineralized water by redispersing the crystals in water and centrifuging the slurry until clear.

The crystals were washed to pH 10.3. The crystals were redispersed in the last washwater. This colloidal suspension was used as seed slurry.

A 10.00 gram sample of this colloidal seed suspension was evaporated to dryness in a porcelain dish for 6 hours at 105 °C followed by 2 hours at 175 °C. The solids content of the suspension was 12.50 weight percent. Scanning electron micrograph (SEM) and X-ray diffraction (XRD) measurements on the dried powder showed that the product consisted of silicalite crystals of about 0.1 micron diameter. A 104000 * SEM micrograph and X-Ray diffractogram are given in Figure 1.

Comparative Example

MFI crystals were prepared in the absence of seed crystals. This example serves as a reference to show the effect using of seed crystals.

Preparation of Synthesis Mixture:

Component	Ingredients	Quantity in Grams
A (aluminate)	NaOH (98.4%) (Baker 0402)	1.353
	Al(OH) ₃ (99.3%) (Baker 0005)	0.205
	H ₂ O	10.03
	Rinse H ₂ O	10.08
B (silicate)	Ludox HS-40	66.73
C (TPA ⁺)	TPABr (Fluka 88105)	10.68
	H ₂ O	40.11
	Rinse H ₂ O	16.18

The ingredients forming solution A were weighed in a 50 ml glass beaker. The ingredients were dissolved in the water by boiling until clear. The solution was cooled to room temperature and the weight loss due to the boiling was corrected with water. The ingredients forming solution C were weighed in a 100 ml glass beaker. Solution B was weighed in the glass mixing beaker belonging to a household mixer. Solution C was added to the contents of the mixing beaker. The rinse water was used to quantitatively transfer solution C. Solutions B and C were mixed together for 2 minutes. Finally, solution A was added, together with the rinse water. The whole was mixed for 5 minutes. A just pourable and smooth synthesis mixture was obtained. The molar composition of the synthesis mixture was:

0.375 Na₂O/0.90 TPABr/0.0294 Al₂O₃/10 SiO₂/146 H₂O

The alkalinity of the synthesis mixture, expressed as the OH⁻/SiO₂ molar ratio was: 0.075.

CRYSTALLISATION: 103.43 grams of the synthesis mixture was transferred to a 150 ml stainless steel autoclave. The autoclave was placed without stirring in a room temperature oven. The oven was heated up linearly within 2 hours to 150 °C and kept at this temperature for 97 hours.

WASHING AND RECOVERY OF THE PRODUCT: The autoclave was cooled to room temperature and its content was collected in a one litre polypropylene centrifuge beaker. The product was separated from the mother liquor by centrifuging. The product was washed several times with water by reslurrying the product in water and subsequent separation by centrifuging. The pH of the last wash water was 9.2. The product was air-dried overnight at 98 °C. The weight of the product recovered was 20.0 grams.

CHARACTERISATION: XRD and SEM showed that the product was excellently crystalline ZSM-5 consisting of spheroidal crystallites with a size of about 14 microns.

The following examples illustrate the effect on the crystallite size when the synthesis mixture is seeded with very small amounts of seed crystal.

Example 1

Synthesis mixture seeded with about 3 wtppm seed crystals.

The 12.50 weight percent seed suspension was diluted with water to 0.127 weight percent.

Preparation of Synthesis Mixture

Component	Ingredients	Quantity in Grams
A (aluminate)	NaOH (98.4%) (Baker 0402)	1.355
	Al(OH) ₃ (99.3%) (Baker 0005)	0.20
	H ₂ O	10.16
	Rinse H ₂ O	15.35
B (silicate)	Ludox HS-40	66.73
C (TPA ⁺)	TPABr (Fluka 88105)	10.67
	H ₂ O	35.00
	Rinse H ₂ O	15.05
D (seed slurry)	seed slurry 0.127 wt% solids in H ₂ O	0.3313

Solution C was added to solution B, the two solutions were mixed for 2 minutes and the seed slurry D was added via a polypropylene pipette. The mixture B/C/D was mixed for 5 minutes. Finally solution A was added and the whole was again mixed for 5 minutes. The molar composition of the synthesis mixture was:

0.376 Na₂O/0.90 TPABr/0.0294 Al₂O₃/10 SiO₂/145 H₂O

Concentration of seed crystals in the synthesis mixture in mg/kg:

$$0.3313 \times 0.127 \times 10 \times \frac{10^3}{154.85} = 2.7$$

CRYSTALLISATION: 102.97 grams of the synthesis mixture was transferred to a 150 ml stainless steel autoclave. The autoclave was placed in a room temperature oven. The oven was heated-up linearly within 2 hours to 150 °C and was kept at this temperature for 97 hours. The synthesis mixture was not stirred during crystallisation.

The product was washed and recovered in the same way as described in the non-seeded comparative example. The weight of the product recovered was 19.7 grams. XRD and SEM showed that the product was excellently crystalline ZSM-5 consisting of spheroidal crystallites with a size of 4.2 microns. The crystallites were remarkably uniform in shape and size.

Examples 2 to 9

A series of eight synthesis mixtures were prepared which were seeded with respectively 10, 20, 30, 60, 200, 400, 800 and 1600 wtppm seed crystals. The molar composition of these synthesis mixtures was the same as in example 1, namely:

0.375 Na₂O/0.90 TPABr/0.0294 Al₂O₃/10 SiO₂/145 H₂O

To avoid unwanted seeding effects, the autoclaves used to crystallise the above eight synthesis mixtures were carefully cleaned. This was done by treating the autoclaves with a 5 M KOH solution for 16 hours at 150 °C. This treatment is believed to destroy zeolite crystals from a previous synthesis which may be adhering to the autoclave wall. The synthesis mixtures were crystallised under static conditions i.e. without stirring at 150 °C for 97 hours. The products were washed with water to pH about 9.2 and dried for 16 hours at 98 °C.

XRD showed that all products were excellently crystalline ZSM-5. SEM measurements showed that per batch the crystallites were remarkably uniform in size and shape, e.g. within one batch there was virtually no crystallite size distribution. SEM also showed that by varying the amount of seed crystals in the synthesis mixture the crystallite size can be very carefully controlled. The effect of the quantity of seed crystals on the crystallite diameter is given in figure 2.

In figure 3 SEM micrographs are shown of ZSM-5 crystals synthesized respectively without seeds, and with 2.7 ppm and 1600 ppm seeds.

Examples 10 to 16

Effect of seeds on the crystallite size of coffin-type silicalite.

A series of synthesis mixtures were prepared which upon crystallisation will give a so-called coffin-type morphology. These synthesis mixtures were seeded with various amounts of seed crystals. The source of the seed crystals was the colloidal seed suspension described earlier.

The molar composition of the synthesis mixtures was:

19.31 NH₄OH/1.40 TPABr/10 SiO₂/185 H₂O

The amount of seed crystals (based on the weight of the synthesis mixtures) in each example is given in Table 1 below:

Table 1

Example	Amount of Seed Crystals (ppm)
10	0
11	2.8
12	8.5
13	16.5
14	30
15	120
16	1200

The synthesis mixtures were crystallised in 300 ml stainless steel autoclaves at 175°C for 120 hours under static conditions. The products were recovered as described for Examples 1 to 9. The morphology and size of the crystals were examined by SEM. All products had the typical coffin-type morphology and were remarkably uniform in crystal shape and size. Depending on the amount of seeds the crystallite length varied from 30 microns (no seeds used) down to 0.5 microns (1200 wtppm seed). Figure 4 shows the relationship between the log of amount of seed in ppm and the log of average crystal length produced. An entry for Example 10, in which log of seeds (ppm) is - infinity, has been omitted.

In figure 5 SEM micrographs are shown of the coffin-type crystals synthesised respectively without seeds, and with 8.5 ppm and 1200 ppm seeds.

Example 17

This example shows the benefit of using colloidal silica, rather than a source of silica particles whose average diameter greatly exceeds 1µm.

Synthesis mixtures were prepared containing the following ingredients: (weight of reactants given in grams)

Colloidal Silica Mixture

Component	Ingredients	Quantity In Grams
A	NaOH (98.4%) (Baker 0402)	3.053
	H ₂ O	22.56
	Rinse H ₂ O	34.19
B	Ludox HS-40	150.28
C	TPABr(Fluka 88105)	24.05
	H ₂ O	80.06
	Rinse H ₂ O	33.98
D	Seed Slurry (3.12 wt% Solids)	0.2743

Solid Silica Mixture

Component	Ingredients	Quantity In Grams
A	NaOH (98.4%)	3.055
	H ₂ O	22.56
	Rinse H ₂ O	34.03
B	SiO ₂ (Baker)	66.78
C	TPABr (Fluka)	24.05
	H ₂ O	81.89
	Rinse H ₂ O	34.22
D	H ₂ O	81.42
E	Seed Slurry (3.12 wt% solids)	0.5594

To prepare the synthesis mixture using colloidal silica, the solutions B, C and D were mixed for five minutes in a household mixer. Solution A was added and the whole was again mixed for a further five minutes.

To prepare the mixture using solid silica, B was mixed with C, D and E for five minutes in a household mixer. A was added and the whole was again mixed for five minutes.

The compositions of the synthesis mixtures (molar ratio) are as follows:

Colloidal Silica : 0.376 Na₂O/0.90 TPA/10 SiO₂/145 H₂O plus 25 weight ppm seeds based on the total weight of synthesis mixture.

Solid Silica : 0.376 Na₂O/0.90 TPA/10 SiO₂/145 H₂O plus 50 weight ppm seeds based on the total weight of synthesis mixture.

310.25 grams of the colloidal silica synthesis mixture was transferred to a 300 millilitre stainless steel autoclave. 338.35 grams of the solid silica synthesis mixture was transferred to another 300 millilitre stainless steel autoclave. The autoclaves were placed in a room temperature oven and heated within two hours to 150 °C under static conditions. This temperature was maintained for 96 hours.

The products were washed and recovered as follows:

Colloidal Synthesis Mixture : washed four times with approximately 600 millilitres water. The last wash water had a pH of 8.6.

Solid Silica Mixture : washed five times with 600 milliliters of water. The last wash water had a pH of 8.8.

The products were dried overnight at 120 °C. 60.5 grams of product was obtained from the colloidal silica synthesis mixture. 59.7 grams of product was obtained from the solid silica synthesis mixture. Figure 6 shows SEM micrographs of the crystals produced. The upper micrographs show the crystals produced using colloidal silica in the synthesis mixture. (magnification 2500 * on the left, 10000 * on the right). The lower micrographs show the crystals produced using solid silica (magnification 1250 * on the left and 5000 *

on the right).

It can be seen that using solid silica results in a mixture of crystal sizes. Small crystals are produced where the silica has "seen" the seeds in the synthesis mixture. Large crystals are produced where the seeding effect has not taken place. Colloidal silica, resulting in an even distribution of silica throughout the synthesis mixture results in extremely uniform crystals.

Example 18

Production of fluoride silicalite at low alkalinity. This is based on Example 4 of US Patent 4073865 and demonstrates that the seeding technique is applicable to this process.

A comparison was made between crystals produced from a seeded and non-seeded synthesis mixture. The synthesis mixtures were prepared from the following ingredients (weight of reactants given in grams)

Non-seeded Mixture

Component	Ingredients	Quantity In Grams
A	TPABr (Fluka)	7.17
B	NH ₄ F (Ventron)	4.98
C	H ₂ O	75.05
	Rinse Water	13.27
D	Ludox AS-40	80.02

Seeded Mixture

Component	Ingredients	Quantity In Grams
A	TPABr(Fluka)	7.17
B	NH ₄ F (Ventron)	4.99
C	H ₂ O	75.03
	Rinse Water	11.40
D	Ludox AS-40	80.01
E	Colloidal Seed Mixture (12.5 wt% solids)	2.39

The colloidal seed mixture was prepared in accordance with the process previously described.

When preparing the non-seeded mixture, A and B were added to C, and mixed until a clear solution was obtained. D was poured into a high shear mixer, and the solution of A/B/C was added, together with the rinse water which was used to rinse the beaker which contained A/B/C. The whole mixture was then mixed for five minutes.

Preparation of the seeded mixture was carried out in the same way as for the non-seeded mixture, but the seed solution, E, was added to the Ludox (D) and mixed for a few seconds before the other ingredients were added.

The pH of each synthesis mixture was 7.8.

The compositions of the synthesis mixtures (expressed in moles) were as follows:

Non-seeded mixture : 0.51 TPABr/2.53 NH₄F/10 SiO₂/142 H₂O.

Seeded mixture : 0.51 TPABr/2.53 NH₄F/10 SiO₂/142 H₂O plus 1650 weight ppm seeds based on the weight of the gel.

The alkalinity of each synthesis mixture was extremely low expressed as OH⁻/SiO₂; this ratio was less than 0.01.

154.05 grams of the non-seeded mixture was placed in a stainless steel autoclave. 154.23 grams of the seed mixture was placed in a second stainless steel autoclave. The autoclaves were placed in a room

temperature oven and heated within 30 minutes to 185°C. This temperature was maintained for 73 hours. The mixture was not stirred during this time.

Recovery of Product

The non-seeded mixture had a mother liquor with a pH of 8.5. This product was washed with five portions of approximately 600 milliliters of water. The last wash water had a pH of 7.2.

The seeded mixture had a mother liquor with a pH of 8.6. This product was washed with four portions of approximately 700 milliliters of water. The last wash water had a pH of 7.3.

The products were dried overnight at 95°C. The non-seeded mixture gave 28.4 grams of product (product yield 18.4 weight percent). The seeded mixture gave 32.0 grams of product (product yield 20.8 weight percent).

The product obtained from the seeded synthesis mixture was calcined in air to remove the organic additive. The material was heated up from room temperature to 500°C at a rate of 2°C per minute, and held at 500°C for 12 hours. The weight loss on calcination was 12.5 weight percent, given a product yield after calcination of 18.2 percent. The higher product yield indicates that this type of synthesis is very effective, the mother liquor should be completely depleted of silica. The weight of SiO₂ in the seeded gel was 27.3 grams. The weight of seed crystals in the gel was 0.255 grams. Assuming that the seed crystals contain approximately 12.5 weight percent of organic additives, the weight of calcined seed is $0.255 - (0.125 \times 0.255) = 0.233$ grams.

The theoretical weight of solids which can be obtained from this synthesis mixture is therefore $27.3 + 0.2 = 27.5$ grams. The actual calcined product obtained was 28.0 grams. This demonstrates the effectiveness of the seeded process.

Figure 7 shows the SEM micrographs of zeolite crystals prepared by this example. The upper left hand micrograph shows the crystals produced from the unseeded synthesis mixture (magnification 1250×). The upper right hand micrograph shows at the same magnification the much smaller crystals produced using the seeded mixture. Small, amorphous portions remaining in the unseeded mixture can be seen in the micrograph as specks or dots on or attached to the coffin-shaped crystals.

The lower micrographs show the crystals produced from the seeded mixture at higher magnification (10,000 times on the left; 40,000 times on the right). It can be seen from this that the seed mixture has produced well formed, uniform crystals.

The average crystallite length produced from the unseeded mixture is about 60 to 70 microns. In the seeded mixture, the crystals produced have a length of approximately 1 micron.

Claims

1. A process for the preparation of an MFI-type zeolite comprising mixing:
 - (i) a source of particulate silica in which silica particles present have an average diameter of 1 µm or less;
 - (ii) seeds of an MFI zeolite having an average diameter of 100 nm or less in the form of a colloidal suspension;
 - (iii) an organic structure directing agent; and
 - (iv) a source of fluorine or an alkali metal;
 to form an aqueous synthesis mixture, the seeds being present in an amount of 0.05 to 1700 ppm by weight of the synthesis mixture, and the synthesis mixture having an alkalinity, expressed as a molar ratio of OH⁻/SiO₂, of less than 0.1, and allowing the synthesis mixture to crystallise.
2. A process according to claim 1 in which the seed suspension has a pH of 8 or more.
3. A process according to claim 1 or 2 in which the synthesis mixture is crystallised at 140 to 200°C.
4. A process according to any one of claims 1 to 3 in which the crystallisation time is 65 to 150 hours.
5. A process according to any one of the preceding claims in which the crystals produced have an average diameter or length of 0.3 to 30 micrometers.
6. A process according to any one of the preceding claims in which the synthesis mixture also comprises a source of aluminium, gallium, boron, iron, zinc or vanadium.

temperature oven and heated within 30 minutes to 185°C. This temperature was maintained for 73 hours. The mixture was not stirred during this time.

Recovery of Product

The non-seeded mixture had a mother liquor with a pH of 8.5. This product was washed with five portions of approximately 600 milliliters of water. The last wash water had a pH of 7.2.

The seeded mixture had a mother liquor with a pH of 8.6. This product was washed with four portions of approximately 700 milliliters of water. The last wash water had a pH of 7.3.

The products were dried overnight at 95°C. The non-seeded mixture gave 28.4 grams of product (product yield 18.4 weight percent). The seeded mixture gave 32.0 grams of product (product yield 20.8 weight percent).

The product obtained from the seeded synthesis mixture was calcined in air to remove the organic additive. The material was heated up from room temperature to 500°C at a rate of 2°C per minute, and held at 500°C for 12 hours. The weight loss on calcination was 12.5 weight percent, given a product yield after calcination of 18.2 percent. The higher product yield indicates that this type of synthesis is very effective, the mother liquor should be completely depleted of silica. The weight of SiO₂ in the seeded gel was 27.3 grams. The weight of seed crystals in the gel was 0.255 grams. Assuming that the seed crystals contain approximately 12.5 weight percent of organic additives, the weight of calcined seed is $0.255 - (0.125 \times 0.255) = 0.233$ grams.

The theoretical weight of solids which can be obtained from this synthesis mixture is therefore $27.3 + 0.2 = 27.5$ grams. The actual calcined product obtained was 28.0 grams. This demonstrates the effectiveness of the seeded process.

Figure 7 shows the SEM micrographs of zeolite crystals prepared by this example. The upper left hand micrograph shows the crystals produced from the unseeded synthesis mixture (magnification 1250×). The upper right hand micrograph shows at the same magnification the much smaller crystals produced using the seeded mixture. Small, amorphous portions remaining in the unseeded mixture can be seen in the micrograph as specks or dots on or attached to the coffin-shaped crystals.

The lower micrographs show the crystals produced from the seeded mixture at higher magnification (10,000 times on the left; 40,000 times on the right). It can be seen from this that the seed mixture has produced well formed, uniform crystals.

The average crystallite length produced from the unseeded mixture is about 60 to 70 microns. In the seeded mixture, the crystals produced have a length of approximately 1 micron.

Claims

1. A process for the preparation of an MFI-type zeolite comprising mixing:
 - (i) a source of particulate silica in which silica particles present have an average diameter of 1 µm or less;
 - (ii) seeds of an MFI zeolite having an average diameter of 100 nm or less in the form of a colloidal suspension;
 - (iii) an organic structure directing agent; and
 - (iv) a source of fluorine or an alkali metal;
 to form an aqueous synthesis mixture, the seeds being present in an amount of 0.05 to 1700 ppm by weight of the synthesis mixture, and the synthesis mixture having an alkalinity, expressed as a molar ratio of OH⁻/SiO₂, of less than 0.1, and allowing the synthesis mixture to crystallise.
2. A process according to claim 1 in which the seed suspension has a pH of 8 or more.
3. A process according to claim 1 or 2 in which the synthesis mixture is crystallised at 140 to 200°C.
4. A process according to any one of claims 1 to 3 in which the crystallisation time is 65 to 150 hours.
5. A process according to any one of the preceding claims in which the crystals produced have an average diameter or length of 0.3 to 30 micrometers.
6. A process according to any one of the preceding claims in which the synthesis mixture also comprises a source of aluminium, gallium, boron, iron, zinc or vanadium.



7. A process according to any one of the preceding claims in which the organic structure directing agent is a tetraethyl ammonium, tetrapropyl ammonium or tetrabutyl ammonium compound.
8. A process according to claim 7 in which the organic structure directing agent is a tetrapropyl ammonium compound.
9. A process according to any one of the preceding claims in which the zeolite produced is calcined.
10. A catalyst or catalyst carrier comprising a zeolite of size from 30 microns to 0.3 microns the variance in diameter of spherical crystals or in length of rhomboid or similar shaped crystals being less than 10% of the average diameter or length produced according to the process of any one of the preceding claims.
11. An adsorbent comprising a zeolite of size from 30 microns to 0.3 microns the variance in diameter of spherical crystals or in length of rhomboid or similar shaped crystals being less than 10% of the average diameter or length produced according to the process of any one of the preceding claims.
12. Use of seeds of an MFI-type zeolite having an average diameter of 100 nm or less in the form of a colloidal suspension, to control the size of MFI-type zeolite crystals produced from a synthesis mixture containing a source of particulate silica in which silica particles have an average diameter of 1 μm or less, the synthesis mixture having an alkalinity, expressed as a molar ratio of OH^-/SiO_2 , of less than 0.1, the seeds being used in an amount of 0.05 to 1700 ppm based on the weight of the synthesis mixture.

25 Patentansprüche

1. Verfahren zur Herstellung von Zeolith vom MFI-Typ, bei dem
 - (i) eine Quelle von teilchenförmigem Siliciumdioxid, in der die vorhandenen Siliciumdioxidteilchen einen mittleren Durchmesser von 1 μm oder weniger aufweisen;
 - (ii) Impfkristalle von MFI-Zeolith mit einem mittleren Durchmesser von 100 nm oder weniger in Form einer kolloidalen Suspension;
 - (iii) ein organisches strukturdirigierendes Mittel und
 - (iv) eine Fluorquelle oder eine Alkalimetallquelle
 unter Bildung einer wäßrigen Synthesemischung gemischt werden, wobei die Impfkristalle in einer Menge von 0,05 bis 1700 Gew.ppm der Synthesemischung vorhanden sind und die Synthesemischung eine Basizität, ausgedrückt als Molverhältnis von OH^-/SiO_2 , von weniger als 0,1 aufweist, und die Synthesemischung kristallisieren gelassen wird.
2. Verfahren nach Anspruch 1, bei dem die Impfkristallsuspension einen pH-Wert von 8 oder darüber aufweist.
3. Verfahren nach Anspruch 1 oder 2, bei dem die Synthesemischung bei 140 bis 200 °C kristallisiert wird.
4. Verfahren nach einem der Ansprüche 1 bis 3, bei dem die Kristallisationszeit 65 bis 150 Stunden beträgt.
5. Verfahren nach einem der vorhergehenden Ansprüche, bei dem die hergestellten Kristalle einen mittleren Durchmesser oder eine mittlere Länge von 0,3 bis 30 μm aufweisen.
6. Verfahren nach einem der vorhergehenden Ansprüche, bei dem die Synthesemischung auch eine Aluminium-, Gallium-, Bor-, Eisen-, Zink- oder Vanadiumquelle umfaßt.
7. Verfahren nach einem der vorhergehenden Ansprüche, bei dem das organische strukturdirigierende Mittel eine Tetraethylammonium-, Tetrapropylammonium- oder Tetrabutylammoniumverbindung ist.
8. Verfahren nach Anspruch 7, bei dem das organische strukturdirigierende Mittel eine Tetrapropylammoniumverbindung ist.



9. Verfahren nach einem der vorhergehenden Ansprüche, bei dem der hergestellte Zeolith calciniert wird.
10. Katalysator oder Katalysatorträger, der nach dem Verfahren gemäß einem der vorhergehenden Ansprüche hergestellten Zeolith mit einer Größe von 30 μm bis 0,3 μm umfaßt, bei dem die Varianz des Durchmessers von kugelförmigen Kristallen oder der Länge von rhomboid oder ähnlich geformten Kristallen weniger als 10 % des mittleren Durchmessers oder der mittleren Länge beträgt.
11. Adsorbens, das nach dem Verfahren gemäß einem der vorhergehenden Ansprüche hergestellten Zeolith mit einer Größe von 30 μm bis 0,3 μm umfaßt, bei dem die Varianz des Durchmessers von kugelförmigen Kristallen oder der Länge von rhomboid oder ähnlich geformten Kristallen weniger als 10 % des mittleren Durchmessers oder der mittleren Länge beträgt.
12. Verwendung von Impfkristallen aus Zeolith vom Typ MFI mit einem Durchmesser von 100 nm oder weniger in Form einer kolloidalen Suspension zur Steuerung der Größe von Zeolithkristallen vom MFI-Typ, die aus einer Synthesemischung hergestellt sind, die eine Quelle von teilchenförmigem Siliciumdioxid enthält, in der die vorhandenen Siliciumdioxidteilchen einen mittleren Durchmesser von 1 μm oder weniger aufweisen, wobei die Synthesemischung eine Basizität, ausgedrückt als Molverhältnis von OH^-/SiO_2 , von weniger als 0,1 aufweist und die Impfkristalle in einer Menge von 0,05 bis 1700 ppm, bezogen auf das Gewicht der Synthesemischung, verwendet werden.

Revendications

1. Procédé de préparation d'une zéolite du type MF1, comprenant les étapes consistant à mélanger :
 - (i) une source de silice en particules, dans laquelle les particules de silice présentes ont un diamètre moyen égal ou inférieur à 1 μm ;
 - (ii) des germes d'une zéolite MF1 ayant un diamètre moyen égal ou inférieur à 100 nm, sous forme d'une suspension colloïdale ;
 - (iii) un agent organique dirigeant la structure ; et
 - (iv) une source de fluor ou d'un métal alcalin ;
 pour former un mélange aqueux de synthèse, les germes étant présents en une quantité de 0,05 à 1700 ppm en poids du mélange de synthèse, et le mélange de synthèse ayant une alcalinité, exprimée par un rapport molaire OH^-/SiO_2 , inférieure à 0,1, et à laisser le mélange de synthèse cristalliser.
2. Procédé suivant la revendication 1, dans lequel la suspension de germes a un pH égal ou supérieur à 8.
3. Procédé suivant la revendication 1 ou 2, dans lequel le mélange de synthèse est cristallisé à une température de 140 à 200 °C.
4. Procédé suivant l'une quelconque des revendications 1 à 3, dans lequel le temps de cristallisation est compris dans l'intervalle de 65 à 150 heures.
5. Procédé suivant l'une quelconque des revendications précédentes, dans lequel les cristaux produits ont un diamètre moyen ou une longueur moyenne de 0,3 à 30 micromètres.
6. Procédé suivant l'une quelconque des revendications précédentes, dans lequel le mélange de synthèse comprend également une source d'aluminium, de gallium, de bore, de fer, de zinc ou de vanadium.
7. Procédé suivant l'une quelconque des revendications précédentes, dans lequel l'agent organique dirigeant la structure est un composé de tétraéthylammonium, un composé de tétrapropylammonium ou un composé de tétrabutylammonium.
8. Procédé suivant la revendication 7, dans lequel l'agent organique dirigeant la structure est un composé de tétrapropylammonium.
9. Procédé suivant l'une quelconque des revendications précédentes, dans lequel la zéolite produite est calcinée.



10. Catalyseur ou support de catalyseur comprenant une zéolite ayant un diamètre de 30 micromètres à 0,3 micromètre, la variance du diamètre des cristaux sphériques ou de la longueur des cristaux rhomboïdaux ou de forme similaire étant inférieure à 10 % du diamètre moyen ou de la longueur moyenne obtenu conformément au procédé suivant l'une quelconque des revendications précédentes.
11. Adsorbant comprenant une zéolite ayant un diamètre de 30 micromètres à 0,3 micromètre, la variance du diamètre des cristaux sphériques ou de la longueur des cristaux rhomboïdaux ou de forme similaire étant inférieure à 10 % du diamètre moyen ou de la longueur moyenne obtenu conformément au procédé suivant l'une quelconque des revendications précédentes.
12. Utilisation de germes d'une zéolite du type MF1 ayant un diamètre moyen égal ou inférieur à 100 nm sous forme d'une suspension colloïdale, pour ajuster les dimensions de cristaux de zéolite du type MF1 produits à partir d'un mélange de synthèse contenant une source de silice en particules, dans lequel les particules de silice ont un diamètre moyen égal ou inférieur à 1 μ m, le mélange de synthèse ayant une alcalinité, exprimée par un rapport molaire OH^-/SiO_2 , inférieure à 0,1, les germes étant utilisés en une quantité de 0,05 à 1700 ppm sur la base du poids du mélange de synthèse.

