

Shape selective acid catalyzed reactions of olefins over crystalline zeolites

This invention relates to reactions of olefins catalyzed by shape selective acidic crystalline zeolites.

The present invention provides a process for conducting preferential acid catalyzed reactions of smaller olefins in mixed stream with larger olefins, the smaller olefins having an effective critical dimension of 6.8 Angstroms and less and the larger olefins having an effective critical dimension in excess of 6.8 Angstroms, which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

Acid catalyzed reactions of olefins comprise isomerization; alkylation, addition reactions, e.g. hydrogen halide addition, hydration, alcohol addition and the Prins reaction; dimerization; oligomerization; and polymerization; aromatization; cracking and hydrocracking.

Alkylation of aromatic hydrocarbons with an olefin in the presence of a crystalline metallic aluminosilicate having uniform pore openings of about 6 to 15 Angstrom units is described in U.S. Patent No. 2,904,607. U.S. Patent No. 3,251,897 describes alkylation of aromatic hydrocarbons in the presence of X- or Y-type crystalline aluminosilicate zeolites, specifically such type zeolites wherein the cation is rare earth and/or hydrogen.

The present invention further provides a process for conducting preferential acid catalyzed reactions, of linear olefins in mixed stream with branched-chain olefins, both linear and branched-chain olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the mixed streams with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

The present invention also provides a process for conducting preferential acid catalyzed reactions of lesser branched olefins in mixed streams with higher branched olefins, both lesser branched olefins and higher branched olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

The present invention also provides a process for conducting preferential acid catalyzed reactions of para-disubstituted and/or mono-substituted aromatic olefins in mixed stream with ortho- and/or meta-disubstituted or more highly substituted aromatic olefins which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

U.S. Patent Nos. 3,751,504 and 3,751,506 describe vapor phase alkylation of aromatic hydrocarbons with olefins, e.g. benzene with ethylene, in the presence of a ZSM-5 type zeolite catalyst.

U.S. Patent Nos. 3,631,120 and 3,641,177 describe a liquid phase process for the alkylation of aromatic hydrocarbons with olefins in the presence of certain zeolites.

Polymerization of olefins over HZSM-38 is disclosed in U.S. Patent No. 4,046,859.

A process for producing Prins-type condensation products (addition reaction) is described in U.S. Patent 3,414,588. The catalyst employed in this reaction of an aldehyde and an olefin is a faujasite-type zeolite.

Processes for the aromatization of olefins are described in U.S. Patent Nos. 3,760,024 and 3,960,978. These processes utilize a ZSM-5 type acidic zeolite catalyst.

It has long been known to contact various hydrocarbon fractions with acidic catalysts and, in particular, with solid siliceous acidic catalysts including those referred to as crystalline zeolites. Contact of the hydrocarbon feed with the acid catalysts was carried out for a wide variety of reactions including cracking, isomerization and hydrocracking. Representative U.S. patents disclosing and claiming the contacting of various hydrocarbon fractions with crystalline zeolites are U.S. Patent Nos. 3,140,249, 3,140,251, 3,140,253 and 3,140,322.

The use of acid Mordenite for cracking, alkylation, isomerization and olefin polymerization is disclosed in U.S. Patent No. 3,597,493.

U.S. Patent No. 3,758,602 describes a process for selectively cracking polar compounds from non-polar saturated hydrocarbons in the presence of a crystalline aluminosilicate catalyst.

In accordance with the present invention, there has now been discovered a process for conducting acid catalyzed reactions of olefins. Smaller olefins, defined as having an "effective critical dimension" of 6.8 Angstroms or less, as measured on molecular models, will react in the presence of the acid zeolite catalysts used in this invention, while larger olefins, i.e. having an "effective critical dimension" in excess of 6.8 Angstroms will not react. Further, of these "smaller olefins", linear olefins will react preferentially over the acid zeolite catalysts as they occur in mixed streams with branched-chain (nonlinear) olefins. Also lesser branched-chain olefins of the class of smaller olefins will react preferentially as they occur in mixed streams with greater branched isomers over the acid zeolite catalysts. Also of this class of "smaller olefins", para-disubstituted aromatic olefins and/or mono-

substituted aromatic olefins will react preferentially over ortho- and/or meta-disubstituted or more highly substituted aromatic olefins when contacted with the acid zeolite catalysts.

The zeolite catalysts used in the present invention change the relative acid catalyzed reactivities of olefins from that observed over conventional acid catalysts, e.g. other zeolites, silica-alumina, hydrofluoric acid and sulfuric acid. In some cases, the order of acid catalyzed activity is unexpectedly, completely reversed. For example, whereas branched-chain olefins are more reactive over linear olefins when contacted by conventional acid catalysts, use of the acid zeolite catalysts according to the present invention results in linear olefins reacting in preference to branched olefins. Similarly, lesser branched olefins react preferentially over greater branched olefins when in contact with the acid zeolite catalysts according to this invention.

The catalysts utilized in this invention comprise acidic crystalline zeolites and acidic crystalline zeolites modified to increase their shape selective potential. The zeolites are characterized by a silica to alumina mole ratio of at least 12 and a constraint index, as hereinafter defined, of from greater than 2 to 12.

According to the present invention, a mixed stream of olefins is contacted over the acidic crystalline zeolites in order to carry out acid catalyzed reactions of olefins.


In one aspect of this invention, smaller olefins having an "effective critical dimension" of 6.8 Angstroms or less, as measured on molecular models, will react when contacted with the acid zeolite catalysts while larger olefins will not react, i.e. olefins having an "effective critical dimension" of greater than 6.8 Angstroms.

The "effective critical dimension" of a molecular is described by Breck in *Zeolite Molecular Sieves*, John Wiley & Sons, Inc. (1974), pages 633—641. Generally, this dimension is the smallest dimension that will permit passage through the pores of the zeolite, i.e. the dimension that most nearly approaches the pore size of the zeolite. For example, the critical dimension of n-hexane is the thickness not the length while the critical dimension for benzene is the cross-sectional diameter, rather than the thickness.

Various olefins may be employed in the process of this invention. These olefins may be mono-olefins or diolefins and may be acyclic monoolefins or acyclic diolefins and cyclic monoolefins or cyclic diolefins. The diolefins may be conjugated or non-conjugated. The acyclic monoolefins may be straight chain or branched chain monoolefins and may contain from 2 to 200 carbon atoms. Preferably, however, the acyclic monoolefins contain from 2 to 92 carbon atoms and, still more preferably, from 2 to 10 carbon atoms. The acyclic diolefins may contain from 3 to 8 carbon atoms. The cyclic mono-olefins and the cyclic diolefins may contain from 5 to 8 carbon atoms. The acyclic monoolefins may contain one or more aromatic groups, preferably phenyl groups, chlorine or bromine substituents or a carboxy or carboxymethyl substituent.

Suitable olefins include ethylene, propylene, the butenes, pentenes, hexenes, heptenes, octenes, monenes, and decenes. Other acyclic monoolefins which may be employed are olefin oligomers such as propylene and isobutylene tetramer, isobutylene trimer, and propylene pentamer and hexamer. Other suitable olefins include allene, butadiene, pentadiene, isoprene, biallyl, heptadiene, and bimethallyl. Still other suitable olefins include cyclopentene, cyclohexene, cycloheptene, cyclooctene, cyclopentadiene, cyclohexadiene, cycloheptadiene, and cyclooctadiene. Acyclic monoolefins containing one or more aromatic groups includes styrene, methyl styrene, stilbene, 1,1-diphenyl ethylene, and methyl cinnamate. Representative olefins containing chlorine, bromine, carboxy or carboxymethyl substituents includes bromostyrene, methyl cinnamate, methylacrylate, dimethyl maleate, polychloroethylene, oleic acid and methyl oleate.

It will be seen that the foregoing olefins are those of the formula



wherein one or more of the R's are hydrogen, straight or branched chain alkyl, aryl, alkaryl or aralkyl groups, the total number of carbon atoms in the alkyl groups being between 1 and 198, an alkenyl group containing 1 to 100 carbon atoms. Each of these above constituent groups may contain one or more substituents such as halogens, e.g. chlorine or bromine; carbonyl; carboxy; or carboxyalkyl. Also included are olefins where two R groups are connected to form a cyclic structure of total ring size ranging from 4 to 10 carbon atoms.

Examples of "smaller olefins" include all linear olefins, e.g. propylene, butylene, hexene and decene; methyl-branched olefins, such as isobutylene; dimethyl-branched olefins; and some aromatic-containing olefins such as styrene and allylbenzene. Examples of "larger olefins" include 1-allyl-naphthalene, 3,5-dimethylstyrene and cyclooctene.

In another aspect of this invention, such "smaller olefins" are preferentially reacted when in mixed streams depending on branching and aromatic substitution, e.g. para, ortho or meta. Linear olefins will

preferentially react when in mixed streams with non-linear olefins over the acidic zeolite catalysts used in this invention.

Examples of such linear olefins include ethylene, propylene, pentene, heptene and nonene. Examples of branched olefins include 2-methylpropene; 3,3-dimethyl-1-butene and 4-methyl-2-pentene. Similarly, lesser branched olefins such as mono-alkyl olefins will react preferentially over greater branched olefins such as di- or polyalkyl substituted olefin when in contact with the acidic zeolite catalysts. For example, 2-methylpropene will react preferentially over 3,3-dimethyl-1-butene. Further, a monomethyl substituted olefin will preferentially react relative to an ethyl or larger substituted olefin.


In a further aspect of the present invention dealing with such "smaller olefins", para-disubstituted aromatic olefins or mono-substituted aromatic olefins are preferentially reacted when in mixed streams with ortho- or meta-disubstituted or more highly substituted aromatic olefins. Examples of such selective acid catalyzed reactions include the selective reaction of para-methylstyrene in mixed stream with ortho-methylstyrene and the selective reaction of para-allyltoluene in mixed stream with meta-allyltoluene.

All acid catalyzed reactions of olefins such as isomerization, alkylation, addition, dimerization, oligomerization, polymerization, aromatization, cracking, and hydrocracking would be shape selective over the crystalline zeolites used in this invention.

The selective acid catalyzed reactions of this invention can also be utilized to selectively separate small amounts of the reactive olefins from the less reactive olefins. For example, para divinyl benzene can be separated from ortho-divinyl benzene by selective reaction of the para compounds.


Isomerization reactions include both the alteration of the arrangement of atoms in a molecule without changing the total number of atoms, i.e. skeletal atom isomerization, or the rearrangement of multiple bond, i.e. double bond isomerization. Conversion conditions for isomerization include a temperature of from 232°C (450°F) to 538°C (1000°F), a pressure of from 101 kPa (0 psig) to 3549 kPa (500 psig), a WHSV of from 0.1 to 200 hr⁻¹, and a hydrogen to olefin mole ratio of from 0.1 to 100.

The addition of an alkene (olefin) to an alkane (paraffin) over an acid is one example of an alkylation reaction. This reaction is represented by the following general formula:




An important alkylation reaction of this type is the addition of isobutylene to isobutane in the presence of acid catalysts to form 2,2,4-trimethylpentane, an aviation fuel. Alkylations can also involve the addition of olefins to aromatic hydrocarbons. Typical of such aromatic alkylation is the combination of ethylene and benzene to form ethylbenzenes. Conditions for conducting alkylations include a temperature of from 38°C (100°F) to 510°C (950°F), a pressure of from 101 kPa (0 psig) to 6996 kPa (1000 psig) and a WHSV of from 1 to 500.

Hydration is the addition of water to an olefin to form an alcohol in the presence of an acid catalyst. This reaction is represented by the following general formula:



Hydration reactions can be conducted at temperatures in the approximate range of from 66°C (150°F) to 316°C (600°F) and at pressures of from atmospheric to 10133 kPa (100 atmospheres).

Hydrogen halide addition is the reaction of an olefin with hydrogen chloride, hydrogen bromide or hydrogen iodide. A typical reaction of this kind is represented by the following general equation:



wherein X=Cl, Br, or I.

Addition reactions of this nature can be conducted at temperatures below 649°C (1200°F) and at pressures ranging from atmospheric to 10133 kPa (100 atmospheres).

Another addition reaction is the Prins reaction. Prins-type products include alcohols, glycols, diolefins and alkyl m-dioxanes. In a typical Prins reaction, an aldehyde is reacted with an olefin in the

presence of an acid catalyst. For example, the reaction of formaldehyde and isobutylene will produce a product mixture of 4,4-dimethyl-m-dioxane and 3-methyl-1,3-butanediol. The Prins reaction can be conducted at temperatures ranging from room temperature up to about 427°C (800°F).

Also included in the class of acid catalyzed addition reactions is alcohol addition to olefins to form ethers. Conditions for conducting such alcohol addition are similar to those described above for hydration.

Dimerization involves the addition of alkenes (olefins) in the presence of an acid catalyst. Dimerization conditions include a temperature of from 93°C (200°F) to 649°C (1200°F), a pressure of from atmospheric to 10133 kPa (100 atmospheres), preferably from atmospheric to 2533 kPa (25 atmospheres) and a WHSV of from 0.1 to 30 hr⁻¹, preferably, 0.5 to 10. A typical dimerization reaction involves the addition of two propylene molecules to form dimethylbutenes.

Oligomerization and polymerization involve the linking of similar molecules in the presence of heat and a catalyst to form larger molecules. Oligomerization involves the forming of dimers, trimers and quatramers, whereas a typical polymerization concerns the joining of light olefins to form a very long chain olefin. Olefin oligomerization and polymerization conditions include a temperature of from 35°C (95°F) to 502°C (935°F), preferably from 199°C (390°F) to 432°C (810°F), a pressure of from atmospheric to 69049 kPa (10,000 psig), preferably from atmospheric to 27680 kPa (4000 psig), especially to 13890 kPa (2,000 psig), a WHSV (when a flow operation) of from 0.1 hr⁻¹ to 50 hr⁻¹, preferably from 0.5 hr⁻¹ to 10 hr⁻¹, and a contact time (when a batch operation) of from 0.1 hour to 48 hours, preferably from 0.5 hour to 24 hours and a hydrogen/olefin mole ratio of from 0 to 20, preferably from 0 to 10.

A typical aromatization is the reaction of a feed stream containing essentially C₂—C₄ paraffins (ethane, propane, butane, isobutane) and/or olefins (ethylene, propylene, butene, isobutene), and mixtures thereof with an acidic catalyst to produce predominantly C₆—C₁₀ aromatics.

When the acid catalyzed reaction is aromatization, catalytic conversion conditions include a temperature of from 288°C (550°F) to 649°C (1200°F), preferably from 343°C (650°F) to 593°C (1100°F), a pressure of from atmospheric to 69049 kPa (10,000 psig), preferably from atmospheric to 27680 kPa (4000 psig), especially to 13890 kPa (2000 psig), a WHSV (when a flow operation) of from 0.1 hr⁻¹ to 10 hr⁻¹, preferably from 1 hr⁻¹ to 5 hr⁻¹, a contact time (when a batch operation) of from 0.1 hour to 48 hours, preferably from 1 hour to 24 hours and a hydrogen/olefin mole ratio of from 0 to 20, preferably from 0 to 10.

Further, when the acid catalyzed reaction of the present invention is cracking, catalytic conversion conditions should be maintained within certain ranges, including a temperature of from 371°C (700°F) to 649°C (1200°F), preferably from 427°C (800°F) to 593°C (1100°F), a pressure of from atmospheric to 1480 kPa (200 psig), a WHSV (when a flow operation) of from 0.5 hr⁻¹ to 50 hr⁻¹, preferably from 1 hr⁻¹ to 10 hr⁻¹, and a contact time (when a batch operation) of from 0.01 hour to 24 hours, preferably from 0.1 hour to 10 hours.

When the reaction is hydrocracking, catalytic conversion conditions should be maintained within somewhat different ranges, including a temperature of from 204°C (400°F) to 538°C (1000°F), preferably from 260°C (500°F) to 454°C (850°F), a pressure of from 3549 kPa (500 psig) to 24233 kPa (3500 psig), a WHSV (when a flow operation) of from 0.1 hr⁻¹ to 10 hr⁻¹, preferably from 0.2 hr⁻¹ to 5 hr⁻¹, a contact time (when a batch operation) of from 0.01 hour to 24 hours, preferably from 0.2 hour to 5 hours and a hydrogen/olefin mole ratio of from 1 to 20, preferably from 3 to 10. The hydrocracking catalyst may contain a metal such as platinum, nickel and palladium.

The class of crystalline zeolites used in this invention is characterized by a constraint index, as hereinafter defined, of from greater than 2 to 12 and a silica to alumina ratio of at least 12.

In reactions dealing with the "smaller olefins", selectivity for the preferred olefins can be increased by various modifications of the zeolites used in this invention. Such modifications include partial ion exchange with bulky cations, the use of larger crystal sizes for the zeolites, and coke selectivation of the zeolites. To increase selectivity, bulky cations such as the heavy metals of Group IA of the Periodic Table of Elements, e.g., rubidium and cesium, and tetramethylammonium (TMA) can be exchanged onto the zeolites used in this invention.

Another method to increase selectivity is to utilize larger crystal sizes for the zeolites employed in this invention. Thus use of a zeolite with a crystal size of 0.5 to 100 microns and larger (hereinafter referred to as larger crystal size zeolite) will be more selective than the same zeolite with a crystal size of 0.02 to 0.5 microns (hereinafter referred to as small crystal size zeolite).

Still another method to increase selectivity is coke selectivation. Coke selectivation involves depositing an amount of carbon on the zeolite used in this invention to improve its selectivity in an amount of at least 2 weight percent and generally not exceeding 60 weight percent.

The zeolite catalysts herein described are members of a novel class of zeolites exhibiting some unusual properties. These catalysts induce profound transformations of aliphatic hydrocarbons to aromatic hydrocarbons in commercially desirable yields and are generally highly effective in conversion reactions involving aromatic hydrocarbons. Although they have unusually low alumina contents, i.e. high silica to alumina mole ratios, they are very active even when the silica to alumina mole ratio exceeds 30. The activity is surprising, since catalytic activity for such transformations is generally

attributed to framework aluminum atoms and cations associated with these aluminum atoms. These catalysts retain their crystallinity for long periods in spite of the presence of steam at high temperature which induces irreversible collapse of the framework of other zeolites, e.g. of the X and A type. Furthermore, carbonaceous deposits, when formed, may be removed by burning at higher than usual temperatures to restore activity. In many environments, the zeolites of this class exhibit very low coke forming capability, conducive to very long times on stream between burning regenerations.

An important characteristic of the crystal structure of this class of zeolites is that it provides constrained access to, and egress from, the intracrystalline free space by virtue of having a pore dimension greater than 5 Angstroms and pore windows of a size such as would be provided by 10-membered rings of silicon atoms interconnected by oxygen atoms. It is to be understood, of course, that these rings are those formed by the regular disposition of the tetrahedra making up the anionic framework of the crystalline zeolite the oxygen atoms themselves being bonded to the silicon or aluminum atoms as the centers of the tetrahedra. Briefly, the preferred type catalyst useful in this invention possesses, in combination: a silica to alumina mole ratio of at least 12 and a structure providing constrained access to the crystalline free space.

The silica to alumina mole ratio referred to may be determined by conventional analysis. This ratio is meant to represent, as closely as possible, the ratio in the rigid anionic framework of the zeolite crystal and to exclude aluminum in the binder or in cationic or other form within the channels. Although catalysts with a silica to alumina mole ratio of at least 12 are useful, it is preferred to use catalysts having higher ratios of at least 30. Such catalysts, after activation, acquire an intracrystalline sorption capacity for normal hexane which is greater than that for water, i.e. they exhibit "hydrophobic" properties.

The zeolites useful in this invention freely sorb normal hexane and have a pore dimension greater than 5 Angstroms. In addition, the structure must provide constrained access to larger molecules. It is sometimes possible to judge from a known crystal structure whether such constrained access exists. For example, if the only pore windows in a crystal are formed by 8-membered rings of silicon and aluminum atoms, then access by molecules of larger cross-section than normal hexane is excluded and the zeolite is not of the desired type. Windows of 10-membered rings are preferred, although, in some instances, excessive puckering or pore blockage may render these zeolites ineffective. Twelve-membered rings do not generally appear to offer sufficient constraint to produce the advantageous selectivities, although puckered structures exist such as TMA offretite which is a known effective zeolite.

Rather than attempt to judge from crystal structure whether or not a catalyst possesses the necessary constrained access, a simple determination of the "constraint index" may be made by passing continuously a mixture of an equal weight of normal hexane and 3-methylpentane over a small sample, approximately 1 gram or less, of catalyst at atmospheric pressure according to the following procedure. A sample of the catalyst, in the form of pellets or extrudate, is crushed to a particle size that of coarse sand and mounted in a glass tube. Prior to testing, the catalyst is treated with a stream of air at 538°C (1000°F) for at least 15 minutes. The catalyst is then flushed with helium and the temperature adjusted between 288°C (550°F) and 510°C (950°F) to give an overall conversion between 10% and 60%. The mixture of hydrocarbons is passed at 1 liquid hourly space velocity (i.e. 1 volume of liquid hydrocarbon per volume of catalyst per hour) over the catalyst with a helium dilution to give a helium to total hydrocarbon mole ratio of 4:1. After 20 minutes on stream, a sample of the effluent is taken and analyzed, most conveniently by gas chromatography, to determine the fraction remaining unchanged for each of the two hydrocarbons.

The "constraint index" is calculated as follows:

$$\text{Constraint Index} = \frac{\log_{10} (\text{fraction of n-hexane remaining})}{\log_{10} (\text{fraction of 3-methylpentane remaining})}$$

The Constraint Index approximates the ratio of the cracking rate constants for the two hydrocarbons.

Zeolites suitable for the present invention are those having a constraint index of from greater than 2 to 12. Constraint Index (C.I.) values for some typical catalysts are:

Zeolite	C.I.
ZSM-5	8.3
ZSM-11	8.7
ZSM-12	2
ZSM-23	9.1
ZSM-35	4.5
ZSM-38	2
TMA offretite	3.7
Beta	0.6

Zeolite	C.I.
ZSM-4	0.5
H-Zeolon	0.5
REY	0.4
Amorphous silica-alumina	0.6
Erionite	38
Clinoptilolite	3.4

10 The above-described Constraint Index is an important and even critical definition of those zeolites which are useful in the instant invention. The very nature of this parameter and the recited technique by which it is determined, however, admit of the possibility that a given zeolite can be tested under somewhat different conditions and thereby have different constraint indices. Constraint Index seems to vary somewhat with severity of operation (conversion) and the presence or absence of binders.

15 Therefore, it will be appreciated that it may be possible to so select test conditions to establish more than one value in the range of greater than 2 to 12 for the Constraint Index of a particular zeolite. Such a zeolite exhibits the constrained access as herein defined and is to be regarded as having a Constraint Index of greater than 2 to 12. Also contemplated herein as having a Constraint Index of greater than 2 to 12 are those zeolites which, when tested under two or more sets of conditions within the above

20 specified ranges of temperature and conversion, produce a value of the Constraint Index slightly less than 2, e.g. 1.9, or somewhat greater than 12, e.g. 14 or 15, with at least one other value of greater than 2 to 12. Thus, it should be understood that the Constraint Index value as used herein is an inclusive rather than an exclusive value. That is, a zeolite when tested by any combination of conditions within the testing definition set forth hereinabove to have a Constraint Index of greater than 2 to 12 is

25 intended to be included in the instant catalyst definition regardless that the same identical zeolite tested under other defined conditions may give a Constraint Index value outside of greater than 2 to 12.

The class of zeolites defined herein is exemplified by ZSM-5, ZSM-11, ZSM-23, ZSM-35, and other similar materials. ZSM-5 is described in U.S. Patent No. 3,702,886, ZSM-11 in U.S. Patent No. 3,709,979, ZSM-23 in U.S. Patent No. 4,076,842 and ZSM-35 in U.S. Patent No. 4,016,245.

30 The specific zeolites described, when prepared in the presence of organic cations, are catalytically inactive, possibly because the intracrystalline free space is occupied by organic cations from the forming solution. They may be activated by heating in an inert atmosphere at 538°C (1000°F) for 1 hour, for example, followed by base exchange with ammonium salts, followed by calcination at 538°C (1000°F) in air. The presence of organic cations in the forming solution may not be absolutely essential

35 to the formation of this type of zeolite; however, the presence of these cations does appear to favor the formation of this special type of zeolite. More generally, it is desirable to activate this type catalyst by base exchange with ammonium salts, followed by calcination in air at about 538°C (1000°F) for from 15 minutes to 24 hours.

40 Natural zeolites may sometimes be converted to this type zeolite catalyst by various activation procedures and other treatments such as base exchange, steaming, alumina extraction and calcination, in combinations. Natural minerals which may be so treated include ferrierite, brewsterite, stilbite, dachiardite, epistilbite, heulandite and clinoptilolite.

In a preferred aspect of this invention, the catalysts hereof are selected as those having a crystal framework density, in the dry hydrogen form, of not substantially below 1.6 grams per cubic centimeter. It has been found that zeolites which satisfy all three of these criteria are most desired

45 because they tend to maximize the production of gasoline boiling range hydrocarbon products. Therefore, the preferred catalysts of this invention are those having a constraint index as defined above of greater than 2 to 12, a silica to alumina mole ratio of at least 12 and a dried crystal density of not less than 1.6 grams per cubic centimeter. The dry density for known structures may be calculated from

50 the number of silicon plus aluminum atoms per 1000 cubic Angstroms, as given, e.g., on page 19 of the article on Zeolite Structure by W. M. Meier in "Proceedings of the Conference on Molecular Sieves, London, April 1967", Society of Chemical Industry, London, 1968. When the crystal structure is unknown, the crystal framework density may be determined by classical pycnometer techniques. For example, it may be determined by immersing the dry hydrogen form of the zeolite in an organic solvent

55 which is not sorbed by the crystal. It is possible that the unusual sustained activity and stability of this class of zeolites are associated with its high crystal anionic framework density of not less than 1.6 grams per cubic centimeter. This high density, of course, must be associated with a relatively small amount of free space within the crystal which might be expected to result in more stable structures. This free space, however, is important as the locus of catalytic activity.

Crystal framework densities of some typical zeolites are:

	Zeolites	Void volume	Framework density
5	Ferrierite	0.28 cc/cc	1.76 g/cc
	Mordenite	.28	1.7
	ZSM-5, 11	.29	1.79
	ZSM-12	—	1.8
10	ZSM-23	—	2.0
	Dachiardite	.32	1.72
	L	.32	1.61
	Clinoptilolite	.34	1.71
	Laumontite	.34	1.77
15	ZSM-4 (Omega)	.38	1.65
	Heulandite	.39	1.69
	P	.41	1.57
	Offretite	.40	1.55
	Levynite	.40	1.54
20	Erionite	.35	1.51
	Gmelinite	.44	1.46
	Chabazite	.47	1.45
	A	.5	1.2
25	Y	.48	1.27

When synthesized in the alkali metal form, the zeolite is conveniently converted to the hydrogen form, generally by intermediate formation of the ammonium form as a result of ammonium ion exchange and calcination of ammonium form to yield the hydrogen form. In addition to the hydrogen form, other forms of the zeolite wherein the original alkali metal has been reduced to less than 1.5 percent by weight may be used. Thus, the original alkali metal of the zeolite or introduced hydrogen cations may be replaced by ion exchange with other suitable ions of Groups IB to VIII of the Periodic Table, including, for example, nickel, cadmium, copper, zinc, palladium, calcium or rare earth metals.

In practicing the desired synthesis method, it may be desirable to incorporate the above-described crystalline zeolite in another material resistant to the temperature and other conditions employed in the process. Such matrix materials include synthetic or naturally occurring substances as well as inorganic materials such as clay, silica and/or metal oxides. The latter may be either naturally occurring or in the form of gelatinous precipitates or gels including mixtures of silica and metal oxides. Naturally occurring clays, which can be composited with the zeolite include those of the montmorillonite and kaolin families, which families include the sub-bentonites and the kaolins commonly known as Dixie, McNamee-Georgia and Florida clays or others in which the main mineral constituent is halloysite, kaolinite, dickite, nacrite or anauxite. Such clays can be used in a raw state as originally mined or initially subjected to calcination, acid treatment or chemical modification.

In addition to the foregoing materials, the zeolites employed herein may be composited with a porous matrix material such as alumina, silica-alumina, silica-magnesia, silica-zirconia, silica-thoria, silica-beryllia and silica-titania as well as ternary compositions such as silica-alumina-thoria, silica-alumina-zirconia, silica-alumina-magnesia and silica-magnesia-zirconia. The matrix may be in the form of a cogel. The relative proportions of zeolite component and inorganic oxide gel matrix may vary widely with the zeolite content ranging from 1 to 99 percent by weight and more usually in the range from 5 to 80 percent by weight of the composite.

The following Examples illustrate the process of the invention. Examples 1 to 4 illustrate the preparation of catalysts used in the present invention.

Example 1

This example illustrates the preparation of smaller crystal size ZSM-5 zeolite.

An organic salt solution was prepared by mixing 1.6 parts of n-propyl bromide, 1.9 parts of tri-n-propylamine, 3.1 parts of methyl ethyl ketone and 10.4 parts of water. The mixture was reacted at about 100°C for 14 hours. The aqueous phase of the reacted mixture is designated Solution A.

A sodium silicate solution was prepared by mixing 16 parts water and 27.7 parts sodium silicate (28.7 wt% SiO₂, 8.9 wt% Na₂O, 62.4% H₂O) followed by addition of 0.08 parts of dispersant (Daxad 27—W.R. Grace Chem. Div. 'Daxad' is a registered Trade Mark). The solution was cooled to approximately 15°C.

An acid solution was prepared by adding 1 part aluminum sulfate (17.2 wt% Al₂O₃) to 16.4 parts water followed by 2.4 parts sulfuric acid (93 wt% H₂SO₄), 1.2 parts NaCl and 2.9 parts of Solution A.

These solutions were mixed in an agitated vessel while 3.9 parts of NaCl were added. The gel molar ratios expressed as oxides are the following:

$$\text{SiO}_2/\text{Al}_2\text{O}_3=78.4$$

$$\text{Na}_2\text{O}/\text{Al}_2\text{O}_3=49.9.$$

The gel was agitated for 4 hours at ambient temperature, then heated to 95—110°C and held for 40 hours with severe agitation. When approximately 65% of the gel was crystallized, the temperature was increased to 150—160°C and held there until crystallization was complete.

The zeolite slurry product was diluted with 4—5 parts water per part slurry and 0.002 parts of flocculent (Rohm & Haas Primafloc C-7 'Primafloc' is a registered Trade Mark) per part slurry, allowed to settle and supernatant liquid was drawn off. The settled solids were reslurried to the original volume of the preceding step with water and 0.00005 parts of flocculent per part slurry. After settling, the aqueous phase was decanted. This procedure was repeated until the sodium level of the zeolite was less than 1.0 wt%. The washed zeolite was then filtered, dried and identified as ZSM-5 having a silica/alumina mole ratio of at least 12; i.e., 70, and a constraint index of between 1 and 12; i.e., 8.3.

The dried zeolite product was calcined in flowing nitrogen for 3 hours at 538°C then ion exchanged twice with 1N NH_4NO_3 solution (5 parts NH_4NO_3 solution/1 part zeolite) for 1 hour at ambient temperature and dried at about 120°C.

Example 2

This example illustrates the preparation of larger crystal size ZSM-5 zeolite.

A sodium silicate solution was prepared by mixing 16 parts water and 27.7 parts sodium silicate (28.7 wt% SiO_2 , 8.9 wt% Na_2O , 62.4% H_2O) followed by addition of 0.08 parts Daxad 27 (W. R. Grace Chem. Co.) The solution was cooled to approximately 15°C.

An acid solution was prepared by adding 1 part aluminum sulfate (17.2 wt% Al_2O_3) to 16.4 parts water followed by 2.4 parts sulfuric acid (93 wt% H_2SO_4) and 1.2 parts NaCl.

These solutions were mixed in an agitated vessel while 3.9 parts of NaCl were added. The gel molar ratios expressed as oxides are the following:

$$\text{SiO}_2/\text{Al}_2\text{O}_3=78.4$$

$$\text{Na}_2\text{O}/\text{Al}_2\text{O}_3=49.9.$$

An organic solution was prepared by adding 1.6 parts n-propyl bromide and 3.1 parts methyl ethyl ketone to 1.9 parts tri-n-propylamine and added to the gel.

The mixture was reacted at 150—160°C with severe agitation for 29 hours.

The zeolite slurry product was diluted with 4—5 parts water per part slurry and 0.0002 parts of flocculent (Rohm & Haas Primafloc C-7) per part slurry, allowed to settle and supernatant liquid was drawn off. The settled solids were reslurried to the original volume of the preceding step with water and 0.00005 parts of flocculent per part slurry. After settling, the aqueous phase was decanted. This procedure was repeated until the decant supernatant liquid was Cl-free. The washed zeolite was then filtered, dried and identified as ZSM-5 having a silica/alumina mole ratio of at least 12; i.e., 70, and a

Constraint Index of from 1 to 12; i.e., 8.3.

The dried zeolite product was calcined in flowing nitrogen for 3 hours at 538°C, then ion exchanged twice with 1N NH_4NO_3 solution (5 parts NH_4NO_3 soln/1 part zeolite) for 1 hour at ambient temperature and dried at about 120°C.

Example 3

Cs-H-ZSM-5 was made by exchanging NH_4 -ZSM-5 from Example 1 (10) g) with 220 cc of a 0.1 M CsCl solution overnight. Ammonia analysis indicated 98.7% exchange took place.

Example 4

TMA-H-ZSM-5 was made by exchanging 26 g NH_4 -ZSM-5 from Example 1 with 700 ml 1M tetramethylammonium bromide containing sufficient TMA hydroxide to raise the pH above 11. The catalyst prior to use was heated in a fixed bed glass reactor under flowing nitrogen at 390°C to 400°C for exactly 6 minutes, so that only a portion of the TMA ions would decompose to generate acidic sites.

All the olefins used in the following examples were obtained in 99+% purity from Chemical Samples Company.

Examples 5 to 10

Examples 5 to 10 illustrate competitive isomerization reactions of olefins conducted over acidic ZSM-5 catalysts at temperatures in the range of 100°C to 175°C. Results of these examples are given in Table 1.

The catalysts of Examples 5 to 7. were prepared by the general procedure of Example 1. The catalysts of Examples 8 to 10 were prepared by the general procedure of Example 2.

The competitive isomerization reactions were run in a down-flow fixed bed glass reactor. An equimolar solution of the two olefins were fed into the reactor by means of a syringe pump and diluted with a flow of nitrogen. The product mixture was analyzed by means of an on-line gas chromatograph containing a 10 ft. n-octane-Durapak column.

The relative diffusivities of variously shaped olefins in ZSM-5 were obtained from competitive isomerization reaction conducted over H-ZSM-5 at temperatures in the 100°C to 175°C range (see Table 1). Both single- and double-branched molecules were studied, and in all cases, the shape selectivities were somewhat greater for the larger crystal size zeolite.

Shape selectivity was observed as follows:

linear olefin > methyl-branched >>

ethyl-branched > gem-dimethyl-branched.

TABLE 1
Competitive isomerizations

Ex. No.	Catalyst	Temp. °C	A	B	% Conversion A	% Conversion B	Selectivity kA/kB
5	(b) H-ZSM-5	105	hexene-1	6-Me heptene-1	59	47	1.4
6	(b) H-ZSM-5	125	hexene-1	3-Et pentene-1	64	10	9.7
7	(b) H-ZSM-5	100	hexene-1	4,4-diMe hexene-1	47	2.6	25
8	(a) H-ZSM-5	150	hexene-1	6-Me heptene-1	41	25	1.8
9	(a) H-ZSM-5	175	hexene-1	3-Et pentene-1	64	2.8	35
10	(a) H-ZSM-5	175	hexene-1	4,4-diMe hexene-1	54	0.65	120

(a) larger crystal size zeolites

(b) smaller crystal size zeolites

Examples 11 to 13

The effect of cation exchange on selectivity is illustrated by Examples 11 to 13 and shown in Table 2. These examples are based on the competitive isomerization of hexene-1 and 6-Me heptene-1. Example 11 is the same as Example 5, and Examples 11 to 13 follow the general experimental procedure as used in Examples 5 to 10.

The catalyst for Example 11 was prepared according to the general procedure of Example 1. In Example 12, the catalyst used was prepared in accordance with the general procedure of Example 3, and in Example 13 the catalyst was prepared in accordance with the general procedure of Example 4.

The shape selectivity of acid catalyzed reactions of olefins over zeolites can be accentuated by the presence of large cations exchanged onto the zeolite. In particular, the preference for linear olefins was enhanced for both cesium and tetramethylammonium exchanged ZSM-5 as shown in Table 2.

TABLE 2
Effect of cation exchange on selectivity

Ex. no.	Catalyst	Temperature °C	Selectivity (hexene-1 6-Me heptene-1)
11	(a) H-ZSM-5	105	1.4
12	(a) Cs-H-ZSM-5	100	3.0
13	(a) TMA-H-ZSM-5	100	3.3

(a) smaller crystal size zeolite

Example 14

An equimolar sample of allylbenzene and 1-allyl-naphthalene was contacted with HZSM-5 as prepared according to Example 1, at 100°C for 5 hours. Allylbenzene was extensively isomerized (double bond isomerization), while the 1-allyl-naphthalene was unreacted. This Example illustrates the selective acid catalyzed reaction of a "smaller olefin" in admixture with a "larger olefin", i.e. 1-allyl-naphthalene with an effective critical dimension greater than 6.8 Angstroms.

Example 15

A mixture of octene-1 and di-isobutylene is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1, at 300°C, atmospheric pressure and at a WHSV of 10. The linear olefin, octene-1 is preferentially cracked to light gases, whereas the branched olefin, di-isobutylene remains largely intact.

Example 16

A mixture of isobutylene and 2,4,4-trimethylpentene-1 is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1, at conditions including a temperature of 300°C, atmospheric pressure and a WHSV of 10. The lesser branched olefin, isobutylene, is preferentially cracked to light gases, whereas the more highly branched olefin 2,4,4-trimethylpentene-1, remains generally unreacted.

Example 17

A mixture of alpha methyl styrene dimer and phenyl hexene is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1, at conditions including a temperature of 300°C, a pressure of 1 atmosphere and a WHSV of 10. Phenyl hexene, a linear olefin, is preferentially cracked while alpha methyl styrene dimer remains essentially unreacted.

Example 18

A mixture of propylene, a linear olefin, and dimethylhexene, a branched olefin, is contacted in a batch reactor with HZSM-5, as prepared according to the general procedure of Example 1, at conditions including a temperature of 100°C, a pressure of 791 kPa (100 psig) and a residence time of 1 hour. The resulting product is a mixture of C₆, C₉ and C₁₂ olefins thus indicating selective oligomerization of the propylene rather than dimethylhexene.

Example 19

Following the same procedure and reaction conditions of Example 18, styrene and 3,5-dimethylstyrene are passed over HZSM-5. The product of this competitive reaction indicates polymerization of styrene with 3,5-dimethylstyrene remaining almost unreacted.

Example 20

A mixture of heptene-1 and 4,4-dimethylpentene-1 is contacted in a down-flow fixed bed reactor

with HZSM-5, as prepared according to Example 1, at conditions including a temperature of 400°C, a pressure of 791 kPa (100 psig) and a WHSV of 1. The product contains aromatics with a significant proportion of the 4,4-dimethylpentene-1 remaining unreacted.

5 Example 21

This example illustrates a typical addition reaction conducted according to this invention. A mixture of hexene-1 and 3,3-dimethylbutene-1 is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1. The reaction is conducted in the presence of steam at 66°C (150°F), 5066 kPa (50 atmospheres) pressure and a WHSV of 1. A mixture containing
10 hexylalcohols is formed, while the 3,3-dimethylbutene-1 remains essentially unreacted.

Example 22

A mixture of hexene-1 and dimethylbutene-1 is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1. The reaction is conducted in the presence of benzene at
15 300°C, a WHSV of 170 kPa (10 psig) and 791 kPa (100 psig). The products contain a mixture of hexyl-benzenes, while the dimethylbutene-1 remains largely unreacted.

Claims

- 20 1. A process for conducting preferential acid catalyzed reactions of smaller olefins in mixed stream with larger olefins, the smaller olefins having an effective critical dimension of 6.8 Angstroms and less and the larger olefins having an effective critical dimension in excess of 6.8 Angstroms, which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a
25 class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.
2. A process for conducting preferential acid catalyzed reactions, of linear olefins in mixed stream with branched-chain olefins, both linear and branched-chain olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the mixed streams with an acidic
30 catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.
3. A process for conducting preferential acid catalyzed reactions of lesser branched olefins in mixed streams with higher branched olefins, both lesser branched olefins and higher branched olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the
35 mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.
4. The process of claim 3 wherein the lesser branched olefin is a monoalkyl olefin and the greater branched olefin is a di- or polyalkyl substituted olefin.
- 40 5. The process of claim 3 wherein the lesser branched olefin is a monomethyl substituted olefin and the greater branched olefin is an alkyl substituted olefin, where the alkyl group has more than one carbon atom.
6. A process for conducting preferential acid catalyzed reactions of para-disubstituted and/or mono-substituted aromatic olefins in mixed stream with ortho- and/or meta-disubstituted or more
45 highly substituted aromatic olefins which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.
7. The process of any one of claims 1 to 6 wherein the zeolite is ZSM-5, ZSM-11, ZSM-23 or ZSM-35.
- 50 8. The process of any one of claims 1 to 6 wherein the zeolite is HZSM-5.
9. The process of any one of claims 1 to 6 wherein the zeolite is composited with a matrix material.
10. The process of any one of claims 1 to 9 wherein the catalyst is partially ion-exchanged with bulky cations selected from rubidium, cesium and tetramethylammonium.
- 55 11. The process of any one of claims 1 to 9 wherein the catalyst is a large crystal zeolite of the crystal size of 0.5 microns to 100 microns.
12. The process of any one of claims 1 to 11 wherein coke in an amount of at least 2 weight percent is deposited on the catalyst.
13. The process of claim 10 wherein the catalyst is Cs-H-ZSM-5.
- 60 14. The process of claims 10 wherein the catalyst is TMA-H-ZSM-5.
15. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is isomerization and the reaction is carried out at a temperature of from 232°C (450°F) to 538°C (1000°F), a pressure of from 101 kPa (0 psig) to 3549 kPa (500 psig), a WHSV of from 0.1 to 200 hr⁻¹, and a hydrogen to olefin mole ratio of from 0.1 to 100.
- 65 16. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is dimerization

with HZSM-5, as prepared according to Example 1, at conditions including a temperature of 400°C, a pressure of 791 kPa (100 psig) and a WHSV of 1. The product contains aromatics with a significant proportion of the 4,4-dimethylpentene-1 remaining unreacted.

5 Example 21

This example illustrates a typical addition reaction conducted according to this invention. A mixture of hexene-1 and 3,3-dimethylbutene-1 is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1. The reaction is conducted in the presence of steam at 66°C (150°F), 5066 kPa (50 atmospheres) pressure and a WHSV of 1. A mixture containing
10 hexylalcohols is formed, while the 3,3-dimethylbutene-1 remains essentially unreacted.

Example 22

A mixture of hexene-1 and dimethylbutene-1 is contacted in a down-flow fixed bed reactor with HZSM-5, as prepared according to Example 1. The reaction is conducted in the presence of benzene at
15 300°C, a WHSV of 170 kPa (10 psig) and 791 kPa (100 psig). The products contain a mixture of hexyl-benzenes, while the dimethylbutene-1 remains largely unreacted.

Claims

20

1. A process for conducting preferential acid catalyzed reactions of smaller olefins in mixed stream with larger olefins, the smaller olefins having an effective critical dimension of 6.8 Angstroms and less and the larger olefins having an effective critical dimension in excess of 6.8 Angstroms, which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a
25 class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

2. A process for conducting preferential acid catalyzed reactions, of linear olefins in mixed stream with branched-chain olefins, both linear and branched-chain olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the mixed streams with an acidic
30 catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

3. A process for conducting preferential acid catalyzed reactions of lesser branched olefins in mixed streams with higher branched olefins, both lesser branched olefins and higher branched olefins having an effective critical dimension of less than 6.8 Angstroms which comprises contacting the
35 mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

4. The process of claim 3 wherein the lesser branched olefin is a monoalkyl olefin and the greater branched olefin is a di- or polyalkyl substituted olefin.

40 5. The process of claim 3 wherein the lesser branched olefin is a monomethyl substituted olefin and the greater branched olefin is an alkyl substituted olefin, where the alkyl group has more than one carbon atom.

6. A process for conducting preferential acid catalyzed reactions of para-disubstituted and/or mono-substituted aromatic olefins in mixed stream with ortho- and/or meta-disubstituted or more
45 highly substituted aromatic olefins which comprises contacting the mixed stream with an acidic catalyst comprising one or more members of a class of zeolites characterized by a silica to alumina mole ratio of at least 12 and a constraint index of from greater than 2 to 12.

7. The process of any one of claims 1 to 6 wherein the zeolite is ZSM-5, ZSM-11, ZSM-23 or ZSM-35.

50 8. The process of any one of claims 1 to 6 wherein the zeolite is HZSM-5.

9. The process of any one of claims 1 to 6 wherein the zeolite is composited with a matrix material.

10. The process of any one of claims 1 to 9 wherein the catalyst is partially ion-exchanged with bulky cations selected from rubidium, cesium and tetramethylammonium.

55 11. The process of any one of claims 1 to 9 wherein the catalyst is a large crystal zeolite of the crystal size of 0.5 microns to 100 microns.

12. The process of any one of claims 1 to 11 wherein coke in an amount of at least 2 weight percent is deposited on the catalyst.

13. The process of claim 10 wherein the catalyst is Cs-H-ZSM-5.

60 14. The process of claims 10 wherein the catalyst is TMA-H-ZSM-5.

15. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is isomerization and the reaction is carried out at a temperature of from 232°C (450°F) to 538°C (1000°F), a pressure of from 101 kPa (0 psig) to 3549 kPa (500 psig), a WHSV of from 0.1 to 200 hr⁻¹, and a hydrogen to olefin mole ratio of from 0.1 to 100.

65 16. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is dimerization



and the reaction is carried out at a temperature of from 93°C (200°F) to 649°C (1200°F), a pressure of from atmospheric to 10133 kPa (0 atmospheres), a WHSV of from 0.1 to 30 hr⁻¹.

17. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is hydration or alcohol addition and the reaction is carried out at a temperature of from 66°C (150°F) to 316°C (600°F) and a pressure of from atmospheric to 10133 kPa (100 atmospheres).

18. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is alkylation and the reaction is carried out at a temperature of from 38°C (100°F) to 510°C (950°F), a pressure of from 101 kPa (0 psig) to 6996 kPa (1000 psig), and a WHSV of from 1 to 500.

19. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is hydrogen halide addition and the reaction is carried out at a temperature below 649°C (1200°F) and at a pressure of from atmospheric to 10133 kPa (100 atmospheres).

20. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is the Prins reaction and is carried out at a temperature between room temperature and 427°C (800°F).

21. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is aromatization conducted in a flow apparatus at a temperature of from 288°C (550°F) to 649°C (1200°F), a pressure of from atmospheric to 69049 kPa (10,000 psig), a hydrogen/olefin mole ratio of from 0 to 20 and a weight hourly space velocity of from 0.1 hr⁻¹ to 10 hr⁻¹.

22. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is aromatization conducted in a batch apparatus at a temperature of from 288°C (550°F) to 649°C (1200°F), a pressure of from atmospheric to 69049 kPa (10,000 psig), a hydrogen/olefin mole ratio of from 0 to 20 and a contact time of from 0.1 hour to 48 hours.

23. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is cracking conducted in a flow apparatus at a temperature of from 371°C (700°F) to 649°C (1200°F), a pressure of from atmospheric to 1480 kPa (200 psig) and a weight hourly space velocity of from 0.5 hr⁻¹ to 50 hr⁻¹.

24. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is cracking conducted in a batch apparatus at a temperature of from 371°C (700°F) to 649°C (1200°F), a pressure of from atmospheric to 1480 kPa (200 psig) and a contact time of from 0.01 hour to 24 hours.

25. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is hydrocracking conducted in a flow apparatus at a temperature of from 204°C (400°F) to 538°C (1000°F), a pressure of from 3549 kPa (500 psig) to 24233 kPa (3500 psig), a weight hourly space velocity of from 0.1 hr⁻¹ to 10 hr⁻¹ and a hydrogen/olefin mole ratio of from 1 to 20.

26. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is hydrocracking conducted in a batch apparatus at a temperature of from 204°C (400°F) to 538°C (1000°F), a pressure of from 3549 kPa (500 psig) to 24233 kPa (3500 psig), a contact time of from 0.01 hour to 24 hours, and a hydrogen/olefin mole ratio of from 1 to 20.

27. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is oligomerization or polymerization conducted in a flow apparatus at a temperature of from 35°C (95°F) to 502°C (935°F), a pressure of from atmospheric to 69049 kPa (10,000 psig), a WHSV of from 0.1 to 50 hr⁻¹ and a hydrogen/olefin mole ratio of from 0 to 20.

28. The process of any one of claims 1 to 14 wherein the acid catalyzed reaction is oligomerization or polymerization conducted in a batch apparatus at a temperature of from 35°C (95°F) to 502°C (935°F), a pressure from atmospheric to 27680 kPa (4,000 psig), a contact time of from 0.1 to 48 hours and a hydrogen/olefin mole ratio of from 0 to 20.

Patentansprüche

1. Verfahren zur Durchführung von bevorzugten säurekatalysierten Reaktionen kleinerer Olefine in vermischem Strom mit größeren Olefinen, wobei die kleineren Olefine eine wirksame kritische Dimension von 6,8 Angström-Einheiten und geringer und die größeren Olefine eine wirksame kritische Dimension von mehr als 6,8 Angström-Einheiten haben, dadurch gekennzeichnet, daß der gemischte Strom mit einem sauren Katalysator in Berührung gebracht wird, der ein oder mehrere Glieder einer Klasse von Zeolithen enthält, die durch ein Siliciumdioxid/Aluminiumoxid-Molverhältnis von wenigstens 12 und einen Zwangsindex von größer als 2 bis 12 charakterisiert sind.

2. Verfahren zur Durchführung von bevorzugten säurekatalysierten Reaktionen von linearen Olefinen in gemischem Strom mit verzweigten Olefinen, wobei sowohl die linearen als auch die verzweigten Olefine eine wirksame kritische Dimension von weniger als 6,8 Angströmeinheiten haben, dadurch gekennzeichnet, daß die gemischten Ströme mit einem sauren Katalysator in Berührung gebracht werden, der ein oder mehrere Glieder einer Klasse von Zeolithen enthält, die durch ein Siliciumdioxid/Aluminiumoxid-Molverhältnis von wenigstens 12 und einen Zwangsindex von größer als 2 bis 12 charakterisiert sind.

3. Verfahren zur Durchführung von bevorzugten säurekatalysierten Reaktionen von geringer verzweigten Olefinen im gemischten Strömen mit höher verzweigten Olefinen, wobei sowohl die geringer verzweigten Olefine als auch die höher verzweigten Olefine eine wirksame kritische Dimension von we-



niger als 6,8 Angström-Einheiten haben, dadurch gekennzeichnet, daß der gemischte Strom mit einem sauren Katalysator in Berührung gebracht wird, der ein oder mehrere Glieder einer Klasse von Zeolithen enthält, die durch ein Siliciumdioxid/Aluminiumoxid-Molverhältnis von wenigstens 12 und einen Zwangsindex von größer als 2 bis 12 charakterisiert sind.

5 4. Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß das geringer verzweigte Olefin ein Monoalkylolefin und das höher verzweigte Olefin ein di- oder polyalkylsubstituiertes Olefin ist.

5. Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß das geringer verzweigte Olefin ein monomethylsubstituiertes Olefin und das höher verzweigte Olefin ein alkylsubstituiertes Olefin ist, wo die Alkylgruppe mehr als ein Kohlenstoffatom hat.

10 6. Verfahren zur Durchführung von bevorzugten säurekatalysierten Reaktionen von para-disubstituierten und/oder monosubstituierten aromatischen Olefinen in gemischtem Strom mit ortho- und/oder meta-disubstituierten oder noch höher substituierten aromatischen Olefinen, dadurch gekennzeichnet, daß der gemischte Strom mit einem sauren Katalysator in Berührung gebracht wird, der ein oder mehrere Glieder einer Klasse von Zeolithen enthält, die durch ein Siliciumdioxid/Aluminiumoxid-Molverhältnis von wenigstens 12 und einen Zwangsindex von größer als 2 bis 12 charakterisiert sind.

15 7. Verfahren nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß der Zeolith ZSM-5, ZSM-11, ZSM-23 oder ZSM-35 ist.

8. Verfahren nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß der Zeolith HZSM-5 ist.

20 9. Verfahren nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß der Zeolith mit einem Matrixmaterial zusammengesetzt ist.

10. Verfahren nach einem der Ansprüche 1 bis 9, dadurch gekennzeichnet, daß der Katalysator mit sperrigen Kationen, ausgewählt aus der Reihe Rubidium, Cäsium und Tetramethylammonium, teilweise ionenausgetauscht ist.

25 11. Verfahren nach einem der Ansprüche 1 bis 9, dadurch gekennzeichnet, daß der Katalysator ein Zeolith mit großen Kristallen einer Kristallgröße von 0,5 μm bis 100 μm ist.

12. Verfahren nach einem der Ansprüche 1 bis 11, dadurch gekennzeichnet, daß Koks in einer Menge von wenigstens 2 Gew.-% auf dem Katalysator niedergeschlagen wird.

13. Verfahren nach Anspruch 10, dadurch gekennzeichnet, daß der Katalysator Cs-H-ZSM-5 ist.

30 14. Verfahren nach Anspruch 10, dadurch gekennzeichnet, daß der Katalysator TMA-H-ZSM-5 ist.

15. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Isomerisierung ist und die Reaktion bei einer Temperatur von 232°C (450°F) bis 538°C (1000°F), einem Druck von 101 kPa (0 psig) bis 3549 kPa (500 psig), einem WHSV-Wert von 0,1 bis 200 h^{-1} und einem Wasserstoff/Olefin-Molverhältnis von 0,1 bis 100 ausgeführt wird.

35 16. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Dimerisierung ist und die Reaktion bei einer Temperatur von 93°C (200°F) bis 649°C (1200°F), einem Druck von Atmosphärendruck bis 10133 kPa (0 Atmosphären) und einem WHSV-Wert von 0,1 bis 30 h^{-1} ausgeführt wird.

40 17. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Hydratation oder Alkoholaddition ist und die Reaktion bei einer Temperatur von 66°C (150°F) bis 316°C (600°F) und einem Druck von Atmosphärendruck bis 10133 kPa (100 Atmosphären) ausgeführt wird.

45 18. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Alkylierung ist und die Reaktion bei einer Temperatur von 38°C (100°F) bis 510°C (950°F), einem Druck von 101 kPa (0 psig) bis 6996 kPa (1000 psig) und einem WHSV-Wert von 1 bis 500 ausgeführt wird.

50 19. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Halogenwasserstoff-Addition ist und die Reaktion bei einer Temperatur unterhalb 649°C (1200°F) und bei einem Druck von Atmosphärendruck bis 10133 kPa (100 Atmosphären) ausgeführt wird.

20. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion die Prins-Reaktion ist und bei einer Temperatur zwischen Raumtemperatur und 427°C (800°F) ausgeführt wird.

55 21. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Aromatisierung ist, ausgeführt in einer Fließvorrichtung bei einer Temperatur von 288°C (550°F) bis 649°C (1200°F), einem Druck von Atmosphärendruck bis 69049 kPa (10000 psig), einem Wasserstoff/Olefin-Molverhältnis von 0 bis 20 und einer gewichtsmäßigen stündlichen Raumströmungsgeschwindigkeit von 0,1 h^{-1} bis 10 h^{-1} .

60 22. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Aromatisierung ist, durchgeführt in einer Chargenvorrichtung bei einer Temperatur von 288°C (550°F) bis 649°C (1200°F), einem Druck von Atmosphärendruck bis 69049 kPa (10000 psig), einem Wasserstoff/Olefin-Molverhältnis von 0 bis 20 und einer Kontaktzeit von 0,1 h bis 48 h.

23. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Crackung ist, durchgeführt in einer Fließvorrichtung bei einer Temperatur von



371°C (700°F) bis 649°C (1200°F), einem Druck von Atmosphärendruck bis 1480 kPa (200 psig) und einer gewichtsmäßigen stündlichen Raumströmungsgeschwindigkeit von 0,5 h⁻¹ bis 50 h⁻¹.

24. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Cracking ist, ausgeführt in einer Chargenvorrichtung bei einer Temperatur von 371°C (700°F) bis 649°C (1200°F), einem Druck von Atmosphärendruck bis 1480 kPa (200 psig) und einer Kontaktzeit von 0,01 h bis 24 h.

25. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Hydrocracking ist, ausgeführt in einer Fließvorrichtung bei einer Temperatur von 204°C (400°F) bis 538°C (1000°F), einem Druck von 3549 kPa (500 psig) bis 24233 kPa (3500 psig), einer gewichtsmäßigen stündlichen Raumströmungsgeschwindigkeit von 0,1 h⁻¹ bis 10 h⁻¹ und einem Wasserstoff/Olefin-Molverhältnis von 1 bis 20.

26. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Hydrocracking ist, ausgeführt in einer Chargenvorrichtung bei einer Temperatur von 204°C (400°F) bis 538°C (1000°F), einem Druck von 3549 kPa (500 psig) bis 24233 kPa (3500 psig), einer Kontaktzeit von 0,01 h bis 24 h und einem Wasserstoff/Olefin-Molverhältnis von 1 bis 20.

27. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Oligomerisation oder Polymerisation ist, ausgeführt in einer Fließvorrichtung bei einer Temperatur von 35°C (95°F) bis 502°C (935°F), einem Druck von Atmosphärendruck bis 69049 kPa (10000 psig), einem WHSV-Wert von 0,1 bis 50 h⁻¹ und einem Wasserstoff/Olefin-Molverhältnis von 0 bis 20.

28. Verfahren nach einem der Ansprüche 1 bis 14, dadurch gekennzeichnet, daß die säurekatalysierte Reaktion eine Oligomerisation oder Polymerisation ist, ausgeführt in einer Chargenvorrichtung bei einer Temperatur von 35°C (95°F) bis 502°C (935°F), einem Druck von Atmosphärendruck bis 27680 kPa (4000 psig), einer Kontaktzeit von 0,1 bis 48 h und einem Wasserstoff/Olefin-Molverhältnis von 0 bis 20.

Revendications

1. Un procédé pour mettre en oeuvre des réactions préférentielles de catalyse acide, d'oléfines inférieures dans un courant mélangé avec des oléfines supérieures, les oléfines inférieures présentant une dimension critique effective de 6,8 Angstroms et moins et les oléfines supérieures présentant une dimension critique effective au-delà de 6,8 Angstroms, qui consiste à mettre en contact le courant mélangé avec un catalyseur acide comportant un ou plus d'un éléments d'une classe de zéolites, caractérisée par un rapport molaire de silice alumine d'au moins 12 et un indice de contrainte plus élevé que 2 à 12.

2. Un procédé pour mettre en oeuvre des réactions préférentielles de catalyse acide, d'oléfines linéaires dans un courant mélangé avec des oléfines à chaîne ramifiée, les deux oléfines linéaire et à chaîne ramifiée présentant une dimension critique effective inférieure à 6,8 Angstroms, qui consiste à mettre en contact le courant mélangé avec un catalyseur acide comportant un ou plus d'un éléments d'une classe de zéolites, caractérisée par un rapport molaire de silice alumine d'au moins 12 et un indice de contrainte plus important que 2 à 12.

3. Un procédé pour mettre en oeuvre des réactions préférentielles de catalyse acide, d'oléfines inférieures ramifiées dans des courants mélangés avec des oléfines supérieures ramifiées, les deux oléfines inférieures ramifiées et supérieures ramifiées présentant une dimension critique effective inférieure à 6,8 Angstroms, qui consiste à mettre en contact le courant mélangé avec un catalyseur acide comportant un ou plus d'un élément d'une classe de zéolites, caractérisée par un rapport molaire de silice alumine moins 12 et un indice de contrainte plus important que 2 à 12.

4. Le procédé de la revendication 3, dans lequel l'oléfine inférieure ramifiée est une oléfine mono-alkylée et l'oléfine supérieure ramifiée est une oléfine di- ou poly-alkyl-substituée.

5. Le procédé de la revendication 3, dans lequel l'oléfine inférieure ramifiée est une oléfine mono-méthyl-substituée et l'oléfine supérieure ramifiée est une oléfine alkyl-substituée, dans laquelle le groupe alkyle possède plus d'un atome de carbone.

6. Un procédé pour mettre en oeuvre des réactions préférentielles de catalyse acide, d'oléfines aromatiques para-disubstituées et/ou mono-substituées dans un courant mélangé avec des oléfines aromatiques ortho- et/ou méta-disubstituées ou plus largement substituées, qui consiste à mettre en contact le courant mélangé avec un catalyseur acide comportant un ou plus d'un élément d'une classe de zéolites, caractérisée par un rapport molaire de silice/alumine d'au moins 12 et un indice de contrainte plus important que 2 à 12.

7. Le procédé de l'une quelconque des revendications 1 à 6, dans lequel la zéolite est ZSM-5, ZSM-11, ZSM-23 ou ZSM-35.

8. Le procédé selon l'une quelconque des revendications 1 à 6, dans lequel la zéolite est HZSM-5.

9. Le procédé selon l'une quelconque des revendications 1 à 6, dans lequel la zéolite est un mélange composite avec un matériau matriciel.

10. Le procédé selon l'une quelconque des revendications 1 à 9, dans lequel le catalyseur est



partiellement ioniquement échangé avec des cations lourds choisis parmi le rubidium, le césium et le tétra-méthylammonium.

11. Le procédé selon l'une quelconque des revendications 1 à 9, dans lequel le catalyseur est une zéolite à grands cristaux d'une dimension cristalline de 0,5 microns à 100 microns.

12. Le procédé selon l'une quelconque des revendications 1 à 11, dans lequel du coke en une quantité d'au moins 2% en poids est déposé sur le catalyseur.

13. Le procédé de la revendication 10, dans lequel le catalyseur est Cs-H-ZSM-5.

14. Le procédé de la revendication 10, dans lequel le catalyseur est TMA-H-ZSM-5.

15. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une isomérisation et la réaction est mise en oeuvre à une température de 232°C à 538°C, une pression de 101 kPa à 3549 kPa, une VSHP de 0,1 à 200 h⁻¹, et un rapport molaire d'oléfine à l'hydrogène de 0,1 à 100.

16. Le procédé selon l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une dimérisation et la réaction est mise en oeuvre à une température de 93°C à 649°C, une pression de l'atmosphérique à 10133 kPa (0 atmosphère), une VSHP de 0,1 à 300 h⁻¹.

17. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une hydratation ou une addition d'alcool, et la réaction est mise en oeuvre à une température de 66°C à 316°C et à une pression de l'atmosphérique à 10133 kPa (100 atmosphères).

18. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une alkylation et la réaction est mise en oeuvre à une température de 38°C à 510°C, une pression de 101 kPa à 6996 kPa, et une VSHP de 1 à 500.

19. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une addition d'halogénure d'hydrogène et la réaction est mise en oeuvre à une température au-dessous de 649°C et une pression de l'atmosphérique à 10133 kPa (100 atmosphères).

20. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est la réaction de Prins et est mise en oeuvre à une température entre la température ambiante et 427°C.

21. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une aromatisation mise en oeuvre dans un appareil à écoulement à une température de 288°C à 649°C, une pression de l'atmosphérique à 69049 kPa, un rapport molaire hydrogène/oléfine de 0 à 20 et une vitesse spatiale horaire pondérale de 0,1 h⁻¹ à 10 h⁻¹.

22. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une aromatisation mise en oeuvre dans un appareil à fonctionnement discontinu à une température de 288°C à 649°C, une pression de l'atmosphérique à 69049 kPa, un rapport molaire hydrogène/oléfine de 0 à 20 et un temps de contact de 0,1 heure à 48 heures.

23. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est mise en oeuvre par craquage dans un appareil à écoulement à une température de 371°C à 649°C, une pression de l'atmosphérique à 1480 kPa et une vitesse spatiale horaire pondérale de 0,5 h⁻¹ à 50 h⁻¹.

24. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est réalisée par craquage dans un appareil à fonctionnement discontinu à une température de 371°C à 649°C, une pression de l'atmosphérique à 1480 kPa et un temps de contact de 0,01 heure à 24 heures.

25. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est mise en oeuvre par hydro-craquage dans un appareil à écoulement à une température de 204°C à 538°C, une pression de 3549 kPa à 24233 kPa, une vitesse spatiale horaire pondérale de 0,1 h⁻¹ à 10 h⁻¹ et un rapport molaire hydrogène/oléfine de 1 à 20.

26. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est mise en oeuvre par hydro-craquage dans un appareil à fonctionnement discontinu à une température de 204°C à 538°C, une pression de 3549 kPa à 24233 kPa, un temps de contact de 0,01 heure à 24 heures, et un rapport molaire hydrogène/oléfine de 1 à 20.

27. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une oligomérisation ou une polymérisation réalisée dans un appareil à écoulement à une température de 35°C à 502°C, une pression de l'atmosphérique à 69049 kPa, une VSHP de 0,1 à 50 h⁻¹ et un rapport molaire hydrogène/oléfine de 0 à 20.

28. Le procédé de l'une quelconque des revendications 1 à 14, dans lequel la réaction de catalyse acide est une oligomérisation ou une polymérisation réalisée dans un appareil à fonctionnement discontinu à une température de 35°C à 502°C, une pression de l'atmosphérique à 27680 kPa, un temps de contact de 0,1 à 48 heures et un rapport molaire hydrogène/oléfine de 0 à 20.

