

DESCRIPTION

PROCESS FOR PRODUCING ALKYLATED AROMATIC COMPOUND AND

PROCESS FOR PRODUCING PHENOL

TECHNICAL FIELD

5 [0001]

The present invention relates to a process for allowing an aromatic compound to react with a ketone and hydrogen to produce a corresponding alkylated aromatic compound by, and to a process for producing a phenol wherein the above process is performed in a step. More specifically, it relates to a process for producing an alkylated aromatic compound by reacting a ketone, an aromatic compound and hydrogen using a specific catalyst in a single reaction step, and to a process for producing a phenol wherein the above process is performed in a step.

15

BACKGROUND OF THE INVENTION

[0002]

A process for producing cumene by reacting benzene and propylene, a process for producing cumene hydroperoxide by oxidizing cumene, and a process for producing phenol and acetone by acid decomposing cumene hydroperoxide are each known. A process in which these reactions are combined is a production process for a phenol generally called as a cumene method, and is a main process for producing a phenol.

20

[0003]

The cumene method has a property that acetone is produced simultaneously. Although the property becomes merits when acetone is simultaneously desired, , when acetone is obtained
5 in an excessive amount with respect to the demand thereof, the cost difference with propylene which is a raw material acts disadvantageously to lead to a bad economic efficiency. Therefore, in order to lead the cost difference between an olefin which is a raw material and a ketone which is co-produced to
10 advantageousness, proposed is, for example, a process for simultaneously producing phenol and methylethyl ketone by oxidizing and acid decomposing secondary butyl benzene obtainable from n-butene and benzene (referred to Patent documents 1 and 2). In this process, since the selectivity of
15 secondary butylbenzene hydroperoxide, which is an aimed product by oxidation of secondary butyl benzene, is only about 80% while acetophenone is incidentally produced in an amount of 15% or more, the yield of this process as a phenol production process does not reach to that of the cumene method.

20 [0004]

Furthermore, a process for obtaining phenol and cyclohexanone by oxidizing and acid decomposing cyclohexylbenzene obtainable from cyclohexene and benzene is also proposed. In this process, since phenol is obtained by

dehydrogenating resulting cyclohexanone, the by-production of a ketone can be avoided formally. In the oxidation reaction of cyclohexylbenzene, however, the yield of aimed cyclohexylbenzenehydroperoxide is low and the industrial value thereof is low.

[0005]

Under the circumstances, for the cumene method having the highest yields of oxidation and acid decomposition, in order to avoid the defect of acetone incidentally produced with propylene which is a raw material while keeping the superiority, methods for reusing the acetone which is by-produced using various methods are proposed.

[0006]

Acetone is easily convertible into isopropanol by hydrogenation. The process where this isopropanol is dehydrated to prepare propylene and then it is allowed to react with benzene to obtain cumene. Namely, a process of reusing acetone as a raw material for the cumene method is proposed (referred to Patent document 3). This process, however, has a problem of having two additional steps of hydrogenation step and dehydration step.

[0007]

Consequently, processes of obtaining cumene by directly allowing isopropanol obtained by hydrogenation of acetone to

react with benzene are proposed (referred to Patent documents 4 to 6). Particularly, the patent document 6 discloses a process of preparing isopropanol from acetone by-produced and producing phenol by using cumene obtained by allowing it to react with benzene. The process, however, also has an additional hydrogenation step as compared with the original cumene method.

[0008]

On the other hand, as a process of reusing by-produced acetone without adding any steps to the conventional cumene method, namely a process of directly react acetone, benzene and hydrogen, a process of allowing them to react in the co-presence of hydrogen using a catalyst system which comprises a solid acid substance and a Cu compound is disclosed (Patent document 7). However, the process described in the patent document 7 has a tendency that propane is by-produced in the preparation of cumene.

Patent document 1: JP-A-S57-91972

Patent document 2: US-A-2004-0162448 specification

Patent document 3: JP-A-H2-174737

Patent document 4: JP-A-H2-231442

Patent document 5: JP-A-H11-35497

Patent document 6: JP-A-2003-523985

Patent document 7: JP-A-2005-513116

DISCLOSURE OF THE INVENTION

OBJECT OF THE INVENTION

[0009]

5 The present invention aims to provide a new process for
producing an alkylated aromatic compound which can establish a
method industrially practical and which is for obtaining cumene
by directly reacting acetone, benzene and hydrogen. The present
invention aims to provide a process for producing a phenol in
10 a step of which the above process is performed and which does
not involve any additional steps as compared with the
conventional cumene method.

MEANS FOR SOLVING THE OBJECT

15 [0010]

The present inventors have been earnestly studied for
solving the above objects and found that, by using a solid acid
substance and a catalyst composition containing a specific metal
as catalysts with a ketone such as acetone, an aromatic compound
20 such as benzene and hydrogen as starting materials, a
corresponding alkylated aromatic compound such as cumene can be
obtained with a high yield in a single reaction step.

[0011]

That is to say, the process for producing an alkylated

aromatic compound according to the present invention is characterized in that it comprises reacting an aromatic compound, a ketone and hydrogen in the presence of a solid acid substance and a catalyst composition containing at least one metal selected
5 from the group consisting of Co, Re, Ni and a platinum group metal.

[0012]

The metal is preferably at least one metal selected from the group consisting of Co, Re, Ni, Pt and Pd, more preferably at least one metal selected from the group consisting of Co, Re
10 and Ni.

[0013]

The aromatic compound is preferably benzene, and the ketone is preferably acetone.

[0014]

15 The solid acid substance is preferably a zeolite compound, more preferably a zeolite compound having 10- to 16-membered oxygen ring pores, particularly preferably a zeolite compound having 10- or 12-membered oxygen ring pores.

[0015]

20 Specifically, the solid acid substance is preferably at least one zeolite compound selected from the group consisting of β zeolite, MCM-22 zeolite, mordenite, ZSM-5 zeolite, ZSM-12 zeolite and Y type zeolite, more preferably at least one zeolite compound selected from the group consisting of β zeolite and

MCM-22 zeolite.

[0016]

The catalyst composition preferably comprises a carrier supporting at least one metal selected from the group consisting of Co, Re, Ni, Pt and Pd, more preferably the metal is at least one metal selected from the group consisting of Co, Re and Ni.

[0017]

The process for producing a phenol according to the present invention comprises:

10 (a) a step of converting cumene into cumene hydroperoxide by oxidation,

(b) a step of synthesizing phenol and acetone by acid decomposing the cumene hydroperoxide,

15 (c) a step of synthesizing cumene by reacting the acetone generated in the step (b) with hydrogen and benzene, and

(d) a step of circulating the cumene obtained in the step (c) into the step (a).

It is characterized in that the step (c) is carried out in accordance with the above process for producing an alkylated aromatic compound.

ADVANTAGES OF THE INVENTION

[0018]

According to the process for producing an alkylated

aromatic compound of the present invention, an alkylated aromatic compound such as cumene can be obtained by an industrially practical method with a ketone such as acetone, an aromatic compound such as benzene and hydrogen as starting materials in a single reaction step. Further, in the process for producing a phenol in a step of which the process for producing an alkylated aromatic compound is performed, by-produced acetone can be reused without adding the number of step in the conventional cumene method. Furthermore, it is an epochal technique such that the cumene obtained by the process for producing an alkylated aromatic compound has no problem in quality as compared with cumene obtained from propylene or isopropanol and benzene. It the process can advantageously produce phenol from the viewpoints of process and economy.

PREFERRED EMBODIMENTS OF THE INVENTION

[0019]

The process for producing an alkylated aromatic compound according to the present invention is characterized in that it comprise reacting an aromatic compound, a ketone and hydrogen in the presence of a solid acid substance and a catalyst composition comprising at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal.

[0020]

In the present invention, the two components of the solid acid substance and the metal-containing catalyst composition should be used and there is particularly no limitation on the use method thereof. The solid acid substance as an acid catalyst component and the catalyst composition containing the metal may be mixed physically in a level of catalytic particles with a centimeter size. Both of them may be pulverized and mixed followed by being molded anew into catalytic particles with a centimeter size. Moreover, the catalyst composition containing the metal may be supported on the solid acid substance acting as an acid catalyst as a carrier. Conversely, the solid acid substance may be supported on the catalyst composition containing the metal as a carrier.

[0021]

The solid acid substance used in the present invention is a catalyst having a function as an acid and should be those being generally called as a solid acid. Zeolite compound, silica alumina, alumina, sulfuric acid ion-supporting zirconia WO₃-supporting zirconia and the like can be used.

[0022]

The zeolite compound, which is an inorganic crystalline porous compound mainly constituted by silicon and aluminum, is a suitable alkylation catalyst from the viewpoint of heat resistance and selectivity of an aimed alkylated aromatic

compound. A suitable zeolite compound varies depending on an aromatic compound used as a raw material and the molecular diameter of an aimed alkylated aromatic compound.

[0023]

5 For example, when cumene is prepared as an alkylated aromatic compound by using benzene as an aromatic compound and acetone as a ketone, it is preferred to use a zeolite compound having 10- to 16-membered oxygen ring pores as the zeolite compound.

10 [0024]

Examples of the zeolite compound having 10- to 16-membered oxygen ring pores include ferrierite, heulandite, ZSM-5 zeolite, ZSM-11 zeolite, ZSM-12 zeolite, NU-87 zeolite, theta 1 zeolite, weinebeneite, X type zeolite, Y type zeolite, USY type zeolite, 15 mordenite, de-aluminized mordenite, β -zeolite, MCM-22 zeolite, MCM-36 zeolite, MCM-56 zeolite, gmelinite, offretite, cloverite, VPI-5 zeolite and UTD-1 zeolite.

[0025]

20 Of these zeolite compounds, those having pores similar to the molecular diameter of cumene are preferable. It is more preferred to use zeolite compounds having 10- or 12-membered oxygen ring pores. Examples of the zeolite compounds having 10- or 12-membered oxygen ring pores include Y type zeolite, USY type zeolite, mordenite, de-aluminized mordenite, β -zeolite, MCM-22

zeolite, MCM-56 zeolite, ZSM-12 zeolite and ZSM-5 zeolite. Among them, from the viewpoint of cumene selectivity, β -zeolite, MCM-22 zeolite, mordenite, ZSM-5 zeolite, ZSM-12 zeolite and Y type zeolite are more preferred, and β -zeolite and MCM-22 zeolite
5 are particularly preferred.

[0026]

The composition ratio of silicon to aluminum (silicon/aluminum) in these zeolite compounds should be in the range of 2/1 to 200/1, and from the viewpoint of activity and
10 heat stability, it is preferably in the range of 5/1 to 100/1. Furthermore, it is also possible to use so-called isomorphically substituted zeolite compounds obtainable by substituting aluminum atom contained in the zeolite skeleton with a metal other than aluminum, such as Ga, Ti, Fe, Mn or B.

15 [0027]

The solid acid substance has a shape which is not particularly limited and may have any one of spherical, cylindrical, extruded and pulverized shapes. Further, a particle size of it may be selected from the range of 0.01 mm
20 to 100 mm depending on the size of a reactor.

[0028]

The solid acid substance may be used singly and two or more kinds thereof may be used.

[0029]

The metal-containing catalyst composition used in the present invention is a catalyst composition containing at least one metal selected from the group consisting of Co, Re, Ni and platinum group metals, preferably at least one metal selected
5 from the group consisting of Co, Re, Ni, Pt and Pd, more preferably at least one metal selected from the group consisting of Co, Re and Ni.

[0030]

Mention may be made of those containing at least one metal
10 selected from the group consisting of Co, Re, Ni and platinum group metals as it is, and those containing at least one such metal as a metal compound, as the metal-containing catalyst composition. Examples are a metal oxide such as CoO, Co₂O₃, ReO₂, Re₂O₇, NiO, PdO, Rh₂O₃ and RuO₂; a metal chloride such as CoCl₂,
15 ReCl₃, NiCl₂, PdCl₂, RhCl₃ and RuCl₃; and those containing in a cluster metal form such as Ru-Rh or Ru-Pt.

[0031]

Other examples include cobalt(II) nitrate, cobalt(II) acetate, cobalt(II) sulfate, cobalt(II) sulfide, diammonium
20 cobalt(II) sulfate, cobalt hydroxide, cobalt (II) bromide, basic cobalt(II) carbonate, cobalt hexammine chloride, cobalt(II) phosphate, cobalt sponge, cobalt powder, Raney cobalt, cobalt(II) benzoate, cobalt naphthenate, sodium hexanitrocobaltate (III), chlorophthalocyaninato cobalt(II),

tetra-t-butylphthalocyaninato cobalt(II),
 tetra-aminochlorophthalocyaninato cobalt(II),
 tetra-carboxyphthalocyaninato cobalt(II),
 2,3,7,8,12,13,17,18-octaethylporphyrinato cobalt(II),
 5 cobalt(II) 2-ethylhexanoate,
 5,10,15,20-tetraphenylporphyrinato cobalt(II), cobalt(II)
 gluconate, sodium dicyanao(phthalocyaninato) cobalt(III),
 dibromo-bis(triphenylphosphine) cobalt and cobalt(II)
 stearate.

10 [0032]

The catalyst composition containing at least one metal
 selected from the group consisting of Co, Re, Ni and platinum
 group metals is used in the present invention. Furthermore, it
 is preferable that the metal is at least one metal selected from
 15 the group consisting of Co, Re, Ni, Pt and Pd because the
 by-production of alkene is decreased in producing an alkylated
 aromatic compound. That is to say, in producing cumene by
 reacting benzene, acetone and hydrogen, hydrocarbons such as
 propane are occasionally by-produced. However, the use of the
 20 catalyst composition containing at least one metal selected from
 the group consisting of Co, Re, Ni, Pt and Pd decreases the
 by-production of hydrocarbons such as propane.

[0033]

The metal is preferably at least one metal selected from

the group consisting of Co, Re and Ni because the by-production of cyclic olefins is decreased in producing the alkylated aromatic compound. That is to say, for example, cyclohexane is occasionally by-produced in producing cumene by reacting benzene, acetone and hydrogen. However, use of the catalyst composition containing at least one metal selected from the group consisting of Co, Re and Ni decreases the by-production of cyclohexane.

[0034]

The catalyst composition containing at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal is not particularly limited as long as it has capability of hydrogenating a carbonyl functional group to alcohol. So-called hydrogenation catalysts which are commercially available can be used as they are, and those supported on various carriers and the like are available in the market.

[0035]

As the carrier, for example, silica, alumina, silica alumina, titania, magnesia, silica magnesia, zirconia, carbon, acid clay and diatomaceous earth can be used. Among them, it is preferred to select at least one of silica, alumina, silica alumina, titania, magnesia, silica magnesia, zirconia and carbon.

[0036]

Examples of the commercially available catalyst compositions include Co on alumina catalyst, Co on silica catalyst, Co on carbon catalyst, 5% Re carbon catalyst, 5% Re alumina catalyst, nickel on silica alumina catalyst, 5% Pd carbon catalyst, Lindlar catalyst (obtainable by adding Pb to Pd carbon catalyst), 5% Pt carbon catalyst, 0.5% Pt sulfided carbon catalyst, 5% Rh alumina catalyst and 5% Ru alumina catalyst. It is also possible to use those obtainable by varying the supported amount to 1% or 0.5%. In these catalysts, it is preferable that at least one metal selected from the group consisting of Co, Re and Ni is contained from the viewpoint of the yield of an aimed compound.

[0037]

These catalyst compositions containing the metal may be used singly and two or more kinds thereof may be used.

[0038]

Furthermore, when a metal salt such as PbSO_4 , FeCl_2 or SnCl_2 , an alkali metal or an alkali metal salt such as K or Na, BaSO_4 or the like is added to these catalyst compositions containing the metal, the activity and the selectivity are improved in a certain case. These can be added in accordance with the necessity.

[0039]

The catalyst composition containing the metal has a shape

which is not particularly limited and may have any one of spherical, cylindrical, extruded and pulverized shapes. Further, a particle size of it may be selected from the range of 0.01 mm to 100 mm depending on the size of a reactor.

5 [0040]

These catalyst compositions containing the metal may be supported on the above-described solid acid substance. Specifically, it can be supported on the solid acid substance by a method of impregnating the solid acid substance with a
10 nitrate aqueous solution of at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal and calcining, a method of making these into a complex bonded with an organic molecule which is called as a ligand in order to make them soluble in an organic solvent, adding them to the organic
15 solvent to prepare a solution, and then impregnating the solid acid substance with the solution followed by calcining, a method of depositing due to that some of the complexes vaporize in a vacuum.

Moreover, in preparing the solid acid substance from the
20 corresponding metal salt, it is possible to employ a coprecipitation method where carrier synthesis and support of the metal-containing catalyst composition are simultaneously carried out by coexisting of a salt of at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal

which is to be a hydrogenation catalyst.

[0041]

In the present invention, compounds having 6 to 20 carbon atoms can be exemplified as examples of the aromatic compound.

5 For example, they include benzene homologues such as benzene, toluene and xylene, and their substituent derivatives; and naphthalene homologues such as naphthalene and methyl naphthalene, and their substituent derivatives. Examples of ketone are compounds having 3 to 20 carbon atoms, and those
10 symmetric and asymmetric can be used.

Examples of the group bonding to a carbonyl group include an alkyl group and an aryl group. Specifically, mention may be made of acetone, methylethyl ketone, acetophenone and the like.

[0042]

15 Of these, the reaction for producing cumene by using benzene as the aromatic compound and acetone as the ketone is industrially most important. In this case, the molar ratio of benzene to acetone (benzene/acetone) is preferably 1 to 20. When it is lower than that range, the productions of diisopropyl
20 benzene and triisopropyl benzene are apt to be increased. In the process of cumene, diisopropyl benzene and triisopropyl benzene can be returned to cumene by trans-alkylation with benzene. However, the trans-alkylation is uneconomical because the reaction temperature is high, and when the amounts of

diisopropyl benzene and triisopropyl benzene are too large, the steam cost is increased. While, when it is over the above range, it is uneconomical because a distillation column is loaded in recovering the excess benzene in the post step of the reactor.

5 [0043]

The reaction of the aromatic compound and ketone according to the present invention is characterized by being carried out in the presence of hydrogen. The hydrogen used herein may be a hydrogen gas in a molecule state or a hydrocarbon such as
10 cyclohexane which generates hydrogen in the reaction condition. When acetone, benzene and hydrogen are reacted, the hydrogen should be equimolecular or larger than acetone in principle. From the viewpoint of recovering with separation, the preferable range is 1 to 10 times mole, more preferably 1 to 5 times mole
15 based on acetone. When it is desired that the convert ratio of acetone be depressed to 100% or less, it can be met by decreasing the amount of hydrogen used from 1 time mole. Furthermore, hydrogen for feeding in the reaction of the present invention is reacted with oxygen atom of acetone to be made into water,
20 and can be taken out together with cumene from the outlet of the reactor. Moreover, hydrogen in an amount more than or equal to the equivalent amount with acetone is not used essentially as long as undesirable side reaction does not proceed.

[0044]

When hydrogen gas is added to the reaction, it is generally fed continuously. However, it is not particularly limited this method. It is possible to employ intermittent feeding that at the beginning of the reaction, hydrogen is added, and then the
5 hydrogen feeding is stopped during the reaction and after a certain time, hydrogen is fed again. Further, in the liquid phase reaction, hydrogen gas may be dissolved in a solvent and fed. Moreover, in the recycle process, hydrogen gas recovered together with light boiling fractions from the top of a tower
10 may be fed. In general, the pressure of hydrogen to be added is the same as the pressure of the reactor, but it may be properly changed according to the method for feeding hydrogen.

[0045]

In carrying out the present reaction, the methods and
15 conditions thereof do not particularly have limitations. For example, it is possible to employ the following conditions and methods.

[0046]

The contact of acetone, benzene and hydrogen gas which are
20 reaction raw materials is conducted in any one of gas-liquid counter current and gas-liquid parallel current, in any one liquid-gas direction of liquid descending - gas ascending, liquid ascending - gas descending, liquid-gas ascending and liquid-gas descending.

[0047]

Although the reaction temperature is also not particularly limited in the present invention, it is preferably in the range of 50 to 300°C, more preferably 60 to 200°C. In general, the pressure range for carrying out is preferably 0.1 to 500 atm, more preferably 0.5 to 100 atm.

[0048]

Furthermore, the catalyst amount used in carrying out the present invention is not particularly limited. For example, in the reaction using a fixed bed flow reactor, the catalyst amount, as represented by a value determined by dividing the feeding amount (weight) of raw materials (ketone + aromatic compound) per hour by the weight of catalyst, namely WHSV, is preferably in the range of 0.1 to 200 /h, more preferably 0.2 to 100/h.

[0049]

The weight ratio of the solid acid substance to the catalyst composition containing at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal is not particularly limited. In general, the solid acid substance : the metal-containing catalyst composition (the weight ratio) is 1 : 0.01 to 1 : 100, preferably 1 : 0.05 to 1 : 50. When the weight ratio of solid acid substance is too small, it is not economical because the alkylation reaction is not sufficiently carried out to decrease the yield of the alkylated aromatic

compound such as cumene. Moreover, when the weight ratio of the solid acid substance is too large, it is also not economical because the conversion rate of acetone is decreased.

[0050]

5 In the process for producing the alkylated aromatic compound of the present invention, it is considered that after a ketone is hydrogenated to generate alcohol by the function of the metal-containing catalyst composition, the alcohol and the aromatic compound are alkylated by the function of the solid acid
10 substance and thereby made into the alkylated aromatic compound. That is to say, it is considered that hydrogenation and alkylation take place step by step in the production process of the present invention.

[0051]

15 When the fixed bed reaction is employed for the reaction form of the present invention, the filling method of the solid acid substance and the metal-containing catalyst composition occasionally affects the reaction result largely. As described above, it is considered that hydrogenation and alkylation take
20 place step by step in the present invention. Therefore, filling of catalyst seeds proper for each step of the reaction in order is a preferable filling method from the viewpoints that the catalyst is used efficiently and undesirable side reactions are controlled.

[0052]

In particular, when the hydrogen pressure or the temperature is increased in order to increase the reaction rate, the occurrence of undesirable side reactions which are not found at a low hydrogen pressure or at a low reaction temperature is
5 common in general chemical reactions. Such a case has a possibility that the method of filling the catalyst largely affects the reaction results.

[0053]

10 Examples of the method of filling the catalyst seeds proper for each step of the reaction in order are as follows:

(1) A method of mixing the solid acid substance and the metal-containing catalyst composition, and filling them.

(2) A method of filling such that a layer of the metal-containing
15 catalyst composition (upper-stream side) and a layer of the solid acid substance (lower-stream side) are formed.

(3) A method of filling the solid acid substance on which the metal-containing catalyst composition is supported.

(4) A method of filling such that a layer of the metal-containing
20 catalyst composition (upper-stream side) and a layer of the solid acid substance and the metal-containing catalyst composition (lower-stream side) are formed.

(5) A method of filling such that a layer of the metal-containing catalyst composition (upper-stream side) and a layer of the solid

acid substance on which the metal-containing catalyst composition is supported(lower-stream side) are formed.

(6) A method of filling such that a layer of the solid acid substance and the metal-containing catalyst composition
5 (upper-stream side) and a layer of the solid acid substance (lower-stream side) are formed.

(7) A method of filling such that a layer of the solid acid substance on which the metal-containing catalyst composition is supported (upper-stream side) and a layer of the solid acid
10 substance (lower-stream side) are formed. The upper-stream side is an inlet side of the reactor, namely, it represents a layer that the raw materials pass through in the first half of the reaction. The lower-stream side is an outlet side of the reactor, namely, it represents a layer which is passed through
15 in the last half of the reaction.

[0054]

The reaction of the present invention may be carried out in a diluting condition by adding a solvent or gas inert to the catalyst and the reaction agents into the reaction system.

20 [0055]

The reaction of the present invention can be carried out in any one method of batch type, semi-batch type and continuous flow type methods. It can be carried out in any one form of liquid phase, gas phase, and gas-liquid mixed phase. As the method of

filling the catalyst, it is possible to employ various methods such as fixed bed, fluid bed, suspension bed and tray fixed bed, and there is no trouble in carrying out with any method.

[0056]

5 In carrying out the present invention, the solid acid substance and the metal-containing composition are preferably dehydrated by known methods. In the case of the fixed bed reaction method, the reactor is filled with the solid acid substance and the metal-containing composition, and should be
10 kept at a temperature of 300°C or higher for 10 min or more while passing an inert gas such as nitrogen and helium. Furthermore, in order to exhibit the activity of the metal-containing catalyst composition which is a hydrogenation catalyst, it is possible to carrying out treatment in a hydrogen gas stream after the
15 dehydration treatment.

[0057]

When the catalyst activity lowers at a certain elapsed time, the activities of the solid acid substance and the metal-containing composition can be recovered by carrying out
20 reproduction with known methods.

[0058]

In order to keep the production of the alkylated aromatic compound such as cumene, it is possible to employ a merry-go-round method that two or three reactors are set in

parallel, and while one reactor is working for reproduction, the reaction is carried out by the remaining one or two reactors. Furthermore, when three reactors are used, it is possible to employ a method that two other reactors are connected linearly to thereby decrease the variation of the production. Moreover, when carrying out by the fluid bed flow reaction method or the moving bed reaction method, it is possible to keep the activities at a constant by taking out a part or all of the catalysts continuously or intermittently from the reactor and supplying the corresponding amount.

[0059]

In the above manner, cumene can be directly obtained from by-produced acetone in the phenol production by the process of producing an alkylated aromatic compound of the present invention.

[0060]

The cumene thus prepared may be utilized as a raw material for production of phenol and acetone. It can be used in a process for producing phenol comprising the following steps (a) to (d) by oxidizing the cumene and then decomposing, and further, various improved processes may be provided. The step (c) is carried out in accordance with the above process for producing an alkylated aromatic compound. The process comprises:

(a) a step of converting the cumene to by oxidization,

(b) a step of synthesizing phenol and acetone by acid-decomposing the cumene hydroperoxide,

(c) a step of synthesizing cumene by reacting the acetone generated in the step (b) with hydrogen and benzene,

5 (d) a step of circulating the cumene obtained in the step (c) to the step (a).

EXAMPLE

The present invention is described in more detail with
10 reference to the examples, but the present invention is not limited by the examples.

Example 1

[0061]

2.0 g of a 5% Re carbon catalyst (manufactured by NE Chemcat
15 Co.) and 2.0 g of β zeolite (classified into 250 to 500 μ after compression molding at 20 MPa, manufactured by Shokubai Kasei Co., Ltd.) were mixed homogenously, and then fed into a quartz glass reactor having a diameter of 3 cm and a length of 40 cm and calcined in a nitrogen gas stream of 30 ml/min at 500°C for
20 1 hr, and then subjected to reduction treatment in a hydrogen gas stream of likewise 30 ml/min at 500°C for 1 hr.

[0062]

In the hydrogen gas stream, the temperature was decreased to 160°C, and then a mixed solution of benzene and acetone

(benzene/acetone (molar ratio) = 5/1) was passed through at a rate of 2.3 ml/min. A resulting product was collected by cooling an outlet.

[0063]

5 One to two hours after the reaction start, the resulting product was analyzed by a gas chromatography. All of acetone was disappeared, and cumene, m-diisopropyl benzene and p-diisopropyl benzene were generated in amounts of 95% on the basis of the amount of acetone fed. The generation of
10 cyclohexane was not found at all.

Example 2

[0064]

1.0 g of a nickel on silica alumina catalyst (manufactured by Süd Chemie Co. G-96D, stabilized nickel, supporting amount
15 of nickel is 59%) and 1.0 g of β zeolite were mixed homogenously, and then fed into a quartz glass reactor having a diameter of 3 cm and a length of 40 cm, and calcined in a nitrogen gas stream of 10 ml/min at 230°C for 1 hr, and then subjected to reduction treatment in a mixed gas stream of the same nitrogen of 10 ml/min
20 and hydrogen of 0.93 ml/min at 230°C for 1 hr. In the nitrogen and hydrogen gas stream, the temperature was decreased to 100°C, and then a mixed solution of benzene and acetone (benzene/acetone (molar ratio)= 5/1) was passed at a rate of 1.2 ml/min through the reactor. A resulting product was collected by cooling an

outlet.

[0065]

One to two hours after the reaction start, the resulting product was analyzed by a gas chromatography. Cumene, m-diisopropyl benzene and p-diisopropyl benzene were generated in amounts of 10% on the basis of the amount of acetone fed. The generation of cyclohexane was not found at all.

Example 3

[0066]

The reaction was performed in the same manner as Example 1 except that 0.5 % Pt sulfided carbon catalyst (manufactured by NE Chemcat Co.) was used in place of 2.0 g of a 5% Re carbon catalyst (manufactured by NE Chemcat Co.).

[0067]

One to two hours after the reaction start, the resulting product was analyzed by a gas chromatography. Cumene, m-diisopropyl benzene and p-diisopropyl benzene were generated in amounts of 10%, and cyclohexane was generated in an amount of 6%, on the basis of the amount of acetone fed.

Example 4

[0068]

The reaction was performed in the same manner as Example 1 except that Lindlar catalyst (obtainable by adding Pb to a Pd carbon catalyst manufactured by NE Chemcat Co.) was used in place

of 2.0 g of a 5% Re carbon catalyst (manufactured by NE Chemcat Co.).

[0069]

One to two hours after the reaction start, the resulting
5 product was analyzed by a gas chromatography. Cumene,
m-diisopropyl benzene and p-diisopropyl benzene were generated
in amounts of 10%, and cyclohexane was generated in an amount
of 5%, on the basis of the amount of acetone fed.

Example 5

10 [0070]

1.0 g of a Co on alumina catalyst (manufactured by Süd
Chemie Co. G-62A, supporting amount of cobalt is 40 - 50%) and
1.0 g of β zeolite (classified into 250 to 500 μ after compression
molding at 20 MPa, manufactured by Shokubai Kasei Co., Ltd.)
15 were mixed homogenously, and then fed into a quartz glass reactor
having a diameter of 3 cm and a length of 40 cm, and then treated
in a nitrogen gas stream of 10 ml/min at 350°C for 1 hr, thereafter
subjected to reduction treatment in a hydrogen gas stream of the
same 10 ml/min at 350°C for 1 hr.

20 [0071]

In the hydrogen gas stream, the temperature was decreased
to 160°C, and then a mixed solution of benzene and acetone
(benzene/acetone (molar ratio) = 5/1) was passed through the
reactor at a rate of 1.2 ml/min. A resulting product was

collected by cooling an outlet.

[0072]

One to two hours after the reaction start, the resulting product was analyzed by a gas chromatography. All of acetone
5 was disappeared, and cumene, m-diisopropyl benzene and p-diisopropyl benzene were generated in amounts of 95% on the basis of the amount of acetone. The generation of cyclohexane was not found at all.

[0073]

10 Comparative Example 1

The reaction was performed in the same manner as Example 1 except for using only a Re catalyst as a catalyst.

[0074]

One to two hours after the reaction start, the resulting
15 product was analyzed by a gas chromatography. Cumene was not generated and only isopropanol was generated.

[0075]

Comparative Example 2

The reaction was performed in the same manner as Example
20 1 except for using only β -zeolite as a catalyst.

[0076]

One to two hours after the reaction start, the resulting product was analyzed by a gas chromatography. Cumene was not generated, and only trimethyl benzene and tert-butyl benzene

were generated.

Example 6

[0077]

1.0 g of a 5% Re on alumina (catalyst which was prepared
5 in accordance with Applied Catalysis A: General 162, PP. 161-169,
in 1997 and whose supporting amount of Re is 5%) and 1.0 g of
the β zeolite were mixed homogenously, and then fed into a quartz
glass reactor having a diameter of 3 cm and a length of 40 cm
and dried in a nitrogen gas stream of 30 ml/min at 350°C for 1
10 hr, thereafter subjected to reduction treatment in a hydrogen
gas stream of 10 ml/min at 400°C for 3 hr.

[0078]

After that, in the hydrogen gas stream of 3 ml/min, the
temperature was decreased to 150°C, and then a mixed solution
15 of benzene and acetone (benzene/acetone (molar ratio) = 3/1) was
passed through the reactor at a rate of 1.2 ml/min. A resulting
liquid product was collected by cooling an outlet.

[0079]

Furthermore, the gas collection was carried out, although
20 it was not carried out in the above examples and comparative
examples. One to three hours after the reaction start, the
resulting product was analyzed by a gas chromatography (column
for gas phase analysis: manufactured by VARIAN Co., PLOT FUSED
SILICA 50M x 0.32 MM ID COATING AL₂O₃/NA₂SO₄ DF = 5UM, column

for liquid phase analysis: ZB-WAX manufactured by Phenomenex Co.). As a result, the acetone conversion rate was 97.2%, and the selectivity on the basis of acetone was, 6.5% for a hydrocarbon such as propane, 54.3% for cumene and 25.9% for diisopropyl benzene.

Example 7

[0080]

The reaction and analysis were performed in the same manner as Example 6 except for using MCM-22 zeolite (obtainable by compression molding a catalyst prepared according to VERIFIED SYNTHESSES OF ZEOLITIC MATERIALS Second Revised Edition 2001, P225, at 20 MPa followed by classification into 250 to 500 μ) in place of β zeolite.

[0081]

As a result, the acetone conversion rate was 95.6%, and the selectivity on the basis of acetone was, 7.5% for a hydrocarbon such as propane, 55.5% for cumene and 13.8% for diisopropyl benzene.

Comparative Example 3

[0082]

The reaction and analysis were performed in the same manner as Example 6 except that copper chromite (product name: G99b, element % by mass: Cu 35%, Cr 31%, Ba 2%, Mn 3%, and an atomic ratio of Zn to Cu of 0, manufactured by Süd Chemie Co.,) was used

in place of the 5% Re on alumina and the reduction treatment was carried out at 200°C.

[0083]

As a result, the acetone conversion rate was 95.0%, and
5 the large amounts of the hydrocarbon such as propane were
by-produced such that the selectivity on the basis of acetone
was, 25.1% for a hydrocarbon such as propane, 33.2% for cumene
and 31.4% for diisopropyl benzene.

10 INDUSTRIAL APPLICABILITY

[0084]

The present invention provides an industrially practical
process for producing an alkylated aromatic compound in a single
reaction step by directly reacting a ketone and an aromatic
15 compound. Using the process, it is possible to obtain cumene
directly from an acetone by-produced in the phenol production
by the cumene method. The cumene thus obtained can be used as
a raw material for production of phenol and acetone, and can be
used for a process of oxidizing cumene and then decomposing it.

CLAIMS

1. A process for producing an alkylated aromatic compound, which process comprises reacting an aromatic compound, a ketone and hydrogen in the presence of a solid acid substance
5 and a catalyst composition comprising at least one metal selected from the group consisting of Co, Re, Ni and a platinum group metal.

2. The process for producing an alkylated aromatic compound according to claim 1, wherein the metal is at least one metal selected from the group consisting of Co, Re, Ni, Pt and
10 Pd.

3. The process for producing an alkylated aromatic compound according to claim 1, wherein the metal is at least one metal selected from the group consisting of Co, Re and Ni.

4. The process for producing an alkylated aromatic
15 compound according to any one of claims 1 to 3, wherein the aromatic compound is benzene and the ketone is acetone.

5. The process for producing an alkylated aromatic compound according to any one of claims 1 to 3, wherein the solid acid substance is a zeolite compound.

20 6. The process for producing an alkylated aromatic compound according to any one of claims 1 to 3, wherein the solid acid substance is a zeolite compound having 10- to 16-membered oxygen ring pores.

7. The process for producing an alkylated aromatic

compound according to any one of claims 1 to 3, wherein the solid acid substance is a zeolite compound having 10- or 12-membered oxygen ring pores.

8. The process for producing an alkylated aromatic
5 compound according to any one of claims 1 to 3, wherein the solid acid substance is at least one zeolite compound selected from the group consisting of β zeolite, MCM-22 zeolite, mordenite, ZSM-5 zeolite, ZSM-12 zeolite and Y type zeolite.

9. The process for producing an alkylated aromatic
10 compound according to any one of claims 1 to 3, wherein the solid acid substance is at least one zeolite compound selected from the group consisting of β zeolite and MCM-22 zeolite.

10. The process for producing an alkylated aromatic
15 compound according to claim 1, wherein the catalyst composition comprises a carrier supporting at least one metal selected from the group consisting of Co, Re, Ni, Pt and Pd.

11. The process for producing an alkylated aromatic
compound according to claim 10, wherein the metal is at least one metal selected from the group consisting of Co, Re and Ni.

20 12. A process for producing a phenol, which process comprises:

(a) a step of converting cumene to cumene hydroperoxide by oxidation,

(b) a step of synthesizing phenol and acetone by

acid-decomposing the cumene hydroperoxide,

(c) a step of synthesizing cumene by reacting the acetone generated in the step (b) with hydrogen and benzene, and

5 (d) a step of circulating the cumene obtained in the step (c) to the step (a),

wherein the step (c) is carried out in accordance with the process as claimed in claim 1.