

ABSTRACT**“POWDERED LIME COMPOSITION, METHOD OF PREPARING SAME
AND USE THEREOF”**

5 Powdered lime composition having a BET specific surface area that is equal to or greater than $25 \text{ m}^2/\text{g}$ and a BJH total pore volume obtained from nitrogen desorption that is equal to or greater than $0.1 \text{ cm}^3/\text{g}$, and furthermore comprising an alkali metal.

Method of preparing the composition and use thereof to reduce flue gases.

10

No figure