

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



162162



(43) International Publication Date
11 April 2002 (11.04.2002)

PCT

(10) International Publication Number
WO 02/029344 A1

(51) International Patent Classification⁷: **F27D 1/14**, 1/16

(21) International Application Number: PCT/EP01/11399

(22) International Filing Date: 2 October 2001 (02.10.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00308764.0 4 October 2000 (04.10.2000) EP

GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V.** [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL).

Published:
— with international search report

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **SCHADENBERG, Hendrik** [NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL). **WOLFERT, Anthonij** [NL/NL]; Badhuisweg 3, NL-1031 CM Amsterdam (NL)

(48) Date of publication of this corrected version:
19 September 2002

(15) Information about Correction:
see PCT Gazette No. 38/2002 of 19 September 2002, Section II

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette

(54) Title: PROCESS FOR PROVIDING A SURFACE WITH A FIRE-PROOF AND/OR WEAR RESISTANT LINING

(57) Abstract: Process to provide a surface with a fire-proof and/or wear resistant lining comprising the following steps: a) mechanically fixing anchoring means to the surface, which anchoring means are pre-coated with a coating that melts at a temperature in the range from 40 to 100 °C; b) applying a lining material onto the surface provided with the anchoring means, c) curing the lining material to obtain a solid mass; d) drying the lining, to a temperature at least sufficient to melt the coating on the anchoring means, to obtain a fire-proof and/or wear resistant lining. Anchoring means used in the process

WO 02/029344 A1

G00002