

THIS SHEET HAS BEEN
REPLACED

SPECIFICATION

POLYESTER RESIN COMPOSITION AND PROCESS FOR THE PREPARATION THEREOF

The present invention generally relates to polyester resin compositions and to processes for their preparation. More particularly, the present invention provides low cost resin compositions exhibiting improved processability from which molded articles having reduced distortion and/or warpage can be made. Moreover, such articles can be made without adversely affecting the polyester resin's otherwise excellent inherent mechanical properties.

Thermoplastic polyester resins such as polyalkylene terephthalate resins have excellent mechanical and electrical properties, as well as desirable physical and chemical characteristics. As a result, polyester resins have been used as engineering plastics in an extensive field of end-use applications including automobiles, electrical and electronic apparatus, and the like.

Although thermoplastic polyester resins can, in and of themselves, be molded into articles, various reinforcements or additives have typically been incorporated in polyester resin compositions (depending upon the field of application) so as to obtain improved resin properties, particularly mechanical properties.

This Sheet Has Been Replaced



It is also well known that the addition of a fibrous reinforcement, such as glass or carbon fibres, imparts desirably high mechanical strength properties and increased rigidity to the thermoplastic polyester resins. However, molded articles formed of thermoplastic polyester resins containing fibrous reinforcement materials tend to distort (warp) and thus cannot be used in environments where close spatial tolerances are required.

The present invention is directed towards solving the distortion problems associated with molded articles formed of fibre-reinforced polyester resins. More particularly, the present invention is directed towards enhancing the distortion resistance of polyester resin compositions containing fibrous reinforcement and/or flaky fillers without damaging the otherwise excellent mechanical properties associated with polyester resins. In this regard, the present invention broadly resides in the use of binder-agglomerated glass granules (to be described below) instead of conventional flaky filler materials in combination with a fibrous reinforcement medium so as to attain polyester resin compositions of decreased distortion when molded.

More specifically, the present invention relates to novel fibre-reinforced polyester resin compositions including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight (based on the total composition weight) of a fibrous reinforcement medium and (C) between 3 and 65% by weight (based on the total composition weight) of binder-agglomerated glass granules.

The present invention is further characterised by methods to obtain such a composition whereby the above-noted components are mixed together and then melt-blended.



The invention thus provides a process for preparing a fibre-reinforced polyester resin composition comprising melt-blending (A) a thermoplastic polyester resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

The invention further provides a process for preparing a fibre-reinforced polyester resin composition comprising the steps of:

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C') glass flakes, and

dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μm and 2000 μm , and a maximum particle diameter which does not exceed 5000 μm , and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

The thermoplastic polyester resin (A) that may be used in the compositions of the present invention is a polyester prepared by the polycondensation of polyester forming monomers. Thus, the polyester may be prepared by polycondensing a dicarboxylic acid compound and a dihydroxy compound, a hydroxy carboxylic acid compound itself or any combination of the same. The compositions of the present invention may include homopolyesters and/or copolyesters.



Examples of the dicarboxylic acid compound that may be used in the preparation of the polyester resin include well-known dicarboxylic acids such as terephthalic, isophthalic, naphthalenedicarboxylic, diphenyldicarboxylic, diphenyl ether dicarboxylic, diphenylethanedicarboxylic, cyclohexanedicarboxylic, adipic and sebacic acids and alkyl, alkoxy or halogen-substituted derivatives thereof. Furthermore, these dicarboxylic acids may each be used in the polycondensation as an ester-forming derivative, such as dimethyl ester. Two or more of the dicarboxylic acid compounds may be used simultaneously, if desired.

Examples of the dihydroxy compound that may be used to prepare the polyester resin employed in the compositions of this invention include dihydroxy compounds, such as ethylene glycol, propylene glycol, butanediol, neopentyl glycol, hydroquinone, resorcinol, dihydroxyphenyl, naphthalenediol, dihydroxydiphenyl ether, cyclohexandiol, 2,2-bis(-hydroxyphenyl)propane and diethoxylated bisphenol A; polyoxyalkylene glycols and alkyl, alkoxy or halogen-substituted derivatives thereof. The dihydroxy compounds may be used either alone or as a mixture of two or more of the same.

Examples of suitable hydroxy carboxylic acids include hydroxy carboxylic acids themselves, such as hydroxybenzoic acid, hydroxynaphthoic acid and diphenyleneoxycarboxylic acid; and alkyl, alkoxy or halogen-substituted derivatives thereof. Furthermore, ester forming derivatives of these hydroxy carboxylic acids may be used. According to the present invention, one or more of the compounds may be employed during the polycondensation reaction.



Polyester resins having branched or cross-linked structures which result when a minor amount of a trifunctional monomer is used in addition to the above-noted monomer components may also be employed in the composition of the present invention. Examples of preferred trifunctional monomers include trimellitic, trimesic and pyromellitic acids, pentaerythritol and trimethylolpropane.

According to the present invention, all of the thermoplastic polyester resins prepared by the polycondensation of the above-noted monomers can be used as the component (A) either alone, or as a mixture of two or more of the same. It is preferred, however, that the polyester resin component (A) be a crystalline polyalkylene terephthalate, for example polybutylene terephthalate (PBT), polyethylene terephthalate (PET) or a copolymer containing at least 60% by weight of polybutylene terephthalate or polyethylene terephthalate units.

If necessary, the thermoplastic polyester resin component (A) may contain up to about 30% by weight of other thermoplastic resins, such as polyamides, polycarbonates, polyolefins, fluororesins or acrylic resins. Particularly, incorporating an amorphous thermoplastic resin in addition to a crystalline polyester resin as component (A) yields further reductions in distortion of molded articles. Thus, in some cases, a combination of a crystalline thermoplastic polyester resin and an amorphous resin is preferred. In this regard, the incorporation of one or more members selected from among polycarbonates, ABS resins and phenoxy resins together with a crystalline thermoplastic polyester resin is especially favorable.



The fibrous reinforcement medium (B) that may be used in the compositions of the present invention is not particularly limited. Thus, usable fibrous reinforcement media within the scope of the present invention includes mineral fibres, such as glass fibres, carbon fibres, graphite fibres, metal whiskers, metal fibres, silicon carbide fibres, asbestos fibres and wollastonite fibres, in addition to various organic fibres. The use of any particular fibrous reinforcement medium or combination of fibrous reinforcement media may suitably be selected in dependence upon the resin properties that may be desired for a given end-use application, for example, structural reinforcement and/or electrical conductivity properties, or improvements to the resin's frictional characteristics or flame retardancy.

The diameter and length of the fibrous reinforcement medium (B) may each be arbitrarily selected depending upon the required performance characteristics, such as mechanical properties or distortion resistance. It is generally suitable to use glass fibres having a diameter of at least $1\mu\text{m}$ and a length of at least $15\mu\text{m}$, and preferably glass fibres having a diameter of between 2 and $20\mu\text{m}$ and a length of at least $50\mu\text{m}$. If necessary, a sizing agent or surface treatment may be used with the fibrous reinforcement medium, examples of which include functional compounds such as epoxy, isocyanate, silane and titanate compounds. If employed, the sizing compounds will be present in amounts up to 10% by weight, and preferably, between 0.5 and 5% by weight (based on the weight of the fibrous reinforcement medium). These sizing compounds may each be pre-applied to the fibrous reinforcement medium, or may be added to the resin composition as an independent component simultaneously with the fibrous reinforcement medium during preparation of the composition.



The amount of the fibrous reinforcement medium that is used in the compositions of this invention is between 3 and 65% by weight, and preferably between 5 and 50% by weight, based on the total composition weight. If less than 3% by weight of the fibrous reinforcement medium is employed, then little (if any) reinforcement effect is obtained. On the other hand, if the amount of fibrous reinforcement medium exceeds 65% by weight, then difficulties are encountered during molding of the resulting composition.

The compositions of the present invention are especially characterized by containing binder-agglomerated glass granules as component (C) in addition to the above described fibrous reinforcement medium as component (B).

The simultaneous use of a fibrous reinforcement medium and a flaky filler material such as glass flakes or mica flakes has previously been proposed for reducing the distortion or warpage of molded articles, and in this regard, such a combination provides some measure of effectiveness. However, the result in terms of distortion and/or warpage is still unsatisfactory. Particularly, when large amounts of reinforcement media are used, productivity problems in forming molded articles are typically encountered thereby lowering productivity.

Surprisingly, it has now been found that the use of glass flakes that have been agglomerated with a binder remarkably reduce distortion and warpage of molded articles. In addition, processing problems such as "flying" and "bridging" are avoided, presumably because the agglomerated glass flakes are more readily dispersible in the polyester base resin as compared with conventional (non-agglomerated) glass flakes employed previously. As a result, essentially no fractures during extrusion and kneading are encountered.



The term "binder-agglomerated glass granules" used herein and in the accompanying claims is intended to refer to a glass granule having a major axis of between 50 and 5000 μ m and obtained by agglomerating a number of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m with a binder (preferably a thermoplastic binder resin). If the effective granule size is too small, then the benefits sought by the present invention cannot be attained. However, if the granule size is too large, then poor dispersibility of the flakes in the matrix resin will result. According to the present invention, it is preferable that the agglomerated glass granules have a mean particle diameter of between 100 and 2000 μ m, and more preferably between 300 and 2000 μ m, and a maximum particle diameter not exceeding 5000 μ m.


The binder used to agglomerate the glass flakes is not particularly limited. Thus, virtually any binder capable of agglomerating glass flakes may be used, provided of course that it does not exert adverse effects upon the polyester matrix resin. Particular examples of the binder that may be used include addition of polymers of an olefinic monomer such as polyvinyl acetate, polyacrylate, polyvinylpyrrolidone, (acid-modified) polyethylene and (acid-modified) polypropylene and copolymers thereof; polyaddition products such as polyurethane and polyurea; polycondensation products such as unsaturated polyester, nylon and epoxy resin; ring-opening polymerization products such as nylon 6 and polyethyloxazoline; addition condensation products such as urea-formalin resin; and epoxysilane, among which thermoplastic resins and epoxy resins are especially preferred.



The binder-agglomerated glass granules can be prepared by the use of a binder as described above according to any known agglomeration technique. For example, the binder-agglomerated glass granules can be prepared by adding glass flakes to a solution of a binder in a suitable organic solvent, and then mixing the components in a fluidized state, followed by drying the resulting mixture.

The glass flakes that are agglomerated may first be subjected to a surface treatment using coupling agents for the purpose of enhancing the adhesion and/or dispersibility of the flakes in the matrix resin. The surface treatment may be carried out simultaneously with the agglomeration of the glass flakes. Alternatively, a coupling agent may be added independently during the preparation of the resin composition. The coupling agents that may be used for the above purpose include epoxy, isocyanate, silane, titanate and zirconia compounds. Of these, epoxy and silane compounds are especially preferred.

The amount of the binder-agglomerated glass granules that may be used in the present invention is between 3 and 65% by weight, and preferably between 5 and 50% by weight (based on the entire composition weight) that the total amount of the fibrous reinforcement medium and the binder-agglomerated glass granules (i.e. the total of components (B) and (C)) does not exceed 65% by weight of the entire composition. If the amount of binder-agglomerated glass granules is less than 3% by weight, then little (if any) beneficial effect is realized. On the other hand, if the amount of binder-agglomerated glass granules exceeds 65% by weight, then molding difficulties will be encountered.



The compositions of the present invention may optionally contain other additives conventionally used in thermoplastic or thermosetting resins so as to impart desired physical characteristics thereto. Examples of additives that may be used include powdery, granular and flaky inorganic fillers, (i.e. other than the binder-agglomerated glass granules noted above); stabilizers such as antioxidants, heat stabilizers, and ultraviolet absorbers; flame retardants, antistatic agents; lubricants; mold release agents; colorants such as dyes and pigments; lubricating oils; plasticizers; crystallization accelerators and nucleating agents.

The compositions of the present invention can be easily prepared using conventional processes for the preparation of a reinforcement-filled resin. More particularly, the fibrous medium (B) may be used in the form of a chopped strand or roving and if necessary, may be cut into suitable sizes or used as a filament. The necessary components according to the present invention may then be mixed together, kneaded and extruded with a conventional extruder to give a pelletized composition. In this regard, little (if any) fracturing and/or pulverization of the glass flakes ensue - a problem associated with processing of prior art compositions.

Alternatively, the fibrous reinforcement medium (B) and the binder-agglomerated glass flakes (C) may be added into a melt phase of the polyester resin in an extruder. Even in such a "two-stage" addition process, the processability of the composition is extremely improved and fracturing of the fibrous reinforcement and/or glass flakes in the extruder is reduced so as to provide a composition exhibiting excellent mechanical properties and distortion resistance.



The compositions of the present invention are thus especially characterized by containing a fibrous reinforcement medium and binder-agglomerated glass granules from which molded articles can be prepared having significantly reduced distortion (warpage), as compared to compositions of the prior art which contain non-agglomerated glass flakes. In addition, the mechanical strength properties (such as tensile strength) are improved. Furthermore, the compositions of the present invention do not exhibit problems associated with the prior art, such as clogging by the glass flakes or poor extrusion properties. Thus, the compositions of the present invention are of a more consistent quality and can be made with enhanced productivity.

The compositions of the present invention may be used to form exterior trim parts and structural and functional parts and components of automobiles, electrical appliances and other devices. Particular examples of the use of the composition include automotive exterior trim parts such as fenders, bumpers, fuel lids, louvres, lamp housings and outer door handles; structural components, such as the chassis audio, video tape recorders and stereos; and working parts such as gears, cams, levers, guide stays; clutches and rollers. Furthermore, the compositions may be used in electrical or electronic components such as connectors, switches, relays, coils, bobbins, key stems or chassis; cameras, radios, various office automation machines such as facsimile, copying machines, or computers; IC cases, capacitor cases or motor parts.





EXAMPLES

The present invention will now be described in detail referring to the following non-limiting Examples.

The methods for evaluating the characteristics employed in the following Examples are as follows:

(1) Determination of distortion:

A flat test piece (80 mm x 80 mm x 2 mm) having one gate on its side was molded and placed on a surface plate so as to measure the distortion of the most significantly distorted part (i.e. that part wherein the gap between the surface plate and the test piece is largest) of the test piece.

(2) Tensile strength:

Determined according to ASTM D 638. The results in Table 1 are given in kg/cm². 1 kg/cm² is equivalent to 0.0981 MPa, i.e. approximately equal to 0.1 MPa.

(3) Processability during extrusion (observed during pelletization of the composition):

A mixture comprising a polyester resin and glass fibre and/or glass flakes was extruded with an extruder having an inner diameter of 40 mm. The feeding state into an extruder (adhesion or clogging of glass fibre or glass flake in a hopper), the bite of the feed and the state of the extrudate (breakage of strand or surging), were visually observed and categorized using the following four criteria:

4	-----	3	-----	2	-----	1
(not observed)		adhesion or clogging in hopper		(significant)		
(good)		strand breakage or surging		(poor)		

Examples 1 to 5

Polybutylene terephthalate alone or a mixture thereof with polyethylene terephthalate or polycarbonate, glass fibres and binder agglomerated glass flakes were preliminarily mixed together in a ratio as specified in Table 1, fed into an extruder at a rate of 12 kg/h and melt-kneaded to obtain a pelletized composition. This composition was then injection molded into various test pieces. These test pieces were evaluated according to the above-mentioned criteria. The results are shown in Table 1.

Comparative Examples 1 and 2

A pelletized composition was prepared in the same manner as that of the foregoing Examples except that polybutylene terephthalate and either glass fibres or agglomerated glass flakes were used and evaluated in a similar manner to that described above. The results are shown in Table 1.

Comparative Examples 3 to 7

Polybutylene terephthalate alone or a mixture thereof with polyethylene terephthalate or polycarbonate, glass fibre and non-agglomerated glass flakes were mixed together at a ratio as specified in Table 1, fed into an extruder at a rate of 5 kg/h and melt-kneaded to obtain a pelletized composition. This composition was then injection-molded into various test pieces. The test pieces were examined according to the above-mentioned methods. The feeding rate in these Examples was first set at a rate of 12 kg/h similar to the foregoing Examples. However, the glass fibres and glass flakes clogged at the joint zone between the feeder and the extruder thereby



THIS SHEET HAS BEEN
REPLACED

making extrusion difficult. Accordingly, the feed rate was lowered to one-half of that of the foregoing Examples so that the compositions could be pelletized. The results are shown in Table 1.

While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit scope of the appended claims.

This Sheet Has Been Replaced



Table 1

Composition										Quality (physical properties)		
		(A) thermoplastic polyester resin (kind)	(1 by wt.)	polycarbonate (1 by wt.)	(B) fibrous reinforcement (glass fiber, 1 by wt.)	(C) granulated glass flake ³ (1 by wt.)	glass flake ⁴ (1 by wt.)	distortion (mm)	tensile strength (kg/cm ²)	processability in extrusion		
Ex. No.	1	PET ¹	60	-	20	20	-	0.9	1160	4		
	2	-	60	-	10	30	-	0.2	965	4		
	3	-	60	-	30	10	-	2.6	1370	4		
	4	PET/PET ²	45/15	-	20	20	-	0.6	1190	4		
	5	PET	50	10	20	20	-	0.03	1220	4		
Comp. Ex. No.	1	PET	60	-	40	-	-	5.5	1480	4		
	2	-	60	-	-	40	-	0.1	765	4		
	3	-	60	-	20	-	20	3.8	1110	2		
	4	-	60	-	10	-	30	0.5	930	1		
	5	-	60	-	30	-	10	4.5	1300	2		
	6	PET/PET	45/15	-	20	-	20	3.5	1370	2		
	7	PET	50	10	20	-	20	0.7	1190	2		

¹ PET: polybutylene terephthalate resin is product of Polyplastics, trade name, "Duramer".

² PET: polyethylene terephthalate resin

³ mean particle diameter: 600 μ m, binder: epoxy resin, coupling agent: epoxysilane

⁴ mean particle diameter: 600 μ m, (ungranulated, coupling agent: epoxysilane)



THIS SHEET HAS BEEN
REPLACED

3

16

This Sheet Has Been Replaced



CLAIMS

1. A process for preparing a fibre-reinforced polyester resin composition comprising melt-blending (A) a thermoplastic polyester resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

2. A process as claimed in claim 1, wherein the binder-agglomerated glass granules (C) include glass flakes agglomerated in a binder resin.

3. A process as claimed in claim 2, wherein the binder-agglomerated glass granules (C) consist essentially of discrete glass flakes agglomerated in the binder resin.

4. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.



* C L M S *

5. A process for preparing a fibre-reinforced polyester resin composition comprising the steps of:

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C') glass flakes, and

dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μm and 2000 μm , and a maximum particle diameter which does not exceed 5000 μm , and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

6. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) is at least one selected from a homopolymer of polybutylene terephthalate resins and polyethylene terephthalate resins or a copolymer containing polybutylene terephthalate or polyethylene terephthalate units in an amount of at least 60% by weight.

7. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) contains between 3 and 30% by weight of a polycarbonate resin.

8. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) includes glass fibres.



THIS SHEET HAS BEEN
REPLACED

18

9. A process as claimed in any preceding claim, wherein the binder for the binder-agglomerated glass granules (C) is selected from thermoplastic resins and epoxy resins.

10. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.

11. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) and the binder-agglomerated glass granules (C) are collectively present in the composition in an amount not exceeding 65% by weight based on the total composition weight.

12. A polyester resin composition prepared by a process as set forth in any preceding claim.

13. A molded article formed of a polyester resin composition prepared by a process as set forth in any of claims 1 to 11.

14. A fibre-reinforced polyester resin composition including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcement medium and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

15. A composition as claimed in claim 14, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

19

16. A composition as claimed in claim 14 or claim 15, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.



This Sheet Has Been Replaced





ABSTRACT

POLYESTER RESIN COMPOSITION AND PROCESS
FOR THE PREPARATION THEREOF

Polyester compositions exhibiting decreased distortion (warpage), improved processability and productivity are produced by melt-blending a thermoplastic polyester resin with between 3 and 65% by weight of a fibrous reinforcing medium, and between 3 and 65% by weight of binder-agglomerated glass granules.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET

Date : 0.4 JUL 1996....

SPECIFICATION

POLYESTER RESIN COMPOSITION AND PROCESS FOR THE PREPARATION THEREOF

The present invention generally relates to polyester resin compositions and to processes for their preparation. More particularly, the present invention provides low cost resin compositions exhibiting improved processability from which molded articles having reduced distortion and/or warpage can be made. Moreover, such articles can be made without adversely affecting the polyester resin's otherwise excellent inherent mechanical properties.

Thermoplastic polyester resins such as polyalkylene terephthalate resins have excellent mechanical and electrical properties, as well as desirable physical and chemical characteristics. As a result, polyester resins have been used as engineering plastics in an extensive field of end-use applications including automobiles, electrical and electronic apparatus, and the like.

Although thermoplastic polyester resins can, in and of themselves, be molded into articles, various reinforcements or additives have typically been incorporated in polyester resin compositions (depending upon the field of application) so as to obtain improved resin properties, particularly mechanical properties.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET
Date 04 JUL 1996

2

It is also well known that the addition of a fibrous reinforcement, such as glass or carbon fibres, imparts desirably high mechanical strength properties and increased rigidity to the thermoplastic polyester resins. However, molded articles formed of thermoplastic polyester resins containing fibrous reinforcement materials tend to distort (warp) and thus cannot be used in environments where close spatial tolerances are required.

The present invention is directed towards solving the distortion problems associated with molded articles formed of fibre-reinforced polyester resins. More particularly, the present invention is directed towards enhancing the distortion resistance of polyester resin compositions containing fibrous reinforcement and/or flaky fillers without damaging the otherwise excellent mechanical properties associated with polyester resins. In this regard, the present invention broadly resides in the use of binder-agglomerated glass granules (to be described below) instead of conventional flaky filler materials in combination with a fibrous reinforcement medium so as to attain polyester resin compositions of decreased distortion when molded.

More specifically, the present invention relates to novel fibre-reinforced polyester resin compositions including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight (based on the total composition weight) of a fibrous reinforcement medium and (C) between 3 and 65% by weight (based on the total composition weight) of binder-agglomerated glass granules.

The present invention is further characterised by methods to obtain such a composition whereby the above-noted components are mixed together and then melt-blended.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET
Date : 0.4 JUL 1996

12

EXAMPLES

The present invention will now be described in detail referring to the following non-limiting Examples.

The methods for evaluating the characteristics employed in the following Examples are as follows:

(1) Determination of distortion:

A flat test piece (80 mm x 80 mm x 2 mm) having one gate on its side was molded and placed on a surface plate so as to measure the distortion of the most significantly distorted part (i.e. that part wherein the gap between the surface plate and the test piece is largest) of the test piece.

(2) Tensile strength:

Determined according to ASTM D 638. The results in Table 1 are given in kg/cm². 1 kg/cm² is equivalent to 0.0981 MPa, i.e. approximately equal to 0.1 MPa.

(3) Processability during extrusion
(observed during pelletization of the composition):

A mixture comprising a polyester resin and glass fibre and/or glass flakes was extruded with an extruder having an inner diameter of 40 mm. The feeding state into an extruder (adhesion or clogging of glass fibre or glass flake in a hopper), the bite of the feed and the state of the extrudate (breakage of strand or surging), were visually observed and categorized using the following four criteria:

4 ----- 3 ----- 2 ----- 1
(not observed) adhesion or clogging in hopper (significant)

(good) strand breakage or surging (poor)



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET

Date : 04 JUL 1996

16

CLAIMS

1. A process for preparing a fibre-reinforced polyester resin composition comprising melt-blending (A) a thermoplastic polyester resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

2. A process as claimed in claim 1, wherein the binder-agglomerated glass granules (C) include glass flakes agglomerated in a binder resin.

3. A process as claimed in claim 2, wherein the binder-agglomerated glass granules (C) consist essentially of discrete glass flakes agglomerated in the binder resin.

4. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.

This Sheet Has Been Replaced





5. A process for preparing a fibre-reinforced polyester resin composition comprising the steps of:

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C') glass flakes, and

dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μm and 2000 μm , and a maximum particle diameter which does not exceed 5000 μm , and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

6. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) is at least one selected from a homopolymer of polybutylene terephthalate resins and polyethylene terephthalate resins or a copolymer containing polybutylene terephthalate or polyethylene terephthalate units in an amount of at least 60% by weight.

7. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) contains between 3 and 30% by weight of a polycarbonate resin.

8. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) includes glass fibres.



This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET

Date: 04 JUL 1996

18

9. A process as claimed in any preceding claim, wherein the binder for the binder-agglomerated glass granules (C) is selected from thermoplastic resins and epoxy resins.

10. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.

11. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) and the binder-agglomerated glass granules (C) are collectively present in the composition in an amount not exceeding 65% by weight based on the total composition weight.

12. A polyester resin composition prepared by a process as set forth in any preceding claim.

13. A molded article formed of a polyester resin composition prepared by a process as set forth in any of claims 1 to 11.

14. A fibre-reinforced polyester resin composition including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcement medium and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

15. A composition as claimed in claim 14, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.



* C L M S *

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACEMENT SHEET

Date 04 JUL 1996

19

16. A composition as claimed in claim 14 or claim 15, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.



* C L M S *

SPECIFICATION

POLYESTER RESIN COMPOSITION AND PROCESS
FOR THE PREPARATION THEREOF

The present invention generally relates to polyester resin compositions and to processes for their preparation. More particularly, the present invention provides low cost resin compositions exhibiting improved processability from which molded articles having reduced distortion and/or warpage can be made. Moreover, such articles can be made without adversely affecting the polyester resin's otherwise excellent inherent mechanical properties.

Thermoplastic polyester resins such as polyalkylene terephthalate resins have excellent mechanical and electrical properties, as well as desirable physical and chemical characteristics. As a result, polyester resins have been used as engineering plastics in an extensive field of end-use applications including automobiles, electrical and electronic apparatus, and the like.

Although thermoplastic polyester resins can, in and of themselves, be molded into articles, various reinforcements or additives have typically been incorporated in polyester resin compositions (depending upon the field of application) so as to obtain improved resin properties, particularly mechanical properties.

21 MAR 1998

Date

2

It is also well known that the addition of a fibrous reinforcement, such as glass or carbon fibres, imparts desirably high mechanical strength properties and increased rigidity to the thermoplastic polyester resins. However, molded articles formed of thermoplastic polyester resins containing fibrous reinforcement materials tend to distort (warp) and thus cannot be used in environments where close spatial tolerances are required.

SEE INSERTION ANNEXED HERETO (PAGE 2a)

The present invention is directed towards solving the distortion problems associated with molded articles formed of fibre-reinforced polyester resins. More particularly, the present invention is directed towards enhancing the distortion resistance of polyester resin compositions containing fibrous reinforcement and/or flaky fillers without damaging the otherwise excellent mechanical properties associated with polyester resins. In this regard, the present invention broadly resides in the use of binder-agglomerated glass granules (to be described below) instead of conventional flaky filler materials in combination with a fibrous reinforcement medium so as to attain polyester resin compositions of decreased distortion when molded.

More specifically, the present invention relates to novel fibre-reinforced polyester resin compositions including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight (based on the total composition weight) of a fibrous reinforcement medium and (C) between 3 and 65% by weight (based on the total composition weight) of binder-agglomerated glass granules.

SEE INSERTION ANNEXED HERETO (PAGE 2b)

The present invention is further characterised by methods to obtain such a composition whereby the above-noted components are mixed together and then melt-blended.

Our earlier European patent specification EP-A-0122560 discloses a thermoplastic resin composition which comprises a crystalline thermoplastic resin, a reinforcing fibre, a flaky filler and polycarbonate, having the object of providing a thermoplastic resin composition with a low degree of deformation and excellent mechanical properties. It in turn mentions that Australian patent specification No. 522577 discloses a fairly satisfactory composition comprising a thermoplastic resin, reinforcing fillers and flaky fillers. Japanese patent specification JP-A-63/201041 discloses glass flakes that have undergone a surface treatment with a binding agent and a coupling agent and which can be used as reinforcement for thermoplastic resins. It mentions that in the past glass flakes used in composites have been surface treated with silane coupling agents, titanium coupling agents or zirconia coupling agents to increase the adhesion of the resin matrix and to provide more even distribution or that they have been treated with inorganic materials, with or without subsequent surface treatment with silane coupling agents.

2b

REPLACEMENT SHEET
21 MAR 1998
Date

such granules having a major axis of between 50 and 5000 μm and being agglomerations of binder resin with pluralities of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm .

The invention thus provides a process for preparing a fibre-reinforced polyester ^{base} resin composition comprising melt-blending (A) a thermoplastic polyester resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules ~~see~~ see insertion annexed hereto,
(Page 3a)

The invention further provides a process for preparing a fibre-reinforced polyester resin composition comprising the steps of:

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C') glass flakes, having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m, and

~~and~~ dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of ^{said} glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μ m and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m, and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

The thermoplastic polyester resin (A) that may be used in the compositions of the present invention is a polyester prepared by the polycondensation of polyester forming monomers. Thus, the polyester may be prepared by polycondensing a dicarboxylic acid compound and a dihydroxy compound, a hydroxy carboxylic acid compound itself or any combination of the same. The compositions of the present invention may include homopolyesters and/or copolyesters.

3a

such granules having a major axis of between 50 and 5000 μm and being agglomerations of binder resin with pluralities of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm .

21 MAR 1998

Date :

Examples of the dicarboxylic acid compound that may be used in the preparation of the polyester resin include well-known dicarboxylic acids such as terephthalic, isophthalic, naphthalenedicarboxylic, diphenyldicarboxylic, diphenyl ether dicarboxylic, diphenylethanedicarboxylic, cyclohexanedicarboxylic, adipic and sebacic acids and alkyl, alkoxy or halogen-substituted derivatives thereof. Furthermore, these dicarboxylic acids may each be used in the polycondensation as an ester-forming derivative, such as dimethyl ester. Two or more of the dicarboxylic acid compounds may be used simultaneously, if desired.

Examples of the dihydroxy compound that may be used to prepare the polyester resin employed in the compositions of this invention include dihydroxy compounds, such as ethylene glycol, propylene glycol, butanediol, neopentyl glycol, hydroquinone, resorcinol, dihydroxyphenyl, naphthalenediol, dihydroxydiphenyl ether, cyclohexandiol, 2,2-bis(-hydroxyphenyl)propane and diethoxylated bisphenol A; polyoxyalkylene glycols and alkyl, alkoxy or halogen-substituted derivatives thereof. The dihydroxy compounds may be used either alone or as a mixture of two or more of the same.

Examples of suitable hydroxy carboxylic acids include hydroxy carboxylic acids themselves, such as hydroxybenzoic acid, hydroxynaphthoic acid and diphenyleneoxycarboxylic acid; and alkyl, alkoxy or halogen-substituted derivatives thereof. Furthermore, ester forming derivatives of these hydroxy carboxylic acids may be used. According to the present invention, one or more of the compounds may be employed during the polycondensation reaction.

Polyester resins having branched or cross-linked structures which result when a minor amount of a trifunctional monomer is used in addition to the above-noted monomer components may also be employed in the composition of the present invention. Examples of preferred trifunctional monomers include trimellitic, trimesic and pyromellitic acids, pentaerythritol and trimethylolpropane.

According to the present invention, all of the thermoplastic polyester resins prepared by the polycondensation of the above-noted monomers can be used as the component (A) either alone, or as a mixture of two or more of the same. It is preferred, however, that the polyester resin component (A) be a crystalline polyalkylene terephthalate, for example polybutylene terephthalate (PBT), polyethylene terephthalate (PET) or a copolymer containing at least 60% by weight of polybutylene terephthalate or polyethylene terephthalate units.

If necessary, the thermoplastic polyester ^{base}resin component (A) may contain up to about 30% by weight of other thermoplastic resins, such as polyamides, polycarbonates, polyolefins, fluororesins or acrylic resins. Particularly, incorporating an amorphous thermoplastic ^{resin}~~resin~~ in addition to a crystalline polyester resin as component (A) yields further reductions in distortion of molded articles. Thus, in some cases, a combination of a crystalline thermoplastic polyester resin and an amorphous resin is preferred. In this regard, the incorporation of one or more members selected from among polycarbonates, ABS resins and phenoxy resins together with a and preferably between 3 and 30% by weight of a polycarbonate resin crystalline thermoplastic polyester resin, is especially favorable.

The fibrous reinforcement medium (B) that may be used in the compositions of the present invention is not particularly limited. Thus, usable fibrous reinforcement media within the scope of the present invention includes mineral fibres, such as glass fibres, carbon fibres, graphite fibres, metal whiskers, metal fibres, silicon carbide fibres, asbestos fibres and wollastonite fibres, in addition to various organic fibres. The use of any particular fibrous reinforcement medium or combination of fibrous reinforcement media may suitably be selected in dependence upon the resin properties that may be desired for a given end-use application, for example, structural reinforcement and/or electrical conductivity properties, or improvements to the resin's frictional characteristics or flame retardancy.

The diameter and length of the fibrous reinforcement medium (B) may each be arbitrarily selected depending upon the required performance characteristics, such as mechanical properties or distortion resistance. It is generally suitable to use glass fibres having a diameter of at least $1\mu\text{m}$ and a length of at least $15\mu\text{m}$, and preferably glass fibres having a diameter of between 2 and $20\mu\text{m}$ and a length of at least $50\mu\text{m}$. If necessary, a sizing agent or surface treatment may be used with the fibrous reinforcement medium, examples of which include functional compounds such as epoxy, isocyanate, silane and titanate compounds. If employed, the sizing compounds will be present in amounts up to 10% by weight, and preferably, between 0.5 and 5% by weight (based on the weight of the fibrous reinforcement medium). These sizing compounds may each be pre-applied to the fibrous reinforcement medium, or may be added to the resin composition as an independent component simultaneously with the fibrous reinforcement medium during preparation of the composition.

The amount of the fibrous reinforcement medium that is used in the compositions of this invention is between 3 and 65% by weight, and preferably between 5 and 50% by weight, based on the total composition weight. If less than 3% by weight of the fibrous reinforcement medium is employed, then little (if any) reinforcement effect is obtained. On the other hand, if the amount of fibrous reinforcement medium exceeds 65% by weight, then difficulties are encountered during molding of the resulting composition.

The compositions of the present invention are especially characterized by containing binder-agglomerated glass granules as component (C) in addition to the above described fibrous reinforcement medium as component (B). see insertion annexed hereto, (Page 7a)

The simultaneous use of a fibrous reinforcement medium and a flaky filler material such as glass flakes or mica flakes has previously been proposed for reducing the distortion or warpage of molded articles, and in this regard, such a combination provides some measure of effectiveness. However, the result in terms of distortion and/or warpage is still unsatisfactory. Particularly, when large amounts of reinforcement media are used, productivity problems in forming molded articles are typically encountered thereby lowering productivity.

Surprisingly, it has now been found that the use of glass flakes prior to their incorporation into the polyester resin composition, that have been agglomerated with a binder, remarkably reduce distortion and warpage of molded articles. In addition, processing problems such as "flying" and "bridging" are avoided, presumably because the agglomerated glass flakes are more readily dispersible in the polyester base resin as compared with conventional (non-agglomerated) glass flakes employed previously. As a result, essentially no fractures during extrusion and kneading are encountered.

7a

Such granules have a major axis of between 50 and 5000 μm and are agglomerations of binder resin with pluralities of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm .

The term "binder-agglomerated glass granules" used herein and in the accompanying claims is intended to refer to a glass granule having a major axis of between 50 and 5000 μ m and obtained by agglomerating a number of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m with a binder (preferably a thermoplastic binder resin). If the effective granule size is too small, then the benefits sought by the present invention cannot be attained. However, if the granule size is too large, then poor dispersibility of the flakes in the matrix resin will result. According to the present invention, it is preferable that the agglomerated glass granules have a mean particle diameter of between 100 and 2000 μ m, and more preferably between 300 and 2000 μ m, and a maximum particle diameter not exceeding 5000 μ m.

The binder used to agglomerate the glass flakes is not particularly limited. Thus, virtually any binder capable of agglomerating glass flakes may be used, provided of course that it does not exert adverse effects upon the polyester matrix resin. Particular examples of the binder that may be used include addition of polymers of an olefinic monomer such as polyvinyl acetate, polyacrylate, polyvinylpyrrolidone, (acid-modified) polyethylene and (acid-modified) polypropylene and copolymers thereof; polyaddition products such as polyurethane and polyurea; polycondensation products such as unsaturated polyester, nylon and epoxy resin; ring-opening polymerization products such as nylon 6 and polyethyloxazoline; addition condensation products such as urea-formalin resin; and epoxysilane, among which thermoplastic resins and epoxy resins are especially preferred.

The binder-agglomerated glass granules can be prepared by the use of a binder as described above according to any known agglomeration technique. For example, the binder-agglomerated glass granules can be prepared by adding glass flakes to a solution of a binder in a suitable organic solvent, and then mixing the components in a fluidized state, followed by drying the resulting mixture.

The glass flakes that are agglomerated may first be subjected to a surface treatment using coupling agents for the purpose of enhancing the adhesion and/or dispersibility of the flakes in the matrix resin. The surface treatment may be carried out simultaneously with the agglomeration of the glass flakes. Alternatively, a coupling agent may be added independently during the preparation of the resin composition. The coupling agents that may be used for the above purpose include epoxy, isocyanate, silane, titanate and zirconia compounds. Of these, epoxy and silane compounds are especially preferred.

The amount of the binder-agglomerated glass granules that may be used in the present invention is between 3 and 65% by weight, and preferably between 5 and 50% by weight (based on the entire composition weight) that the total amount of the fibrous reinforcement medium and the binder-agglomerated glass granules (i.e. the total of components (B) and (C)) does not exceed 65% by weight of the entire composition. If the amount of binder-agglomerated glass granules is less than 3% by weight, then little (if any) beneficial effect is realized. On the other hand, if the amount of binder-agglomerated glass granules exceeds 65% by weight, then molding difficulties will be encountered.

The compositions of the present invention may optionally contain other additives conventionally used in thermoplastic or thermosetting resins so as to impart desired physical characteristics thereto. Examples of additives that may be used include powdery, granular and flaky inorganic fillers, (i.e. other than the binder-agglomerated glass granules noted above); stabilizers such as antioxidants, heat stabilizers, and ultraviolet absorbers; flame retardants, antistatic agents; lubricants; mold release agents; colorants such as dyes and pigments; lubricating oils; plasticizers; crystallization accelerators and nucleating agents.

The compositions of the present invention can be easily prepared using conventional processes for the preparation of a reinforcement-filled resin. More particularly, the fibrous medium (B) may be used in the form of a chopped strand or roving and if necessary, may be cut into suitable sizes or used as a filament. The necessary components according to the present invention may then be mixed together, kneaded and extruded with a conventional extruder to give a pelletized composition. In this regard, little (if any) fracturing and/or pulverization of the glass flakes ensue - a problem associated with processing of prior art compositions.

Alternatively, the fibrous reinforcement medium (B) and the binder-agglomerated glass flakes (C) may be added into a melt phase of the polyester resin in an extruder. Even in such a "two-stage" addition process, the processability of the composition is extremely improved and fracturing of the fibrous reinforcement and/or glass flakes in the extruder is reduced so as to provide a composition exhibiting excellent mechanical properties and distortion resistance.

11-

The compositions of the present invention are thus especially characterized by containing a fibrous reinforcement medium and binder-agglomerated glass granules from which molded articles can be prepared having significantly reduced distortion (warpage), as compared to compositions of the prior art which contain non-agglomerated glass flakes. In addition, the mechanical strength properties (such as tensile strength) are improved. Furthermore, the compositions of the present invention do not exhibit problems associated with the prior art, such as clogging by the glass flakes or poor extrusion properties. Thus, the compositions of the present invention are of a more consistent quality and can be made with enhanced productivity.

The compositions of the present invention may be used to form exterior trim parts and structural and functional parts and components of automobiles, electrical appliances and other devices. Particular examples of the use of the composition include automotive exterior trim parts such as fenders, bumpers, fuel lids, louvres, lamp housings and outer door handles; structural components, such as the chassis audio, video tape recorders and stereos; and working parts such as gears, cams, levers, guide stays; clutches and rollers. Furthermore, the compositions may be used in electrical or electronic components such as connectors, switches, relays, coils, bobbins, key stems or chassis; cameras, radios, various office automation machines such as facsimile, copying machines, or computers; IC cases, capacitor cases or motor parts.

EXAMPLES

The present invention will now be described in detail referring to the following non-limiting Examples.

The methods for evaluating the characteristics employed in the following Examples are as follows:

(1) Determination of distortion:

A flat test piece (80 mm x 80 mm x 2 mm) having one gate on its side was molded and placed on a surface plate so as to measure the distortion of the most significantly distorted part (i.e. that part wherein the gap between the surface plate and the test piece is largest) of the test piece.

(2) Tensile strength:

Determined according to ASTM D 638. The results in Table 1 are given in kg/cm². 1 kg/cm² is equivalent to 0.0981 MPa, i.e. approximately equal to 0.1 MPa.

(3) Processability during extrusion
(observed during pelletization of the composition):

A mixture comprising a polyester resin and glass fibre and/or glass flakes was extruded with an extruder having an inner diameter of 40 mm. The feeding state into an extruder (adhesion or clogging of glass fibre or glass flake in a hopper), the bite of the feed and the state of the extrudate (breakage of strand or surging), were visually observed and categorized using the following four criteria:

4 -----	3 -----	2 -----	1
(not observed)	adhesion or clogging in hopper	(significant)	
(good)	strand breakage or surging	(poor)	

Examples 1 to 5

Polybutylene terephthalate alone or a mixture thereof with polyethylene terephthalate or polycarbonate, glass fibres and binder agglomerated glass flakes were preliminarily mixed together in a ratio as specified in Table 1, fed into an extruder at a rate of 12 kg/h and melt-kneaded to obtain a pelletized composition. This composition was then injection molded into various test pieces. These test pieces were evaluated according to the above-mentioned criteria. The results are shown in Table 1.

Comparative Examples 1 and 2

A pelletized composition was prepared in the same manner as that of the foregoing Examples except that polybutylene terephthalate and either glass fibres or agglomerated glass flakes were used and evaluated in a similar manner to that described above. The results are shown in Table 1.

Comparative Examples 3 to 7

Polybutylene terephthalate alone or a mixture thereof with polyethylene terephthalate or polycarbonate, glass fibre and non-agglomerated glass flakes were mixed together at a ratio as specified in Table 1, fed into an extruder at a rate of 5 kg/h and melt-kneaded to obtain a pelletized composition. This composition was then injection-molded into various test pieces. The test pieces were examined according to the above-mentioned methods. The feeding rate in these Examples was first set at a rate of 12 kg/h similar to the foregoing Examples. However, the glass fibres and glass flakes clogged at the joint zone between the feeder and the extruder thereby

making extrusion difficult. Accordingly, the feed rate was lowered to one-half of that of the foregoing Examples so that the compositions could be pelletized. The results are shown in Table 1.

~~While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit scope of the appended claims.~~

21 MAR 1998

Date :

15

Table 1

	Composition					Quality (physical properties)		
	(A) thermoplastic polyester resin (kind) (t by wt.)	polycarbonate (t by wt.)	(B) fibrous reinforcement (glass fiber, t by wt.)	Agglomerated glass flake ³ (t by wt.)	Unagglomerated glass flake ⁴ (t by wt.)	distortion (mm)	tensile strength (kg/cm ²)	processability in extrusion
Zn. No.	1 PET ¹ 60	-	20	20	-	0.9	1160	4
	2 - 60	-	10	30	-	0.2	965	4
	3 - 60	-	30	10	-	2.6	1320	4
	4 PET/PET ² 45/15	-	20	20	-	0.6	1190	4
	5 PET 50	10	20	20	-	0.03	1220	4
Comp. Ex. No.	1 PET 60	-	40	-	-	5.5	1480	4
	2 - 60	-	-	40	-	0.1	765	4
	3 - 60	-	20	-	20	1.8	1140	2
	4 - 60	-	10	-	30	0.5	930	1
	5 - 60	-	30	-	10	4.5	1300	2
	6 PET/PET 45/15	-	20	-	20	1.5	1370	2
	7 PET 50	10	20	-	20	0.7	1190	2

*1 PET: polybutylene terephthalate resin is product of Polyplastics, trade name: "Duralex"

*2 PET: polyethylene terephthalate resin

*3 mean particle diameter: 600 μ m, binder: epoxy resin, coupling agent: epoxysilane*4 mean particle diameter: 600 μ m, (unagglomerated), coupling agent: epoxysilane

21 MAR 1998

Date :

~~CLAIMS~~

1. A process for preparing a fibre-reinforced polyester resin composition comprising melt-blending (A) a thermoplastic polyester resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

2. A process as claimed in claim 1, wherein the binder-agglomerated glass granules (C) include glass flakes agglomerated in a binder resin.

3. A process as claimed in claim 2, wherein the binder-agglomerated glass granules (C) consist essentially of discrete glass flakes agglomerated in the binder resin.

4. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.

5. A process for preparing a fibre-reinforced polyester resin composition comprising the steps of:

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C) glass flakes, and

dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μm and 2000 μm , and a maximum particle diameter which does not exceed 5000 μm , and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

6. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) is at least one selected from a homopolymer of polybutylene terephthalate resins and polyethylene terephthalate resins or a copolymer containing polybutylene terephthalate or polyethylene terephthalate units in an amount of at least 60% by weight.

7. A process as claimed in any preceding claim, wherein the said thermoplastic polyester resin (A) contains between 3 and 30% by weight of a polycarbonate resin.

8. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) includes glass fibres.

9. A process as claimed in any preceding claim, wherein the binder for the binder-agglomerated glass granules (C) is selected from thermoplastic resins and epoxy resins.

10. A process as claimed in any preceding claim, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.

11. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) and the binder-agglomerated glass granules (C) are collectively present in the composition in an amount not exceeding 65% by weight based on the total composition weight.

12. A polyester resin composition prepared by a process as set forth in any preceding claim.

13. A molded article formed of a polyester resin composition prepared by a process as set forth in any of claims 1 to 11.

14. A fibre-reinforced polyester resin composition including (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester resin with (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcement medium and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules.

15. A composition as claimed in claim 14, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μ m, and a maximum particle diameter which does not exceed 5000 μ m.

~~16.~~ A composition as claimed in claim 14 or claim 15, wherein the binder-agglomerated glass granules (C) include glass flakes each having a mean particle diameter of between 5 and 1000 μ m and a mean thickness of between 0.5 and 7 μ m.

CLAIMS

1. A process for preparing a fibre-reinforced polyester resin composition comprising melt-blending (A) a thermoplastic polyester base resin, (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcing medium, and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules, such granules having a major axis of between 50 and 5000 μm and being agglomerations of binder resin with pluralities of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm .

2. A process as claimed in claim 1, wherein the binder-agglomerated glass granules (C) consist of discrete glass flakes agglomerated in the binder resin.

3. A process as claimed in claim 1 or 2, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μm .

4. A process for preparing a fibre-reinforced polyester resin composition comprising the steps of :

forming a mixture of (A) a thermoplastic polyester base resin, (B) a fibrous reinforcing medium and (C) glass flakes having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm , and dispersing the said glass flakes in the said mixture, wherein

the step of dispersing the said glass flakes includes the steps of (i) introducing the glass flakes into the mixture in the form of binder-agglomerated glass granules (C) each comprised of said glass flakes and a binder, said binder-agglomerated glass granules (C) having a mean particle diameter of between 100 μm and 2000 μm , and a maximum particle diameter which does not



exceed 5000 μm , and then (ii) melt-blending the said polyester base resin (A), the said fibrous reinforcing medium (B), and the said binder-agglomerated glass granules (C) to form a molding composition.

5. A process as claimed in any preceding claim, wherein the said thermoplastic polyester base resin (A) is at least one selected from a homopolymer of polybutylene terephthalate resins and polyethylene terephthalate resins or a copolymer containing polybutylene terephthalate or polyethylene terephthalate units in an amount of at least 60% by weight.
6. A process as claimed in any preceding claim, wherein the said thermoplastic polyester base resin (A) contains between 3 and 30% by weight of a polycarbonate resin.
7. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) comprises glass fibres.
8. A process as claimed in any preceding claim, wherein the binder for the binder-agglomerated glass granules (C) is selected from thermoplastic resins and epoxy resins.
9. A process as claimed in any preceding claim, wherein the fibrous reinforcing medium (B) and the binder-agglomerated glass granules (C) are collectively present in the composition in an amount not exceeding 65% by weight based on the total composition weight.



10. A fibre-reinforced polyester resin composition comprising a mixture of (A) between 20 and 94% by weight (based on the total composition weight) of a thermoplastic polyester base resin with (B) between 3 and 65% by weight, based on the total composition weight, of a fibrous reinforcement medium and (C) between 3 and 65% by weight, based on the total composition weight, of binder-agglomerated glass granules, such granules having a major axis of between 50 and 5000 μm and being agglomerations of binder resin with pluralities of discrete glass flakes each having a mean particle diameter of between 5 and 1000 μm and a mean thickness of between 0.5 and 7 μm .

11. A composition as claimed in claim 10, wherein the binder-agglomerated glass granules (C) have a mean particle diameter of between 100 and 2000 μm .



ABSTRACT

POLYESTER RESIN COMPOSITION AND PROCESS
FOR THE PREPARATION THEREOF

Polyester compositions exhibiting decreased distortion (warpage), improved processability and productivity are produced by melt-blending a thermoplastic polyester resin with between 3 and 65% by weight of a fibrous reinforcing medium, and between 3 and 65% by weight of binder-agglomerated glass granules.