

Description

The invention relates to a polarisation-sensitive beam splitter having a polarisation-separating layer interposed between two transparent elements, said polarisation-separating layer comprising a birefringent material.

The invention also relates to a method of manufacturing a polarisation-sensitive beam splitter, in which a polarisation-separating layer is interposed between two transparent elements.

According to the state of the art a polarisation-sensitive beam splitter can be manufactured in the form of a Wollaston prism as described in McGraw-Hill Encyclopedia of Science and Technology, vol. 10, page 499 (1960). To avoid the use of birefringent prisms, a polarisation-separating layer which is interposed between two transparent elements can be used in known manner, said elements may be composed of ordinary glass or of a synthetic resin having the same single refractive index, see United States Patent Specification US 4,702,557. In said specification, the polarisation-separating birefringent layer consists of a liquid-crystalline layer having a thickness of 5 to 10 μm . One of the refractive indices of said layer must be equal to the refractive index of said elements and the other refractive index must be smaller than the refractive index of said elements.

According to the state of the art, a thin liquid-crystalline layer is applied between two substrates (the transparent elements) by means of capillary forces. Means for sealing the thin layer from the environment must be provided. Further, it is necessary to position and secure the two substrates at a fixed distance from each other. A further disadvantage of the known devices is the difficulty of providing suitable liquid-crystalline materials having the above-described refractive indices. Moreover, the temperature resistance of liquid-crystalline layers is generally small.

One of the objects of the invention is to provide a polarisation-sensitive beam splitter of a simpler construction. In this connection an object of the invention is to provide means to atune the refractive indices of the polarisation-separating layer and the transparent elements to each other in a simple manner. Another object of the invention is to provide a beam splitter which is little temperature dependent and which is also temperature resistant. Yet another object of the invention is to provide a simple and efficacious method of manufacturing a polarisation-sensitive beam splitter.

According to the invention, this object is achieved by a polarisation-sensitive beam splitter as described in the opening paragraph, which is characterized in that the polarisation-separating layer is a birefringent adhesive layer. In a preferred

embodiment of the polarisation-sensitive beam splitter according to the invention the polarisation-separating layer is a uniaxially oriented polymer layer.

According to the invention, a very temperature-resistant beam splitter is obtained when the polymer layer is formed from a cured liquid-crystalline monomer composition. Preferably, the polymer layer is formed from a polymer network having nematic groups in the molecular chains.

In order to orient the polymer layer by rubbing the surface of the transparent elements, it is efficacious for a layer of polyimide to be present between the polymer layer and each of the transparent elements.

According to the invention, the object of providing a method of manufacturing a polarisation-sensitive beam splitter is achieved by a method as described in the opening paragraph, which method is characterized in that the polarisation-separating layer is a birefringent layer manufactured from a curable synthetic resin composition which comprises liquid-crystalline monomers or oligomers, the molecules in the curable synthetic resin composition being uniaxially oriented after which the synthetic resin composition is cured.

A particularly temperature-resistant polarisation-sensitive beam splitter is obtained when the liquid-crystalline monomers or oligomers consist of compounds having two or more acrylate-ester groups.

An additional advantage of the polarisation-sensitive beam splitter according to the invention is that it can be used for a wide range of wavelengths. When the thickness of the polarisation-separating layer is sufficiently large the operation is substantially independent of the layer thickness selected. The layer thickness must be sufficiently large to bring about a complete reflection of the ordinary light ray, for example larger than 1 μm . The permissible layer thickness is limited, however, by material cost and absorption of the extraordinary light ray.

In a suitable embodiment of the method according to the invention, the orientation is obtained by rubbing each of the surfaces contacting the curable synthetic resin composition in one direction. In a preferred embodiment of such a method the surfaces to be rubbed are coated with a layer of polyimide.

In an alternative embodiment of the method according to the invention, the orientation is obtained by means of an electric or magnetic field whose field lines extend perpendicularly to the optical axis of the beam splitter.

A particular advantage of the method according to the invention is the possibility of influencing the refractive indices of the polarisation-separating layer.

er by the choice of the temperature at which the curable synthetic resin composition is cured. A free choice of said curing temperature is possible when the synthetic resin composition is made to cure by means of actinic radiation. Moreover, in this process the orientation provided is rapidly fixed. It is additionally possible to cure the synthetic resin composition in a thermal manner, for example by using a thermal initiator such as benzoyl peroxide.

In the non-prepublished Netherlands Patent Application NL 8802683 a description is given of the use of an adhesive which is composed of liquid-crystalline monomers which are optionally oriented before the curing operation in order to obtain an adhesive bond having a high positional accuracy. The adhesive compositions described therein are suitable for use in the beam splitter and the method according to the invention.

In United States Patent Specification US 4,293,435 a description is given of liquid-crystalline polymers. Said polymers do not form a network and the nematic groups are present only in side chains of the polymer molecules. The temperature resistance of such compounds is higher than that of low-molecular liquid-crystalline compounds, but once the temperature has exceeded the glass transition temperature the orientation in the material is permanently lost.

For clarity, it is to be noted that a polarisation-sensitive beam splitter can also be used in known manner as a beam adder, see also United States Patent Specification US 4,702,557.

The invention will be explained in greater detail by means of an exemplary embodiment and with reference to the accompanying drawing, in which

Fig. 1 is a suitable embodiment of a polarisation-sensitive beam splitter according to the invention,

Fig. 2 shows the structural formula of a suitable liquid-crystalline monomer, and

Fig. 3 shows the refractive indices of a cured liquid-crystalline material.

Exemplary embodiment.

Fig. 1 is a cross-sectional view of a polarisation-sensitive beam splitter 10 which is composed of two glass prisms 11 and 12. A birefringent adhesive layer 13 is interposed between said prisms, the extraordinary refractive index of said adhesive layer being equal to the refractive index of the material of the prisms. The ordinary refractive index of the birefringent adhesive layer is smaller than the extraordinary refractive index and, hence, it is also smaller than that of the prisms. According to the example, the molecules in the birefringent adhesive layer are uniaxially oriented in the direction perpendicular to the plane of the

drawing.

An incident light ray 14 is split into an extraordinary light ray 16 which, according to the exemplary embodiment, extends in a straight line, and an ordinary light ray 15 which is totally reflected at the interface with the polarisation-separating layer. The light rays 15 and 16 are polarised in mutually perpendicular directions. Unlike polarisers which are based on absorption of one of the principal light rays, in this case, no light is lost. A further important aspect is that in the polarisation-sensitive beam splitter according to the invention no heating-up takes place as a result of such absorption.

Suitable birefringent adhesive compositions are liquid-crystalline acrylates, epoxides and vinyl ethers as described in, for example, Netherlands Patent Application NL 8802683. Particularly suitable are network-forming monomer compositions such as diacrylates, according to this exemplary embodiment the compound shown in Fig. 2, by means of which a product is manufactured having a small temperature dependence.

According to the example, the thickness of layer 13 ranges between 5 and 10 μm . An orientation layer of polyimide having a thickness of 50 nm is applied to the part of the surfaces of the prisms 11 and 12 contacting the adhesive layer 13. The surfaces are rubbed with a cloth after which the liquid-crystalline monomers orient themselves in the direction of rubbing. The orientation can alternatively be attained by placing the assembly of prisms in a magnetic field having a strength of, for example, 15 kGauss, which extends perpendicularly to the optical axis of the beam splitter.

The liquid-crystalline monomers are made to cure in the oriented state by exposure to actinic radiation, in this example by UV light. For this purpose, 1 to 2 % by weight of a light-sensitive initiator such as 2,2-dimethoxy-2-phenyl-acetophenone is added to the monomer composition.

Fig. 3 shows the refractive index n of the cured adhesive layer as a function of the temperature T . n_o is the ordinary refractive index, n_e is the extraordinary refractive index. The refractive indices are plotted for a curing temperature of 90°C and a curing temperature of 140°C. The diagram shows that in particular the extraordinary refractive index, which has to be adapted to the refractive index of the material of the prisms, can be influenced by the choice of the temperature at which the monomer composition is made to cure by exposure to UV light.

Claims

1. A polarisation-sensitive beam splitter (10) having a polarisation-separating layer interposed between two transparent elements (11, 12),



er by the choice of the temperature at which the curable synthetic resin composition is cured. A free choice of said curing temperature is possible when the synthetic resin composition is made to cure by means of actinic radiation. Moreover, in this process the orientation provided is rapidly fixed. It is additionally possible to cure the synthetic resin composition in a thermal manner, for example by using a thermal initiator such as benzoyl peroxide.

In the non-published Netherlands Patent Application NL 8802683 a description is given of the use of an adhesive which is composed of liquid-crystalline monomers which are optionally oriented before the curing operation in order to obtain an adhesive bond having a high positional accuracy. The adhesive compositions described therein are suitable for use in the beam splitter and the method according to the invention.

In United States Patent Specification US 4,293,435 a description is given of liquid-crystalline polymers. Said polymers do not form a network and the nematic groups are present only in side chains of the polymer molecules. The temperature resistance of such compounds is higher than that of low-molecular liquid-crystalline compounds, but once the temperature has exceeded the glass transition temperature the orientation in the material is permanently lost.

For clarity, it is to be noted that a polarisation-sensitive beam splitter can also be used in known manner as a beam adder, see also United States Patent Specification US 4,702,557.

The invention will be explained in greater detail by means of an exemplary embodiment and with reference to the accompanying drawing, in which

Fig. 1 is a suitable embodiment of a polarisation-sensitive beam splitter according to the invention,

Fig. 2 shows the structural formula of a suitable liquid-crystalline monomer, and

Fig. 3 shows the refractive indices of a cured liquid-crystalline material.

Exemplary embodiment.

Fig. 1 is a cross-sectional view of a polarisation-sensitive beam splitter 10 which is composed of two glass prisms 11 and 12. A birefringent adhesive layer 13 is interposed between said prisms, the extraordinary refractive index of said adhesive layer being equal to the refractive index of the material of the prisms. The ordinary refractive index of the birefringent adhesive layer is smaller than the extraordinary refractive index and, hence, it is also smaller than that of the prisms. According to the example, the molecules in the birefringent adhesive layer are uniaxially oriented in the direction perpendicular to the plane of the

drawing.

An incident light ray 14 is split into an extraordinary light ray 16 which, according to the exemplary embodiment, extends in a straight line, and an ordinary light ray 15 which is totally reflected at the interface with the polarisation-separating layer. The light rays 15 and 16 are polarised in mutually perpendicular directions. Unlike polarisers which are based on absorption of one of the principal light rays, in this case, no light is lost. A further important aspect is that in the polarisation-sensitive beam splitter according to the invention no heating-up takes place as a result of such absorption.

Suitable birefringent adhesive compositions are liquid-crystalline acrylates, epoxides and vinyl ethers as described in, for example, Netherlands Patent Application NL 8802683. Particularly suitable are network-forming monomer compositions such as diacrylates, according to this exemplary embodiment the compound shown in Fig. 2, by means of which a product is manufactured having a small temperature dependence.

According to the example, the thickness of layer 13 ranges between 5 and 10 μm . An orientation layer of polyimide having a thickness of 50 nm is applied to the part of the surfaces of the prisms 11 and 12 contacting the adhesive layer 13. The surfaces are rubbed with a cloth after which the liquid-crystalline monomers orient themselves in the direction of rubbing. The orientation can alternatively be attained by placing the assembly of prisms in a magnetic field having a strength of, for example, 15 kGauss, which extends perpendicularly to the optical axis of the beam splitter.

The liquid-crystalline monomers are made to cure in the oriented state by exposure to actinic radiation, in this example by UV light. For this purpose, 1 to 2 % by weight of a light-sensitive initiator such as 2,2-dimethoxy-2-phenyl-acetophenone is added to the monomer composition.

Fig. 3 shows the refractive index n of the cured adhesive layer as a function of the temperature T . n_o is the ordinary refractive index, n_e is the extraordinary refractive index. The refractive indices are plotted for a curing temperature of 90°C and a curing temperature of 140°C. The diagram shows that in particular the extraordinary refractive index, which has to be adapted to the refractive index of the material of the prisms, can be influenced by the choice of the temperature at which the monomer composition is made to cure by exposure to UV light.

Claims

1. A polarisation-sensitive beam splitter (10) having a polarisation-separating layer interposed between two transparent elements (11, 12),



which polarisation-separating layer comprises a birefringent material, characterized in that the polarisation-separating layer is a birefringent adhesive layer (13).

2. A polarisation-sensitive beam splitter (10) as claimed in Claim 1, characterized in that the polarisation-separating layer is a uniaxially oriented polymer layer.
3. A polarisation-sensitive beam splitter (10) as claimed in Claim 2, characterized in that the polymer layer is formed from a cured liquid-crystalline monomer composition.
4. A polarisation-sensitive beam splitter (10) as claimed in Claim 3, characterized in that the polymer layer is formed from a polymeric network having nematic groups in the molecular chains.
5. A polarisation-sensitive beam splitter (10) as claimed in Claim 3 or 4, characterized in that a polyimide layer is present between the polymer layer and each of the transparent elements (11, 12).
6. A method of manufacturing a polarisation-sensitive beam splitter (10), in which a polarisation-separating layer is interposed between two transparent elements, characterized in that the polarisation-separating layer is a birefringent adhesive layer (13) manufactured from a curable synthetic resin composition which comprises liquid-crystalline monomers or oligomers, the molecules in the curable synthetic resin composition being oriented uniaxially, after which the synthetic resin composition is cured.
7. A method as claimed in Claim 6, characterized in that the liquid-crystalline monomers or oligomers consist of compounds having two or more acrylate ester groups.
8. A method as claimed in Claim 6 or 7, characterized in that the orientation is obtained by rubbing each of the surfaces contacting the curable synthetic resin composition in one direction.
9. A method as claimed in Claim 8, characterized in that the surfaces to be rubbed are coated with a layer of polyimide.
10. A method as claimed in Claim 6 or 7, characterized in that the orientation is obtained by means of an electric or magnetic field, the field

lines of which extend perpendicularly to the optical axis of the beam splitter.

11. A method as claimed in any one of the Claims 6 up to and including 10, characterized in that the synthetic resin composition is cured by means of actinic radiation.

Patentansprüche

1. Polarisationsempfindlicher Bündelspalter (10) mit einer Polarisationsstrennschicht zwischen zwei durchsichtigen Elementen (11, 12), wobei diese Schicht ein doppelbrechendes Material umfaßt, dadurch gekennzeichnet, daß die Polarisationsstrennschicht eine doppelbrechende Kleberschicht (13) ist.
2. Polarisationsempfindlicher Bündelspalter (10) nach Anspruch 1, dadurch gekennzeichnet, daß die Polarisationsstrennschicht eine uniaxial orientierte Polymerschicht ist.
3. Polarisationsempfindlicher Bündelspalter (10) nach Anspruch 2, dadurch gekennzeichnet, daß die Polymerschicht aus einer ausgehärteten flüssigkristallinen Monomierzusammensetzung gebildet ist.
4. Polarisationsempfindlicher Bündelspalter (10) nach Anspruch 3, dadurch gekennzeichnet, daß die Polymerschicht aus einem Polymer Netzwerk mit nematischen Gruppen in den Molekülketten gebildet ist.
5. Polarisationsempfindlicher Bündelspalter (10) nach Anspruch 3 oder 4, dadurch gekennzeichnet, daß sich zwischen der Polymerschicht und jedem der durchsichtigen Elemente (11, 12) eine Polyimidschicht befindet.
6. Verfahren zum Herstellen eines polarisationsempfindlichen Bündelspalters (10), wobei zwischen zwei durchsichtigen Elementen eine Polarisationsstrennschicht vorgesehen wird, dadurch gekennzeichnet, daß die Polarisationsstrennschicht eine doppelbrechende Kleberschicht (13) ist, die aus einer härtbaren Kunststoffzusammensetzung hergestellt wird, die flüssigkristalline Monomere oder Oligomere umfaßt, wobei die Moleküle in der härtbaren Kunststoffzusammensetzung uniaxial orientiert werden, wonach die Kunststoffzusammensetzung ausgehärtet wird.
7. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die flüssigkristallinen Monomere oder Oligomere aus Verbindungen mit zwei



oder mehr Acrylatestergruppen bestehen.

8. Verfahren nach Anspruch 6 oder 7, dadurch gekennzeichnet, daß die Orientierung dadurch erhalten wird, daß jede der Oberflächen, welche die härtbare Kunststoffzusammensetzung berühren, in nur einer Richtung gerieben werden.
9. Verfahren nach Anspruch 8, dadurch gekennzeichnet, daß die zu reibenden Oberflächen mit einer Polyimidschicht verkleidet werden.
10. Verfahren nach Anspruch 6 oder 7, dadurch gekennzeichnet, daß die Orientierung mittels eines elektrischen oder magnetischen Feldes erhalten wird, dessen Feldlinien sich senkrecht zu der optischen Achse des Bündelsplatters erstrecken.
11. Verfahren nach einem der Ansprüche 6 bis 10, dadurch gekennzeichnet, daß die Kunststoffzusammensetzung mittels aktinischer Strahlung ausgehärtet wird.

Revendications

1. Diviseur de faisceau (10) sensible à la polarisation présentant une couche de séparation de polarisation interposée entre deux éléments transparents (11, 12), ladite couche de séparation de polarisation comportant un matériau biréfringent, caractérisé en ce que la couche de séparation de polarisation est une couche adhésive biréfringente (13).
2. Diviseur de faisceau (10) sensible à la polarisation selon la revendication 1, caractérisé en ce que la couche de séparation de polarisation est une couche polymère orientée uniaxialement.
3. Diviseur de faisceau (10) sensible à la polarisation selon la revendication 2, caractérisé en ce que la couche polymère est formée à partir d'une composition monomère durcie à cristaux liquides.
4. Diviseur de faisceau (10) sensible à la polarisation selon la revendication 3, caractérisé en ce que la couche polymère est formée à partir d'un réseau polymère comportant des groupes nématiques dans les chaînes moléculaires.
5. Diviseur de faisceau (10) sensible à la polarisation selon la revendication 3 ou 4, caractérisé en ce qu'une couche en polyimide est présente entre la couche polymère et chacun

des éléments transparents (11, 12).

6. Procédé de fabrication d'un diviseur de faisceau (10) sensible à la polarisation (10), dans lequel une couche de séparation de polarisation est interposée entre deux éléments transparents, caractérisé en ce que la couche de séparation de polarisation est une couche adhésive biréfringente (13) fabriquée à partir d'une composition de résine synthétique durcissable comportant des monomères ou des oligomères à cristaux liquides, les molécules dans la composition de résine synthétique durcissable étant orientées uniaxialement après quoi la composition de résine synthétique est durcie.
7. Procédé selon la revendication 6, caractérisé en ce que les monomères ou les oligomères à cristaux liquides consistent en composés présentant deux ou plusieurs groupes d'acrylatesters.
8. Procédé selon la revendication 6 ou 7, caractérisé en ce que l'orientation s'obtient par frottement unidirectionnel de chacune des surfaces en contact avec la composition de résine synthétique durcissable.
9. Procédé selon la revendication 8, caractérisé en ce que les surfaces à frotter sont revêtues d'une couche en polyimide.
10. Procédé selon la revendication 6 ou 7, caractérisé en ce que l'orientation s'obtient au moyen d'un champ électrique ou magnétique dont les lignes de champ s'étendent perpendiculairement à l'axe optique du diviseur de faisceau.
11. Procédé selon l'une quelconque des revendications 6 à 10, caractérisé en ce que la composition de résine synthétique est durcie par rayonnement actinique.