

5

10

15

20

25

30

1-10-1945

unsaturation in the lubricating oil, to remove heteroatom-containing impurities and color bodies. In mineral oils, the removal of impurities and color bodies is of particular significance but for mineral oils which have been subjected to hydrocracking or catalytic dewaxing. For both mineral and synthetic stocks, the saturation of lube boiling range olefins is a major objective.

The polyolefins comprise one class of synthetic hydrocarbon lubricants which has achieved importance in the lubricating oil market. These materials are typically produced by the polymerization (the term oligomerization is often used for the lower molecular weight products which are used as low viscosity basestocks) of alpha olefins typically ranging from 1-octene to 1-dodecene, with 1-decene being a preferred material, although polymers of lower olefins such as ethylene and propylene may also be used, including copolymers of ethylene with higher olefins, as described in U.S. Patent No. 4,956,122 and the patents referred to there. The poly alpha-olefin (PAO) products may be obtained with a wide range of viscosities varying from highly mobile fluids of 3 mm²/s to higher molecular weight, viscous materials which may be used as VI improvers for the lower viscosity PAO stocks. The PAO's are conventionally produced by the polymerization of the olefin feed in the presence of a catalyst such as aluminum trichloride, or boron trifluoride or trifluoride complexes. Processes for the production of PAO lubricants in this way are disclosed, for example, in U.S. Patent Nos. 3,382,291, 4,172,855, 3,780,128, 3,149,178, 3,742,082, and 4,956,122. The PAO

This Sheet Has Been Replaced



lubricants are also discussed in Lubrication Fundamentals, J. G. Wills, Marcel Dekker Inc., New York, 1980 ISBN 0-8247-6976-7, especially Pages 77 to 81. Subsequent to the polymerization, the lubricant range products are hydrogenated in order to reduce the residual unsaturation. In the course of this reaction, the bromine number of the lubricant is reduced from a typical value of 10 or higher to a value of not more than 1 or even lower.

5
10
15
20
25
30
A novel type of PAO lubricant has recently been disclosed as having exceptional and advantageous properties. These materials are the HVI-PAO materials which are disclosed in U.S. Patent Nos. 4,827,064 and 4,827,073. These materials are produced by the oligomerization of one olefins, especially 1-decene, using a reduced Group VI metal oxide catalyst, preferably a reduced chromium oxide catalyst. The HVI-PAO products may be derivatized by reaction with aromatics, as disclosed EP 377305 and higher molecular weight versions prepared by the use of lower oligomerization temperatures, as disclosed in U.S. Patent No. 5,012,020, to which reference is made for a disclosure of the higher molecular weight products. Although the oligomerization process using the reduced metal oxide catalysts produces a material of characteristic structure, residual unsaturation remains in the oligomer product and, like the conventional PAO oligomers, it is subjected to hydrogenation in order to improve its stability as a lubricant. The hydrogenation is carried out in the same manner as with the conventional PAO-type materials.

The catalysts used for hydrogenating lubricants, whether of mineral oil or synthetic origin, require a



strong hydrogenation function provided by the metal component and large pore diameters in the porous support material in order to minimize the diffusion resistance of the bulky lubricant molecules. For reactions with bulky molecules, the optimum ratio of catalytic pore diameter to molecule size is 1.5:1. Table 1 below shows the optimum pore sizes required for normal alkanes in the C-7 to C-25 range. The table shows that for alkanes in this range, the chain-length varies from 9.9 to 37.6 Å so that active hydrogenation catalysts for these materials should have a major amount of their pore volume with pore openings in the range of 1.5 to 5.6 nm (15 to 56 Å), and preferably with a major amount of this in the range 3.8 to 5.6 nm (38 to 56 Å).



Table 1
Optimum Pore Size

	<u>Carbon Number</u>	<u>Alkane Length, nm (1)</u>	<u>Optimum Pore Diameter, nm (2)</u>
5	C ₇	0.99	1.5
	C ₈	1.15	1.7
	C ₁₀	1.45	2.2
	C ₁₂	1.76	2.6
	C ₁₇	2.53	3.8
10	C ₁₉	2.84	4.3
	C ₂₁	3.15	4.7
	C ₂₃	3.46	5.2
	C ₂₅	3.76	5.6

(1) Based on bond lengths of 0.154 and 0.111 nm for C-C and C-H bond lengths, respectively.

(2) Based on an optimum ratio of catalyst pore to molecule size ratio of 1.5.

Conventional amorphous support materials such as alumina, silica and silica-alumina, typically have a pore size distribution with most of the pores larger than 5 nm and most of these are larger than 10nm. Although these large pores enable the bulky lubricant molecules to traverse the molecular structure of the catalyst freely with little diffusion resistance, the reduced surface area associated with the larger pore sizes diminishes the area which is available for the hydrogenation reactions. It would therefore be desirable to utilize a hydrogenation catalyst which possesses a significant amount of its pores in the range of 1.5 to 6 nm (15 to 60 Å), close to the optimum ratio



for the lower molecular weight materials making up the bulk of many synthetic lubricants as well as the lower viscosity mineral oils.

5 We have now found that another class of catalytic materials - the mesoporous crystalline materials - which have high pore volume, high surface area and controlled pore openings of at least 13 Å, is particularly suitable for the hydrogenation of lubricant hydrocarbons, especially synthetic PAO-type materials.

10 According to the presednt invention, therefore, the hydrogenation process utilizes a hydrogenation catalyst which comprises a hydrogenation function in the form of a metal on a support material which
15 comprises a mesoporous siliceous material with a novel and unique structure and pore geometry described below. These materials are inorganic, porous, non-layered crystalline phase materials which, in their calcined forms exhibit an X-ray diffraction pattern with at
20 least one peak at a d-spacing greater than 1.8 nm (18 Angstrom Units (Å)). They also have a benzene adsorption capacity greater than 15 grams benzene per 100 grams of the material at 6.7 kPa (50 torr) and 25°C. In a preferred form, the support material is
25 characterized by a substantially uniform hexagonal honeycomb microstructure with uniform pores having a cell diameter greater than 1.3 nm (13 Å) and typically in the range of 2 to 10 nm (20 to 100 Å). Most prominent among these materials is a new crystalline
30 material identified as MCM-41 which is usually synthesized as a metallosilicate with Brønsted acid sites by incorporating a tetrahedrally coordinated trivalent element such as Al, Ga, B, or Fe within the



silicate framework. The preferred forms of these materials are the aluminosilicates although other metallosilicates may also be utilized.

5 MCM-41 is characterized by a microstructure with a uniform, hexagonal arrangement of pores with diameters of at least 1.3 nm (13 Å). After calcination, it exhibits an X-ray diffraction pattern with at least one d-spacing greater than 18 Å and a hexagonal electron
10 diffraction pattern that can be indexed with a d_{100} value greater than 18 Å which corresponds to the d-spacing of the peak in the X-ray diffraction pattern.

A preferred catalyst for the present purpose is an alumina bound crystalline material which has a significant pore volume with pore diameters greater
15 than 20 nm (200 Å). The large diameter pores provide channels for bulky PAO oligomers to transport freely with diminished diffusion resistance to the smaller particles of the crystalline material which provide a large surface area for the hydrogenation reaction. The
20 preferred crystalline materials for use in the present process have pore diameters greater than 1.5 nm (15 Å) and the preferred pore diameters are in the range of 1.5 to 6 nm (15 to 60 Å).

The single figure of the accompanying drawings is a graphical representation of testing results reported
25 in the Examples below.

In the present process, lubricant range hydrocarbons are hydrogenated or hydrotreated or hydrotreated in the presence of a hydrogenation
30 catalyst which comprises a mesoporous crystalline material, preferably with a binder which possesses a significant pore volume having pore diameters greater than 20 nm (200 Å). The process may be carried out



with mineral oil lubricants or synthetic hydrocarbon lubricants, of which the PAO materials are preferred, both conventional type PAO's prepared using Friedel-Crafts type catalysts as well as the HVI-PAO materials produced using a reduced Group VIB metal oxide catalyst.

The mineral oil lubricants may generally be characterized as having a minimum boiling point of at least 650°F (345°C) and usually they will be neutral i.e., distillate, stocks with an end point of not more than 1050°F (565°C), although residual lube stocks such as bright stock may also be treated by the same catalytic process. Mineral oil stocks of this kind are typically prepared by the conventional refining process involving atmospheric and vacuum distillation of a crude of suitable composition, followed by removal of undesirable aromatic components by solvent extraction using a solvent such as phenol, furfural or N,N-dimethylformamide (DMF). Dewaxing to the desired product pour point may be carried out using either solvent dewaxing or catalytic dewaxing techniques and it is particularly preferred that a hydrogenative treatment according to the present invention should follow any catalytic dewaxing treatment in order to saturate lube boiling range olefins which may be produced during the catalytic dewaxing process.

The present process is, however, particularly applicable to the hydrogenative treatment of synthetic lubricating oils, especially the poly alpha-olefins (PAO) including the HVI-PAO type materials. These types of lubricants may be produced by the polymerization or oligomerization procedures described above using Friedel-Crafts type catalysts such as



aluminum trichloride, boron trifluoride or boron trifluoride complexes, e.g., with water, lower alkanols or esters in the conventional manner. The HVI-PAO type oligomers may be prepared by the methods described in U.S. Patent Nos. 4,827,064 and 4,827,073, using a reduced Group VIB metal oxide catalyst, normally chromium on silica. The HVI-PAO materials include the higher molecular weight versions prepared by the use of lower oligomerization temperatures, as disclosed in U.S. Patent No. 5,012,020, to which reference is made for a full description of these materials and their preparation. Derivatives of the PAO lubricants may be prepared by reaction with aromatics as disclosed, for example, in EP 377305, referred to above. The HVI-PAO materials are characterized by a branch ratio below 0.19 which results from the use of the unique reduced metal oxide catalyst during the oligomerization process.

The lubricant materials are subjected to the hydrogenative treatment in the presence of a catalyst which comprises a metal component for hydrogenation together with the mesoporous crystalline material and, optionally, a binder.

The hydrogenation reaction is carried out under conventional conditions with temperatures from 93° to 371°C (200° to 700°F), and preferably in the range of 149° to 260°C (300° to 500°F). Hydrogen pressure may vary up to 17340 kPa abs. (2,500 psig) but normally will be from 790 to 3550 kPa abs. (100 to 500 psig). Hydrogen circulation rates are typically in the range 178 to 1424 n.l.l.⁻¹ (1,000 to 8,000 scf/bbl) and once through circulation is preferred in order to maximize the purity of the hydrogen. Space velocities are



typically in the range of 0.5 to 10 LHSV, usually from 1 to 3 LHSV. The products of the hydrogenation reaction have a low degree of unsaturation consistent with the hydrogenative treatment and in most cases the bromine number of the product will be less than 2 and is preferably less than 1.


The catalytic material used in the present invention includes a novel synthetic composition of matter comprising an ultra-large pore size crystalline phase as a support for the metal component of the catalyst. This material is an inorganic, porous, non-layered crystalline phase material which can be characterized (in its calcined form) by an X-ray diffraction pattern with at least one peak at a d-spacing greater than 1.8 nm (18 Å) with a relative intensity of 100 and a benzene sorption capacity of greater than 15 grams of benzene per 100 grams of the material at 6.7 kPa (50 torr) and 25°C.

The preferred form of the crystalline material is an inorganic, porous, non-layered material having a hexagonal arrangement of uniformly-sized pores with a maximum perpendicular cross-section pore dimension of at least 1.3 nm (13 Å), and typically within the range of from 1.3 to 20 nm (13 Å to 200 Å). A preferred form of this hexagonal crystalline composition, identified as MCM-41, with the characteristic structure of hexagonally-arranged, uniformly-sized pores of at least 1.3 nm (13 Å) diameter, exhibits a hexagonal electron diffraction pattern that can be indexed with a d_{100} value greater than 1.8 nm (18 Å) which corresponds to at least one peak in the X-ray diffraction pattern.

This Sheet Has Been Replaced




The inorganic, non-layered mesoporous crystalline material used as a component of the catalyst has the following composition:



5 wherein W is a divalent element, such as a divalent first row transition metal, e.g. manganese, cobalt and iron, and/or magnesium, preferably cobalt; X is a trivalent element, such as aluminum, boron, iron and/or gallium, preferably aluminum; Y is a tetravalent
10 element such as silicon and/or germanium, preferably silicon; Z is a pentavalent element, such as phosphorus; M is one or more ions, such as, for example, ammonium, Group IA, IIA and VIIB ions, usually hydrogen, sodium and/or fluoride ions; n is the charge
15 of the composition excluding M expressed as oxides; q is the weighted molar average valence of M; n/q is the number of moles or mole fraction of M; a, b, c, and d are mole fractions of W, X, Y and Z, respectively; h is a number of from 1 to 2.5; and (a+b+c+d) = 1.

20 A preferred embodiment of the above crystalline material is when (a+b+c) is greater than d, and h = 2. A further embodiment is when a and d = 0, and h = 2. The preferred materials for use in making the present catalysts are the aluminosilicates although other
25 metallosilicates may also be used.

In the as-synthesized form, the support material has a composition, on an anhydrous basis, expressed empirically as follows:



30 where R is the total organic material not included in M as an ion, and r is the coefficient for R, i.e. the number of moles or mole fraction of R.



The M and R components are associated with the material as a result of their presence during crystallization, and are easily removed or, in the case of M, replaced by post-crystallization methods described below.

To the extent desired, the original M, e.g. sodium or chloride, ions of the as-synthesized material of this invention can be replaced in accordance with conventional ion-exchange techniques. Preferred replacing ions include metal ions, hydrogen ions, hydrogen precursor, e.g. ammonium, ions and mixtures of these ions. Particularly preferred ions are those which provide the desired metal functionality in the final catalyst. These include hydrogen, rare earth metals and metals of Groups VIIA (e.g. Mn), VIIIA (e.g. Ni), IB (e.g. Cu), IVB (e.g. Sn) of the Periodic Table of the Elements and mixtures of these ions.

The crystalline (i.e. having sufficient order to provide a diffraction pattern such as, for example, by X-ray, electron or neutron diffraction, following calcination with at least one peak) mesoporous material may be characterized by its structure, which includes extremely large pore windows as well as by its high sorption capacity. The term "mesoporous" is used here to indicate crystals having uniform pores within the range of from 1.3 to 20 nm (13 Å to 200 Å). The mesoporous materials have uniform pores within the range of from 1.3 to 20 nm (13 Å to 200 Å), more usually from 1.5 to 10 nm (15 Å to 100 Å). Since these pores are significantly larger than those of other crystalline materials, it is appropriate to refer to them as ultra-large pore size materials. For the purposes of this application, a working definition of



"porous" is a material that adsorbs at least 1 gram of a small molecule, such as Ar, N₂, n-hexane or cyclohexane, per 100 grams of the solid.

5 The catalytic material can be distinguished from
other porous inorganic solids by the regularity of its
large open pores, whose pore size more nearly resembles
that of amorphous or paracrystalline materials, but
whose regular arrangement and uniformity of size (pore
size distribution within a single phase of, for
10 example, $\pm 25\%$, usually $\pm 15\%$ or less of the average
pore size of that phase) resemble more those of
crystalline framework materials such as zeolites. The
preferred materials have a hexagonal arrangement of
large open channels that can be synthesized with open
15 internal diameters from 1.3 to 20 nm (13 Å to 200 Å).
The term "hexagonal" is intended to encompass not only
materials that exhibit mathematically perfect hexagonal
symmetry within the limits of experimental measurement,
but also those with significant observable deviations
20 from that ideal state. A working definition as applied
to the microstructure of the present invention would be
that most channels in the material would be surrounded
by six nearest neighbor channels at roughly the same
distance. Defects and imperfections will cause
25 significant numbers of channels to violate this
criterion to varying degrees, depending on the quality
of the material's preparation. Samples which exhibit
as much as $\pm 25\%$ random deviation from the average
repeat distance between adjacent channels still clearly
30 give recognizable images of the present ultra-large
pore materials. Comparable variations are also
observed in the d_{100} values from the electron
diffraction patterns.

This Sheet Has Been Replaced



The most regular preparations of the support material give an X-ray diffraction pattern with a few distinct maxima in the extreme low angle region. The positions of these peaks approximately fit the
5 positions of the $hk0$ reflections from a hexagonal lattice. The X-ray diffraction pattern, however, is not always a sufficient indicator of the presence of these materials, as the degree of regularity in the microstructure and the extent of repetition of the
10 structure within individual particles affect the number of peaks that will be observed. Indeed, preparations with only one distinct peak in the low angle region of the X-ray diffraction pattern have been found to contain substantial amounts of the material in them.
15 Other techniques to illustrate the microstructure of this material are transmission electron microscopy and electron diffraction. Properly oriented specimens of the material show a hexagonal arrangement of large channels and the corresponding electron diffraction
20 pattern gives an approximately hexagonal arrangement of diffraction maxima. The d_{100} spacing of the electron diffraction patterns is the distance between adjacent spots on the $hk0$ projection of the hexagonal lattice and is related to the repeat distance a_0 between
25 channels observed in the electron micrographs through the formula $d_{100} = a_0/\sqrt{3}$. This d_{100} spacing observed in the electron diffraction patterns corresponds to the d-spacing of a low angle peak in the X-ray diffraction pattern of the material. The most highly ordered
30 preparations of the material obtained so far have 20-40 distinct spots observable in the electron diffraction patterns. These patterns can be indexed with the



hexagonal hko subset of unique reflections of 100, 110, 200, 210, etc., and their symmetry-related reflections.

In its calcined form, the crystalline material may be further characterized by an X-ray diffraction pattern with at least one peak at a position greater than 1.8 nm (18 Angstrom Units) d-spacing ($4.909^\circ 2\theta$ for Cu K-alpha radiation) which corresponds to the d_{100} value of the electron diffraction pattern of the material, and an equilibrium benzene adsorption capacity of greater than 15 grams benzene/100 grams crystal at 6.7 kPa (50 torr) and 25°C (basis: crystal material having been treated in an attempt to insure no pore blockage by incidental contaminants, if necessary).

The equilibrium benzene adsorption capacity characteristic of this material is measured on the basis of no pore blockage by incidental contaminants. For instance, the sorption test will be conducted on the crystalline material phase having any pore blockage contaminants and water removed by ordinary methods. Water may be removed by dehydration techniques, e.g. thermal treatment. Pore blocking inorganic amorphous materials, e.g. silica, and organics may be removed by contact with acid or base or other chemical agents such that the detrital material will be removed without detrimental effect on the crystal.

More particularly, the calcined crystalline non-layered material may be characterized by an X-ray diffraction pattern with at least two peaks at positions greater than 1.0 nm (10 Å) d-spacing ($8.842^\circ 2\theta$ for Cu K-alpha radiation), at least one of which is at a position greater than 1.8 nm (18 Å) d-spacing, and no peaks at positions less than 1.0 nm (10 Å) d-spacing



with relative intensity greater than 20% of the strongest peak. Still more particularly, the X-ray diffraction pattern of the calcined material of this invention will have no peaks at positions less than 1.0 nm (10 Å) d-spacing with relative intensity greater than 10% of the strongest peak. In any event, at least one peak in the X-ray diffraction pattern will have a d-spacing that corresponds to the d_{100} value of the electron diffraction pattern of the material.

The calcined inorganic, non-layered crystalline material may also be characterized as having a pore size of 1.3 nm (13 Å) or greater as measured by physisorption measurements, described below. Pore size is considered a maximum perpendicular cross-section pore dimension of the crystal.

X-ray diffraction data were collected on a Scintag PAD X automated diffraction system employing theta-theta geometry, Cu K-alpha radiation, and an energy dispersive X-ray detector. Use of the energy dispersive X-ray detector eliminated the need for incident or diffracted beam monochromators. Both the incident and diffracted X-ray beams were collimated by double slit incident and diffracted collimation systems. The slit sizes used, starting from the X-ray tube source, were 0.5, 1.0, 0.3 and 0.2 mm, respectively. Different slit systems may produce differing intensities for the peaks. The materials of the present invention that have the largest pore sizes may require more highly collimated incident X-ray beams in order to resolve the low angle peak from the transmitted incident X-ray beam.

The diffraction data were recorded by step-scanning at 0.04 degrees of 2θ , where θ is the



5 Bragg angle, and a counting time of 10 seconds for each
step. The interplanar spacings, d 's, were calculated
in Å (A), and the relative intensities of the lines,
 I/I_0 , where I_0 is one-hundredth of the intensity of the
strongest line, above background, were derived with the
10 use of a profile fitting routine. The intensities were
uncorrected for Lorentz and polarization effects. The
relative intensities are given in terms of the symbols
vs = very strong (75-100), s = strong (50-74), m =
15 medium (25-49) and w = weak (0-24). The diffraction
data listed as single lines may consist of multiple
overlapping lines which under certain conditions, such
as very high experimental resolution or
crystallographic changes, may appear as resolved or
15 partially resolved lines. Typically, crystallographic
changes can include minor changes in unit cell
parameters and/or a change in crystal symmetry, without
a substantial change in structure. These minor
effects, including changes in relative intensities, can
20 also occur as a result of differences in cation
content, framework composition, nature and degree of
pore filling, thermal and/or hydrothermal history, and
peak width/shape variations due to particle size/shape
effects, structural disorder or other factors known to
25 those skilled in the art of X-ray diffraction.

The equilibrium benzene adsorption capacity is
determined by contacting the material of the invention,
after dehydration or calcination at, for example, 540°C
for at least one hour and other treatment, if
30 necessary, in an attempt to remove any pore blocking
contaminants, at 25°C and 6.7 kPa (50 torr) benzene
until equilibrium is reached. The weight of benzene
sorbed is then determined as described below.



The ammonium form of the catalytic material may be readily converted to the hydrogen form by thermal treatment (calcination). This thermal treatment is generally performed by heating one of these forms at a temperature of at least 400°C for at least 1 minute and generally not longer than 20 hours, preferably from 1 to 10 hours. While subatmospheric pressure can be employed for the thermal treatment, atmospheric pressure is desired for reasons of convenience, such as in air, nitrogen, ammonia, etc. The thermal treatment can be performed at a temperature up to 750°C. The thermally treated product is particularly useful in the catalysis of certain hydrocarbon conversion reactions and it is preferred that the material should be in this form for use in the present catalysts.

The crystalline material can be prepared by one of several methods, each with particular limitations.

A first method involves a reaction mixture having an X_2O_3/YO_2 mole ratio of from 0 to 0.5, but an Al_2O_3/SiO_2 mole ratio of from 0 to 0.01, a crystallization temperature of from 25° to 250°C, preferably from 50° to 175°C, and an organic directing agent, hereinafter more particularly described, or, preferably a combination of that organic directing agent plus an additional organic directing agent, described below. This first method comprises preparing a reaction mixture containing sources of, for example, alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or a combination of oxides selected from the group consisting of divalent element W, e.g. cobalt, trivalent element X, e.g. aluminum, tetravalent element Y, e.g. silicon, and pentavalent element Z, e.g. phosphorus, an organic (R)



directing agent, described below, and a solvent or solvent mixture, such as, for example, C₁-C₆ alcohols, C₁-C₆ diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:

	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
	X ₂ O ₃ /YO ₂	0 to 0.5	0.001 to 0.5
	Al ₂ O ₃ /SiO ₂	0 to 0.01	0.001 to 0.01
	X ₂ O ₃ /(YO ₂ +Z ₂ O ₅)	0.1 to 100	0.1 to 20
10	X ₂ O ₃ /(YO ₂ +WO+Z ₂ O ₅)	0.1 to 100	0.1 to 20
	Solvent/ (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	1 to 1500	5 to 1000
	OH ⁻ /YO ₂	0 to 10	0 to 5
	(M ₂ /e ^O +R ₂ /f ^O)/ (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0.01 to 20	0.05 to 5
15	M ₂ /e ^O / (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0 to 10	0 to 5
	R ₂ /f ^O / (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0.01 to 2.0	0.03 to 1.0

20 where e and f are the weighted average valences of M and R, respectively.

25 In this first method, when no Z and/or W oxides are added to the reaction mixture, the pH is important and must be maintained at from 9 to 14. When Z and/or W oxides are present in the reaction mixture, the pH is not narrowly important for synthesis of the present crystalline material. In this, as well as the following methods for synthesis of the present material the R₂/f^O/(YO₂+WO+Z₂O₅+X₂O₃) ratio is important. When
30 this ratio is less than 0.01 or greater than 2.0,

This Sheet Has Been Replaced



impurity products tend to be synthesized at the expense of the desired crystalline material.

5 A second method for synthesis of the crystalline material involves a reaction mixture having an X_2O_3/YO_2 mole ratio of from 0 to 0.5, a crystallization temperature of from 25° to 250°C, preferably from 50° to 175°C, and two separate organic directing agents, i.e. the organic and additional organic directing agents, described below. This second method comprises
10 preparing a reaction mixture containing sources of, for example, alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or a combination of oxides selected from the group consisting of divalent element W, e.g. cobalt,
15 trivalent element X, e.g. aluminum, tetravalent element Y, e.g. silicon, and pentavalent element Z, e.g. phosphorus, a combination of organic directing agent and additional organic directing agent (R), each described below, and a solvent or solvent mixture, such
20 as, for example, C_1-C_6 alcohols, C_1-C_6 diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:



	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
	X_2O_3/YO_2	0 to 0.5	0.001 to 0.5
	$X_2O_3/(YO_2+Z_2O_5)$	0.1 to 100	0.1 to 20
	$X_2O_3/(YO_2+WO+Z_2O_5)$	0.1 to 100	0.1 to 20
5	Solvent/ $(YO_2+WO+Z_2O_5+X_2O_3)$	1 to 1500	5 to 1000
	OH^-/YO_2	0 to 10	0 to 5
	$(M_2/e^{O+R_2/f^{O}})/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0.01 to 20	0.05 to 5
10	$M_2/e^{O}/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0 to 10	0 to 5
	$R_2/f^{O}/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0.1 to 2.0	0.12 to 1.0

15 where e and f are the weighted average valences of M and R, respectively.

In this second method, when no Z and/or W oxides are added to the reaction mixture, the pH is important and must be maintained at from 9 to 14. When Z and/or W oxides are present in the reaction mixture, the precise value of the pH is not important for crystallization.

25 A third method for synthesis of the crystalline material is where X comprises aluminum and Y comprises silicon, the crystallization temperature must be from 25° to 175°C, preferably from 50° to 150°C, and an organic directing agent, described below, or, preferably a combination of that organic directing agent plus an additional organic agent, described below, is used. This third method comprises preparing
30 a reaction mixture containing sources of, for example,



alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or more sources of aluminum and/or silicon, an organic (R) directing agent, hereinafter more particularly described, and a solvent or solvent mixture, such as, for example C₁-C₆ alcohols, C₁-C₆ diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:

	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
10	Al ₂ O ₃ /SiO ₂	0 to 0.5	0.001 to 0.5
	Solvent/SiO ₂	1 to 1500	5 to 1000
	OH ⁻ /SiO ₂	0 to 10	0 to 5
	(M ₂ /e ^O +R ₂ /f ^O)/ (SiO ₂ +Al ₂ O ₃)	0.01 to 20	0.05 to 5
15	M ₂ /e ^O / (SiO ₂ +Al ₂ O ₃)	0 to 5	0 to 3
	R ₂ /f ^O / (SiO ₂ +Al ₂ O ₃)	0.01 to 2	0.03 to 1

where e and f are the weighted average valences of M and R, respectively.

In this third method, the pH is important and must be maintained at from 9 to 14. This method involves the following steps:

(1) Mix the organic (R) directing agent with the solvent or solvent mixture such that the mole ratio of solvent/R₂/f^O is within the range of from 50 to 800, preferably from 50 to 500. This mixture constitutes the "primary template" for the synthesis method.

(2) To the primary template-mixture of step (1) add the sources of oxides, e.g. silica and/or alumina



such that the ratio of $R_{2/f}O/(SiO_2+Al_2O_3)$ is within the range of from 0.01 to 2.0.

5 (3) Agitate the mixture resulting from step (2) at a temperature of from 20° to 40°C, preferably for from 5 minutes to 3 hours.

(4) Allow the mixture to stand with or without agitation, preferably at a temperature of from 20° to 100°C, and preferably for from 10 minutes to 24 hours.

10 (5) Crystallize the product from step (4) at a temperature of from 50° to 175°C, preferably for from 1 hour to 72 hours. Crystallization temperatures higher in the given ranges are most preferred.

15 A fourth method for the present synthesis involves the reaction mixture used for the third method, but the following specific procedure with tetraethylorthosilicate the source of silicon oxide:

20 (1) Mix the organic (R) directing agent with the solvent or solvent mixture such that the mole ratio of solvent/ $R_{2/f}O$ is within the range of from 50 to 800, preferably from 50 to 500. This mixture constitutes the "primary template" for the synthesis method.

25 (2) Mix the primary template mixture of step (1) with tetraethylorthosilicate and a source of aluminum oxide, if desired, such that the $R_{2/f}O/SiO_2$ mole ratio is in the range of from 0.5 to 2.0.

30 (3) Agitate the mixture resulting from step (2) for from 10 minutes to 6 hours, preferably from 30 minutes to 2 hours, at a temperature of from 0° to 25°C, and a pH of less than 12. This step permits hydrolysis/ polymerization to take place and the resultant mixture will appear cloudy.

(4) Crystallize the product from step (3) at a temperature of from 25° to 150°C, preferably from 95°



to 110°C, for from 4 to 72 hours, preferably from 16 to 48 hours.

5 In each of the above methods, batch
crystallization of the crystalline material can be
carried out under either static or agitated, e.g.
10 stirred, conditions in a suitable reactor vessel, such
as for example, polypropylene jars or teflon lined or
stainless steel autoclaves. Crystallization
may also be conducted continuously in suitable
15 equipment. The total useful range of temperatures for
crystallization is noted above for each method for a
time sufficient for crystallization to occur at the
temperature used, e.g. from 5 minutes to 14 days. The
crystals are then separated from the liquid and
20 recovered. Following the synthesis, the crystalline
material should be subjected to treatment to remove
part or all of any organic constituent.

When a source of silicon is used in the synthesis
method, it is preferred to use at least in part an
20 organic silicate, such as, for example, a quaternary
ammonium silicate. Non-limiting examples of such a
silicate include tetramethylammonium silicate and
tetraethylorthosilicate.

By adjusting conditions of the synthesis reaction
25 for each method, like temperature, pH and time of
reaction, etc., within the above limits, various
embodiments of the present non-layered crystalline
material with a desired average pore size may be
prepared. In particular, changing the pH, the
30 temperature or the reaction time may promote formation
of product crystals with different average pore size.




Non-limiting examples of various combinations of W, X, Y and Z contemplated for the first and second synthesis methods include:

	W	X	Y	Z
5	--	Al	Si	--
	--	Al	--	P
	--	Al	Si	P
	Co	Al	--	P
	Co	Al	Si	P
10	--	--	Si	--

including the combinations of W being Mg, or an element selected from the divalent first row transition metals, e.g. Mn, Co and Fe; X being B, Ga or Fe; and Y being Ge.

15 An organic directing agent for use in each of the above methods for synthesizing the present material from the respective reaction mixtures is an ammonium or phosphonium ion of the formula $R_1R_2R_3R_4Q^+$, i.e.:



25 ny where Q is nitrogen or phosphorus and wherein at least one of R_1 , R_2 , R_3 and R_4 is aryl or alkyl of from 6 to 36 carbon atoms, e.g. $-C_6H_{13}$, $-C_{10}H_{21}$, $-C_{16}H_{33}$ and $-C_{18}H_{37}$, or combinations thereof, the remainder of R_1 , R_2 , R_3 and R_4 being selected from hydrogen, alkyl of
 30 from 1 to 5 carbon atoms and combinations of these. The compound from which the above ammonium or



phosphonium ion is derived may be, for example, the hydroxide, halide, silicate, or mixtures of these.

5 In the first and third methods above it is preferred to have an additional organic directing agent and in the second method it is required to have a combination of the above organic directing agent and an additional organic directing agent. That additional organic directing agent is the ammonium or phosphonium ion of the above directing agent formula wherein R_1 ,
10 R_2 , R_3 and R_4 together or separately are selected from the group consisting of hydrogen and alkyl of 1 to 5 carbon atoms and combinations thereof. Any such combination of organic directing agents go to make up "R" and will be in molar ratio of 100/1 to 0.01/1,
15 first above listed organic directing agent/additional organic directing agent.

The particular effectiveness of the required directing agent, when compared with other such agents known to direct synthesis of one or more other crystal
20 structures, is believed due to its ability to function as a template in the above reaction mixture in the nucleation and growth of the desired ultra-large pore crystals with the limitations discussed above. Non-limiting examples of these directing agents include
25 cetyltrimethylammonium, cetyltrimethylphosphonium, benzyltrimethylammonium, cetylpyridinium, myristyltrimethylammonium, decyltrimethylammonium, dodecyltrimethylammonium and dimethyldidodecylammonium.

30 The reaction mixture components can be supplied by more than one source. The reaction mixture can be prepared either batchwise or continuously. Crystal size and crystallization time of the new crystalline



material will vary with the nature of the reaction mixture employed and the crystallization conditions.

5 The crystals prepared by the synthesis procedure can be shaped into a wide variety of particle sizes. Generally speaking, the particles can be in the form of a powder, a granule, or a molded product, such as an extrudate having particle size sufficient to pass through a 2 mesh (Tyler) screen and be retained on a 400 mesh (Tyler) screen. In cases where the catalyst is molded, such as by extrusion, the crystals can be extruded before drying or partially dried and then extruded.

10 The size of the pores in the present mesoporous catalytic materials is large enough that the spatioselectivity with respect to transition state species in reactions such as cracking is minimized (Chen et al., "Shape Selective Catalysis in Industrial Applications", 36 CHEMICAL INDUSTRIES, pgs. 41-61 (1989) to which reference is made for a discussion of the factors affecting shape selectivity). Diffusional limitations are also minimized as a result of the very large pores.

20 The crystals of the mesoporous support material will be composited with a matrix material which is resistant to the temperatures and other conditions employed in the hydrogenation process to form the finished catalyst. Such materials include active and inactive materials and synthetic or naturally occurring zeolites as well as inorganic materials such as clays and/or oxides such as alumina, silica or silica-alumina. The latter may be either naturally occurring or in the form of gelatinous precipitates or gels including mixtures of silica and metal oxides.



Use of a material in conjunction with the zeolite, i.e., combined therewith or present during its synthesis, which itself is catalytically active may change the conversion and/or selectivity of the catalyst. Inactive materials suitably serve as diluents to control the amount of conversion so that alkylation products can be obtained economically and orderly without employing other means for controlling the rate of reaction. These materials may be incorporated into naturally occurring clays, e.g., bentonite and kaolin, to improve the crush strength of the catalyst under commercial operating conditions and function as binders or matrices for the catalyst. The mesoporous material is usually composited with the matrix in amounts from 80:20 to 20:80 by weight, typically from 80:20 to 50:50 mesoporous material:matrix. Compositing may be done by conventional means including mulling the materials together followed by extrusion of pelletizing into the desired finished catalyst particles.

The preferred catalysts for the present purpose have a significant pore volume with pore diameters greater than 20 nm (200 Å). The large diameter pores provide channels for bulky PAO oligomers to transport freely with diminished diffusion resistance to the smaller particles of the crystalline material which provide a large surface area for the hydrogenation reaction. A number of commercially available alumina binders conform to this requirement and may be used. The pore size distributions of three are set out below.

Consistent with the requirement to permit the lube molecules to obtain ready, diffusion-free access to the crystalline material which acts as the support for the

This Sheet Has Been Replaced



metal component which performs the essential hydrogenation function, the binder should have a pore size and distribution which is adequate to permit the feed components to enter the interior pore structure of the catalyst where the desired hydrogenation reactions take place at the metal sites on the crystalline material. To this extent, the binder will normally have a minimum pore size of 5.0 nm (50 Å), i.e with no less than 5% of the pores having a pore size less than 5.0 nm (50 Å) pore size, with the majority of the pores having a pore size in the range of 5.0 to 50 nm (50-400 Å) (no more than 5% having a pore size above 40 nm (400 Å)), preferably with no more than 30% having pore sizes in the range of 20 to 40 nm (200-400 Å).

Metal Component

Catalyst Metal Component

The hydrogenation catalyst includes a metal as the hydrogenation- dehydrogenation component. The hydrogenation-dehydrogenation component is provided by a metal or combination of metals. Noble metals of Group VIIIA, especially palladium, platinum, or base metals of Groups IVA, VIA and VIIIA, especially chromium, molybdenum, tungsten, cobalt and nickel, may be used. The combination of at least one Group VIA metal such as tungsten with at least one Group VIIA metal such as nickel is particularly preferred for many applications, for example, combinations such as nickel-molybdenum, cobalt-nickel, nickel-tungsten, cobalt-nickel-molybdenum and nickel-tungsten-titanium. For certain applications, where sulfur and other contaminants such as phosphorus are in low



concentrations in the feedstock, e.g. <10 ppm, palladium or platinum is preferred.

5 The content of the metal component will vary according to its catalytic activity. Thus, the highly active noble metals may be used in smaller amounts than the less active base metals. For example, 1 wt % or less palladium or platinum will be effective and in a preferred base metal combination, 7 wt % nickel and 2.1 to 21 wt % tungsten, expressed as metal. The present support materials are, however, notable in that they are capable of including a greater proportion of metal than previous support materials because of their extraordinarily large surface area. The metal component may exceed 30% in a monolayer. The hydrogenation component can be exchanged onto the support material, impregnated into it or physically admixed with it. If the metal is to be impregnated into or exchanged onto the mesoporous support, it may be done, for example, by treating the zeolite with a palladium or platinum metal-containing ion. Suitable platinum compounds include chloroplatinic acid, platinous chloride and various compounds containing the platinum ammine complex. The metal compounds may be either compounds in which the metal is present in the cation of the compound and compounds in which it is present in the anion of the compound. Both types of compounds can be used. Palladium or platinum compounds in which the metal is in the form of a cation of cationic complex, e.g., $\text{Pd}(\text{NH}_3)_4\text{Cl}_2$ or $\text{Pt}(\text{NH}_3)_4\text{Cl}_2$ are particularly useful, as are anionic complexes such as the vanadate and metatungstate ions. Cationic forms of other metals are also very useful since they may be

10

15

20

25

30



exchanged onto the crystalline material or impregnated into it.

Examples

5 Examples 1 to 19 below illustrate the preparation of the mesoporous crystalline materials used to prepare the catalysts. In these examples, the sorption data for water, cyclohexane, benzene and/or n-hexane, they are Equilibrium Adsorption values determined as follows:

10 A weighed sample of the adsorbent, after calcination at 540°C for at least 1 hour and other treatment, if necessary, to remove any pore blocking contaminants, is contacted with the desired pure adsorbate vapor in an adsorption chamber. The increase
15 in weight of the adsorbent is calculated as the adsorption capacity of the sample in terms of grams/100 grams adsorbent based on adsorbent weight after calcination at 540°C. The present composition exhibits an equilibrium benzene adsorption capacity at 6.7 kPa
20 (50 Torr) and 25°C of greater than 15 grams/100 grams, particularly greater than 17.5 g/100 g/ and more particularly greater than 20 g/100 g.

25 A preferred way to do this is to contact the desired pure adsorbate vapor in an adsorption chamber evacuated to less than 1 mm at conditions of 1.6 kPa (12 Torr) of water vapor, 5.3 kPa (40 Torr) of n-hexane or cyclohexane vapor, or 6.7 kPa (50 Torr) of benzene
30 vapor, at 25°C. The pressure is kept constant (within ± 0.5 mm) by addition of adsorbate vapor controlled by a manostat during the adsorption period. As adsorbate is adsorbed by the new crystal, the decrease in



pressure causes the manostat to open a valve which admits more adsorbate vapor to the chamber to restore the above control pressures. Sorption is complete when the pressure change is not sufficient to activate the manostat.

Another way of doing this for benzene adsorption data is on a suitable thermogravimetric analysis system, such as a computer-controlled 990/951 duPont TGA system. The adsorbent sample is dehydrated (physically sorbed water removed) by heating at, for example, 350° or 500°C to constant weight in flowing helium. If the sample is in as-synthesized form, e.g. containing organic directing agents, it is calcined at 540°C in air and held to constant weight instead of the previously described 350° or 500°C treatment. Benzene adsorption isotherms are measured at 25°C by blending a benzene saturated helium gas stream with a pure helium gas stream in the proper proportions to obtain the desired benzene partial pressure. The value of the adsorption at 6.7 kPa (50 Torr) of benzene is taken from a plot of the adsorption isotherm.

In the examples, percentages are by weight unless otherwise indicated.

Example 1

One hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution, prepared by contacting a 29 wt % N,N,N- trimethyl-1-hexadecanaminium chloride solution with a hydroxide-for-halide exchange resin, was combined with 100 grams of an aqueous solution of tetramethylammonium (TMA) silicate (10% silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt



5 % bound water of hydration and having an ultimate
particle size of 0.02 micron, was added. The resulting
mixture was placed in a polypropylene bottle, which was
placed in a steam box at 95°C overnight. The mixture
had a composition in terms of moles per mole Al_2O_3 :

2.7 moles Na_2O
392 moles SiO_2
35.7 moles $(\text{CTMA})_2\text{O}$
61.7 moles $(\text{TMA})_2\text{O}$
10 6231 moles H_2O

The resulting solid product was recovered by
filtration and dried in air at ambient temperature.
The product was then calcined at 540°C for 1 hour in
nitrogen, followed by 6 hours in air.

15 The calcined product proved to have a surface area
of 475 m^2/g and the following equilibrium adsorption
capacities in grams/100 grams:

	H_2O	8.3
	Cyclohexane	22.9
20	n-Hexane	18.2
	Benzene	21.5

25 The product of this example may be characterized
by X-ray diffraction as including a very strong
relative intensity line at 37.8 ± 2.0 Å d-spacing, and
weak lines at 21.6 ± 1.0 and 19.2 ± 1.0 Å.
Transmission electron microscopy (TEM) produced images
of a hexagonal arrangement of uniform pores and
hexagonal electron diffraction pattern with a d_{100}
value of 39 Å.



Example 2

One hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 100 grams of an aqueous solution of tetramethylammonium (TMA) hydroxide (25%) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of 0.02 micron, was added. The resulting mixture was placed in a static autoclave at 150°C overnight. The mixture had a composition in terms of moles per mole Al_2O_3 :

2.7 moles Na_2O
291 moles SiO_2
35.7 moles $(\text{CTMA})_2\text{O}$
102 moles $(\text{TMA})_2\text{O}$
6120 moles H_2O

The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

The calcined product proved to have a surface area of 993 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

H_2O	7.1
Cyclohexane	47.2
n-Hexane	36.2
Benzene	49.5



The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 39.3 ± 2.0 Å d-spacing, and weak lines at 22.2 ± 1.0 and 19.4 ± 1.0 Å. TEM indicated that the product contained the ultra-large pore material.

A portion of the above product was then contacted with 100% steam at 1450°F for two hours. The surface area of the steamed material was measured to be 440 m²/g, indicating that 45% was retained following severe steaming.

Another portion of the calcined product of this example was contacted with 100% steam at 677°C (1250°F) for two hours. The surface area of this material was measured to be 718 m²/g, indicating that 72% was retained after steaming at these conditions.

Example 3

Water, cetyltrimethylammonium hydroxide solution prepared as in Example 1, aluminum sulfate, HiSil and an aqueous solution of tetrapropylammonium (TPA) bromide (35%) were combined to produce a mixture having a composition in terms of moles per mole Al₂O₃:

0.65 moles Na₂O
65 moles SiO₂
8.8 moles (CTMA)₂O
1.22 moles (TPA)₂O
1336 moles H₂O

The resulting mixture was placed in a polypropylene bottle, which was kept in a steam box at

This Sheet Has Been Replaced



95°C for 192 hours. The sample was then cooled to room temperature and combined with CTMA hydroxide solution prepared as in Example 1 and TMA hydroxide (25% by weight) in the weight ratio of 3 parts mixture, 1 part CTMA hydroxide and 2 parts TMA hydroxide. The combined mixture was then placed in a polypropylene bottle and kept in a steam box at 95°C overnight. The combined mixture had a composition in terms of moles per mole Al_2O_3 :

10	0.65 moles Na_2O
	65 moles SiO_2
	15 moles $(\text{CTMA})_2\text{O}$
	1.22 moles $(\text{TPA})_2\text{O}$
	35.6 moles $(\text{TMA})_2\text{O}$
15	2927 moles H_2O

The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

20 The calcined product proved to have a surface area of 1085 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

	H_2O	11.5
	Cyclohexane	> 50
25	n-Hexane	39.8
	Benzene	62

The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 38.2



± 2.0 Å d-spacing, and weak lines at 22.2 ± 1.0 and 19.4 ± 1.0 Å. TEM indicated the product contained the ultra-large pore material.

Example 4

5 Two hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 2 grams of Catapal alumina (alpha-alumina monohydrate, 74% alumina) and 100 grams of an aqueous solution of tetramethylammonium (TMA) silicate (10%
10 silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of 0.02 micron, was added. The resulting mixture was placed in a static autoclave
15 at 150°C for 48 hours. The mixture had a composition in terms of moles per mole Al_2O_3 :

0.23 moles Na_2O
33.2 moles SiO_2
6.1 moles $(\text{CTMA})_2\text{O}$
20 5.2 moles $(\text{TMA})_2\text{O}$
780 moles H_2O

25 The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

 The calcined product proved to have a surface area of $1043 \text{ m}^2/\text{g}$ and the following equilibrium adsorption capacities in grams/100 grams:



H ₂ O	6.3
Cyclohexane	> 50
n-Hexane	49.1
Benzene	66.7

5 The X-ray diffraction pattern of the calcined
product may be characterized as including a very strong
relative intensity line at 40.8 ± 2.0 Å d-spacing, and
weak lines at 23.1 ± 1.0 and 20.1 ± 1.0 Å. TEM
10 indicated that the product contained the ultra-large
pore material.

Example 5

Two-hundred sixty grams of water was combined with
77 grams of phosphoric acid (85%), 46 grams of Catapal
alumina (74% alumina), and 24 grams of pyrrolidine
15 (Pyr) with stirring. This first mixture was placed in
a stirred autoclave and heated to 150°C for six days.
The material was filtered, washed and air-dried. Fifty
grams of this product was slurried with 200 grams of
water and 200 grams of cetyltrimethylammonium hydroxide
20 solution prepared as in Example 1. Four hundred grams
of an aqueous solution of tetraethylammonium silicate
(10% silica) was then added to form a second mixture
which was placed in a polypropylene bottle and kept in
a steam box at 95°C overnight. The first mixture had a
25 composition in terms of moles per mole Al₂O₃:

1.0 moles P₂O₅
0.51 moles (Pyr)₂O
47.2 moles H₂O



The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

5 The calcined product proved to have a surface area of 707 m²/g and the following equilibrium adsorption capacities in grams/100 grams:

	H ₂ O	33.2
	Cyclohexane	19.7
10	n-Hexane	20.1
	Benzene	23.3

15 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 25.4 ± 1.5 Å d-spacing. TEM indicated the product contained the present ultra-large pore material.

Example 6

20 A solution of 1.35 grams of NaAlO₂ (43.5% Al₂O₃, 30% Na₂O) dissolved in 45.2 grams of water was mixed with 17.3 grams of NaOH, 125.3 grams of colloidal silica (40%, Ludox HS-40) and 42.6 grams of 40% aqueous solution of tetraethylammonium (TEA) hydroxide. After stirring overnight, the mixture was heated for 7 days in a steam box (95°C). Following filtration, 151 grams of this solution was mixed with 31 grams of cetyltri-
25 methylammonium hydroxide solution prepared as in Example 1 and stored in the steam box at 95°C for 13 days. The mixture had the following relative molar composition:



5 0.25 moles Al_2O_3
 10 moles Na_2O
 36 moles SiO_2
 0.95 moles $(\text{CTMA})_2\text{O}$
 2.5 moles $(\text{TEA})_2\text{O}$
 445 moles H_2O

10 The resulting solid product was recovered by
 filtration and washed with water and ethanol. The
 product was then calcined at 540°C for 1 hour in
 nitrogen, followed by 6 hours in air.

 The calcined product composition included 0.14 wt
 % Na, 68.5 wt % SiO_2 and 5.1 wt % Al_2O_3 , and proved to
 have a benzene equilibrium adsorption capacity of 58.6
 grams/100 grams.

15 The X-ray diffraction pattern of the calcined
 product may be characterized as including a very strong
 relative intensity line at $31.4 \pm 1.5 \text{ \AA}$ d-spacing. TEM
 indicated that the product contained the present
 ultra-large pore material.

20 Example 7

 A mixture of 300 grams of cetyltrimethylammonium
 (CTMA) hydroxide solution prepared as in Example 1 and
 41 grams of colloidal silica (40%, Ludox HS-40) was
 heated in a 600 cc autoclave at 150°C for 48 hours with
25 stirring at 200 rpm. The mixture has a composition in
 terms of moles per mole SiO_2 :

 0.5 mole $(\text{CTMA})_2\text{O}$
 46.5 moles H_2O



The resulting solid product was recovered by filtration, washed with water, then calcined at 540°C for 1 hour in nitrogen, followed by 10 hours in air.

5 The calcined product composition included less than 0.01 wt % Na, 98.7 wt % SiO₂ and 0.01 wt % Al₂O₃, and proved to have a surface area of 896 m²/g. The calcined product had the following equilibrium adsorption capacities in grams/100 grams:

	H ₂ O	8.4
10	Cyclohexane	49.8
	n-Hexane	42.3
	Benzene	55.7

15 The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 40.0 ± 2.0 Å d-spacing and a weak line at 21.2 ± 1.0 Å. TEM indicated that the product of this example contained at least three separate phases, one of which was the ultra-large pore material.

20 Example 8

A mixture of 150 grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 and 21 grams of colloidal silica (40%, Ludox HS-40) with an initial pH of 12.64 was heated in a 300 cc autoclave at 25 150°C for 48 hours with stirring at 200 rpm. The mixture had a composition in terms of moles per mole SiO₂:

0.5 mole (CTMA)₂O
46.5 moles H₂O



The resulting solid product was recovered by filtration, washed with water, then calcined at 540°C for 6 hours in air.

5 The calcined product composition was measured to include 0.01 wt % Na, 93.2 wt % SiO₂ and 0.016 wt % Al₂O₃, and proved to have a surface area of 992 m²/g and the following equilibrium adsorption capacities in grams/100 grams:

10	H ₂ O	4.6
	Cyclohexane	> 50
	n-Hexane	> 50
	Benzene	62.7

15 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 43.6 ± 2.0 Å d-spacing and weak lines at 25.1 ± 1.5 and 21.7 ± 1.0 Å. TEM indicated that the product contained the ultra-large pore material.

Example 9

20 Sodium aluminate (4.15g) was added slowly into a solution containing 16g of myristyltrimethylammonium bromide (C₁₄TMABr) in 100g of water. Tetramethyl-
25 ammonium silicate (100g-10% SiO₂), HiSil (25g) and tetramethylammonium hydroxide (14.2g-25% solution) were then added to the mixture. The mixture was
crystallized in an autoclave at 120°C with stirring for 24 hours.

The product was filtered, washed and air dried. Elemental analysis showed the product contained 53.3 wt
30 % SiO₂, 3.2 wt % Al₂O₃, 15.0 wt % C, 1.88 wt % N, 0.11



wt % Na and 53.5 wt % ash at 1000°C. The X-ray diffraction pattern of the material after calcination at 540°C for 1 hour in N₂ and 6 hours in air includes a very strong relative intensity line at 35.3 ± 2.0 Å d-spacing and weak lines at 20.4 ± 1.0 and 17.7 ± 1.0 Å d-spacing. TEM indicated that the product contained the ultra-large pore material.

The washed product, having been exchanged with 1N ammonium nitrate solution at room temperature, then calcined, proved to have a surface area of 827 m²/g and the following equilibrium adsorption capacities in g/100g anhydrous sorbent:

	H ₂ O	30.8
	Cyclohexane	33.0
15	n-Hexane	27.9
	Benzene	40.7

Example 10

Sodium aluminate (8.3g) was added slowly into a solution containing 184g of dodecyltrimethylammonium hydroxide (C₁₂TMAOH, 50%) solution diluted with 480g of water. UltraSil (50g) and an aqueous solution of tetramethylammonium silicate (200g-10% SiO₂) and tetramethylammonium hydroxide (26.38g-25% solution) were then added to the mixture. The mixture was crystallized in an autoclave at 100°C with stirring for 24 hours.

The product was filtered, washed and air dried. After calcination at 540°C for 1 hour in N₂ and 6 hours in air, the X-ray diffraction pattern includes a very strong relative intensity line at 30.4 ± 1.5 Å d-spacing and weak lines at 17.7 ± 1.0 and 15.3 ± 1.0



Å d-spacing. TEM indicated that the product contained the ultra-large pore material.

5 The washed product, having been exchanged with 1N ammonium nitrate solution at room temperature, then calcined, proved to have a surface area of 1078 m²/g and the following equilibrium adsorption capacities in g/100g anhydrous sorbent:

	H ₂ O	32.6
	Cyclohexane	38.1
10	n-Hexane	33.3
	Benzene	42.9

Example 11

15 A solution of 4.9 grams of NaAlO₂ (43.5 % Al₂O₃, 30% NaO₂) in 37.5 grams of water was mixed with 46.3 cc of 40% aqueous tetraethylammonium hydroxide solution and 96 grams of colloidal silica (40%, Ludox HS-40). The gel was stirred vigorously for 0.5 hour, mixed with an equal volume (150 ml) of cetyltrimethylammonium hydroxide solution prepared as in Example 1 and reacted
20 at 100°C for 168 hours. The mixture had the following composition in terms of moles per mole Al₂O₃:

	1.1 moles Na ₂ O
	30.6 moles SiO ₂
	3.0 moles (TEA) ₂ O
25	3.25 moles (CTMA) ₂ O
	609 moles H ₂ O

The resulting solid product was recovered by filtration, washed with water then calcined at 540°C for 16 hours in air. The calcined product proved to



have a surface area of $1352 \text{ m}^2/\text{g}$ and the following equilibrium adsorption capacities in grams/100 grams:

5	H_2O	23.6
	Cyclohexane	>50
	n-Hexane	49
	Benzene	67.5

10 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at $38.5 \pm 2.0 \text{ \AA}$ d-spacing and a weak line at $20.3 \pm 1.0 \text{ \AA}$. TEM indicated that the product contained the ultra-large pore material.

Example 12

15 Two hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 4.15 grams of sodium aluminate and 100 grams of aqueous tetramethylammonium (TMA) silicate solution (10% silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of $0.02 \text{ }\mu\text{m}$, was added. The resulting mixture was placed in a static autoclave at 150°C for 24 hours. The mixture had a composition in terms of moles per mole Al_2O_3 :

25	1.25 moles Na_2O
	27.8 moles SiO_2
	5.1 moles $(\text{CTMA})_2\text{O}$
	4.40 moles $(\text{TMA})_2\text{O}$
	650 moles H_2O



5 The resulting solid product was recovered by
filtration and dried in air at ambient temperature.
The product was then calcined at 540°C for 1 hour in
nitrogen, followed by 6 hours in air. TEM indicated
that this product contained the ultra-large pore
material. The X-ray diffraction pattern of
the calcined product of this example can be
characterized as including a very strong relative
intensity line at 44.2 ± 2.0 Å d-spacing and weak lines
10 at 25.2 ± 1.5 and 22.0 ± 1.0 Å.

The calcined product proved to have a surface area
of 932 m²/g and the following equilibrium adsorption
capacities in grams/100 grams:

	H ₂ O	39.3
15	Cyclohexane	46.6
	n-Hexane	37.5
	Benzene	50

Example 13

20 Two hundred grams of cetyltrimethylammonium (CTMA)
hydroxide solution prepared as in Example 1 was
combined with 4.15 grams of sodium aluminate and 100
grams of aqueous tetramethylammonium (TMA) silicate
solution (10% silica) with stirring. Twenty-five grams
of HiSil, a precipitated hydrated silica containing 6
25 wt % free water and 4.5 wt % bound water of hydration
and having an ultimate particle size of 0.02 micron,
was added. The resulting mixture was placed in a steam
box at 100°C for 48 hours. The mixture had a
composition in terms of moles per mole Al₂O₃:



5 1.25 moles Na_2O
 27.8 moles SiO_2
 5.1 moles $(\text{CTMA})_2\text{O}$
 4.4 moles $(\text{TMA})_2\text{O}$
 650 moles H_2O

10 The resulting solid product was recovered by
 filtration and dried in air at ambient temperature.
 The product was then calcined at 540°C for 1 hour in
 nitrogen, followed by 6 hours in air. The calcined
 product proved to have the following equilibrium
 adsorption capacities in grams/100 grams:

15	H_2O	35.2
	Cyclohexane	> 50
	n-Hexane	40.8
	Benzene	53.5

20 The X-ray diffraction pattern of the calcined
 product may be characterized as including a very strong
 relative intensity line at $39.1 \pm 2.0 \text{ \AA}$ d-spacing and
 weak lines at 22.4 ± 1.0 and $19.4 \pm 1.0 \text{ \AA}$. TEM
 indicated that this product contained the ultra-large
 pore material.

Example 14

25 A mixture of 125 grams of 29% CTMA chloride
 aqueous solution, 200 grams of water, 3 grams of sodium
 aluminate (in 50 grams H_2O), 65 grams of Ultrasil,
 amorphous precipitated silica available from PQ
 Corporation, and 21 grams NaOH (in 50 grams H_2O) was
 stirred thoroughly and crystallized at 150°C for 168



hours. The reaction mixture had the following relative molar composition in terms of moles per mole silica:

5 0.10 moles (CTMA)₂O
 21.89 moles H₂O
 0.036 moles NaAlO₂
 0.53 moles NaOH

10 The solid product was isolated by filtration, washed with water, dried for 16 hours at room temperature and calcined at 540°C for 10 hours in air. The calcined product proved to have a surface area of 840 m²/g, and the following equilibrium adsorption capacities in grams/100 grams:

15 H₂O 15.2
 Cyclohexane 42.0
 n-Hexane 26.5
 Benzene 62

20 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 40.5 ± 2.0 Å d-spacing. TEM indicated that the product contained the ultra-large pore material.

Example 15

25 To make the primary template mixture for this example, 240 grams of water was added to a 92 gram solution of 50% dodecyltrimethylammonium hydroxide, 36% isopropyl alcohol and 14% water such that the mole ratio of Solvent/R_{2/f}O was 155. The mole ratio of H₂O/R_{2/f}O in this mixture was 149 and the IPA/R_{2/f}O



5 mole ratio was 6. To the primary template mixture was added 4.15 grams of sodium aluminate, 25 grams of HiSil, 100 grams of aqueous tetramethylammonium silicate solution (10% SiO_2) and 13.2 grams of 25% aqueous tetramethylammonium hydroxide solution. The mole ratio of $\text{R}_2/\text{f}^{\text{O}}/(\text{SiO}_2 + \text{Al}_2\text{O}_3)$ was 0.28 for the mixture.

10 This mixture was stirred at 25°C for 1 hour. The resulting mixture was then placed in an autoclave at 100°C and stirred at 100 rpm for 24 hours. The mixture in the autoclave had the following relative molar composition in terms of moles per mole SiO_2 :

15 0.05 mole Na_2O
0.036 mole Al_2O_3
0.18 mole $(\text{C}_{12}\text{TMA})_2\text{O}$
0.12 mole $(\text{TMA})_2\text{O}$
36.0 moles H_2O
1.0 mole IPA

20 The resulting solid product was recovered by filtration, washed with water and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

25 The calcined product proved to have a surface area of 1223 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

30

H_2O	25.5
Cyclohexane	41.1
n-Hexane	35.1
Benzene	51



The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 30.8 ± 1.5 Å d-spacing and weak lines at 17.9 ± 1.0 and 15.5 ± 1.0 Å. TEM indicated this product to contain the ultra-large pore material.

Example 16

A 50.75 gram quantity of decyltrimethylammonium hydroxide (prepared by contacting a ca. 29 wt % solution of decyltrimethylammonium bromide with a hydroxide-for-halide exchange resin) was combined with 8.75 grams of tetraethylorthosilicate. The mixture was stirred for 1 hour and then transferred to a polypropylene jar which was then placed in a steambox for 24 hours. The mixture had a composition in terms of moles per mole SiO_2 :

0.81 mole $(\text{C}_{10}\text{TMA})_2\text{O}$
47.6 moles H_2O

The resulting solid product was filtered and washed several times with warm ($60^\circ\text{--}70^\circ\text{C}$) distilled water and with acetone. The final product was calcined to 538°C in N_2 /air mixture and then held in air for 8 hours. The calcined product proved to have a surface area of $915 \text{ m}^2/\text{g}$ and an equilibrium benzene adsorption capacity of 35 grams/100 grams. Argon physisorption data indicated an argon uptake of 0.34 cc/gram, and a pore size of 1.5 nm (15 Å).

The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 27.5



± 1.5 Å d-spacing and weak lines at 15.8 ± 1.0 and 13.7 ± 1.0 Å. TEM indicated that the product of this example contained the ultra-large pore material.

Example 17

5 To eighty grams of cetyltrimethylammonium
hydroxide (CTMAOH) solution prepared as in Example 1
was added 1.65 grams of NaAlO_2 . The mixture was
stirred at room temperature until the NaAlO_2 was
dissolved. To this solution was added 40 grams of
10 aqueous tetramethylammonium (TMA) silicate solution (10
wt % SiO_2), 10 grams of HiSil, 200 grams of water and
70 grams of 1,3,5-trimethylbenzene (mesitylene). The
resulting mixture was stirred at room temperature for
several minutes. The gel was then loaded into a 600 ml
15 autoclave and heated at 105°C for sixty-eight hours
with stirring at 150 rpm. The mixture had a
composition in terms of moles per mole Al_2O_3 :

20 1.25 moles Na_2O
 27.8 moles SiO_2
 5.1 moles $(\text{CTMA})_2\text{O}$
 2.24 moles $(\text{TMA})_2\text{O}$
 2256 moles H_2O
 80.53 moles 1,3,5-trimethylbenzene

25 The resulting product was filtered and washed
several times with warm ($60^\circ\text{--}70^\circ\text{C}$) distilled water and
with acetone. The final product was calcined to 538°C
in N_2 /air mixture and then held in air for 10 hours.
The calcined product proved to have an equilibrium
benzene adsorption capacity of >25 grams/100 grams.



The X-ray diffraction pattern of the calcined product may be characterized as including a broad, very strong relative intensity line at 102 Å d-spacing, but accurate positions of lines in the extreme low angle region of the X-ray diffraction pattern are very difficult to determine with conventional X-ray diffractometers. Furthermore, finer collimating slits were required to resolve a peak at this low 2-theta angle. The slits used in this example, starting at the X-ray tube, were 0.1, 0.3, 0.5 and 0.2 mm, respectively. TEM indicated that the product of this example contained several materials with different d_{100} values as observed in their electron diffraction patterns. These materials were found to possess d_{100} values between 8.5 nm (85 Å) d-spacing and 12 nm (120 Å) d-spacing.

Example 18

To eighty grams of cetyltrimethylammonium hydroxide (CTMAOH) solution prepared as in Example 1 was added 1.65 grams of NaAlO_2 . The mixture was stirred at room temperature until the NaAlO_2 was dissolved. To this solution was added 40 grams of aqueous tetramethylammonium (TMA) silicate solution (10 wt % SiO_2), 10 grams of HiSil, 200 grams of water and 120 grams of 1,3,5-trimethylbenzene (mesitylene). The resulting mixture was stirred at room temperature for several minutes. The gel was then loaded into a 600 ml autoclave and heated at 105°C for ninety hours with stirring at 150 rpm. The mixture had a composition in terms of moles per mole Al_2O_3 :



5 1.25 moles Na_2O
 27.8 moles SiO_2
 5.1 moles $(\text{CTMA})_2\text{O}$
 2.24 moles $(\text{TMA})_2\text{O}$
 2256 moles H_2O
 132.7 moles 1,3,5-trimethylbenzene

10 The resulting product was filtered and washed
several times with warm (60-70°C) distilled water and
with acetone. The final product was calcined to 538°C
15 in N_2 /air mixture and then held in air for 10 hours.
The calcined product proved to have a surface area of
915 m^2/g and an equilibrium benzene adsorption capacity
of >25 grams/100 grams. Argon physisorption data
indicated an argon uptake of 0.95 cc/gram, and a pore
15 size centered on 7.8 nm (78 Å) (Dollimore-Heal Method,
see Example 22(b)), but running from 7 to greater than
10.5 nm (70 to greater than 105 Angstroms). The X-ray
diffraction pattern of the calcined product of this
example may be characterized as having only enhanced
20 scattered intensity in the very low angle region of the
X-ray diffraction, where intensity from the transmitted
incident X-ray beam is usually observed. However, TEM
indicated that the product contained several materials
with different d_{100} values as observed in their
25 electron diffraction patterns. These materials were
found to possess d_{100} values between 85 Å d-spacing and
110 Å d-spacing.

Example 19

30 To eighty grams of cetyltrimethylammonium
hydroxide (CTMAOH) solution prepared as in Example 1
was added 1.65 grams of NaAlO_2 . The mixture was



stirred at room temperature until the NaAlO_2 was dissolved. To this solution was added 40 grams of aqueous tetramethylammonium (TMA) silicate solution (10 wt % SiO_2), 10 grams of HiSi1 , and 18 grams of 1,3,5-trimethylbenzene (mesitylene). The resulting mixture was stirred at room temperature for several minutes. The gel was then loaded into a 300 ml autoclave and heated at 105°C for four hours with stirring at 150 rpm. The mixture had a composition in terms of moles per mole Al_2O_3 :

	1.25 moles Na_2O
	27.8 moles SiO_2
	5.1 moles $(\text{CTMA})_2\text{O}$
	2.24 moles $(\text{TMA})_2\text{O}$
15	650 moles H_2O
	19.9 moles 1,3,5-trimethylbenzene

The resulting product was filtered and washed several times with warm (60 - 70°C) distilled water and with acetone. The final product was calcined to 538°C in N_2 /air mixture and then held in air for 8 hours.

The calcined product proved to have a surface area of $975 \text{ m}^2/\text{g}$ and an equilibrium benzene adsorption capacity of >40 grams/100 grams. Argon physisorption data indicated an argon uptake of 0.97 ml/gram , and a pore size of 6.3 nm ($63 \text{ \AA}$) (Dollimore-Heal Method), with the peak occurring at $P/P_0=0.65$.

The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at $63 \pm 5 \text{ \AA}$ d-spacing and weak lines at 36.4 ± 2.0 , $31.3 \pm 1.5 \text{ \AA}$ and $23.8 \pm 1.0 \text{ \AA}$ d-spacing. TEM indicated that the



product of this example contained the ultra-large pore material.

Example 20

Argon Physisorption Determination

5 To determine the pore diameters of the mesoporous products with pores up to 6.0 nm (60 Å) in diameter, 0.2 gram samples of the products of Examples 1 through 17 were placed in glass sample tubes and attached to a physisorption apparatus as described in U.S. Patent No.
10 4,762,010.

The samples were heated to 300°C for 3 hours in vacuo to remove adsorbed water. Thereafter, the samples were cooled to 87°K by immersion of the sample tubes in liquid argon. Metered amounts of gaseous
15 argon were then admitted to the samples in stepwise manner as described in U.S. Patent No. 4,762,010, column 20. From the amount of argon admitted to the samples and the amount of argon left in the gas space above the samples, the amount of argon adsorbed can be
20 calculated. For this calculation, the ideal gas law and the calibrated sample volumes were used. (See also S.J. Gregg et al., Adsorption, Surface Area and Porosity, 2nd ed., Academic Press, 1982). In each instance, a graph of the amount adsorbed versus the
25 relative pressure above the sample, at equilibrium, constitutes the adsorption isotherm. It is common to use relative pressures which are obtained by forming the ratio of the equilibrium pressure and the vapor pressure P_0 of the adsorbate at the temperature where
30 the isotherm is measured. Sufficiently small amounts of argon were admitted in each step to generate 168 data points in the relative pressure range from 0 to



0.6. At least 100 points are required to define the isotherm with sufficient detail.

The step (inflection) in the isotherm, indicates filling of a pore system. The size of the step indicates the amount adsorbed, whereas the position of the step in terms of P/P_0 reflects the size of the pores in which the adsorption takes place. Larger pores are filled at higher P/P_0 . In order to better locate the position of the step in the isotherm, the derivative with respect to $\log (P/P_0)$ is formed. The adsorption peak (stated in terms of $\log (P/P_0)$) may be related to the physical pore diameter ($\text{\AA}$) by the following formula:

$$\log(P/P_0) = \frac{K}{d-0.38} \left[\frac{s^4}{3(L-D/2)^3} - \frac{s^{10}}{9(L-D/2)^9} - \frac{s^4}{3(D/2)^3} + \frac{s^{10}}{9(D/2)^9} \right]$$

where d = pore diameter in nanometers, $K = 32.17$, $S = 0.2446$, $L = d + 0.19$, and $D = 0.57$.

This formula is derived from the method of Horvath and Kawazoe (G. Horvath et al., J. Chem. Eng. Japan, 16 (6) 470(1983)). The constants required for the implementation of this formula were determined from a measured isotherm of ALPO-5 and its known pore size. This method is particularly useful for microporous materials having pores of up to 60 $\text{\AA}$ in diameter.

The results of this procedure for the samples from Examples 1 through 17 are tabulated below. The samples from Examples 10, 13 and 15 gave two separate peaks, believed to be the result of two separate ultra-large pore phases in the products.



	<u>Example</u>	<u>Pore Diameter, Å</u>
	1	32.2
	2	35.4
	3	42.5
5	4	39.6
	5	16.9
	6	27.3
	7	36.6
	8	42.6
10	9	28.3
	10	22.8, 30.8
	11	36.8
	12	36.1
	13	35.0, 42.1
15	14	40.0
	15	22.4, 30.4
	16	15.0

20 The above method of Horvath and Kawazoe for determining pore size from physisorption isotherms was intended to be applied to pore systems of up to 20 Å diameter; but with some care as above detailed, its use can be extended to pores of up to 60 Å diameter.

In the pore regime above 60 Å diameter, the Kelvin



equation can be applied. It is usually given as:

$$\ln(P/P_0) = \frac{-2\gamma V}{r_k RT} \cos \theta$$

5 where:

- γ = surface tension of sorbate
 V = molar volume of sorbate
 θ = contact angle (usually taken for practical reasons to be 0)
10 R = gas constant
 T = absolute temperature
 r_k = capillary condensate (pore) radius
 P/P_0 = relative pressure (taken from the
15 physisorption isotherm)

20 The Kelvin equation treats adsorption in pore systems as a capillary condensation phenomenon and relates the pressure at which adsorption takes place to the pore diameter through the surface tension and contact angle of the adsorbate (in this case, argon). The principles upon which the Kelvin equation are based are valid for pores in the size range 50 to 1000 Angstrom diameter. Below this range the equation no longer reflects physical reality, since true capillary condensation cannot occur in smaller pores; above this
25 range the logarithmic nature of the equation precludes obtaining sufficient accuracy for pore size determination.

30 The particular implementation of the Kelvin equation often chosen for measurement of pore size is that reported by Dollimore and Heal (D. Dollimore and



G.R. Heal, J. Applied Chem, 14, 108 (1964)). This method corrects for the effects of the surface layer of adsorbate on the pore wall, of which the Kelvin equation proper does not take account, and thus provides a more accurate measurement of pore diameter. While the method of Dollimore and Heal was derived for use on desorption isotherms, it can be applied equally well to adsorption isotherms by simply inverting the data set.

5. In order to illuminate the microstructure of the materials by transmission electromicroscopy (TEM), samples must be thin enough for an electron beam to pass through them, generally 500-1000 Å or so thick. The crystal morphology of the present materials usually required that they be prepared for study by ultramicrotomy. While time consuming, this technique of sample preparation is conventional. The materials are embedded in a resin, in this case a commercially available low viscosity acrylic resin L.R. WHITE (hard), which is then cured at 80°C for 1 1/2 hours. Thin sections of the block are cut on an ultramicrotome using a diamond knife and sections in the thickness range 500-1000 Å are collected on fine mesh electron microscope support grids. For these materials, an LKB model microtome with a 45°C diamond knife edge was used; the support grids were 400 mesh copper grids. After evaporation of a thin carbon coating on the sample to prevent charging in the microscope (light gray color on a white sheet of paper next to the sample in the evaporator), the samples are ready for examination in the TEM.

High resolution TEM micrographs show projections of structure along the direction that the sample is



viewed. For this reason, it is necessary to have a sample in specific orientations to see certain details of the microstructure of the material. For crystalline materials, these orientations are most easily chosen by observing the electron diffraction pattern (EDP) that is produced simultaneously with the electron microscope image. Such EDPs are readily produced on modern TEM instruments using, e.g. the selected area field limiting aperture technique familiar to those skilled in the art of electron microscopy. When an EDP with the desired arrangement of diffraction spots is observed, the corresponding image of the crystal giving that EDP will reveal details of the microstructure along the direction of projection indicated by the EDP. In this way, different projections of a crystal's structure can be observed and identified using TEM.

In order to observe the salient features of the crystalline product of the present invention, it is necessary to view the material in an orientation wherein the corresponding EDP gives a hexagonal arrangement of diffraction spots from a single individual crystal. If multiple crystals are present within the field limiting aperture, overlapping diffraction patterns will occur that can be quite difficult to interpret. The number of diffraction spots observed depends to a degree upon the regularity of the crystalline arrangement in the material, among other things. At the very least the inner ring of bright spots should be observed to obtain a good image. Individual crystals can be manipulated by specimen tilt adjustments on the TEM until this orientation is achieved. More often, it is easier to take advantage of the fact that the specimen contains many randomly



oriented crystals and to simply search through the sample until a crystal giving the desired EDP (and hence orientation) is located.

5 Microtomed samples of materials from the Examples were examined by the techniques described above in a JEOL 200 CX transmission electron microscope operated at 200,000 volts with an effective 2 Å objective aperture in place. The instrument has a point-to-point resolution of 4.5 Å. Other conventional experimental
10 arrangements in high resolution (phase contrast) TEM could be used to produce equivalent images provided care is taken to keep the objective lens on the underfocus (weak leans) side of the minimum contrast lens current setting.

15 Example 21

Pt/MCM-41 Catalyst Preparation

A sample of MCM-41 (40 Å) was prepared in accordance with the method described below.

20 The following mixture (parts by weight - pbw) was charged to an autoclave:

83.7pbw Cetyltrimethylammonium (CTMA) hydroxide,
prepared by contacting a 29 wt % N,N,N-trimethyl-1-hexadecylammonium chloride solution with a hydroxide-for-halide
25 exchange resin,
1.7pbw Sodium aluminate,
4.1pbw Tetramethylammonium silicate (10% aqueous solution),
10.5pbw Precipitated hydrated silica (HiSil ♦).

30 The mixture was crystallized at 100°C for 20 hours with stirring under autogeneous pressure. The



resulting product was recovered by filtration and dried in air at ambient temperature. A sample of the product was calcined at 540° C for 1 hour in nitrogen, followed by 6 hours in air for characterization.

5 The calcined product had a surface area of 1120 m²/g and the following equilibrium absorption capacities in grams/100 grams:

	H2O	10.8
	Cyclohexane	>50
10	n-hexane	>50
	Benzene	67

15 The product was identified as MCM-41 with an X-ray diffraction pattern which included a very strong relative intensity line at 38.4 + 2.0 Å d-spacing, and weak lines at 22.6 + 1.0, 20.0 + 1.0, and 15.2 +1.0 Å.

20 The MCM-41 crystalline product was exchanged with room temperature aqueous solutions of ammonium nitrate and subsequently dried overnight at 121°C (250°F). A portion of the resultant crystals was combined with Al₂O₃ (Versal 250 ♦) to form a mixture of 65 parts, by weight MCM-41 and 35 parts alumina. Water was added to this mixture to allow the resulting catalyst to be formed into extrudates. The catalyst was activated by calcination at 510°C (950°F) in 5v/v/min of nitrogen for 6 hours followed by the replacement of the nitrogen with 5v/v/min of air. The calcination was completed by raising the temperature to 1000°F and maintaining that temperature in 5v/v/min air for 18 hours.

25 The calcined extrudate was exchanged with a 30 0.0062M Pt(NH₃)₄Cl₂ solution, followed by washing,



drying and calcination in air at 343°C (650°F) for three hours.

Example 22

Pd/MCM-41 Catalyst Preparation

5 A sample of MCM-41 (40 Å) was prepared in accordance with the method described below.

 The following mixture was charged to an autoclave:

60.7pbw Cetyltrimethylammonium (CTMA) hydroxide,
 prepared by contacting a 29wt.% N,N,N-
10 trimethyl-1-hexadecylammonium chloride
 solution with a hydroxide-for-halide
 exchange resin,
1.3pbw Sodium aluminate,
30.4pbw Tetramethylammonium silicate (10% aqueous
15 solution),
7.6pbw Precipitated hydrated silica (HiSil ♦).

 The mixture was crystallized at 100°C for 20 hours with stirring under autogeneous pressure. The
20 resulting product was recovered by filtration and dried
 in air at ambient temperature. A sample of the product
 was calcined at 540° C for 1 hour in nitrogen, followed
 by 6 hours in air. The identity of the material as
 MCM-41 was consistent with its properties.

 The MCM-41 crystalline product was formulated into
25 a catalyst in the same way as the platinum-containing
 catalyst described in Example 22 with the exception
 that the calcined catalyst was exchanged with aqueous
 Pd(NH₃)₄Cl₂ solution, followed by drying at room
 temperature for 4 hours and overnight at 250°F before
30 the final calcination.

This Sheet Has Been Replaced



Example 23

5 A Pd/SiO₂ catalyst was made by impreganting silica spheres (Shell S-980 C 1.5) with a Pd(NH₃)₄Cl₂ solution using the incipient wetness method. The impregnated spheres were then dried at room temperature for 4 hours, followed by 250°F overnight after which the catalyst was calcined in 5 v/v/min air at 550°F for 3 hours.

Example 24

10 The three noble metal containing catalysts described above (Pt MCM-41/Al₂O₃, Pd MCM-41/Al₂O₃, Pd SiO₂) were evaluated for hydrogenating a PAO lubricant. The properties of the three catalysts are summarized in Table 2 below.

15

Table 2

Catalyst Properties

	<u>Pd MCM-41⁽¹⁾</u>	<u>Pt MCM-41⁽¹⁾</u>	<u>Pd SiO₂</u>
<u>Metal Loading.</u>			
<u>Wt%</u>			
20 Pd	0.83	-	0.84
Pt	-	0.54	-
<u>Surface Area.</u>			
<u>m²/g</u>			
	800	682	330
<u>Pore Volume.</u>			
25 <u>cc/g</u>	0.96	0.97	0.88
<u>Pore Distribution, %</u>			
	<50 Å 32	42	0
	50-100 Å 16	12	41
	100-200 Å 15	11	32
30 >200 Å 37		35	37

(1) Contains 65 wt % MCM-41 and 35 wt % alumina prior to the metal addition.

This Sheet Has Been Replaced



The MCM-41 materials used in the catalysts containing this crystalline material had a pore opening of 40 Å. All three catalysts have 30% pore volume with pore diameters greater than 200 Å but the MCM-41 catalysts have 30-40% pore volume with pore diameters less than 50 Å.

All catalysts were evaluated in a fixed-bed pilot unit. A poly-alpha olefin (PAO) lube oligomer having the composition shown in Table 3 below was used as the feed.

Table 3
Properties of PAO

Gravity, °API	39.2
Hydrogen, wt %	14.6
Bromine Number	27.3
KV @ 40°C, mm ² /s	26.22
KV @100°C, mm ² /s	5.253
Viscosity Index	136

The PAO was hydrogenated at 2.0 LHSV, 2520 kPa abs. (350 psig) H₂ and 890 n.l.l.⁻¹ (5000 scf/b) of once-through hydrogen circulation rate. Reactor temperature was varied to obtain catalyst activity as a function of temperature. Catalyst activity is measured by the reduction of bromine number of the oil.

The results are summarized graphically in the figure. The PAO feed had a bromine number of 27.3 units and, as shown in the figure, the Pd MCM-41/Al₂O₃ catalyst is the most active catalyst. It achieved the reduction of bromine number to less than 1 at 177°C (350°F), the lowest temperature of the experiments. Pt

MCM-41/ Al_2O_3 is also quite active. The Pd/SiO_2 catalyst, which does not have pore volume associated with pore openings less than 50 Å, is the least active catalyst.





CLAIMS:

1. A process for hydrogenating a lubricant hydrocarbon which comprises contacting a hydrocarbon lubricant feed in the presence of hydrogen with a hydrogenation catalyst containing a metal hydrogenation component on a support comprising an inorganic, porous crystalline phase material having pores with diameters of at least 1.3 nm (13 Angstrom Units) and exhibiting, after calcination, an X-ray diffraction pattern with at least one peak at a d-spacing greater than 1.8 nm (18 Å) with a relative intensity of 100.

2. A hydrogenation process according to claim 1 in which the crystalline phase exhibits, after calcination, a hexagonal arrangement of uniformly sized pores with diameters of at least 13 Å and which exhibits, after calcination, a hexagonal electron diffraction pattern that can be indexed with a d_{100} value greater than 1.8 nm (18 Angstrom Units).


3. A hydrogenation process according to claim 1 in which the crystalline phase has an X-ray diffraction pattern following calcination with at least one peak whose d-spacing corresponds to the d_{100} value from the electron diffraction pattern.

4. A hydrogenation process according to claim 1 in which the crystalline phase exhibits a benzene adsorption capacity of greater than 15 grams benzene per 100 grams at 6.7 kPa (50 torr) and 25°C.





5. A hydrogenation process according to claim 1 in which the crystalline phase has a composition expressed as follows:



5 wherein M is one or more ions; n is the charge of the composition excluding M expressed as oxides; q is the weighted molar average valence of M; n/q is the number of moles or mole fraction of M; W is one or more
10 divalent elements; X is one or more trivalent elements; Y is one or more tetravalent elements; Z is one or more pentavalent elements; a, b, c, and d are mole fractions of W, X, Y, and Z, respectively; h is a number of from 1 to 2.5; and (a+b+c+d) = 1.

6. A hydrogenation process according to claim 4 wherein W comprises a divalent first row transition metal or magnesium; X comprises aluminum, boron, gallium or iron; Y comprises silicon or germanium; and
5 Z comprises phosphorus.

7. A hydrogenation process according to claim 4 wherein a and d are 0 and h = 2.

8. A hydrogenation process according to claim 7 wherein X comprises aluminum, boron, gallium or iron and Y comprises silicon or germanium.

9. A hydrogenation process according to claim 8 wherein X comprises aluminum and Y comprises silicon.





- 70 -

10. A hydrogenation process according to claim 1 in which the catalyst comprises at least one metal of Groups VIA, VIIA or VIIIA of the Periodic Table.

11. A hydrogenation process according to claim 1 in which the catalyst comprises at least one noble metal of Group VIIIA of the Periodic Table.

12. A process according to claim 11 in which the noble metal comprises palladium.

13. A hydrogenation process according to claim 1 in which the feed is contacted with the catalyst at a pressure of from 1480 to 10500 kPa (200 to 1500 psig) (reactor inlet), a temperature from 93° to 371°C (200° to 700°F), and a space velocity from 0.2 to 2.0 LHSV.

14. A hydrogenation process according to claim 1 in which the lubricant comprises a poly alpha olefin.

15. A process according to claim 14 in which the polyalphaolefin comprises a poly alpha olefin produced by the polymerization of a C₈-C₁₂ alpha-olefin.

16. A process according to claim 14 in which the poly alpha olefin is produced by the polymerisation of the olefin in the presence of a Friedel-Crafts catalyst.

This Sheet Has Been Replaced





- 71 -

5 17. A process according to claim 14 in which the poly alpha olefin is a poly alpha olefin having a branch ratio of less than 0.19, produced by the polymerization of the olefin in the presence of a reduced Group VIA metal oxide catalyst.


18. A process according to claim 1 in which the bromine number of the lubricant is reduced from a value of at least 5 to a value of not more than 1.

19. A process according to claim 18 in which the bromine number of the lubricant is recued from a value of at least 10 to a value of not more than 0.5.

This Sheet Has Been Replaced



PAO Hydrogenation



■ Pd MCM-41/Al₂O₃

▨ Pt MCM-41/Al₂O₃

□ Pd/SiO₂

This Sheet Has Been Replaced



- 1 -

HYDROGENATION PROCESS

This invention relates to hydrogenation catalysts and their use in a hydrogenation process which is particularly applicable to the hydrogenation or

5 hydrotreating of lubricant oils, especially synthetic lubricant oils produced by the oligomerization of lower molecular weight olefins.

Hydrogenation is a well-established process both in the chemical and petroleum refining industries.

10 Hydrogenation is conventionally carried out in the presence of a catalyst which usually comprises a metal hydrogenation component on a porous support material, such as a natural clay or a synthetic oxide. Metals such as nickel, platinum, palladium and combinations of


15 metals are often used. Typical support materials include kieselguhr, alumina, silica and silica-alumina. Depending upon the ease with which the feed may be hydrogenated, the hydrogen pressures used may vary from quite low to very high values, typically from 790 to

20 17340 kPa abs. (100 to 2,500 psig) and in most cases from 790 to 8400 kPa abs. (100 to 1,200 psig). Hydrogenation is an exothermic process and is therefore thermodynamically favored by lower temperatures but for kinetic reasons, moderately elevated temperatures are

25 normally used and for petroleum refining processes, temperatures in the range of 149° to 371°C (300° to 700°F) are typical.

Hydrogenative treatment is frequently used in petroleum refining to improve the qualities of


30 lubricating oils, both of natural mineral oil and synthetic origin. Hydrogenation, or hydrotreating as it is frequently termed, is used to reduce any residual



REPLACEMENT SHEET	
✓ Description of item	page 11 to page 16
✓ Drawing(s)	page 17 to page 20
✓ Abstract	page 21 to page 22
DATE OF RECEIPT 17/6/96	

unsaturation in the lubricating oil, to remove heteroatom-containing impurities and color bodies. In mineral oils, the removal of impurities and color bodies is of particular significance but for mineral oils which have been subjected to hydrocracking or catalytic dewaxing. For both mineral and synthetic stocks, the saturation of lube boiling range olefins is a major objective.


The polyolefins comprise one class of synthetic hydrocarbon lubricants which has achieved importance in the lubricating oil market. These materials are typically produced by the polymerization (the term oligomerization is often used for the lower molecular weight products which are used as low viscosity basestocks) of alpha olefins typically ranging from 1-octene to 1-dodecene, with 1-decene being a preferred material, although polymers of lower olefins such as ethylene and propylene may also be used, including copolymers of ethylene with higher olefins, as described in U.S. Patent No. 4,956,122 and the patents referred to there. The poly alpha-olefin (PAO) products may be obtained with a wide range of viscosities varying from highly mobile fluids of 3 mm²/s to higher molecular weight, viscous materials which may be used as VI improvers for the lower viscosity PAO stocks. The PAO's are conventionally produced by the polymerization of the olefin feed in the presence of a catalyst such as aluminum trichloride, or boron trifluoride or trifluoride complexes. Processes for the production of PAO lubricants in this way are disclosed, for example, in U.S. Patent Nos. 3,382,291, 4,172,855, 3,780,128, 3,149,178, 3,742,082, and 4,956,122. The PAO



lubricants are also discussed in Lubrication Fundamentals, J. G. Wills, Marcel Dekker Inc., New York, 1980 ISBN 0-8247-6976-7, especially Pages 77 to 81. Subsequent to the polymerization, the lubricant range products are hydrogenated in order to reduce the residual unsaturation. In the course of this reaction, the bromine number of the lubricant is reduced from a typical value of 10 or higher to a value of not more than 1 or even lower.

A novel type of PAO lubricant has recently been disclosed as having exceptional and advantageous properties. These materials are the HVI-PAO materials which are disclosed in U.S. Patent Nos. 4,827,064 and 4,827,073. These materials are produced by the oligomerization of one olefins, especially 1-decene, using a reduced Group VI metal oxide catalyst, preferably a reduced chromium oxide catalyst. The HVI-PAO products may be derivatized by reaction with aromatics, as disclosed EP 377305 and higher molecular weight versions prepared by the use of lower oligomerization temperatures, as disclosed in U.S. Patent No. 5,012,020, to which reference is made for a disclosure of the higher molecular weight products. Although the oligomerization process using the reduced metal oxide catalysts produces a material of characteristic structure, residual unsaturation remains in the oligomer product and, like the conventional PAO oligomers, it is subjected to hydrogenation in order to improve its stability as a lubricant. The hydrogenation is carried out in the same manner as with the conventional PAO-type materials.

The catalysts used for hydrogenating lubricants, whether of mineral oil or synthetic origin, require a



strong hydrogenation function provided by the metal component and large pore diameters in the porous support material in order to minimize the diffusion resistance of the bulky lubricant molecules. For reactions with bulky molecules, the optimum ratio of catalytic pore diameter to molecule size is 1.5:1. Table 1 below shows the optimum pore sizes required for normal alkanes in the C-7 to C-25 range. The table shows that for alkanes in this range, the chain-length varies from 9.9 to 37.6 Å so that active hydrogenation catalysts for these materials should have a major amount of their pore volume with pore openings in the range of 1.5 to 5.6 nm (15 to 56 Å), and preferably with a major amount of this in the range 3.8 to 5.6 nm (38 to 56 Å).





Table 1
Optimum Pore Size

	<u>Carbon Number</u>	<u>Alkane Length, nm (1)</u>	<u>Optimum Pore Diameter, nm (2)</u>
5	C ₇	0.99	1.5
	C ₈	1.15	1.7
	C ₁₀	1.45	2.2
	C ₁₂	1.76	2.6
	C ₁₇	2.53	3.8
10	C ₁₉	2.84	4.3
	C ₂₁	3.15	4.7
	C ₂₃	3.46	5.2
	C ₂₅	3.76	5.6

- (1) Based on bond lengths of 0.154 and 0.111 nm for C-C and C-H bond lengths, respectively.
- (2) Based on an optimum ratio of catalyst pore to molecule size ratio of 1.5.


Conventional amorphous support materials such as alumina, silica and silica-alumina, typically have a pore size distribution with most of the pores larger than 5 nm and most of these are larger than 10nm. Although these large pores enable the bulky lubricant molecules to traverse the molecular structure of the catalyst freely with little diffusion resistance, the reduced surface area associated with the larger pore sizes diminishes the area which is available for the hydrogenation reactions. It would therefore be desirable to utilize a hydrogenation catalyst which posses a significant amount of its pores in the range of 1.5 to 6 nm (15 to 60 Å), close to the optimum ratio



for the lower molecular weight materials making up the bulk of many synthetic lubricants as well as the lower viscosity mineral oils.

5 We have now found that another class of catalytic materials - the mesoporous crystalline materials - which have high pore volume, high surface area and controlled pore openings of at least 13 Å, is particularly suitable for the hydrogenation of lubricant hydrocarbons, especially synthetic PAO-type materials.

10 According to the presednt invention, therefore, the hydrogenation process utilizes a hydrogenation catalyst which comprises a hydrogenation function in the form of a metal on a support material which
15 comprises a mesoporous siliceous material with a novel and unique structure and pore geometry described below. These materials are inorganic, porous, non-layered crystalline phase materials which, in their calcined forms exhibit an X-ray diffraction pattern with at
20 least one peak at a d-spacing greater than 1.8 nm (18 Ångstrom Units (Å)). They also have a benzene adsorption capacity greater than 15 grams benzene per 100 grams of the material at 6.7 kPa (50 torr) and 25°C. In a preferred form, the support material is
25 characterized by a substantially uniform hexagonal honeycomb microstructure with uniform pores having a cell diameter greater than 1.3 nm (13 Å) and typically in the range of 2 to 10 nm (20 to 100 Å). Most prominent among these materials is a new crystalline
30 material identified as MCM-41 which is usually synthesized as a metallosilicate with Brønsted acid sites by incorporating a tetrahedrally coordinated trivalent element such as Al, Ga, B, or Fe within the




silicate framework. The preferred forms of these materials are the aluminosilicates although other metallosilicates may also be utilized.

5 MCM-41 is characterized by a microstructure with a uniform, hexagonal arrangement of pores with diameters of at least 1.3 nm (13 Å). After calcination, it exhibits an X-ray diffraction pattern with at least one d-spacing greater than 18 Å and a hexagonal electron
10 diffraction pattern that can be indexed with a d_{100} value greater than 18 Å which corresponds to the d-spacing of the peak in the X-ray diffraction pattern.

A preferred catalyst for the present purpose is an alumina bound crystalline material which has a significant pore volume with pore diameters greater
15 than 20 nm (200 Å). The large diameter pores provide channels for bulky PAO oligomers to transport freely with diminished diffusion resistance to the smaller particles of the crystalline material which provide a large surface area for the hydrogenation reaction. The
20 preferred crystalline materials for use in the present process have pore diameters greater than 1.5 nm (15 Å) and the preferred pore diameters are in the range of 1.5 to 6 nm (15 to 60 Å).

25 The single figure of the accompanying drawings is a graphical representation of testing results reported in the Examples below.


In the present process, lubricant range hydrocarbons are hydrogenated or hydrotreated or hydrotreated in the presence of a hydrogenation
30 catalyst which comprises a mesoporous crystalline material, preferably with a binder which possesses a significant pore volume having pore diameters greater than 20 nm (200 Å). The process may be carried out



with mineral oil lubricants or synthetic hydrocarbon lubricants, of which the PAO materials are preferred, both conventional type PAO's prepared using Friedel-Crafts type catalysts as well as the HVI-PAO materials produced using a reduced Group VIB metal oxide catalyst.

The mineral oil lubricants may generally be characterized as having a minimum boiling point of at least 650°F (345°C) and usually they will be neutral i.e., distillate, stocks with an end point of not more than 1050°F (565°C), although residual lube stocks such as bright stock may also be treated by the same catalytic process. Mineral oil stocks of this kind are typically prepared by the conventional refining process involving atmospheric and vacuum distillation of a crude of suitable composition, followed by removal of undesirable aromatic components by solvent extraction using a solvent such as phenol, furfural or N,N-dimethylformamide (DMF). Dewaxing to the desired product pour point may be carried out using either solvent dewaxing or catalytic dewaxing techniques and it is particularly preferred that a hydrogenative treatment according to the present invention should follow any catalytic dewaxing treatment in order to saturate lube boiling range olefins which may be produced during the catalytic dewaxing process.


The present process is, however, particularly applicable to the hydrogenative treatment of synthetic lubricating oils, especially the poly alpha-olefins (PAO) including the HVI-PAO type materials. These types of lubricants may be produced by the polymerization or oligomerization procedures described above using Friedel-Crafts type catalysts such as



aluminum trichloride, boron trifluoride or boron trifluoride complexes, e.g., with water, lower alkanols or esters in the conventional manner. The HVI-PAO type oligomers may be prepared by the methods described in U.S. Patent Nos. 4,827,064 and 4,827,073, using a reduced Group VIB metal oxide catalyst, normally chromium on silica. The HVI-PAO materials include the higher molecular weight versions prepared by the use of lower oligomerization temperatures, as disclosed in U.S. Patent No. 5,012,020, to which reference is made for a full description of these materials and their preparation. Derivatives of the PAO lubricants may be prepared by reaction with aromatics as disclosed, for example, in EP 377305, referred to above. The HVI-PAO materials are characterized by a branch ratio below 0.19 which results from the use of the unique reduced metal oxide catalyst during the oligomerization process.

The lubricant materials are subjected to the hydrogenative treatment in the presence of a catalyst which comprises a metal component for hydrogenation together with the mesoporous crystalline material and, optionally, a binder.


The hydrogenation reaction is carried out under conventional conditions with temperatures from 93° to 371°C (200° to 700°F), and preferably in the range of 149° to 260°C (300° to 500°F). Hydrogen pressure may vary up to 17340 kPa abs. (2,500 psig) but normally will be from 790 to 3550 kPa abs. (100 to 500 psig). Hydrogen circulation rates are typically in the range 178 to 1424 n.l.l.⁻¹ (1,000 to 8,000 scf/bbl) and once through circulation is preferred in order to maximize the purity of the hydrogen. Space velocities are




typically in the range of 0.5 to 10 LHSV, usually from 1 to 3 LHSV. The products of the hydrogenation reaction have a low degree of unsaturation consistent with the hydrogenative treatment and in most cases the bromine number of the product will be less than 2 and is preferably less than 1.

The catalytic material used in the present invention includes a novel synthetic composition of matter comprising an ultra-large pore size crystalline phase as a support for the metal component of the catalyst. This material is an inorganic, porous, non-layered crystalline phase material which can be characterized (in its calcined form) by an X-ray diffraction pattern with at least one peak at a d-spacing greater than 1.8 nm (18 Å) with a relative intensity of 100 and a benzene sorption capacity of greater than 15 grams of benzene per 100 grams of the the material at 6.7 kPa (50 torr) and 25°C.

The preferred form of the crystalline material is an inorganic, porous, non-layered material having a hexagonal arrangement of uniformly-sized pores with a maximum perpendicular cross-section pore dimension of at least 1.3 nm (13 Ångstron Units (Å)), and typically within the range of from 1.3 to 20 nm (13 Å to 200 Å). A preferred form of this hexagonal crystalline composition, identified as MCM-41, with the characteristic structure of hexagonally-arranged, uniformly-sized pores of at least 1.3 nm (13 Å) diameter, exhibits a hexagonal electron diffraction pattern that can be indexed with a d_{100} value greater than 1.8 nm (18 Å) which corresponds to at least one peak in the X-ray diffraction pattern.




The inorganic, non-layered mesoporous crystalline material used as a component of the catalyst has the following composition:



5 wherein W is a divalent element, such as a divalent first row transition metal, e.g. manganese, cobalt and iron, and/or magnesium, preferably cobalt; X is a trivalent element, such as aluminum, boron, iron and/or gallium, preferably aluminum; Y is a tetravalent
10 element such as silicon and/or germanium, preferably silicon; Z is a pentavalent element, such as phosphorus; M is one or more ions, such as, for example, ammonium, Group IA, IIA and VIIB ions, usually hydrogen, sodium and/or fluoride ions; n is the charge of the composition excluding M expressed as oxides; q
15 is the weighted molar average valence of M; n/q is the number of moles or mole fraction of M; a, b, c, and d are mole fractions of W, X, Y and Z, respectively; h is a number of from 1 to 2.5; and $(a+b+c+d) = 1$.

20 A preferred embodiment of the above crystalline material is when $(a+b+c)$ is greater than d, and $h = 2$. A further embodiment is when a and d = 0, and $h = 2$. The preferred materials for use in making the present catalysts are the aluminosilicates although other
25 metallocosilicates may also be used.

In the as-synthesized form, the support material has a composition, on an anhydrous basis, expressed empirically as follows:




30 where R is the total organic material not included in M as an ion, and r is the coefficient for R, i.e. the number of moles or mole fraction of R.

The M and R components are associated with the material as a result of their presence during crystallization, and are easily removed or, in the case of M, replaced by post-crystallization methods described below.


To the extent desired, the original M, e.g. sodium or chloride, ions of the as-synthesized material of this invention can be replaced in accordance with conventional ion-exchange techniques. Preferred replacing ions include metal ions, hydrogen ions, hydrogen precursor, e.g. ammonium, ions and mixtures of these ions. Particularly preferred ions are those which provide the desired metal functionality in the final catalyst. These include hydrogen, rare earth metals and metals of Groups VIIA (e.g. Mn), VIIIA (e.g. Ni), IB (e.g. Cu), IVB (e.g. Sn) of the Periodic Table of the Elements and mixtures of these ions.

The crystalline (i.e. having sufficient order to provide a diffraction pattern such as, for example, by X-ray, electron or neutron diffraction, following calcination with at least one peak) mesoporous material may be characterized by its structure, which includes extremely large pore windows as well as by its high sorption capacity. The term "mesoporous" is used here to indicate crystals having uniform pores within the range of from 1.3 to 20 nm (13 Å to 200 Å). The mesoporous materials have uniform pores within the range of from 1.3 to 20 nm (13 Å to 200 Å), more usually from 1.5 to 10 nm (15 Å to 100 Å). Since these pores are significantly larger than those of other crystalline materials, it is appropriate to refer to them as ultra-large pore size materials. For the purposes of this application, a working definition of




"porous" is a material that adsorbs at least 1 gram of a small molecule, such as Ar, N₂, n-hexane or cyclohexane, per 100 grams of the solid.

5 The catalytic material can be distinguished from other porous inorganic solids by the regularity of its large open pores, whose pore size more nearly resembles that of amorphous or paracrystalline materials, but whose regular arrangement and uniformity of size (pore size distribution within a single phase of, for
10 example, $\pm 25\%$, usually $\pm 15\%$ or less of the average pore size of that phase) resemble more those of crystalline framework materials such as zeolites. The preferred materials have a hexagonal arrangement of large open channels that can be synthesized with open
15 internal diameters from 1.3 to 20 nm (13 Å to 200 Å). The term "hexagonal" is intended to encompass not only materials that exhibit mathematically perfect hexagonal symmetry within the limits of experimental measurement, but also those with significant observable deviations
20 from that ideal state. A working definition as applied to the microstructure of the present invention would be that most channels in the material would be surrounded by six nearest neighbor channels at roughly the same distance. Defects and imperfections will cause
25 significant numbers of channels to violate this criterion to varying degrees, depending on the quality of the material's preparation. Samples which exhibit as much as $\pm 25\%$ random deviation from the average repeat distance between adjacent channels still clearly
30 give recognizable images of the present ultra-large pore materials. Comparable variations are also observed in the d_{100} values from the electron diffraction patterns.



The most regular preparations of the support material give an X-ray diffraction pattern with a few distinct maxima in the extreme low angle region. The positions of these peaks approximately fit the positions of the $hk0$ reflections from a hexagonal lattice. The X-ray diffraction pattern, however, is not always a sufficient indicator of the presence of these materials, as the degree of regularity in the microstructure and the extent of repetition of the structure within individual particles affect the number of peaks that will be observed. Indeed, preparations with only one distinct peak in the low angle region of the X-ray diffraction pattern have been found to contain substantial amounts of the material in them. Other techniques to illustrate the microstructure of this material are transmission electron microscopy and electron diffraction. Properly oriented specimens of the material show a hexagonal arrangement of large channels and the corresponding electron diffraction pattern gives an approximately hexagonal arrangement of diffraction maxima. The d_{100} spacing of the electron diffraction patterns is the distance between adjacent spots on the $hk0$ projection of the hexagonal lattice and is related to the repeat distance a_0 between channels observed in the electron micrographs through the formula $d_{100} = a_0/\sqrt{3}$. This d_{100} spacing observed in the electron diffraction patterns corresponds to the d-spacing of a low angle peak in the X-ray diffraction pattern of the material. The most highly ordered preparations of the material obtained so far have 20-40 distinct spots observable in the electron diffraction patterns. These patterns can be indexed with the




hexagonal hko subset of unique reflections of 100, 110, 200, 210, etc., and their symmetry-related reflections.

In its calcined form, the crystalline material may be further characterized by an X-ray diffraction pattern with at least one peak at a position greater than 1.8 nm (18 Angstrom Units) d-spacing ($4.909^\circ 2\theta$ for Cu K-alpha radiation) which corresponds to the d_{100} value of the electron diffraction pattern of the material, and an equilibrium benzene adsorption capacity of greater than 15 grams benzene/100 grams crystal at 6.7 kPa (50 torr) and 25°C (basis: crystal material having been treated in an attempt to insure no pore blockage by incidental contaminants, if necessary).

The equilibrium benzene adsorption capacity characteristic of this material is measured on the basis of no pore blockage by incidental contaminants. For instance, the sorption test will be conducted on the crystalline material phase having any pore blockage contaminants and water removed by ordinary methods. Water may be removed by dehydration techniques, e.g. thermal treatment. Pore blocking inorganic amorphous materials, e.g. silica, and organics may be removed by contact with acid or base or other chemical agents such that the detrital material will be removed without detrimental effect on the crystal.

More particularly, the calcined crystalline non-layered material may be characterized by an X-ray diffraction pattern with at least two peaks at positions greater than 1.0 nm (10 Å) d-spacing ($8.842^\circ 2\theta$ for Cu K-alpha radiation), at least one of which is at a position greater than 1.8 nm (18 Å) d-spacing, and no peaks at positions less than 1.0 nm (10 Å) d-spacing




with relative intensity greater than 20% of the strongest peak. Still more particularly, the X-ray diffraction pattern of the calcined material of this invention will have no peaks at positions less than 1.0 nm (10 Å) d-spacing with relative intensity greater than 10% of the strongest peak. In any event, at least one peak in the X-ray diffraction pattern will have a d-spacing that corresponds to the d_{100} value of the electron diffraction pattern of the material.

The calcined inorganic, non-layered crystalline material may also be characterized as having a pore size of 1.3 nm (13 Å) or greater as measured by physisorption measurements, described below. Pore size is considered a maximum perpendicular cross-section pore dimension of the crystal.


X-ray diffraction data were collected on a Scintag PAD X automated diffraction system employing theta-theta geometry, Cu K-alpha radiation, and an energy dispersive X-ray detector. Use of the energy dispersive X-ray detector eliminated the need for incident or diffracted beam monochromators. Both the incident and diffracted X-ray beams were collimated by double slit incident and diffracted collimation systems. The slit sizes used, starting from the X-ray tube source, were 0.5, 1.0, 0.3 and 0.2 mm, respectively. Different slit systems may produce differing intensities for the peaks. The materials of the present invention that have the largest pore sizes may require more highly collimated incident X-ray beams in order to resolve the low angle peak from the transmitted incident X-ray beam.

The diffraction data were recorded by step-scanning at 0.04 degrees of 2θ , where θ is the



5 Bragg angle, and a counting time of 10 seconds for each
step. The interplanar spacings, d 's, were calculated
in Å (Å), and the relative intensities of the lines,
 I/I_0 , where I_0 is one-hundredth of the intensity of the
strongest line, above background, were derived with the
10 use of a profile fitting routine. The intensities were
uncorrected for Lorentz and polarization effects. The
relative intensities are given in terms of the symbols
vs = very strong (75-100), s = strong (50-74), m =
15 medium (25-49) and w = weak (0-24). The diffraction
data listed as single lines may consist of multiple
overlapping lines which under certain conditions, such
as very high experimental resolution or
crystallographic changes, may appear as resolved or
20 partially resolved lines. Typically, crystallographic
changes can include minor changes in unit cell
parameters and/or a change in crystal symmetry, without
a substantial change in structure. These minor
effects, including changes in relative intensities, can
25 also occur as a result of differences in cation
content, framework composition, nature and degree of
pore filling, thermal and/or hydrothermal history, and
peak width/shape variations due to particle size/shape
effects, structural disorder or other factors known to
those skilled in the art of X-ray diffraction.


30 The equilibrium benzene adsorption capacity is
determined by contacting the material of the invention,
after dehydration or calcination at, for example, 540°C
for at least one hour and other treatment, if
necessary, in an attempt to remove any pore blocking
contaminants, at 25°C and 6.7 kPa (50 torr) benzene
until equilibrium is reached. The weight of benzene
sorbed is then determined as described below.



The ammonium form of the catalytic material may be readily converted to the hydrogen form by thermal treatment (calcination). This thermal treatment is generally performed by heating one of these forms at a temperature of at least 400°C for at least 1 minute and generally not longer than 20 hours, preferably from 1 to 10 hours. While subatmospheric pressure can be employed for the thermal treatment, atmospheric pressure is desired for reasons of convenience, such as in air, nitrogen, ammonia, etc. The thermal treatment can be performed at a temperature up to 750°C. The thermally treated product is particularly useful in the catalysis of certain hydrocarbon conversion reactions and it is preferred that the material should be in this form for use in the present catalysts.

The crystalline material can be prepared by one of several methods, each with particular limitations.

A first method involves a reaction mixture having an X_2O_3/YO_2 mole ratio of from 0 to 0.5, but an Al_2O_3/SiO_2 mole ratio of from 0 to 0.01, a crystallization temperature of from 25° to 250°C, preferably from 50° to 175°C, and an organic directing agent, hereinafter more particularly described, or, preferably a combination of that organic directing agent plus an additional organic directing agent, described below. This first method comprises preparing a reaction mixture containing sources of, for example, alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or a combination of oxides selected from the group consisting of divalent element W, e.g. cobalt, trivalent element X, e.g. aluminum, tetravalent element Y, e.g. silicon, and pentavalent element Z, e.g. phosphorus, an organic (R)




directing agent, described below, and a solvent or solvent mixture, such as, for example, C₁-C₆ alcohols, C₁-C₆ diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:

	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
	X ₂ O ₃ /YO ₂	0 to 0.5	0.001 to 0.5
	Al ₂ O ₃ /SiO ₂	0 to 0.01	0.001 to 0.01
	X ₂ O ₃ /(YO ₂ +Z ₂ O ₅)	0.1 to 100	0.1 to 20
10	X ₂ O ₃ /(YO ₂ +WO+Z ₂ O ₅)	0.1 to 100	0.1 to 20
	Solvent/ (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	1 to 1500	5 to 1000
	OH ⁻ /YO ₂	0 to 10	0 to 5
	(M ₂ /e ^O +R ₂ /f ^O)/ (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0.01 to 20	0.05 to 5
15	M ₂ /e ^O / (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0 to 10	0 to 5
	R ₂ /f ^O / (YO ₂ +WO+Z ₂ O ₅ +X ₂ O ₃)	0.01 to 2.0	0.03 to 1.0


where e and f are the weighted average valences of M and R, respectively.

In this first method, when no Z and/or W oxides are added to the reaction mixture, the pH is important and must be maintained at from 9 to 14. When Z and/or W oxides are present in the reaction mixture, the pH is not narrowly important for synthesis of the present crystalline material. In this, as well as the following methods for synthesis of the present material the R₂/f^O/(YO₂+WO+Z₂O₅+X₂O₃) ratio is important. When this ratio is less than 0.01 or greater than 2.0,



impurity products tend to be synthesized at the expense of the desired crystalline material.

5 A second method for synthesis of the crystalline material involves a reaction mixture having an X_2O_3/YO_2 mole ratio of from 0 to 0.5, a crystallization temperature of from 25° to 250°C, preferably from 50° to 175°C, and two separate organic directing agents, i.e. the organic and additional organic directing agents, described below. This second method comprises
10 preparing a reaction mixture containing sources of, for example, alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or a combination of oxides selected from the group consisting of divalent element W, e.g. cobalt,
15 trivalent element X, e.g. aluminum, tetravalent element Y, e.g. silicon, and pentavalent element Z, e.g. phosphorus, a combination of organic directing agent and additional organic directing agent (R), each described below, and a solvent or solvent mixture, such
20 as, for example, C_1-C_6 alcohols, C_1-C_6 diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:




	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
	X_2O_3/YO_2	0 to 0.5	0.001 to 0.5
	$X_2O_3/(YO_2+Z_2O_5)$	0.1 to 100	0.1 to 20
5	$X_2O_3/(YO_2+WO+Z_2O_5)$	0.1 to 100	0.1 to 20
	Solvent/ $(YO_2+WO+Z_2O_5+X_2O_3)$	1 to 1500	5 to 1000
	OH^-/YO_2	0 to 10	0 to 5
	$(M_2/e^{O+}R_2/f^{O-})/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0.01 to 20	0.05 to 5
10	$M_2/e^{O-}/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0 to 10	0 to 5
	$R_2/f^{O-}/$ $(YO_2+WO+Z_2O_5+X_2O_3)$	0.1 to 2.0	0.12 to 1.0

15 where e and f are the weighted average valences of M and R, respectively.

In this second method, when no Z and/or W oxides are added to the reaction mixture, the pH is important and must be maintained at from 9 to 14. When Z and/or W oxides are present in the reaction mixture, the
20 precise value of the pH is not important for crystallization.

A third method for synthesis of the crystalline material is where X comprises aluminum and Y comprises silicon, the crystallization temperature must be from
25 25° to 175°C, preferably from 50° to 150°C, and an organic directing agent, described below, or, preferably a combination of that organic directing agent plus an additional organic agent, described below, is used. This third method comprises preparing
30 a reaction mixture containing sources of, for example,



alkali or alkaline earth metal (M), e.g. sodium or potassium, cation if desired, one or more sources of aluminum and/or silicon, an organic (R) directing agent, hereinafter more particularly described, and a solvent or solvent mixture, such as, for example C₁-C₆ alcohols, C₁-C₆ diols and/or water, especially water. The reaction mixture has a composition, in terms of mole ratios of oxides, within the following ranges:


	<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
10	Al ₂ O ₃ /SiO ₂	0 to 0.5	0.001 to 0.5
	Solvent/SiO ₂	1 to 1500	5 to 1000
	OH ⁻ /SiO ₂	0 to 10	0 to 5
	(M ₂ /e ^O +R ₂ /f ^O)/ (SiO ₂ +Al ₂ O ₃)	0.01 to 20	0.05 to 5
15	M ₂ /e ^O / (SiO ₂ +Al ₂ O ₃)	0 to 5	0 to 3
	R ₂ /f ^O / (SiO ₂ +Al ₂ O ₃)	0.01 to 2	0.03 to 1

where e and f are the weighted average valences of M and R, respectively.

In this third method, the pH is important and must be maintained at from 9 to 14. This method involves the following steps:

(1) Mix the organic (R) directing agent with the solvent or solvent mixture such that the mole ratio of solvent/R₂/f^O is within the range of from 50 to 800, preferably from 50 to 500. This mixture constitutes the "primary template" for the synthesis method.

(2) To the primary template mixture of step (1) add the sources of oxides, e.g. silica and/or alumina



such that the ratio of $R_{2/f}O/(SiO_2+Al_2O_3)$ is within the range of from 0.01 to 2.0.

5 (3) Agitate the mixture resulting from step (2) at a temperature of from 20° to 40°C, preferably for from 5 minutes to 3 hours.

(4) Allow the mixture to stand with or without agitation, preferably at a temperature of from 20° to 100°C, and preferably for from 10 minutes to 24 hours.

10 (5) Crystallize the product from step (4) at a temperature of from 50° to 175°C, preferably for from 1 hour to 72 hours. Crystallization temperatures higher in the given ranges are most preferred.


A fourth method for the present synthesis involves the reaction mixture used for the third method, but the
15 following specific procedure with tetraethylorthosilicate the source of silicon oxide:

(1) Mix the organic (R) directing agent with the solvent or solvent mixture such that the mole ratio of solvent/ $R_{2/f}O$ is within the range of from 50 to 800,
20 preferably from 50 to 500. This mixture constitutes the "primary template" for the synthesis method.

(2) Mix the primary template mixture of step (1) with tetraethylorthosilicate and a source of aluminum oxide, if desired, such that the $R_{2/f}O/SiO_2$ mole ratio
25 is in the range of from 0.5 to 2.0.

(3) Agitate the mixture resulting from step (2) for from 10 minutes to 6 hours, preferably from 30 minutes to 2 hours, at a temperature of from 0° to 25°C, and a pH of less than 12. This step permits
30 hydrolysis/ polymerization to take place and the resultant mixture will appear cloudy.

(4) Crystallize the product from step (3) at a temperature of from 25° to 150°C, preferably from 95°




to 110°C, for from 4 to 72 hours, preferably from 16 to 48 hours.

In each of the above methods, batch crystallization of the crystalline material can be carried out under either static or agitated, e.g. stirred, conditions in a suitable reactor vessel, such as for example, polypropylene jars or teflon lined or stainless steel autoclaves. Crystallization may also be conducted continuously in suitable equipment. The total useful range of temperatures for crystallization is noted above for each method for a time sufficient for crystallization to occur at the temperature used, e.g. from 5 minutes to 14 days. The crystals are then separated from the liquid and recovered. Following the synthesis, the crystalline material should be subjected to treatment to remove part or all of any organic constituent.

When a source of silicon is used in the synthesis method, it is preferred to use at least in part an organic silicate, such as, for example, a quaternary ammonium silicate. Non-limiting examples of such a silicate include tetramethylammonium silicate and tetraethylorthosilicate.

By adjusting conditions of the synthesis reaction for each method, like temperature, pH and time of reaction, etc., within the above limits, various embodiments of the present non-layered crystalline material with a desired average pore size may be prepared. In particular, changing the pH, the temperature or the reaction time may promote formation of product crystals with different average pore size.




Non-limiting examples of various combinations of W, X, Y and Z contemplated for the first and second synthesis methods include:


	W	X	Y	Z
5	--	Al	Si	--
	--	Al	--	P
	--	Al	Si	P
	Co	Al	--	P
	Co	Al	Si	P
10	--	--	Si	--

including the combinations of W being Mg, or an element selected from the divalent first row transition metals, e.g. Mn, Co and Fe; X being B, Ga or Fe; and Y being Ge.

15 An organic directing agent for use in each of the above methods for synthesizing the present material from the respective reaction mixtures is an ammonium or phosphonium ion of the formula $R_1R_2R_3R_4Q^+$, i.e.:



25 ny where Q is nitrogen or phosphorus and wherein at least one of R_1 , R_2 , R_3 and R_4 is aryl or alkyl of from 6 to 36 carbon atoms, e.g. $-C_6H_{13}$, $-C_{10}H_{21}$, $-C_{16}H_{33}$ and $-C_{18}H_{37}$, or combinations thereof, the remainder of R_1 , R_2 , R_3 and R_4 being selected from hydrogen, alkyl of
 30 from 1 to 5 carbon atoms and combinations of these. The compound from which the above ammonium or




phosphonium ion is derived may be, for example, the hydroxide, halide, silicate, or mixtures of these.

5 In the first and third methods above it is preferred to have an additional organic directing agent and in the second method it is required to have a combination of the above organic directing agent and an additional organic directing agent. That additional organic directing agent is the ammonium or phosphonium ion of the above directing agent formula wherein R_1 ,
10 R_2 , R_3 and R_4 together or separately are selected from the group consisting of hydrogen and alkyl of 1 to 5 carbon atoms and combinations thereof. Any such combination of organic directing agents go to make up "R" and will be in molar ratio of 100/1 to 0.01/1,
15 first above listed organic directing agent/additional organic directing agent.

The particular effectiveness of the required directing agent, when compared with other such agents known to direct synthesis of one or more other crystal
20 structures, is believed due to its ability to function as a template in the above reaction mixture in the nucleation and growth of the desired ultra-large pore crystals with the limitations discussed above. Non-limiting examples of these directing agents include
25 cetyltrimethylammonium, cetyltrimethylphosphonium, benzyltrimethylammonium, cetylpyridinium, myristyltrimethylammonium, decyltrimethylammonium, dodecyltrimethylammonium and dimethyldidodecylammonium.

30 The reaction mixture components can be supplied by more than one source. The reaction mixture can be prepared either batchwise or continuously. Crystal size and crystallization time of the new crystalline




material will vary with the nature of the reaction mixture employed and the crystallization conditions.

The crystals prepared by the synthesis procedure can be shaped into a wide variety of particle sizes. Generally speaking, the particles can be in the form of a powder, a granule, or a molded product, such as an extrudate having particle size sufficient to pass through a 2 mesh (Tyler) screen and be retained on a 400 mesh (Tyler) screen. In cases where the catalyst is molded, such as by extrusion, the crystals can be extruded before drying or partially dried and then extruded.

The size of the pores in the present mesoporous catalytic materials is large enough that the spatioselectivity with respect to transition state species in reactions such as cracking is minimized (Chen et al., "Shape Selective Catalysis in Industrial Applications", 36 CHEMICAL INDUSTRIES, pgs. 41-61 (1989) to which reference is made for a discussion of the factors affecting shape selectivity). Diffusional limitations are also minimized as a result of the very large pores.


The crystals of the mesoporous support material will be composited with a matrix material which is resistant to the temperatures and other conditions employed in the hydrogenation process to form the finished catalyst. Such materials include active and inactive materials and synthetic or naturally occurring zeolites as well as inorganic materials such as clays and/or oxides such as alumina, silica or silica-alumina. The latter may be either naturally occurring or in the form of gelatinous precipitates or gels including mixtures of silica and metal oxides.



Use of a material in conjunction with the zeolite, i.e., combined therewith or present during its synthesis, which itself is catalytically active may change the conversion and/or selectivity of the catalyst. Inactive materials suitably serve as diluents to control the amount of conversion so that alkylation products can be obtained economically and orderly without employing other means for controlling the rate of reaction. These materials may be incorporated into naturally occurring clays, e.g., bentonite and kaolin, to improve the crush strength of the catalyst under commercial operating conditions and function as binders or matrices for the catalyst. The mesoporous material is usually composited with the matrix in amounts from 80:20 to 20:80 by weight, typically from 80:20 to 50:50 mesoporous material:matrix. Compositing may be done by conventional means including mulling the materials together followed by extrusion of pelletizing into the desired finished catalyst particles.

The preferred catalysts for the present purpose have a significant pore volume with pore diameters greater than 20 nm (200 Å). The large diameter pores provide channels for bulky PAO oligomers to transport freely with diminished diffusion resistance to the smaller particles of the crystalline material which provide a large surface area for the hydrogenation reaction. A number of commercially available alumina binders conform to this requirement and may be used. The pore size distributions of three are set out below.

Consistent with the requirement to permit the lube molecules to obtain ready, diffusion-free access to the crystalline material which acts as the support for the




metal component which performs the essential hydrogenation function, the binder should have a pore size and distribution which is adequate to permit the feed components to enter the interior pore structure of the catalyst where the desired hydrogenation reactions take place at the metal sites on the crystalline material. To this extent, the binder will normally have a minimum pore size of 5.0 nm (50 Å), i.e with no less than 5% of the pores having a pore size less than 5.0 nm (50 Å) pore size, with the majority of the pores having a pore size in the range of 5.0 to 50 nm (50-400 Å) (no more than 5% having a pore size above 40 nm (400 Å)), preferably with no more than 30% having pore sizes in the range of 20 to 40 nm (200-400 Å).

Metal Component


Catalyst Metal Component

The hydrogenation catalyst includes a metal as the hydrogenation- dehydrogenation component. The hydrogenation-dehydrogenation component is provided by a metal or combination of metals. Noble metals of Group VIIIA, especially palladium, platinum, or base metals of Groups IVA, VIA and VIIIA, especially chromium, molybdenum, tungsten, cobalt and nickel, may be used. The combination of at least one Group VIA metal such as tungsten with at least one Group VIIA metal such as nickel is particularly preferred for many applications, for example, combinations such as nickel-molybdenum, cobalt-nickel, nickel-tungsten, cobalt-nickel-molybdenum and nickel-tungsten-titanium. For certain applications, where sulfur and other contaminants such as phosphorus are in low



concentrations in the feedstock, e.g. <10 ppm, palladium or platinum is preferred.

5 The content of the metal component will vary according to its catalytic activity. Thus, the highly active noble metals may be used in smaller amounts than the less active base metals. For example, 1 wt % or less palladium or platinum will be effective and in a preferred base metal combination, 7 wt % nickel and 2.1 to 21 wt % tungsten, expressed as metal. The present support materials are, however, notable in that they are capable of including a greater proportion of metal than previous support materials because of their extraordinarily large surface area. The metal component may exceed 30% in a monolayer. The hydrogenation component can be exchanged onto the support material, impregnated into it or physically admixed with it. If the metal is to be impregnated into or exchanged onto the mesoporous support, it may be done, for example, by treating the zeolite with a palladium or platinum metal-containing ion. Suitable platinum compounds include chloroplatinic acid, platinumous chloride and various compounds containing the platinum ammine complex. The metal compounds may be either compounds in which the metal is present in the cation of the compound and compounds in which it is present in the anion of the compound. Both types of compounds can be used. Palladium or platinum compounds in which the metal is in the form of a cation of cationic complex, e.g., $\text{Pd}(\text{NH}_3)_4\text{Cl}_2$ or $\text{Pt}(\text{NH}_3)_4\text{Cl}_2$ are particularly useful, as are anionic complexes such as the vanadate and metatungstate ions. Cationic forms of other metals are also very useful since they may be




exchanged onto the crystalline material or impregnated into it.

Examples

5 Examples 1 to 19 below illustrate the preparation of the mesoporous crystalline materials used to prepare the catalysts. In these examples, the sorption data for water, cyclohexane, benzene and/or n-hexane, they are Equilibrium Adsorption values determined as follows:

10 A weighed sample of the adsorbent, after calcination at 540°C for at least 1 hour and other treatment, if necessary, to remove any pore blocking contaminants, is contacted with the desired pure adsorbate vapor in an adsorption chamber. The increase
15 in weight of the adsorbent is calculated as the adsorption capacity of the sample in terms of grams/100 grams adsorbent based on adsorbent weight after calcination at 540°C. The present composition exhibits an equilibrium benzene adsorption capacity at 6.7 kPa
20 (50 Torr) and 25°C of greater than 15 grams/100 grams, particularly greater than 17.5 g/100 g/ and more particularly greater than 20 g/100 g.

25 A preferred way to do this is to contact the desired pure adsorbate vapor in an adsorption chamber evacuated to less than 1 mm at conditions of 1.6 kPa (12 Torr) of water vapor, 5.3 kPa (40 Torr) of n-hexane or cyclohexane vapor, or 6.7 kPa (50 Torr) of benzene
30 vapor, at 25°C. The pressure is kept constant (within ± 0.5 mm) by addition of adsorbate vapor controlled by a manostat during the adsorption period. As adsorbate is adsorbed by the new crystal, the decrease in




pressure causes the manostat to open a valve which admits more adsorbate vapor to the chamber to restore the above control pressures. Sorption is complete when the pressure change is not sufficient to activate the manostat.

Another way of doing this for benzene adsorption data is on a suitable thermogravimetric analysis system, such as a computer-controlled 990/951 duPont TGA system. The adsorbent sample is dehydrated (physically sorbed water removed) by heating at, for example, 350° or 500°C to constant weight in flowing helium. If the sample is in as-synthesized form, e.g. containing organic directing agents, it is calcined at 540°C in air and held to constant weight instead of the previously described 350° or 500°C treatment. Benzene adsorption isotherms are measured at 25°C by blending a benzene saturated helium gas stream with a pure helium gas stream in the proper proportions to obtain the desired benzene partial pressure. The value of the adsorption at 6.7 kPa (50 Torr) of benzene is taken from a plot of the adsorption isotherm.

In the examples, percentages are by weight unless otherwise indicated.

Example 1

One hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution, prepared by contacting a 29 wt % N,N,N- trimethyl-1-hexadecanaminium chloride solution with a hydroxide-for-halide exchange resin, was combined with 100 grams of an aqueous solution of tetramethylammonium (TMA) silicate (10% silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt



5 % bound water of hydration and having an ultimate particle size of 0.02 micron, was added. The resulting mixture was placed in a polypropylene bottle, which was placed in a steam box at 95°C overnight. The mixture had a composition in terms of moles per mole Al_2O_3 :


2.7 moles Na_2O
392 moles SiO_2
35.7 moles $(\text{CTMA})_2\text{O}$
61.7 moles $(\text{TMA})_2\text{O}$
10 6231 moles H_2O

The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

15 The calcined product proved to have a surface area of 475 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

	H_2O	8.3
	Cyclohexane	22.9
20	n-Hexane	18.2
	Benzene	21.5

25 The product of this example may be characterized by X-ray diffraction as including a very strong relative intensity line at 37.8 ± 2.0 Å d-spacing, and weak lines at 21.6 ± 1.0 and 19.2 ± 1.0 Å. Transmission electron microscopy (TEM) produced images of a hexagonal arrangement of uniform pores and hexagonal electron diffraction pattern with a d_{100} value of 39 Å.



Example 2


One hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 100 grams of an aqueous solution of tetramethylammonium (TMA) hydroxide (25%) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of 0.02 micron, was added. The resulting mixture was placed in a static autoclave at 150°C overnight. The mixture had a composition in terms of moles per mole Al_2O_3 :

2.7 moles Na_2O
291 moles SiO_2
35.7 moles $(\text{CTMA})_2\text{O}$
102 moles $(\text{TMA})_2\text{O}$
6120 moles H_2O

The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

The calcined product proved to have a surface area of 993 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

H_2O	7.1
Cyclohexane	47.2
n-Hexane	36.2
Benzene	49.5



The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 39.3 ± 2.0 Å d-spacing, and weak lines at 22.2 ± 1.0 and 19.4 ± 1.0 Å. TEM indicated that the product contained the ultra-large pore material.

A portion of the above product was then contacted with 100% steam at 1450°F for two hours. The surface area of the steamed material was measured to be 440 m²/g, indicating that 45% was retained following severe steaming.


Another portion of the calcined product of this example was contacted with 100% steam at 677°C (1250°F) for two hours. The surface area of this material was measured to be 718 m²/g, indicating that 72% was retained after steaming at these conditions.

Example 3

Water, cetyltrimethylammonium hydroxide solution prepared as in Example 1, aluminum sulfate, HiSil and an aqueous solution of tetrapropylammonium (TPA) bromide (35%) were combined to produce a mixture having a composition in terms of moles per mole Al₂O₃:

0.65 moles Na₂O
65 moles SiO₂
8.8 moles (CTMA)₂O
1.22 moles (TPA)₂O
1336 moles H₂O

The resulting mixture was placed in a polypropylene bottle, which was kept in a steam box at



95°C for 192 hours. The sample was then cooled to room temperature and combined with CTMA hydroxide solution prepared as in Example 1 and TMA hydroxide (25% by weight) in the weight ratio of 3 parts mixture, 1 part CTMA hydroxide and 2 parts TMA hydroxide. The combined mixture was then placed in a polypropylene bottle and kept in a steam box at 95°C overnight. The combined mixture had a composition in terms of moles per mole Al_2O_3 :


10	0.65 moles Na_2O
	65 moles SiO_2
	15 moles $(\text{CTMA})_2\text{O}$
	1.22 moles $(\text{TPA})_2\text{O}$
	35.6 moles $(\text{TMA})_2\text{O}$
15	2927 moles H_2O

The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

20 The calcined product proved to have a surface area of $1085 \text{ m}^2/\text{g}$ and the following equilibrium adsorption capacities in grams/100 grams:

	H_2O	11.5
	Cyclohexane	> 50
25	n-Hexane	39.8
	Benzene	62

The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 38.2



± 2.0 Å d-spacing, and weak lines at 22.2 ± 1.0 and 19.4 ± 1.0 Å. TEM indicated the product contained the ultra-large pore material.


Example 4

5 Two hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 2 grams of Catapal alumina (alpha-alumina monohydrate, 74% alumina) and 100 grams of an aqueous
10 solution of tetramethylammonium (TMA) silicate (10% silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of 0.02 micron, was added. The resulting mixture was placed in a static autoclave
15 at 150°C for 48 hours. The mixture had a composition in terms of moles per mole Al_2O_3 :

0.23 moles Na_2O
33.2 moles SiO_2
6.1 moles $(\text{CTMA})_2\text{O}$
20 5.2 moles $(\text{TMA})_2\text{O}$
780 moles H_2O

 The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in
25 nitrogen, followed by 6 hours in air.

 The calcined product proved to have a surface area of $1043 \text{ m}^2/\text{g}$ and the following equilibrium adsorption capacities in grams/100 grams:




H ₂ O	6.3
Cyclohexane	> 50
n-Hexane	49.1
Benzene	66.7

5 The X-ray diffraction pattern of the calcined
product may be characterized as including a very strong
relative intensity line at 40.8 ± 2.0 Å d-spacing, and
weak lines at 23.1 ± 1.0 and 20.1 ± 1.0 Å. TEM
10 indicated that the product contained the ultra-large
pore material.

Example 5

Two-hundred sixty grams of water was combined with
77 grams of phosphoric acid (85%), 46 grams of Catapal
alumina (74% alumina), and 24 grams of pyrrolidine
15 (Pyr) with stirring. This first mixture was placed in
a stirred autoclave and heated to 150°C for six days.
The material was filtered, washed and air-dried. Fifty
grams of this product was slurried with 200 grams of
water and 200 grams of cetyltrimethylammonium hydroxide
20 solution prepared as in Example 1. Four hundred grams
of an aqueous solution of tetraethylammonium silicate
(10% silica) was then added to form a second mixture
which was placed in a polypropylene bottle and kept in
a steam box at 95°C overnight. The first mixture had a
25 composition in terms of moles per mole Al₂O₃:

1.0 moles P₂O₅
0.51 moles (Pyr)₂O
47.2 moles H₂O



The resulting solid product was recovered by filtration and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.


5 The calcined product proved to have a surface area of 707 m²/g and the following equilibrium adsorption capacities in grams/100 grams:

	H ₂ O	33.2
	Cyclohexane	19.7
10	n-Hexane	20.1
	Benzene	23.3

15 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 25.4 ± 1.5 Å d-spacing. TEM indicated the product contained the present ultra-large pore material.

Example 6

20 A solution of 1.35 grams of NaAlO₂ (43.5% Al₂O₃, 30% Na₂O) dissolved in 45.2 grams of water was mixed with 17.3 grams of NaOH, 125.3 grams of colloidal silica (40%, Ludox HS-40) and 42.6 grams of 40% aqueous solution of tetraethylammonium (TEA) hydroxide. After stirring overnight, the mixture was heated for 7 days in a steam box (95°C). Following filtration, 151 grams of this solution was mixed with 31 grams of cetyltri-
25 methylammonium hydroxide solution prepared as in Example 1 and stored in the steam box at 95°C for 13 days. The mixture had the following relative molar composition:



0.25 moles Al_2O_3
10 moles Na_2O
36 moles SiO_2
0.95 moles $(\text{CTMA})_2\text{O}$
2.5 moles $(\text{TEA})_2\text{O}$
445 moles H_2O

5

The resulting solid product was recovered by filtration and washed with water and ethanol. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

10

The calcined product composition included 0.14 wt % Na, 68.5 wt % SiO_2 and 5.1 wt % Al_2O_3 , and proved to have a benzene equilibrium adsorption capacity of 58.6 grams/100 grams.

15

The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at $31.4 \pm 1.5 \text{ \AA}$ d-spacing. TEM indicated that the product contained the present ultra-large pore material.


20

Example 7

A mixture of 300 grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 and 41 grams of colloidal silica (40%, Ludox HS-40) was heated in a 600 cc autoclave at 150°C for 48 hours with stirring at 200 rpm. The mixture has a composition in terms of moles per mole SiO_2 :

25

0.5 mole $(\text{CTMA})_2\text{O}$
46.5 moles H_2O



The resulting solid product was recovered by filtration, washed with water, then calcined at 540°C for 1 hour in nitrogen, followed by 10 hours in air.

5 The calcined product composition included less than 0.01 wt % Na, 98.7 wt % SiO₂ and 0.01 wt % Al₂O₃, and proved to have a surface area of 896 m²/g. The calcined product had the following equilibrium adsorption capacities in grams/100 grams:


10	H ₂ O	8.4
	Cyclohexane	49.8
	n-Hexane	42.3
	Benzene	55.7

15 The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 40.0 ± 2.0 Å d-spacing and a weak line at 21.2 ± 1.0 Å. TEM indicated that the product of this example contained at least three separate phases, one of which was the ultra-large pore material.

20 Example 8

25 A mixture of 150 grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 and 21 grams of colloidal silica (40%, Ludox HS-40) with an initial pH of 12.64 was heated in a 300 cc autoclave at 150°C for 48 hours with stirring at 200 rpm. The mixture had a composition in terms of moles per mole SiO₂:

0.5 mole (CTMA)₂O
46.5 moles H₂O



The resulting solid product was recovered by filtration, washed with water, then calcined at 540°C for 6 hours in air.

5 The calcined product composition was measured to include 0.01 wt % Na, 93.2 wt % SiO₂ and 0.016 wt % Al₂O₃, and proved to have a surface area of 992 m²/g and the following equilibrium adsorption capacities in grams/100 grams:


	H ₂ O	4.6
10	Cyclohexane	> 50
	n-Hexane	> 50
	Benzene	62.7

15 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 43.6 ± 2.0 Å d-spacing and weak lines at 25.1 ± 1.5 and 21.7 ± 1.0 Å. TEM indicated that the product contained the ultra-large pore material.

Example 9

20 Sodium aluminate (4.15g) was added slowly into a solution containing 16g of myristyltrimethylammonium bromide (C₁₄TMABr) in 100g of water. Tetramethyl-
25 ammonium silicate (100g-10% SiO₂), HiSil (25g) and tetramethylammonium hydroxide (14.2g-25% solution) were then added to the mixture. The mixture was
crystallized in an autoclave at 120°C with stirring for 24 hours.

30 The product was filtered, washed and air dried. Elemental analysis showed the product contained 53.3 wt % SiO₂, 3.2 wt % Al₂O₃, 15.0 wt % C, 1.88 wt % N, 0.11



wt % Na and 53.5 wt % ash at 1000°C. The X-ray diffraction pattern of the material after calcination at 540°C for 1 hour in N₂ and 6 hours in air includes a very strong relative intensity line at 35.3 ± 2.0 Å d-spacing and weak lines at 20.4 ± 1.0 and 17.7 ± 1.0 Å d-spacing. TEM indicated that the product contained the ultra-large pore material.


The washed product, having been exchanged with 1N ammonium nitrate solution at room temperature, then calcined, proved to have a surface area of 827 m²/g and the following equilibrium adsorption capacities in g/100g anhydrous sorbent:

	H ₂ O	30.8
	Cyclohexane	33.0
15	n-Hexane	27.9
	Benzene	40.7

Example 10

Sodium aluminate (8.3g) was added slowly into a solution containing 184g of dodecyltrimethylammonium hydroxide (C₁₂TMAOH, 50%) solution diluted with 480g of water. UltraSil (50g) and an aqueous solution of tetramethylammonium silicate (200g-10% SiO₂) and tetramethylammonium hydroxide (26.38g-25% solution) were then added to the mixture. The mixture was crystallized in an autoclave at 100°C with stirring for 24 hours.

The product was filtered, washed and air dried. After calcination at 540°C for 1 hour in N₂ and 6 hours in air, the X-ray diffraction pattern includes a very strong relative intensity line at 30.4 ± 1.5 Å d-spacing and weak lines at 17.7 ± 1.0 and 15.3 ± 1.0



A d-spacing. TEM indicated that the product contained the ultra-large pore material.

5 The washed product, having been exchanged with 1N ammonium nitrate solution at room temperature, then calcined, proved to have a surface area of $1078 \text{ m}^2/\text{g}$ and the following equilibrium adsorption capacities in g/100g anhydrous sorbent:


	H_2O	32.6
	Cyclohexane	38.1
10	n-Hexane	33.3
	Benzene	42.9

Example 11

15 A solution of 4.9 grams of NaAlO_2 (43.5 % Al_2O_3 , 30% NaO_2) in 37.5 grams of water was mixed with 46.3 cc of 40% aqueous tetraethylammonium hydroxide solution and 96 grams of colloidal silica (40%, Ludox HS-40). The gel was stirred vigorously for 0.5 hour, mixed with an equal volume (150 ml) of cetyltrimethylammonium hydroxide solution prepared as in Example 1 and reacted
20 at 100°C for 168 hours. The mixture had the following composition in terms of moles per mole Al_2O_3 :

	1.1 moles Na_2O
	30.6 moles SiO_2
	3.0 moles $(\text{TEA})_2\text{O}$
25	3.25 moles $(\text{CTMA})_2\text{O}$
	609 moles H_2O

The resulting solid product was recovered by filtration, washed with water then calcined at 540°C for 16 hours in air. The calcined product proved to



have a surface area of 1352 m²/g and the following equilibrium adsorption capacities in grams/100 grams:


	H ₂ O	23.6
	Cyclohexane	>50
5	n-Hexane	49
	Benzene	67.5

The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 38.5 ± 2.0 Å d-spacing and a weak line at 20.3 ± 1.0 Å. TEM indicated that the product contained the ultra-large pore material.

Example 12

Two hundred grams of cetyltrimethylammonium (CTMA) hydroxide solution prepared as in Example 1 was combined with 4.15 grams of sodium aluminate and 100 grams of aqueous tetramethylammonium (TMA) silicate solution (10% silica) with stirring. Twenty-five grams of HiSil, a precipitated hydrated silica containing 6 wt % free water and 4.5 wt % bound water of hydration and having an ultimate particle size of 0.02 μm, was added. The resulting mixture was placed in a static autoclave at 150°C for 24 hours. The mixture had a composition in terms of moles per mole Al₂O₃:

	1.25 moles Na ₂ O
	27.8 moles SiO ₂
	5.1 moles (CTMA) ₂ O
	4.40 moles (TMA) ₂ O
25	650 moles H ₂ O




5 The resulting solid product was recovered by
filtration and dried in air at ambient temperature.
The product was then calcined at 540°C for 1 hour in
nitrogen, followed by 6 hours in air. TEM indicated
that this product contained the ultra-large pore
material. The X-ray diffraction pattern of
the calcined product of this example can be
characterized as including a very strong relative
intensity line at 44.2 ± 2.0 Å d-spacing and weak lines
10 at 25.2 ± 1.5 and 22.0 ± 1.0 Å.

The calcined product proved to have a surface area
of 932 m²/g and the following equilibrium adsorption
capacities in grams/100 grams:

15	H ₂ O	39.3
	Cyclohexane	46.6
	n-Hexane	37.5
	Benzene	50

Example 13

20 Two hundred grams of cetyltrimethylammonium (CTMA)
hydroxide solution prepared as in Example 1 was
combined with 4.15 grams of sodium aluminate and 100
grams of aqueous tetramethylammonium (TMA) silicate
solution (10% silica) with stirring. Twenty-five grams
25 of HiSil, a precipitated hydrated silica containing 6
wt % free water and 4.5 wt % bound water of hydration
and having an ultimate particle size of 0.02 micron,
was added. The resulting mixture was placed in a steam
box at 100°C for 48 hours. The mixture had a
composition in terms of moles per mole Al₂O₃:



5 1.25 moles Na_2O
 27.8 moles SiO_2
 5.1 moles $(\text{CTMA})_2\text{O}$
 4.4 moles $(\text{TMA})_2\text{O}$
 650 moles H_2O


10 The resulting solid product was recovered by
 filtration and dried in air at ambient temperature.
 The product was then calcined at 540°C for 1 hour in
 nitrogen, followed by 6 hours in air. The calcined
 product proved to have the following equilibrium
 adsorption capacities in grams/100 grams:

15 H_2O 35.2
 Cyclohexane > 50
 n-Hexane 40.8
 Benzene 53.5

20 The X-ray diffraction pattern of the calcined
 product may be characterized as including a very strong
 relative intensity line at 39.1 ± 2.0 Å d-spacing and
 weak lines at 22.4 ± 1.0 and 19.4 ± 1.0 Å. TEM
 indicated that this product contained the ultra-large
 pore material.

Example 14

25 A mixture of 125 grams of 29% CTMA chloride
 aqueous solution, 200 grams of water, 3 grams of sodium
 aluminate (in 50 grams H_2O), 65 grams of Ultrasil,
 amorphous precipitated silica available from PQ
 Corporation, and 21 grams NaOH (in 50 grams H_2O) was
 stirred thoroughly and crystallized at 150°C for 168



mole ratio was 6. To the primary template mixture was added 4.15 grams of sodium aluminate, 25 grams of HiSil, 100 grams of aqueous tetramethylammonium silicate solution (10% SiO_2) and 13.2 grams of 25% aqueous tetramethylammonium hydroxide solution. The mole ratio of $\text{R}_2/\text{fO}/(\text{SiO}_2 + \text{Al}_2\text{O}_3)$ was 0.28 for the mixture.


This mixture was stirred at 25°C for 1 hour. The resulting mixture was then placed in an autoclave at 100°C and stirred at 100 rpm for 24 hours. The mixture in the autoclave had the following relative molar composition in terms of moles per mole SiO_2 :

0.05 mole Na_2O
0.036 mole Al_2O_3
0.18 mole $(\text{C}_{12}\text{TMA})_2\text{O}$
0.12 mole $(\text{TMA})_2\text{O}$
36.0 moles H_2O
1.0 mole IPA

The resulting solid product was recovered by filtration, washed with water and dried in air at ambient temperature. The product was then calcined at 540°C for 1 hour in nitrogen, followed by 6 hours in air.

The calcined product proved to have a surface area of 1223 m^2/g and the following equilibrium adsorption capacities in grams/100 grams:

H_2O	25.5
Cyclohexane	41.1
n-Hexane	35.1
Benzene	51



hours. The reaction mixture had the following relative molar composition in terms of moles per mole silica:

5 0.10 moles (CTMA)₂O
 21.89 moles H₂O
 0.036 moles NaAlO₂
 0.53 moles NaOH


10 The solid product was isolated by filtration, washed with water, dried for 16 hours at room temperature and calcined at 540°C for 10 hours in air. The calcined product proved to have a surface area of 840 m²/g, and the following equilibrium adsorption capacities in grams/100 grams:

15 H₂O 15.2
 Cyclohexane 42.0
 n-Hexane 26.5
 Benzene 62

20 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 40.5 ± 2.0 Å d-spacing. TEM indicated that the product contained the ultra-large pore material.

Example 15

25 To make the primary template mixture for this example, 240 grams of water was added to a 92 gram solution of 50% dodecyltrimethylammonium hydroxide, 36% isopropyl alcohol and 14% water such that the mole ratio of Solvent/R₂/f⁰ was 155. The mole ratio of H₂O/R₂/f⁰ in this mixture was 149 and the IPA/R₂/f⁰



5 The X-ray diffraction pattern of the calcined product may be characterized as including a very strong relative intensity line at 30.8 ± 1.5 Å d-spacing and weak lines at 17.9 ± 1.0 and 15.5 ± 1.0 Å. TEM indicated this product to contain the ultra-large pore material.


Example 16

10 A 50.75 gram quantity of decyltrimethylammonium hydroxide (prepared by contacting a ca. 29 wt % solution of decyltrimethylammonium bromide with a hydroxide-for-halide exchange resin) was combined with 8.75 grams of tetraethylorthosilicate. The mixture was stirred for 1 hour and then transferred to a polypropylene jar which was then placed in a steambox
15 for 24 hours. The mixture had a composition in terms of moles per mole SiO_2 :

0.81 mole $(\text{C}_{10}\text{TMA})_2\text{O}$
47.6 moles H_2O

20 The resulting solid product was filtered and washed several times with warm ($60^\circ\text{--}70^\circ\text{C}$) distilled water and with acetone. The final product was calcined to 538°C in N_2 /air mixture and then held in air for 8 hours. The calcined product proved to have a surface area of $915 \text{ m}^2/\text{g}$ and an equilibrium benzene adsorption
25 capacity of 35 grams/100 grams. Argon physisorption data indicated an argon uptake of 0.34 cc/gram, and a pore size of 1.5 nm (15 Å).

30 The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 27.5




± 1.5 Å d-spacing and weak lines at 15.8 ± 1.0 and 13.7 ± 1.0 Å. TEM indicated that the product of this example contained the ultra-large pore material.

Example 17

5 To eighty grams of cetyltrimethylammonium
hydroxide (CTMAOH) solution prepared as in Example 1
was added 1.65 grams of NaAlO_2 . The mixture was
stirred at room temperature until the NaAlO_2 was
dissolved. To this solution was added 40 grams of
10 aqueous tetramethylammonium (TMA) silicate solution (10
wt % SiO_2), 10 grams of HiSi1 , 200 grams of water and
70 grams of 1,3,5-trimethylbenzene (mesitylene). The
resulting mixture was stirred at room temperature for
several minutes. The gel was then loaded into a 600 ml
15 autoclave and heated at 105°C for sixty-eight hours
with stirring at 150 rpm. The mixture had a
composition in terms of moles per mole Al_2O_3 :

1.25 moles Na_2O
27.8 moles SiO_2
20 5.1 moles $(\text{CTMA})_2\text{O}$
2.24 moles $(\text{TMA})_2\text{O}$
2256 moles H_2O
80.53 moles 1,3,5-trimethylbenzene


25 The resulting product was filtered and washed
several times with warm ($60^\circ\text{--}70^\circ\text{C}$) distilled water and
with acetone. The final product was calcined to 538°C
in N_2 /air mixture and then held in air for 10 hours.
The calcined product proved to have an equilibrium
benzene adsorption capacity of >25 grams/100 grams.



The X-ray diffraction pattern of the calcined product may be characterized as including a broad, very strong relative intensity line at 102 Å d-spacing, but accurate positions of lines in the extreme low angle region of the X-ray diffraction pattern are very difficult to determine with conventional X-ray diffractometers. Furthermore, finer collimating slits were required to resolve a peak at this low 2-theta angle. The slits used in this example, starting at the X-ray tube, were 0.1, 0.3, 0.5 and 0.2 mm, respectively. TEM indicated that the product of this example contained several materials with different d_{100} values as observed in their electron diffraction patterns. These materials were found to possess d_{100} values between 8.5 nm (85 Å) d-spacing and 12 nm (120 Å) d-spacing.

Example 18

To eighty grams of cetyltrimethylammonium hydroxide (CTMAOH) solution prepared as in Example 1 was added 1.65 grams of NaAlO_2 . The mixture was stirred at room temperature until the NaAlO_2 was dissolved. To this solution was added 40 grams of aqueous tetramethylammonium (TMA) silicate solution (10 wt % SiO_2), 10 grams of HiSil, 200 grams of water and 120 grams of 1,3,5-trimethylbenzene (mesitylene). The resulting mixture was stirred at room temperature for several minutes. The gel was then loaded into a 600 ml autoclave and heated at 105°C for ninety hours with stirring at 150 rpm. The mixture had a composition in terms of moles per mole Al_2O_3 :




1.25 moles Na_2O
27.8 moles SiO_2
5.1 moles $(\text{CTMA})_2\text{O}$
2.24 moles $(\text{TMA})_2\text{O}$
5 2256 moles H_2O
132.7 moles 1,3,5-trimethylbenzene

The resulting product was filtered and washed several times with warm (60-70°C) distilled water and with acetone. The final product was calcined to 538°C
10 in N_2 /air mixture and then held in air for 10 hours. The calcined product proved to have a surface area of 915 m^2/g and an equilibrium benzene adsorption capacity of >25 grams/100 grams. Argon physisorption data
15 indicated an argon uptake of 0.95 cc/gram, and a pore size centered on 7.8 nm (78 Å) (Dollimore-Heal Method, see Example 22(b)), but running from 7 to greater than 10.5 nm (70 to greater than 105 Angstroms). The X-ray
20 diffraction pattern of the calcined product of this example may be characterized as having only enhanced scattered intensity in the very low angle region of the X-ray diffraction, where intensity from the transmitted
incident X-ray beam is usually observed. However, TEM indicated that the product contained several materials
25 with different d_{100} values as observed in their electron diffraction patterns. These materials were found to possess d_{100} values between 85 Å d-spacing and 110 Å d-spacing.

Example 19

To eighty grams of cetyltrimethylammonium
30 hydroxide (CTMAOH) solution prepared as in Example 1 was added 1.65 grams of NaAlO_2 . The mixture was




5 stirred at room temperature until the NaAlO_2 was dissolved. To this solution was added 40 grams of aqueous tetramethylammonium (TMA) silicate solution (10 wt % SiO_2), 10 grams of HiSil, and 18 grams of 1,3,5-trimethylbenzene (mesitylene). The resulting mixture was stirred at room temperature for several minutes. The gel was then loaded into a 300 ml autoclave and heated at 105°C for four hours with stirring at 150 rpm. The mixture had a composition in terms of moles per mole Al_2O_3 :

1.25 moles Na_2O
27.8 moles SiO_2
5.1 moles $(\text{CTMA})_2\text{O}$
2.24 moles $(\text{TMA})_2\text{O}$
15 650 moles H_2O
19.9 moles 1,3,5-trimethylbenzene

The resulting product was filtered and washed several times with warm ($60-70^\circ\text{C}$) distilled water and with acetone. The final product was calcined to 538°C in N_2 /air mixture and then held in air for 8 hours.

20 The calcined product proved to have a surface area of $975 \text{ m}^2/\text{g}$ and an equilibrium benzene adsorption capacity of >40 grams/100 grams. Argon physisorption data indicated an argon uptake of 0.97 ml/gram, and a pore size of 6.3 nm (63 Å) (Dollimore-Heal Method), with the peak occurring at $P/P_0=0.65$.

25 The X-ray diffraction pattern of the calcined product of this example may be characterized as including a very strong relative intensity line at 63 ± 5 Å d-spacing and weak lines at 36.4 ± 2.0 , 31.3 ± 1.5 Å and 23.8 ± 1.0 Å d-spacing. TEM indicated that the




product of this example contained the ultra-large pore material.

Example 20

Argon Physisorption Determination

5 To determine the pore diameters of the mesoporous products with pores up to 6.0 nm (60 Å) in diameter, 0.2 gram samples of the products of Examples 1 through 17 were placed in glass sample tubes and attached to a physisorption apparatus as described in U.S. Patent No.
10 4,762,010.

 The samples were heated to 300°C for 3 hours in vacuo to remove adsorbed water. Thereafter, the samples were cooled to 87°K by immersion of the sample tubes in liquid argon. Metered amounts of gaseous
15 argon were then admitted to the samples in stepwise manner as described in U.S. Patent No. 4,762,010, column 20. From the amount of argon admitted to the samples and the amount of argon left in the gas space above the samples, the amount of argon adsorbed can be
20 calculated. For this calculation, the ideal gas law and the calibrated sample volumes were used. (See also S.J. Gregg et al., Adsorption, Surface Area and Porosity, 2nd ed., Academic Press, 1982). In each
25 instance, a graph of the amount adsorbed versus the relative pressure above the sample, at equilibrium, constitutes the adsorption isotherm. It is common to use relative pressures which are obtained by forming the ratio of the equilibrium pressure and the vapor pressure P_0 of the adsorbate at the temperature where
30 the isotherm is measured. Sufficiently small amounts of argon were admitted in each step to generate 168 data points in the relative pressure range from 0 to



0.6. At least 100 points are required to define the isotherm with sufficient detail.


The step (inflection) in the isotherm, indicates filling of a pore system. The size of the step indicates the amount adsorbed, whereas the position of the step in terms of P/P_0 reflects the size of the pores in which the adsorption takes place. Larger pores are filled at higher P/P_0 . In order to better locate the position of the step in the isotherm, the derivative with respect to $\log (P/P_0)$ is formed. The adsorption peak (stated in terms of $\log (P/P_0)$) may be related to the physical pore diameter ($\text{\AA}$) by the following formula:

$$\log(P/P_0) = \frac{K}{d-0.38} \left[\frac{s^4}{3(L-D/2)^3} - \frac{s^{10}}{9(L-D/2)^9} - \frac{s^4}{3(D/2)^3} + \frac{s^{10}}{9(D/2)^9} \right]$$

where d = pore diameter in nanometers, $K = 32.17$, $S = 0.2446$, $L = d + 0.19$, and $D = 0.57$.

This formula is derived from the method of Horvath and Kawazoe (G. Horvath et al., J. Chem. Eng. Japan, 16 (6) 470(1983)). The constants required for the implementation of this formula were determined from a measured isotherm of ALPO-5 and its known pore size. This method is particularly useful for microporous materials having pores of up to 60 $\text{\AA}$ in diameter.


The results of this procedure for the samples from Examples 1 through 17 are tabulated below. The samples from Examples 10, 13 and 15 gave two separate peaks, believed to be the result of two separate ultra-large pore phases in the products.



	<u>Example</u>	<u>Pore Diameter, Å</u>
	1	32.2
	2	35.4
	3	42.5
5	4	39.6
	5	16.9
	6	27.3
	7	36.6
	8	42.6
10	9	28.3
	10	22.8, 30.8
	11	36.8
	12	36.1
	13	35.0, 42.1
15	14	40.0
	15	22.4, 30.4
	16	15.0

20 The above method of Horvath and Kawazoe for determining pore size from physisorption isotherms was intended to be applied to pore systems of up to 20 Å diameter; but with some care as above detailed, its use can be extended to pores of up to 60 Å diameter.

In the pore regime above 60 Å diameter, the Kelvin



equation can be applied. It is usually given as:


$$\ln(P/P_0) = \frac{-2\gamma V}{r_k RT} \cos \theta$$

5 where:

γ = surface tension of sorbate
 V = molar volume of sorbate
 θ = contact angle (usually taken for practical
 reasons to
10 be 0)
 R = gas constant
 T = absolute temperature
 r_k = capillary condensate (pore) radius
 P/P_0 = relative pressure (taken from the
15 physisorption
 isotherm)

 The Kelvin equation treats adsorption in pore
systems as a capillary condensation phenomenon and
relates the pressure at which adsorption takes place to
20 the pore diameter through the surface tension and
 contact angle of the adsorbate (in this case, argon).
The principles upon which the Kelvin equation are based
are valid for pores in the size range 50 to 1000
Angstrom diameter. Below this range the equation no
25 longer reflects physical reality, since true capillary
condensation cannot occur in smaller pores; above this
range the logarithmic nature of the equation precludes
obtaining sufficient accuracy for pore size
determination.


30 The particular implementation of the Kelvin
equation often chosen for measurement of pore size is
that reported by Dollimore and Heal (D. Dollimore and



G.R. Heal, J. Applied Chem, 14, 108 (1964)). This method corrects for the effects of the surface layer of adsorbate on the pore wall, of which the Kelvin equation proper does not take account, and thus provides a more accurate measurement of pore diameter. While the method of Dollimore and Heal was derived for use on desorption isotherms, it can be applied equally well to adsorption isotherms by simply inverting the data set.


In order to illuminate the microstructure of the materials by transmission electromicroscopy (TEM), samples must be thin enough for an electron beam to pass through them, generally 500-1000 Å or so thick. The crystal morphology of the present materials usually required that they be prepared for study by ultramicrotomy. While time consuming, this technique of sample preparation is conventional. The materials are embedded in a resin, in this case a commercially available low viscosity acrylic resin L.R. WHITE (hard), which is then cured at 80°C for 1 1/2 hours. Thin sections of the block are cut on an ultramicrotome using a diamond knife and sections in the thickness range 500-1000 Å are collected on fine mesh electron microscope support grids. For these materials, an LKB model microtome with a 45°C diamond knife edge was used; the support grids were 400 mesh copper grids. After evaporation of a thin carbon coating on the sample to prevent charging in the microscope (light gray color on a white sheet of paper next to the sample in the evaporator), the samples are ready for examination in the TEM.

High resolution TEM micrographs show projections of structure along the direction that the sample is



viewed. For this reason, it is necessary to have a sample in specific orientations to see certain details of the microstructure of the material. For crystalline materials, these orientations are most easily chosen by observing the electron diffraction pattern (EDP) that is produced simultaneously with the electron microscope image. Such EDPs are readily produced on modern TEM instruments using, e.g. the selected area field limiting aperture technique familiar to those skilled in the art of electron microscopy. When an EDP with the desired arrangement of diffraction spots is observed, the corresponding image of the crystal giving that EDP will reveal details of the microstructure along the direction of projection indicated by the EDP. In this way, different projections of a crystal's structure can be observed and identified using TEM.

In order to observe the salient features of the crystalline product of the present invention, it is necessary to view the material in an orientation wherein the corresponding EDP gives a hexagonal arrangement of diffraction spots from a single individual crystal. If multiple crystals are present within the field limiting aperture, overlapping diffraction patterns will occur that can be quite difficult to interpret. The number of diffraction spots observed depends to a degree upon the regularity of the crystalline arrangement in the material, among other things. At the very least the inner ring of bright spots should be observed to obtain a good image. Individual crystals can be manipulated by specimen tilt adjustments on the TEM until this orientation is achieved. More often, it is easier to take advantage of the fact that the specimen contains many randomly



oriented crystals and to simply search through the sample until a crystal giving the desired EDP (and hence orientation) is located.

5 Microtomed samples of materials from the Examples were examined by the techniques described above in a JEOL 200 CX transmission electron microscope operated at 200,000 volts with an effective 2 Å objective aperture in place. The instrument has a point-to-point resolution of 4.5 Å. Other conventional experimental
10 arrangements in high resolution (phase contrast) TEM could be used to produce equivalent images provided care is taken to keep the objective lens on the underfocus (weak leans) side of the minimum contrast lens current setting.

15 Example 21


Pt/MCM-41 Catalyst Preparation

A sample of MCM-41 (40 Å) was prepared in accordance with the method described below.

20 The following mixture (parts by weight - pbw) was charged to an autoclave:

83.7pbw Cetyltrimethylammonium (CTMA) hydroxide,
prepared by contacting a 29 wt % N,N,N-trimethyl-1-hexadecylammonium chloride solution with a hydroxide-for-halide
25 exchange resin,
1.7pbw Sodium aluminate,
4.1pbw Tetramethylammonium silicate (10% aqueous solution),
10.5pbw Precipitated hydrated silica (HiSil ♦).

30 The mixture was crystallized at 100°C for 20 hours with stirring under autogeneous pressure. The



resulting product was recovered by filtration and dried in air at ambient temperature. A sample of the product was calcined at 540° C for 1 hour in nitrogen, followed by 6 hours in air for characterization.


5 The calcined product had a surface area of 1120 m²/g and the following equilibrium absorption capacities in grams/100 grams:

	H2O	10.8
	Cyclohexane	>50
10	n-hexane	>50
	Benzene	67

15 The product was identified as MCM-41 with an X-ray diffraction pattern which included a very strong relative intensity line at 38.4 + 2.0 Å d-spacing, and weak lines at 22.6 + 1.0, 20.0 + 1.0, and 15.2 +1.0 Å.

20 The MCM-41 crystalline product was exchanged with room temperature aqueous solutions of ammonium nitrate and subsequently dried overnight at 121°C (250°F). A portion of the resultant crystals was combined with Al₂O₃ (Versal 250 +) to form a mixture of 65 parts, by weight MCM-41 and 35 parts alumina. Water was added to this mixture to allow the resulting catalyst to be formed into extrudates. The catalyst was activated by calcination at 510°C (950°F) in 5v/v/min of nitrogen for 6 hours followed by the replacement of the nitrogen with 5v/v/min of air. The calcination was completed by raising the temperature to 1000°F and maintaining that temperature in 5v/v/min air for 18 hours.

25 The calcined extrudate was exchanged with a
30 0.0062M Pt(NH₃)₄Cl₂ solution, followed by washing,



drying and calcination in air at 343°C (650°F) for three hours.

Example 22

Pd/MCM-41 Catalyst Preparation


5 A sample of MCM-41 (40 Å) was prepared in accordance with the method described below.

 The following mixture was charged to an autoclave:

60.7pbw Cetyltrimethylammonium (CTMA) hydroxide,
 prepared by contacting a 29wt.% N,N,N-
10 trimethyl-1-hexadecylammonium chloride
 solution with a hydroxide-for-halide
 exchange resin,
1.3pbw Sodium aluminate,
30.4pbw Tetramethylammonium silicate (10% aqueous
15 solution),
7.6pbw Precipitated hydrated silica (HiSil ♦).

 The mixture was crystallized at 100°C for 20 hours with stirring under autogeneous pressure. The
20 resulting product was recovered by filtration and dried
 in air at ambient temperature. A sample of the product
 was calcined at 540° C for 1 hour in nitrogen, followed
 by 6 hours in air. The identity of the material as
 MCM-41 was consistent with its properties.

 The MCM-41 crystalline product was formulated into
25 a catalyst in the same way as the platinum-containing
 catalyst described in Example 22 with the exception
 that the calcined catalyst was exchanged with aqueous
 Pd(NH₃)₄Cl₂ solution, followed by drying at room
 temperature for 4 hours and overnight at 250°F before
30 the final calcination.



Example 23

A Pd/SiO₂ catalyst was made by impregnating silica spheres (Shell S-980 C 1.5) with a Pd(NH₃)₄Cl₂ solution using the incipient wetness method. The impregnated spheres were then dried at room temperature for 4 hours, followed by 250°F overnight after which the catalyst was calcined in 5 v/v/min air at 550°F for 3 hours.


Example 24

The three noble metal containing catalysts described above (Pt MCM-41/Al₂O₃, Pd MCM-41/Al₂O₃, Pd SiO₂) were evaluated for hydrogenating a PAO lubricant.

The properties of the three catalysts are summarized in Table 2 below.

Table 2			
<u>Catalyst Properties</u>			
	<u>Pd MCM-41⁽¹⁾</u>	<u>Pt MCM-41⁽¹⁾</u>	<u>Pd SiO₂</u>
<u>Metal Loading.</u>			
<u>Wt%</u>			
Pd	0.83	-	0.84
Pt	-	0.54	-
<u>Surface Area.</u>			
<u>m²/g</u>	800	682	330
<u>Pore Volume.</u>			
<u>cc/g</u>	0.96	0.97	0.88
<u>Pore Distribution, %</u>			
<50 Å	32	42	0
50-100 Å	16	12	41
100-200 Å	15	11	32
>200 Å	37	35	37

(1) Contains 65 wt % MCM-41 and 35 wt % alumina prior to the metal addition.



The MCM-41 materials used in the catalysts containing this crystalline material had a pore opening of 40 Å. All three catalysts have 30% pore volume with pore diameters greater than 200 Å but the MCM-41 catalysts have 30-40% pore volume with pore diameters less than 50 Å.


All catalysts were evaluated in a fixed-bed pilot unit. A poly-alpha olefin (PAO) lube oligomer having the composition shown in Table 3 below was used as the feed.

Table 3
Properties of PAO


Gravity, °API	39.2
Hydrogen, wt %	14.6
Bromine Number	27.3
KV @ 40°C, mm ² /s	26.22
KV @100°C, mm ² /s	5.253
Viscosity Index	136

The PAO was hydrogenated at 2.0 LHSV, 2520 kPa abs. (350 psig) H₂ and 890 n.l.l.⁻¹ (5000 scf/b) of once-through hydrogen circulation rate. Reactor temperature was varied to obtain catalyst activity as a function of temperature. Catalyst activity is measured by the reduction of bromine number of the oil.

The results are summarized graphically in the figure. The PAO feed had a bromine number of 27.3 units and, as shown in the figure, the Pd MCM-41/Al₂O₃ catalyst is the most active catalyst. It achieved the reduction of bromine number to less than 1 at 177°C (350°F), the lowest temperature of the experiments. Pt



MCM-41/ Al_2O_3 is also quite active. The Pd/ SiO_2 catalyst, which does not have pore volume associated with pore openings less than 50 Å, is the least active catalyst.






CLAIMS:

1. A process for hydrogenating a lubricant hydrocarbon which comprises contacting a hydrocarbon lubricant feed in the presence of hydrogen with a hydrogenation catalyst containing a metal hydrogenation component on a support comprising an inorganic, porous crystalline phase material having pores with diameters of at least 1.3 nm (13 Angstrom Units) and exhibiting, after calcination, an X-ray diffraction pattern with at least one peak at a d-spacing greater than 1.8 nm (18 Å) with a relative intensity of 100.

2. A hydrogenation process according to claim 1 in which the crystalline phase exhibits, after calcination, a hexagonal arrangement of uniformly sized pores with diameters of at least 13 Å and which exhibits, after calcination, a hexagonal electron diffraction pattern that can be indexed with a d_{100} value greater than 1.8 nm (18 Angstrom Units).


3. A hydrogenation process according to claim 1 in which the crystalline phase has an X-ray diffraction pattern following calcination with at least one peak whose d-spacing corresponds to the d_{100} value from the electron diffraction pattern.

4. A hydrogenation process according to claim 1 in which the crystalline phase exhibits a benzene adsorption capacity of greater than 15 grams benzene per 100 grams at 6.7 kPa (50 torr) and 25°C.





5. A hydrogenation process according to claim 1 in which the crystalline phase has a composition expressed as follows:




5 wherein M is one or more ions; n is the charge of the composition excluding M expressed as oxides; q is the weighted molar average valence of M; n/q is the number of moles or mole fraction of M; W is one or more
10 divalent elements; X is one or more trivalent elements; Y is one or more tetravalent elements; Z is one or more pentavalent elements; a, b, c, and d are mole fractions of W, X, Y, and Z, respectively; h is a number of from 1 to 2.5; and $(a+b+c+d) = 1$.

6. A hydrogenation process according to claim 4 wherein W comprises a divalent first row transition metal or magnesium; X comprises aluminum, boron, gallium or iron; Y comprises silicon or germanium; and
5 Z comprises phosphorus.

7. A hydrogenation process according to claim 4 wherein a and d are 0 and $h = 2$.

8. A hydrogenation process according to claim 7 wherein X comprises aluminum, boron, gallium or iron and Y comprises silicon or germanium.

9. A hydrogenation process according to claim 8 wherein X comprises aluminum and Y comprises silicon.





10. A hydrogenation process according to claim 1 in which the catalyst comprises at least one metal of Groups VIA, VIIA or VIIIA of the Periodic Table.

11. A hydrogenation process according to claim 1 in which the catalyst comprises at least one noble metal of Group VIIIA of the Periodic Table.


12. A process according to claim 11 in which the noble metal comprises palladium.

5 13. A hydrogenation process according to claim 1 in which the feed is contacted with the catalyst at a pressure of from 1480 to 10500 kPa (200 to 1500 psig) (reactor inlet), a temperature from 93° to 371°C (200° to 700°F), and a space velocity from 0.2 to 2.0 LHSV.

14. A hydrogenation process according to claim 1 in which the lubricant comprises a poly alpha olefin.

15. A process according to claim 14 in which the polyalphaolefin comprises a poly alpha olefin produced by the polymerization of a C_8 - C_{12} alpha-olefin.

16. A process according to claim 14 in which the poly alpha olefin is produced by the polymerisation of the olefin in the presence of a Friedel-Crafts catalyst.






5 17. A process according to claim 14 in which the poly alpha olefin is a poly alpha olefin having a branch ratio of less than 0.19, produced by the polymerization of the olefin in the presence of a reduced Group VIA metal oxide catalyst.

18. A process according to claim 1 in which the bromine number of the lubricant is reduced from a value of at least 5 to a value of not more than 1.

19. A process according to claim 18 in which the bromine number of the lubricant is recued from a value of at least 10 to a value of not more than 0.5.




HYDROGENATION PROCESS

Abstract

5 A hydrogenation process for reducing the
unsaturation of lubricants uses a catalyst which is
based on an ultra-large pore crystalline material. The
crystalline material has pores of at least 1.3 nm (13
10 Å) diameter arranged in a uniform manner and exhibits
unusually large sorption capacity demonstrated by its
benzene adsorption capacity of greater than 15 grams
benzene/100 grams (6.7 kPa/50 torr and 25°C). A
15 preferred form of the catalyst has a hexagonal
structure which exhibits a hexagonal electron
diffraction pattern that can be indexed with a d_{100}
value greater than 1.8 nm (18 Å). The hydrogenation
catalysts based on these materials are capable of
reducing the unsaturation in poly alpha olefin
lubricants to a low level.

FIGURE 1 IS SUGGESTED FOR PUBLICATION



PAO Hydrogenation




FIG. 1

REPLACEMENT SHEET

17 JUN 1996

- 1 -

HYDROGENATION PROCESSAbstract

5 A hydrogenation process for reducing the
 unsaturation of lubricants uses a catalyst which is
 based on an ultra-large pore crystalline material. The
 crystalline material has pores of at least 1.3 nm (13
 Å) diameter arranged in a uniform manner and exhibits
 unusually large sorption capacity demonstrated by its
 benzene adsorption capacity of greater than 15 grams
 10 benzene/100 grams (6.7 kPa/50 torr and 25°C). A
 preferred form of the catalyst has a hexagonal
 structure which exhibits a hexagonal electron
 diffraction pattern that can be indexed with a d_{100}
 value greater than 1.8 nm (18 Å). The hydrogenation
 15 catalysts based on these materials are capable of
 reducing the unsaturation in poly alpha olefin
 lubricants to a low level.

FIGURE 1 IS SUGGESTED FOR PUBLICATION

REPLACED SHEETS	SC
✓ Description : paged <u>2</u> to paged <u>67</u>	
✓ Claim(s) : paged <u>47</u> to paged <u>71</u>	
✓ Drawing(s) : paged <u>71</u> to paged <u>71</u>	
✓ Abstract : paged <u>71</u> to paged <u>71</u>	
DATE OF RECEIPT	

This Sheet Has Been Replaced

