

Sintered and doped product based on zircon + Nb₂O₅ or Ta₂O₅

The invention relates to novel sintered materials produced from zircon, to a process for manufacturing them and to their use in a glass furnace.

5 Among refractory products, a distinction is made between fused-cast products and sintered products.

Unlike sintered products, fused-cast products usually include a highly abundant intergranular glass phase that fills the network of crystallized grains. The problems encountered by sintered products and by fused-cast products in their respective applications and the technical solutions adopted for solving them are therefore generally
10 different. Moreover, owing to the considerable differences between the manufacturing processes, a composition developed for manufacturing a fused-cast product cannot *a priori* be used as such for manufacturing a sintered product, and vice versa.

Sintered products are obtained by mixing suitable raw materials, then forming this mixture in the green state, before firing the resulting green form at a temperature and for a
15 time that are sufficient to sinter this green form.

Depending on their chemical composition and their method of production, sintered products are intended for a very wide variety of industries.

A sintered product suitable for one particular application will therefore not *a priori* possess the properties needed for being used in another application in which the
20 temperature, corrosion or abrasion conditions are different.

For example, US 3 899 341 describes sintered products produced from zircon (50-90%) and zirconia. The zirconia is partially stabilized in order to limit elastic deformation of the products, which leads to cracking. However, the products in US 3 899 341 are designed to be used in contact with molten steel. They are therefore not *a priori*
25 suitable for being used in contact with a molten glass.

Among sintered products, dense products produced from zircon (zirconium silicate: ZrO₂.SiO₂ or ZrSiO₄) and optionally zirconia (zirconium oxide: ZrO₂) may be used in applications in which they are directly in contact with molten glass, in particular in the case of non-alkaline glasses.

30 EP 952125 thus describes sintered products intended for glass furnaces and produced from zircon (5-40%) and zirconia. These products also contain titanium, aluminium and yttrium oxides, allowing large crack-free blocks to be produced. The SiO₂

content of these products is less than 14% while their $\text{ZrO}_2 + \text{HfO}_2$ content is greater than 82%.

WO 02/44102 describes "isopipes" used for the manufacture of glass sheets. The isopipes comprise more than 95% zircon by weight and, unless they also contain between
5 0.2 et 0.4% titanium oxide, their creep behaviour is insufficient. To illustrate the prior art, WO 02/44102 cites US 5 124 287.

US 5124287 describes compositions containing 75 to 95% zircon and titanium oxide that are intended to be in contact with molten glass. The presence of titanium oxide is considered to be favourable to the densification of the products obtained after sintering.
10 In the end product, the zirconia must be unstabilized and it is therefore preferable to use unstabilized zirconia in the starting mixture. However, the use of stabilized zirconia, for example with zirconia stabilizers such as yttrium oxide or calcium oxide, is not unacceptable since heating the mixture causes the zirconia to be destabilized.

WO 2006/073841 describes refractory materials intended for the glass industry.
15 These zircon-based materials may contain Y_2O_3 . They always contain at least 1% P_2O_5 or V_2O_5 .

The creep of a material under the action of a stress (compressive, tensile or flexural stress) may be defined as the ability of the material to be plastically deformed, that is to say permanently deformed, under the effect of this load. In refractory ceramics, the
20 creep is in general thermally activated, that is to say increasing the temperature tends to increase the creep rate of the material.

In certain glass applications, and in particular for forming glass sheets, creep must be limited as far as possible since this may induce deformation of the refractory block that makes it difficult for the glass sheet to meet the dimensional specifications and
25 results in a substantial drop in yield for the glass producer.

There therefore exists a need for a product having improved creep resistance and able to be used in glass furnaces. The present invention aims to satisfy this need.

To this end, the invention proposes a sintered product produced from a starting charge containing 75 to 99% zircon, and having the following average chemical
30 composition by weight, the percentages by weight being based on the oxides:

$$60\% \leq \text{ZrO}_2 + \text{HfO}_2 \leq 75\%;$$

$$27\% \leq \text{SiO}_2 \leq 34\%;$$

$$0 \leq \text{TiO}_2;$$

$$0 \leq Y_2O_3 \leq 3.5\%;$$

$$0.1\% \leq Nb_2O_5 + Ta_2O_5 \leq 5\%; \text{ and}$$

$$\text{Other oxides: } \leq 1.5\%$$

for a total of 100%.

- 5 As we will see later, this sintered refractory product has an improved creep resistance with respect to the products described hitherto. Advantageously, it also has a high density, equivalent to or higher than the known products.

Preferably, the product according to the invention also has one or more of the following optional features:

- 10 - $Ta_2O_5 > 0.00\%$, preferably $Ta_2O_5 \geq 0.1\%$, preferably $Ta_2O_5 \geq 0.25\%$, in percentages by weight on the basis of the oxides;
- In an embodiment, $Nb_2O_5 \leq 1\%$, preferably $Nb_2O_5 \leq 0.5\%$, preferably $Nb_2O_5 \leq 0.3\%$, or even $Nb_2O_5 \leq 0.25\%$, in percentages by weight on the basis of the oxides; In one embodiment $Nb_2O_5 \leq 0.05\%$. The product of the invention may also not contain any
- 15 Nb_2O_5 .
- $TiO_2 < 1.5\%$, preferably $TiO_2 < 1\%$, more preferably $TiO_2 < 0.5\%$, even more preferably $TiO_2 < 0.15\%$ and even more preferably still $TiO_2 < 0.10\%$ in percentages by weight on the basis of the oxides. TiO_2 may even be an impurity;
- the total content of oxides Nb_2O_5 and Ta_2O_5 , preferably the content of at least one of these oxides, and in particular the content of Ta_2O_5 , is greater than 0.2%, preferably greater than 0.3%, preferably greater than 0.5% and more preferably greater than
- 20 0.8%, in percentages by weight on the basis of the oxides;
- the total content of the oxides Nb_2O_5 and Ta_2O_5 , preferably the content of at least one of these oxides, and in particular the content of Ta_2O_5 , is less than 4% or 3%, preferably less than 2%, preferably less than 1.7%, preferably less than 1.5% and
- 25 more preferably less than 1%, in percentages by weight on the basis of the oxides;
- $SiO_2 \geq 30\%$;
- $ZrO_2 + HfO_2 \leq 72.9\%$ or $ZrO_2 + HfO_2 \leq 70\%$;
- the "other oxides" are impurities - preferably the content of "other oxides" is less than
- 30 1.2%, more preferably less than 1%, even more preferably less than 0.7%, even more preferably less than 0.5% and more preferably still less than 0.2%, in percentages by weight on the basis of the oxides;

- $P_2O_5 < 1\%$, preferably $P_2O_5 < 0.9\%$, more preferably $P_2O_5 < 0.5\%$, even more preferably $P_2O_5 < 0.3\%$, and even more preferably still $P_2O_5 < 0.2\%$, in percentages by weight on the basis of the oxides;
- 5 - $V_2O_5 < 1\%$, preferably $V_2O_5 < 0.9\%$, more preferably $V_2O_5 < 0.5\%$, even more preferably $V_2O_5 < 0.3\%$, and even more preferably still $V_2O_5 < 0.2\%$, in percentages by weight on the basis of the oxides;
- $Al_2O_3 < 1\%$, preferably $Al_2O_3 < 0.6\%$, more preferably $Al_2O_3 < 0.4\%$, in percentages by weight on the basis of the oxides;
- 10 - $CaO < 0.1\%$, preferably $CaO < 0.05\%$, in percentages by weight on the basis of the oxides;
- $Fe_2O_3 < 0.2\%$, preferably $Fe_2O_3 < 0.08\%$, in percentages by weight on the basis of the oxides;
- the zircon content in the starting charge is greater than or equal to 80%, preferably greater than 90%, preferably greater than 95%, as percentages by weight on the basis of the oxides;
- 15 - the product of the invention has the form of a block, at least one of the dimensions of which, preferably all the dimensions of which, are greater than 100 mm. In particular, the block may be square or rectangular shaped;
- the product of the invention contains more than 80% by weight of zircon ($ZrSiO_4$);
- 20 - the apparent porosity is more than 2%, or more than 4%;
- the apparent porosity is less than 15 %, or less than 10 % or even less than 8%;

In one embodiment, the zirconia content in the product is greater than 5%, preferably greater than 10%, and/or less than 15%, in percentages by weight on the basis of the oxides.

- 25 In one embodiment, the Y_2O_3 content may be greater than 0.05%, greater than 0.10%, greater than 0.15% and even greater than 0.5%, in percentages by weight on the basis of the oxides. The zirconia in the product may be at least partially stabilized with yttrium oxide, the percentage by weight of stabilized zirconia being greater than 10%, preferably greater than 20%, of the zirconia.

- 30 The yttrium oxide content Y_2O_3 is preferably less than 3%, preferably less than 1.7% and more preferably less than 1%, in percentages by weight on the basis of the oxides. Advantageously, a significant modification of the crystalline phases is thus

avoided, as are therefore the risks of feasibility problems associated with an increase in rigidity.

The invention also relates to a process for manufacturing a sintered product comprising the following steps:

- 5 a) raw materials are mixed to form a starting charge;
 b) a green part is formed from said starting charge; and
 c) said green part is sintered so as to obtain said sintered product,
said process being noteworthy in that the starting charge is determined in such a way that said product is in accordance with the invention.

- 10 Preferably, zircon and optionally zirconia are added in step a) in amounts such that the total of the zircon and zirconia contents represents at least 95% of the starting charge, as a percentage of the weight on the basis of the oxides.

In one embodiment, in step a), monoclinic zirconia and/or at least 1% of silica are added to the starting charge, in percentages by weight on the basis of the oxides.

- 15 Optional yttrium oxide, provided with the zirconia or provided separately, may also be added to the starting charge. At least 1% yttrium oxide, in percentages by weight on the basis of the oxides, may be added.

In an embodiment, no Y_2O_3 , associated with zirconia or provided separately, is added to the starting charge. However Y_2O_3 may still be an impurity.

- 20 Preferably, in step a) one or more of the oxides Nb_2O_5 , and Ta_2O_5 , are intentionally (that is to say systematically and methodically) added in amounts guaranteeing that the sintered product obtained in step e) is in accordance with the invention.

- 25 The invention also relates to the use of a refractory product according to the invention, or one manufactured using a process according to the invention, in a glass furnace, in particular in furnace zones that are in contact with molten glass.

The invention finally relates to such a glass furnace.

- 30 In the present description and in accordance with the usage, "zirconia" refers to ZrO_2 molecules that are not associated with SiO_2 molecules to form zircon. Likewise, "silica" refers to SiO_2 molecules that are not associated with ZrO_2 molecules to form zircon.

The term "impurities" is understood to mean inevitable constituents, necessarily introduced with the raw materials or resulting from reactions with these constituents.

Unless mentioned otherwise, all the percentages are percentages by weight on the basis of the oxides.

The zircon may be provided by zircon sand (natural or synthetic, optionally milled) or else a chamotte of dense products having a high zircon content.

5 The composition according to the invention, determined by chemical analysis, supplies only the overall SiO_2 and ZrO_2 contents, without distinguishing the corresponding zircon contents.

10 According to the invention, it is essential for the starting charge to contain at least 75%, preferably at least 80%, zircon. The advantageous properties of the product according to the invention would in fact not be achieved if the amounts of SiO_2 and ZrO_2 provided by the zircon according to the invention were provided in the form of silica and zirconia.

Preferably, the total of the zircon and zirconia contents represents at least 95% of the starting charge.

15 The zirconia-containing raw materials also contain small amounts of HfO_2 (1.5 to 2%) and, according to the usual practice, these two oxides are not distinguished from each other.

20 Zirconia exhibits large dilatometric variations due to its change of crystallographic state at high temperature. To limit these dilatometric variations, in particular in large blocks, it is necessary to limit the zirconia content. The starting charge must therefore contain less than 25% zirconia, this being provided by having a zircon content of at least 75%.

25 In one embodiment, the zirconia in the product according to the invention is at least partially stabilized with yttrium oxide, the percentage by weight of stabilized zirconia being greater than 10% of the zirconia. For this purpose, the zirconia must be introduced in unstabilized form and the yttrium oxide must be added to the starting charge separately.

30 According to the invention, the presence of niobium and/or tantalum oxide improves the creep resistance of the zircon-based refractory product. Advantageously, this also avoids having to add titanium oxide. This is because titanium oxide is known by those skilled in the art as being an additive that promotes bubbling of the zircon in very many specialty glasses. It is therefore desirable to limit the concentration of this sintering additive.

If zirconia is added to the starting charge, it is possible to use yttrium-oxide-stabilized zirconia to provide the yttrium oxide. As explained above, the yttrium oxide is preferably added to the starting charge independently of the zirconia so as to promote, at least partly, the stabilization of the zirconia in the product according to the invention.

However, it is desirable to limit the amount of yttrium oxide in order to avoid dissociation of the zircon at high temperature. The yttrium oxide content is therefore limited to 3.5%.

The SiO_2 content of the product according to the invention corresponds to the SiO_2 content of zircon and to free silica. In one embodiment, at least 1% of silica is added to the starting charge so as to promote the onset of densification at lower temperatures than would be needed to densify pure zircon.

The "other oxides" are oxides such as Na_2O , Al_2O_3 , P_2O_5 or Fe_2O_3 . The contents of Na_2O (which promotes the dissociation of zircon) and of Fe_2O_3 must be minimized. Preferably, these oxides are impurities provided by the raw materials, which oxides are not necessary constituents but are merely tolerated. At contents of less than 1.5%, it is considered that the effect of these "other oxides" does not substantially modify the result obtained.

Preferably, the content of each of the abovementioned oxides in the sintered product according to the invention is less than 0.5%, more preferably less than 0.3% and more preferably still less than 0.15% in percentages by weight on the basis of the oxides.

The following non-limiting examples are given for the purpose of illustrating the invention.

In these examples, the raw materials employed (the percentages given being percentages by weight) were chosen from:

- zircon sand containing 66.8% $\text{ZrO}_2 + \text{HfO}_2$, 32.7% SiO_2 , 0.2% Al_2O_3 and 0.1% TiO_2 ;
- titanium oxide containing 96.6% TiO_2 , 1.7% Fe_2O_3 , 0.8% SiO_2 and 0.6% Al_2O_3 (for reference only);
- niobium oxide with a purity of greater than 99.9%, having particles with a median diameter (D_{50}) of about 15 μm (example 2) or about 1 μm (examples 13,14);
- tantalum oxide with a purity of greater than 99.9%, having particles with a median diameter (D_{50}) of about 15 μm (examples 3, 4) or about 1 μm (examples 6-14);

- yttrium oxide with a purity of greater than 99.9%, having particles with a median diameter of 3 to 4 μm ;
 - phosphoric acid (85% aqueous H_3PO_4 solution); and
 - crystalline silica containing more than 98% SiO_2 and having a median diameter
- 5 (D₅₀) of about 10 μm .

Sintered refractory blocks were manufactured according to a process conventionally comprising the following steps:

- a') milling of the zircon sources and other raw materials;
- b') mixing of the raw materials to form the starting charge;
- 10 c') forming of a green part from said mixture; and
- d') sintering of said green part.

Step a') makes it possible to achieve the conventional particle size characteristics required for good subsequent densification of the material. For the examples described here, the powders thus prepared had a median diameter (D₅₀) of less than 5 μm .

- 15 In step b'), all the raw materials were metered so that the mixture had the desired mean chemical composition by weight and then mixed in the presence of one or more deflocculants and/or binders conventionally used in zircon sintering processes, for example phosphoric acid.

The mixture of the raw materials could optionally be spray dried before passing to

20 step c').

In step c'), the mixture was then formed by isostatic pressing so as to produce blocks of the desired size (100 x 100 x 150 mm).

Other techniques, such as slip casting, uniaxial pressing, casting of a gel, vibro-casting, or a combination of these techniques, could be used.

- 25 In step d'), the green part was then sintered in air, at atmospheric pressure and at a temperature between 1400°C and 1700°C, so as to produce a dense refractory block.

Examples 1 to 4 were prepared in the same sintering batch. Examples 5 to 14 were prepared together in the same conditions but in another sintering batch.

- Specimens were removed from the various blocks produced, so as to carry out
- 30 characterization tests.

In an "isothermal" creep test, a four-point bending test configuration was used (the distance of L between the outer supports was 80 mm and the distance l between the inner supports was 40 mm). A strip measuring 8 mm x 9 mm x 100 mm was placed on

these supports and a stress of 2 MPa was applied at the centre of the strip, the temperature being kept constant and equal to 1275°C or 1180°C. The change in sag (in mm) of the strip over 50 hours was recorded. The mean deformation rate (V_d), given in mm/mm/hour, was then calculated.

- 5 The density was determined on three weighings of each specimen. A first weighing, of the dry specimen (after drying at 110°C), gave the weight W_{dry} . Next, a wet specimen was prepared by taking a specimen that had been under vacuum for 30 minutes and then immersed in water so as to impregnate the accessible pore volume of the material. Weighing this wet specimen gave the weight W_{wet} . Finally, weighing the
- 10 specimen in water gave W_{water} .

$W_{wet} - W_{water}$ provides a measure of the total volume of the specimen excluding accessible porosity. The bulk density of the material corresponds to the ratio of the $W_{dry}/(W_{wet} - W_{water})$.

- 15 The apparent porosity is deduced from these measurements considering that the difference $W_{wet} - W_{dry}$ corresponds to the volume of the open porosity infiltrated with water. The ratio $W_{wet} - W_{dry} / (W_{wet} - W_{water}) * 100$ gives the apparent porosity proportion.

The composition of the mixture of raw materials is indicated in Table 1 (in percentages by weight on the basis of the mixture).

The reference products are products 1 and 5.

Table 1

No.	Zircon sand (%)	Silica (%)	Titanium oxide (%)	Yttrium oxide (%)	Additive	Additive (%)	Phosphoric acid (%)
1	98.1	1.3	0.3	/	/	/	0.3
2	97.3	1.4	/	/	Nb ₂ O ₅	1	0.3
3	97.4	1.3	/	/	Ta ₂ O ₅	1	0.3
4	95.8	1.4		1.5	Ta ₂ O ₅	1	0.3
5	99.5	/	0.2				0.3
6	99.45	/	/	/	Ta ₂ O ₅	0.25	0.3
7	99.2	/	/	/	Ta ₂ O ₅	0.5	0.3
8	98.95	/	/	/	Ta ₂ O ₅	0.75	0.3
9	98.7	/	/	/	Ta ₂ O ₅	1	0.3
10	98.2	/	/	/	Ta ₂ O ₅	1.5	0.3
11	96.7	/	/	/	Ta ₂ O ₅	3	0.3
12	99.45	/	/	/	Nb ₂ O ₅	0.25	0.3
13	98.7	/	/	/	Ta ₂ O ₅ Nb ₂ O ₅	0.5 0.5	0.3
14	98.2	/	/	/	Ta ₂ O ₅ Nb ₂ O ₅	1 0.5	0.3

The average chemical composition of the various products tested and the results of the tests are given in Table 2 (the percentages by weight being on the basis of the oxides). The content of minor oxides, such as P₂O₅, Fe₂O₃, etc., is not given in the table. The total content of minor oxides is less than 1%.

Table 2

No.	ZrO ₂ + HfO ₂ (%)	SiO ₂ (%)	TiO ₂ (%)	Al ₂ O ₃ (%)	Y ₂ O ₃ (%)	Additive	Additive (%)	V _d (1275°C)	V _d (1180°C)	Density (g/cm ³)
1	65.7	33.3	0.34	0.28	0.12	/		1.3 x 10 ⁻⁴		3.72
2	65.0	33.2	0.11	0.29	0.11	Nb ₂ O ₅	0.89	5.2 x 10 ⁻⁵		4.21
3	64.8	33.1	0.11	0.29	0.12	Ta ₂ O ₅	0.92	4.6 x 10 ⁻⁶	4.8 x 10 ⁻⁷	3.97
4	64.3	33.0	0.12	0.29	0.57	Ta ₂ O ₅	0.96	7.8 x 10 ⁻⁶		3.78
5	64.4	33.3	0.38	0.30		/		1.5 x 10 ⁻⁴	2.2 x 10 ⁻⁵	3.92
6	64.3	33.2	0.16	0.30		Ta ₂ O ₅	0.34	5.3 x 10 ⁻⁵		3.93
7	64.2	33.1	0.15	0.29		Ta ₂ O ₅	0.52	5.0 x 10 ⁻⁵		4.00
8	64.6	33.1	0.16	0.29		Ta ₂ O ₅	0.93	1.6 x 10 ⁻⁵		4.13
9	64.5	33.0	0.15	0.29		Ta ₂ O ₅	1.13	1.4 x 10 ⁻⁵		4.21
10	64.2	32.8	0.15	0.29		Ta ₂ O ₅	1.68	1.0 x 10 ⁻⁵		4.13
11	62.5	32.3	0.14	0.29		Ta ₂ O ₅	2.74	8.4 x 10 ⁻⁶		4.26
12	64.3	33.2	0.16	0.30		Nb ₂ O ₅	0.26		4.5 x 10 ⁻⁶	3.92
13	63.8	32.9	0.15	0.29		Ta ₂ O ₅ Nb ₂ O ₅	0.61 0.52		1.4 x 10 ⁻⁵	4.30
14	63.5	32.8	0.15	0.29		Ta ₂ O ₅ Nb ₂ O ₅	1.31 0.51		5.2 x 10 ⁻⁶	4.28

The examples show that the addition of Nb₂O₅ and/or Ta₂O₅ makes it possible for the creep deformation to be very significantly reduced. Advantageously, this reduction is possible whether or not the yttrium oxide has been added to the starting charge.

- 5 Moreover, it has also been found that the presence of Nb₂O₅ or Ta₂O₅ advantageously makes it unnecessary to add titanium oxide in order to obtain sufficient densification. This is because the density of the products of the invention is equivalent to or greater than that of the reference product.

10 Example 3, according to the invention, is preferred when maximum creep resistance is desired. A comparison between examples 3 and 4 shows that small additions of Y₂O₃ maintain a good resistance to creep deformation. For instance, the product according to the invention may contain at least 0.5% Y₂O₃ and at least 0.9% Ta₂O₅.

15 Examples 12 to 14 show the positive influence of Nb₂O₅ on the density. Example 13, according to the invention, is preferred when a maximum density is desired. However,

high contents of Nb_2O_5 may lead to a decrease in the mechanical resistance of the product. When mechanical resistance is important, Nb_2O_5 content should be limited, preferably to values less than 1% or less than 0.5, or even less than 0.3% %, especially when Nb_2O_5 is the sole additive. Its content should then preferably be less than 0.3% or less than or equal to 0.25%.

In an embodiment, the product according to the invention may contain at least 0.05% Y_2O_3 and at least 0.8% Nb_2O_5 .

The best compromises between resistance to creep deformation and high density were obtained with Ta_2O_5 contents higher than 0.95%, preferably higher than or equal to 2 % or 3%. Example 11 is regarded as the preferred embodiment. In this example, no Nb_2O_5 is added to the starting charge. In other words, it may be preferred that the product of the invention does not contain any Nb_2O_5 , but as impurities.

Of course, the present invention is not limited to the embodiments described and represented, which are provided as illustrative and non-limiting examples.

CLAIMS

1. Sintered product produced from a starting charge containing 75% or more of zircon, and having the following average chemical composition by weight, the percentages by weight being based on the oxides:

$$60\% \leq \text{ZrO}_2 + \text{HfO}_2 \leq 75\%;$$

$$27\% \leq \text{SiO}_2 \leq 34\%;$$

$$0 \leq \text{TiO}_2;$$

$$0 \leq \text{Y}_2\text{O}_3 \leq 3.5\%;$$

$$0.1\% \leq \text{Nb}_2\text{O}_5 + \text{Ta}_2\text{O}_5 \leq 5\%; \text{ and}$$

$$\text{other oxides: } \leq 1.5\%;$$

for a total of 100%

2. Sintered product according to the preceding claim in which $\text{Ta}_2\text{O}_5 \geq 0.1\%$.
3. Sintered product according to the preceding claim in which $\text{Ta}_2\text{O}_5 \geq 0.5\%$.
4. Sintered product according to the preceding claim in which $\text{Ta}_2\text{O}_5 \geq 0.8\%$.
5. Sintered product according to any preceding claim in which $\text{Nb}_2\text{O}_5 \leq 1\%$.
6. Sintered product according to the preceding claim in which $\text{Nb}_2\text{O}_5 \leq 0.5\%$.
7. Sintered product according to the preceding claim in which $\text{Nb}_2\text{O}_5 \leq 0.3\%$.

8. Sintered product according to the preceding claim in which Nb_2O_5 is an impurity.
9. Sintered product according to any preceding claim, in which $\text{TiO}_2 < 1.5\%$ as a percentage by weight on the basis of the oxides.
10. Sintered product according to the preceding claim, in which $\text{TiO}_2 < 0.5\%$ as a percentage by weight on the basis of the oxides.
11. Sintered product according to the preceding claim, in which $\text{TiO}_2 < 0.15\%$ as a percentage by weight on the basis of the oxides.
12. Sintered product according to any one of the preceding claims, in which the total content of the oxides Nb_2O_5 and Ta_2O_5 is greater than 0.5% and less than 1.5%, in percentages by weight on the basis of the oxides.
13. Sintered product according to any one of the preceding claims, in which the Y_2O_3 content is greater than 0.15% and less than 1.7%, in percentages by weight on the basis of the oxides.
14. Sintered product according to the preceding claim, in which the Y_2O_3 content is greater than 0.5% and less than 1%, in percentages by weight on the basis of the oxides.
15. Sintered product according to any one of the preceding claims, in which the content of "other oxides" is less than 0.7% as a percentage by weight on the basis of the oxides.
16. Sintered product according to any one of the preceding claims, in which $\text{P}_2\text{O}_5 < 1\%$ and/or $\text{V}_2\text{O}_5 < 1\%$ and/or $\text{Al}_2\text{O}_3 < 1\%$ and/or $\text{CaO} < 0.1\%$ and/or $\text{Fe}_2\text{O}_3 < 0.2\%$.
17. Sintered product according to the preceding claim, in which $\text{P}_2\text{O}_5 < 0.3\%$ and/or $\text{V}_2\text{O}_5 < 0.3\%$ and/or $\text{CaO} < 0.05\%$ and/or $\text{Fe}_2\text{O}_3 < 0.1\%$.
18. Sintered product according to any one of the preceding claims, obtained from a starting charge having a zircon content greater than or equal to 80%, as a percentage by weight on the basis of the oxides.

19. Sintered product according to the preceding claim, obtained from a starting charge having a zircon content greater than or equal to 95%, as a percentage by weight on the basis of the oxides.
20. Sintered product according to any one of claims 1 to 12 and 15 to 19, obtained from a starting charge in which no Y_2O_3 has been added.
21. Sintered product according to any one of the preceding claims in the form of a block presenting at least one dimension which is greater than 100 mm.
22. Sintered product according to the preceding claim, all the dimensions of said block are greater than 100 mm.
23. Sintered product according to any one of the preceding claims, having a zirconia content of greater than 5% and/or less than 15%, in percentages by weight on the basis of the oxides.
24. Sintered product according to any one of the preceding claims, having zirconia at least partially stabilized by yttrium oxide, the percentage by weight of stabilized zirconia being greater than 10% of the zirconia.
25. Sintered product according to any one of the preceding claims containing 99.45% or less of zircon.
26. Sintered product according to any one of the preceding claims containing 99% or less of zircon.
27. Sintered product according to any one of the preceding claims, in which the total content of the oxides Nb_2O_5 and Ta_2O_5 is greater than 0.2% and less than 2%, in percentages by weight on the basis of the oxides.
28. Process for manufacturing a sintered product comprising the following steps:
 - a) raw materials are mixed to form a starting charge;
 - b) a green part is formed from said starting charge; and

c) said green part is sintered so as to obtain said sintered product,

said process being characterized in that the starting charge is determined in such a way that said product is in accordance with any one of the preceding claims.

29. Process according to the preceding Claim, in which, in step a) one or more of the oxides Nb_2O_5 and Ta_2O_5 are intentionally added in amounts guaranteeing that the sintered product obtained in step e) is in accordance with any one of claims 1 to 27.
30. Process according to either of claims 28 and 29, in which monoclinic zirconia is added in step a).
31. Manufacturing process according to any one of claims 28 to 30, in which no yttrium oxide not associated with zirconia is added in step a).
32. Process according to any one of claims 28 to 31, in which zircon and optionally zirconia are added in step a) in amounts such that the total of the zircon and zirconia contents represents at least 95% of the starting charge as a percentage of the weight on the basis of the oxides.
33. Process according to any one of claims 28 to 32, in which at least 1% silica is added in step a) to the starting charge as a percentage by weight on the basis on the oxides.
34. Glass furnace comprising a refractory product according to any one of Claims 1 to 27 or manufactured using a process according to any one of Claims 28 to 33.