

## Description

The present invention relates to a process for the dehydrogenation of hydrocarbons and/or oxygenated hydrocarbons.

Dehydrogenation processes, and in particular the dehydrogenation of alkanes, are well known. The process generally employs a dehydrogenation catalyst which is contacted by the feedstock to produce the dehydrogenated product and hydrogen. The hydrogen may then be separated from the product stream to provide the desired product.

It would be desirable to develop a process having little or no external heat input for the dehydrogenation reaction, with or without separation into its individual components, to obtain high conversion values without the co-production of undesirable by-products and avoiding the extensive separation plant associated with cracking.

FR-A-2609982 discloses a dehydrogenation process using a catalyst which consists of at least one metal, one salt or one metal complex from Group VIIa, VIII and Ib and a hydrogen capture vehicle. During the reaction, the hydrogen capture vehicle is converted into metal hydride  $MH_x$  whose subsequent thermal dehydrogenation leads to the formation of hydrogen and restores the capture vehicle M in its initial form.

Chemical Abstract Vol. 114, 130165r discloses a supported metal catalyst. The catalyst comprises platinum and gold.

Accordingly, the present invention provides a continuous process for the dehydrogenation of a hydrocarbon and/or oxygenated hydrocarbon feed, which process comprises contacting the hydrocarbon and/or oxygenated hydrocarbon feed at an elevated temperature in a reaction zone with a dehydrogenation catalyst system characterised in that the dehydrogenation catalyst is a catalyst capable of retaining hydrogen, or is a catalyst incapable of retaining hydrogen, said catalyst incapable of retaining hydrogen in combination with a hydrogen retention agent; and

(a) is contacted with the feed to form a dehydrogenated product and hydrogen, wherein at least some of the hydrogen formed is adsorbed by the dehydrogenation catalyst or the hydrogen retention agent or reacted with the catalyst or the hydrogen retention agent to reduce at least part of the catalyst or hydrogen retention agent; (b) removing from the reaction zone the dehydrogenated product and any hydrogen which is not adsorbed by or reacted with the catalyst system;

(c) regenerating the catalyst system by removing at least some of the adsorbed hydrogen from the catalyst or hydrogen retention agent and/or oxidising at least some of the reduced

catalyst or hydrogen retention agent by contacting the catalyst or retention agent with an oxygen-containing gas thereby providing heat to maintain the catalyst at the elevated temperature.

(d) re-using the regenerated catalyst system from step (c) in step (a).

The process of the present invention can provide a method for the dehydrogenation of hydrocarbons or oxygenated hydrocarbons without the need for an external heat supply. High conversion rates can be obtained without the co-production of undesirable by-products. Furthermore, the cyclic nature of the process avoids the simultaneous presence of free oxygen and hydrocarbon or oxygenated hydrocarbon in the reactor minimising loss of selectivity through carbon oxide formation as experienced in other oxidative dehydrogenation processes.

The process of the present invention is particularly suitable for the dehydrogenation of an alkane feed to the corresponding alkene. Suitably, the feed may comprise  $C_2$  to  $C_{20}$  alkanes. Suitably, the alkane feed may comprise alkanes, optionally with one or more aryl groups. Preferably, the alkane feed is  $C_2$ ,  $C_3$  or  $C_4$  alkanes, especially  $C_2$  alkanes. Alternatively, the hydrocarbon feed may comprise oxygenated hydrocarbons. Suitably, the oxygenated hydrocarbons are alcohols, e.g. aliphatic alcohols of  $C_1$  to  $C_{20}$  carbons. Preferably the alcohol is a  $C_1$  to  $C_{10}$  alcohol such as methanol, ethanol and isopropanol.

The process may be operated at a conversion and selectivity sufficiently high so as to avoid distillative purification, thereby economising on plant and operating costs. Where the feed comprises alkanes, the process may also be operated at a temperature sufficient to promote cracking, for example, for the co-production of mixtures of ethene, propene and butene from mixtures of ethane, propane, butane or higher hydrocarbons. In this event, if individual alkenes are required, distillative separation and purification of the mixed alkene product would be necessary.

The feed is contacted with a dehydrogenation catalyst to produce the dehydrogenated product and hydrogen. The dehydrogenation catalyst must either be capable itself of adsorbing the hydrogen or be combined with a hydrogen retention agent. The dehydrogenation catalyst per se or in combination with a hydrogen retention agent must be capable of retaining hydrogen released in the dehydrogenation process. Preferably, substantially all of the hydrogen is reacted with or adsorbed by the catalyst. The hydrogen may be retained chemically or physically or by a combination of both. The catalyst should have preferably a greater affinity for hydrogen than for oxygen or water, otherwise these

could be preferentially retained, if oxygen is used in step (c) of the present process. A suitable catalyst, for example, may be one that retains oxygen and converts hydrogen to water at a selectivity sufficient to prevent gross product contamination with acid and carbon oxides.

Catalysts suitable for use in the process and capable of adsorbing hydrogen include reducible metal oxides, optionally with a metal selected from Group IB, IIB, and Group VIII of the periodic table. Suitably, rare earth metal oxides, optionally with a metal selected from the group including nickel, palladium, platinum, copper, silver and gold may be employed in the process of the present invention. The preferred metal is one which has little methanation activity, for example, gold. The catalysts may contain 1-30% such as 10-25% of said metal, especially gold (expressed by weight as metal, irrespective of whether it is present as metal and/or metal oxide); the catalysts preferably consist essentially of the said metal and/or metal oxide, and said rare earth metal oxide. They may be made by impregnation of said rare earth metal oxide by a solution of a thermally decomposable salt of said metal, or preferably by co-precipitation by contact of base, e.g. ammonium bicarbonate, with a solution of salts of the metal and rare earth metal, preferably by addition of said solution to said base. The preferred catalyst is gold/ceria. The aforementioned catalysts may have sufficient hydrogen retention ability not to require a separate hydrogen retention agent, although one may be used if desired.

Catalysts incapable of adsorbing the hydrogen may also be used when combined with a hydrogen retention agent. Suitable catalysts include non-reducible metal oxides, with a metal selected from Group IB, IIB, IVA, VIB and VIII of the Periodic Table. Preferably, the catalysts may be platinum/zinc on silicalite, platinum/tin on alumina or chromium oxide on alumina. Suitable hydrogen retention agents may be selected from Group VIA metal oxides and rare earth metal oxides, especially molybdenum oxide, tungsten oxide and ceria. Optionally, the oxide may comprise a second metal selected from the group comprising nickel, palladium, platinum, copper, silver and gold. Some of the aforementioned dehydrogenation catalysts capable of adsorbing hydrogen e.g. gold/ceria may be added to the non-reducible metal oxide, thus primarily acting as the hydrogen retention agent. Where it is desired to use a catalyst incapable of adsorbing hydrogen in combination with a hydrogen retention agent, the two components may be used in a mole ratio of suitably 100:1 to 1:10, preferably 20:1 to 1:5 catalyst to agent.

The feed is firstly contacted with the dehydrogenation catalyst to produce the dehydrogenated

product and hydrogen. The hydrogen produced is adsorbed by the catalyst. Unadsorbed hydrogen is removed from the reaction chamber, but preferably the process is performed so that there is substantially no hydrogen with the dehydrogenated product leaving the chamber.

Where the hydrogen is adsorbed on to the catalyst, the adsorbed hydrogen must be removed from the catalyst. Suitably, this may be carried out by contacting the catalyst with a component which is capable of being reduced by hydrogen, thus liberating the dehydrogenation catalyst. Suitably, the catalyst may be contacted with an oxygen-containing gas. The oxygen-containing gas may be suitably air or a synthetic gaseous mixture either richer or poorer in molecular oxygen than air. Oxygen itself may also be employed. Alternatively, the hydrogen may be removed by the action of heat, applying a vacuum or through the action of a chemical reagent. Suitable chemicals include carbon monoxide and carbon dioxide. Where the hydrogen is reacted with the catalyst in step (a) of the process of the present invention, to form a reduced catalyst, the catalyst is then partly oxidised to regenerate the catalyst. Suitably, an oxygen-containing gas may be used for the oxidation step.

The overall reaction, for example, ethane and oxygen to ethene and water is exothermic giving an adiabatic temperature rise of about 1,000 °C in air. This heat may be removed by performing the dehydrogenation reaction adiabatically, employing the ethane feed and the component used to remove the hydrogen from the catalyst at ambient temperature. If desired, the feed gases may be pre-heated, suitably by partial flow reversal. Pre-heating may reduce physical stress on the catalyst, but may also reduce the rate of heat removal from the catalyst into the passing gas, necessitating a larger bed and increasing the total gas flow required per unit of heat generated i.e. per tonne of product produced.

Cycle times which may be used in the operation of the process of the invention depend upon factors such as bed dimensions and gas velocity. Over the chosen cycle time the heat capacity of a bed of solid can be high compared to the gas passing through it, such that there is a substantially constant temperature over the cycle. A bed of the dehydrogenation catalyst may be maintained at a uniform temperature by controlling the hydrogen adsorption capacity at each distance into the bed such that the cooling due to gas flow over the cycle balances the heat produced at that position in the catalyst bed at burn off. This method of temperature control/stabilisation is made possible by the cyclic nature of the process and avoids the need for an expensive reactor with a large heat transfer area as used for conventional fixed bed

exothermic reactions. Typically, the first stage of the process which comprises feeding in the alkane may comprise from one tenth to a quarter the time involved in feeding in the component required to remove the hydrogen and/or oxidise the reduced catalyst.

The elevated temperature at which the dehydrogenation process of step (a) is operated may suitably be in the range from 150 to 1200°C, preferably 300-700°C. A temperature of about 500°C is preferred. The pressure may suitably be atmospheric, subatmospheric or elevated.

An embodiment of the invention will now be described with reference to the Figure 1 which takes the form of a process flow sheet and to Examples 1 and 2.

With reference to Figure 1, to a reactor (1) is fed for 2 seconds cold ethane via a pressure control valve (2), a steam accumulator (3) and a timed valve (4). The reactor (1) contains a bed of dehydrogenation catalyst pellets, the catalyst being capable of adsorbing hydrogen. In contact with the catalyst, maintained at a temperature of about 500°C, ethane is dehydrogenated to ethylene, the hydrogen released thereby being retained by the catalyst. After two seconds the timer valve (4) closes cutting off the flow of ethane into the reactor.

Ethylene is removed from the reactor through the heat exchanger (5) and the time valve (6) by suction at slightly below atmospheric pressure by a blower (7) into a gasometer (8).

Air is then driven by a blower (9) through a non-return valve (10) into the reactor (1) for a period of 13 seconds, the timed valves (4) and (6) being closed. Combustion of the retained hydrogen and any carbon deposits on the catalyst and/or oxidation of the reduced catalyst occurs thereby generating heat to maintain the catalyst temperature. Combustion gas exits from the reactor through the heat exchanger (5) and a non-return device (11). A sufficient portion of the combustion gas is recycled to the reactor (1) via damper (12) and line (13) to the air feed in order to ensure that the oxygen concentration is below the flammable limit for safety reasons and that the inlet temperature of the gas into reactor (1) is warmed above the dew point; the remainder of the combustion gas leaves through line 14 via damper (15).

At the end of the 15 seconds cycle the timed valve (4) opens allowing a 'pig' of steam to be admitted to the reactor through line 16 from accumulator (3) where steam has been accumulating because of its continuous admission through valve (17). The 'pig' of steam serves to flush any remaining flue gases from the reactor and to separate the ethane and air.

The timed valves (4 and 6) are controlled by a timer (not shown). Adjustment of the timer is used

to control the ethane feed per cycle to match the hydrogen adsorption capacity of the catalyst. Flow during the ethane phase is controlled to match or be less than bed activity. Too little feed per cycle could manifest itself in a distorted temperature profile through the catalyst bed, in particular high at the inlet. Too little catalyst activity could show as a distorted temperature profile and a high-residual ethane content in the gas leaving reactor (1).

Bed temperature can be controlled by adjusting the time period and velocity of the air feed. A longer admission time for air gives lower temperatures, particularly at the inlet. Higher air flow rates reduce the catalyst temperature, particularly at the outlet.

The foregoing description assumes an ethane pressure greater than blower discharge pressure and an ethylene pressure below atmospheric pressure, so that the non-return devices can function. Flow through the reactor during the ethane input would be slightly greater than during the air input phase because of the extra pressure drop.

The ability of catalyst to strongly adsorb hydrogen under low partial pressures of hydrogen and high temperatures was determined using a temperature programmed desorption technique (TPD). The catalysts were reduced in hydrogen at 400°C and purged at this temperature in an inert gas for several hours before heating to 800°C to desorb the retained hydrogen. The catalyst is suitably capable of adsorbing/reacting with at least 2 ml of hydrogen per gram of catalyst at 400°C. Metal-ceria catalysts were all observed to retain appreciable amounts of hydrogen at 400°C (4 cm<sup>3</sup>/g) whereas other metal oxide catalysts investigated, e.g. Ru/TiO<sub>2</sub>, showed no detectable hydrogen retention capacity.

#### Example 1 - Preparation of Gold/Ceria Catalyst

A solution of cerous nitrate hexahydrate (10g) and hydrogen tetrachloroaurate (2g) in 25 cm<sup>3</sup> of water was added dropwise with stirring to a saturated aqueous solution (800 cm<sup>3</sup>) of ammonia bicarbonate. The resultant precipitate was separated by filtration and washed three times by redispersing in 500 cm<sup>3</sup> of water followed by filtering. The washed precipitate was then dried at 110°C for 18 hours before crushing and sieving to give particles of 1 mm diameter. The catalyst particles were then heated under flowing air or an inert gas at a flow rate of 100 cm<sup>3</sup> per minute from room temperature to 500°C at a heating rate of 2°C per minute. The catalyst was then held at this temperature for 10 hours before being cooled to room temperature. The resulting catalyst was found to have 15% w/w gold and a surface area of 80m<sup>2</sup> per gram. The prepared catalyst was tested for its hydrogen re-

tention capability and showed to retain 4 cm<sup>3</sup>/g of hydrogen at 400 °C.

#### Example 2 - Dehydrogenation of Ethane

The process as described above with reference to Figure 1 was carried out at 500 °C in a 7 mm internal diameter quartz reactor at 1 barA, using 25% v/v ethane in helium at a flow rate of 40 cm<sup>3</sup>/min (at STP) and the gold/ceria catalyst (4 g) prepared as disclosed in Example 1. The regeneration was carried out at the same temperature, pressure and flow rate using 5% oxygen in helium.

##### (i) Ethane Addition to a Regenerated Catalyst

Gas chromatographic and mass spectral analysis of the exit gas stream indicated a high conversion of ethane to ethene initially with no hydrogen being present. Water and some methane were also detected in the exit gas. The concentration of ethene reached a maximum, 5% v/v, before decreasing to approximately 1% v/v. 5% v/v is above the expected thermodynamic equilibrium value of 2% v/v. The conversion and selectivity calculated from the exit gas analysis gave a maximum in ethane conversion of approximately 28% with an ethene selectivity of 95%. The conversion was then found to fall to approximately 4% with a selectivity of 85% when hydrogen breakthrough into the exit gas occurred as the hydrogen adsorption capacity of the ceria became saturated. The thermodynamic equilibrium conversion under the conditions used for the experiments was approximately 8%.

An intermediate purge using helium rather than steam was used to separate the ethane and oxygen containing gases.

##### (ii) Regeneration

Gas chromatographic and mass spectral analysis of the exit gas showed a large quantity of carbon dioxide to be released from the catalyst bed prior to oxygen breakthrough into the exit gas. Some water was also observed.

The cumulative performance data calculated through a complete process cycle (starting at the regeneration stage) gives a cumulative ethane conversion of approximately 28% with a cumulative ethene selectivity of 20% at the maxima in ethene productivity.

#### Claims

1. A continuous process for the dehydrogenation of a hydrocarbon and/or oxygenated hydrocarbon feed, which process comprises contacting the hydrocarbon and/or oxygenated hydrocarbon feed at an elevated temperature in a reaction zone with a dehydrogenation catalyst sys-

tem characterised in that the dehydrogenation catalyst is a catalyst capable of retaining hydrogen or is a catalyst incapable of retaining hydrogen, said catalyst incapable of retaining hydrogen in combination with a hydrogen retention agent

(a) is contacted with the feed to form a dehydrogenated product and hydrogen, wherein at least some of the hydrogen formed is adsorbed by the dehydrogenation catalyst or the hydrogen retention agent or reacted with the catalyst or the hydrogen retention agent to reduce at least part of the catalyst or hydrogen retention agent;

(b) removing from the reaction zone the dehydrogenated product and any hydrogen which is not adsorbed by or reacted with the catalyst system;

(c) regenerating the catalyst system by removing at least some of the adsorbed hydrogen from the catalyst or hydrogen retention agent and/or oxidising at least some of the reduced catalyst or hydrogen retention agent by contacting the catalyst or retention agent with an oxygen-containing gas thereby providing heat to maintain the catalyst at the elevated temperature.

(d) re-using the regenerated catalyst system from step (c) in step (a).

2. A process according to claim 1 in which the hydrocarbon feed comprises one or more alkanes.
3. A process according to claim 2 in which the alkane is a C<sub>2</sub>, C<sub>3</sub> or C<sub>4</sub> alkane.
4. A process according to claim 1 in which the hydrocarbon feed is an alcohol.
5. A process according to claim 4 in which the alcohol is a C<sub>1</sub> to C<sub>20</sub> alcohol.
6. A process according to any one of the preceding claims in which the dehydrogenation catalyst capable of adsorbing hydrogen is a reducible metal oxide, optionally with a metal selected from Group IB, IIB and Group VIII of the periodic table.
7. A process according to claim 6 in which the dehydrogenation catalyst is gold/ceria.
8. A process according to any one of claims 1 to 5 in which the dehydrogenation catalyst incapable of adsorbing hydrogen is a non-reducible metal oxide with a metal selected from Group IB, IIB, IVA VIB and VIII of the periodic

tention capability and showed to retain 4 cm<sup>3</sup>/g of hydrogen at 400 °C.

### Example 2 - Dehydrogenation of Ethane

The process as described above with reference to Figure 1 was carried out at 500 °C in a 7 mm internal diameter quartz reactor at 1 barA, using 25% v/v ethane in helium at a flow rate of 40 cm<sup>3</sup>/min (at STP) and the gold/ceria catalyst (4 g) prepared as disclosed in Example 1. The regeneration was carried out at the same temperature, pressure and flow rate using 5% oxygen in helium.

#### (i) Ethane Addition to a Regenerated Catalyst

Gas chromatographic and mass spectral analysis of the exit gas stream indicated a high conversion of ethane to ethene initially with no hydrogen being present. Water and some methane were also detected in the exit gas. The concentration of ethene reached a maximum, 5% v/v, before decreasing to approximately 1% v/v. 5% v/v is above the expected thermodynamic equilibrium value of 2% v/v. The conversion and selectivity calculated from the exit gas analysis gave a maximum in ethane conversion of approximately 28% with an ethene selectivity of 95%. The conversion was then found to fall to approximately 4% with a selectivity of 85% when hydrogen breakthrough into the exit gas occurred as the hydrogen adsorption capacity of the ceria became saturated. The thermodynamic equilibrium conversion under the conditions used for the experiments was approximately 8%.

An intermediate purge using helium rather than steam was used to separate the ethane and oxygen containing gases.

#### (ii) Regeneration

Gas chromatographic and mass spectral analysis of the exit gas showed a large quantity of carbon dioxide to be released from the catalyst bed prior to oxygen breakthrough into the exit gas. Some water was also observed.

The cumulative performance data calculated through a complete process cycle (starting at the regeneration stage) gives a cumulative ethane conversion of approximately 28% with a cumulative ethene selectivity of 20% at the maxima in ethene productivity.

### Claims

1. A continuous process for the dehydrogenation of a hydrocarbon and/or oxygenated hydrocarbon feed, which process comprises contacting the hydrocarbon and/or oxygenated hydrocarbon feed at an elevated temperature in a reaction zone with a dehydrogenation catalyst sys-

tem characterised in that the dehydrogenation catalyst is a catalyst capable of retaining hydrogen or is a catalyst incapable of retaining hydrogen, said catalyst incapable of retaining hydrogen in combination with a hydrogen retention agent

(a) is contacted with the feed to form a dehydrogenated product and hydrogen, wherein at least some of the hydrogen formed is adsorbed by the dehydrogenation catalyst or the hydrogen retention agent or reacted with the catalyst or the hydrogen retention agent to reduce at least part of the catalyst or hydrogen retention agent;

(b) removing from the reaction zone the dehydrogenated product and any hydrogen which is not adsorbed by or reacted with the catalyst system;

(c) regenerating the catalyst system by removing at least some of the adsorbed hydrogen from the catalyst or hydrogen retention agent and/or oxidising at least some of the reduced catalyst or hydrogen retention agent by contacting the catalyst or retention agent with an oxygen-containing gas thereby providing heat to maintain the catalyst at the elevated temperature.

(d) re-using the regenerated catalyst system from step (c) in step (a).

2. A process according to claim 1 in which the hydrocarbon feed comprises one or more alkanes.
3. A process according to claim 2 in which the alkane is a C<sub>2</sub>, C<sub>3</sub> or C<sub>4</sub> alkane.
4. A process according to claim 1 in which the hydrocarbon feed is an alcohol.
5. A process according to claim 4 in which the alcohol is a C<sub>1</sub> to C<sub>20</sub> alcohol.
6. A process according to any one of the preceding claims in which the dehydrogenation catalyst capable of adsorbing hydrogen is a reducible metal oxide, optionally with a metal selected from Group IB, IIB and Group VIII of the periodic table.
7. A process according to claim 6 in which the dehydrogenation catalyst is gold/ceria.
8. A process according to any one of claims 1 to 5 in which the dehydrogenation catalyst incapable of adsorbing hydrogen is a non-reducible metal oxide with a metal selected from Group IB, IIB, IVA VIB and VIII of the periodic



table.

9. A process according to any one of the preceding claims in which the elevated temperature is from 150 to 1200 °C.
10. A process according to claim 8 in which the elevated temperature is from 500 to 1200 °C.
11. The use of a dehydrogenation catalyst capable of retaining hydrogen or a dehydrogenation catalyst incapable of retaining hydrogen in combination with a hydrogen retention agent in the dehydrogenation of a hydrocarbon and/or oxygenated hydrocarbon feed.

#### Patentansprüche

1. Kontinuierliches Verfahren zur Dehydrierung eines Zustroms aus Kohlenwasserstoff und/oder sauerstoffhaltigem Kohlenwasserstoff, umfassend das In-Kontakt-Bringen des Zustroms aus Kohlenwasserstoff und/oder sauerstoffhaltigem Kohlenwasserstoff bei erhöhter Temperatur in einer Reaktionszone mit einem Dehydrierungskatalysatorsystem, dadurch gekennzeichnet, daß es sich bei dem Dehydrierungskatalysator um einen Katalysator, der Wasserstoff zurückhalten kann, oder um einen Katalysator, der keinen Wasserstoff zurückhalten kann, handelt, wobei der Katalysator, der keinen Wasserstoff zurückhalten kann, in Kombination mit einem Wasserstoffrückhaltemittel vorliegt,
  - (a) unter Bildung eines dehydrierten Produkts und Wasserstoff mit dem Zustrom in Kontakt gebracht wird, wobei wenigstens ein Teil des gebildeten Wasserstoffs von dem Dehydrierungskatalysator oder dem Wasserstoffrückhaltemittel adsorbiert wird oder unter Reduktion wenigstens eines Teils des Katalysators oder Wasserstoffrückhaltemittels mit dem Katalysator oder dem Wasserstoffrückhaltemittel umgesetzt wird;
  - (b) Entfernen des dehydrierten Produkts und des Wasserstoffs, der nicht von dem Katalysatorsystem adsorbiert oder mit diesem umgesetzt wurde, aus der Reaktionszone;
  - (c) Regenerieren des Katalysatorsystems durch Entfernen wenigstens eines Teils des adsorbierten Wasserstoffs aus dem Katalysator oder Wasserstoffrückhaltemittel und/oder Oxidieren wenigstens eines Teils des reduzierten Katalysators oder Wasserstoffrückhaltemittels durch In-Kontakt-Bringen des Katalysators oder Rückhaltemittels mit einem sauerstoffhaltigen Gas, wodurch

Wärme geliefert wird, um den Katalysator auf der erhöhten Temperatur zu halten;  
(d) Wiederverwenden des regenerierten Katalysatorsystems aus Schritt (c) in Schritt (a).

2. Verfahren gemäß Anspruch 1, bei dem der Kohlenwasserstoffzustrom ein oder mehrere Alkane umfaßt.
3. Verfahren gemäß Anspruch 2, bei dem das Alkan ein C<sub>2</sub>-, C<sub>3</sub>- oder C<sub>4</sub>-Alkan ist.
4. Verfahren gemäß Anspruch 1, bei dem der Kohlenwasserstoffzustrom ein Alkohol ist.
5. Verfahren gemäß Anspruch 4, bei dem der Alkohol ein C<sub>1</sub>- bis C<sub>20</sub>-Alkohol ist.
6. Verfahren gemäß einem der vorangehenden Ansprüche, bei dem der Dehydrierungskatalysator, der Wasserstoff adsorbieren kann, ein reduzierbares Metalloxid ist, gegebenenfalls mit einem Metall, das aus Gruppe IB, IIB und Gruppe VIII des Periodensystems ausgewählt wird.
7. Verfahren gemäß Anspruch 6, wobei es sich bei dem Dehydrierungskatalysator um Gold/Ceroxid handelt.
8. Verfahren gemäß einem der Ansprüche 1 bis 5, bei dem der Dehydrierungskatalysator, der keinen Wasserstoff adsorbieren kann, ein nichtreduzierbares Metalloxid mit einem Metall, das aus Gruppe IB, IIB, IVA, VIB und VIII des Periodensystems ausgewählt wird, ist.
9. Verfahren gemäß einem der vorangehenden Ansprüche, bei dem die erhöhte Temperatur 150 bis 1200 °C beträgt.
10. Verfahren gemäß Anspruch 9, bei dem die erhöhte Temperatur 500 bis 1200 °C beträgt.
11. Verwendung eines Dehydrierungskatalysators, der Wasserstoff zurückhalten kann, oder eines Dehydrierungskatalysators, der keinen Wasserstoff zurückhalten kann, in Kombination mit einem Wasserstoffrückhaltemittel bei der Dehydrierung eines Zustroms aus Kohlenwasserstoff und/oder sauerstoffhaltigem Kohlenwasserstoff.

#### Revendications

1. Procédé continu de déshydrogénation d'une charge d'hydrocarbures et/ou d'hydrocarbures



oxygénés, procédé qui comprend la mise en contact de la charge d'hydrocarbure et/ou d'hydrocarbure oxygéné à une température élevée dans une zone réactionnelle avec une formulation de catalyseur de déshydrogénation, caractérisé en ce que le catalyseur de déshydrogénation est un catalyseur capable de retenir l'hydrogène, ou est un catalyseur incapable de retenir l'hydrogène, ledit catalyseur incapable de retenir l'hydrogène, en association avec un agent de rétention d'hydrogène,

(a) est mis en contact avec la charge d'alimentation pour former un produit de déshydrogénation et de l'hydrogène, au moins une partie de l'hydrogène formé étant adsorbée par le catalyseur de déshydrogénation ou l'agent de rétention d'hydrogène ou étant soumise à une réaction avec le catalyseur ou l'agent de rétention d'hydrogène pour réduire au moins une partie du catalyseur ou de l'agent de rétention d'hydrogène ;

(b) le produit de déshydrogénation et toute quantité d'hydrogène qui n'est pas adsorbée par, ou amenée à réagir avec, la formulation de catalyseur sont évacués de la zone réactionnelle ;

(c) la formulation de catalyseur est régénérée en éliminant au moins une partie de l'hydrogène adsorbé du catalyseur ou de l'agent de rétention d'hydrogène et/ou en oxydant au moins une partie du catalyseur ou de l'agent de rétention d'hydrogène réduit par mise en contact du catalyseur ou de l'agent de rétention avec un gaz contenant de l'oxygène, ce qui fournit de la chaleur pour le maintien du catalyseur à la température élevée ;

(d) la formulation de catalyseur régénérée de l'étape (c) est réutilisée dans l'étape (a).

2. Procédé suivant la revendication 1, dans lequel la charge d'hydrocarbures comprend un ou plusieurs alcanes.

3. Procédé suivant la revendication 2, dans lequel l'alcane est un alcane en  $C_2$ ,  $C_3$  ou  $C_4$ .

4. Procédé suivant la revendication 1, dans lequel la charge hydrocarbonée est un alcool.

5. Procédé suivant la revendication 4, dans lequel l'alcool est un alcool en  $C_1$  à  $C_{20}$ .

6. Procédé suivant l'une quelconque des revendications précédentes, dans lequel le catalyseur de déshydrogénation capable d'adsorber l'hydrogène est un oxyde métallique réductible,

facultativement avec un métal choisi dans les groupes IB, IIB et VIII du Tableau Périodique.

7. Procédé suivant la revendication 6, dans lequel le catalyseur de déshydrogénation consiste en or/oxyde de cérium.

8. Procédé suivant l'une quelconque des revendications 1 à 5, dans lequel le catalyseur de déshydrogénation incapable d'adsorber l'hydrogène est un oxyde métallique non réductible formé avec un métal choisi dans les groupes IB, IIB, IVA, VIB et VIII du Tableau Périodique.

9. Procédé suivant l'une quelconque des revendications précédentes, dans lequel la température élevée est comprise dans l'intervalle de 150 à 1200 °C.

10. Procédé suivant la revendication 9, dans lequel la température élevée est comprise dans l'intervalle de 500 à 1200 °C.

11. Utilisation d'un catalyseur de déshydrogénation capable de retenir l'hydrogène ou d'un catalyseur de déshydrogénation incapable de retenir l'hydrogène en association avec un agent de rétention d'hydrogène dans la déshydrogénation d'une charge d'hydrocarbures et/ou d'hydrocarbures oxygénés.

