

INDUSTRIAL EQUIPMENT FOR THE HOT RECYCLING OF ASPHALT MIXES

FIELD OF INVENTION

5 The present invention relates to the industry of processing and transformation of solid asphalt residues, and more particularly it refers to an industrial equipment for the hot recycling of asphalt mixes.

BACKGROUND OF INVENTION

10 All over the world there are asphalt-paved highways, driveways, avenues, and streets. Asphalts in pavement are 100% recyclable; they can be recycled many times. Asphalts are mainly composed of asphaltenes and maltenes. Asphalts are exposed to weathering, which provokes aging due to a decrease in the
15 maltenes phase, produced by oxidation.

 Asphalt pavements are flexible, but aging and lack of maltenes cause them to be rigid, which causes cracking (alligator skin) and a subsequent detachment of blocks.

20 In the market, there are plants manufactured abroad with attachments to process asphalt mixes, in lower percentages. These are large plants, highly expensive and not easily transportable. Moreover, the process used differs from this invention, as explained below.

25 These plants have a device between the first and the second third of the rotary dryer, into which a lesser percentage of RAP (Reclaimed Asphalt Pavement or Recycled Asphalt Pavement) enters by means of a hopper, with the purpose of mixing it with a high content of hot unadulterated stone
30 materials, which will heat it toward recycling.

These industrial equipments present the following disadvantages:

- 5 a) Recycled RAP percentage is very low.
- b) Supplying of rejuvenating agent cannot be made in the manner conducted in this equipment
- 10 c) Lower quality of resulting material.
- d) Large equipment not easily transportable.
- e) Highly expensive.
- 15 There are other equipments for production of asphalt mixes called double barrel, such as the one disclosed in international request WO 2007/103345.

These industrial equipments present the following disadvantages:

- 20 a) RAP is not 100% recycled.
- b) Large size, not easily transportable because these equipments are provided with: the first dryer adapted to receive and mix unadulterated aggregates and fine RAP; a primary burner adapted to produce a burner flame for heating and drying fine aggregates in the first dryer; a second dryer adapted to receive ordinary RAP; the second burner adapted to produce a burner flame and to dry the ordinary RAP in the second dryer; a mixer adapted to receive unadulterated aggregates and fine RAP from the first dryer and the ordinary RAP from the second dryer and mix the unadulterated aggregates, the fine RAP and the ordinary RAP to produce a hot asphalt mix.
- 25
- 30
- c) Highly expensive.

5 In the state of the art, it was found patent MX 183720 of Robert H. Nath, et al., filed on August 08, 1992 and granted on January 9, 1997, which holder is Cycleclean, Inc. claiming US priorities US754264 and US803642. Said patent protects an apparatus to control the production speed at a drum plant to produce asphalt from pavement, recycled asphalt; characterized in that it comprises a combination: assembly to detect tons per hour (TPHa) produced at the plant; assembly to compare tons per hour (TPHa) with tons per hour desired (TPHd); assembly to detect the drum inlet gas temperature, when (TPHd) is lower than (TPHa); assembly to compare the drum inlet gas temperature (TDI) at a maximum drum inlet gas temperature (TDI_{max}); assembly to increase the drum inlet gas temperature (TDI), when the drum inlet gas temperature (TDI) is lower than the maximum drum inlet gas temperature (TDI) and assembly to increase the hourly rating when the drum inlet gas temperature (TDI) is increased.

15 It was also found Mexican patent MX192620 of Robert H. Nath et al., filed on November 27, 1992 and granted on July 13, 1999, which holder is Cycleclean, Inc., and claiming US priorities US803642 and US951084. Said patent protects an apparatus to control production speed at a drum plant to produce asphalt from pavement, recycled asphalt; characterized for comprising combination: assembly to detect tons per hour (TPHa) produced at the plant; assembly to compare tons per hour (TPHa) with tons per hour desired (TPHd); assembly to detect the drum inlet gas temperature, when (TPHd) is lower than (TPHa); assembly to compare the drum inlet gas temperature (TDI) at a maximum drum inlet gas temperature (TDI_{max}); assembly to increase the drum inlet gas temperature (TDI), when the drum inlet gas temperature (TDI) is lower than the maximum drum inlet gas temperature (TDI) and assembly to increase the hourly rating when the drum inlet gas temperature (TDI) is increased.

30 However, the processes applied in this type of equipment differ from those in the present invention.

Besides, in document E2 184 964 published on March 4, 1988, discloses a drum mixer for asphalt concrete production comprising a drum rotating about one axis; the drum has an inlet in the first end of the drum to receive gravel flowing downstream along the drum toward a second end of the drum opposite to the first end, and an outlet next to the second end to discharge asphalt concrete. The drum is provided with a burner with a burner head to generate a flame delimiting a combustion volume, located in the middle of the first and second ends of the drum; the burner head divides the drum in a drying zone located between the burner head and the first end of the drum, and a mixing zone located between the burner head and the second end of the drum. The head generates hot combustion gases flowing upstream along the drum through the drying zone toward the first end of the drum in a counterflow relation with respect to the gravel flow from the first end, through the drying zone, toward the second end of the drum to dry the gravel. Drum has a plurality of radiant heat shielded paddles separated inward a portion of inner wall of the drum extending circumferentially; the paddles extend from a portion within the drum next to the burner head in general axially toward the first end of the drum and circumferentially to the drum surrounding the combustion volume at the inner side of the paddles and delimiting a chamber substantially annular between the paddles and the portion of the inner wall of the drum. Next to an upstream end of the plurality of paddles there is a drum inlet for placing a recycling asphalt material in the annular chamber, being the paddles circumferentially separated from each other with respect to the drum in order to cause the received gravel flowing inside the combustion volume and along some surfaces radially internal to it, from the upstream flow gravel, in general radially outwards between the paddles and into the chamber to be mixed with the recycling asphalt material in the chamber, while the paddles substantially avoid a back-flow of gravel from the chamber to the inside of the combustion volume. This is intended to produce asphalt concrete with higher returns and reduce heat loss and, particularly, to produce an asphalt concrete product from the recycling gravel and unadulterated gravel, where a recycling asphalt material with higher humidity content can be combined with the unadulterated gravel without reducing the production capacity or increase of the residence time.

Document US 4 095 285 published on June 13, 1978, discloses a slanting rotary mixing drum to prepare coated products (e.g. products of asphalt concrete or hot or cold asphalt products/ mixtures of aggregate) which comprises, at the frontal end a burner extending inside that frontal end; a pipe to spray the aggregate, this pipe extends inside the drum with adjustable length; the first zone provided with paddles extending inside the drum and extending in "spiral" in the inner surface of the drum, where the pitch of the "spiral" is set to be sufficiently thick for the material to be rapidly introduced inside the next zone of the drum; paddles are intended only to guide and transport the aggregates from the first zone to the second zone, said second zone is an pre-heating zone, used to pre-dry, from this second zone the drum has material lifting elements that lift the material up to a given height for the material to subsequently fall during the drum rotation; a third zone to dry, mix and heat the product coming from the second zone, at this zone an aggregate is discharged through a pipe; an anti-dust screen is provided at the end of the third zone to prevent the dust escaping from the rotary drum. In this way, a device is provided to obtain coated materials through pre-heating, pre-drying and mixing, and the coating is performed under satisfactory conditions and the residual humidity content of the aggregate coat results in a low dust emission.

It is clear that none of the above documents discloses a continuous helix (as shown in figure 2 of this application), and said helix takes 30-80%, preferably a 60%, of the total length of the rotary cylinder, which allows recycling 100% of RAP.

OBJECTIVE OF THE INVENTION

5 The main objective of the present invention is to make available an industrial equipment for the hot recycling of asphalt mixes to recycle aged asphalt pavements.

10 Another objective of this invention is to provide this industrial equipment for the hot recycling of asphalt mixes to obtain a hot recycled asphalt mix of excellent quality and higher durability.

Another objective of this invention is to provide this industrial equipment for the hot recycling of asphalt mixes, being also sustainable and ecological.

15 Another objective of this invention is to provide this industrial equipment for the hot recycling of asphalt mixes also reducing the use of unadulterated stone materials and avoiding depredation of woods, hills and rivers.

20 Another objective of this invention is to provide this industrial equipment for the hot recycling of asphalt mixes, which also uses the asphalt contained in the RAP thereby decreasing the excessive use of fossil hydrocarbons, which tend to be more expensive and scarce.

25 A further objective of this invention is to provide this industrial equipment for the hot recycling of asphalt mixes to secure sustainability of pavements in the long term.

30 Another objective of this invention is to make available this industrial equipment for the hot recycling of asphalt mixes permitting to recycle 100% RAP and avoiding clandestine disposition of RAP.

35 Another objective of this invention is to make available this industrial equipment for the hot recycling of asphalt mixes also avoiding the use of confined areas which may be occupied by organic materials producing methane gas for electric power generation.

Another objective of this invention is to make available this industrial equipment for the hot recycling of asphalt mixes to further reduce cost of road rebuilding.

5

And all other attributes and objectives which will be clearly evident upon making a general and detailed description of this invention supported by the illustrated modalities.

10

BRIEF DESCRIPTION OF THE INVENTION

For the development of the equipment and process for the hot recycling of asphalt mixes, different tests were conducted with the following objectives: an indirectly heating equipment allowing to recycle 100% RAP; with sufficient production capacity; of low cost; portable, easy to install and uninstall; that the material to be recycled not be subject to combustion because asphalt lose properties; with good energy transfer for lowering costs; with option to supply unadulterated stone material to improve the recycled asphalt mixture; allowing a controlled metering of RAP and unadulterated stone material prior to the Industrial Hot Recycling Asphalt Mixes for a good quality of recycled asphalt mixture and also to have a built-in zone for mixing RAP materials, stone materials, asphalt-rejuvenating agent enhanced with polymers, in an optimal metering to obtain an asphalt mixture of excellent quality.

25

As it is known, asphalts are mainly composed of asphaltenes and maltenes. Asphalts are exposed to weathering leading to aging; such aging is due to the decrease in the maltenes phase, produced by oxidation. Asphalt pavements are flexible, but aging and lack of maltenes cause them to be rigid, which causes cracking (alligator skin) and a subsequent detachment of blocks. If the same portion of lost maltenes are added to those asphalts they regained their original physical and chemical characteristics.

30

Better yet when those added maltenes are enhanced with polymers, the asphalts exceed their original physical and chemical characteristics.

It is internationally known in the field of roadways construction the term of RAP (Reclaimed Asphalt Pavement or Recycled Asphalt Pavement).

RAP is obtained through:

5

1. Milling of the asphalt surface, which may be in cold or previously preheating the asphalt surface

2. Milling of the preheated asphalt surface.

10

3. Blocks of Asphalt Mixture obtained in reconstructions. The size of these materials are reduced through grinding systems.

15 In general terms, the industrial equipment for the hot recycling of asphalt mixes according to the present invention comprises a portable bank of hoppers of continuous metering of RAP and unadulterated stone materials; this metering system is necessary to adjust the granulometric curve of the Resulting Recycled Asphalt Mixture. The bank of hoppers are mounted on a supporting structure that include gear motors with frequency converter (as observed in figure 1), in
20 order to control the metering amount of RAP and unadulterated stone material; such gear motors send a signal to a RAP flow indicator. Also an input flow indicator of unadulterated stone material sends another signal to a control panel where it is recorded and controlled; such control panel may be adjacent or located remotely. Below the portable bank of hoppers used for metering,
25 there is a conveyor belt that receives RAP and unadulterated stone material and transport them to the steel plate rotary cylinder supported on 4 load rollers also used as a power system to rotate the cylinder.

30 The diameter and length of the rotary cylinder depend on the production capacity required. The inner part of the cylinder is provided with an internal metal helix forming a circular space in the middle forming a flame conduction zone through its internal portion thus generating the indirect heating zone. The helix takes 30-80%, preferably a 60%, of the total length of the rotary cylinder. The remaining percentage is made by straight paddles located in the internal
35 perimeter of the cylinder defining the mixing zone.

At the point in which the helix ends and the mixing paddles begin, there is the injection of asphalt – rejuvenating agent enhanced with polymers (injected mixture); this injection is made through a volumetric gear pump through an injection pipe coming from the storage tank.

The rotary cylinder is provided with an industrial open-flame burning system used to transmit heat energy to the RAP and to the supply of stone material. The heat capacity of the industrial burner depends on the recycling production requirements.

The fire of the industrial burner makes no contact with the RAP or stone materials since they are protected by the metal walls of the helix, thus forming the zone for indirect heating of the materials to be processed. The direction of the flame is parallel to the direction of the heating flow of RAP and supply of unadulterated stone material.

These RAP materials, stone materials, asphalt-rejuvenating agent enhanced with polymers, in their optimal metering and temperature, arrive to the mixing zone where they homogenized forming a hot asphalt mixture.

This hot asphalt mix moves toward the outlet where there is an assembly made of paddles expelling it from the rotary cylinder, that mix then passes to a recycled asphalt mix lifting system serving as a paddle conveyor, to a silo of recycled asphalt mix for discharging into trucks for purposes of transportation and application on roads.

The outlet of the rotary cylinder of the industrial equipment for the hot recycling of asphalt mixes comprises a temperature sensor that sends a signal to the recycled asphalt mix temperature indicator in the control panel where it is recorded and controlled.

5 The industrial equipment for the hot recycling of asphalt mixes is provided with a gear motor with frequency converter under the rotary cylinder that through transmissions and load rollers causes the rotation of the industrial equipment cylinder.

10 The frequency converter is controlled from the control panel in order to increase or decrease the rotation speed of the industrial equipment cylinder. This is made to maintain an optimal temperature of the recycled asphalt mixture.

15 This parameter is very important because when the exhaust temperature of the recycled asphalt mixture is over the optimal temperature, the frequency of the converter is increased in order to process a higher amount of material and in this way to decrease the exhaust temperature of the recycled asphalt mixture.

20 On the contrary, when the exhaust temperature of the recycled asphalt mixture is below the optimal temperature, the frequency of the converter is decreased in order to process a lower quantity of material and in this way to increase the exhaust temperature of the recycled asphalt mixture.

25 The industrial equipment for the hot recycling of asphalt mixes is provided with a tank for storing asphalt-rejuvenating agent enhanced with polymers.

30 Said storage tank is a cylindrical horizontal tank with a temperature control heating system, equipped with temperature sensor systems, that sends a signal to the asphalt-rejuvenating agent enhanced with polymers temperature indicator located in the control panel.

35 This tank is also provided with a system to meter asphalt-rejuvenating agent enhanced with polymers through a volumetric gear pump which injects through a pipe until the mixing zone.

11

This system to meter the asphalt-rejuvenating agent enhanced with polymers has a flow sensor that sends a signal to the asphalt – rejuvenating agent enhanced with polymers flow indicator located in the control panel for registration.

5

The industrial equipment for the hot recycling of asphalt mixes is also provided with a fuel storage tank. This is a cylindrical horizontal tank containing the industrial liquid fuel to be used in the industrial burning system of the rotary cylinder of the industrial equipment for the hot recycling of asphalt mixes.

10

The control panel comprises instruments to measure temperatures, material metering control; RAP; stone materials, asphalt-rejuvenating agent enhanced with polymers of the industrial equipment for the hot recycling of asphalt mixes.

15

From this point, the production is operated and the quality of the hot recycled asphalt mix is controlled, in the industrial equipment for the hot recycling of asphalt mix.

20

The process for the hot recycling of asphalt mixes includes the following steps:

I. Preliminary analysis

25

1. Lab test of the samples of pavement to be recycled.

a) Determination of the existing granulometry.

30

b) Determination of the percentage of supply of unadulterated stone material to optimize the granulometry of the Recycled Asphalt Mix.

c) Determination of the degree of aging of RAP through testing of penetration, viscosity, softening point.

35

12

e) Determination of the amount of supply of Asphalt-Rejuvenating Agent enhanced with Polymers to restore the physical and chemical properties of the asphalt to reach optimal content of asphalt in the Recycled asphalt mix.

5 2.- Milling of the asphalt surface.

10 a.- Cold: Cold milling modifies the granulometric curve of the Asphalt Mix. It also modifies the asphalt content in the Asphalt Mix. This is corrected by supplying the unadulterated stone material before introducing the materials into the Industrial Recycling Equipment. The content of asphalt is corrected by supplying the lacking quantity of asphalt-rejuvenating agent enhanced with polymers, in the mixing zone until reaching the optimal content of project.

15 b.- Hot: Hot milling does not modify the granulometric curve of the Asphalt Mix. It neither modifies the asphalt content in the Asphalt Mix.

20 3. Loading and Transportation of RAP into the Industrial Equipment for Hot Recycling of Asphalt Mixes.

25 4.- RAP is deposited in one of the Hopper of the Hopper System and the unadulterated stone material is deposited in the remaining hoppers.

30 5. The RAP and the supply of stone materials are metered by means of the hopper system. This metering is made based on a previous lab test to determine the optimal supply of unadulterated stone material to obtain an optimal granulometric curve. The hopper system is provided with a belt conveying the mixture of RAP and supply of exhausted stone materials, a weight measuring and control system to record the amount of material to be supplied in weight into the Industrial Equipment for Hot Recycling Asphalt Mixes.

35 6.- The RAP material and the supply of stone material are introduced into the rotary cylinder of the Industrial Equipment for the Hot Recycling of Asphalt Mixes through a belt conveying the mixture of RAP and supply of stone materials.

II. Hot Recycling of Asphalt Mixes

5 1. Upon entering the RAP and the supply of unadulterated stone material in the Industrial Equipment for the Hot Recycling of Asphalt Mixes, they are indirectly heated because they are protected from fire through the metal walls of the internal helix until the RAP material and the supply of the stone material reach optimal temperatures at which the solid asphalt in RAP becomes liquid without reaching combustion. These temperatures can be 140-160 °C preferably.

10 This heating is produced indirectly since fire does not contact the materials to be recycled for being protected by the metal walls of the helix. The materials to be recycled move due to the rotation of the metal helix inside the cylinder up to the mixing zone. The helix takes from 30-80%, preferably a 60%, of the length of the cylinder, and the rest is located in the mixing zone. This
15 proportion has allowed the optimization of the mixing and heating process to recycle 100% of RAP, as mentioned above.

2.- Once the materials to be recycled reach the mixing point, they are injected with asphalt – rejuvenating agents enhanced with polymers through a pipe to
20 improve the characteristic of the resulting Asphalt Recycled Mix.

The Rejuvenating Agent modified with polymers, with a percentage of asphalt, metered in optimal amounts to the mixture of RAP and supply of unadulterated stone material will result in a hot recycled asphalt mix of
25 excellent quality.

By conducting a preliminary lab test, the optimal metering is determined to achieve the desired amount by combining:

30 a) RAP

b) Unadulterated stone materials

c) Asphalt

35

d) Rejuvenating Agent enhanced with Polymers

5 In order to readily understand the features of this invention, the foregoing description includes, as an integral part, the drawings as a way of illustration but not of limitation, described below corresponding to the preferred embodiment.

BRIEF DESCRIPTION OF THE FIGURES

10 Figure 1 shows a conventional perspective view of the industrial equipment for the hot recycling of asphalt mixes.

15 Figure 2 shows a conventional perspective view of the internal part of the rotary drum of the industrial equipment for the hot recycling of asphalt mixes.

Figure 3 shows a conventional perspective view of the control panel of the industrial equipment for the hot recycling of asphalt mixes.

20 For a better understanding of this invention, a detailed description of any of its embodiments will be made, shown in the drawings that as a way of illustration but not of limitation are attached to the present description.

DETAILED DESCRIPTION OF THE INVENTION

25 The characteristic details of the industrial equipment for the hot recycling of asphalt mixes are clearly shown in the following description and in the illustrative drawings attached, the same reference signals are used to indicate the same parts.

30 As for figure 1 that shows a conventional view of the industrial equipment for the hot recycling of asphalt mixes comprising a portable bank of hoppers for continuous metering 1 preferable comprising a hopper for metering of RAP 2 and two or more compartments of hoppers for metering of unadulterated stone materials 3 necessary to adjust the granulometric curve of the resulting recycled asphalt mixture, mounted on a supporting structure that include gear motors 4 with frequency converter in its conveyor belt (see figure 1), in order to control the amount of metering of RAP and unadulterated stone material; which send a signal to a RAP flow indicator 34 (see Fig. 3) and an unadulterated stone material flow indicator 35 (see Fig. 3) to a control panel 5 where it is recorded, which may be adjacent or remotely located; below of that portable bank of hoppers used to meter 1, there is a conveyor belt 6 receiving RAP and unadulterated stone material and transporting them to a rotary cylinder 7 in steel plate, supported on four load rollers 8 also used as a power system to rotate the cylinder, and mounted on a supporting structure 9.

45

5 The rotary cylinder 7 is provided with an industrial open-flame burning system 10 mounted at the beginning of the rotary cylinder 7 in order to transmit the heat energy to the RAP and to the supply of stone material. The heat capacity of the industrial burner 10 depends on the requirements of production of the hot recycled asphalt mix.

10 The industrial equipment for the hot recycling of asphalt mixes is provided with a tank for storing asphalt-rejuvenating agent enhanced with polymers 11 from which the mixture of asphalt-rejuvenating agent enhanced with polymers is metered through a volumetric gear pump 12 injecting through a pipe 13 until the mixing zone 24 (see Fig. 2)

15 These RAP materials, stone materials, asphalt-rejuvenating agent enhanced with polymers, in their optimal metering and temperature, arrive to the mixing zone 24 (see Fig. 2) within the rotary cylinder 7 where they homogenized, said mixing zone 24 has a plurality of mixing paddles located in the internal part of the rotary cylinder 7, and that plurality of paddles is formed by two series of paddles 23 separated one from the other, one of
20 these series is formed by straight teethed paddles for mixing and the second series is "V" shaped.

25 This hot asphalt mix moves toward the outlet where there is an assembly made of paddles 23b (see Fig. 2) that expels the mix from the rotary cylinder 7, from there it moves to a recycled asphalt mix lifting system 14, which serves as a paddle conveyor, to a silo of recycled asphalt mix 15 used to discharge it into trucks for purposes of transportation and application on roads.

30 The outlet of the rotary cylinder 7 of the industrial equipment for the hot recycling of asphalt mixes is provided with a temperature sensor 24b (see Fig. 2) that sends a signal to the recycled asphalt mixture temperature indicator in the control panel 5 where it is recorded.

16

5 The industrial equipment for the hot recycling of asphalt mixes is provided with a gear motor with frequency converter 16 under the rotary cylinder that, through transmissions and load rollers 8, makes the cylinder 7 of the industrial equipment to rotate.

10 The frequency converter is controlled from the control panel 5 in order to increase or decrease the rotation speed of the industrial equipment cylinder. This is intended to control the optimal temperature of the recycled asphalt mixture.

15 This parameter is very important because when the exhaust temperature of the recycled asphalt mixture is over the optimal temperature, the frequency of the converter is increased in order to process a higher amount of material and in this way to decrease the exhaust temperature.

20 On the contrary, when the exhaust temperature of the recycled asphalt mixture is below the optimal temperature, the frequency of the converter is decreased in order to process a lower amount of material and in this way to increase the exhaust temperature of the recycled asphalt mixture.

25 The industrial equipment for the hot recycling of asphalt mixes also has a fuel storage tank 17. This is a cylindrical horizontal tank containing the industrial liquid fuel to be used in the industrial burning system 10 of the rotary cylinder 7 of the industrial equipment for the hot recycling of asphalt mixes.

Such rotary cylinder 7 comprises a combustion gas extractor 18 through which combustion gases are discharged.

30 A weight measuring element 19 is provided below the conveyor belt 6 at the inlet of the rotary cylinder 7, recording the amount of RAP material and the supply of unadulterated stone material to be provided in weight to the Industrial Equipment for the Hot Recycling of Asphalt Mixes. And it also sends a signal to RAP flow indicator 34 (see Fig. 3), and the supply of unadulterated stone material flow indicator 35 (see Fig. 3) to a control panel 5.

As for figure 2 that shows a conventional perspective view of the internal part of the rotary drum of the industrial equipment for the hot recycling of asphalt mixes. In that figure, the internal part of rotary cylinder 7 is provided with an internal metal helix 20 delimiting the walls of the helix 26 a circular space in its center thereby forming the flame conduction zone 21 through its inner part and between those metallic walls of the helix there is a zone to convey RAP and supply of unadulterated stone material 27, it is also generated an indirectly heating zone 22. The helix takes 30-80%, preferable a 60%, of the total length of the rotary cylinder. The rest of the percentage is formed by mixing straight paddles 23, located in the internal perimeter of the cylinder forming the mixing zone 24. This hot asphalt mix moves toward the outlet housing an assembly made of paddles 23b that expel it from the rotary cylinder 7, this point is provided with a temperature sensor 24b, which sends a signal to the recycled asphalt mix temperature indicator in the control panel 5 for registration. At the point where the helix ends and the mixing paddles begin, there is an injection point for injecting asphalt- rejuvenating agent enhanced with polymers 25, this injection is made through a volumetric gear pump of Asphalt-Rejuvenating Agent enhanced with polymers through an injecting pipe 13, coming from the storage tank 11 (see Fig. 1)

Figure 3 shows a conventional view of the control panel of the industrial equipment for the hot recycling of asphalt mixes. In this figure, the control panel 5 includes means of control to start and shut down the engines and gear motors of the industrial equipment 28, means of control of frequency converters of gear motors 29, indicators of amperage of engines and gear motors 30, recycled asphalt mix temperature indicators 31, asphalt-rejuvenating agent temperature indicators 32, indicators of temperature of the inner part of the rotary cylinder 33, RAP flow indicators 34, stone material supply flow indicator 35, asphalt-rejuvenating agent flow indicator 36 and a screen with the operation flow diagram of the industrial equipment 37.

5 The invention has been sufficiently described so that a person with average knowledge in the field to be able to reproduce and obtain the results we mentioned in the present invention. However, any person with skills in the technical area covering this invention may be able to make modifications not described in this application; however, if for the application of these modifications in a determined structure or in the manufacturing process of the same, it is required the subject matter mentioned in the following claims, such structures should be included within the scope of the invention.

CLAIMS

1. Industrial equipment for the hot recycling of asphalt mixes, characterised in that it comprises

a portable bank of hoppers which are used to meter RAP and unadulterated stone materials, which are mounted on a supporting structure, along with gear motors with frequency converter to control metering and sending a flow indicator signal to a control panel where it is recorded;

a conveyor belt is provided below the hopper bank to receive the material and transport it toward the inlet of the rotary cylinder, supported on four load rollers serving also as driving system to transmit the movement from a gear motor for cylinder rotation;

a tank for storing a mixture of asphalt - rejuvenating agent enhanced with polymers which is metered by a volumetric gear pump through a pipe towards the rotary cylinder, the outlet of said cylinder comprising a temperature sensor that sends the signal to the recycled asphalt mix temperature indicator in the control panel;

a recycled asphalt mix lifting system adjacent to an outlet of the rotary cylinder which conveys said mix to a discharge silo;

a combustion gas extractor in the rotary cylinder for discharging combustion gases from the burner;

a fuel storage tank used in the industrial burner and a weight measuring element is provided

under the conveyor belt at the inlet of the rotary drum, which records the amount of material to be supplied in weight, said cylinder comprises an open-flame industrial burner mounted at the beginning of the cylinder to transmit heat energy to the RAP and the supply of unadulterated stone material ; an inlet and an outlet;

an Internal continuous metal helix taking 30-80% of the total length of the rotary cylinder;

the walls of the helix form a circular space in its center forming a flame conduction zone, between said walls of the helix there is a zone for conduction or conveyance of RAP and supply of unadulterated stone material, in the flame direction, as the cylinder rotates, and generating a zone for indirect heat energy transfer, so that the solid asphalt contained in the RAP changes to its liquid phase, without reaching combustion;

an injection zone of asphalt-rejuvenating agent enhanced with polymers, adjacent to the end of the helix, a plurality of mixing paddles forming a mixing zone, which are located at the internal perimeter of said cylinder and after the metal helix, to mix the RAP and the supply of unadulterated stone material with the asphalt - rejuvenating agent modified with polymers injected;

a plurality of paddles for expelling the mixed material, adjacent to the mixing paddles, for a subsequent expulsion of the hot asphalt mix which has moved from the mixing paddles,

through the outlet of the metal cylinder, where such mixing and expelling paddles occupy the rest of the total length of the cylinder in order to recycle 100% RAP.

2. Industrial equipment for the hot recycling of asphalt mixes, according to claim 1, characterised in that said gear motor, transmits movement to the load rollers generating the rotation of the rotary cylinder; and it is provided with a frequency converter, which is controlled from the panel to regulate the rotation speed and control the temperature and capacity of production of the recycled asphalt mix.

3. Industrial equipment for the hot recycling of asphalt mixes, according to claim 1, characterised in that the asphalt-rejuvenating agent is improved with polymers.

4. Industrial equipment for the hot recycling of asphalt mixes, according to claim 1, characterised in that the helix preferably occupies 60% of the length of the rotary cylinder.

5. Industrial equipment for the hot recycling of asphalt mixes, according to claim 1, characterised in that said tank for storing asphalt-rejuvenating agent enhanced with polymers, consists in a horizontal cylindrical tank with heating system and temperature control, and with temperature sensor systems, which sends a signal to the asphalt-rejuvenating agent enhanced temperature indicator with polymers located in the control panel.

6. Industrial equipment for the hot recycling of asphalt mixes, according to claim 1, characterised in that the system that meters the asphalt-rejuvenating agent enhanced with polymers, includes a flow sensor that sends a signal to the asphalt-rejuvenating agent enhanced with polymers flow indicator in the control panel where it is recorded and controlled.

7. Industrial equipment for the hot recycling of asphalt mixes, according to the previous claims, characterised in that said control panel comprises

means to shut down and start the engines and gear motors of the industrial equipment;
means of control of frequency converters of gear motors;

indicators of amperage of engines and gear motors;

recycled asphalt mix temperature Indicators;

asphalt-rejuvenating agent temperature indicators;

indicators of temperature of the inner part of the rotary cylinder;

RAP flow indicator;

stone material supply flow indicator;

asphalt-rejuvenating agent flow indicator and a screen with the operation flow diagram of the industrial equipment.

8. A hot asphalt mixes recycling process, characterised in that it comprises the stages of:

providing an industrial equipment for the hot recycling of asphalt mixes of any of the preceding claims;

depositing RAP to be recycled in the hopper system;

depositing the unadulterated stone material in hoppers different from that containing RAP;

metering the RAP material and supply of stone materials through a hopper system, in the optimal amount;

measure the weight of the material to be supplied through a weight measuring element located under the conveyor belt, transporting RAP and supply of stone materials through the conveyor belt towards to the inlet of the rotary cylinder;

moving that material to the direction of the burner flame (parallel flow) by rotation of the rotary cylinder, from the inlet of the cylinder to its subsequent outlet, transporting the material deposited in the cylinder along the lower zone of the metal internal helix taking 30-80% of the total length of the rotary cylinder, by means of the walls of the metal helix delimiting the zone of conduction or conveyance of material;

indirectly heating the material at 140-160 °C by means of an open-flame industrial burner, mounted at the beginning of the rotary cylinder; the material is protected from direct fire by means of the metal walls of the internal helix of the cylinder;

for the heat transfer to change the asphalt contained in said RAP to its liquid phase, without reaching combustion;

injecting asphalt-rejuvenating agent enhanced with polymers to the material and then move it along the metal helix, through a pipe coming from the storage tank which is connected at an injection point located at the end of the metal helix;

mixing RAP and unadulterated stone material and the asphalt-rejuvenating agent modified with polymers by means of mixing paddles;

expelling from the metal cylinder the hot recycled asphalt mix through the expelling paddles; and

discharging combustion gases through the gas extractor during the recycling process.