

The present application claims priority from U.S. Patent Application Serial No. 09/374,499, entitled "LIQUID RESISTANT LAMINATE WITH STRONG BACKER", filed on August 13, 1999, which is related to co-pending and commonly assigned U.S. Patent Application Serial No. 09/173,065, entitled "LAMINATE", filed October 16, 1998, which is incorporated herein by reference. Reference is hereby made to the following co-pending, commonly assigned, U.S. Patent Applications: Serial No. 09/267,493, entitled "SYSTEM AND METHOD FOR TWO SIDED SHEET TREATING", filed March 12, 1999; Serial No. 09/249,033, entitled "PIGMENTED BACKER FILM AND METHOD OF PRODUCTION", filed February 11, 1999; Serial No. 09/226,572, entitled "SYSTEM AND METHOD FOR ADHERING LAMINATE TO AN ALTERNATE SUBSTRATE MATERIAL", filed January 7, 1999; Serial No. 09/294,723, entitled "LAMINATE EMPLOYING LIQUID RESISTANT

5 MADE FROM SUCH COMPOSITIONS AND METHOD OF MAKING, PRODUCTS
MADE FROM SUCH SUBSTRATES AND METHOD OF MAKING", filed September 26,
1998; and [Attorney Docket No. 47526-P020-992466], entitled "SYSTEM AND METHOD
FOR PRODUCING A LAMINATE EMPLOYING A PLASTIC FILM", filed July 29, 1999;
the disclosures of which are incorporated herein by reference.

systems and methods for manufacturing such products to include a liquid resistant film and

5

another laminate material providing a desired balancing characteristic to the laminated product.

cabinets, counter tops, flooring and other surfaces. In each of these applications, a decorative surface may be applied to a core layer or substrate, namely, plywood, particle board, chipboard, hardboard, wood waste, medium density fiberboard, high density fiberboard, inert mineral board, sheet rock, plaster board and other substances. The core layer or substrate may also be made of Alternate Substrate Materials (ASM). Such ASM may include non-wood cores or substrates, such as synthetic or non-cellulose substrate material, for example, recycled plastic substrates, ABS/PC, nylon, PVC, or the like. However, a core or substrate is not included with all laminate products.

Often, a backing layer is secured to the opposite side of the substrate to balance the movement of the decorative surface or provide other benefits. It is well known in the art that traditional high pressure laminates expand or contract with an increase or decrease in the environmental humidity. Moreover, it is also known that prolonged exposure of the flooring composite, made of laminates bound to a wood-based substrate, to liquids, for example water, such as by flooding through the sub-floor, adversely effects not only traditionally constructed laminates, but also the substrate, such as by causing swelling, peaking or blistering.

Generally the decorative surface of a laminate composite, such as a laminate flooring, is designed as shown in FIGURE 1. A high pressure laminate 10 may be comprised of a thin aluminum oxide incorporated overlay sheet 11 impregnated with a protective substance, such as melamine resin, which provides color fastness, hardness, chemical resistance, and also resistance to brief exposure to water. The high pressure laminate 10 may employ a decorative sheet 12 disposed under overlay sheet 11, which may be a melamine treated sheet, and sheets 13 and 14 of kraft paper impregnated with phenolic resin disposed below the decorative sheet.

Traditionally, the backing layer is similarly designed. As shown in FIGURE 1, the backing layer of a decorative high pressure laminate 10 may comprise two sheets 16 and 17 of kraft paper impregnated with phenolic resin disposed below substrate 15, and a balancing layer 18 of an overlay paper impregnated with a protective substance disposed below the kraft

As those of ordinary skill in the art will appreciate, the decorative and backing layers
discussed above are purely exemplary and not intended to limit the description of the present
invention to the above discussed structures.

After installation, such as by gluing several pieces of laminate flooring together at the
seams, the decorative laminate is subject to a different environment than the backer laminate.
That is, the exposed decorative laminate experiences temperature and humidity fluctuations of
the room environment. In contrast, the backer laminate, is exposed to temperature and
moisture changes of the sub-floor over which the laminate flooring is applied. Moreover,
prolonged exposure of the backer laminate to liquids, for example water, such as by moisture
penetration through the sub-floor, adversely effects not only the backer laminate but also the
substrate. The traditional flooring panels are, however, not designed or otherwise properly
adapted to compensate for the difference between the environments to which the decorative
and backer laminates are exposed.

One inventive solution to prevent the penetration of moisture, such as water vapor or
humidity into the backer layer, is to use a layer that is liquid impermeable, such as a styrene-
maleic anhydride copolymer layer, at the bottom of the backing layer to substantially prevent
the penetration of moisture, such as water, in liquid form. This inventive solution is disclosed
in detail in the above referenced U.S. Patent Application, entitled "LAMINATE".

Although the incorporation of the liquid impermeable layer into the backer of the
laminate flooring in accordance with a preferred embodiment of U.S. Patent Application,
entitled "LAMINATE" provides a significant improvement in the resistance of the entire
composite to standing water, the sensitivity of the decorative laminate to conditions of low
humidity has been discovered to increase, as in the preferred embodiment disclosed therein the
melamine balancing layer 18 in the backer laminate is replaced with a liquid impermeable layer.
Thus, the movement of the melamine layer 11 of the decorative side in conditions of low
humidity may cause the flooring panel to warp without resistance as the liquid impermeable

Application, entitled "LAMINATE", is comprised of the liquid impermeable layer positioned at an exterior surface of one of several phenolic resin impregnated kraft paper sheets. The melamine treated balancing sheet is not incorporated into the backer laminate described in the preferred embodiment of the above referenced U.S. Patent Application entitled "LAMINATE" as a sufficient bond may not be achieved between the liquid impermeable layer and the melamine layer. Attempts have been made to balance and/or counteract the humidity driven movement of the decorative laminate by increasing the number and weight of the phenolic resin impregnated kraft paper sheets in the backer laminate to yield a strong backer. However, such efforts did not provide a backer strong enough to balance the movement of the decorative laminate when two or more melamine treated sheets were used in the decorative laminate to improve wear resistance.

In the preferred embodiment of the above referenced U.S. Patent Application, entitled "LAMINATE EMPLOYING LIQUID RESISTANT FILM AND TWO SIDED SHEET" a method of incorporating a melamine treated balancing sheet in the backer laminate is described. In the preferred embodiment of the above referenced application, a layer of phenolic resin may be inserted between the liquid impermeable layer and the melamine layer so that both the liquid impermeable layer and the melamine layer may be used in the same laminate to provide the desired liquid impermeable and balancing characteristics. However, in order to properly balance a composite having a particular characteristic material associated with the exterior of the top or decorative laminate, it may be desirable to have the balancing layer close to the bottom exterior of the backer laminate. Thus, when a laminate flooring has a melamine impregnated overlay layer as a top exterior surface of the decorative side, it may be desired to have a balancing layer of melamine close to the bottom exterior of the laminate in order to properly balance the top overlay layer. However, as in the preferred embodiment of the above referenced patent application, entitled "LAMINATE EMPLOYING LIQUID RESISTANT FILM AND TWO SIDED SHEET", the balancing layer is not adjacent to the

Thus, there is a need in the art for a system and method of manufacturing laminates
5 providing the advantages of the melamine balancing layer and also providing the advantages
offered by the liquid impermeable layer.

There is a further need in the art for a system and method of manufacturing laminates
such that two layers, such as a balancing layer and a liquid impermeable layer, providing
desired characteristics may be placed adjacent to each other in a laminate assembly.

layer having a desired characteristic, such that both layers providing desired characteristics
5 may be used adjacent to each other in a laminate panel. For example, a substance in a
balancing layer of a laminate composite, such as melamine in a melamine resin impregnated
sheet, may be adapted to provide enhanced bonding with a liquid impermeable layer, such as a
styrene-maleic anhydride copolymer layer.

Accordingly in an embodiment of the present invention, a balancing sheet, such as a
10 melamine impregnated sheet, is placed adjacent to the layer providing the liquid impermeable
characteristics, such as a styrene-maleic anhydride layer. The balancing sheet preferably
balances the stress caused from the movement of a protective layer in the decorative laminate
and prevents positive warpage of a flooring composite, for example. The styrene-maleic
anhydride layer provides another desired characteristic to the composite, such as
15 impermeability to liquids. The melamine impregnated sheet of the preferred embodiment may
be adapted to provide a desired bonding with the liquid impermeable sheet. This is specially
useful as traditional melamine impregnated sheets do not provide a desired bonding with the
liquid impermeable sheet.

Therefore, in this embodiment of the present invention, the melamine layer and the
20 liquid impermeable layer are placed adjacent to each other, and thus both flatness and
enhanced liquid resistance may be provided to the composite employing the backer laminate.
The order of the sheets in the backer laminate is changed from the traditional laminate design
such that the balancing sheet is no longer the outermost layer. However, in this embodiment,
the balancing sheet may be placed close to the exterior surface of the laminate to balance a
25 corresponding layer of the decorative side thus providing a desired balancing laminate.

In the preferred embodiment, an adhesion promoting agent, such as silane, is mixed
with a substance providing the desired balancing characteristic, such as melamine resin, in a
predetermined amount to provide the desired adhesive characteristic to the balancing
substance. In the preferred embodiment, the amount of silane added to a melamine resin used

that are well known in the art, such as by using a Kiss coater or a reverse roll coater. The

5 melamine treated laminate material may be placed adjacent to the liquid impermeable layer and subjected to heat and pressure to cure the resin, as is known in the art, to manufacture the desired laminate having the desired liquid resistant and balancing characteristics with the layers providing the desired characteristics adjacent to each other.

10 In an alternative embodiment of the present invention, a first side of a laminate material, such as a sheet of kraft paper, may be treated with the melamine resin and silane mixture. The other side of the kraft paper may be treated with melamine, a mixture of melamine and silane, or a substance providing structural characteristics to the laminate, such as phenolic resin. A system and method for manufacturing such a laminate material as well as an outline of the advantages of the double treated sheet, has been disclosed in detail in the
15 above referenced commonly assigned U.S. Patent Application, entitled "SYSTEM AND METHOD FOR TWO SIDED SHEET TREATING". Thus, in this alternative embodiment, such a sheet of kraft paper may be placed adjacent to a layer providing another desired characteristic to the laminate, such as the liquid impermeable layer, with the melamine resin treated surface next to the liquid impermeable layer to thereby dispose the layer providing the
20 desired balancing characteristic adjacent to the layer providing the desired liquid impermeable characteristic. Such a placement of layers positions the melamine resin impregnated sheet close to the exterior of the laminate thereby providing better balancing characteristics to the laminate to substantially prevent positive warpage of the composite.

25 The different embodiments of the present invention as discussed above provide advantages not available in the prior art. For example, the laminate panel so constructed provides impermeability to liquids, such as water, due to the addition of the liquid impermeable layer, preferably as the outermost layer, and balancing characteristics due to the incorporation of a layer, such as the melamine resin impregnated layer, in the backer laminate, thereby allowing the composite to remain substantially flat over a broader range of

the liquid impermeable layer, thereby providing the desired balancing characteristics. In

5 typical laminates, the surface to be balanced, such as the melamine impregnated overlay sheet of the decorative laminate, forms the outermost surface of the decorative laminate. Therefore, it is desirable to have the balancing layer close to the exterior of the backer laminate.

Moreover, a prior art overlay sheet impregnated with the balancing substance allows only a limited amount of the balancing substance, such as melamine, to be used, and thus is not
10 able to resist the pull of the melamine layer of the decorative laminate, especially when more than one layer of melamine resin impregnated sheet is used in the decorative side of the laminate. On the other hand, more melamine resin per unit area of the sheet may be provided to the laminate of the alternative embodiment discussed above, as kraft paper sheet is capable of absorbing more melamine than a traditional overlay sheet used in prior art backer laminates,
15 thereby yielding a stronger backer. Thus, in the alternative embodiment discussed above, the laminate may be saturated with a greater amount of the balancing substance, such as melamine, thereby allowing the laminate to remain flat even in cases where the decorative side uses more than one melamine resin impregnated sheet to provide a desired protective characteristic to the laminate.

20 Therefore, it is a technical advantage of the present invention to provide a liquid impermeable laminate for use with decorative panels, such as flooring panels.

It is another technical advantage of the present invention to provide a hydrophobic laminate with the desired balancing characteristics to prevent warping of the laminate in extreme conditions.

25 It is yet another technical advantage of the present invention to provide a laminate with a liquid impermeable layer and a balancing layer disposed adjacent to the liquid impermeable layer.

It is still another technical advantage of the present invention to provide a liquid impermeable flooring laminate with a wood based substrate.

It is a further technical advantage of the present invention to provide an outermost
5 water resistant flooring laminate with a layer providing desired balancing characteristics
disposed adjacent to the outermost water resistant layer.

The foregoing has outlined rather broadly the features and technical advantages of the
present invention in order that the detailed description of the invention that follows may be
better understood. Additional features and advantages of the invention will be described
10 hereinafter which form the subject of the claims of the invention. It should be appreciated by
those skilled in the art that the conception and specific embodiment disclosed may be readily
utilized as a basis for modifying or designing other structures for carrying out the same
purposes of the present invention. It should also be realized by those skilled in the art that
such equivalent constructions do not depart from the spirit and scope of the invention as set
15 forth in the appended claims.

accompanying drawings, in which:

5 FIGURE 1 is a schematic of a prior art laminate panel;

FIGURE 2 is a schematic of a backer in accordance with a first embodiment of the present invention;

FIGURE 3 is a schematic of a backer in accordance with a second embodiment of the present invention;

10 FIGURE 4 is a schematic of a backer in accordance with a third embodiment of the present invention;

FIGURE 5 is a schematic of a backer in accordance with a fourth embodiment of the present invention;

15 FIGURE 6 is a schematic of a backer in accordance with a fifth embodiment of the present invention;

FIGURE 7 shows a system for treating a sheet with a substance according to a preferred embodiment of the present invention; and

FIGURE 8 is a table showing the results of experimental testing performed on a flooring panel using the laminate of FIGURE 2.

FIGURE 2, laminate 20 includes a layer having a desired characteristic, such as a liquid impermeable layer 21, preferably a styrene-maleic anhydride copolymer layer. The styrene-maleic anhydride copolymer is preferably DYLARK[®] manufactured by NOVA Chemicals, Inc. A laminate material providing another desired characteristic, such as a melamine resin impregnated layer 22, may be disposed adjacent to the liquid impermeable styrene-maleic anhydride copolymer layer 21. The laminate material used in layer 22 may be a traditional overlay sheet. If desired, one or more phenolic resin impregnated kraft paper sheets, such as sheet 23, may be disposed adjacent to the melamine resin impregnated layer 22.

The styrene copolymer is hydrophobic which makes it less permeable to liquids, such as water. Of course, where other materials are utilized in providing the laminate adapted according to the present invention, polymers or unsaturated monomers having other characteristics and/or chemical composition may be utilized to provide impermeability to liquids, such as water, and bonding as described above. Styrene-maleic anhydride exhibits good thermal stability, in addition to exhibiting outstanding bonding characteristics with phenolic resin impregnated kraft paper. The excellent bonding of styrene-maleic anhydride with phenolic resin is a result of the strong hydrogen bonding between the acid anhydride and the unreacted hydroxyl groups of the phenolic resin, and/or actual chemical crosslinking between those same two sites. However, the styrene-maleic anhydride copolymer does not provide the same desired bonding with melamine resin impregnated layer 22. It is believed that several additives in the melamine resin used for the treating process during manufacture of the laminate, interfere with the hydrogen bonding that could occur between the amine sites and the acid anhydride.

Therefore, in the preferred embodiment, the melamine in the melamine resin impregnated layer 22 is adapted, preferably prior to impregnating the laminate material, in order to provide a desired bonding characteristic to layer 22 to facilitate superior bonding of the melamine impregnated layer 22 with liquid impermeable layer 21. In order to provide the

associated with a mixing shaft with propellers to disperse the adhesion promoting agent, such as silane, into the melamine. Once the melamine and silane have been mixed, the mixture may be pumped or otherwise transported to a treating area for treating a laminate material, such as an overlay sheet, with the melamine. In the preferred embodiment, the amount of silane in the melamine mixture is between 0.1 to 0.5 percent by weight of the melamine. Preferably, Z-6040 Silane manufactured by Dow Corning® is used for best results, although any type of silane may be used without departing from the spirit of the present invention. The Z-6040 Silane may be designated as a 3-glycidoxypentyltri-methoxysilane.

Silane exhibits good thermal stability, in addition to exhibiting outstanding bonding characteristics with the styrene-maleic anhydride copolymer layer. The excellent bonding characteristics of silane are a result of the hydroxy (OH) groups found on the silane. The hydroxy groups of silane provide bond sites that act as receptors or ties between the styrene-maleic anhydride and the melamine. Thus, the silane in the melamine resin impregnated layer 22 provides bond sites that facilitate the creation of bonds and hence better adhesion between the preferred embodiment styrene-maleic anhydride copolymer layer 21 and the melamine resin impregnated layer 22.

The melamine resin impregnated layer 22 of the preferred embodiment may be treated with melamine by any suitable method. In the preferred embodiment, a conventional kiss roll coater, known to one skilled in the art, may be used to treat the laminate material, such as an overlay sheet. FIGURE 7 shows a schematic diagram of a preferred system 70 that may be used for impregnating the overlay sheet with melamine. The system comprises a sheet S in the form of a roll 701, a series of rollers 702, 703, 704, 705, 706, 707, 710, pan 708, metering device 711 and a conditioner 712 such as may be an oven for applying a controlled amount of heat for subsequent curing of a substance. Pan 708 contain substance 709. Metering device 711 controls the amount of substance 709 remaining on sheet S.

varied by adjusting the speed of the rollers and/or the pressure exerted thereon by idler rollers
5 702, 703, 704, 705, 706 and/or 710. Although a series of rollers 702, 703, 704, 705, 706,
707, and 710 are shown in the preferred system, the operation of the present invention does
not require that all these rollers be used. For example, only select ones of these rollers may be
provided depending on the desired tension and pressure to be applied on sheet S.

Substance 709 is fed into pan 708 by means of a pump (not shown). The level of
10 substance 709 in pan 708 may be controlled by the pump such that the pump automatically
feeds more substance 709 to pan 708 whenever substance 709 falls below a certain level.

Roller 707 may be submerged in substance 709 up to a desired level depending on the amount
of substance 709 needed to be impregnated into sheet S. Roller 707 may be raised or lowered
to control the depth to which sheet S is submerged in substance 709 in pan 708 to control the
15 amount of substance 709 impregnated into sheet S. Thus, a greater amount of substance 709
may be impregnated into sheet S by lowering the roller 707. Moreover, the desired amount of
substance 709 to be impregnated into sheet S may also be controlled by the pump.

Additionally, by controlling the speed of the rollers the amount of time that different parts of
sheet S remain submerged in pan 708 may be controlled, thus, further controlling the amount
20 of substance 709 that is applied to different parts of sheet S.

In the preferred embodiment illustrated, sheet S passes around roller 710 which is
positioned after roller 707. Metering device 711 preferably located near roller 710 in order to
take advantage of the disposition of the surface of sheet S provided thereby, may be used to
further control the amount of substance 709 remaining on sheet S. Thus, once sheet S has
25 been impregnated with substance 709 by submergence into pan 708, the amount of substance
709 remaining on sheet S may be further and precisely controlled by metering device 711 to
maintain a desired amount of the substance in the sheet. Thus, if desired, metering device 711
may be adjusted, such as by being moved towards roller 710, thereby reducing the amount of
substance 709 remaining on sheet S. The excess of substance 709 that is removed from sheet

Metering device 711 may be any device capable of precisely controlling the amount of substance 709 that remains in sheet S. In the preferred embodiment, metering device 711 is an air knife which may be used to precisely control the amount of coating material remaining in sheet S by removing excess coating of substance 709 from sheet S. Thus, in the preferred embodiment, metering device 711 comprises a sheet of air projected under pressure at an angle from a slot-shaped air nozzle onto the surface of sheet S. Thus, while sheet S is supported on a moving support such as roller 710, the sheet of air is projected onto sheet S so that the air strikes sheet S at an angle such that a desired amount of substance 709 may be removed from sheet S.

The amount of substance 709 remaining on sheet S may be adjusted by controlling how much air is blown across the surface of sheet S, the force of the air blown across the surface of sheet S, the angle at which the sheet of air strikes the surface of sheet S, and/or the time during which the air knife engages the surface of sheet S, i.e. the speed at which the sheet is moved past the air knife and/or the time transpiring between the application of the substance and the engaging of the air knife. For example, by increasing the distance of metering device 711 from roller 710 the amount of substance 709 remaining in sheet S may be increased due to the striking force of the sheet of air of the preferred embodiment air knife, against the surface of sheet S being reduced. Accordingly, the preferred embodiment includes, a set of screw adjusters which are provided at the end of metering device 711 to adjust its distance from sheet S. However, any means may be used to adjust the distance of the metering device from the surface of sheet S, e.g., a pneumatic mechanical adjuster, an eccentric and follower, an electrically powered adjusting means such as a computer controlled servo mechanism, etc.

Sheet S is then preferably subjected to a B-staging process or other conditioning step to preferably condition substance 709, such as by drying or curing. For this purpose, sheet S may be passed through a conditioner 712. The environment inside conditioner 712 may be controlled such that, if desired, different temperatures, airflow, speed, pressures, catalysts, or

suitable for curing substance 709 and another part of conditioner 712 is more suitable for curing a different substance.

Furthermore, if desired an optimum temperature or other conditioning attribute, which when applied in combination with the precisely controlled application of the coating material according to the present invention, may be calculated such that substance 709 is cured to an acceptable degree. The acceptable degree of curing may be determined based on the ultimate use of sheet S.

Although, conditioner 712 has been described as a single apparatus, a series of apparatus may be used to achieve the desired curing of the substances. The series of apparatus may be a combination of conditioners, refrigerators, wetting devices, drying devices etc. Moreover, it may be desirable to control a combination of conditions, such as the temperature, pressure, moisture level, etc., inside conditioner 712 to achieve a desired result, such as a desired penetration level of sheet S by substance 709.

The embodiment shown in FIGURE 2 provides a liquid impermeable layer 21 that prevents the penetration of moisture into the backer laminate. Additionally, the balancing layer 22 of the embodiment shown in FIGURE 2, provides the required balancing characteristics to the composite and balances a layer of the decorative side, such as an overlay layer of protective substance, like melamine, by counteracting the pressure exerted by the corresponding layer of the decorative laminate (not shown in the FIGURE), thus preventing warpage of the composite, i.e. causing the composite to remain substantially flat. Moreover, as the layer of protective substance in typical decorative laminates is the outermost surface on the decorative side, it may be desirable to have the balancing layer 22 of the embodiment shown in FIGURE 2 as close to the exterior surface as possible on the backer side to more effectively counteract the pressure exerted by the layer of protective substance. As the melamine resin impregnated balancing layer 22 of the embodiment of FIGURE 2 is positioned

thickness of the melamine resin layer 22 varies from 3 mils to 7 mils, and the thickness of the phenolic resin impregnated kraft paper 23 varies from 7 mils to 11 mils. Therefore, in the embodiment of the present invention as shown in FIGURE 2, the thickness of the backer laminate typically varies from 15 mils to 23 mils. However, in some applications it may be desirable to have backers of thickness less than 15 mils.

Therefore, an alternative embodiment of the present invention as shown in FIGURE 3, comprises a laminate material 32, such as a kraft paper sheet, treated with a substance providing desired characteristic, such as a balancing substance, like melamine, on one side, and a same or different substance providing another desired characteristic, such as a substance providing structural characteristics, like phenolic resin, on the other side. A system and method for providing such a laminate material has been shown and described in the above referenced commonly assigned U.S. Patent Application, entitled "SYSTEM AND METHOD FOR TWO SIDED SHEET TREATING", the disclosure of which is hereby incorporated herein by reference.

In the embodiment shown in FIGURE 3, laminate 30 includes from the bottom up a liquid impermeable layer 31, such as a styrene-maleic anhydride copolymer layer, and a laminate material 32, such as a kraft paper sheet, treated with melamine resin on one side and phenolic resin on the other side. In the embodiment of FIGURE 3, the melamine resin treated side of the kraft paper sheet 32 faces the liquid impermeable layer 31, as the melamine in layer 32 has been adapted, as described above with reference to FIGURE 2, to provide superior bonding characteristics with the styrene-maleic anhydride copolymer layer 31. The liquid impermeable layer 31 provides a first desired characteristics to the laminate, such as making the laminate substantially moisture resistant. The melamine/phenolic resin impregnated kraft paper 32 provides both a desired balancing characteristic and a desired structural characteristic to the laminate.

5 vary from 12 mils to 16 mils depending on the thickness of the liquid impermeable layer 31,
and the thickness of the melamine/phenolic resin impregnated kraft paper layer 32. The ratio
of phenolic resin and melamine resin in kraft paper 32 may be changed to increase the
balancing characteristic of the sheet, as shown in the above referenced U.S. Patent
Application, entitled "SYSTEM AND METHOD FOR TWO SIDED SHEET TREATING".
10 In this embodiment of the present invention, the thickness of the backer is less than the
thickness of the backer shown in the embodiment of FIGURE 2. Moreover, like the
embodiment of FIGURE 2, the backer laminate of FIGURE 3 allows two layers providing
desired characteristics which do not naturally bond together to be placed adjacent to each
other while providing a desired bonding.

15 The embodiment of the present invention as shown in FIGURE 3 provides the desired
characteristics, such as impermeability to liquids and balancing characteristics, to the laminate
in cases where the number of protective layers on the decorative side is one. However, this
embodiment may not provide adequate balancing characteristics, in other cases, for example,
when the number of protective layers on the decorative side is more than one, such as in
commercial or other high wear applications which require greater abrasion resistance. In such
20 cases, the total melamine on the combined protective layers in the decorative side is very
strong and has an increased tendency to pull the laminate in the upward direction causing
positive warping. This effect is especially pronounced under dry and low humidity conditions.
Thus, it may be desirable to have a greater amount of the balancing substance in the backer or
balancing side of the laminate to counteract the movement of the additional protective layers.

25 Therefore, in the embodiment shown in FIGURE 4, an additional layer 42 of a
laminate material, such as a traditional overlay sheet, impregnated with a substance providing
a desired characteristic, such as a balancing substance, like melamine is included in the backer
laminate. Laminate 40 of the embodiment of FIGURE 4 includes from the bottom up a liquid
impermeable layer 41, such as a styrene-maleic anhydride copolymer layer, a laminate material

provides a first desired characteristic to the laminate, such as making the laminate substantially
5 moisture resistant. The melamine resin impregnated layer 42 is disposed next adjacent to the
liquid impermeable layer 41, as it is desirable to have the melamine layer close to the exterior
surface of the backer to balance the protective layer of the decorative side. The kraft paper
sheet 43 may be disposed adjacent to the laminate material 42, with the melamine side of kraft
10 paper sheet 43 next adjacent to the melamine impregnated laminate material 42. In the
embodiment shown in FIGURE 4, if desired, the phenolic layer of kraft paper sheet 43 may be
adjacent to a substrate (not shown in the FIGURE), such as a traditional wood-based substrate
or a non-wood based substrate such as described in the above referenced U.S. Patent
Application, entitled "POLYMERIC FOAM COMPOSITIONS AND METHOD OF
15 MAKING, SUBSTRATES MADE FROM SUCH COMPOSITIONS AND METHOD OF
MAKING, PRODUCTS MADE FROM SUCH SUBSTRATES AND METHOD OF
MAKING", to allow bonding of the backer laminate with the substrate.

Typically the thickness of the liquid impermeable layer 41 of FIGURE 4 is 5 mils, the
thickness of the melamine layer 42 varies from 3 mils to 7 mils, and thickness of the
melamine/phenolic resin impregnated kraft paper 43 varies from 7 mils to 11 mils depending
20 on the type of kraft paper used. It is desirable that the laminate of the embodiment of
FIGURE 4 have more melamine than the laminate of the embodiment of FIGURE 3 in order
to properly balance the multiple protective layers on the decorative side and to keep the
composite flat. Prior art backers use special overlay type sheets that are impregnated with
melamine resin. However, the kraft paper sheet with phenolic resin on one side and melamine
25 resin on the other side has been adapted to be able to incorporate a desired amount of
melamine as discussed in the above referenced U.S. Patent Application, entitled "SYSTEM
AND METHOD FOR TWO SIDED SHEET TREATING". Thus, the kraft paper sheet may
incorporate a greater amount of melamine than is possible in an overlay sheet. Although in the
preferred embodiment, only half of the kraft paper is impregnated with melamine, the amount
30 of the melamine in layer 43 may be increased depending on the particular application and in

resin, a greater amount of the balancing substance is included in the backer laminate.

5 Furthermore, in the embodiment of FIGURE 4, an additional layer of melamine resin impregnated laminate material is being used to provide better balancing characteristics, such as by providing more strength and stiffness, to balance the multiple protective layers of the decorative side. Thus, in this embodiment, the flatness of the composite is maintained under both high and low humidity conditions due to the heavy concentration of melamine in the
10 backer laminate.

Additionally, if desired only the melamine in the melamine resin impregnated layer 42 may be adapted with an adhesion promoting agent, such as silane, to provide the desired bonding with the liquid impermeable layer 41, as melamine resin does not naturally provide the desired bonding with the liquid impermeable layer. It is not desirable to adapt the melamine
15 (with an adhesion promoting agent) used in the melamine/phenolic layer 43 as the melamine in the melamine/phenolic layer 43 bonds easily with melamine in layer 42. This would result in cost savings as the amount of silane desirable to be mixed with melamine is reduced. However, if desired, the melamine in both layers 42 and 43 may be adapted with silane. Furthermore, the laminate so produced is moisture resistant and does not warp in flooding or
20 sitting water due to the presence of the liquid impermeable layer 41.

Although the embodiment of FIGURE 4 has been described with the melamine side of kraft paper 43 facing the melamine impregnated layer 42, in alternative embodiments kraft paper 43 may be inverted so that the phenolic side of kraft paper 43 faces the melamine side of kraft paper 42 to give a balanced laminate.

25 FIGURE 5 shows an alternate embodiment of the laminate of the embodiment of the present invention illustrated in FIGURE 4 in which the melamine impregnated layer 42 of FIGURE 4 has been substituted with a laminate material 52 coated with melamine on both sides, and the melamine/phenolic layer 43 has been substituted with a phenolic resin impregnated kraft paper sheet 53. Laminate 50 of the illustrated embodiment of FIGURE 5

5, the melamine/melamine layer 52 is disposed adjacent to liquid impermeable layer 51 as it is desirable to have the melamine layer close to the exterior of the laminate in order to balance the protective layer which forms the exterior surface of the decorative side. The melamine on the surface of layer 52 facing the liquid impermeable layer 51 may be adapted to provide a desired bonding with the liquid impermeable layer 51. As discussed above, this may be accomplished by mixing an adhesion promoting agent, such as silane, in melamine resin using the method described above preferably prior to treating the laminate material with melamine preferably using the method described in the above referenced U. S. Patent Application, entitled "SYSTEM AND METHOD FOR TWO SIDED SHEET TREATING". Moreover, it is not critical to adapt the melamine that is coated on the side of laminate material 52 facing the phenolic resin impregnated kraft paper 53 as the phenolic resin impregnated kraft paper 53 would bond easily with the adjacent melamine coated side of kraft paper 52. In alternative embodiments, the additional layer 53 may be impregnated with other resins or may be eliminated without departing from the spirit of the present invention.

The two sided coated sheet 52 treated with the same substance, such as melamine, on both sides, as discussed above, eliminates the need to use overlay type sheets impregnated with melamine in order to balance the melamine resin impregnated overlay type sheets of the decorative side. Typically the overlay type sheets are more expensive than the kraft paper sheet. Thus, an advantage of the embodiment of FIGURE 5 of the present invention is that the cost of producing the liquid impermeable laminates is reduced. Furthermore, the amount of the balancing substance may be controlled depending on the amount desirable to balance the overlay type melamine impregnated sheet or sheets of the decorative side. Thus, the amount of the impregnated melamine may be increased or reduced depending on the particular application. Moreover, the amount of adhesion promoting agent, such as silane, used may be adjusted so that less than a determined percentage, such as for example 50%, of the total melamine content of kraft paper sheet 52 contains the adhesion promoting agent.

is introduced preferably between the melamine/melamine layer 52 of FIGURE 5 and the

5 phenolic resin impregnated kraft paper 53 of FIGURE 5. Thus, laminate 60 of the illustrated embodiment of FIGURE 6 includes from the bottom up a liquid impermeable layer 61, such as a styrene-maleic anhydride copolymer layer, a laminate material 62, such as a kraft paper, coated with melamine resin on both sides, and another laminate material 63, such as a melamine resin impregnated overlay sheet. In alternative embodiments, any sheet suitable for
10 impregnation with a resin, such as a melamine resin, may be used as laminate material 63. In the embodiment of FIGURE 6, the melamine/melamine layer 62 is disposed adjacent to the liquid impermeable layer 61 as it is desirable to have the melamine layer close to the exterior surface of the laminate in order to balance the protective layer which forms the exterior surface of the decorative side. The melamine on the side of layer 62 facing the liquid
15 impermeable layer 61 may be adapted to provide a desired bonding with the liquid impermeable layer 61. Moreover, it is not necessary to adapt the melamine that is coated on the side of the laminate material 62 facing the melamine resin impregnated layer 63 as the melamine resin impregnated layer 63 would bond easily with the adjacent melamine coated side of the kraft paper 62. If desired, one or more layers of kraft paper 64 impregnated with
20 phenolic resin may be disposed on top of layer 63. In alternative embodiments, the additional layer 64 may be impregnated with other resins or may not be present without departing from the spirit of the present invention.

Thus, one can conceive of any combination of laminate configurations in which the liquid impermeable layer, such as a styrene-maleic anhydride copolymer layer, is the outermost
25 sheet. The liquid impermeable layer may be followed by a combination of any desirable number of sheets of melamine, double treated melamine/melamine sheets, or double treated melamine/phenolic sheets in any order, such that a melamine layer is next adjacent to the styrene-maleic anhydride copolymer layer and the melamine resin next adjacent to the styrene-maleic anhydride copolymer layer contains a silane coupling agent. Moreover, a desired
30 number of phenolic resin impregnated kraft paper sheets may be positioned in between the

5 Experimentation has revealed that the embodiments of the laminates of the present invention as discussed above provide improved balancing characteristics. The effect of the addition of the melamine balancing sheet to the backer laminate is shown in the table of FIGURE 8. In conducting the experiment, two 7'x5' floors were installed over a particle board subfloor set-up in an environmentally controlled chamber. The panels making up each floor were bonded together using urethane adhesive. The first flooring 1 employed a backer laminate comprising a layer of styrene-maleic anhydride copolymer and three sheets of 140 lb kraft paper impregnated with phenolic resin. The second flooring 2 employed a backer laminate, comprising a layer of styrene-maleic anhydride copolymer, one sheet of overlay material treated with silane and melamine, and three sheets of 140 lb kraft paper treated with phenolic resin. Both floors employed identical substrate and decorative laminates. The warpage of each flooring plank was measured across the 7' length at installation, after wet conditioning and after dry conditioning. The installed, wet and dry warpage of the different flooring panels is shown in the table of FIGURE 8. The average value of all planks for each floor is given in the last row of the table of FIGURE 8. In the table of FIGURE 8, a negative value indicates that the flooring panel is curved downward toward the subfloor. A positive value indicates that the flooring panel is curved upward away from the subfloor. All values are denoted in inches.

The specific conditioning program for the flooring samples is outlined as follows. The temperature inside the humidity chamber was maintained at 70°F and the relative humidity maintained at 50% from 9 a.m. to 11 a.m. At 11 a.m., a cycling process was started inside the humidity chamber in which the temperature and humidity were changed twice. The temperature and relative humidity inside the chamber was changed first to 90°F, 90% rH (hot and wet conditions) at 11 a.m. and maintained until 5 p.m. and changed to 90°F, 10% rH (hot and dry conditions) at 5 p.m. and maintained until 8 a.m. the next day.

On the other hand, panels of flooring 2 comprising of a styrene-maleic anhydride copolymer layer, the silane adapted melamine treated overlay layer, and the three phenolic resin layers, demonstrated more negative warping when installed. As the flooring panels were conditioned at high temperature and high humidity, such as from 11 a.m. to 5 p.m., the exposed melamine overlay layer (the protective layer) on the exterior of the decorative side of the flooring composite had a tendency to absorb water and swell the panels slightly. This swelling of the top laminate panel forces the panels of the flooring downward causing increased negative warpage, as indicated by the values in the "WET" column in the table of FIGURE 8. As the flooring panels are subsequently conditioned at high temperature and low humidity, such as from 5 p.m. to 8 a.m. the next day, the exposed melamine of the decorative side of the panels dries out and shrinks. It was observed that the panels of flooring 1 with no balancing layer demonstrated more positive warping as compared to panels of flooring 2 comprising of the balancing and liquid impermeable layers disposed adjacent to each other, as indicated in the "DRY" column in the table of FIGURE 8. Positive warpage of the composite is undesirable as the seams between the planks lift upward becoming visually unpleasant. This gives the impression that the seams between the flooring planks are opening, and thus, hurts the appearance of the surface. Flooring composite 1 demonstrated more positive warpage as compared to flooring composite 2. Moreover, the positive cupping of flooring 1 was physically observable, whereas the negative cupping of flooring 2 was not visible. Thus, it should be clear that laminates utilizing a liquid impermeable layer and a balancing layer adjacent to each other, as discussed above, provide improved balancing characteristics.

As mentioned above, flooring composite 2, comprising the backer of the embodiment of FIGURE 2 of the present invention, demonstrated more and consistent negative warping on or before installation than flooring 1. Accordingly, the flooring, or other laminates, manufactured according to a preferred embodiment of the present invention may be produced to result in products with consistent negative warping. Negative warping is not generally noticeable to the casual observer and is perceived as being flat. However, in contrast, even

Accordingly, providing a consistent but small amount of negative warpage in the natural state
5 of the product may be relied upon to counteract such later positive warping and thereby
provide a superior product as the observable positive warping may be avoided or eliminated.
In a preferred embodiment, therefore, an amount of the balancing substance, such as
melamine, is determined which, due to its characteristics, provides the aforementioned initial
negative warping in a laminate. For example, using two layers of melamine balancing material
10 has been found to provide the consistent and slight negative warping described above.

The different embodiments of the present invention as discussed above are considered
to be exemplary of laminates that may be used in accordance with the present invention.
Different embodiments of the present invention may be used as decorative and/or backer type
laminates without departing from the scope of the present invention. For example, decorative
15 layers may take various forms and employ laminate layers in a variety of combinations. As
such, the layers of the backer laminate may be varied to complement changes in the decorative
layer without departing from the spirit of the present invention. Moreover, the liquid
impermeable layer and the balancing layer of the present invention as discussed above may be
used in the decorative layer or the backer layer without corresponding use of a substrate, if
20 desired. For example, a panel having a liquid impermeable layer on one or all sides and a
balancing layer adjacent to the liquid impermeable layer may be utilized in any of a number of
orientations to provide a surface which is liquid impermeable and does not warp, where a
substrate may not be desired.

The prior art laminates use wood based materials such as plywood, particle board,
25 chipboard, medium density fiberboard, high density fiberboard, etc. as substrate. Although the
different embodiments of the present invention as discussed above may be used with any kind
of substrates, such as wood based and non-wood based substrates, the present invention is
especially useful for use with substrates made from Alternate Substrate Materials (ASM).
Such ASM may include non-wood cores or substrates, such as synthetic or non-cellulose

smoke suppressors, wollastonite, if desired. The lack of stiffness of the non-wood based
5 substrates makes the use of different embodiments of the laminates as discussed above more
desirable to provide the desired characteristics, such as strength and balancing, to the
laminates than the traditional laminates using wood based substrates.

In the different embodiments of the present invention as discussed above, the substance
used in the layer providing the second desired characteristic, such as melamine, has been
10 adapted to provide the desired bonding with the layer providing the first desired
characteristics, such as the preferred embodiment liquid impermeable layer. However, the
invention is not so limited and in alternative embodiments, the layer providing the first desired
characteristic may be adapted to provide the desired bonding. For example, in an alternative
embodiment, the liquid impermeable layer itself may be treated with an adhesion enhancing
15 substance, such as silane, to provide the desired bonding with the layer providing the second
desired characteristics, such as the melamine resin impregnated balancing layer. In one
embodiment, the layer providing the first desired characteristic, such as the liquid impermeable
layer, may be immersed in a bath of silane, such that the surface of the liquid impermeable
layer is treated with silane, which would then provide bond sites for bonding with the
20 substance in the layer providing the second desired characteristics.

Moreover, although in the preferred embodiment, the substance providing the second
desired characteristics, such as melamine, is adapted prior to treating a laminate material, the
invention is not so limited and in alternative embodiments, melamine may be treated with silane
after treating the laminate material. For example, in another embodiment of the present
25 invention, the laminate material may be treated with melamine resin first to provide the desired
balancing characteristics and then treated with an adhesion enhancing agent, such as silane, to
promote bonding with a layer providing liquid impermeable characteristics to the laminate.

Moreover, more than two sheets of laminate material coated with a substance,
providing a desired characteristic, on one side and a different or same substance, providing a

provide a structure with good bonding having desired characteristics even when materials

5 having these characteristics do not readily bond.

It shall be appreciated by those skilled in the art, that although the embodiments of the present invention have been described above with regard to a liquid impermeable layer and a balancing layer, the invention is not so limited and the teachings of the present invention may be used in any situation where it is desirable to have two substances adjacent to each other and
10 the two substances are incapable of adhering to each other. Moreover, although the exemplary embodiments have been discussed with regard to backer laminates, the present invention may be used for the decorative side of the laminates.

Although the present invention and its advantages have been described in detail, it should be understood that various changes, substitutions and alterations can be made herein
15 without departing from the spirit and scope of the invention as defined by the appended claims. Moreover, the scope of the present application is not intended to be limited to the particular embodiments of the process, machine, manufacture, composition of matter, means, methods and steps described in the specification. As one of ordinary skill in the art will readily appreciate from the disclosure of the present invention, processes, machines, manufacture,
20 compositions of matter, means, methods, or steps, presently existing or later to be developed that perform substantially the same function or achieve substantially the same result as the corresponding embodiments described herein may be utilized according to the present invention. Accordingly, the appended claims are intended to include within their scope such processes, machines, manufacture, compositions of matter, means, methods, or steps.

a first thermoplastic layer; and

- 5 a second melamine resin treated layer disposed adjacent the first thermoplastic layer for balancing a third layer in said end product, wherein said melamine resin of said second melamine resin treated layer has been treated with a silane to provide enhanced adhesion of said second layer with said first layer.

10 2. The laminate of claim 1, wherein said first thermoplastic layer is liquid resistant.

3. The laminate of claim 1, wherein said first thermoplastic layer is a styrene-maleic anhydride copolymer layer which substantially prevents the penetration of moisture into said end product.

15

4. The laminate of claim 1, wherein the amount of silane in said second melamine resin treated layer is between 0.1 to 0.5 percent by weight of said melamine resin.

20

5. The laminate of claim 1, wherein said second melamine resin treated layer comprises a kraft paper sheet.

25

6. The laminate of claim 4, wherein said kraft paper sheet is coated with said melamine resin and silane on one side and a phenolic resin on the other side, and wherein the phenolic resin coated side of said kraft paper sheet faces away from said first thermoplastic layer.

7. The laminate of claim 1, further comprising:
a phenolic resin impregnated kraft paper sheet positioned adjacent to said second layer.

30

8. The laminate of claim 1, wherein said end product is selected from the group

9. An end product including a laminate according to any one of claims 1 to 8.