


CLAIMS

1. A bulk catalyst precursor comprising:
 - (a) 1 to 60 wt. % of Ni, on a metal oxide basis;
 - (b) 1 to 40 wt. % of Mo, on a metal oxide basis;
 - (c) 5 to 80 wt. % of W, on a metal oxide basis; and
 - (d) 2 to 45 wt. % of Ti, on a metal oxide basis.
2. The bulk catalyst precursor of claim 1, further comprising an organic compound-based component.
3. The bulk catalyst precursor of claim 2, wherein the organic compound-based component is selected from the group of an organic acid or salt thereof, a sugar, a sugar alcohol, or a combination thereof.
4. The bulk catalyst precursor of claim 2, wherein the organic compound-based component is selected from the group of glyoxylic acid, pyruvic acid, lactic acid, malonic acid, oxaloacetic acid, malic acid, fumaric acid, maleic acid, tartaric acid, gluconic acid, citric acid, oxamic acid, serine, aspartic acid, glutamic acid, iminodiacetic acid, ethylenediaminetetraacetic acid, fructose, glucose, galactose, mannose, sucrose, lactose, maltose, erythritol, xylitol, mannitol, sorbitol, or a combination thereof.
5. The bulk catalyst precursor of claim 2, wherein a molar ratio of Ni to the organic compound-based component is in a range of 3:1 to 20:1.
6. The bulk catalyst precursor of claim 1, wherein a molar ratio of Ti/(Ni+Mo+W) is in a range of from 10:1 to 1:10.

7. The bulk catalyst precursor of claim 1, wherein a molar ratio of Ni/W is in a range of 10:1 to 1:10.

8. The bulk catalyst precursor of claim 1, wherein a molar ratio of W/Mo is in a range of 100:1 to 1:100.

9. The bulk catalyst precursor of claim 1, wherein the bulk catalyst precursor is of formula:



wherein:

- (i) A is an alkali metal cation, a rare earth metal cation, an ammonium cation, an organic ammonium cation, phosphonium cation, or a combination thereof;
- (ii) L is an organic compound-based component; and
- (iii) $0 \leq y \leq 2/p$; $0 \leq x < 2$; $0 \leq v < 2$; $0 < z$; $0 < m < 1$; $0 < n < 4$; $0.1 < w/(z+1) < 10$.

10. The bulk catalyst precursor of claim 1, wherein the bulk catalyst precursor is defined by a region of a quaternary phase diagram wherein the region is defined by ten points *ABCDEFGHIJ* and wherein the ten points, on a metal oxide basis (wt. %), are: A (Ni=0.39, Mo=0.00, W=0.41, Ti=0.2), B (Ni=0.08, Mo=0.00, W=0.72, Ti=0.2), C (Ni=0.09, Mo=0.17, W=0.54, Ti=0.2), D (Ni=0.31, Mo=0.25, W=0.24, Ti=0.2), E (Ni=0.40, Mo=0.14, W=0.26, Ti=0.2), F (Ni=0.34, Mo=0.00, W=0.36, Ti=0.3), G (Ni=0.07, Mo=0.00, W=0.63, Ti=0.3), H (Ni=0.08, Mo=0.15, W=0.48, Ti=0.3), I (Ni=0.27, Mo=0.22, W=0.21, Ti=0.3), and J (Ni=0.35, Mo=0.12, W=0.23, Ti=0.3).

11. The bulk catalyst precursor of claim 1, wherein the bulk catalyst precursor defined by a region of a quaternary phase diagram defined by eight points *ABCDEFGH* and wherein the eight points, on a metal oxide basis (wt. %), are: A

(Ni=52.5, Mo=3.5, W=14, Ti=30), *B* (Ni=38.5, Mo=17.5, W=14, Ti=30), *C* (Ni=21, Mo=17.5, W=31.5, Ti=30), *D* (Ni=35, Mo=3.5, W=31.5, Ti=30), *E* (Ni=60, Mo=4, W=16, Ti=20), *F* (Ni=44, Mo=20, W=16, Ti=20), *G* (Ni=24, Mo=20, W=36, Ti=20), and *H* (Ni=40, Mo=4, W=36, Ti=20).

12. The bulk catalyst precursor of claim 1, further comprising 1 to 15 wt. % of a binder.

13. The bulk catalyst precursor of claim 1, having one or more of the following properties: a BET specific surface area of from 50 to 250 m²/g; a pore volume of from 0.02 to 0.80 cm³/g; and particle density of 1.00 to 3.00 cm³/g.

14. A sulfided bulk catalyst characterized in that it is a bulk catalyst precursor according to claim 1 that has been sulfided.

15. A method for preparing the bulk catalyst precursor of claim 1, the method comprising:

(a) combining in a reaction mixture:

- (i) a Ni-containing precursor;
- (ii) a Mo-containing precursor;
- (iii) a W-containing precursor;
- (iv) a Ti-containing precursor;
- (v) optionally, an organic compound-based component; and
- (vi) a protic liquid; and

(b) reacting the mixture under conditions sufficient to cause precipitation of the bulk catalyst precursor;

wherein the steps to prepare the bulk catalyst precursor are carried out at a temperature of no more than 200°C.

16. The method of claim 15, wherein the reaction mixture is prepared by:
- preparing a first mixture comprising a Ni-containing precursor, a protic liquid, and, optionally, an organic compound-based component;
 - preparing a second mixture comprising a Mo-containing precursor, a W-containing precursor, and a protic liquid;
 - adding a Ti-containing precursor to the first mixture, the second mixture, or a combination thereof;
 - heating both the first and second mixtures to a temperature of from 60°C to 150°C;
 - combining the first and second mixtures together.
17. The method of claim 16, wherein the Ti-containing precursor is selected from TiO₂ nanoparticles, colloidal TiO₂, fumed TiO₂, titanium hydroxide, organotitanium compounds, titanium halides, organotitanium halides, water-soluble titanium salts, or a combination thereof.
18. A method for preparing the bulk catalyst precursor of claim 1, the method comprising:
- (a) combining in a reaction mixture:
 - (i) a Ni-containing precursor;
 - (ii) a Mo-containing precursor;
 - (iii) a W-containing precursor;
 - (iv) optionally, an organic compound-based component; and
 - (v) a protic liquid; and
 - (b) reacting the mixture under conditions sufficient to cause precipitation of an intermediate bulk catalyst precursor; and
 - (c) compositing the intermediate bulk catalyst precursor with a Ti-containing precursor to form the bulk catalyst precursor;

wherein the steps to prepare the bulk catalyst precursor are carried out at a temperature of no more than 200°C.

19. The method of claim 18, wherein the reaction mixture is prepared by:

preparing a first mixture comprising a Ni-containing precursor, a protic liquid, and, optionally, an organic compound-based component;

preparing a second mixture comprising a Mo-containing precursor, a W-containing precursor, and a protic liquid;

heating both the first and second mixtures to a temperature of from 60°C to 150°C; and

combining the first and second mixtures together.

20. The method of claim 18, wherein the Ti-containing precursor is selected from TiO₂ nanoparticles, fumed TiO₂, or a combination thereof.

21. The method of claim 18, wherein the intermediate bulk catalyst precursor is a Ni–Mo–W bulk catalyst precursor.

22. The method of claim 15 or claim 18, wherein the reacting is carried out at one or more temperatures either (a) in a range of 60°C to 100°C under atmospheric pressure or (b) above 100°C under autogenous pressure.

23. The method of claim 15 or claim 18, wherein the organic compound-based component is selected from an organic acid or salt thereof, a sugar, a sugar alcohol, or a combination thereof.

24. The method of claim 23, wherein the organic compound-based component is selected from glyoxylic acid, pyruvic acid, lactic acid, malonic acid, oxaloacetic acid, malic acid, fumaric acid, maleic acid, tartaric acid, gluconic acid, citric acid, oxamic

acid, serine, aspartic acid, glutamic acid, iminodiacetic acid, ethylenediaminetetraacetic acid, fructose, glucose, galactose, mannose, sucrose, lactose, maltose, erythritol, xylitol, mannitol, sorbitol, or a combination thereof.

25. The method of claim 15 or claim 18, further comprising one or more of the following steps:

compositing the bulk catalyst precursor with 0 to 40 wt. % with a material selected from the group of binder materials, conventional hydroprocessing catalysts, cracking compounds, or mixtures thereof;

spray-drying, (flash) drying, milling, kneading, slurry-mixing, dry or wet mixing, or combinations thereof;

shaping,

drying and/or thermally treating at a temperature of no more than 200°C; or sulfiding.

26. A process for hydroprocessing a hydrocarbon feedstock, the process comprising contacting the hydrocarbon feedstock with hydrogen in the presence of a bulk catalyst at hydroprocessing conditions to give at least one product, wherein the bulk catalyst is a derived or derivable from a bulk catalyst precursor comprising:

- (a) 1 to 60 wt. % of Ni, on a metal oxide basis;
- (b) 1 to 40 wt. % of Mo, on a metal oxide basis;
- (c) 5 to 80 wt. % of W, on a metal oxide basis; and
- (d) 2 to 45 wt. % of Ti, on a metal oxide basis.

27. The process of claim 26, wherein the hydroprocessing is selected from the group consisting of hydrodesulfurization, hydrodenitrogenation, hydrodeoxygenation, hydrodemetallation, hydrodearomatization, hydrogenation, hydrogenolysis, hydrotreating, hydroisomerization, and hydrocracking.

28. The process of claim 26, wherein the hydroprocessing conditions include a temperature of from 200°C to 450°C; a pressure of from 250 to 5000 psig (1.7 to 34.6 MPa); a liquid hourly space velocity of from 0.1 to 10 h⁻¹; and a hydrogen gas rate of from 100 to 15,000 SCF/B (17.8 to 2672 m³/m³).