

ABSTRACTAQUEOUS COATING COMPOSITION

5 An aqueous dispersed, low VOC coating containing a
polymeric binder comprises an addition copolymer grafted
epoxy-polyester terpolymer. The graft terpolymer comprises
by weight between 1% and 70% unsaturated polyester, 5% and
80% epoxy resin, and 5% and 70% addition copolymer, where
10 the terpolymer has an Acid Number above about 30 and is
dispersed into water with a volatile base.