

- 1 -

PROCESS TO PREPARE A PARAFFIN WAX

The present invention provides a paraffin wax and a process to prepare said paraffin wax.

Paraffin wax may be obtained by various processes. US 2,692,835 discloses a method for deriving paraffin wax from crude oil. Also, paraffin wax may be obtained using the so called Fischer-Tropsch process. An example of such process is disclosed in WO 2002/102941, EP 1 498 469, WO 2004/009739 and WO 2013/064539.

WO 2000/11113 discloses a process to prepare Fischer-Tropsch derived wax products, by feeding a Fischer-Tropsch derived paraffinic into a distillation column, followed by operating the distillation column to produce wax products, which wax products are withdrawn from the distillation column.

A problem of the process disclosed in WO 2000/11113 is that although this process delivers wax products, the wax products are not refined enough to be used in applications such as candles, hot melt adhesives, crayons, packaging, and PVC extrusion lubricants in an advantageous way.

It is an object of the invention to solve or minimize at least of one of the above problems. It is a further object of the present invention to provide a paraffin wax which can be advantageously used in applications such as candles, hot melt adhesives, crayons, packaging, and PVC extrusion lubricants.

Moreover, an object of the present invention is to provide an efficient method for preparing refined paraffin wax product in a high yield. One of the above or other objects may be achieved according to the present invention by providing a paraffin wax having a congealing

- 2 -

point according to ASTM D938 of at least 75°C and a Saybolt colour according to ASTM D156 of at least 25 cm.

It has now surprisingly been found according to the present invention that the paraffin wax is a fully refined wax which may be advantageously used in several wax applications.

An important advantage of the present invention is that the paraffin wax may be advantageously used in wax applications such as candles, hot melt adhesives, crayons, packaging, and PVC extrusion lubricants.

In another embodiment of the present invention there is provided a process to prepare Fischer-Tropsch paraffin waxes.

An advantage of said process according to the present invention is that by distilling the Fischer-Tropsch derived feed without a preceding hydrogenation step results in paraffin waxes having high Saybolt colours.

The relation between hydrogenation of the Fischer-Tropsch derived feed and the Saybolt colour of Fischer-Tropsch derived waxes is for example described on page 181 in the "Handbook of Commercial Catalysts, Heterogeneous catalysts", Howard F. Rase, CRC Press LLC, Florida, 2000, ISBN 0-8493-9417-1.

A further advantage is that the hydrogenated Fischer-Tropsch product stream is more stable with respect to product degradation in subsequent distillation steps. Degradation may be caused by exposure to high temperature and by oxygen ingress in vacuum columns.

Hydrogenation generally results in higher quality of the normal paraffinic products, e.g. in terms of colour or odour.

- 3 -

The following detailed description does not limit the invention. Instead, the scope of the invention is defined by the appended claims.

5 According to the present invention, a paraffin wax has a congealing point according to ASTM D938 of at least 75°C.

The paraffin wax comprises primarily n-paraffins. The paraffin wax according to the present invention comprises more than 85 wt.% of n-paraffins, preferably
10 more than 90 wt.% of n-paraffins.

Paraffin waxes are known and described for example in US 2,692,835, WO2002/102941, EP 1 498 469 and WO 2004/009739.

Suitably, the paraffin wax according to the present
15 invention has a congealing point according to ASTM D938 in the range of from 75 to 85°C.

Also, the paraffin wax according to the present invention has a congealing point according to ASTM D938 of at least 80°C.

20 Further, the paraffin wax according to the present invention has a Saybolt colour according to ASTM D156 of at least 25 cm.

Preferably, the paraffin wax according to the present invention has a Saybolt colour according to ASTM
25 D156 of at least 30 cm.

Typically, the Saybolt colour scale is used to quantify colour intensity for mildly coloured substances in liquid state. For this objective waxes are molten for measurement. The scale runs from <-16 cm to >30cm. >30 cm
30 means water white. The higher the number the better (i.e. the lesser) the colour.

The paraffin wax according to the present invention has preferably an oil content according to ASTM D721 of

- 4 -

less than 0.5 wt.%, more preferably less than 0.45 wt.%.

It is preferred that the paraffin wax according to the present invention is a Fischer-Tropsch derived paraffin wax.

5 The Fischer-Tropsch derived paraffin wax is derived from a Fischer-Tropsch process. Fischer-Tropsch product stream is known in the art. By the term "Fischer-Tropsch derived" is meant a paraffin wax is, or is derived from a Fischer-Tropsch process. A Fischer-Tropsch derived
10 paraffin wax may also be referred to a GTL (Gas-to-Liquids) product. An example of a Fischer-Tropsch process is given in WO2002/102941, EP 1 498 469 and WO2004/009739, the teaching of which is incorporated by reference.

15 The Fischer-Tropsch derived paraffin wax comprises paraffins, primarily n-paraffins. Preferably, the Fischer-Tropsch derived paraffin wax comprises more than 85 wt.% of n-paraffins, preferably more than 90 wt.% of n-paraffins.

20 In a further aspect, the present invention provides a process to prepare a Fischer-Tropsch derived paraffin wax, the process at least comprising the following steps:
(a) providing a Fischer-Tropsch product stream comprising paraffins having from 10 to 300 carbon atoms;
25 (b) separating the Fischer-Tropsch product stream of step (a), thereby obtaining at least a fraction comprising 10 to 17 carbon atoms and a fraction comprising 18 to 300 carbon atoms;
(c) subjecting the fraction comprising 18 to 300 carbon
30 atoms of step (b) to a hydrogenation step, thereby obtaining a hydrogenated fraction comprising 18 to 300 carbon atoms;

- 5 -

(d) separating the hydrogenated fraction comprising 18 to 300 carbon atoms of step (c), thereby obtaining one or more first light waxes having a congealing point in the range of 30 to 75°C and a second heavy wax having a congealing point in the range of 75 to 120°C;

(e) separating the heavy wax of step (d) to obtain a distillate wax fraction having a congealing point of at least 75°C, preferably of at least 80°C;

f) hydrofinishing the distillate wax fraction of step (e) thereby obtaining a hydrofinished distillate wax fraction having a congealing point of at least 75°C, preferably of at least 80°C.

In step (a) of the process according to the present invention a Fischer-Tropsch product stream comprising paraffins having from 10 to 300 carbon atoms is provided.

By the part "a Fischer-Tropsch product stream comprising paraffins having from 10 to 300 carbon atoms is meant 10 to 300 carbon atoms per molecule.

The Fischer-Tropsch product stream as provided in step (a) is derived from a Fischer-Tropsch process. Fischer-Tropsch product stream is known in the art. By the term "Fischer-Tropsch product" is meant a synthesis product of a Fischer-Tropsch process. In a Fischer-Tropsch process synthesis gas is converted to a synthesis product. Synthesis gas or syngas is a mixture of hydrogen and carbon monoxide that is obtained by conversion of a hydrocarbonaceous feedstock. Suitable feedstock include natural gas, crude oil, heavy oil fractions, coal, biomass and lignite. A Fischer-Tropsch product derived from a hydrocarbonaceous feedstock which is normally in the gas phase may also be referred to a GTL (Gas-to-Liquids) product. The preparation of a Fischer-Tropsch product has been described in e.g. WO2003/070857.

- 6 -

The product stream of the Fischer-Tropsch process is usually separated into a water stream, a gaseous stream comprising unconverted synthesis gas, carbon dioxide, inert gasses and C1 to C3, and a C4+ stream.

5 The full Fischer-Tropsch hydrocarbonaceous product suitably comprises a C1 to C300 fraction.

 Lighter fractions of the Fischer-Tropsch product, which suitably comprises C3 to C9 fraction are separated from the Fischer-Tropsch product by distillation thereby
10 obtaining a Fischer-Tropsch product stream, which suitably comprises C10 to C300 fraction.

 The weight ratio of compounds having at least 60 or more carbon atoms and compounds having at least 30 carbon atoms in the Fischer-Tropsch product is preferably at
15 least 0.2, more preferably 0.3.

 Suitably, in case of preparation of Fischer-Tropsch derived wax fraction having a congealing point of above 90°C weight ratio is at least 0.5.
 The weight ratio in the Fischer-Tropsch product may lead
20 to Fischer-Tropsch derived paraffin waxes having a low oil content.

 In step (b) of the process according to the present invention the Fischer-Tropsch product stream of step (a) is separated to obtain at least a fraction comprising 10
25 to 17 carbon atoms and a fraction comprising 18 to 300 carbon atoms.

 The separation is preferably performed by means of a distillation at atmospheric or slightly below atmospheric pressure conditions. It is preferred that the
30 distillation is carried out at a pressure of 500 mbara to atmospheric and a temperature of 250 to 330°C in the bottom section of the column.

- 7 -

In step (c) of the process according to the present invention the fraction comprising 18 to 300 carbon atoms of step (b) is subjected to a hydrogenation step, thereby obtaining a hydrogenated fraction comprising 18 to 300 carbon atoms. The hydrogenation is suitably carried out at a temperature between 200 and 275°C and at a pressure between 20 and 70 bar.

Typical hydrogenation conditions for hydrogenation of the above fractions are described in e.g. WO2007/082589.

In step (d) of the process according to the present invention the hydrogenated fraction comprising 18 to 300 carbon atoms of step (c) is separated to obtain one or more first light waxes having a congealing point in the range of 30 to 75 °C and a second heavy wax having a congealing point in the range of 75 to 120°C.

By light wax is meant wax having a congealing point in the range of from 30 to 75°C. By heavy wax is meant wax having a congealing point in the range of from 75 to 120°C.

Suitably, the hydrogenated fraction comprising 18 to 300 carbon atoms of step (c) is separated by vacuum distillation at a pressure between 5 and 20 mbar, preferably between 5 and 15 mbar, and more preferably between 10 and 15 mbar. Also the distillation is preferably carried out at a temperature of from 300 to 350°C.

Preferably, the first light one or more waxes are obtained as distillate and/or side cuts in vacuum distillation, e.g. a first light wax fraction having a congealing point in the range of from 30 to 35°C, a second light wax fraction having a congealing point in the range of from 50 to 60°C, and a third light wax

- 8 -

fraction having a congealing point in the range of from 65 to 75°C.

Suitably, the first light wax fraction is obtained as top cut of the vacuum distillation, the second light
5 wax fraction is obtained as a side cut of the vacuum distillation and the third light wax fraction is obtained as heavier side cut of the vacuum distillation.

Preferably, one or more light wax fractions having a congealing point in the range of from 30 to 75°C of step
10 (d) are hydrofinished thereby obtaining one or more hydrofinished wax fractions having a congealing point in the range of from 30 to 75°C. Suitably, a wax fraction having a congealing point in the range 30 to 75°C is hydrofinished thereby obtaining a hydrofinished wax
15 fraction having a congealing point in the range of from 30 to 75°C.

Optionally, the first and second light wax fractions are hydrofinished thereby obtaining a first light hydrofinished wax fraction having a congealing point in
20 the range of from 30 to 35°C, and a second light hydrofinished wax fraction having a congealing point in the range of from 50 to 60°C.

Preferably at least the third light wax i.e. the heaviest side cut of the vacuum distillation step is hydrofinished thereby obtaining a hydrofinished wax
25 fraction having a congealing point in the range of 65-75°C.

Typical hydrofinishing conditions for hydrofinishing of the above fractions are described in e.g.
30 WO2007/082589.

In step (e) of the process according to the present invention, the heavy wax of step (d) is separated thereby

- 9 -

obtaining distillate wax having a congealing point of at least 75°C, preferably of at least 80°C.

Preferably, the second heavy wax of step (d) is separated, thereby obtaining at least one distillate wax fraction having a congealing point in the range of from 75 to 85°C and at least one residual wax fraction having a congealing point from 95 to 120°C.

Further, the heavy second wax of step (d) is separated, thereby obtaining at least one distillate wax fraction having a congealing point in the range of from 70 to 90°C, preferably 70 to 85°C and more preferably 75 to 85°C.

In step (f) of the process according to the present invention, the distillate fraction of step (e) is hydrofinished thereby obtaining a hydrofinished distillate wax having a congealing point of at least 75°C, more preferably of at least 80°C.

Suitably, the heavy distillate wax fraction having a congealing point in the range of from 75 to 85°C is hydrofinished thereby obtaining a hydrofinished heavy distillate wax fraction having a congealing point in the range of from 75 to 85°C.

Further, the heavy distillate wax fraction having a congealing point in the range of from 70 to 90°C, preferably in the range of from 70 to 85°C and more preferably in the range of from 75 to 85°C are hydrofinished thereby obtaining hydrofinished heavy distillate wax fraction having a congealing point in the range of from 70 to 90°C, preferably in the range of from 70 to 85°C and more preferably in the range of from 75 to 85°C.

Preferably, the heavy residual wax fraction having a congealing point in the range of from 95 to 120°C is

- 10 -

hydrofinished thereby obtaining a hydrofinished heavy residual wax fraction having a congealing point in the range of from 95 to 120°C.

5 Typical hydrofinishing conditions for hydrofinishing of the above fractions are described in e.g. WO2007/082589.

10 The heavy second wax of step (e) is preferably separated by short path distillation at a pressure between 0.05 and 0.5 mbar, and more preferably between 0.1 and 0.3 mbar. The distillation is preferably carried out at a temperature of from 200 to 350°C and more preferably from 250 to 300°C.

15 Typically, the distillate wax fraction having a congealing point of at least 75°C, preferably of at least 80°C is obtained as the distillate fraction of the short path distillation. By the term distillate is meant a fraction obtained with distillation which is a top cut or side cut but not a residual bottom fraction.

20 Short path distillation, also known as molecular distillation is known in the art and therefore not described here in detail. An example of a form of short path distillation is a Wiped Film Evaporator. Typical short path distillations are for example described in Chapter 9.1 in "Distillation, operations and applications", Andrzej Górak and Hartmut Schoenmakers, Elsevier Inc, Oxford, 2014.

25 Figure 1 schematically shows a process scheme of the process scheme of a preferred embodiment of the process according to the present invention.

30 For the purpose of this description, a single reference number will be assigned to a line as well as a stream carried in that line.

- 11 -

The process scheme is generally referred to with reference numeral 1.

In a Fischer-Tropsch process reactor a Fischer-Tropsch product stream is obtained (not shown). This product is separated in a distillation column 2 into a fraction 10 comprising 10 to 17 carbon atoms and a fraction 20 comprising 18 to 300 carbon atoms. Fraction 20 is fed to a hydrogenation reactor 3 wherein fraction 20 is converted to a hydrogenated fraction 30. Fraction 30 is distilled in a vacuum distillation column 4 to recover one or more wax fractions 40 having a congealing point in the range of from 30 to 75°C and a heavy fraction 50. Fractions 40 is fed to a hydrofinishing reactor 5 wherein fractions 40 is converted to hydrofinished fractions 60 having a congealing point in the range of from 30 to 75°C.

Heavy wax 50 is distilled in a short path distillation column 6 to recover a distillate wax fraction 70 having a congealing point of at least 80°C.

Fraction 70 is fed to a hydrofinishing reactor 7 wherein fraction 70 is converted to a hydrofinished fraction 80 having a congealing point of at least 80°C.

The fraction 10 is fed to a hydrogenation reactor 8 wherein fraction 10 is converted to a hydrogenated fraction 90 comprising 10 to 17 carbon atoms.

The present invention is described below with reference to the following Examples, which are not intended to limit the scope of the present invention in any way.

Examples

Example

Preparation of Fischer-Tropsch derived paraffin wax fractions having a congealing point of at least 80°C

- 12 -

A Fischer-Tropsch derived paraffin wax having a
congealing point of at least 80°C was obtained using a
Fischer-Tropsch process. To this end a Fischer-Tropsch
effluent was prepared according to the method described
5 in US6858127. Based on C1+ hydrocarbons the effluent had
a C30+ content of 51.1 %m and a C60+ content of 28.5 %m.

The effluent was separated in a fraction A which is
in the gas phase at ambient conditions and a fraction B
which is in the liquid or solid phase at ambient
10 conditions. For all distillations described below care
was taken to avoid temperatures above 370°C for any part
of the distillation equipment in contact with
hydrocarbons and to avoid contact of hydrocarbons with
oxygen. All distillations described below were carried
15 out in a continuous mode.

Fraction B was subjected to a distillation at atmospheric
pressure yielding a top stream comprising a fraction
containing molecules with 9 or less carbon atoms, a side
cut C containing molecules with 10 to 17 carbons atoms
20 and a bottom stream D containing molecules with 18 to 300
carbon atoms. The effective cutpoint for the separation
between streams C and D was 310°C.

Fraction C was hydrogenated over a nickel catalyst
as described in WO 2007/082589 (Catalyst G). Process
25 conditions were: a weight hourly space velocity (WHSV) of
1.0 kg/l/h, 30 bar of pure hydrogen at reactor inlet, a
hydrogen over feedstock ratio of 1000 Nl/kg and a
temperature of 220°C.

The hydrogenated product was separated in a fraction
30 E which is in the gas phase at ambient conditions and a
fraction F which is in the liquid phase at ambient
conditions. Fraction F consists of hydrogenated normal
paraffins in the C10 to C17 range.

- 13 -

The residue of the atmospheric distillation (fraction D) was subjected hydrogenated over a nickel catalyst as described in WO 2007/082589 (Catalyst G). Process conditions were: a weight hourly space velocity (WHSV) of 1.0 kg/l/h, 30 bar of pure hydrogen at reactor inlet, a hydrogen over feedstock ratio of 1000 Nl/kg and a temperature of 220°C.

The hydrogenated product was separated in a fraction G which is in the gas phase at ambient conditions and a fraction H which is in the solid phase at ambient conditions. Fraction H consists of hydrogenated normal paraffins in the C18 to C300 range.

Fraction H is subjected to a vacuum distillation. The distillation was run at a bottom temperature of 320°C and a pressure of 15 mbar. The effective cutpoint between bottom stream and heaviest distillate was 490°C. Several refined waxes were obtained as distillates of which the heaviest was subjected to a hydrofinishing operation over a nickel catalyst as described in WO 2007/082589 (Catalyst G). Process conditions were: a weight hourly space velocity (WHSV) of 1.0 kg/l/h, 60 bar of pure hydrogen at reactor inlet, a hydrogen over feedstock ratio of 1000 Nl/kg and a temperature of 240°C.

The residue of this vacuum distillation (fraction J) is subjected to a short path distillation with an effective cut point of 540°C. The distillation was run at 0.2 mbar and 260°C.

The distillate of the short path distillation (fraction K) is subjected to a hydrofinishing operation over a nickel catalyst as described in WO 2007/082589 (Catalyst G). Process conditions were: a weight hourly space velocity (WHSV) of 1.0 kg/l/h, 60 bar of pure

- 14 -

hydrogen at reactor inlet, a hydrogen over feedstock ratio of 1000 Nl/kg and a temperature of 240°C.

5 The product was separated in a fraction L which is in the gas phase at ambient conditions and a fraction M which is in the solid phase at ambient conditions. Fraction M is obtained as a refined wax with a congealing point of about 80°C The yield of fraction M was 6.8 %m of the Fischer-Tropsch effluent on a hydrocarbon basis.

10 Fraction M is the desired heavy Fischer-Tropsch based distillate hard wax. Properties of fraction M can be found in Table 1.

Table 1

Paraffin wax product (fraction L)	
Congealing point, °C According to ASTM D938	81.1
Oil content, %w, According to ASTM D721	0.33
Saybolt colour ^a , cm According to ASTM D156	30+
Cloud point, °C According to ASTM D5773	88
Kinematic viscosity at 120°C, mm ² /s According to ASTM D445	3.95

^a The Saybolt colour scale is used to quantify colour intensity for mildly coloured substances in liquid state. For this objective waxes are molten for measurement. The scale runs from <-16 cm to >30cm. >30 cm means water white. The higher the number the better (i.e. the lesser) the colour.

Discussion

The results in Table 1 show that starting from a hydrogenated Fischer-Tropsch effluent having C30+ content of 51.1% and a C60+ content of 28.5 % a Fischer-Tropsch derived paraffin wax having a congealing point of about 80°C was obtained. Furthermore, the paraffin wax has a low oil content and a high Saybolt colour.

These observations indicate that the obtained refined Fischer-Tropsch paraffin wax can be advantageously used in applications such as candles, hot melt adhesives, crayons, packaging, and PVC extrusion lubricants.

C L A I M S

1. A paraffin wax having a congealing point according to ASTM D938 in the range of from 75 to 85°C and a Saybolt colour according to ASTM D156 of at least 25 cm.

2. A paraffin wax according to claim 1, having a congealing point according to ASTM D938 of at least 80°C.

3. A paraffin wax according to claim 1 or 2, having a Saybolt colour according to ASTM D156 of at least 30 cm.

4. A paraffin wax according to any one of claims 1 to 3, having an oil content according to ASTM D721 of less than 0.5 wt.%, preferably less than 0.45 wt.%

5. A paraffin wax according to any one of claims 1 to 4, wherein the paraffin wax is a Fischer-Tropsch derived paraffin wax.

6. Process to prepare a paraffin wax according to claim 5, the process at least comprising the following steps:
(a) providing a Fischer-Tropsch product stream comprising paraffins having from 10 to 300 carbon atoms;
(b) separating the Fischer-Tropsch product stream of step (a), thereby obtaining at least a fraction comprising 10 to 17 carbon atoms and a fraction comprising 18 to 300 carbon atoms;
(c) subjecting the fraction comprising 18 to 300 carbon atoms of step (b) to a hydrogenation step, thereby obtaining a hydrogenated fraction comprising 18 to 300 carbon atoms;
(d) separating the hydrogenated fraction comprising 18 to 300 carbon atoms of step (c), thereby obtaining one or more first

light waxes having a congealing point in the range of 30 to 75°C and a second heavy wax having a congealing point in the range of 75 to 120°C;

(e) separating the heavy wax of step (d) to obtain a distillate wax fraction having a congealing point of at least 75°C, preferably of at least 80°C;

(f) hydrofinishing the distillate wax fraction of step (e) thereby obtaining a hydrofinished wax fraction having a congealing point of at least 75°C, preferably of at least 80°C.

7. Process according to claim 6, wherein the heavy wax of step is separated in step (e) by short path distillation at a pressure between 0.05 mbar and 0.5 mbar, preferably between 0.1 and 0.3 mbar.