

TITLE OF INVENTION: PHOTOCURABLE RESIN SHEET

DESCRIPTION

5 TECHNICAL FIELD

[0001]

The present invention relates to a photocurable resin sheet.

10 BACKGROUND ART

[0002]

Conventionally, photocurable resin compositions have been widely used in optical applications such as adhesives for displays or optical semiconductors, lenses, and
15 protective films. Most of these resin compositions are liquid at normal temperature (25°C) and used by dispensing methods.

[0003]

Patent Literature 1, for example, discloses an
20 optical photosensitive resin composition which achieves both high photocurability and high transparency by combining a dicyclopentadiene type epoxy resin having no aromatic ring and a monofunctional oxetane resin having no aromatic ring as resins curable by a photoacid generator.
25 However, the resin composition is liquid at normal temperature and therefore cannot be formed into a sheet. In addition, the resin composition incapable of maintaining its shape has the problem of poor handleability because it may have an uneven thickness when applied to a substrate or
30 may flow out from between adherends when used as an adhesive.

[0004]

Moreover, Patent Literature 2 discloses a photocurable resin composition sheet containing a solid
35 epoxy resin, a liquid epoxy resin, and a photoacid

generator, which is excellent in properties such as transparency and heat resistance. However, disadvantageously, the photocurable resin composition sheet is poor in photocurability.

5

CITATION LIST

- Patent Literature

[0005]

Patent Literature 1: JP 2017-141356 A

10

Patent Literature 2: JP 2015-96571 A

SUMMARY OF INVENTION

- Technical Problem

[0006]

15

The present invention aims to provide a photocurable resin sheet excellent in handleability, photocurability, and transparency.

- Solution to problem

20

[0007]

Specifically, the present invention relates to a photocurable resin sheet, containing a high molecular compound (A) and a low molecular compound (B), wherein an epoxy group, an oxetanyl group, and a photopolymerization initiating group are each individually present in the high molecular compound (A) or the low molecular compound (B).

25

[0008]

Preferably, the high molecular compound (A) has a weight average molecular weight of 1,000 to 1,000,000.

30

[0009]

Preferably, the low molecular compound (B) has a molecular weight of less than 1,000.

[0010]

35

Preferably, the photocurable resin sheet has a storage modulus G' at 25°C of 50,000 Pa or higher.

[0011]

Preferably, a cured product of the photocurable resin sheet at 25°C has an optical transmittance at a wavelength of 400 nm of 70% or higher and a refractive index with
5 respect to light at a wavelength of 589 nm of 1.40 or higher.

[0012]

Preferably, the high molecular compound (A) includes at least one selected from the group consisting of
10 poly(meth)acrylic resins, phenoxy resins, polyurethane resins, silicone resins, polyester resins, polyamide resins, and polyimide resins.

[0013]

Preferably, the low molecular compound (B) includes a
15 compound containing an oxetanyl group.

[0014]

Preferably, the low molecular compound (B) includes a photoacid generator.

[0015]

20 The present invention also relates to an optical material obtained by curing the photocurable resin sheet of the present invention.

- Advantageous Effects of Invention

25 [0016]

The photocurable resin sheet of the present invention is capable of maintaining its shape without becoming liquid at normal temperature even before curing, and therefore has excellent handleability as well as excellent
30 photocurability and transparency. Moreover, the photocurable resin sheet has improved moldability and workability such as facilitating collective sealing or fine control of thickness, and therefore has improved productivity of products as well.

35

DESCRIPTION OF EMBODIMENTS

[0017]

The photocurable resin sheet of the present invention contains a high molecular compound (A) and a low molecular compound (B). Further, an epoxy group, an oxetanyl group, and a photopolymerization initiating group are each individually present in the high molecular compound (A) or the low molecular compound (B).

By "an epoxy group, an oxetanyl group, and a photopolymerization initiating group are each individually present in the high molecular compound (A) or the low molecular compound (B)", as used herein, it is meant that each of the groups is present in either of the compounds irrespective of the other groups. For example, there may be a case where an epoxy group is present in a high molecular compound (A), an oxetanyl group is present in a low molecular compound (B1), and a photopolymerization initiating group is present in a low molecular compound (B2) or a case where an epoxy group, an oxetanyl group, and a photopolymerization initiating group are each present in one high molecular compound (A).

[0018]

High molecular compound (A)

The high molecular compound (A) may have any weight average molecular weight, but the weight average molecular weight is preferably 1,000 to 1,000,000, more preferably 10,000 to 100,000. A high molecular compound (A) having a weight average molecular weight of less than 1,000 may be liquid at normal temperature, failing to maintain a sheet shape. A high molecular compound (A) having a weight average molecular weight of more than 1,000,000 may not be dissolved in a solvent, failing to be processed into a sheet shape. The high molecular compound (A) may be a single compound or a combination of two or more compounds.

As used herein, the weight average molecular weight

of the high molecular compound is determined by dissolving the high molecular compound in tetrahydrofuran and measuring the solution under the following conditions using a GPC device (HLC-8320 GPC, Tosoh Corporation) relative to polystyrene standards.

Column: TSKgel Super HZMH/HZ4000/HZ3000/HZ2000

Column size: 6.0 mm I.D. × 150 mm

Eluent: THF

Flow rate: 0.6 mL/min

Detector: RI

Column temperature: 40°C

Injection amount: 20 µL

[0019]

The high molecular compound (A) may have any glass transition temperature (T_g). In order to achieve higher handleability and storage modulus G' , the glass transition temperature is preferably -20°C or higher, more preferably -10°C or higher, still more preferably 0°C or higher, particularly preferably 5°C or higher, most preferably 10°C or higher. The upper limit of the glass transition temperature is not limited but is preferably 100°C or lower, more preferably 80°C or lower, still more preferably 60°C or lower.

As used herein, the glass transition temperature (T_g) of the high molecular compound refers to the temperature at which a loss tangent ($\tan\delta$) peak is exhibited in DMA (tensile test) under conditions including a rate of temperature rise of 5°C/min, a sample width of 5 mm, a distance between chucks of 20 mm, and a frequency of 10 Hz.

[0020]

Non-limiting examples of the high molecular compound (A) include poly(meth)acrylic resins, phenoxy resins, polyurethane resins, silicone resins, polyester resins, polyamide resins, and polyimide resins. Among these, poly(meth)acrylic resins are preferred from the standpoint

of photocurability and solubility in a solvent.

[0021]

Examples of the poly(meth)acrylic resins include polymers polymerized from (meth)acrylic acid esters as monomers such as (meth)acrylic acid alkyl esters, (meth)acrylic acid cycloalkyl esters, (meth)acrylic acid aryl esters. The term "(meth)acrylic" as used herein means acrylic and/or methacrylic.

[0022]

Examples of the (meth)acrylic acid alkyl esters include methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, isopropyl (meth)acrylate, butyl (meth)acrylate, isobutyl (meth)acrylate, s-butyl (meth)acrylate, t-butyl (meth)acrylate, pentyl (meth)acrylate, isopentyl (meth)acrylate, hexyl (meth)acrylate, heptyl (meth)acrylate, octyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, isooctyl (meth)acrylate, nonyl (meth)acrylate, decyl (meth)acrylate, isodecyl (meth)acrylate, undecyl (meth)acrylate, dodecyl (meth)acrylate, tridecyl (meth)acrylate, tetradecyl (meth)acrylate, hexadecyl (meth)acrylate, octadecyl (meth)acrylate, and eicosyl (meth)acrylate. Examples of the (meth)acrylic acid cycloalkyl esters include cyclopentyl (meth)acrylate and cyclohexyl (meth)acrylate. Examples of the (meth)acrylic acid aryl esters include phenyl (meth)acrylate and benzyl (meth)acrylate. These (meth)acrylic acid esters may be used alone or in combinations of two or more.

[0023]

The poly(meth)acrylic resins may also be produced by copolymerization of the aforementioned (meth)acrylic acid esters with additional monomers copolymerizable therewith. Examples of such additional monomers include carboxy group-containing monomers, acid anhydride monomers, hydroxy group-containing monomers, sulfonic acid group-containing

monomers, phosphoric acid group-containing monomers, acrylamides, and acrylonitriles. Examples of the carboxy group-containing monomers include (meth)acrylic acid, carboxyethyl (meth)acrylate, carboxypentyl (meth)acrylate, itaconic acid, maleic acid, fumaric acid, and crotonic acid. Examples of the acid anhydride monomers include maleic anhydride and itaconic anhydride. Examples of the hydroxy group-containing monomers include 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 4-hydroxybutyl (meth)acrylate, 6-hydroxyhexyl (meth)acrylate, 8-hydroxyoctyl (meth)acrylate, 10-hydroxydecyl (meth)acrylate, 12-hydroxylauryl (meth)acrylate, and [4-(hydroxymethyl)cyclohexyl]methyl (meth)acrylate. Examples of the sulfonic acid group-containing monomers include styrenesulfonic acid, allylsulfonic acid, 2-(meth)acrylamido-2-methylpropanesulfonic acid, (meth)acrylamidopropanesulfonic acid, and (meth)acryloyloxynaphthalenesulfonic acid. Examples of the phosphoric acid group-containing monomers include 2-hydroxyethylacryloyl phosphate. These additional monomers may be used alone or in combinations of two or more.

[0024]

The poly(meth)acrylic resins may be produced by any polymerization method, including, for example, solution polymerization, emulsion polymerization, suspension polymerization, and bulk polymerization.

[0025]

Examples of the phenoxy resins include polyhydroxy polyethers polymerized from bisphenols and epichlorohydrin. Examples of the bisphenols include bisphenol A and bisphenol F. Bisphenol A is preferred from the standpoint of transparency and heat resistance.

[0026]

The polyurethane resins may be any resin containing a urethane bond as a repeating unit in the backbone.

Examples include polymers of aliphatic or aromatic diols and aromatic or aliphatic diisocyanates. These may be used alone or in combinations of two or more.

[0027]

5 The silicone resins may be any resin containing a siloxane bond as a repeating unit in the backbone. Examples include polymers of diphenylsilane or dimethylsilane. These may be used alone or in combinations of two or more.

10 [0028]

 The polyester resins may be any resin containing an ester bond as a repeating unit in the backbone. Examples include polymers of aliphatic or aromatic diols and aliphatic or aromatic dicarboxylic acids. These may be

15 used alone or in combinations of two or more.

[0029]

 The polyamide resins may be any resin containing an amide bond as a repeating unit in the backbone. Examples include polymers of aliphatic or aromatic diamines and

20 aliphatic or aromatic dicarboxylic acids and ring-opening polymers of cyclic lactams. These may be used alone or in combinations of two or more.

[0030]

 The polyimide resins may be any resin containing an

25 imide bond as a repeating unit in the backbone. Examples include polymers of aliphatic or aromatic diamines and aliphatic or aromatic acid anhydrides. These may be used alone or in combinations of two or more.

[0031]

30 The high molecular compound (A) may contain all of the epoxy, oxetanyl, and photopolymerization initiating groups. Alternatively, the high molecular compound (A) may contain only some of these substituents or none of these substituents. These substituents may be present in both

35 the high molecular compound (A) and the low molecular

compound (B), but the substituent(s) not present in the high molecular compound (A) should be present in the low molecular compound (B). In the case where the high molecular compound (A) contains multiple such substituents, the high molecular compound (A) does not need to be a single compound containing the multiple substituents and may be a combination of multiple compounds each containing one of the substituents. Among these substituents, the high molecular compound (A) preferably contains an epoxy group, more preferably an aliphatic epoxy group, still more preferably a glycidyl (meth)acrylate group.

[0032]

When the high molecular compound (A) is a high molecular compound produced by radical polymerization, such as a poly(meth)acrylic resin, the epoxy, oxetanyl, or photopolymerization initiating group may be introduced by any method. An exemplary method includes copolymerizing a monomer containing an epoxy group, an oxetanyl group, or a photopolymerization initiating group with any of the monomers described above.

[0033]

Examples of the monomer containing an epoxy group include monomers containing aliphatic epoxy groups, monomers containing alicyclic epoxy groups, and monomers containing aromatic epoxy groups. Preferred among these are monomers containing aliphatic epoxy groups.

[0034]

Examples of the monomers containing aliphatic epoxy groups include (meth)acrylates of aliphatic epoxy compounds such as glycidyl ethers of polyhydric alcohols (e.g., 1,4-butanediol diglycidyl ether, 1,6-hexanediol diglycidyl ether, triglycidyl ether of glycerol, triglycidyl ether of trimethylolpropane, tetraglycidyl ether of sorbitol, hexaglycidyl ether of dipentaerythritol, diglycidyl ether of polyethylene glycol, and diglycidyl ether of

polypropylene glycol), polyglycidyl ethers of polyether polyols obtained by addition of one or two or more alkylene oxides to aliphatic polyhydric alcohols (e.g., propylene glycol, trimethylolpropane, glycerol), diglycidyl esters of
 5 aliphatic long-chain dibasic acids, monoglycidyl ethers of aliphatic higher alcohols, glycidyl esters of higher fatty acids, epoxidized soybean oil, octyl epoxystearate, butyl epoxystearate, and epoxidized polybutadiene. Specific examples include epoxy group-containing (meth)acrylates
 10 such as 4-hydroxybutyl (meth)acrylate glycidyl ether and glycidyl (meth)acrylate.

[0035]

Examples of the monomers containing alicyclic epoxy groups include (meth)acrylates of alicyclic epoxy compounds
 15 such as 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexane carboxylate, 3,4-epoxy-1-methylcyclohexyl-3,4-epoxy-1-methylhexane carboxylate, 6-methyl-3,4-epoxycyclohexylmethyl-6-methyl-3,4-epoxycyclohexane carboxylate, 3,4-epoxy-3-methylcyclohexylmethyl-3,4-epoxy-
 20 3-methylcyclohexane carboxylate, 3,4-epoxy-5-methylcyclohexylmethyl-3,4-epoxy-5-methylcyclohexane carboxylate, bis(3,4-epoxycyclohexylmethyl)adipate, 3,4-epoxy-6-methylcyclohexylcarboxylate, methylene-bis(3,4-epoxycyclohexane), propane-2,2-diyl-bis(3,4-
 25 epoxycyclohexane), 2,2-bis(3,4-epoxycyclohexyl)propane, dicyclopentadiene diepoxide, ethylene-bis(3,4-epoxycyclohexane carboxylate), 1-epoxyethyl-3,4-epoxycyclohexane, 1,2-epoxy-2-epoxyethylcyclohexane, and caprolactone-modified products, trimethylcaprolactone-
 30 modified products, and valerolactone-modified products of the foregoing.

[0036]

Examples of the monomers containing aromatic epoxy groups include (meth)acrylates of aromatic epoxy compounds
 35 such as monoglycidyl ethers of polyether alcohols obtained

by addition of alkylene oxides to phenol, cresol, or butylphenol.

[0037]

Examples of the monomer containing an oxetanyl group include oxetanyl group-containing (meth)acrylates such as 3-oxetanylmethyl (meth)acrylate, 3-methyl-oxetanylmethyl (meth)acrylate, 3-ethyl-oxetanylmethyl (meth)acrylate, 3-butyl-oxetanylmethyl (meth)acrylate, and 3-hexyl-oxetanylmethyl (meth)acrylate. Examples of the monomer containing a photopolymerization initiating group include acryloyl group-containing triarylsulfonium salts.

[0038]

When the high molecular compound (A) is a phenoxy resin, a polyurethane resin, a silicone resin, a polyester resin, a polyamide resin, or a polyimide resin, the epoxy, oxetanyl, or photopolymerization initiating group may be introduced by any method. An exemplary method for introducing the epoxy group includes reacting a hydroxy group-containing resin with a chloro group-containing epoxy compound such as epichlorohydrin. An exemplary method for introducing the oxetanyl group includes reacting a hydroxy group-containing resin with a chloro group-containing oxetane compound such as 3-chlorooxetane. An exemplary method for introducing the photopolymerization initiating group includes crosslinking a hydroxy group-containing resin and a hydroxy group-containing photopolymerization initiator with a poly- or diisocyanate.

[0039]

In the case where the high molecular compound (A) contains an epoxy group, the epoxy equivalent of the high molecular compound (A) is not limited, but is preferably 100 to 10,000 g/eq, more preferably 100 to 1,000 g/eq. When the epoxy equivalent is less than 100 g/eq, the density of epoxy groups may be too high, so that the reaction may not be completed due to the steric hindrance

between side chains. When the epoxy equivalent is more than 10,000 g/eq, the density of epoxy groups may be too low to allow the reaction to proceed.

As used herein, the epoxy equivalent of the high molecular compound (A) is measured in conformity with JIS K7236 (2001).

[0040]

In the case where the high molecular compound (A) contains an oxetanyl group, the oxetanyl equivalent of the high molecular compound (A) is not limited, but is preferably 100 to 10,000 g/eq, more preferably 100 to 1,000 g/eq. When the oxetanyl equivalent is less than 100 g/eq, the density of oxetanyl groups may be too high, so that the reaction may not be completed due to the steric hindrance between side chains. When the oxetanyl equivalent is more than 10,000 g/eq, the density of oxetanyl groups may be too low to allow the reaction to proceed.

[0041]

In the case where the high molecular compound (A) contains a photopolymerization initiating group, the amount of the photopolymerization initiating group in the high molecular compound (A) is preferably 0.1 to 50 mol%. When the amount is less than 0.1 mol%, the photocurability may be impaired. When the amount is more than 50 mol%, the molecular weight may not increase due to excessive initiating groups, thereby impairing the photocurability.

[0042]

Although the amount of the high molecular compound (A) in the photocurable resin sheet of the present invention is not limited, the amount is preferably 85% by mass or more, more preferably 88% by mass or more, still more preferably 92% by mass or more, particularly preferably 95% by mass or more, but is preferably 99% by mass or less, more preferably 98% by mass or less. When the amount is less than 85% by mass, the sheet shape may

not be maintained at normal temperature. When the amount is 95% by mass or more, the storage modulus G' achieved tends to be better.

[0043]

5 Low molecular compound (B)

The upper limit of the molecular weight of the low molecular compound (B) is not limited, but is preferably less than 1,000, more preferably 800 or less, still more preferably 700 or less. A low molecular compound (B) having a molecular weight of 1,000 or more may show a lower diffusion rate in the system, thereby impairing the photocurability. The lower limit of the molecular weight is also not limited, but is preferably 100 or more, more preferably 400 or more. The low molecular compound (B) may be a single compound or a combination of two or more compounds.

As used herein, the molecular weight of the low molecular compound is calculated from the molecular structure of the compound. The molecular structure of the compound herein is determined by NMR.

[0044]

The low molecular compound (B) may contain all of the epoxy, oxetanyl, and photopolymerization initiating groups. Alternatively, the low molecular compound (B) may contain only some of these substituents or none of these substituents. These substituents may be present in both the high molecular compound (A) and the low molecular compound (B), but the substituent(s) not present in the low molecular compound (B) should be present in the high molecular compound (A). In the case where the low molecular compound (B) contains multiple such substituents, the low molecular compound (B) does not need to be a single compound containing the multiple substituents and may be a combination of multiple compounds each containing one of the substituents. Among these substituents, the low

molecular compound (B) preferably contains an oxetanyl group or a photopolymerization initiating group.

[0045]

5 Examples of the low molecular compound (B) containing an epoxy group include aliphatic epoxy compounds, alicyclic epoxy compounds, and aromatic epoxy compounds. Preferred among these are alicyclic epoxy compounds.

[0046]

10 Examples of the aliphatic epoxy compounds include glycidyl ethers of polyhydric alcohols such as 1,4-butanediol diglycidyl ether, 1,6-hexanediol diglycidyl ether, triglycidyl ether of glycerol, triglycidyl ether of trimethylolpropane, tetraglycidyl ether of sorbitol, hexaglycidyl ether of dipentaerythritol, diglycidyl ether
15 of polyethylene glycol, and diglycidyl ether of polypropylene glycol; polyglycidyl ethers of polyether polyols obtained by addition of one or two or more alkylene oxides to aliphatic polyhydric alcohols (e.g., propylene glycol, trimethylolpropane, glycerol), diglycidyl esters of
20 aliphatic long-chain dibasic acids, monoglycidyl ethers of aliphatic higher alcohols, glycidyl esters of higher fatty acids, epoxidized soybean oil, octyl epoxystearate, butyl epoxystearate, and epoxidized polybutadiene. These may be used alone or in combinations of two or more.

25 [0047]

Examples of the alicyclic epoxy compounds include 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexane carboxylate, 3,4-epoxy-1-methylcyclohexyl-3,4-epoxy-1-methylhexane carboxylate, 6-methyl-3,4-epoxycyclohexylmethyl-6-methyl-
30 3,4-epoxycyclohexane carboxylate, 3,4-epoxy-3-methylcyclohexylmethyl-3,4-epoxy-3-methylcyclohexane carboxylate, 3,4-epoxy-5-methylcyclohexylmethyl-3,4-epoxy-5-methylcyclohexane carboxylate, bis(3,4-epoxycyclohexylmethyl)adipate, 3,4-epoxy-6-
35 methylcyclohexylcarboxylate, methylene-bis(3,4-

epoxycyclohexane), propane-2,2-diyl-bis(3,4-epoxycyclohexane), 2,2-bis(3,4-epoxycyclohexyl)propane, dicyclopentadiene diepoxide, ethylene-bis(3,4-epoxycyclohexane carboxylate), 1-epoxyethyl-3,4-epoxycyclohexane, and 1,2-epoxy-2-epoxyethylcyclohexane. Also usable are caprolactone-modified products, trimethylcaprolactone-modified products, and valerolactone-modified products of the foregoing. These may be used alone or in combinations of two or more.

10 [0048]

Examples of the aromatic epoxy compounds include monoglycidyl ethers of polyether alcohols obtained by addition of alkylene oxides to phenol, cresol, or butylphenol. These may be used alone or in combinations of two or more.

15

[0049]

Examples of the low molecular compound (B) containing an oxetanyl group include 3-ethyl-3-[(3-ethyloxetan-3-yl)methoxy)methyl]oxetane, 3-methyl-3-hydroxymethyl oxetane, 3-ethyl-3-hydroxymethyl oxetane, 3-ethyl-3-(2-ethylhexyloxymethyl)oxetane, 1,4-bis[(3-ethyl-3-oxetanyl)methoxymethyl]benzene, 3-ethyl-3-(phenoxy)methyl oxetane, di[(3-ethyl-3-oxetanyl)methyl] ether, 3-ethyl-3-(2-ethylhexyloxymethyl)oxetane, phenol novolac oxetane, isobutoxymethyl (3-ethyl-3-oxetanylmethyl) ether, isobornyloxyethyl (3-ethyl-3-oxetanylmethyl) ether, isobornyl (3-ethyl-3-oxetanylmethyl) ether, 2-ethylhexyl (3-ethyl-3-oxetanylmethyl) ether, ethyl diethylene glycol (3-ethyl-3-oxetanylmethyl) ether, di[1-ethyl(3-oxetanyl)]methyl ether, 3,7-bis(3-oxetanyl)-5-oxa-nonane, 1,2-bis[(3-ethyl-3-oxetanylmethoxy)methyl]ethane, 1,3-bis[(3-ethyl-3-oxetanylmethoxy)methyl]propane, ethylene glycol bis(3-ethyl-3-oxetanylmethyl) ether, tricyclodecane diyl dimethylene (3-ethyl-3-oxetanylmethyl) ether, trimethylolpropane tris(3-ethyl-3-oxetanylmethyl) ether,

35

1,4-bis(3-ethyl-3-oxetanylmethoxy)butane, 1,6-bis(3-ethyl-3-oxetanylmethoxy)hexane, pentaerythritol tris(3-ethyl-3-oxetanylmethyl) ether, pentaerythritol tetrakis(3-ethyl-3-oxetanylmethyl) ether, polyethylene glycol bis(3-ethyl-3-oxetanylmethyl) ether, dipentaerythritol hexakis(3-ethyl-3-oxetanylmethyl) ether, dipentaerythritol pentakis(3-ethyl-3-oxetanylmethyl) ether, and dipentaerythritol tetrakis(3-ethyl-3-oxetanylmethyl) ether. These may be used alone or in combinations of two or more. Preferred among these is 3-ethyl-3{[(3-ethyloxetan-3-yl)methoxy]methyl}oxetane.

[0050]

The low molecular compound (B) containing a photopolymerization initiating group may be any low molecular compound containing a group that will generate an ion pair or a radical by photoabsorption. Examples include photocationic polymerization initiators containing photocationic polymerization initiating groups and photoradical polymerization initiators containing photoradical generating groups.

[0051]

The photocationic polymerization initiators, when irradiated with active energy rays such as visible light, ultraviolet light, X-rays, or electron beams, generate cationic species or Lewis acids, thereby initiating polymerization of an epoxy group and an oxetanyl group. Preferred among the photocationic polymerization initiators are photoacid generators or photobase generators, with photoacid generators being more preferred. When the active energy rays used are visible light rays, preferred are photocationic polymerization initiators particularly sensitive to light at 380 nm or longer. Photocationic polymerization initiators generally show maximum absorption at around 300 nm or shorter wavelengths. Thus, photosensitizers with maximum absorption of light in the range of longer wavelengths, specifically at a wavelength

longer than 380 nm may be incorporated to allow the photocationic polymerization initiators to be sensitive to light at around such wavelengths, thereby promoting generation of cationic species or Lewis acids from the photocationic polymerization initiators.

[0052]

Examples of the photoacid generators include onium salts containing anionic and cationic components. Examples of onium cationic components include aromatic diazoniums, aromatic sulfoniums, aromatic iodoniums, aromatic seleniums, aromatic pyridiniums, aromatic ferroceniums, and aromatic phosphoniums. Preferred among these are aromatic sulfoniums.

[0053]

Examples of anionic components include PF_6^- , $\text{PF}_4(\text{CF}_2\text{CF}_3)_2^-$, SbF_6^- , AsF_6^- , SbCl_6^- , BiCl_5^- , SnCl_6^- , ClO_4^- , dithiocarbamate anions, SCN^- , and trifluoromethanesulfonate. Preferred among these are PF_6^- , SbF_6^- , and AsF_6^- , with PF_6^- or SbF_6^- being more preferred.

[0054]

The low molecular compound (B) is more preferably a combination of a low molecular compound (B) containing an oxetanyl group and a low molecular compound (B) containing a photopolymerization initiating group. In particular, it is preferred to combine a high molecular compound (A) containing an epoxy group, a low molecular compound (B) containing an oxetanyl group, and a low molecular compound (B) containing a photopolymerization initiating group. More preferred is a combination of a high molecular compound (A) that is a poly(meth)acrylic resin containing an epoxy group, a low molecular compound (B) containing an oxetanyl group, and a low molecular compound (B) containing a photopolymerization initiating group. The low molecular compound (B) containing a photopolymerization initiating group is preferably a photocationic polymerization

initiator, more preferably a photoacid generator, still more preferably an aromatic sulfonium salt.

[0055]

The amount of the low molecular compound (B) in the photocurable resin sheet of the present invention is not limited, but is preferably 0.5 to 15% by mass, more preferably 1 to 12% by mass. The lower limit of the amount is still more preferably 2% by mass or more, while the upper limit is still more preferably 8% by mass or less, particularly preferably 5% by mass or less. When the amount is less than 0.5% by mass, the photocurability may be impaired. When the amount is more than 15% by mass, the low molecular compound (B) may bleed to the sheet surface, impairing the handleability. When the amount is 5% by mass or less, the storage modulus G' achieved tends to be better.

[0056]

In the case where the low molecular compound (B) is a combination of a low molecular compound (B) containing an oxetanyl group and a low molecular compound (B) containing a photopolymerization initiating group, the amount of the low molecular compound (B) containing an oxetanyl group in the photocurable resin sheet is preferably 0.5 to 10% by mass, more preferably at least 0.5% by mass but less than 5% by mass. The upper limit of the amount is still more preferably 4% by mass or less. When the amount is less than 0.5% by mass, the photocurability may be impaired. When the amount is more than 10% by mass, the low molecular compound (B) may bleed to the sheet surface, impairing the handleability. In the case where the low molecular compound (B) is a combination of a low molecular compound (B) containing an oxetanyl group and a low molecular compound (B) containing a photopolymerization initiating group, the amount of the low molecular compound (B) containing a photopolymerization initiating group in the photocurable resin sheet is preferably 0.01 to 5% by mass,

more preferably 0.05 to 2.5% by mass. When the amount is less than 0.01% by mass, the photocurability may be impaired. When the amount is more than 5% by mass, the low molecular compound (B) may bleed to the sheet surface, impairing the handleability or transparency.

[0057]

The combined amount of the high molecular compound (A) and the low molecular compound (B) in the photocurable resin sheet of the present invention is preferably 90% by mass or more, more preferably 95% by mass or more, still more preferably 98% by mass or more, particularly preferably 99% by mass or more, and may be 100% by mass.

[0058]

The photocurable resin sheet of the present invention may contain additional components in addition to the high molecular compound (A) and the low molecular compound (B) as long as the advantageous effect of the present invention is not impaired. Examples of such additional components include photosensitizers and colorants. These may be used alone or in combinations of two or more.

[0059]

Examples of the photosensitizers include anthracene compounds, pyrene compounds, carbonyl compounds, organic sulfur compounds, persulfides, redox compounds, azo or diazo compounds, halogen compounds, and photoreducing dyes. These may be used alone or in combinations of two or more. Particularly preferred are anthracene compounds excellent in a photosensitizing effect. The amount of the photosensitizers is preferably 0.1 to 5% by mass, more preferably 0.5 to 3% by mass.

[0060]

The photocurable resin sheet of the present invention preferably has a storage modulus G' at 25°C of 50,000 Pa or higher, more preferably 100,000 Pa or higher, still more preferably 200,000 Pa or higher, particularly preferably

300,000 Pa or higher, most preferably 400,000 Pa or higher, further most preferably 420,000 Pa or higher. The upper limit of the storage modulus G' is not limited, but is preferably 1,000,000 Pa or lower. When the storage modulus
5 G' is lower than 50,000 Pa, the photocurable resin sheet may have poor handleability due to stickiness (tackiness). The storage modulus can be measured using a dynamic viscoelastometer.

Increasing the amount of the high molecular compound
10 (A) in the photocurable resin sheet tends to provide a higher storage modulus G' . Also, the use of a high molecular compound (A) having a higher glass transition temperature tends to provide a higher storage modulus G' . Moreover, removing more residual solvent such as methyl
15 ethyl ketone from the sheet tends to provide a higher storage modulus G' .
[0061]

A cured product of the photocurable resin sheet of the present invention at 25°C preferably has an optical
20 transmittance at a wavelength of 400 nm of 70% or higher, more preferably 80% or higher. The upper limit of the optical transmittance is not limited, but is preferably 99% or lower. When the optical transmittance is lower than 70%, the cured product may have insufficient transparency,
25 failing to be usable in optical applications. The optical transmittance can be measured using a spectrophotometer.

The optical transmittance at a wavelength of 400 nm may be adjusted within the above range by reducing the photoabsorption in the UV region by the raw materials used.
30 [0062]

The preferred range of the refractive index with respect to light at a wavelength of 589 nm of the cured product of the photocurable resin sheet of the present invention depends on the application of the photocurable
35 resin sheet. For example, in the case where the

photocurable resin sheet of the present invention is used in lenses, the refractive index is preferably 1.40 or higher, more preferably 1.47 or higher. The upper limit of the refractive index is not limited, but is preferably 1.80 or lower. The refractive index can be measured using a refractive index meter.

The refractive index with respect to light at a wavelength of 589 nm may be adjusted within the above range by varying the refractive indexes of the raw materials used and their compounding ratio.

[0063]

As a specific method for adjusting the optical transmittance or refractive index within the above range, for example, materials with low photoabsorption in the UV region may be used and if necessary the amount of photoabsorbent materials (e.g., photopolymerization initiating group-containing compounds) may be adjusted to be small.

[0064]

The photocurable resin sheet of the present invention may be prepared by casting a photocurable resin composition containing the above-described high molecular compound (A) and low molecular compound (B) and a solvent onto a substrate, and optionally drying the solvent.

Alternatively, a photocurable resin composition containing the above-described high molecular compound (A) and low molecular compound (B) may be processed into a film using a roll or extruded through a T die into a film. Then, the substrate, if used, may or may not be separated. Moreover, another substrate may be further placed on the photocurable resin sheet prepared on the substrate to sandwich the photocurable resin sheet between the substrates. In this case, the photocurable resin sheet may be wound around a winding core into a roll. Alternatively, such sheets cut to a predetermined size may be stacked into a stack of

sheets.

[0065]

Any solvent may be used. Examples include esters such as ethyl lactate, methyl acetate, and butyl acetate, ketones such as acetone, methyl ethyl ketone, and methyl isobutyl ketone, polar solvents such as dimethylformamide and dimethyl sulfoxide, halogenated solvents such as 1,1,1-trichloroethane and chloroform, ethers such as tetrahydrofuran and dioxane, aromatic compounds such as benzene, toluene, and xylene, and fluorinated inert liquids such as perfluorooctane and perfluoro-tri-N-butylamine. These may be used alone or in combinations of two or more. Among these, methyl ethyl ketone is preferred from the standpoint of compatibility with the solute.

15 [0066]

In the case where the photocurable resin composition contains a solvent, the amount of the solvent is not limited, but is preferably 20 to 50 parts by mass relative to 100 parts by mass in total of the above-described high molecular compound (A) and low molecular compound (B).

[0067]

The substrate may be, for example, a plastic substrate, suitably a plastic film. The material of the plastic substrate is not limited, and examples include polyolefins, polyesters, polyurethanes, polycarbonates, polyether ether ketones, polyimides, polyether imides, polyamides, wholly aromatic polyamides, polyvinyl chlorides, polyvinylidene chlorides, polyphenyl sulfides, aramids, fluororesins, cellulosic resins, and silicone resins. Examples of the polyolefins include low-density polyethylene, linear low-density polyethylene, medium-density polyethylene, high-density polyethylene, very-low-density polyethylene, random copolymer polypropylene, block copolymer polypropylene, homopolypropylene, polybutene, polymethyl pentene, ethylene-vinyl acetate copolymers,

ionomer resins, ethylene-(meth)acrylic acid copolymers, ethylene-(meth)acrylic acid ester copolymers, ethylene-butene copolymers, and ethylene-hexene copolymers.

Examples of the polyesters include polyethylene

5 terephthalate, polyethylene naphthalate, and polybutylene terephthalate. These materials may be used alone or in combinations of two or more. Moreover, the substrate may have a monolayer structure or a multilayer structure. Moreover, the substrate preferably has optical transparency.

10 [0068]

The photocurable resin sheet of the present invention can be cured by photoirradiation such as irradiation with ultraviolet light (at a wavelength around 365 nm, for example). Examples of light sources for photoirradiation
15 include LEDs, low-pressure mercury lamps, high-pressure mercury lamps, ultra-high-pressure mercury lamps, and xenon lamps. The irradiation dose is not limited, but is preferably 100 to 10,000 mJ/cm². Moreover, a heat curing step may be carried out, if needed. The heating conditions
20 may be, for example, at 120 to 180°C for 5 to 60 minutes.
[0069]

The photocurable resin sheet of the present invention preferably has a thickness (excluding the substrate thickness) of 10 to 1,000 μm, more preferably 50 to 500 μm.
25 When the thickness of the photocurable resin sheet is less than 10 μm, the handleability may be impaired, while when the thickness is more than 1,000 μm, the photocurability may be impaired.
[0070]

30 Moreover, the optical material of the present invention is obtained by curing the photocurable resin sheet of the present invention.

Non-limiting examples of the optical material include adhesives for displays or optical semiconductors, lenses,
35 protective films, and other optical electronic components.

EXAMPLES

[0071]

The present invention is more specifically described
 5 hereinbelow with reference to, but not limited to, examples.
 Hereafter, "part(s)" and "%" mean "part(s) by mass" and "%
 by mass", respectively, unless otherwise specified.

[0072]

The materials used in the examples and comparative
 10 examples are listed below.

[0073]

- High molecular compound (A)

Epoxy group-containing (meth)acrylic resin 1 (1HM2067
 available from Taisei Fine Chemical Co., Ltd., weight
 15 average molecular weight 60,000, epoxy equivalent 433 g/eq,
 glass transition temperature 15°C, (meth)acrylic resin
 containing an aliphatic epoxy group (glycidyl
 (meth)acrylate group))

Epoxy group-containing (meth)acrylic resin 2 (1HM2072
 20 available from Taisei Fine Chemical Co., Ltd., weight
 average molecular weight 60,000, epoxy equivalent 433 g/eq,
 glass transition temperature 0°C, (meth)acrylic resin
 containing an aliphatic epoxy group (glycidyl
 (meth)acrylate group))

25 [0074]

- Low molecular compound (B)

Epoxy group-containing compound (3,4-epoxycyclohexylmethyl-
 3,4-epoxycyclohexane carboxylate, Celloxide 2021P available
 from Daicel Corporation, molecular weight 252)

30 Oxetanyl group-containing compound (3-ethyl-3{[(3-
 ethyloxetan-3-yl)methoxy]methyl}oxetane, OXT221 available
 from Toagosei Co., Ltd., molecular weight 214)

Photopolymerization initiating group-containing compound
 (triarylsulfonium salt, CPI101A available from San-Apro
 35 Ltd., molecular weight 558, anion: SbF_6^-)

[0075]

- Others

Thermal curing initiator (KAOLIZER No. 20 available from
Kao Corporation, dimethylbenzylamine (DMBA))

5 [0076]

Examples 1 to 4 and Comparative Examples 1 to 3

The components at the ratio (solid content ratio)
shown in Table 1 were dissolved in methyl ethyl ketone to
provide a photocurable resin composition. The photocurable
10 resin composition was cast onto a PET film used as a
substrate and dried to obtain a photocurable resin sheet
having a thickness of about 100 μm . The photocurable resin
sheet was evaluated in terms of the amount of heat
generated during curing, handleability, storage modulus G' ,
15 optical transmittance, and refractive index as described
below. Table 1 shows the evaluation results.

[0077]

<Amount of heat generated during curing>

A 5-mg sheet cut out from each of the photocurable
20 resin sheets prepared in the examples and comparative
examples was placed in an aluminum pan for reaction
calorimetry (DSC) and continuously irradiated with Hg i-
line at an illuminance of 10 mW under a stream of nitrogen,
and the total amount of heat generated for up to 15 minutes
25 following the start of irradiation was determined using a
photoDSC device (EXSTAR6000 DSC available from Hitachi
High-Tech Corporation). The larger the amount of heat
generated during curing is, the better the photocurability
is. An amount of heat generated during curing of not
30 smaller than 10 mJ/mg is considered to indicate excellent
photocurability.

[0078]

<Handleability>

A contact test was performed on the surface of each
35 photocurable resin sheet prepared in the examples and

comparative examples, and the results were evaluated based on the following criteria.

Excellent: not sticky, no contact marks.

Good: sticky, but no adhesion of the photocurable resin composition.

Fair: sticky with slight adhesion of the photocurable resin composition.

Poor: very sticky with significant adhesion of the photocurable resin composition.

10 [0079]

<Storage modulus G' >

The storage modulus G' of the photocurable resin sheets prepared in the examples and comparative examples was measured using a dynamic viscoelastometer HAAKE MARS (Ta Instruments, Inc.) under the following conditions.

15 (Ta Instruments, Inc.) under the following conditions.

Sample size: diameter 8 mm Φ , thickness 250 μ m

Measurement mode: shear oscillation

Frequency: 1 Hz

Rate of temperature rise: 5°C/min

20 [0080]

<Optical transmittance>

The photocurable resin sheets prepared in the examples and comparative examples were photocured by irradiation with ultraviolet light at a dose of 500 mJ/cm², followed by post-curing (at 150°C for 30 minutes). The optical transmittance (at a wavelength of 400 nm) of the cured products at 25°C was measured using a spectrophotometer (JASCO Corporation).

25 followed by post-curing (at 150°C for 30 minutes). The optical transmittance (at a wavelength of 400 nm) of the cured products at 25°C was measured using a spectrophotometer (JASCO Corporation).

[0081]

30 <Refractive index>

The photocurable resin sheets prepared in the examples and comparative examples were photocured by irradiation with ultraviolet light at a dose of 500 mJ/cm², followed by post-curing (at 150°C for 30 minutes). The refractive index with respect to sodium D-line (light at a

35 refractive index with respect to sodium D-line (light at a

wavelength of 589 nm) of the cured products was measured in a 25°C environment using a refractive index meter (Atago Co., Ltd.).

[0082]

5 [Table 1]

Example number	Example 1	Example 2	Example 3	Example 4	Comparative Example 1	Comparative Example 2	Comparative Example 3
High molecular compound (A)	Epoxy group-containing (meth)acrylic resin 1	10	—	10	10	—	10
	Epoxy group-containing (meth)acrylic resin 2	—	10	—	—	—	—
	Epoxy group-containing compound	—	—	—	—	1	—
Low molecular compound (B)	Oxetanyl group-containing compound	1	1	0.1	1	1	—
	Photopolymerization initiating group-containing compound	0.2	0.2	0.2	—	0.2	—
	Thermal curing initiator	—	—	—	—	—	0.2
Others	Amount of heat generated during curing Q (mJ/mg)	35.4	49.0	11.3	0.4	184.0	0.2
	Handleability	Excellent	Good	Excellent	Excellent	Poor	Excellent
	Storage modulus G' (25 °C) (Pa)	410000	110000	440000	410000	Not measurable	410000
	Optical transmittance (%) (400nm)	90	90	90	Not measurable	Not measurable	90
	Refractive index (589 nm)	1.49	1.49	1.49	Not measurable	Not measurable	1.49

INDUSTRIAL APPLICABILITY

[0083]

5 The present invention relates to a photocurable resin
sheet which can be used in optical electronic component
applications including adhesives for displays or optical
semiconductors, lenses, and protective films.

CLAIMS

Claim 1. A photocurable resin sheet, comprising a high molecular compound (A) and a low molecular compound (B),

wherein an epoxy group, an oxetanyl group, and a photopolymerization initiating group are each individually present in the high molecular compound (A) or the low molecular compound (B).

Claim 2. The photocurable resin sheet according to claim 1,

wherein the high molecular compound (A) has a weight average molecular weight of 1,000 to 1,000,000.

Claim 3. The photocurable resin sheet according to claim 1 or 2,

wherein the low molecular compound (B) has a molecular weight of less than 1,000.

Claim 4. The photocurable resin sheet according to any one of claims 1 to 3,

wherein the photocurable resin sheet has a storage modulus G' at 25°C of 50,000 Pa or higher.

Claim 5. The photocurable resin sheet according to any one of claims 1 to 4,

wherein a cured product of the photocurable resin sheet at 25°C has an optical transmittance at a wavelength of 400 nm of 70% or higher and a refractive index with respect to light at a wavelength of 589 nm of 1.40 or higher.

Claim 6. The photocurable resin sheet according to any one of claims 1 to 5,

wherein the high molecular compound (A) comprises at least one selected from the group consisting of poly(meth)acrylic resins, phenoxy resins, polyurethane resins, silicone resins, polyester resins, polyamide resins,
5 and polyimide resins.

Claim 7. The photocurable resin sheet according to any one of claims 1 to 6,

wherein the low molecular compound (B) comprises a
10 compound containing an oxetanyl group.

Claim 8. The photocurable resin sheet according to any one of claims 1 to 7,

wherein the low molecular compound (B) comprises a
15 photoacid generator.

Claim 9. An optical material obtained by curing the photocurable resin sheet according to any one of claims 1 to 8.

20