

DESCRIPTION

PARTICULATE WATER-ABSORBING AGENT CONTAINING WATER-ABSORBING
RESIN AS MAIN COMPONENT AND METHOD FOR PRODUCING THE SAME

5 TECHNICAL FIELD

[0001]

The present invention relates to a particulate
water-absorbing agent containing a water-absorbing resin as a main
component and a method for producing same, which is preferably
10 used for absorbent articles such as disposable diapers, sanitary
napkins and incontinence pads.

BACKGROUND ART

[0002]

15 In recent years, for absorbent articles such as disposable
diapers, sanitary napkins and incontinence pads, a
water-absorbing resin is widely used as its constituent material
for the purpose of absorbing a body fluid such as urine and
menstrual blood. As to the foregoing water-absorbing resin, for
20 instance, partially neutralized crosslinked polyacrylic acid; a
hydrolyzed starch-acrylic acid graft polymer; a saponified vinyl
acetate-acrylic acid ester copolymer; a hydrolyzed copolymer of:
acrylonitrile or acrylamide, or its crosslinked product; and a
crosslinked polymer of cationic monomers are known.

[0003]

When a water-absorbing resin is used as an absorbent material for disposable diapers, after absorbing urine, the water-absorbing resin can get degraded over time and lose its liquid permeability and gel strength, causing a problem of urine leakage from the disposable diapers. Specifically, such a problem has been pointed out to be an issue over gel stability.

[0004]

As a means of improving gel stability of said water-absorbing resin, various additives for a water-absorbing resin are suggested, and the following: a method for adding a reducing agent (Patent Literatures 1 to 3); a method for adding a reducing agent and an anti-oxidizing agent (Patent Literature 4); a method for adding an oxidizing agent (Patent Literature 5); a method for adding an anti-oxidizing agent (Patent Literature 6); a method for adding a chain-transfer agent to monomers in polymerization (Patent Literature 7); a method for adding a chelating agent (Patent Literatures 8 to 13) and the like, are suggested. Because this type of deterioration of a water-absorbing resin, due to urine in particular, is believed to be caused by the presence of a trace amount of metal ions, a technique to improve gel stability of the water-absorbing resin by adding so-called chelating agent to a water-absorbing resin so as to trap metal ions and suppress generation of radical species has been suggested.

[0005]

As a means of improving gel stability of said water-absorbing resin, for instance, a technique of adding a chelating agent to monomers (Patent Literature 8); a method for adding a chelating agent to a hydrogel of a water-absorbing resin and drying same
5 (Patent Literature 9); a method for adding a chelating agent when mixing a water-absorbing resin with an aqueous solution of a surface crosslinking agent (Patent Literature 10); a method for adding an aqueous solution of a chelating agent after surface crosslinking a water-absorbing resin and granulating same (Patent
10 Literatures 11 and 12); and a method for adding a chelating agent to fine powder generated during a production step of a water-absorbing resin for reuse (Patent Literature 13) and the like are disclosed.

[0006]

15 Further, a chelating agent is also used for: the prevention of coloration of a water-absorbing resin (Patent Literatures 14 to 16 and 19 to 21) as well as the removal of odors from disposable diapers, in addition to the prevention of deterioration of a water-absorbing resin due to urine.

20 [0007]

Furthermore, also disclosed are: a method for granting light resistance, coloration resistance and deodorizing properties by reducing impurities in aminoacetic acid based chelating agents (Patent Literature 17); and a method for granting both gel
25 stability and coloration resistance by simultaneously using an aminocarboxylic acid based chelating agent, an oxygen-containing

reducing inorganic salt and an organic anti-oxidizing agent
(Patent Literature 18).

[0008]

Further, a water-absorbing resin is known to have different
5 kinds of residual monomers and a different degree of liquid
permeability depending upon its particle sizes (Patent
Literatures 22 and 23).

CITATION LIST

10 PATENT LITERATURES

[0009]

Patent Literature 1: US Patent No. 4,959,060

Patent Literature 2: US Patent No. 4,863,989

Patent Literature 3: EP Patent No. 1477349

15 Patent Literature 4: US Patent No. 4,972,019

Patent Literature 5: JP Publication No.S63-153060

Patent Literature 6: JP Unexamined Patent Publication No.
S63-127754

Patent Literature 7: US Patent No. 6,335,406

20 Patent Literature 8: JP Unexamined Patent Publication No.
2000-038407

- Patent Literature 9: JP Unexamined Patent Publication No.
H11-246674
- Patent Literature 10: JP Unexamined Patent Publication No.
H11-315148
- 5 Patent Literature 11: JP Unexamined Patent Publication No.
H11-315147
- Patent Literature 12: US Patent No. 7,473,470
- Patent Literature 13: JP Unexamined Patent Publication No.
2000-007790
- 10 Patent Literature 14: JP Patent No. 3107873
- Patent Literature 15: JP Unexamined Patent Publication No.
2003-206381
- Patent Literature 16: US Patent No. 7,737,231
- Patent Literature 17: JP Unexamined Patent Publication No.
15 2001-234087
- Patent Literature 18: EP Patent No. 1645596
- Patent Literature 19: EP Patent No. 2112172
- Patent Literature 20: EP Patent No. 2163302
- Patent Literature 21: WO Publication No. 2011/040530
- 20 Patent Literature 22: US Patent No. 8,182,916
- Patent Literature 23: US Patent No. 5,599,335

SUMMARY OF THE INVENTION

TECHNICAL PROBLEMS

[0010]

5 Even when gel stability or the like is improved by way of
the foregoing means, evaluation of gel stability of
water-absorbing agents removed from absorbent articles, which
have water-absorbing resins as a main component, such as
disposable diapers and the like, show that gel stability of a
10 water-absorbing agent can vary amongst absorbing articles, and
a problem that gel stability has not achieved its optimal level
remains. A decline in gel stability is significant especially
in the case of absorbent articles, where particles of fine particle
sizes are largely concentrated.

15 [0011]

 Further, in the above Patent Literatures 8 to 21, a method
for adding a chelating agent: to monomers at the time of
polymerization; to a hydrogel-forming crosslinked polymer prior
to drying; at the time of surface crosslinking; at the time of
20 granulation; and at the time of collection of granules is
disclosed. In such methods, a chelating agent is evenly added
as per each particle size. However, there is a problem that a
degree of variation in gel stability of the obtained
water-absorbing agents is magnified.

25 [0012]

The present invention is devised in view of the foregoing problems in the art, and one objective of the present invention is to provide a water-absorbing agent having high gel stability, little variation in gel stability amongst different particle
5 sizes, and good water-absorbing properties (for example, Absorbency Against Pressure, Centrifuge Retention Capacity, saline flow conductivity, anti-blocking property after moisture absorption, low coloration, or the like), and a method for producing such a water-absorbing agent.

10

SOLUTION TO PROBLEMS

[0013]

To solve the foregoing problems, the inventors of the present invention conducted extensive studies and found that variation
15 in gel stability amongst absorbent articles such as disposable diapers or the like was due to the fact that the likelihood of deterioration of a water-absorbing resin varies, depending upon a particle size.

[0014]

20 To be more specific, for a particulate water-absorbing agent, particles with small particle size can be more easily deteriorated than particles with large particle size, as they have a larger surface area to be in contact with urine, requiring more chelating agent to be included.

25 [0015]

Also, when a particulate water-absorbing agent is incorporated into an absorbent article, or in particular, when a predetermined amount of a water-absorbing resin (5 to 20 g per diaper) is incorporated into a disposable diaper, variation in particle size within each diaper, as well as variation in particle size depending on a location in a single diaper (a central portion, a peripheral portion, top and bottom portions in a thickness direction of a disposable diaper) can cause variation in gel stability.

10 [0016]

Accordingly, in supplying a powdered-form particulate water-absorbing agent to an absorbent article from an apparatus to produce absorbent articles such as disposable diapers and the like, if the particulate water-absorbing agent with its fine particle size is too concentrated, there is a problem of the decline of gel stability even if a chelating agent is added in its predetermined amount. In other words, it was discovered that gel stability would vary even when a chelating agent is added evenly as per each different particle size.

20 [0017]

In view of the above, to control varying gel stability amongst particles in a particulate water-absorbing agent, the inventors of the present application adjusted an amount of the chelating agents to be added in a way that satisfies Formula (1), instead of evenly adding as per each particle size, so as to obtain a particulate water-absorbing agent having high gel stability and

few variations of the gel stability amongst particles in the particulate water-absorbing agent.

[0018]

To be more specific, to solve the foregoing problems the first
5 embodiment of the present invention provides a particulate
water-absorbing agent comprising a water-absorbing resin as a main
component and a chelating agent, the water-absorbing resin
containing particles with a particle diameter of less than 300
μm and particles with a particle diameter of 300 μm or more but
10 less than 850 μm, as specified by a Japanese Industrial Standard
(JIS) standardized sieve, wherein an amount of the chelating agent
included is 0.001 to 5 parts by weight per 100 parts by weight
of a water-absorbing resin in solid and satisfies Formula (1):

[0019] [Mathematical 1]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

15 [0020]

where, in Formula (1), C1 indicates that an amount (ppm) of
the chelating agent present in the particles of a particle diameter
of less than 300 μm, as specified by a JIS standardized sieve,
amongst particle components for the particulate water-absorbing
20 agent, and C2 indicates that an amount (ppm) of the chelating agent
present in the particles of a particle diameter of 300 μm or more
but less than 850 μm, as specified by a JIS standardized sieve,
amongst particle components for the particulate water-absorbing
agent.

[0021]

The second embodiment of the present invention provides a method for producing a particulate water-absorbing agent comprising a water-absorbing resin as a main component and a
5 chelating agent, the water-absorbing resin containing particles with a particle diameter of less than 300 μm and particles with a particle diameter of 300 μm or more but less than 850 μm , as specified by a Japanese Industrial Standard (JIS) standardized sieve, wherein an amount of the chelating agent included is 0.001
10 to 5 parts by weight per 100 parts by weight of a water-absorbing resin in sold and satisfies Formula (1):

[0022]

[Mathematical 2]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

[0023]

15 where, in Formula (1), C1 indicates that an amount (ppm) of the chelating agent present in the particles of a particle diameter of less than 300 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent, and C2 indicates that an amount (ppm) of the chelating agent
20 present in the particles of a particle diameter of 300 μm or more but less than 850 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent.

ADVANTAGEOUS EFFECT OF THE INVENTION

[0024]

According to the embodiment of the present invention, a particulate water-absorbing agent having high gel stability,
5 little variation in gel stability amongst different particle sizes, and good water-absorbing properties (for example, Absorbency Against Pressure, Centrifuge Retention Capacity, saline flow conductivity, anti-blocking property after moisture absorption, low coloration, or the like) can be obtained.

10

DESCRIPTION OF EMBODIMENTS

[0025]

Description regarding the embodiments of the present invention is provided below. However, the scope of the present
15 invention is not intended to be restrained by these descriptions, and embodiments other than the following examples can also be appropriately modified and carried out to the extent that the spirit of the present invention is not impaired. Specifically, the present invention is not intended to be limited to each
20 embodiment described below, and can be modified into various embodiments within the scope illustrated by the claims. Exemplary embodiments that can be obtained by appropriately combining the technical means that are respectively disclosed in different exemplary embodiments are also included in the technical scope
25 of the present invention.[0026]

[1] Definitions of Terms

(1-1) "Water-absorbing resin" and "water-absorbing agent"

In the embodiment of the present invention, the term "water-absorbing resin" means a polymer gelling agent for aqueous matter and is water-swellaable and water-insoluble, and has the physical properties described below. Specifically, it is intended to be the polymer gelling agent having the following properties: for "water swellability", CRC (Centrifuge Retention Capacity; fluid retention capacity without pressure) of 5 (g/g) or higher as defined in ERT 441.2-02 (2002), and for "water insolubility", Ext (Extractable; soluble amount) of 50% by weight or less as defined in ERT 470.2-02 (2002). The water-absorbing resin may be appropriately designed according to its use and can be, but not limited to, a hydrophilic crosslinked polymer, where carboxyl group-containing unsaturated monomers are polymerized and crosslinked.

[0027]

Further, in the embodiment of the present invention, the "water-absorbing agent" means an absorbent gelling agent having the foregoing water-absorbing resin as a main component. The term "main component" indicates a condition where an amount contained is: at least 50% by weight or more, preferably at least 70% by weight or more, more preferably at least 80% by weight or more, and even more preferably at least 90% by weight or more. Thus, said water-absorbing agent is not limited to a formation where the polymers make up the entire amount (100% by weight), and as

long as the foregoing physical properties (CRC, Ext) are satisfied, it is preferably a composition that contains additives. Furthermore, the "aqueous matter" may be a gas, liquid or solid, and as long as water is contained, it may be either water, aqueous
5 solution or aqueous dispersion. Specific examples include: urine, blood, menstrual blood, sea water and various kinds of waste water.

[0028]

For a form of the foregoing water-absorbing resin and the
10 water-absorbing agent, it can be, without limiting, in the form of sheet, fiber, film, gel and various others, but in the embodiment of this invention, preferably in the form of particle for ease of handling.

[0029]

15 Meanwhile, in the embodiment of the present invention, intermediates generated in the process of producing a water-absorbing resin (for example, hydrogel-forming crosslinked polymers after polymerization process, dry polymers after drying process, water-absorbing resin granules prior to surface
20 crosslinking process and the like) are collectively referred to as a "water-absorbing resin". On the other hand, if some additives or the like are contained, such a composition is referred to as a "water-absorbing agent". For a form of a final product obtained according to the embodiment of the present invention, particulate
25 form is preferred, hence a particulate water-absorbing agent.

[0030]

(1-2) "Polyacrylic acid (salt))"

In the embodiment of the present invention, the term "polyacrylic acid (salt)" indicates polyacrylic acid and/or
5 polyacrylic acid salt, which optionally includes a graft component, and it means a polymer having acrylic acid and/or acrylic acid salt (hereinafter referred to as "acrylic acid (salt)") as a repeat unit. Said "main component" means a condition in which a portion (amount) of acrylic acid (salt) used is, in
10 general, 50 to 100 Mol% of the entire monomers (not including internal crosslinkers) used in polymerization (excluding the internal cross-linking agent), preferably 70 to 100 Mol%, more preferably 80 to 100 Mol%, even more preferably 90 to 100 Mol%, or substantially 100 Mol%. In addition, polyacrylic acid salt
15 as a polymer essentially includes a water soluble salt, and preferably includes a monovalent salt, and more preferably includes an alkali metal salt or an ammonium salt.

[0031]

(1-3) "EDANA" and "ERT"

20 The term "EDANA" is an abbreviation for the European Disposables and Nonwovens Associations, and the term "ERT" is an abbreviation for EDANA Recommended Test Methods, European standard (meaning essentially world standard) test methods for superabsorbent resins.

25 [0032]

In the embodiment of the present invention, unless specifically stated otherwise, the physical properties of water-absorbing resins were measured in accordance with the original ERT (Revised in 2002, public art). Also, the physical
5 properties of a particulate water-absorbing agent according to the embodiment of the present invention were measured likewise.

[0033]

(1-3-1) "CRC" (ERT441.2-02)

The term "CRC" is an abbreviation for Centrifuge Retention
10 Capacity, meaning fluid retention capacity without pressure (it can also be called "absorption rate"). To be more specific, CRC is a fluid retention capacity (unit; g/g) obtained after 0.2 g of a water-absorbing resin or a particulate water-absorbing agent was placed in a non-woven fabric bag and allowed to soak in a large
15 excess of a 0.9% by weight of an aqueous sodium chloride solution for 30 minutes for free swelling, followed by drying in a centrifuge (250 G). In the embodiment of the present invention, the evaluation was made on values including corrections for moisture content.

20 [0034]

(1-3-2) "AAP" (ERT442.2-02)

The term "AAP" is an abbreviation for Absorption Against Pressure, meaning fluid retaining capacity under pressure. Specifically, AAP is a fluid retention capacity (unit: g/g)
25 obtained after 0.9 g of a water-absorbing resin or a particulate

water-absorbing agent was allowed to swell in a large excess of 0.9% by weight of an aqueous sodium chloride solution for one hour under a pressure of 2.06 kPa (0.3 psi).

[0035]

5 According to ERT442.2-02, it is listed as "Absorption Under Pressure", the foregoing AAP means essentially the same. Furthermore, in the embodiment of the present invention, a measurement can be made after modifying the condition for pressure to be 4.83 kPa (0.7 psi), and a measurement result obtained under
10 such condition is indicated as AAP 4.83 kPa (AAP measured under 2.06 kPa is indicated as AAP 2.06 kPa). In addition, the evaluation was made on values including corrections for moisture content.

[0036]

15 (1-3-3) "Ext" (ERT470.2-02)

 The term "Ext" is an abbreviation for Extractables, meaning an amount for soluble content. Specifically, Ext is a value (unit:% by weight) obtained after 1.0 g of a water-absorbing resin or a particulate water-absorbing agent is added to 200 ml of 0.9%
20 by weight of an aqueous sodium chloride solution and stirred for 16 hours at 500 rpm, and then a value (unit; % by weight) for the amount of polymers dissolved was measured through pH titration.

[0037]

 In the embodiment of the present invention, the measurement
25 was taken by modifying the stirring time to 1 hour. Further, the

evaluation was made on values including corrections for moisture content.

[0038]

(1-3-4) "Moisture Content" (ERT430.2-02)

5 The "moisture content" means an amount of moisture in a water-absorbing resin or a particulate water-absorbing agent. Specifically, for 4.0g of a water-absorbing resin or a particulate water-absorbing agent, it is a value computed based upon an amount lost from drying for 3 hours at 105°C (unit; % by weight). In the
10 embodiment of the present invention, the measurement was made by modifying a sample amount to 1.0 g and a drying temperature to 180°C.

[0039]

(1-3-5) "PSD" (ERT420.2-02)

15 "PSD" is an abbreviation for Particle Size Distribution, meaning a particle size distribution measured by sieve classification. Meanwhile, a weight average particle diameter (D50) and logarithmic standard deviation for particle size distribution (σ_ζ) are measured in the same manner as indicated
20 in "(3) Mass-Average Particle Diameter (D50) and Logarithmic Standard Deviation (σ_ζ) of Particle Diameter Distribution", which is described in the U.S. Patent No. 7,638,570. In the embodiment of the present invention, an amount and other measurements of a chelating agent according to particle sizes were obtained using
25 the method described above.

[0040]

(1-4) Others

In this specification, the expression for a range, "X to Y", means "X or more and Y or less". Also, unless otherwise noted, a unit for weight, "t (ton)" means "Metric ton", and "ppm" means "ppm by weight" or "ppm by mass". Further, "weight" and "mass", "parts by weight" and "parts by mass", and "% by weight" and "% by mass", respectively, are used as synonyms. In addition, "-acid (salt)" means "-acid and/or salt", and "(meth)acrylic" means "acrylic and/or methacrylic", respectively.

[0041]

[2] Method for producing polyacrylic acid (salt)-based water-absorbing resin

Hereinafter, described is a method for producing a polyacrylic acid (salt)-based water-absorbing resin, which is used for a particulate water-absorbing agent according to the embodiment of the present invention.

[0042]

(2-1) Step for preparing aqueous monomer solution

The present step is one for producing an aqueous solution containing acrylic acid (salt) as a main component (hereinafter referred to as an "aqueous monomer solution"). Here, the "main component" means the same as the contents described in (1-2) "Polyacrylic acid (salt)". Further, instead of the aqueous

monomer solution, a slurry of monomers can be used within the extent in which the fluid retention capacity is not lowered, although the below is described using an aqueous monomer solution for simplicity.

5 [0043]

(Acrylic acid)

From the viewpoint of the effectiveness of the embodiment of the present invention, acrylic acid is used as a monomer, yet acrylic acid such as this usually contains a trace amount of
10 polymerization inhibitors, impurities and the like.

[0044]

As for a polymerization inhibitor, preferably phenols, more preferably methoxyphenols, and even more preferably p-methoxyphenols can be given, and their concentrations are, from
15 the viewpoint of polymerization inhibition effect and color of a water-absorbing resin or a particulate water-absorbing agent to be obtained, preferably 1 to 200 ppm, and more preferably 10 to 160 ppm. Further, as for the foregoing impurities, a reference is made to the U.S. Patent Application Publication No.
20 2008/0161512 and the like.

[0045]

(Basic compositions)

A main component of a water-absorbing resin or a particulate water-absorbing agent obtained through the embodiment of the

present invention is polyacrylic acid (salt), in which acrylic acid (salt) is polymerized and crosslinked. To obtain said polyacrylic acid (salt), it is preferable to neutralize acrylic acid with a basic composition. Here, the "basic composition" means a composition containing a basic compound.

[0046]

As examples of the basic compounds, carbonate (hydrogen) salt of an alkali metal, alkali metal hydroxides, ammonia, organic amine and the like are included. In particular, from the viewpoint of obtaining a water-absorbing resin or a particulate water-absorbing agent with even better physical properties, alkali metal hydroxides such as sodium hydroxide, potassium hydroxide and lithium hydroxide are preferred, and even more preferable is sodium hydroxide.

[0047]

(Neutralization process)

A neutralization process in this step (or it may also be referred to as a neutralization step) encompasses neutralization of acrylic acid as a monomer, or neutralization of a hydrogel forming crosslinked polymer (hereinafter referred to as "hydrogel"), which is obtained through polymerizing and crosslinking acrylic acid (post-neutralization). In either case, it can be done on a batch basis or a continuous basis, but preferably a continuous basis.

[0048]

For preferable conditions for neutralization, including basic composition, temperature retention time, device and the like, the neutralization conditions as described in International Publication No. 2009/123197 and U.S. Patent Application

5 Publication No. 2008/0194863 are applied.

[0049]

A rate of neutralization according to the embodiment of the present invention is preferably 10 to 90 mol%, more preferably 40 to 85 mol%, even more preferably 50 to 80 mol%, and yet even
10 more preferably 60 to 75 mol%, with respect to an acid group in a monomer aqueous solution or in post-polymerization hydrogel.

[0050]

If the rate of neutralization is less than 10 mol%, the fluid retention capacity without load (CRC) significantly decreases.
15 On the other hand, if the rate of neutralization exceeds 90 mol%, it is possible that a water-absorbing resin with good fluid retention capacity under load (AAP) may not be obtained.

[0051]

This can be said for neutralization following polymerization
20 (subsequent neutralization), or for a rate of neutralization for a particulate water-absorbing agent as a final product.

[0052]

Further, although acrylic acid salt is essentially a monovalent salt, it can be neutralized as a polyvalent metal salt

if in an extremely small amount (for example, approximately 5 mol%).

[0053]

(Internal crosslinking agent)

5 Examples of an internal crosslinking agent that can be used in the embodiment of the present invention include a compound having two or more substituent groups that could react with acrylic acid. To be more specific, one or more species out of the internal crosslinking agent(s) described in the 14th column of the U.S.
10 Patent No. 6,241,928 are used.

[0054]

Meanwhile, from the viewpoint of fluid retention capacity of a water-absorbing resin or a particulate water-absorbing agent to be obtained, the following are used: preferably a compound
15 having two or more polymerizable unsaturated groups, more preferably compound having thermal decomposability at around a drying temperature described below, even more preferably a compound having two or more polymerizable unsaturated groups in (poly)alkylene glycol structural unit (namely, an allyl group and
20 a (meth)acrylate group, but especially preferably acrylate group).

[0055]

More specifically, it is preferable to use (poly)alkylene glycol di(meth)acrylate or tri(meth)acrylate at polymerization.
25 As for an alkylene glycol unit, a polyethylene glycol unit where

a number of n in an internal crosslinking agent is preferably 1 to 100, and more preferably 6 to 50 are used.

[0056]

In the embodiment of the present invention, the amount used
5 for the foregoing internal crosslinking agent is preferably 0.005 to 2 mol%, more preferably 0.01 to 1 mol%, and even more preferably 0.05 to 0.5 mol% per a monomer. By setting the amount used for the internal crosslinking agent to be these ranges mentioned above, desirable water-absorbing properties can be achieved.

10 [0057]

Aside from the aforementioned method of crosslinking in which the internal crosslinking agent is added prior to polymerization, a method of adding the internal crosslinking agent (preferably a polyglycidyl compound) during or after
15 polymerization and conducting subsequent crosslinking, a method of radical crosslinking using a radical polymerization and a method of crosslinking using radiation such as electron beam and the like can be employed.

[0058]

20 In particular, a method for preparing an aqueous monomer solution in which a predetermined amount of an internal crosslinking agent is added, and crosslinking concurrently with polymerization of said aqueous monomer solution is preferable. Meanwhile, if needed, an internal crosslinking agent (preferably

a polyglycidyl compound) may be added during or after polymerization.

[0059]

(Other monomers used in combination)

5 According to the embodiment of the present invention, it is possible to use another monomer besides acrylic acid (salt) (hereinafter referred to as "another monomer"). An example of such a monomer includes a water soluble unsaturated monomer or a hydrophobic unsaturated monomer.

10 [0060]

To be more specific, one or more species of monomers described in Paragraph [0035] of the U.S. Patent Application Publication No. 2005/215734 (yet excluding acrylic acid) are used depending upon a purpose.

15 [0061]

Meanwhile, a particulate water-absorbing agent according to the embodiment of the present invention encompasses one having said water soluble unsaturated monomer or hydrophobic unsaturated monomer as a copolymerization component.

20 [0062]

(Other substances added to an aqueous monomer solution)

In the embodiment of the present invention, the following substance can be added at the time of preparing an aqueous monomer solution besides the aforementioned substances.

[0063]

5 To be more specific, for the purpose of improving various physical properties associated with a water-absorbing resin or a particulate water-absorbing agent, preferably 50% by weight or less, or more preferably 20% by weight or less of a water soluble resin or a water-absorbing resin can be added, or various kinds
10 of foaming agents (such as a carbonate, an azo compound and an air bubble), a surfactant, a chain transfer agent and the like can be added at preferably 5% by weight or less, and at more preferably 1% by weight or less. Those substances can take a formation of being added to an aqueous monomer solution or being
15 added during polymerization.

[0064]

While a use of the water soluble resin or the water-absorbing resin generates a graft polymer or a water-absorbing resin composition (for example, a starch-acrylic acid polymer, a
20 PVA-acrylic acid polymer and the like), these polymers, including the water-absorbing resin composition, are called "polyacrylic acid (salt)-based water-absorbing resin" in the embodiment of the present invention. Further, the particulate water-absorbing agent according to the embodiment of the present invention can
25 also be made using these polymers and a water-absorbing resin composition.

[0065]

(Concentration of a monomer component)

In the present step, an aqueous monomer solution is prepared by mixing each substance described above. In so doing, a
5 concentration of a monomer component in an aqueous monomer solution is, but not limited to, preferably 10 to 80% by weight, more preferably 20 to 75% by weight, and even more preferably 30 to 70% by weight, from the viewpoint of physical properties for a water-absorbing resin or a particulate water-absorbing agent.

10 [0066]

Further, when aqueous solution polymerization or reverse phase suspension polymerization is employed, a solvent other than water can be additionally used, if needed. A type of the solvent used is not to be limited.

15 [0067]

Meanwhile, said "concentration of a monomer component" is a value that can be obtained by Formula (3), and the aqueous monomer solution does not include a graft component, a water-absorbing resin and a hydrophobic solvent for a reverse phase suspension
20 polymerization.

[0068]

[Mathematical 3]

Concentration of Monomer Component (% by weight) = (Weight of Monomer Component) / (Weight of Aqueous Monomer Solution) × 100 ...

(3)

[0069]

(2-2) Polymerization step

This is a step for obtaining a hydrogel-forming crosslinked polymer (hereinafter referred to as "hydrogel") through

5 polymerization of the acrylic acid (salt)-based aqueous monomer solution obtained from the aforementioned step for preparing the aqueous monomer solution.

[0070]

(Polymerization initiator)

10 The polymerization initiator employed in the embodiment of the present invention is selected in accordance with a form of polymerization and the like, including, for instance, a thermal decomposition polymerization initiator and a photolysis polymerization initiator, or a redox polymerization initiator,
15 which concurrently uses a reducing agent that facilitates decomposition of these polymerization initiators.

[0071]

To be more specific, out of all the initiators indicated in the 5th column of the U.S. Patent No. 7,265,190, one or more species
20 are used. For ease of handling and the standpoint of physical properties of a water-absorbing resin or a particulate water-absorbing agent to be obtained, preferably peroxides or azo

compounds, more preferably peroxides, and even more preferably persulfates are used.

[0072]

In the embodiment of the present invention, an amount of the
5 foregoing polymerization initiators used is preferably 0.001 to
1 mol%, more preferably 0.001 to 0.5 mol% per a monomer. An amount
of the reducing agent used is preferably 0.0001 to 0.02 mol% per
a monomer.[0073]

Instead of the foregoing polymerization initiators,
10 polymerization reaction can be carried out by irradiating active
energy beams such as radial rays, electron rays or ultraviolet
rays, and it is also possible to use said active energy beams in
combination with the polymerization initiators.[0074]

(Polymerization method)

15 Methods of polymerization for the embodiment of the present
invention are, from the viewpoint of water absorbency and
manageability of polymerization control and the like, preferably
a gas-phase spray droplets polymerization, an aqueous solution
polymerization or a reverse phase suspension polymerization in
20 a hydrophobic solvent, more preferably an aqueous solution
polymerization or reverse phase suspension polymerization, even
more preferably an aqueous solution polymerization, and yet even
more preferably a continuous aqueous solution polymerization. A
polymerization may be performed in a single stage or a multi-stage
25 fashion with two or more stages, and especially for a reverse phase

suspension polymerization, a multi-stage polymerization is favorable from the standpoint of particle diameter control, granulation (particle size enlargement caused by aggregation of spherical particles), or a removal of the heat of polymerization.

5 [0075]

Preferred embodiments for the foregoing continuous aqueous solution polymerization include a continuous polymerization involving a kneader (disclosed in the U.S. Patent No. 6987151 or No. 6710141) and a continuous polymerization involving a belt
10 (disclosed in the U.S. Patent No. 4893999 and No. 6241928, or the U.S. Patent Application Publication No. 2005/215734). The continuous aqueous solution polymerization enables a production of a water-absorbing resin or a particulate water-absorbing agent with high efficiency.[0076]

15 Further, a preferred example of the foregoing continuous aqueous solution polymerization includes a polymerization with a high initial temperature and a polymerization in high concentrations. The "polymerization with a high initial temperature" is a method of polymerization, in which a temperature
20 of the aqueous monomer solution is preferably 30°C or higher, more preferably 35°C or higher, even more preferably 40°C or higher, and yet even more preferably 50°C or higher (the upper limit is a boiling point), and the "polymerization in high concentrations" is a method of polymerization where a polymerization occurs with
25 a monomer concentration of preferably 30% by weight or more, more preferably 35% by weight or more, even more preferably 40% by weight

or more, and yet even more preferably 45% by weight or more (the upper limit is a saturation concentration). Those polymerization methods can be used in combination.

[0077]

5 Further, the aforementioned polymerization method can allow a solids content concentration to increase during polymerization. In such a case, an "increase in solids content" identified by Formula (4) and Formula (5) is used as an index for evaluation. For the embodiment of the present invention, the increase in solids
10 content is preferably 1% by weight or more, and more preferably 2% by weight or more.

[0078]

[Mathematical. 4]

Increase in solids content (% by weight) = (Solids content concentration in hydrogel after polymerization) - (Solids content concentration in aqueous monomer solution) ... (4)

[0079]

15 Meanwhile, in Formula (4), the "Solids content concentration in aqueous monomer solution" indicates a value obtained by Formula (5), meaning content percentage (% by weight) for the components which become a solid after polymerization.

[0080]

20 [Mathematical 5]

Solids content concentration in aqueous monomer solution (% by weight) = Weight of (monomer component + graft component +

water-absorbing resin + other solids content)/(Weight of components in polymer system) × 100 ... (5)

[0081]

In Formula (5), the "weight of components in polymer system" indicates a total weight of an aqueous monomer solution, a graft component, a water-absorbing resin, and other solids content (for
5 example, water-insoluble fine particles and the like), and a hydrophobic solvent for a reverse phase suspension polymerization is not included therein.

[0082]

In the embodiment of the present invention, polymerization
10 can be carried out in air atmosphere, although, from the viewpoint of color of a water-absorbing resin or a particulate water-absorbing agent to be obtained, it is carried out preferably under inert gas atmosphere such as nitrogen or argon. In this case, an oxygen concentration is controlled to be preferably 1%
15 by volume or less. Further, as to oxygen dissolved in monomers or an aqueous monomer solution, it is preferable to substitute fully using an inert gas (for instance, the dissolved oxygen to be less than 1 (mg/l)).

[0083]

20 Furthermore, in said aqueous monomer solution, bubbles (especially said inert gases) and various foaming agents (especially carbonates) can be dispersed and polymerized, conducting thereby foaming polymerization.

[0084]

(2-3) Gel-crushing step

This is a step for gel-crushing a hydrogel obtained from the foregoing polymerization step by a gel crusher such as a kneader, a meat chopper or a cutter mill and the like to obtain a hydrogel in a particle shape (hereinafter referred to as a "particulate hydrogel"). If said polymerization step is kneader polymerization, a polymerization step and a gel-crushing step are conducted simultaneously.

10 [0085]

As for a gel-crushing step for the embodiment of the present invention, a gel crushing method disclosed in the International Publication No. 2011/126079 is preferably applied.

[0086]

15 (2-4) Drying step

This is a step for drying a hydrogel and/or a particulate hydrogel, which is obtained through said polymerization step and/or the gel-crushing step, to a desirable level of resin solids content so as to obtain a dry polymer.

20 [0087]

The resin solids content is a value calculated based on the amount lost from drying (a change in weight when a 1g sample is heated at 180°C for 3 hours) and is preferably 80% by weight or more, more preferably 85 to 99% by weight, even more preferably

90 to 98% by weight, and yet even more preferably 92 to 97% by weight.

[0088]

As to a drying method for the embodiment of the present
5 invention, as long as the hydrogel and/or the particulate hydrogel
is dried until the aforementioned resin solids content is
obtained, one or more can be appropriately selected from the drying
methods including: heat drying, hot air drying, reduced-pressure
drying, fluid bed drying, infrared drying, microwave drying, drum
10 dryer drying, azeotropic dehydration drying using a hydrophobic
organic solvent or drying in high humidity with high-temperature
water vapor and the like.

[0089]

Amongst the various drying methods described above, the hot
15 air drying is preferable from the viewpoint of drying efficiency.
Band drying, where hot air drying is performed on a belt, can be
more preferable. A temperature of the hot air is, from the
viewpoint of color or water-absorbing properties of a
water-absorbing resin or a particulate water-absorbing agent to
20 be obtained, preferably 100 to 300°C, and more preferably 120 to
220°C.

[0090]

When performing band drying for the embodiment of the present
invention, band drying conditions described in the International

Publication Nos. 2006/100300, 2011/025012, 2011/025013,
2011/111657 and or the like are preferably applied.

[0091]

(2-5) Crushing step and classification step

5 This is a step for crushing a dry polymer obtained from the
foregoing drying step (crushing step) and making adjustments to
the particle size to fit within a predetermined range (classifying
step), to obtain water-absorbing resin powder (for simplicity,
the powder-form water-absorbing resin prior to performing surface
10 crosslinking is referred to as "water-absorbing resin powder").

[0092]

Types of apparatus used in said crushing step include, for
example: a high-speed rotary crusher such as a roll mill, a hammer
mill, a screw mill, a pin mill and the like; a vibration mill;
15 a knuckle-type crusher; a cylindrical mixer; and the like, and
they can be combined if needed.

[0093]

As a method for adjusting the particle size in the
classification step, for instance, sieve classification which is
20 carried out using a JIS (Japanese Industrial Standard)
standardized sieve (JIS Z8801-1 (2000)) and air stream
classification are included. Particle size adjustment for the
water-absorbing resin can be appropriately conducted not only at
the crushing step or at the classification step, but also at the
25 polymerization step (especially reverse phase suspension

polymerization or liquid drop spray polymerization) and other steps (for example, granulating step).

[0094]

5 To solve the problems described in the embodiment of the present invention, and also to produce the particulate water-absorbing agent according to the embodiment of the present invention more efficiently, the particle size of the water-absorbing resin powder obtained in this step should be controlled desirably to be within the range described below.

10 [0095]

Namely, the weight average particle diameter (D50) is controlled to be: preferably 200 to 600 μm , more preferably 200 to 550 μm , and even more preferably 250 to 500 μm .

[0096]

15 Furthermore, as a ratio of particles having a particle diameter of less than 150 μm (fine particles) to particles having a particle diameter of 850 μm or more (coarse particles), it is controlled to be: preferably 5% by weight or less, more preferably 3% by weight or less, and even more preferably 1% by weight or
20 less (the lower limit is 0% by weight). Meanwhile, the ratio of the particles having a particle diameter of less than 850 μm is preferably 90 to 100% by weight, and more preferably 95 to 100% by weight per relative to the entire particles.

[0097]

Furthermore, the weight ratio between the particles having a particle diameter of less than 300 μm and particles having a particle diameter of 300 μm or more but less than 850 μm is preferably 70:30 to 10:90, more preferably 60:40 to 15:85, even
5 more preferably 50:50 to 20:80, and particularly preferably 40:60 to 25:75. Meanwhile, the "particles having a particle diameter of less than 300 μm " indicates the water-absorbing resin powder which passes through a JIS standardized sieve with an opening size of 300 μm . The "particles having particle diameter of 300 μm or
10 more but less than 850 μm " indicates the water-absorbing resin powder, which is sifted through a JIS standardized sieve with an opening size of 850 μm but remains over a JIS standardized sieve with an opening size of 300 μm .

[0098]

15 Logarithmic standard deviation (σ_z) of particle size distribution is controlled such that it is preferably 0.20 to 0.50, more preferably 0.25 to 0.40, and even more preferably 0.27 to 0.35.

[0099]

20 Each of the particle size described above is measured using a JIS standardized sieve in accordance with the measuring methods disclosed in the U.S. Patent No. 7,638,570 or EDANA ERT420.2-02.

[0100]

25 Furthermore, the aforementioned particle size is also applied for a water-absorbing resin after surface crosslinking

(hereinafter referred to as "water-absorbing resin particles" for simplicity) or a water-absorbing resin to which a chelating agent has been added (hereinafter, it might be referred to as "water-absorbing resin granulate" for simplicity). Therefore,
5 it is preferable to carry out surface crosslinking or granulation process so that the above described particle size range is maintained. Meanwhile, the particles size of a particulate water-absorbing agent as a final product is described in section (3-7).

10 [0101]

(2-6) Surface crosslinking step

This is a step for forming a portion having a higher crosslinking density on a surface layer of the water-absorbing resin powder (a part within a few tens of micrometers from the
15 surface of water-absorbing resin powder) which is obtained through the above described steps, and include following steps (2-6-1) to (2-6-3).

[0102]

According to this surface crosslinking step, a
20 water-absorbing resin (water-absorbing resin particles), of which surface is crosslinked, is obtained through radical crosslinking, surface polymerization, or crosslinking reaction with the surface crosslinking agent on the surface layer of the water-absorbing resin powder.

25 [0103]

(2-6-1) Mixing step

(Surface crosslinking agent)

For instance, the surface crosslinking agent used in the embodiment of the present invention includes, but not limited to, various organic or inorganic surface crosslinking agents. In particular, from the viewpoint of the physical properties of a water-absorbing resin or a particulate water-absorbing agent or the manageability of a surface crosslinking agent, an organic surface crosslinking agent capable of forming a covalent bond upon reaction with carboxyl group is preferable.

[0104]

Specifically, one or more types of the surface crosslinking agent described in the 9th to 10th columns of the U.S. Patent No. 7,183,456 are used. In that case, a total amount of the surface crosslinking agent used is, relative to 100 parts by weight of water-absorbing resin powder, preferably 0.01 to 10 parts by weight, and more preferably 0.01 to 5 parts by weight.

[0105]

Furthermore, it is preferable to use water at the time of adding a surface crosslinking agent to water-absorbing resin powder. It is more preferable to add in an aqueous solution. In that case, an amount of water used is, relative to 100 parts by weight of water-absorbing resin powder, preferably 0.1 to 20 parts by weight, and more preferably 0.5 to 10 parts by weight.

[0106]

Furthermore, a hydrophilic organic solvent is applied to the embodiment of the present invention, if necessary. In that case, an amount of the hydrophilic organic solvent used is, relative to 100 parts by weight of water-absorbing resin powder, preferably
5 10 parts by weight or less, and more preferably 5 parts by weight or less.

[0107]

Furthermore, additives can be added during a re-moistening step described below by mixing with a surface crosslinking agent
10 (aqueous solution) within a range of 5 parts by weight or less, or they can be added during a separate mixing step.

[0108]

(Method for addition and mixing)

As to a method for adding and mixing the aforementioned
15 surface crosslinking agent, although it is not limited, the surface crosslinking agent and, water, hydrophilic organic solvent or a combination thereof, as a solvent, are prepared in advance, and then those are added and combined by spraying or dropwise against the water-absorbing resin powder. Spraying
20 followed by mixing is more preferable.

[0109]

A mixing device used for mixing the surface crosslinking agent and the water-absorbing resin powder is, but not limited to, preferably a high-speed stirring mixer, and more preferably
25 a continuous high-speed stirring type mixer.

[0110]

(2-6-2) Heat treatment step

Heat treatment for the mixture of the aforementioned surface crosslinking agent and water-absorbing resin powder causes a surface crosslinking reaction, and therefore water-absorbing resin particles, with their surface being crosslinked, are obtained.

[0111]

For heat treatment, a publicly known dryer is used, but preferably, it is a paddle dryer. A temperature for heating (temperature of heating medium) is preferably 80 to 250°C, more preferably 100 to 220°C, and even more preferably 160 to 200°C.

[0112]

(2-6-3) Cooling step

For the purpose of terminating the aforementioned surface crosslinking reaction or proceeding to a next step or other purposes, if needed, a cooling process is performed after surface crosslinking .

[0113]

For the cooling process, a device, which is the same type as the publicly known dryer used for the step of heat treatment, is applied. The cooling temperature (temperature of cooling medium) is preferably 0 to 90°C, more preferably 20 to 85°C, and even more preferably 40 to 80°C.

[0114]

(2-7) Re-moistening step

This is a step for adding at least one type of additives, which is selected from the group consisting of: a polyvalent metal
5 salt compound, a cationic polymer, a chelating agent, an inorganic reducing agent, and α -hydroxycarboxylic compound, to the water-absorbing resin particles that are obtained in the above surface crosslinking step.

[0115]

10 The additive is preferably added in the form of an aqueous solution or slurry. In this case, as the water-absorbing resin is re-swollen with water, this step is called "re-moistening step". Meanwhile, the aforementioned additive can be added and mixed simultaneously with the surface crosslinking agent solution
15 described above.

[0116]

(Polyvalent metal salt and/or cationic polymer)

In the embodiment of the present invention, from the viewpoint of enhancing a water absorption speed (Vortex),
20 enhancing a liquid permeability (SFC), or fluidity during moisture absorption of a water-absorbing resin or a particulate water-absorbing agent to be obtained, a polyvalent metal salt and/or a cationic polymer is preferably added.

[0117]

Specifically, the polyvalent metal salt and/or the cationic polymer and an amount used thereof that are described in "[7] Polyvalent metal salt and/or cationic polymer" of the International Publication No. 2011/040530 can also be applied to
5 the present invention.

[0118]

(α -Hydroxycarboxylic acid compound)

In the embodiment of the present invention, from the viewpoint of preventing coloration of a water-absorbing resin or
10 a particulate water-absorbing agent to be obtained, an α -hydroxycarboxylic acid compound can be additionally added. Meanwhile, the " α -hydroxycarboxylic acid compound" indicates carboxylic acid or a salt thereof having hydroxyl group in the molecules, and it is hydroxycarboxylic acid which has a hydroxyl
15 group at the α position.

[0119]

As for the α -hydroxycarboxylic acid compound, an α -hydroxycarboxylic acid compound and an amount used thereof that are described in "[6] α -Hydroxycarboxylic acid compound" of the
20 International Publication No. 2011/040530 can also be applied to the present invention.

[0120]

Meanwhile, a specific compound or an amount used of the chelating agent or inorganic reducing agent are described in
25 sections (3-1) and (3-2) below.

[0121]

(2-8) Step for adding other additives

In order to grant various functions to a water-absorbing resin, it is possible to add an additive other than the ones
5 described above. Specifically, examples of such an additive encompass a surfactant, a compound having phosphorus atom, an oxidizing agent, an organic reducing agent, water-insoluble inorganic fine particle, organic powder such as metal soap, a water soluble deodorizing agent, an antibacterial agent, pulp,
10 thermoplastic fiber and the like. Further, as a surfactant, the surfactant disclosed in the International Publication No. 2005/075070 can preferably be applied.

[0122]

Furthermore, an amount of those additives used is determined
15 as appropriately in accordance with the purpose for use and is not particularly limited. However, it is preferably 0 to 3% by weight, and more preferably 0 to 1% by weight relative to the water-absorbing resin.

[0123]

20 Furthermore, from the viewpoint of damage resistance, the water-absorbing resin (in particular, particulate water-absorbing agent) preferably contains polyol. The polyol is more preferably ethylene glycol, diethylene glycol, polyethylene glycol, propylene glycol, glycerin, or
25 pentaerythritol. More preferably, it is polyethylene glycol or

propylene glycol. An amount of the polyol used is determined appropriately in accordance with the purpose of use and is not particularly limited. However, it is preferably 0.005 to 5% by weight, and more preferably 0.01 to 1% by weight relative to the
5 water-absorbing resin.

[0124]

Meanwhile, a specific compound or an amount of the water insoluble inorganic fine particles and water soluble deodorizing agent used are described in sections (3-1) and (3-2) below.

10 [0125]

(2-9) Other steps

In addition to the above described steps, it is possible to have, if needed, steps such as a granulating step, a sizing step, a fine powder removing step, a fine powder recycling step, or the
15 like. Moreover, it is possible to further include one or more of the steps such as a transporting step, a storing step, a packaging step, and a reserving step. As described herein, the sizing step includes a fine powder removing step after surface crosslinking step and a step of classifying and crushing when the
20 water-absorbing resin is aggregated to yield a size larger than intended size. Furthermore, the fine powder recycling step includes a step for adding, during any step for producing a water-absorbing resin, fine powder itself or hydrogel prepared to have large size by fine powder granulating step. Meanwhile,
25 the same applies to the step for producing the particulate

water-absorbing agent according to the embodiment of the present invention.

[0126]

[3] Particulate water-absorbing agent and method for
5 producing same

The particulate water-absorbing agent according to the embodiment of the present invention is characterized in that it contains a water-absorbing resin obtained by the aforementioned production method as an example and a chelating agent and satisfies
10 the following requirements.

[0127]

Namely, the particulate water-absorbing agent of the embodiment of the present invention contains a water-absorbing resin as a main component and a chelating agent, the
15 water-absorbing resin containing particles with a particle diameter of less than 300 μm , as specified by a JIS standardized sieve, and particles with a particle diameter of 300 μm or more but less than 850 μm , as specified by a JIS standardized sieve, wherein an amount of the chelating agent included is 0.001 to 5
20 parts by weight per 100 parts by weight of a water-absorbing resin in solid and satisfies Formula (1):

[0128]

[Mathematical 6]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

[0129]

where, in Formula (1), C1 indicates an amount (ppm) of the chelating agent present in the particles of a particle diameter of less than 300 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent, and C2 indicates that an amount (ppm) of the chelating agent present in the particles of a particle diameter of 300 μm or more but less than 850 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent.

[0130]

Furthermore, the value for "C1/C2" is adjusted such that it is essentially higher than 1.2, preferably higher than 1.3, more preferably higher than 1.5, and even more preferably higher than 1.7. The effect of the embodiment of the present invention is exhibited more significantly as the value increases. Meanwhile, the upper limit is adjusted such that it is essentially lower than 4.0, preferably lower than 3.9, more preferably lower than 3.7, and even more preferably lower than 3.5. When the value is 4.0 or higher, the effect corresponding to the amount of chelating agent used is not obtained, and thus not economically favorable.

[0131]

According to the embodiment of the present invention, the chelating agent is mainly localized on the surface of the water-absorbing resin particles, and the presence of the chelating

agent can be confirmed by polishing the particle surface.
Hereinbelow, the method for producing the particulate
water-absorbing agent and the physical properties thereof
according to the embodiment of the present invention are
5 described.

[0132]

(3-1) Chelating agent

The particulate water-absorbing agent according to the
embodiment of the present invention essentially contains a
10 chelating agent to overcome problems according to the embodiment
of the present invention. From the viewpoint of the effect, the
chelating agent may be preferably either a polymerized compound
or a non-polymerized compound, and it is preferably a
non-polymerized compound. Furthermore, it is desired to have a
15 chelating agent having preferably an element other than carbon,
hydrogen, or oxygen, and more preferably nitrogen or phosphorus
contained in the molecule.

[0133]

Meanwhile, the expression "an element other than carbon,
20 hydrogen, or oxygen is contained in the molecule" means that that
the neutralizing counter ion in an acidic group is excluded. For
examples, in COONa, an element other than carbon, hydrogen, or
oxygen is contained in the molecule of a chelating agent in addition
to the neutralizing Na⁺. Representative examples of a substituent
25 group include an amino group and a sulfonic acid group.

[0134]

Specific examples of the chelating agent used in the embodiment of the present invention include: amino polyvalent carboxylic acid, organic polyvalent phosphoric acid, inorganic
5 polyvalent phosphoric acid, amino polyvalent phosphoric acid, and tropolone derivatives. At least one compound selected from a group consisting of those compounds is used in the embodiment of the present invention. Meanwhile, the term "polyvalent" means that a plurality of functional groups are present in one molecule.
10 Preferably, there are 2 to 30, more preferably 3 to 20, and even more preferably 4 to 10 functional groups.

[0135]

From the viewpoint of the influence on polymerization or properties of a particulate water-absorbing agent to be obtained,
15 the chelating agent has a molecular weight preferably of 100 to 5000, and more preferably of 200 to 1000. When the molecular weight is more than 5000, the aqueous monomer solution may have increased viscosity depending on the time point for addition of the chelating agent, and in such case polymerization control or
20 homogeneous mixing is difficult to achieve, and therefore undesirable.

[0136]

Examples of the amino polyvalent carboxylic acid include: iminodiacetic acid, hydroxyethyl iminodiacetic acid,
25 nitrilotriacetic acid, nitrilotripropionic acid,

ethylenediamine tetraacetic acid, diethylenetriamine
pentaacetic acid, triethylene tetramine hexaacetic acid,
trans-1,2-diaminocyclohexane tetraacetic acid,
N,N-bis(2-hydroxyethyl)glycine, diaminopropanol tetraacetic
5 acid, ethylenediamine dipropionic acid,
N-hydroxyethylenediamine triacetic acid, glycol ether
diaminetetraacetic acid, diaminopropane tetraacetic acid,
N,N'-bis(2-hydroxybenzil)ethylenediamine-N,N'-diacetic acid,
1,6-hexamethylenediamine-N,N,N',N'-tetraacetic acid, and a salt
10 thereof.

[0137]

Examples of the organic polyvalent phosphoric acid include:
nitriloacetic acid-di(methylenephosphinic acid),
nitrilodiacetic acid-(methylenephosphinic acid), nitriloacetic
15 acid- β -propionic acid-methylenephosphonic acid,
nitrilotris(methylenephosphonic acid), and
1-hydroxyethylidenediphosphonic acid.

[0138]

Examples of the inorganic polyvalent phosphoric acid include
20 pyrophosphoric acid, tripolyphosphoric acid, and a salt thereof.

[0139]

Examples of the amino polyvalent phosphoric acid include:
ethylenediamine-N,N'-di(methylenephosphinic acid),
ethylenediaminetetra(methylenephosphinic acid),
25 cyclohexanediaminetetra(methylenephosphonic acid),

ethylenediamine-N,N' -diacetic acid-N,N' -di(methylenephosphonic acid), ethylenediamine-N,N' -di(methylenephosphonic acid), ethylenediaminetetra(methylenephosphonic acid), polymethylenediaminetetra(methylenephosphonic acid),
5 diethylenetriaminepenta(methylenephosphonic acid), and a salt thereof.

[0140]

Examples of the tropolone derivatives include tropolone, β -thujaplicin, and γ -thijaplicin.

10 [0141]

Amongst them, a chelating agent selected from amino polyvalent carboxylic acid, organic polyvalent phosphoric acid, and amino polyvalent phosphoric acid is preferable. A chelating agent of amino polyvalent carboxylic acid having 3 or more
15 carboxylic groups is more preferable. From the viewpoint of gel stability, diethylenetriamine pentaacetic acid, triethylene tetramine hexaacetic acid, trans-1,2-diaminocyclohexane tetraacetic acid, and a salt thereof are even more preferable.

[0142]

20 In the embodiment of the present invention, the content (an amount used) of the chelating agent is, relative to 100 parts by weight of the solids content in water-absorbing resin, 0.001 to 5 parts by weight, preferably 0.02 to 1 parts by weight, more preferably 0.03 to 0.9 parts by weight, even more preferably 0.04
25 to 0.8 parts by weight, even sill more preferably 0.05 to 0.7 parts

by weight, particularly preferably 0.06 to 0.6 parts by weight, and most preferably 0.07 to 0.5 parts by weight. When the content is more than 5 parts by weight, the effect corresponding to addition is not obtained so that it is not economically favorable and also
5 problems like reduced absorption occur. On the other hand, when the content is less than 0.02 parts by weight, in particular less than 0.001 parts by weight, the gel stability or the effect of preventing coloration is not obtained at sufficient level.

[0143]

10 In the embodiment of the present invention, the time point for adding the chelating agent is not particularly limited, and it can be added during any one or more steps of each step described for above [2] Method for producing polyacrylic acid (salt)-based water-absorbing resin. Furthermore, an amount used in each step
15 corresponds to the content in a particulate water-absorbing agent which is substantially obtained.

[0144]

Similar to the quantification of residual monomers or water soluble components, the chelating agent in the particulate
20 water-absorbing agent can be suitably quantified by extracting the chelating agent in water or physiological saline and quantifying it using liquid chromatography or ion chromatography.

[0145]

According to the embodiment of the present invention,
25 because the chelating agent is preferably blended in surface of

a water-absorbing resin, the chelating agent is preferably added during the surface crosslinking step or the re-moistening step after surface crosslinking step. Because deterioration of a water-absorbing resin progresses from resin surface, as the
5 chelating agent is placed near the surface of a water-absorbing resin, the gel stability can be improved.

[0146]

(3-2) Method for adding chelating agent

The method for producing a particulate water-absorbing agent
10 according to the embodiment of the present invention is a method for producing a particulate water-absorbing agent containing a water-absorbing resin as a main component and a chelating agent, which comprises particles with a particle diameter, of less than 300 μm and particles with a particle diameter, as specified by
15 a JIS standardized sieve, of 300 μm or more but less than 850 μm , wherein a chelating agent content is 0.001 to 5 parts by weight relative to 100 parts by weight of the water-absorbing resin and satisfies Formula (1).

[0147]

20 [Mathematical 7]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

[0148]

Meanwhile, in Formula (1), C1 indicates a chelating agent content (ppm) which is present in the particles with the particle

diameter of less than 300 μm in which the particle diameter is specified by a JIS standardized sieve amongst the particles constituting the particulate water-absorbing agent and C2 indicates a chelating agent content (ppm) which is present in the particles with the particle diameter of 300 μm or more but less than 850 μm in which the particle diameter is specified by a JIS standardized sieve amongst the particles constituting the particulate water-absorbing agent.

[0149]

10 More specifically, according to the production method of the following (a) to (d), in particular (a) or (b), a particulate water-absorbing agent satisfying Formula (1) can be obtained.

[0150]

(a) Production method including a step of adding a chelating agent to a water-absorbing resin with crosslinked surface to obtain a granulate (particulated granulate) of a water-absorbing resin with increased weight average particle diameter (D50) (for example, 1.01 to 10 times relative to the weight average particle diameter before adding chelating agent), and a step of disintegrating the granulate (particulated granulate) of the water-absorbing resin to lower the weight average particle diameter (D50) by 5% or more (for example, the weight average particle diameter after disintegration is 0.1 to 0.95 times relative to the granulate).

25 [0151]

(b) Production method including a step of classifying a surface crosslinked water-absorbing resin into several different particle sizes (for example, step of classifying into two particle sizes by using a JIS standardized sieve with opening size of 300 μm), a step of adding a chelating agent for each of the several different particle sizes (for example, a step of adding a larger amount of chelating agent to the particles with particle size of less than 300 μm compared to the particles with particle size of 300 μm or more, in particular, in the amount of 1.2 to 4.0 times), and a step of re-mixing several water-absorbing resins after addition of the chelating agent to obtain a particulate water-absorbing agent (for example, a step of re-mixing the particles which have been classified by using a JIS standardized sieve with opening size of 300 μm).

[0152]

(c) Production method including a step of mixing and preparing a predetermined amount of particulate water-absorbing agent with different particle size distribution.

[0153]

(d) Production method include a step of classifying a water-absorbing resin before surface crosslinking into several different particle sizes, a step of performing surface crosslinking and addition of a chelating agent for each of the different particle sizes, and a step of re-mixing several water-absorbing resins obtained after the surface crosslinking

and addition of chelating agent to obtain a particulate water-absorbing agent.

[0154]

Meanwhile, in order to achieve the subject of the embodiment
5 of the present invention, the chelating agent is added for each different particle size of the water-absorbing resin, preferably before drying, and more preferably after classification, and even more preferably after surface crosslinking. It is also possible to have a step of adding a chelating agent to monomers during
10 polymerization or a hydrogel forming crosslinked polymer before drying. The added amount of the chelating agent relative to monomers or a hydrogel forming crosslinked polymer is, relative to the whole amount added, preferably 0 to 50 mol%, more preferably 0 to 30 mol%, and even more preferably 0 to 10 mol%.

15 [0155]

The chelating agent may be added to a water-absorbing resin without using a solvent. When the chelating agent is a solid, in particular, it may be powder mixing (dry blend). However, from the viewpoint of the fixing property on a surface of a
20 water-absorbing resin, the chelating agent is preferably added as a solution or an aqueous dispersion. Examples of the solvent or dispersion medium which may be used therefor include water, a hydrophilic organic solvent, and a mixture solvent of water and a hydrophilic organic solvent.

25 [0156]

Specific examples of the hydrophilic organic solvent include monovalent alcohols of C1 to C10, or C2 to C6 or so, polyols (for example, propylene glycol and glycerin), polyether polyols such as polyethylene glycols or polypropylene glycols and an
5 alkoxyated compound thereof (for example, propoxyether of glycerin and methoxypolyethylene glycol). Amongst them, polyols, polyether polyols, or an alkoxyated compound thereof is preferable. From the viewpoint of controlling the dust property, polyols of C2 or C6 or so are particularly preferable.

10 [0157]

When the chelating agent is added as a solution or an aqueous dispersion, it is added at, as a solution or an aqueous dispersion, preferably 0.1 to 25% by weight, more preferably 0.5 to 20% by weight, and even more preferably 1.0 to 10% by weight relative
15 to the water-absorbing resin. Furthermore, it is sufficient that the concentration of the chelating agent in the solution or aqueous dispersion is 1 to 50% by weight or so. If necessary, a surfactant or the like can be used. The solvent can be dried, if necessary.

[0158]

20 (3-3) Additives other than chelating agent

In addition to the above chelating agent, the particulate water-absorbing agent according to the embodiment of the present invention may be added with various additives for obtaining desired performances. Preferred examples of the additives
25 include water insoluble inorganic fine particles, an inorganic

reducing agent, a water soluble deodorizing agent, and polyvalent metal salts (with the proviso that, iron ions are excluded).

[0159]

(Water insoluble inorganic fine particles)

5 When a water-absorbing agent having a water-absorbing resin as a main component is blended in an absorbent article like disposable diaper, fluidity of the water-absorbing agent is lowered in an environment with high humidity, thus making it difficult to have homogeneous mixing. Such difficulty is a cause
10 of having particle segregation in water-absorbing resin which is admixed in an absorbent article.

[0160]

Accordingly, it is important in the embodiment of the present invention to prevent blocking during moisture absorption, and it
15 is desirable to add water insoluble inorganic particles to ensure the fluidity.

[0161]

Specific examples of the water insoluble inorganic fine particles include metal oxide like silicon dioxide, titan oxide,
20 zinc oxide, and aluminum oxide, calcium phosphate, silicic acid (salt) like natural zeolite and synthetic zeolite, kaolin, talc, clay, bentonite, and hydrotalcite. Amongst them, inorganic fine particles having average particle diameter of 200 μm or less, or 20 μm or less, in which the average particle diameter is measured

by Coulter counter method, in particular silicon dioxide and silicic acid (salt) are more preferable.

[0162]

The amount of the water insoluble inorganic fine particles added is, relative to the water-absorbing resin, preferably 0.05 to 1.0% by weight, more preferably 0.05 to 0.8% by weight, even more preferably 0.05 to 0.7% by weight, and particularly preferably 0.1 to 0.5% by weight. When the added amount is 0.05% by weight or more, a decrease in gel stability can be suppressed. On the other hand, when the added amount is 1.0% by weight or less, a decrease in the fluid retention capacity under pressure (AAP) of a particulate water-absorbing agent can be suppressed.

[0163]

(Inorganic reducing agent)

Inorganic reducing agents mean a compound having reducing inorganic elements, which are added to prevent coloration or reduce residual monomers. Specific examples thereof include compounds having reducing sulfur atoms or reducing phosphorus atoms. In the embodiment of the present invention, it can be either an inorganic compound or an organic compound. As it can further enhance the gel stability and achieve the subject of the embodiment of the present invention, an inorganic reducing agent is preferable.

[0164]

The inorganic reducing agent may be in acid form or salt form, but is preferably in salt form. Monovalent or polyvalent metal salts are more preferred, and monovalent metal salts are even more preferred. Amongst them, the oxygen-containing reducing
5 inorganic compounds listed below as examples, that is, inorganic reducing agents in which sulfur or phosphorus is bonded to oxygen are preferred. The oxygen-containing reducing inorganic salts are more preferred.

[0165]

10 Also, the inorganic reducing agent may also be an inorganic reducing agent formed from organic compounds having an alkyl group, a hydroxyalkyl group and the like, which carry reducing inorganic atoms, and preferably reducing sulfur atoms or phosphorus atoms.

15 [0166]

Furthermore, as for the inorganic reducing agent carrying a reducing sulfur atom or a reducing phosphorus atom, examples include: sulfur compounds having valency of +4 (for example, sulfite, bisulfite, and pyrosulfite), sulfur compounds having
20 valency of +3 (for example, dithionite), sulfur compounds having valency of +2 (for example, sulfoxylate), phosphorus compounds having valency of +4 (for example, hypophosphate), phosphorus compounds having valency of +3 (for example, phosphite and pyrophosphorous phosphate), and phosphorus compounds having
25 valency of +1 (for example, hypophosphite). Meanwhile, sulfur compounds having valency of +6 (valency of positive number 6) and

phosphorus compounds having valency of +5 (valency of positive number 5) are most stable, and each element having oxidation number equal to or lower than them has a reducing property. Furthermore, the reducing sulfur atoms or reducing phosphorus atoms may be
5 replaced with an organic substance.

[0167]

Foregoing inorganic reducing agents carrying a reducing sulfur atom include, but not limited to, for instance, inorganic compounds including: sulfites such as sodium sulfite, potassium
10 sulfite, calcium sulfite, zinc sulfite, and ammonium sulfite; bisulfites such as sodium bisulfite, potassium bisulfite, calcium bisulfite, and ammonium bisulfite; pyrosulfites such as sodium pyrosulfite, potassium pyrosulfite, and ammonium pyrosulfite; dithionites such as sodium dithionite, potassium dithionite,
15 ammonium dithionite, calcium dithionite, and zinc dithionite; trithionates such as potassium trithionate and sodium trithionate; tetrathionates such as potassium tetrathionate and sodium tetrathionate; thiosulfates such as sodium thiosulfate, potassium thiosulfate, and ammonium thiosulfate; and a water
20 soluble organic compound such as 2-hydroxy-2-sulfinic acetic acid, sodium formaldehyde sulfoxylate, formamidine sulfinic acid and thioglycolic acid tris(2-carboxyethyl)phosphine hydrochloride (TCEP), and tributylphosphine (TBP) and the like. Amongst the water soluble organic compounds, preferred examples
25 are 2-hydroxy-2-sulfinic acetic acid, 2-hydroxy-2-sulfonatoacetate and/or a salt thereof. Preferred salts include alkali metal and alkaline earth metal salts, and

preferred examples include lithium salts, sodium salts, and potassium salts, while sodium salts are particularly preferred. 2-Hydroxy-2-sulfinic acid (salt) may be used in combination with 2-hydroxy-2-sulfonacetic acid (salt), or in
5 combination with the inorganic compounds that are described above.

[0168]

The inorganic reducing agent carrying a reducing phosphorus atom includes, but not limited to, for instance, sodium hypophosphite.

10 [0169]

In particular, preferred are sulfite, bisulfite, pyrosulfite, and dithionite. More preferred are sodium sulfite, sodium bisulfite, potassium pyrosulfite, and sodium dithionite.

[0170]

15 An amount of the inorganic reducing agent added is, relative to the water-absorbing resin, preferably 0.01 to 1.0% by weight, more preferably 0.05 to 1.0% by weight, and even more preferably 0.05 to 0.5% by weight. When the added amount is 0.01% by weight or more, coloration with the lapse of time can be suppressed.
20 Furthermore, when the added amount is 1.0% by weight or less, malodor can be suppressed, and in particular, malodor after absorbing an aqueous solution can be effectively suppressed.

[0171]

(Water soluble deodorizing agent)

The water soluble deodorizing agent is added to provide the particulate water-absorbing agent with a deodorizing property. Meanwhile, the reason why a water soluble one is used as the deodorizing agent is that it can give an excellent deodorizing
5 property to the particulate water-absorbing agent without deteriorating the water absorption performance. Herein, the expression "water soluble" means that not less than 0.1 g, preferably not less than 1 g, more preferably not less than 10 g is dissolved in 100 g of water at 25°C.

10 [0172]

As for such water soluble deodorizing agent, various known ones such as extracts from leaves of Theaceae plants are usable. Example of the "Theaceae plants" include camellia, tea plant, sasanqua camellia, sakaki plant, and scarlet sakaki plant, and
15 deodorizable components are extracted from their leaves with organic solvents, such as alcohols and ketones, or water, or their mixed solvents. Examples of the deodorizing components include flavonol, flavanols, organic polymers, and tannin.

[0173]

20 An amount of the water soluble deodorizing agent added is, relative to the water-absorbing resin, preferably 0.0001 to 10% by weight. When the added amount is less than 0.0001% by weight, the deodorizing effect is not obtained. Meanwhile, when the added amount is more than 10% by weight, the effect is not obtained as
25 much as the increased cost.

[0174]

(Polyvalent metal salt)

The polyvalent metal salt (with the proviso that, iron ions are excluded) is added to improve the water absorbent speed or liquid permeability or to increase the fluidity during moisture absorption. Examples of the polyvalent metal salt include an organic acid salt or an inorganic acid salt which contains at least one metal (polyvalent metal cation) selected from typical metal or transition metal of Group 4 to Group 11. For example, an organic acid salt or an inorganic acid salt which contains at least one metal (polyvalent metal cation) selected from Mg, Ca, Ti, Zr, V, Cr, Mn, Co, Ni, Pd, Cu, Zn, Cd, and Al is preferable. Specific examples include aluminum sulfate, aluminum lactate, aluminum polychloride, magnesium sulfate, and zirconium sulfate.

15 [0175]

(Other additives)

In addition to the aforementioned water insoluble inorganic fine particles, inorganic reducing agent, water soluble deodorizing agent, and polyvalent metal salt (with the proviso that, iron ions are excluded), an anti-bacterial agent, a fragrance, a foaming agent, a pigment, a dye, a plasticizer, an adhesive, a surfactant, a fertilizer, an oxidizing agent, salts, a bactericidal agent, a hydrophilic polymer like polyethylene glycol and polyethyleneimine, a hydrophobic polymer like paraffin, a thermoplastic resin like polyethylene and

polypropylene, a thermosetting resin like polyester resin or urea resin, or the like can be suitably added to the particulate water-absorbing agent of the embodiment of the present invention to have desired functions.

5 [0176]

Meanwhile, those additives may be added either simultaneously or separately with the chelating agent described above. The amount of the additives to be added is, relative to 100 parts by weight of the water-absorbing resin, preferably 30
10 parts by weight or less, more preferably 10 parts by weight or less, and even more preferably 1 part by weight or less.

[0177]

(Method for adding additives)

The method for adding the water insoluble inorganic fine
15 particles, inorganic reducing agent, water soluble deodorizing agent, or polyvalent metal salt to the water-absorbing resin is not particularly limited, and it can be performed either simultaneously or separately with the chelating agent described above. Furthermore, a so-called wet mixing method in which
20 addition is performed after suspension in water or the like can be employed, or a dry blend method in which powders are admixed with each other can be employed.

[0178]

Furthermore, each material described above can be added at
25 any time. However, except the inorganic reducing agent, it can

be preferably added after the drying step, more preferably before the surface crosslinking step or during the surface crosslinking step, and even more preferably after surface crosslinking step. The inorganic reducing agent is added preferably to a hydrogel
5 forming crosslinked polymer before drying, more preferably after the drying step, even more preferably before the surface crosslinking step or during the surface crosslinking step, and particularly preferably after the surface crosslinking step.

[0179]

10 (Addition for each different particle size)

In the embodiment of the present invention, the amount added of the additives other than the chelating agent, that is, the water insoluble inorganic fine particles, inorganic reducing agent, water soluble deodorizing agent, or polyvalent metal salt (with
15 the proviso that, iron ions are excluded), is also different for each different particle size. In particular, it is preferable that they are added in a larger amount to the particles with small particle size.

[0180]

20 Namely, amongst the particles constituting the particulate water-absorbing agent, when "B1" is the amount (ppm) of additives other than chelating agent which are present in particles with the particle diameter of less than 300 μm in which the particle diameter is specified by a JIS standardized sieve and "B2"
25 indicates the amount (ppm) of additives other than chelating agent

which are present in particles with the particle diameter of 300 μm or more but less than 850 μm in which the particle diameter is specified by a JIS standardized sieve, adjustment is made such that the value calculated as "B1/B2" is preferably more than 1.2, more preferably more than 1.3, even more preferably more than 1.5, and particularly preferably more than 1.7. The effect of the embodiment of the present invention is exhibited more significantly as the value increases. Meanwhile, the upper limit is adjusted such that it is essentially lower than 4.0, preferably lower than 3.9, more preferably lower than 3.7, and even more preferably lower than 3.5. When the value is 4.0 or higher, the effect corresponding to the amount of additives used other than chelating agent is not obtained, and thus not economically favorable.

[0181]

(3-4) Amount of soluble contents

From the viewpoint of tackiness caused by eluted components during use of disposable diaper, the amount of soluble contents in the particulate water-absorbing agent of the embodiment of the present invention (soluble amount per hour specified by Examples that are described below) is controlled such that it is preferably 5 to 30% by weight, more preferably 5 to 25% by weight, and even more preferably 5 to 20% by weight in terms of a value with corrections for moisture content. The control method can be suitably performed by using an internal crosslinking agent or the like. Meanwhile, in order to obtain a particulate water-absorbing

agent in which the amount of soluble contents is less than 5% by weight, a large amount of the internal crosslinking agent needs to be used. As such, the fluid retention capacity without pressure (CRC) is significantly lowered in addition to cost increase and
5 an occurrence of residual crosslinking agent, and therefore undesirable.

[0182]

(3-5) Amount of deteriorated solubles

The amount of deteriorated solubles of the particulate
10 water-absorbing agent according to the embodiment of the present invention (the amount of deteriorated solubles per hour specified by Examples that are described below) is controlled such that it is preferably 0 to 40% by weight, more preferably 0 to 35% by weight, and even more preferably 0 to 31% by weight in terms of a value
15 corrected for moisture content. When the amount of deteriorated solubles is more than 40% by weight, gel deterioration is caused by urine during use of disposable diaper, and it may cause leakage or reverse liquid flow.

[0183]

20 Furthermore, according to the embodiment of the present invention, the difference in the amount of deteriorated solubles depending on particle size is small. As such, by combining the particulate water-absorbing agent of the embodiment of the present invention to an absorbent article like disposable diaper, only

a small variation in the amount of deteriorated solubles is caused during actual use of disposable diaper.

[0184]

The difference in the amount of deteriorated solubles
5 (defined by (the amount of deteriorated solubles of particles with
the particle diameter of less than 300 μm) - (the amount of
deteriorated solubles of particles with the particle diameter of
300 μm or more but less than 850 μm)) is preferably 5% by weight
or less, more preferably 3% by weight or less, even more preferably
10 2% by weight or less, and particularly preferably 1% by weight
or less. The ratio between them (defined by (the amount of
deteriorated solubles of particles with the particle diameter of
less than 300 μm)/(the amount of deteriorated solubles of
particles with particle diameter 300 μm or more but less than 850
15 μm)) is preferably 1.1 times or less, more preferably 1.05 or less,
and even more preferably 1.02 times or less.

[0185]

(3-6) Increased amount of deteriorated solubles

The increased amount of deteriorated solubles of the
20 particulate water-absorbing agent according to the embodiment of
the present invention (as specified by Examples that are described
below is controlled such that it satisfies the following
conditions. Namely, in the particles constituting the
particulate water-absorbing agent, 1) the increased amount of
25 deteriorated solubles of the particles with the particle diameter

of less than 300 μm , in which the particle diameter is specified by a JIS standardized sieve, is 0 to 15% by mass, and 2) the increased amount of deteriorated solubles of the particles with the particle diameter of 300 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, is 0 to 20% by mass.

[0186]

The increased amount of deteriorated solubles of the particles with the particle diameter of less than 300 μm is preferably 0 to 14% by weight, and more preferably 0 to 12% by weight. Furthermore, the increased amount of deteriorated solubles of the particles with the particle diameter of 300 μm or more but less than 850 μm is preferably 0 to 18% by weight, and more preferably 0 to 16% by weight. Meanwhile, those values include corrections for moisture content.

[0187]

As the increased amount of deteriorated solubles is within the aforementioned range, the water absorption performance can be maintained as it is designed even in an environment in which the particulate water-absorbing agent can undergo deterioration. For example, even for a case where the particulate water-absorbing agent is used as a disposable diaper for a long period time, the water absorption performance of a disposable diaper is not lowered so that urine leakage or troubles like skin irritation can be reduced.

[0188]

Meanwhile, if the increased amount of deteriorated solubles is not within the above range, the water absorption performance is lowered over the time in an environment in which the particulate
5 water-absorbing agent can undergo deterioration. For examples, when the particulate water-absorbing agent is used as a disposable diaper for a long period time, the water absorption performance of a disposable diaper is lowered so that urine leakage or troubles like skin irritation may increase.

10 [0189]

(3-7) Particle size

The particle size (specified by JIS Z8801-01(2000)) of the particulate water-absorbing agent according to the embodiment of the present invention is controlled to the following range in order
15 to achieve the subject of the embodiment of the present invention more easily and to produce the particulate water-absorbing agent more efficiently.

[0190]

Namely, the weight average particle diameter (D50) of the
20 particulate water-absorbing agent is controlled preferably to 200 to 600 μm , more preferably to 200 to 550 μm , and even more preferably to 250 to 500 μm .

[0191]

Furthermore, the ratio of particles (fine particles) having particle diameter of less than 150 μm in the particulate water-absorbing agent is controlled such that it is preferably 5% by weight or less, more preferably 3% by weight or less, and
5 even more preferably 1% by weight or less (the lower limit is 0% by weight). Meanwhile, the ratio of the particles with the particle diameter of less than 850 μm is preferably 90 to 100% by weight, and more preferably 95 to 100% by weight.

[0192]

10 Meanwhile, the weight ratio between the particles with the particle diameter of less than 300 μm and the particles with the particle diameter of 300 μm or more but less than 850 μm in the particulate water-absorbing agent is preferably 70 : 30 to 10 :
15 : 90, more preferably 60 : 40 to 15 : 85, even more preferably 50 : 50 to 20 : 80, and particularly preferably 40 : 60 to 25 : 75. Meanwhile, the "particles with the particle diameter of less than 300 μm " indicate a particulate water-absorbing resin which passes through a JIS standardized sieve with opening size of 300 μm and the "particles with the particle diameter of 300 μm or more but
20 less than 850 μm " indicate a particulate water-absorbing resin which passes through a JIS standardized sieve with opening size of 850 μm but remains on a JIS standardized sieve with opening size of 300 μm .

[0193]

25 From the above, according to the preferred embodiment of the embodiment of the present invention, the ratio of the particles

with the particle diameter of 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, is preferably 90% by weight or more in the particulate water-absorbing agent. Furthermore, the weight
5 ratio between the particles with the particle diameter of less than 300 μm and the particles with the particle diameter of 300 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, is preferably 70 : 30 to 10 : 90.

10 [0194]

The ratio of the particles with the particle diameter of 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, is more preferably 95% by weight or more, and even more preferably 98% by weight or more.

15 [0195]

The arithmetic standard deviation of particle size distribution ($\sigma\zeta$) of the particulate water-absorbing agent is controlled such that it is preferably 0.20 to 0.50, more preferably 0.25 to 0.40, and even more preferably 0.27 to 0.35.

20 [0196]

(3-8) Fluid retention capacity without pressure (CRC)
(ERT441.2-02)

The fluid retention capacity without pressure (CRC) of the particulate water-absorbing agent according to the embodiment of
25 the present invention is controlled such that, in terms of a value

corrected for moisture content, 25 (g/g) or more, more preferably
30 (g/g) or more, and even more preferably 33 (g/g) or more for
physiological saline. Furthermore, from the viewpoint of balance
with other properties (for example, the fluid retention capacity
5 under pressure (AAP)), the upper limit is 60 (g/g) or less, more
preferably 50 (g/g) or less, and even more preferably 45 (g/g)
or less. The fluid retention capacity without pressure (CRC) can
be controlled based on the crosslinking density during
polymerization or surface crosslinking.

10 [0197]

Meanwhile, if the fluid retention capacity without pressure
(CRC) is lower than 25 (g/g), only poor efficiency is yielded when
used for a hygienic material like disposable diaper, and therefore
undesirable.

15 [0198]

(3-9) Fluid retention capacity under pressure (AAP)
(ERT442.2-02)

The fluid retention capacity under pressure (AAP) of the
particulate water-absorbing agent according to the embodiment of
20 the present invention is controlled such that, in terms of a value
corrected for moisture content, 15 (g/g) or more, more preferably
20 (g/g) or more, and even more preferably 23 (g/g) or more for
physiological saline at a load of 2.06 kPa. Furthermore, from
the viewpoint of balance with other properties (for example, the
25 fluid retention capacity without pressure (CRC)), the upper limit

is 40 (g/g) or less, more preferably 35 (g/g) or less, and even more preferably 33 (g/g) or less. The fluid retention capacity under pressure (AAP) can be controlled based on surface crosslinking.

5 [0199]

Meanwhile, when the fluid retention capacity under pressure (AAP) is less than 15 (g/g) and it is used for an absorbent body of a hygienic material like disposable diaper, an absorbent body having low returning amount of liquid (referred to as "Re-Wet")
10 is not obtained when pressure is applied to an absorbent body, and thus not desirable.

[0200]

Taken together, according to a preferred embodiment of the embodiment of the present invention, the fluid retention capacity
15 without pressure (CRC) of the particulate water-absorbing agent is 30 (g/g) or more after corrected for moisture content against physiological saline, and the fluid retention capacity under pressure (AAP) at the pressure of 2.06 kPa is 20 (g/g) or more after corrections for moisture content against physiological
20 saline.

[0201]

(3-10) Moisture content

A moisture content in the particulate water-absorbing agent according to the embodiment of the present invention (specified
25 by the loss after drying for 3 hours at 180°C) is controlled such

that it is preferably 0.5 to 15% by weight, more preferably 1.0 to 10% by weight from the viewpoint of water absorbent speed or impact resistance. The moisture content is adjusted to a preferred range during the drying step or re-moistening step
5 described above.

[0202]

(3-11) Amount of Fe (iron ions)

An amount of Fe in the particulate water-absorbing agent according to the embodiment of the present invention is, from the
10 viewpoint of preventing coloration of a particulate water-absorbing agent, preferably 2 ppm or less, more preferably 1.5 ppm or less, even more preferably 1 ppm or less, and particularly preferably 0.5 ppm or less. Furthermore, the lower limit is, from the viewpoint of the cost of purification of base
15 (in particular, caustic soda), preferably 0.001 ppm or more, and more preferably 0.01 ppm or more. Meanwhile, control of the Fe amount can be achieved by suitably purifying the materials of a water-absorbing resin, in particular, the base used for neutralization, for example, by removing Fe present in NaOH or
20 Na₂CO₃.

[0203]

The amount of Fe present in a particulate water-absorbing agent or a base can be quantified by ICP emission spectrophotometric analysis specified in JIS K1200-6. With

regard to details of the quantification method, reference can be made to International Publication No. 2008/090961.

[0204]

Meanwhile, when Fe is contained at 5 ppm in caustic soda
5 (molecular weight: 40), it may be contained at 1.7 ppm ($= 5 \times (40 \times 0.75/88.5)$) in sodium acrylate with neutralization rate of 75 mol% (average molecular weight of 88.5).

[0205]

(3-12) Initial color

10 The particulate water-absorbing agent according to the embodiment of the present invention is used for absorbent articles like disposable diaper, and it is required to be present as white powder. Thus, the initial color of the particulate water-absorbing agent has, based on Hunter's Lab color system
15 using spectrophotometric colorimetric system, an L-value (lightness) of preferably 88 or more, more preferably 89 or more, and even more preferably 90 or more. Meanwhile, the upper limit of the L-value is 100, and no problem occurs in absorbent articles like disposable diaper due to color, provided that the L-value
20 is 88 or more. Moreover, an a-value is in a range of preferably -3 to 3, more preferably -2 to 2, still more preferably -1 to 1. Moreover, a b-value is in a range of preferably 0 to 12, more preferably 0 to 10, still more preferably 0 to 9. Note that, as the L-value approaches 100, whiteness is increased, and as the

a-value and the b-value approach 0, the color fades and becomes substantially white.

[0206]

(3-13) Color with the lapse of time

5 The particulate water-absorbing agent according to the embodiment of the present invention is used for absorbent articles like disposable diaper, and it is required to maintain a clean white state even when it is stored for a long period of time under high humidity and high temperature conditions. Thus, the color
10 with the lapse of time of the particulate water-absorbing agent of the embodiment of the present invention has, based on the Hunter's Lab color system, an L-value (Lightness) of preferably 80 or more, more preferably 81 or more, still more preferably 82 or more, particularly preferably 83 or more. Meanwhile, the upper
15 limit is 100, and no problem occurs due to color even after long-term storage under high humidity and high temperature conditions, provided that the L-value is 80 or more. Moreover, an a-value is in a range of preferably -3 to 3, more preferably -2 to 2, still more preferably -1 to 1. Moreover, a b-value is
20 in a range of preferably 0 to 15, more preferably 0 to 12, still more preferably 0 to 10. Note that, as the L-value approaches 100, whiteness is increased, and as the a-value and the b-value approach 0, the color fades and becomes substantially white.

[0207]

25 (3-14) Blocking ratio after moisture absorption

The particulate water-absorbing agent according to the embodiment of the present invention has a blocking ratio after moisture absorption of preferably 30% by weight or less, more preferably 20% by weight or less, even more preferably 10% by weight or less, and particularly preferably 5% by weight or less. The lower limit is preferably 0% by weight, but it can be 0.1% by weight or so. As the blocking ratio after moisture absorption is within the aforementioned range, excellent powder handleability is obtained, and therefore desirable. Meanwhile, when the blocking ratio after moisture absorption is more than 30% by weight, the particulate water-absorbing agent exhibits poor fluidity during production of absorbent articles like disposable diaper, and thus problems like difficult production of disposable diaper or the like may be caused.

[0208]

(3-15) SFC (Saline flow conductivity)

The SFC (saline flow conductivity) of the particulate water-absorbing agent according to the embodiment of the present invention is preferably $1 (\times 10^{-7} \cdot \text{cm}^3 \cdot \text{s} \cdot \text{g}^{-1})$ or greater, and more preferably $10 (\times 10^{-7} \cdot \text{cm}^3 \cdot \text{s} \cdot \text{g}^{-1})$ or greater. The upper limit is $1,000 (\times 10^{-7} \cdot \text{cm}^3 \cdot \text{s} \cdot \text{g}^{-1})$ or less. When the SFC is lower than $1 (\times 10^{-7} \cdot \text{cm}^3 \cdot \text{s} \cdot \text{g}^{-1})$, permeability of liquid including body fluid like urine or blood is low, and thus it is not suitable for an absorbent body of absorbent articles like disposable diaper. On the other hand, when the SFC exceeds $1,000 (\times 10^{-7} \cdot \text{cm}^3 \cdot \text{s} \cdot \text{g}^{-1})$ or greater, liquid including body fluid like urine or blood is not sufficiently

absorbed and liquid leakage may occur, and thus it is not suitable for an absorbent body of a hygiene product like disposable diaper. Meanwhile, SFC can be controlled based on particle size, surface crosslinking agent, polyvalent metal salt, cationic polymer, or
5 the like.

[0209]

[4] Use of particulate water-absorbing agent

The particulate water-absorbing agent according to the embodiment of the present invention can be used for various
10 applications, however, as it is stable due to a small variation in properties, it is used for absorbent articles, in particular absorbent articles like disposable diaper, sanitary napkin, and incontinence pad. In that case, the particulate water-absorbing agent is molded into sheet-like form by preparing it as a composite
15 with hydrophilic fiber or the like. Meanwhile, if no hydrophilic fiber is used, the particulate water-absorbing agent is fixed in paper, non-woven fabric or the like to give absorbent articles.

[0210]

The amount of the particulate water-absorbing agent (core
20 concentration) in the absorbent articles is preferably 10 to 100% by weight, more preferably 30 to 100% by weight, and even more preferably 50 to 100% by weight. Furthermore, the amount of the particulate water-absorbing agent used is preferably 1 to 30 g, more preferably 5 to 20 g, and even more preferably 10 to 20 g
25 per absorbent article (for example, per disposable diaper).

Furthermore, it is preferable that the absorbent article is adjusted to have density in the range of 0.06 to 0.5 (g/cm³) and grammage in the range of 0.01 to 0.2 (g/cm²).

[0211]

5 Meanwhile, specific examples of the fiber substrate used for absorbent articles include hydrophilic fiber like crushed wood pulp, cotton linter, crosslinked cellulose fiber, rayon, cotton, wool, acetate, and vinylon. Those fiber substrates are preferably air-layered.

10 EXAMPLES

[0212]

 The embodiment of the present invention is more specifically described with the Examples given below. However, the embodiment of the present invention is not limited to the Examples and the
15 examples derived from a proper combination of technical means disclosed in respective different Examples are also encompassed in the scope of the embodiment of the present invention.

[0213]

 Meanwhile, a power source of an electric apparatus
20 (including measurement of properties of the water-absorbing agent) used in Production Examples, Examples, and Comparative Examples was 200 V or 100 V, unless otherwise noted. Moreover, the properties of the water-absorbing agent of the embodiment of the present invention were measured at a room temperature (in a

range of 20°C to 25°C) and at a relative humidity of 50% RH, unless otherwise noted.

[0214]

[Measurement properties of particulate water-absorbing
5 agent]

The method for measuring properties of particulate water-absorbing agent, which is described below, can also be suitably applied to measurement of properties of a water-absorbing resin. In that case, the embodiment of the present invention is
10 made by substituting the "particulate water-absorbing agent" with a "water-absorbing resin".

[0215]

Furthermore, even for a particulate water-absorbing agent which has been produced with the same raw materials or production
15 method, the moisture content may greatly vary depending on the storage period or environment for storage. Other properties are also affected depending on the moisture content, and there can be a case where precise evaluation cannot be made.

[0216]

20 Accordingly, in the embodiment of the present invention, the properties that are affected by moisture content (the following (b), (c), and (e) to (h)) were evaluated after correcting measured value for moisture content. The value corrected for moisture content is obtained by dividing the measured value by (1-moisture

content/100). Furthermore, it is expressed as a value relative to 100 parts by weight of solids content of a water-absorbing resin.

[0217]

(a) Particle size (weight average particle diameter (D50),
5 content for different particle sizes)

The particle size of the particulate water-absorbing agent according to the embodiment of the present invention (weight average particle diameter (D50), an amount for each different particle sizes) was measured by using a JIS standardized sieve
10 based on the measurement method described in the U.S. Patent Application Publication No. 2006/204755.

[0218]

Meanwhile, the amount for different particle sizes can be obtained by measuring weight of each of particles with the particle
15 diameter of less than 300 μm and particles with the particle diameter of 300 μm or more but less than 850 μm .

[0219]

(b) Fluid retention capacity without pressure (CRC)

The water absorption capacity without pressure (CRC) of the
20 particulate water-absorbing agent according to the embodiment of the present invention was measured on the basis of ERT441.2-02 (2002).

[0220]

Meanwhile, because the fluid retention capacity without pressure (CRC) is affected by moisture content, in the embodiment of the present invention the evaluation was made by using a value corrected for moisture content.

5 [0221]

As a specific examples of moisture content correction, when moisture content is 5% by weight and measured value of fluid retention capacity without pressure (CRC) is 30 (g/g), the value corrected for moisture content is 31.6 (g/g) ($= 30 / (1 - 5/100)$).

10 [0222]

(c) Fluid retention capacity under pressure (AAP)

The fluid retention capacity under pressure (AAP) of the particulate water-absorbing agent according to the embodiment of the present invention was measured on the basis of ERT442.2-02
15 (2002). The measurement was performed with a load of 2.06 kPa (0.3 psi).

[0223]

Meanwhile, because the fluid retention capacity under pressure (AAP) is affected by moisture content, in the embodiment
20 of the present invention the evaluation was made by using a value corrected for moisture content.

[0224]

(d) Moisture content

Moisture content of the particulate water-absorbing agent according to the present embodiment of the present invention was measured on the basis of ERT430.2-02 (2002). Meanwhile, in the embodiment of the present invention, the measurement was made
5 while the sample amount was changed to 1.0 g and a drying temperature was changed to 180°C, respectively.

[0225]

(e) Amount of chelating agent

An amount of the chelating agent in the particulate
10 water-absorbing agent of the embodiment of the present invention was measured according to the method described below.

[0226]

1 g of the particulate water-absorbing agent was added to 100 g of physiological saline (0.9% by weight aqueous solution
15 of sodium chloride) and, by stirring for 1 hour at room temperature, the chelating agent in physiological saline was extracted (revolution number for stirring: 500 ± 50 rpm). Meanwhile, in the embodiment of the present invention, the particulate water-absorbing agent is classified in advance by using a JIS
20 standardized sieve with opening size of 300 μm , and for each of the product passed through the sieve (pass-product/particle diameter of less than 300 μm) and the product not passed through the sieve (on-product/particle diameter of 300 μm or more and less than 850 μm), measurement of the chelating agent content was
25 carried out.

[0227]

After that, the expanded gel was filtered by using a filter paper (manufactured by Toyo Roshi Kaisha Ltd., No. 2, retained particle size specified by JIS P 3801: 5 μm).

5 [0228]

After that, the obtained filtrate was further subjected to filtration for pretreatment of HPLC sample (chromatodisc 25A/aqueous system type, manufactured by Kurabo Industries Ltd., pore size: 0.45 μm) to measure the chelating agent content in
10 filtrate with the use of high-performance liquid chromatography (HPLC).

[0229]

An amount of chelating agent in the particulate water-absorbing agent was obtained by taking into consideration
15 of dilution rate of the particulate water-absorbing agent in physiological saline while using the calibration curve obtained by measuring a monomer standard solution with known concentration as an external standard.

[0230]

20 Meanwhile, the conditions for measuring HPLC were suitably modified depending on the type of a chelating agent. Specifically, the quantification was carried out as follows: Measurement condition 1 for diethylene triamine pentaacetic acid (DTPA), Measurement condition 2 for triethylene tetraamine

hexaacetic acid (TTHA), and Measurement condition 3 for ethylene diamine tetra(methylenephosphonic acid (EDTMP).

[0231]

Measurement condition 1:

5 <<Eluent>>; Mixture solution of 0.3 ml of 0.4 mol/L aqueous alum solution, 450 ml of 0.1 N aqueous solution of sodium hydroxide, 3 ml of 0.4 mol/L aqueous solution of tetra n-butyl ammonium hydroxide, 3 ml of sulfuric acid, 1.5 ml of ethylene glycol, and 2550 ml of ion exchange water.

10 <<Column>>; LichroCART 250-4 Superspher 100 RP-18e (4 μ m) (manufactured by Merck)

<<Column temperature>>; 23 $\pm$ 2°C

<<Flow rate>>; 1 ml/min

<<Detector>>; UV, wavelength of 258 nm

15 Measurement condition 2:

<<Eluent>>; 0.01 mol/L aqueous solution of sodium carbonate, 0.01 mol/L aqueous solution of sodium hydrogen carbonate, and 0.002 mol/L aqueous solution of tetra n-butyl ammonium hydroxide, each in the same amount, were admixed with one another followed
20 by addition of 2 N hydrochloric acid to adjust pH to 7.5.

[0232]

<<Column>>; Shodex Asahipak ODP-40 4D (Showa Denko K.K.)

<<Column temperature>>; 40°C

<<Column temperature>>; 0.7 ml/min

<<Detector>>; UV, wavelength of 254 nm

<<Preparation of sample solution>>; To a filtrate obtained
5 by extracting the chelating agent from particulate
water-absorbing agent, 0.01 mol/L aqueous solution of iron
chloride (III) in an amount larger than the chelating agent content
was added (for example, about 2 mL of 0.01 mol/L aqueous solution
of iron chloride (III) can be added to 20 mL aqueous solution in
10 which the chelating agent content is 100 ppm).

Measurement condition 3:

<<Eluent>>; 0.003 mol/L aqueous solution of sulfuric acid

<<Column>>; Shodex IC NI-424 (Showa Denko K.K.)

<<Column temperature>>; 40°C

15 <<Column temperature>>; 1 ml/min

<<Detector>>; RI

Since the chelating agent content is affected by the moisture
content, the value of the embodiment of the present invention is
a value corrected for moisture content, and it is converted to
20 the value relative to 100 parts by weight of the solids content
of a water-absorbing resin.

[0233]

Meanwhile, when a chelating agent containing acidic group was used, calculation was made on the assumption that all of the contained acidic groups were neutralized with alkali. For example, in the case of diethylene triamine pentaacetic acid, it
5 was calculated in terms of pentasodium salt.

[0234]

(f) Amount of soluble contents

The amount of soluble contents in the particulate water-absorbing agent of the embodiment of the present invention
10 was measured according to the following method.

[0235]

First, the pH electrode used for measurement of the amount of soluble contents was calibrated by using a pH standard buffer solution (pH 4.0, pH 7.0, pH 10.0).

15 [0236]

Next, 50 ml of previously prepared physiological saline (0.9% by weight aqueous solution of sodium chloride) was weighed in a 100 ml glass beaker, and under stirring using a stirrer chip (length: 30 mm), 0.1 mol/L aqueous solution of sodium hydroxide
20 was added dropwise till to have pH 10. The dripping amount (V_{ab} [ml]) of that case was obtained as blank. Subsequently, 0.1 mol/L aqueous hydrochloric acid solution was added dropwise thereto till to have pH 2.7. The dripping amount (V_{bb} [ml]) of that case was also obtained as blank.

[0237]

Subsequently, to a polypropylene container provided with a cover (volume: 250 ml), 200 ml of previously prepared physiological saline was added followed by addition of 1.0 g of the particulate water-absorbing agent. Meanwhile, in the embodiment of the present invention, the particulate water-absorbing agent was classified in advance by using a JIS standardized sieve with opening size of 300 μm , and for each of the product passed through the sieve (pass-product/particle diameter of less than 300 μm) and the product not passed through the sieve (on-product/particle diameter of 300 μm or more and less than 850 μm), measurement of the amount of solubles was carried out.

[0238]

Next, by using a stirrer chip (length of 30 mm $\times$ outer diameter of 8 mm), stirring was performed for 1 hour at 500 ± 50 rpm under room temperature to extract solubles. After that, filtration was performed by using a filter paper (manufactured by Toyo Roshi Kaisha Ltd., No. 2, retained particle size specified by JIS P 3801: 5 μm) to obtain a filtrate.

[0239]

20 ml of the filtrate obtained from above operations (recorded as F [ml]) was weighed in a glass beaker with volume of 100 ml, and according to mess-up to 50 ml with physiological saline, a liquid for titration was obtained. Meanwhile, even when

the filtrate is less than 20 ml, the amount (F [ml]) was recorded, and according to mess-up to 50 ml with physiological saline, a liquid tor titration was obtained.

[0240]

5 Subsequently, by using a stirrer chip (length of 30 mm × outer diameter of 8 mm), the liquid for titration was stirred and 0.1 mol/L aqueous solution of sodium hydroxide was added dropwise thereto till to have pH of 10. The titration amount (Va [ml]) was obtained. Subsequently, 0.1 mol/L aqueous hydrochloric acid
10 solution was added dropwise thereto till to have pH of 2.7 and the titration amount (Vb [ml]) was obtained.

[0241]

According to the following formulae (6) to (11), the amount of soluble contents was obtained.

15 [0242]

[Mathematical 8]

Amount of soluble contents (% by weight) = $\{(W_a + W_b)/m\} \times 100$
... (6)

[0243]

Meanwhile, in Formula (6), "Wa" means the relative weight of a unit having acidic groups in the solubles of the particulate
20 water-absorbing agent, "Wb" means the relative weight of a unit having carboxylate groups, which are neutralized by a basic substance, in the solubles of the particulate water-absorbing

agent, and they are obtained by the following formula.
Furthermore, "m" represents the weight of a particulate
water-absorbing agent.

[0244]

5 [Mathematical 9]

$$W_a (g) = N_a \times 72 \times 200/F \dots (7)$$

[0245]

[Mathematical 10]

$$W_b (g) = N_b \times 94 \times 200/F \dots (8)$$

[0246]

Meanwhile, "72" in Formula (7) indicates weight per mole of
10 repeating unit in an acrylic acid polymer and "94" in Formula (8)
indicates weight per mole of repeating unit in a sodium acrylate
polymer. However, when monomers having acidic groups other than
acrylic acid are co-polymerized or other salt such as a potassium
salt or a lithium salt is used as an alkali metal salt instead
15 of a sodium salt, those values are calculated with suitable
modification to average weight of repeating units including the
monomer.

[0247]

Furthermore, "Na" in Formula (9) indicates a number of moles
20 for acidic groups in the solubles that are contained in a liquid
for titration (filtrate), and "Nb" in Formula (10) indicates a
number of moles for carboxylate groups, which are neutralized by

a basic substance, in the solubles that are contained in a liquid for titration (filtrate). They are obtained by the following formula.

[0248]

5 [Mathematical 11]

$$N_a \text{ (mole)} = (V_a - V_{ab})/1000 \times 0.1 \dots (9)$$

[0249]

[Mathematical 12]

$$N_b \text{ (mole)} = N_1 - N_a \dots (10)$$

[0250]

10 Meanwhile, " N_1 " in Formula (10) indicates a total number of moles for the solubles that are contained in a liquid for titration (filtrate), and it is obtained by the following Formula (11).

[0251]

[Mathematical 13]

$$N_1 \text{ (mole)} = (V_b - V_{bb})/1000 \times 0.1 \dots (11)$$

[0252]

15 Meanwhile, because the amount of soluble contents is affected by moisture content, in the embodiment of the present invention the evaluation was made by using a value corrected for moisture content.

[0253]

(g) Amount of deteriorated solubles

The amount of deteriorated solubles in the particulate water-absorbing agent of the embodiment of the present invention was measured according to the following method.

5 [0254]

Namely, as a solution for deterioration test, to a previously prepared physiological saline, L-ascorbic acid was added to make a 0.1% by weight of such a solution. Specifically, 1.0 g of L-ascorbic acid was added and then dissolved in 999.0 g of
10 physiological saline.

[0255]

Next, to a polypropylene container provided with a cover (volume: 250 ml), 200 ml of the above deterioration test solution was added followed by addition of 1.0 g of a particulate
15 water-absorbing agent to form an expanded gel. Specifically, the container was sealed with a cover, and the expanded gel was allowed to stand for 2 hours in an atmosphere of 60°C. Thereafter, a stirrer chip (length of 30 mm × outer diameter of 8 mm) was added thereto, and stirring was performed for 1 hour in the same manner
20 as above (amount of soluble contents) to extract the deteriorated solubles. After that, by performing the same measurement as the method for measuring the amount of soluble contents, the amount of deteriorated solubles was obtained (% by weight).

[0256]

Meanwhile, because the amount of deteriorated solubles is affected by moisture content, in the embodiment of the present invention the evaluation was made by using a value corrected for moisture content.

5 [0257]

(h) Increased amount of deteriorated solubles

The increased amount of deteriorated solubles in the particulate water-absorbing agent of the embodiment of the present invention is obtained by using Formula (2).

10 [0258]

[Mathematical 14]

Increased amount of deteriorated solubles (% by weight) = (Amount of 1 hour-solubles in deterioration test solution) - (Amount of 1 hour-solubles in physiological saline) ... (2)

[0259]

Meanwhile, the "increased amount of deteriorated solubles" is an index for evaluating the gel stability, and it means the amount of soluble contents which increases in accordance with deterioration of a particulate water-absorbing agent.

15

[0260]

(i) Evaluation of coloration of particulate water-absorbing agent (Hunter Lab color values/L, a, b values)

20

Coloration of the particulate water-absorbing agent was evaluated by LabScan (registered trademark) XE manufactured by

HunterLab. A reflection measurement was selected as a preset condition of measurement, and a container for powder and paste sample having internal diameter of 30 mm and height of 12 mm was used. Further, a standard round white plate No. 2 for powder
5 paste was used as a standard and 30Φ light-transmitting pipe was used. About 5 g of a particulate water-absorbing agent was provided in the built-in sample container so as to occupy about 60% of the built-in sample container. Then, an L value (Lightness: lightness index) on a surface was measured by the
10 spectrophotometric colorimeter at room temperature (20 to 25°C) and humidity of 50 RH %. This value indicates "lightness index before exposure". The higher index value indicates a color close to white.

[0261]

15 Furthermore, by using the same device and the same measurement method, values of a and b (color) as an article color based on other scale can also be measured. Smaller values of a and b indicate low coloration, that is, a color substantially close to white color. The result of evaluating coloration of a
20 particulate water-absorbing agent immediately after the production, or a particulate water-absorbing agent after storage for 1 year or less in an atmosphere at temperature of 30°C or lower and relative humidity of 50 RH % or less corresponds to the initial color.

25 [0262]

Subsequently, after filling the container for paste sample with about 5 g of a particulate water-absorbing agent, the container for paste sample filled with a particulate water-absorbing agent was exposed for 7 days in a constant
5 temperature and constant humidity chamber (small-size environmental testing machine manufactured by Espec Corp.; Model SH-641) that had been adjusted to an atmosphere at a temperature of $70 \pm 1^{\circ}\text{C}$ and relative humidity of $65 \pm 1 \text{ RH } \%$. This exposure corresponds to the coloration acceleration test for 7 days. After
10 the exposure, values of L, a, b on a surface were measured by using the aforementioned spectrophotometric colorimeter. The resulting measurement value was used as coloration over the time after acceleration test.

[0263]

15 (j) Malodor test

One part by weight of a particulate water-absorbing agent was added to a 100 ml beaker. After adding 20 parts by weight of 0.9% by weight aqueous solution of sodium chloride, the beaker was sealed with a film and allowed to stand for 1 hour at 37°C .
20 After that, the malodor sensory test was performed with 10 adult subjects. With regard to the evaluation method, when there is no unpleasant malodor so that the odor is determined to be acceptable for use in a hygienic material like diaper, it was evaluated as O. When there is unpleasant malodor so that the odor
25 is determined to be unacceptable for use in a hygienic material

like diaper, it was evaluated as x. Particularly strong malodor was evaluated as xx.

[0264]

(k) Blocking ratio after moisture absorption

5 In an aluminum cup having a bottom surface diameter of about 52 mm and a height of 22 mm, 2 g of a particulate water-absorbing agent was evenly scattered on the bottom and quickly transferred to a constant-temperature and constant-humidity incubator which has been adjusted in advance to 25°C and relative humidity of 90%
10 (PLATIOOUS LUCIFER PL-2G manufactured by Tabai Espec Corp. Inc.), and it was allowed to stand for 60 minutes. After that, the water-absorbing agent after moisture absorption was transferred to a JIS standardized sieve with diameter of 7.5 cm and opening size of 2000 μm . At that time, when the water-absorbing agent
15 after moisture absorption is strongly fixed onto the aluminum cup so that it cannot be transferred to a sieve, the water-absorbing agent which absorbs moisture and is in blocking state is carefully peeled off so as not to disrupt it as much as possible, and then transferred to a sieve. It was directly sieved for 8 seconds by
20 using a vibration classifying device (IIDA SIEVE SHAKER, TYPE: ES-65, SER. No. 0501), and the weight of the water-absorbing agent remained on top of the sieve (W_o (g)) and the weight of the water-absorbing agent passed through the sieve (W_p (g)) were measured. According to the following calculation formula, the
25 blocking ratio after moisture absorption (% by weight) was calculated. Smaller blocking ratio after moisture absorption

indicates better moisture absorption fluidity and more improved powder handleability.

[0265]

[Mathematical 15]

Blocking ratio after moisture absorption (% by weight) = {Weight Wo (g)/(Weight Wo (g) + Weight Wp (g))} × 100

5 [0266]

(1) SFC (Saline flow conductivity)

SFC (Saline flow conductivity) of the water-absorbing resin of the embodiment of the present invention was measured according to the measurement method described in the U.S. Patent No.

10 5,669,894.

[0267]

[Preparation Example 1]

To 5500 g (monomer concentration of 38% by weight) of an aqueous sodium acrylate solution with neutralization rate of 75
15 mol% in which acrylic acid containing p-methoxyphenol at 70 ppm was neutralized with an aqueous solution of sodium hydroxide, 2.5 g of polyethylene glycol diacrylate (average molecular weight of 523) was dissolved as an internal crosslinking agent to give an aqueous monomer solution (1).

20 [0268]

Next, to a reactor formed by adding a cover to a stainless steel kneader equipped with double-arm type jacket having two sigma-shaped blades (internal volume of 10 L), the above aqueous monomer solution (1) was introduced, and nitrogen gas was blown
5 into the reactor to replace the inside of the system with nitrogen while maintaining the liquid temperature at 30°C.

[0269]

Subsequently, while stirring the above aqueous monomer solution (1), 14.2 g of 20% by weight aqueous solution of sodium
10 persulfate and 2.4 g of 1% by weight aqueous solution of L-ascorbic acid were added separately as a polymerization initiator. As a result, after about 1 minute, the polymerization reaction was initiated.

[0270]

15 The polymerization was performed while crushing the produced hydrogel forming crosslinked polymer (hereinafter referred to as "hydrogel") (1), and the polymerization peak temperature of 90°C was exhibited after lapse of 15 minutes. After 60 minutes from the start of the polymerization, the hydrogel (1) was extracted.
20 Meanwhile, the obtained hydrogel (1) was found to be finely crushed to have particle diameter of 1 to 4 mm.

[0271]

Next, the finely crushed hydrogel (1) was spread on a wire mesh with opening size of 300 μm (50 mesh), and then dried with
25 hot air at 180°C for 45 minutes. Subsequently, pulverization was

carried out by using a roll mill, and classification was performed with JIS standardized sieves with opening size of 850 μm or 150 μm . According to this series of operations, the water-absorbing resin powder (1) in amorphous and crushed form of which particle diameter is 150 μm or more but less than 850 μm was obtained. The solids content in the water-absorbing resin powder (1) was 96% by weight.

[0272]

Subsequently, by homogeneously mixing 100 parts by weight of the water-absorbing resin powder (1) with 3.52 parts by weight of a surface crosslinking agent solution containing 0.02 parts by weight of ethylene glycol diglycidyl ether, 0.5 parts by weight of propylene glycol, 2.7 parts by weight of ion exchange water, and 0.3 parts by weight of 1,4-butane diol and heating them for 40 minutes at 164°C, the water-absorbing resin particle (1) with crosslinked surface was obtained. A weight average particle diameter (D50) of the water-absorbing resin particle (1) was 446 μm .

[0273]

[Example 1]

A mixed solution containing 0.1 part by weight of diethylene triamine pentaacetic acid·trisodium and 1 part by weight of ion exchange water was added dropwise to 100 parts by weight of the water-absorbing resin particle (1) which was obtained in Preparation Example 1 followed by homogenous mixing. After that,

as a result of keeping it for 60 minutes in a hot air dryer at 60°C, a granulate product in which several particles are aggregated (hereinbelow, it is referred to as a "water-absorbing resin granulate" for the sake of convenience) was obtained. The weight
5 average particle diameter (D50) of the water-absorbing resin granulate (1) of Example 1 was 477 μm (1.07 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)).

[0274]

10 Next, 30 g of the above water-absorbing resin granulate (1) and 10 g of glass beads with diameter of 6 mm were added to a glass container (diameter of 6 cm, and height of 11 cm), and the water-absorbing resin granulate (1) was disintegrated by using a paint shaker (product No. 488/Toyo Seiki Seisaku-Sho, Ltd.).
15 Meanwhile, the disintegration was performed by shaking the paint shaker for 30 minutes at 800 (cycle/min) (CPM). Details of the paint shaker are disclosed in JP No. 9-235378 A.

[0275]

20 After the shaking, by removing the glass beads using a JIS standardized sieve with opening size of 2 mm, a particulate water-absorbing agent (1) was obtained. The weight average particle diameter (D50) of the particulate water-absorbing agent (1) was 430 μm (0.90 time the weight average particle diameter (D50) of the water-absorbing resin granulate (1), and 0.96 time
25 the weight average particle diameter (D50) of the water-absorbing

resin particle (1)). Meanwhile, properties like moisture content were shown in Table 1.

[0276]

Furthermore, in the above particulate water-absorbing agent
5 (1), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of
10 deteriorated solubles in the entire particulate water-absorbing agent (1) was 27.2% by weight.

[0277]

[Example 2]

Except that the amount of diethylene triamine pentaacetic
15 acid · trisodium that was used was changed to 0.05 parts by weight, the same operations as in Example 1 (granulation using 1.05 parts by weight of aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a particulate water-absorbing agent (2).

20 [0278]

The weight average particle diameter (D50) of the water-absorbing resin granulate (2) after the addition of a chelating agent was 480 μm (1.08 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)), and
25 the weight average particle diameter (D50) of the particulate

water-absorbing agent (2) was 431 μm (0.90 time the weight average particle diameter (D50) of the water-absorbing resin granulate (2), and 0.97 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)). Meanwhile, physical
5 properties like moisture content are shown in Table 1.

[0279]

Furthermore, in the above particulate water-absorbing agent (2), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified
10 by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (2) was 27.5% by weight.

15 [0280]

[Example 3]

Except that the amount of diethylene triamine pentaacetic acid trisodium that was used was changed to 0.003 parts by weight, the same operations as in Example 1 (granulation using 1.003 parts
20 by weight of aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain the particulate water-absorbing agent (3).

[0281]

The weight average particle diameter (D50) of the
25 water-absorbing resin granulate (3) after the addition of a

chelating agent was 479 μm (1.07 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)), and the weight average particle diameter (D50) of the particulate water-absorbing agent (3) was 426 μm (0.89 time the weight average
5 particle diameter (D50) of the water-absorbing resin granulate (3), and 0.96 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0282]

10 Furthermore, in the above particulate water-absorbing agent (3), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle
15 distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (3) was 30.6% by weight.

[0283]

[Comparative Example 1]

20 Except that the paint shaker of Example 3 is not used, the same operations as in Example 3 (granulation using 1.003 parts by weight of aqueous solution of chelating agent) were performed to obtain a comparative particulate water-absorbing agent (1).

[0284]

The weight average particle diameter (D50) of the comparative water-absorbing resin granulate (1) after the addition of a chelating agent was 479 μm (1.07 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)), and the weight average particle diameter (D50) of the comparative particulate water-absorbing agent (3) was also 479 μm (1.0 time the weight average particle diameter (D50) of the comparative water-absorbing resin granulate (1), and 1.07 times the weight average particle diameter (D50) of the water-absorbing resin particle (1)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0285]

Furthermore, in the above comparative particulate water-absorbing agent (1), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire comparative particulate water-absorbing agent (1) was 30.9% by weight.

[0286]

[Comparative Example 2]

Except that the amount of diethylene triamine pentaacetic acid·trisodium of Comparative Example 1 that was used was changed

to 0.002 parts by weight, the same operations as in Comparative Example 1 (granulation using 1.002 parts by weight of aqueous solution of chelating agent) were performed to obtain a comparative particulate water-absorbing agent (2).

5 [0287]

The weight average particle diameter (D50) of the comparative water-absorbing resin granulate (2) after the addition of a chelating agent was 479 μm (1.07 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)), and the weight average particle diameter (D50) of the comparative particulate water-absorbing agent (2) was also 479 μm (1.0 time the weight average particle diameter (D50) of the comparative water-absorbing resin granulate (2), and 1.07 time the weight average particle diameter (D50) of the water-absorbing resin particle (1)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0288]

Furthermore, in the above comparative particulate water-absorbing agent (2), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire comparative particulate water-absorbing agent (2) was 51.4% by weight.

[0289]

[Example 4]

The water-absorbing resin particle (1) obtained from Preparation Example 1 was classified by using a JIS standardized
5 sieve with opening size of 300 μm , and divided into a portion remained on the sieve (hereinbelow, described as "water-absorbing resin particle (1-on)") and a portion passed through the sieve (hereinbelow, described as "water-absorbing resin particle (1-pass)"). Meanwhile, the particle size distribution of the
10 water-absorbing resin particle (1-on) was 300 μm or more but less than 850 μm and the particle size distribution of the water-absorbing resin particle (1-pass) was less than 300 μm .

[0290]

Next, to 100 parts by weight of the water-absorbing resin
15 particle (1-on), a mixed solution containing 0.01 parts by weight of diethylene triamine pentaacetic acid·trisodium and 1 part by weight of ion exchange water was added dropwise followed by homogenous mixing. To 100 parts by weight of the water-absorbing resin particle (1-pass), a mixed solution containing 0.025 parts
20 by weight of diethylene triamine pentaacetic acid·trisodium and 1 part by weight of ion exchange water was added dropwise followed by homogenous mixing.

[0291]

Subsequently, the mixture was allowed to stand for 60 minutes
25 in a hot air dryer at 60°C followed by re-mixing. According to

this series of the operations, a particulate water-absorbing agent (4) was obtained. Meanwhile, physical properties like moisture content are shown in Table 1.

[0292]

5 Furthermore, in the above particulate water-absorbing agent (4), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 99.3% by weight. The amount of deteriorated solubles for different particle sizes and particle
10 distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the particulate water-absorbing agent (4) was 28.8% by weight.

[0293]

[Preparation Example 2]

15 To a polypropylene container covered with foamed styrol as an insulating material (volume: 1 L), 291 g of acrylic acid, 0.63 g of polyethylene glycol diacrylate (average molecular weight of 523) as an internal crosslinking agent, 1.80 g of 1.0% by weight aqueous solution of diethylene triamine pentaacetic
20 acid·trisodium, and 3.60 g of 1.0% by weight acrylic acid solution of IRGACURE (registered trademark) 184 were added to prepare a mixture solution (a).

[0294]

Furthermore, to a separate polypropylene container covered
25 with foamed styrol as an insulating material (volume: 1 L), 247

g of 48.5% by weight aqueous solution of sodium hydroxide and 255 g of ion exchange water adjusted to 50°C were added to prepared a mixture solution (b).

[0295]

5 While stirring the mixture solution (a) at 800 rpm using a magnetic stirrer (length of 5 cm), the mixture solution (b) was quickly added and mixed to obtain an aqueous monomer solution (2). According to neutralization heat and dissolution heat, the aqueous monomer solution (2) was heated to have liquid temperature of about
10 100°C. Meanwhile, the rate of neutralization of acrylic acid was 73.5 mol%. Furthermore, the amount of diethylene triamine pentaacetic acid·trisodium (chelating agent) was 0.005% by weight (50 ppm) relative to the monomer solids content.

[0296]

15 Subsequently, by adding 1.8 g of 3% by weight aqueous solution of sodium persulfate as a polymerization initiator to the aqueous monomer solution (2), a reaction solution (2) was prepared.

[0297]

20 The above reaction solution (2) was stirred for about 1 second, and immediately injected to a stainless vat type reaction apparatus (bottom surface; 340 × 340 mm, height; 25 mm, inner surface; coated with Teflon (registered trademark)) in an open air system. Furthermore, according to simultaneous irradiation of ultraviolet rays, the polymerization reaction was initiated

about 10 seconds later. Within one minute thereafter, a peak temperature was shown.

[0298]

When three minutes were passed after start of the
5 polymerization reaction, the ultraviolet ray irradiation was terminated and the hydrogel forming crosslinked polymer (hereinafter referred to as "hydrogel") (2) was extracted. Meanwhile, the above series of the operations was performed in an open air system.

10 [0299]

Subsequently, the hydrogel (2) was subjected to gel-crushing by using a meat chopper (MEAT-CHOPPER TYPE 12VR-400KSOX; die pore diameter: 6.4 mm, number of pores: 38, die thickness: 8 mm/ manufactured by Iizuka Kogyo Co., Ltd.) to obtain a finely crushed
15 hydrogel (2).

[0300]

Next, the finely crushed hydrogel (2) was spread on a wire mesh with opening size of 300 μm (50 mesh), and then dried with hot air at 180°C for 45 minutes. Subsequently, pulverization was
20 carried out by using a roll mill, and classification was performed with JIS standardized sieves with opening size of 850 μm or 150 μm . According to this series of operations, a water-absorbing resin powder (2) in amorphous and crushed form of which particle diameter is 150 μm or more but less than 850 μm was obtained. The

solids content in the water-absorbing resin powder (2) was 97% by weight.

[0301]

Subsequently, by homogeneously mixing 100 parts by weight
5 of the water-absorbing resin powder (2) with 3.52 parts by weight
of a surface crosslinking agent solution containing 0.02 parts
by weight of ethylene glycol diglycidyl ether, 0.5 parts by weight
of propylene glycol, 2.7 parts by weight of ion exchange water,
and 0.3 parts by weight of 1,4-butane diol and heating them for
10 40 minutes at 195°C and classification using a JIS standardized
sieve with opening size of 850 μm , a surfaced crosslinked
water-absorbing resin particle (2) was obtained. The
water-absorbing resin particle (2) has a weight average particle
diameter (D50) of 367 μm .

15 [0302]

Initial color and color with the lapse of time were measured
for the water-absorbing resin particle (2) which was obtained
according to the above operations. The results are shown in Table
2.

20 [0303]

[Example 5]

Except that water-absorbing resin particle (1) (without
chelating agent) of Example 1 was changed to the water-absorbing
resin particle (2) (chelating agent was added at 50 ppm during
25 polymerization), the same operations as in Example 1 (granulation

using 1.1 parts by weight of aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a particulate water-absorbing agent (5).

[0304]

5 The weight average particle diameter (D50) of the water-absorbing resin granulate (5) after the addition of a chelating agent was 376 μm (1.02 times the weight average particle diameter (D50) of the water-absorbing resin particle (2)), and the weight average particle diameter (D50) of the particulate
10 water-absorbing agent (5) was 347 μm (0.92 time the weight average particle diameter (D50) of the water-absorbing resin granulate (5), and 0.95 time the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like moisture content are shown in Table 1.

15 [0305]

 Furthermore, in the above particulate water-absorbing agent (5), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 97.8% by weight. The amount of
20 deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (5) was 21.3% by weight. Furthermore, initial color and color with the lapse of time were measured for particulate
25 water-absorbing agent (5). The results are shown in Table 2.

[0306]

[Example 6]

Except for having an additional operation in which 1.5 parts by weight of 10% by weight aqueous solution of hydrogen sulfite
5 was added dropwise as an inorganic reducing agent to 100 parts by weight of the water-absorbing resin granulate (5) after addition of a chelating agent followed by homogeneous mixing, the same operations as in Example 5 (disintegration using a paint shaker, and removal of glass beads) were performed to obtain a
10 particulate water-absorbing agent (6).

[0307]

The weight average particle diameter (D50) of the water-absorbing resin granulate (6) after the addition of a chelating agent and an inorganic reducing agent was 380 μm (1.04
15 times the weight average particle diameter (D50) of the water-absorbing resin particle (2)), and the weight average particle diameter (D50) of the particulate water-absorbing agent (6) was 345 μm (0.91 time the weight average particle diameter (D50) of the water-absorbing resin granulate (6), and 0.94 time
20 the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0308]

Furthermore, in the above particulate water-absorbing agent
25 (6), the ratio of particles with particle diameter 150 μm or more

but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are described in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (6) was 21.0% by weight. Furthermore, initial color and color with the lapse of time were measured for particulate water-absorbing agent (6). The results are shown in Table 2.

[0309]

Meanwhile, the reducing agent content for different particle sizes ($B1/B2 = 2.02$) was also within a preferred range. Herein, amongst the particles constituting the particulate absorbing agent (6), B1 indicates a reducing agent content (ppm) which is present in particles with a particle diameter of less than 300 μm , in which the particle diameter is specified by a JIS standardized sieve, and B2 indicates a reducing agent content (ppm) which is present in particles with a particle diameter of 300 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve. The reducing agent content was measured by, after extracting it from a particulate water-absorbing agent with physiological saline, HPLC by using the method described in Chem. Pharm. Bull. Vol. 29, P. 3755-3757 (1987).

[0310]

[Example 7]

By dry mixing of 0.3 part by weight of silicon dioxide (Aerosil 200; Aerosil Japan) as water insoluble inorganic fine particles with 100 parts by weight of the particulate water-absorbing agent (5) obtained from Example 5, a particulate
5 water-absorbing agent (7) was obtained.

[0311]

The weight average particle diameter (D50) of the particulate water-absorbing agent (7) was 346 μm (0.92 time the weight average particle diameter (D50) of the water-absorbing
10 resin granulate (5), and 0.94 time the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0312]

15 Furthermore, in the above particulate water-absorbing agent (7), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle
20 distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (7) was 21.3% by weight. Furthermore, the particulate water-absorbing agent (7) was confirmed to have an improved blocking ratio after moisture absorption (Example 5; 100% by
25 weight $\rightarrow$ Example 7; 0% by weight).

[0313]

Meanwhile, the silicon dioxide content for different particle sizes was 2.01 (= B1/B2) for the particulate water-absorbing agent (7). The silicon dioxide content was
5 measured by, after extracting it from a particulate water-absorbing agent, molybdenum blue spectrophotometric method.

[0314]

[Example 8]

10 Except for having, in Example 5, an additional operation in which 1.0 part by weight of 15% by weight aqueous solution of camellia leaf extract (FS-89MO manufactured by SHIRAIMATSU PHARMACEUTICAL Co., LTD) was added dropwise as a water soluble
15 resin granulate (5) after addition of a chelating agent followed by homogeneous mixing, the same operations as in Example 5 (disintegration using a paint shaker, and removal of glass beads) were performed to obtain a particulate water-absorbing agent (8).

[0315]

20 The weight average particle diameter (D50) of the water-absorbing resin granulate (8) after the addition of a chelating agent and a water insoluble deodorizing agent was 379 μm (1.03 times the weight average particle diameter (D50) of the water-absorbing resin particle (2)), and the weight average
25 particle diameter (D50) of the particulate water-absorbing agent

(8) was 345 μm (0.91 time the weight average particle diameter (D50) of the water-absorbing resin granulate (8), and 0.94 time the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like
5 moisture content are shown in Table 1.

[0316]

Furthermore, in the above particulate water-absorbing agent (8), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified
10 by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (8) was 20.9% by weight.

15 [0317]

Furthermore, improved deodorizing property was confirmed for the particulate water-absorbing agent (8). Namely, the result of the malodor test was "x" in Example 5, but it was improved in Example 8 showing "O."

20 [0318]

[Example 9]

Except having, in Example 5, an additional operation in which 1.2 parts by weight of aluminum sulfate mixed solution containing 1.0 part by weight of 27% by weight aqueous solution of aluminum
25 sulfate, 0.3 part by weight of 60% by weight aqueous solution of

sodium lactate and 0.025 part by weight of polypropylene glycol was added dropwise to 100 parts by weight of the water-absorbing resin granulate (5) after addition of a chelating agent followed by homogeneous mixing, the same operations as in Example 5 (disintegration using a paint shaker, and removal of glass beads) were performed to obtain a particulate water-absorbing agent (9).

[0319]

The weight average particle diameter (D50) of the water-absorbing resin granulate (9) after the addition of a chelating agent and a polyvalent metal salt was 380 μm (1.04 times the weight average particle diameter (D50) of the aqueous resin particle (2)), and the weight average particle diameter (D50) of the particulate water-absorbing agent (9) was 345 μm (0.91 time the weight average particle diameter (D50) of the water-absorbing resin granulate (9), and 0.94 time the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0320]

Furthermore, in the above particulate water-absorbing agent (9), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of

deteriorated solubles in the entire particulate water-absorbing agent (9) was 18.9% by weight.

[0321]

Furthermore, the aluminum content for different particle sizes was 2.03 (= B1/B2) for the particulate water-absorbing agent (9), and an improved SFC (Example 5; 0 → Example 9; 10) and an improved blocking ratio after moisture absorption (Example 5; 100% by weight → Example 9; 0% by weight) were confirmed. Meanwhile, the aluminum content was measured based on "(G) Extraction rate of polyvalent metal components (% by weight), method for quantifying polyvalent metal components contained in water-absorbing resin" which is disclosed in the U.S. 7,960,269.

[0322]

[Example 10]

To 100 parts by weight of the water-absorbing resin particle (2) obtained from Preparation Example 2, a mixed solution containing 0.1 part by weight of diethylene triamine pentaacetic acid·trisodium, 0.05 part by weight of propylene glycol, and 1.5 parts by weight of ion exchange water was added dropwise followed by homogenous mixing. Next, the same operations as in Example 1 (granulation using 1.1 parts by weight aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a water-absorbing resin granulate (10) and a particulate water-absorbing agent (10).

[0323]

The weight average particle diameter (D50) of the water-absorbing resin granulate (10) after the addition of a chelating agent and polyol was 376 μm (1.02 times the weight average particle diameter (D50) of the aqueous resin particle (2)), and
5 the weight average particle diameter (D50) of the particulate water-absorbing agent (10) was 347 μm (0.92 time the weight average particle diameter (D50) of the water-absorbing resin granulate (8), and 0.95 time the weight average particle diameter (D50) of the water-absorbing resin agent (2)). Meanwhile, physical
10 properties like moisture content are shown in Table 1.

[0324]

Furthermore, in the above particulate water-absorbing agent (10), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified
15 by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (10) was 19.3% by weight.

20 [0325]

[Example 11]

To 100 parts by weight of the water-absorbing resin particle (2) obtained from Preparation Example 2, a mixed solution containing 0.1 part by weight of triethylene tetraamine hexaacetic
25 acid and 1 part by weight of 1 N aqueous solution of sodium hydroxide

was added dropwise followed by homogenous mixing. Next, the same operations as in Example 1 (granulation using 1.1 parts by weight aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a
5 water-absorbing resin granulate (11) and a particulate water-absorbing agent (11).

[0326]

The weight average particle diameter (D50) of the water-absorbing resin granulate (11) after the addition of a
10 chelating agent was 380 μm (1.04 times the weight average particle diameter (D50) of the aqueous resin particle (2)), and the weight average particle diameter (D50) of the particulate water-absorbing agent (11) was 345 μm (0.91 time the weight average particle diameter (D50) of the water-absorbing resin granulate
15 (11), and 0.94 time the weight average particle diameter (D50) of the water-absorbing resin particle (2)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0327]

Furthermore, in the above particulate water-absorbing agent
20 (11), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 97.8% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of
25 deteriorated solubles in the entire particulate water-absorbing agent (11) was 17.8% by weight.

[0328]

[Preparation Example 3]

Except that the amount of ethylene glycol diglycidyl ether that was used was changed to 0.024 parts by weight relative to
5 100 parts by weight of the water-absorbing resin powder (2) and also the heating treatment was performed for 40 minutes at 176°C, the same operations as in Preparation Example 2 were performed to obtain a particulate water-absorbing agent (3). The weight average particle diameter (D50) of the water-absorbing resin
10 particle (3) was 355 μm .

[0329]

[Example 12]

Except that the water-absorbing resin particle (1) of Example 1 was changed to the water-absorbing resin particle (3),
15 the same operations as in Example 1 (granulation using 1.1 parts by weight aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a water-absorbing resin granulate (12). By dry mixing of 0.3 part by weight of silicon dioxide (Aerosil 200; Aerosil
20 Japan) as water insoluble inorganic fine particles with 100 parts by weight of the obtained particulate water absorbent granulate (12), a particulate water-absorbing agent (12) was obtained.

[0330]

The weight average particle diameter (D50) of the
25 water-absorbing resin granulate (12) after the addition of a

chelating agent was 370 μm (1.04 times the weight average particle diameter (D50) of the aqueous resin particle (3)), and the weight average particle diameter (D50) of the particulate water-absorbing agent (12) was 340 μm (0.92 time the weight average particle diameter (D50) of the water-absorbing resin granulate (12), and 0.96 time the weight average particle diameter (D50) of the water-absorbing resin particle (3)). Meanwhile, physical properties like moisture content are shown in Table 1.

[0331]

Furthermore, in the above particulate water-absorbing agent (12), the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is specified by a JIS standardized sieve, was 98.5% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate water-absorbing agent (12) was 22.1% by weight. Furthermore, the particulate water-absorbing agent (12) was confirmed to have an improved blocking ratio after moisture absorption (Example 1; 100% by weight $\rightarrow$ Example 12; 0% by weight).

[0332]

[Preparation Example 4]

In Preparation Example 2, except for homogeneously mixing 100 parts by weight of the water-absorbing resin powder (2) with a surface crosslinking agent solution containing 0.024 part by

weight of ethylene glycol diglycidyl ether, 0.52 part by weight of propylene glycol, 2.1 parts by weight of ion exchange water, and 0.31 part by weight of ethylene carbonate and heating the mixture for 40 minutes at 176°C, a water-absorbing resin particle (4) was obtained according to the same operations as in Preparation Example 2. The water-absorbing resin particle (4) has a weight average particle diameter (D50) of 356 μm .

[0333]

[Example 13]

Except that the water-absorbing resin particle (1) of Example 1 was changed to the water-absorbing resin particle (4), the same operations as in Example 1 (granulation using 1.1 parts by weight aqueous solution of chelating agent, disintegration using a paint shaker, and removal of glass beads) were performed to obtain a water-absorbing resin granulate (13). By dry mixing of 0.3 part by weight of silicon dioxide (Aerosil 200; Aerosil Japan) as water insoluble inorganic fine particles with 100 parts by weight of the obtained particulate water absorbent granulate (13), a particulate water-absorbing agent (13) was obtained.

[0334]

The weight average particle diameter (D50) of the water-absorbing resin granulate (13) after the addition of a chelating agent was 374 μm (1.05 times the weight average particle diameter (D50) of the aqueous resin particle (4)), and the weight average particle diameter (D50) of the particulate

water-absorbing agent (13) was 340 μm (0.91 time the weight average particle diameter (D50) of the water-absorbing resin granulate (13), and 0.96 time the weight average particle diameter (D50) of the water-absorbing resin particle (4)). Meanwhile, physical
5 properties like moisture content are shown in Table 1.

[0335]

Furthermore, in the above particulate water-absorbing agent, the ratio of particles with particle diameter 150 μm or more but less than 850 μm , in which the particle diameter is
10 specified by a JIS standardized sieve, was 98.5% by weight. The amount of deteriorated solubles for different particle sizes and particle distribution are shown in Table 1. Meanwhile, the amount of deteriorated solubles in the entire particulate
water-absorbing agent (13) was 23.9% by weight. Furthermore, the
15 particulate water-absorbing agent (13) was confirmed to have an improved blocking ratio after moisture absorption (Example 1; 100% by weight $\rightarrow$ Example 13; 0% by weight).

[0336]

[Example 14]

20 Except that the chelating agent is changed to 0.1 parts by weight of ethylene diamine tetra(methylenephosphonic acid) (EDTMP) pentasodium, the same operations as in Example 1 (disintegration using a paint shaker, and removal of glass beads) were performed to obtain a particulate water-absorbing agent (14).

25 [0337]

Physical properties of the obtained particulate water-absorbing agent (14) were as follows. CRC; 45 (g/g), AAP; 27 (g/g), moisture content; 5.5% by weight, C1/C2; 2.73, an increased amount of deteriorated solubles; particles that are less than 300 μm : 11.1% by weight, particles that are 300 μm or more but less than 850 μm : 14.2% by weight.

[Comparative Example 3]

The water-absorbing resin particle (2) obtained from Preparation Example 2 (chelating agent is added at 0.005% by mass during polymerization (relative to monomer solids content)) was used as the comparative particulate water-absorbing agent (3).

[0338]

Physical properties of the obtained comparative particulate water-absorbing agent (3) are as follows. CRC; 39 (g/g), AAP; 29 (g/g), moisture content; 2.9% by weight, C1/C2; 1.05, an increased amount of deteriorated solubles; particles that are less than 300 μm : 17.2% by weight, particles that are 300 μm or more but less than 850 μm : 15.0% by weight.

[0339]

[Table 1]

	Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2	Example 4	Example 5	Example 6	Example 7	Example 8	Example 9	Example 10	Example 11	Example 12	Example 13
Water-absorbing resin particles D50	{1} 446	{1} 446	{1} 446	{1} 446	{1} 446	{1} 446	{2} 367	{2} 367	{2} 367	{2} 367	{2} 367	{2} 367	{2} 367	{3} 355	{4} 356
Chelating agent 1)	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	DTEA	TTHA	DTEA	DTEA
Water-absorbing resin granulate D50	{1} 477	{2} 480	{3} 479	Comparative Example (1) 479	Comparative Example (2) 479	-	{4} 376	{5} 380	{4} 376	{6} 379	{7} 380	{8} 376	{9} 380	{10} 370	{11} 374
Paint shaker	O	O	O	X	X	X	O	O	O	O	O	O	O	O	O
Particulate water-absorbing agent	{1}	{2}	{3}	Comparative Example (1)	Comparative Example (2)	{4}	{5}	{6}	{7}	{8}	{9}	{10}	{11}	{12}	{13}
D50	430	431	426	479	479	-	347	345	346	345	345	347	345	340	340
CRC	45	45	45	45	45	45	36	36	36	36	36	36	36	39	41
RAI	27	27	27	27	27	27	33	33	30	33	33	33	33	29	27
Moisture content	5.6	5.3	5.4	5.5	5.5	5.4	4.1	5.4	4.1	5.1	5.0	4.4	4.1	4.0	4.1
SFC	-	-	-	-	-	-	0	-	-	-	1.0	-	-	-	-
Blocking ratio after moisture absorption	100	-	-	-	-	-	100	-	0	-	0	-	-	0	0
Content for different particle sizes															

Particle diameter 300 ↓ ²⁾	[wt%]	17	17	17	12	12	16	32	33	33	32	33	30	35	38	37
Particle diameter 300-850 ²⁾	[wt%]	83	83	83	88	88	84	68	67	67	68	67	70	65	62	63
Chelating agent content																
Particle diameter 300 ↓ ²⁾ (C1)	[ppm]	2471	1082	61	30	21	239	1650	1668	1688	1588	1544	1820	1714	1256	1454
Particle diameter 300-850 ²⁾ (C2)	[ppm]	891	399	27	31	21	93	830	832	840	721	765	733	706	753	803
CI/C2		2.77	2.71	2.26	0.97	1.00	2.57	1.99	2.00	2.01	2.20	2.02	2.48	2.43	1.67	1.81
Amount of soluble contents																
Particle diameter 300 ↓ ²⁾	[wt%]	15.7	16.3	17.7	18.0	18.2	18.0	10.2	9.9	10.4	10.5	10.8	10.1	8.9	12.5	14.2
Particle diameter 300-850 ²⁾	[wt%]	13.5	14.0	14.5	14.3	15.0	14.0	9.0	8.7	9.2	8.9	8.7	9.3	8.2	10.2	12.1
Amount of deteriorated solubles																
Total	[wt%]	27.2	27.5	30.6	30.9	51.4	28.8	21.3	21.0	21.3	20.9	18.9	19.3	17.8	22.1	23.9
Particle diameter 300 ↓ ²⁾	[wt%]	26.8	27.0	29.5	36.0	76.0	27.9	19.7	19.5	19.8	19.3	18.4	18.2	15.1	21.7	23.2
Particle diameter 300-850 ²⁾	[wt%]	27.3	27.6	30.8	30.2	48.0	29.0	22.0	21.8	22.1	21.6	19.1	19.7	19.2	22.4	24.3

[0340]

(Summary)

As shown in the above Table 1, by adjusting the chelating agent content depending on different particle sizes, a variation
5 in gel stability can be suppressed and also high water absorption performance can be obtained.

[0341]

Namely, as shown in Comparative Example 1, when the chelating agent amount (C1) contained in particles with the particle
10 diameter of less than 300 μm and the chelating agent amount (C2) contained in particles with the particle diameter of 300 μm or more but less than 850 μm are similar to each other (C1/C2 is about 1), the increased amount of deteriorated solubles in the particles with the particle diameter of 300 μm or more but less than 850
15 μm can be suppressed but the increased amount of deteriorated solubles in the particles with the particle diameter of less than 300 μm cannot be sufficiently suppressed.

[0342]

Furthermore, in Comparative Example 1, a difference between
20 the amount of deteriorated solubles in the particles with the particle diameter of less than 300 μm and the amount of deteriorated solubles in the particles with the particle diameter of 300 μm or more but less than 850 μm was high (5.8% by weight = 36.0 - 30.2). Thus, for example, due to a variation in particle size

of the particulate water-absorbing agent, the amount of deteriorated solubles is varied greatly.

[0343]

Meanwhile, it was found that, when the ratio of the above
5 C1 and C2 (C1/C2) is controlled to satisfy Formula (1) (Examples 1 to 5), there was no influence of the particle diameter and thus excellent gel stability is exhibited.

[0344]

[Mathematical 16]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

10 [0345]

Namely, in Example 3, a difference between the amount of deteriorated solubles in the particles with the particle diameter of less than 300 μm and the amount of deteriorated solubles in the particles with the particle diameter of 300 μm or more but
15 less than 850 μm was small (1.3% by weight = 30.8 - 29.5) even when the chelating agent amount was the same as that in Comparative Example 1 (chelating agent: 0.003 part by weight), and thus a variation in the amount of deteriorated solubles in the particulate water-absorbing agent was small. It was also found
20 that the amount of deteriorated solubles in the entire water-absorbing agent was improved in Example 3 as compared to Comparative Example 1 (Example 3; 30.6% by weight, Comparative Example 1; 30.9% by weight).

[0346]

When Examples 1 to 3 and 5 to 13 are compared to Comparative Examples 1 and 2, it was found that, according to disintegration of the water-absorbing resin granulate, which has been in
5 granulate form due to aggregation of particles, with a paint shaker, a water-absorbing agent having good water absorption performance including high gel stability and little variation in gel stability amongst different particle sizes can be obtained more efficiently.

10 [0347]

Furthermore, when Comparative Example 1 (0.003 parts by weight of chelating agent) is compared to Comparative Example 2 (0.002 parts by weight of chelating agent), and Example 1 (0.1 parts by weight of chelating agent), Example 2 (0.05 parts by weight
15 of chelating agent), and Example 3 (0.003 parts by weight of chelating agent) are compared to one another, it was found that, as the chelating agent amount is increased to a predetermined amount or more, not only the amount of deteriorated solubles but also a difference between the amount of deteriorated solubles in
20 the particles with the particle diameter of less than 300 μm and the amount of deteriorated solubles in the particles with the particle diameter of 300 μm or more but less than 850 μm decreases.

[0348]

[Table 2]

25

	Chelating agent content	Reducing agent content	Initial color			Color with the lapse of time		
	[wt%]	[wt%]	L	a	b	L	a	b
Water-absorbing resin particle (2)	0	0	90.09	-0.02	6.76	68.80	4.09	14.52
Particulate water-absorbing agent (5)	0.1	0	90.04	-0.06	6.74	73.68	3.20	12.75
Particulate water-absorbing agent (6)	0.1	0.15	90.39	-0.42	6.52	82.89	0.99	8.61

[0349]

(Summary)

With the particulate water-absorbing agent (6), coloration was improved compared to Preparation Example 2 (without any additives) or the particulate water-absorbing agent (5) (only with chelating agent).

Industrial Applicability

[0350]

The particulate water-absorbing agent of the present invention is preferably applied to a use in which a dehydrating property and a water-retaining property are required, that is, a water-absorbing agent of a hygienic material like disposable diaper and sanitary napkin, a water-retaining agent for medical use, a water-retaining agent for agricultural and horticultural use, and other various industrial dehydrating agents or the like.

CLAIMS

1. A particulate water-absorbing agent comprising a water-absorbing resin as a main component and a chelating agent,

5 wherein a ratio of particles with a particle diameter of 150 μm or more but less than 850 μm , as specified by a Japanese Industrial Standard (JIS) standardized sieve, is 90% by weight or more,

wherein the water-absorbing agent contains particles with
10 a particle diameter of less than 300 μm and particles with a particle diameter of 300 μm or more but less than 850 μm , as specified by a Japanese Industrial Standard (JIS) standardized sieve, in the weight ratio of 70:30 to 10:90,

wherein an amount of the chelating agent included is 0.02
15 to 1 part by weight per 100 parts by weight of a water-absorbing resin in solid and satisfies Formula (1):

[Mathematical 1]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

where, in the Formula (1), C1 indicates an amount (ppm) of the chelating agent present in the particles of a particle diameter
20 of less than 300 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent, and C2 indicates an amount (ppm) of the chelating agent present in the particles of a particle diameter of 300 μm or more

but less than 850 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent.

5 2. The particulate water-absorbing agent according to claim 1, wherein the amount of the chelating agent included is 0.03 to 0.9 part by weight per 100 parts by weight of the water-absorbing resin in solid.

10 3. The particulate water-absorbing agent according to claim 1 or 2, wherein:

1) an increased amount of deteriorated solubles having a particle diameter of less than 300 μm , as specified by a JIS standardized sieve, is 0 to 15% by weight, and

15 2) an increased amount of deteriorated solubles having a particle diameter of 300 μm or more but less than 850 μm , as specified by a JIS standardized sieve, is 0 to 20% by weight,

wherein the increased amount of deteriorated solubles is a value defined by the Formula (2):

20 [Mathematical 2]

Increased amount of deteriorated solubles (% by weight) = (Amount of 1 hour-solubles in deterioration test solution) - (Amount of 1 hour-solubles in physiological saline) ... (2)

where, in the Formula 2, the deterioration test solution means physiological saline to which 0.1% by weight of L-ascorbic acid is added.

5 4. The particulate water-absorbing agent according to any one
of claims 1 to 3, wherein: (the amount of deteriorated solubles
of particles with the particle diameter of less than 300 μm) -
(the amount of deteriorated solubles of particles with the
particle diameter of 300 μm or more but less than 850 μm)) is 5%
10 by weight or less.

5. The particulate water-absorbing agent according to any one
of claims 1 to 4, wherein an amount of solubles is 5 to 30% by
weight.

15

6. The particulate water-absorbing agent according to any one
of claims 1 to 5, wherein a coloration over the time (a value of
L, exposed for 7 days under an atmosphere at a temperature of 70
 $\pm 1^\circ\text{C}$ and relative humidity of $65 \pm 1 \text{ RH } \%$) is 80 or more.

20

7. The particulate water-absorbing agent according to any one
of claims 1 to 6, wherein the chelating agent is at least one
compound selected from the group consisting of: amino polyvalent
carboxylic acid, organic polyvalent phosphoric acid, inorganic

polyvalent phosphoric acid, amino polyvalent phosphoric acid and a tropolone derivative.

8. The particulate water-absorbing agent according to any one
5 of claims 1 to 7, wherein the chelating agent is diethylene triamine pentaacetic acid, triethylene tetraamine hexaacetic acid and those salts.

9. The particulate water-absorbing agent according to any one
10 of claims 1 to 8 further comprising an inorganic reducing agent.

10. The particulate water-absorbing agent according to claim 9, wherein the inorganic reducing agent contains a reductive sulfur atom.

15

11. The particulate water-absorbing agent according to any one of claims 1 to 10 further comprising water-insoluble inorganic fine particles.

20 12. The particulate water-absorbing agent according to any one of claims 1 to 11 further comprising a water-soluble deodorizing agent.

13. The particulate water-absorbing agent according to any one of claims 1 to 12 further comprising a polyvalent metal salt and/or a cationic polymer.

5 14. The particulate water-absorbing agent according to any one of claims 1 to 13 further comprising polyol.

15. The particulate water-absorbing agent according to any one of claims 1 to 14 further comprising an iron ion, wherein an amount
10 of the iron ion is 0.001 to 2 ppm.

16. The particulate water-absorbing agent according to any one of claims 1 to 15, wherein the particulate water-absorbing agent has: fluid retention capacity without pressure (CRC) including
15 moisture content correction to be 30 (g/g) or more against physiological saline, and fluid retention capacity under pressure at a pressure of 2.06 kPa (AAP) including moisture content correction to be 20 (g/g) or more against physiological saline.

20 17. The particulate water-absorbing agent according to any one of claims 1 to 16, wherein a moisture content obtained from an amount lost from drying at 180°C for 3 hours is 0.5 to 15% by weight.

18. A method for producing a particulate water-absorbing agent comprising a water-absorbing resin as a main component and a chelating agent, wherein a ratio of particles with a particle diameter of 150 μm or more but less than 850 μm , as specified by
5 a Japanese Industrial Standard (JIS) standardized sieve, is 90% by weight or more,

wherein the water-absorbing agent contains particles with a particle diameter of less than 300 μm and particles with a particle diameter of 300 μm or more but less than 850 μm , as
10 specified by a Japanese Industrial Standard (JIS) standardized sieve, in the weight ratio of 70:30 to 10:90,

wherein an amount of the chelating agent included is 0.02 to 1 part by weight per 100 parts by weight of a water-absorbing resin in solid,

15 wherein the method comprises

(a) steps of: classifying a surface-crosslinked water-absorbing resin into a plurality of different particle sizes; adding the chelating agent as per the plurality of the different particle sizes; and re-mixing a plurality of the
20 water-absorbing resins, to which said chelating agent was added, to obtain a particulate water-absorbing agent or

(b) steps of: adding the chelating agent to a surface-crosslinked water-absorbing resin to obtain water-absorbing resin granules, of which weight average particle
25 diameter (D50) is increased; and crushing the water-absorbing

resin granules and reducing the weight average particle diameter (D50) by 5% or more to obtain a particulate water-absorbing agent, and wherein the amount of the chelating agent included satisfies the Formula (1):

5 [Mathematical 3]

$$1.2 < C1/C2 < 4.0 \dots (1)$$

where, in the Formula (1), C1 indicates an amount (ppm) of the chelating agent present in the particles of a particle diameter of less than 300 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent, and C2 indicates an amount (ppm) of the chelating agent
10 present in the particles of a particle diameter of 300 μm or more but less than 850 μm , as specified by a JIS standardized sieve, amongst particle components for the particulate water-absorbing agent.

15

19. The method according to claim 18, wherein in the (b), the chelating agent is added during plural steps.

20. The method according to claim 18 or 19, wherein the chelating agent is added to a monomer or a hydrogel forming crosslinked
20 polymer and added to water-absorbing resin after drying.

21. The method according to claim 20, wherein the chelating agent is added to the monomer or hydrogel forming crosslinked polymer in an amount of 0 to 50% by mol relative to the whole amount added of the chelating agent.

5

22. The method according to any one of claims 18 to 21, wherein the chelating agent in a state of being dissolved and/or dispersed into a mixed solvent containing water and a hydrophilic organic solvent is added to the water-absorbing resin particles.

10

23. The method according to claim 22, wherein the hydrophilic organic solvent is polyol.

24. The method according to any one of claims 18 to 23, wherein
15 the chelating agent is at least one compound selected from the group consisting of: amino polyvalent carboxylic acid, organic polyvalent phosphoric acid, inorganic polyvalent phosphoric acid, amino polyvalent phosphoric acid and a tropolone derivative.

20 25. The method according to any one of claims 18 to 24, wherein the chelating agent is diethylene triamine pentaacetic acid, triethylene tetraamine hexaacetic acid and those salts.

26. An absorbent article comprising the particulate water-absorbing agent as set forth in any one of claims 1 to 17.

ABSTRACT

PARTICULATE WATER-ABSORBING AGENT CONTAINING WATER-ABSORBING
RESIN AS MAIN COMPONENT AND METHOD FOR PRODUCING THE SAME

[Objective] Provides is a water-absorbing agent which exhibits
5 high gel stability, little variation in gel stability amongst
different particle sizes and good water absorption
characteristics.

[Solving Means] Disclosed is a particulate water-absorbing agent
comprising a water-absorbing resin as a main component and a
10 chelating agent, the water-absorbing resin having particles with
a particle diameter of less than 300 μm and particles with a
particle diameter of 300 μm or more but less than 850 μm , as
specified by a JIS standardized sieve, wherein an amount of the
chelating agent is 0.001 to 5 parts by weight per 100 parts by
15 weight of a solids content of the water-absorbing resin and
satisfies Formula (1):

$$1.2 < C1/C2 < 4.0 \dots (1)$$