

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

CASE	TYPE OF MOTOR	JOINING STRUCTURE	KIND OF STEEL	SHEET THICKNESS mm	DIAMETER mm	CORE THICKNESS DEVIATION mm	AMPLITUDE AMOUNT AT 16000 rpm	EVALUATION
EXAMPLE 1	IPM	EPOXY ADHESIVE RESIN	25HX1300	0.25	166	0.04	150 μ m OR LESS	Excellent
EXAMPLE 2	IPM	CRIMPING PORTION	30HX1800	0.30	133	0.20	150 μ m OR LESS	Excellent
EXAMPLE 3	INDUCTION	EPOXY ADHESIVE RESIN	25HX1300	0.25	166	0.06	150 μ m OR LESS	Excellent
EXAMPLE 4	IPM	EPOXY ADHESIVE RESIN	20HTH1200	0.20	160	0.25	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
EXAMPLE 5	IPM	CRIMPING PORTION	35H210	0.35	133	0.25	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
EXAMPLE 6	INDUCTION	EPOXY ADHESIVE RESIN	27HX1400	0.27	163	0.25	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
COMPARATIVE EXAMPLE A	IPM	EPOXY ADHESIVE RESIN	25HX1300	0.25	163	0.28	MORE THAN 250 μ m	No Good
COMPARATIVE EXAMPLE B	IPM	CRIMPING PORTION	30HX1800	0.30	163	0.28	MORE THAN 250 μ m	No Good
COMPARATIVE EXAMPLE C	INDUCTION	EPOXY ADHESIVE RESIN	25HX1300	0.25	163	0.28	MORE THAN 250 μ m	No Good
EXAMPLE 7	IPM	EPOXY ADHESIVE RESIN	25HX1300	0.25	300	0.08	150 μ m OR LESS	Excellent
EXAMPLE 8	IPM	EPOXY ADHESIVE RESIN	27HX1400	0.27	330	0.14	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
EXAMPLE 9	IPM	EPOXY ADHESIVE RESIN	25HX1300 COLD-ROLLED	0.15	133	0.25	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
EXAMPLE 10	IPM	EPOXY ADHESIVE RESIN	25HX1300 COLD-ROLLED	0.12	133	0.25	MORE THAN 150 μ m AND 250 μ m OR LESS	Good
EXAMPLE 11	IPM	EPOXY ADHESIVE RESIN	25CS1250	0.25	133	0.09	150 μ m OR LESS	Excellent
EXAMPLE 12	IPM	ACRYLIC ADHESIVE RESIN	25HX1300	0.25	133	0.06	150 μ m OR LESS	Excellent