

A B S T R A C T

NONWOVEN FABRIC AND METHOD FOR MAKING SAME

A nonwoven fabric suitable to be used as a kitchen paper including thermoplastic synthetic fibers 3 being 7 ~ 30 mm long and as fine as of 0.1 ~ 0.8 d, in 90 ~ 10 % by weight and pulp fibers 4 being 2 ~ 7 mm long, in 10 ~ 90 % by weight, these component fibers being mixed together as homogeneously as possible and mechanically entangled so as to have a basis weight of 10 ~ 80 g/m² as a whole.

Refer to Fig. 2.