

PREPARATION OF COPOLYCARBONATES

ABSTRACT OF THE DISCLOSURE

A process for the preparation of transparent copolycarbonate is disclosed. The copolycarbonate the molecular structure of which contains more than 35 mole % of units derived from dihydroxydiphenylene is prepared by the melt transesterification process wherein the final temperature of the reaction is reached in less than 40 minutes after reaching the starting temperature.



162162



G00002