

ABSTRACT

A plurality of recesses having the same interval and array as those of pores of an alumina film, which are to be formed in anodizing, are formed on a smooth surface of an aluminum plate in advance, and
5 then, the aluminum plate is anodized. With this process, the roundness of the pores of the porous anodized alumina film and the uniformity of pore size are improved, and the pores are regularly arrayed at a predetermined interval.

10 The recesses are formed by pressing a substrate having a plurality of projections on its surface against the aluminum plate surface to be anodized.

4-322088

THIS SHEET HAS BEEN
REPLACED