

TITLE: FORMED SHEET MEMBRANE ELEMENT AND FILTRATION SYSTEM**FIELD**

[0001] This specification relates to devices for membrane separation and methods of making them, and in particular to microfiltration (MF), ultrafiltration (UF) or nanofiltration (NF) membrane elements or modules suitable for immersed, alternatively called submerged, operation.

BACKGROUND

[0002] The following is not an admission that anything discussed below is common general knowledge or citable as prior art.

10 [0003] Immersed MF or UF membranes may be made in a flat sheet, alternatively called plate and frame, configuration. In this configuration, a roll of membrane sheet is made by casting a polymeric separation layer cast onto a roll of non-woven substrate. Two generally rectangular pieces of membrane sheet are attached at their edges, for example by supersonic welding, onto opposing sides of hollow plastic frame. This creates a panel with a hollow interior channel to collect filtered water, alternatively called permeate. Several panels slide side by side into a frame that can be immersed in water to be filtered. The insides of the panels are connected to the suction side of a pump to draw permeate through the membrane sheets. Bubbles provided from below the frame cause a mixed flow of bubbles and liquid to rise through vertical slots between the panels to help clean the membrane surfaces. Examples of this type of device are shown in US Patent Numbers 5,482,625; 5,651,888; 5,772,831; 6,287,467; and, 6,843,908, all owned by Kubota Corporation.

25 [0004] Flat sheet membrane modules are generally robust and have a low manufacturing cost (relative to hollow fiber membranes) because they can be cast in a wide sheet. However, flat sheet membranes have poor packing densities (membrane surface area per unit volume of the module) relative to hollow fiber membranes and so the total cost of a large flat sheet plant can be very high. Further, typical flat sheet membrane panels cannot be backwashed vigorously enough to clean the membranes mechanically.

30

[0005] A variation of a flat sheet membrane element is shown in International Publication Number WO 2007/036332 to Microdyn-Nadir GMBH. In these elements, two layers of membrane material are cast onto the front and back sides of a fabric having a porous central area between two dense layers. The central area provides a permeate channel also connects the two dense layers together allowing the element to be backwashed for mechanical cleaning. These elements do not require a four-sided frame and they are about 2 mm thick, which is thinner than the plate and frame elements described above. However, these elements are also flexible and they are spaced apart by about 10 mm center to center in a frame. The packing density is better than for the plate and frame elements described above, but still much lower than a hollow fiber membrane module. The central area of the fabric, although porous, also provides a resistance against flow in the permeate channel and increases the cost of the element.

15 INTRODUCTION

[0006] The following introduction is intended to introduce the reader to the detailed description to follow and not to limit or define any claimed invention.

[0007] A piece of substrate material, for example a non-woven fabric, is formed under heat and pressure, for example against the inner surface of a mold cavity, into a shaped substrate sheet having one or more depressions, for example a series of generally parallel depressions, relative to a plane. Two substrate sheets, at least one of which has depressions, are bonded together, for example along or beside the edges of the depressions. Optionally, an additional intermediate sheet may be bonded between the two substrate sheets. The two substrate sheets form a substrate having a plurality of interior channels in combination with each other or the intermediate sheet, if there is one. If the pieces of substrate material were not previously coated with a membrane material, the substrate is coated with a dope and quenched or coagulated to form a membrane sheet.

[0008] The membrane sheet is generally planar, but with one or more ridges corresponding to the interior channels providing a surface area larger than an equivalent flat plate area. The interior channels provide open passages for

permeate to flow to the edges of the sheet. A membrane sheet is preferably bonded together along one or more lines between interior channels as well as along outer edges parallel to the depressions. When bonded together between a sufficient number of interior channels, optionally on each side of each interior channel, the membrane sheet can be used without a four-sided frame and can be mechanically cleaned by backwashing.

[0009] A plurality of membrane sheets may be placed side by side in a bundle. Permeating edges of the membrane sheets, which intersect with and are open to one or more of the interior channels, may be separated from the edges of adjacent membrane sheets in the bundle by spacers. The bundle is connected to one or more headers to produce a module. The connection to a header may be permanent or removable. A plurality of modules can be assembled into a cassette. The cassette may hold the modules in a tank of water to be filtered such that the membranes are generally vertical and the interior channels are generally horizontal. Permeate flows to the headers, which are at the sides of the cassette. The liquid being filtered, and optionally gas bubbles, flows vertically through spaces between the membranes.

DRAWINGS

- [0010] Figure 1 is an isometric view of a formed substrate sheet.
- [0011] Figure 2 is an isometric view of a substrate sheet as in Figure 1 on the bottom cavity of a mold.
- [0012] Figure 3 is an isometric view of a substrate sheet on the bottom cavity of a mold as in Figure 2 with a mold insert on the substrate sheet.
- [0013] Figure 4 is an isometric view of a substrate sheet on the bottom cavity of a mold with a mold insert on the substrate sheet as in Figure 3 with an upper cavity of the mold.
- [0014] Figure 5 is a cross section of a substrate made of two formed substrate sheets as in Figure 1.
- [0015] Figure 6 is an isometric view of the substrate of Figure 5.

[0016] Figure 7 is a cross-section of a membrane having a semi-permeable coating on a substrate as in Figure 5.

[0017] Figure 8 is an exploded isometric view of a plurality of membranes as in Figure 7 being assembled into a bundle.

5 [0018] Figure 9 is an end view of a membrane bundle.

[0019] Figure 10 is a cross section of a membrane bundle potted at one end into a permeate header.

[0020] Figure 11 is a top view of membrane module having a membrane bundle potted into permeate headers at both ends.

10 [0021] Figure 12 is a top view of a cassette having a plurality of the modules of Figure 11.

[0022] Figure 13 is an enlarged view of a corner of the cassette of Figure 12.

[0023] Figure 14 is a side view of the cassette of Figure 12.

15 [0024] Figure 15 is a side view of a permeate sheet having an intermediate flat sheet between two substrate sheets.

[0025] Figure 16 is a side view of a permeate sheet made with substrates having an undulating profile.

DETAILED DESCRIPTION

20 [0026] In this specification, a “sheet” or “substrate sheet” typically refers to a piece of a substrate material, which may be shaped to have a plurality of depressions. A “permeate sheet” or a “substrate” typically refers to two sheets bonded together. A “permeate channel” typically refers to a channel on the inside of a substrate defined by the inside surfaces of the sheets, through which liquid
25 can flow parallel to the plane of the substrate to the edge of the substrate. A “connector” may refer to a portion of a sheet between two adjacent depressions, or a portion of a permeate sheet between two adjacent permeate channels. An “insert” may refer to a part of a mold that is placed between a top and bottom die of the mold and used to shape some or all of the inside surface of a depression or

a permeate channel. A “membrane sheet” may refer to a permeate sheet that has a separation layer coated on it.

[0027] In an example of a sheet and a method of making it, to be described in more detail below, a sheet is made from a piece of a non-woven material that is
5 heat treated and pressed into a cavity to form a shape having a plurality of depressions, alternatively called ripples. In the example described herein, the depressions are separated by connectors. The connectors contact or lie in a common plane. In the example described herein, the connectors are essentially flat and the depressions are essentially semi-cylindrical. Two of these sheets are
10 attached together at one or more, preferably all, of their connectors and at their two outer edges, alternatively called flanges, that are parallel to the depressions. This forms a permeate sheet that has an array of parallel generally cylindrical permeate channels, each channel formed by two of the semi-cylindrical ripples, one from each of the sheets. The permeate sheet has two open edges
15 perpendicular to the channels, where the permeate channels discharge. The permeate sheet may be trimmed if necessary to a final size and shape. If the sheet was not pre-coated with a membrane material, the permeate sheet is fed into a coater where a membrane dope is cast on the outer surfaces of the permeate sheet. The coated permeate sheet then passes into a quench or
20 coagulation bath wherein the dope is transformed into a solid membrane material having a separation layer. The membrane material may be formed by a phase separation process, for example a TIPS or NIPS process. The resulting membrane sheet is removed from the quench bath and further rinsed and impregnated (if needed) and dried. A plurality, for example between 2 and 50
25 membranes sheets may be attached together at their open ends according to a target inter-sheet spacing to form a bundle. At least one open end of the bundle is attached, permanently or with a removable seal, to a permeating header to form a module. The module may be integrity tested, for example by a pressure decay test. Modules are assembled into a cassette comprising structural elements to
30 make the cassette suitable to insertion into a filtration tank. The membrane sheets are oriented generally vertically in the tank, with the channels oriented generally horizontally, and the headers located at the sides of the cassette and

oriented generally vertically. The cassette preferably also has a lower aeration grid configured to discharge bubbles into spaces between the membrane sheets. The Figures, to be discussed in detail below, show an example of a sheet, a mold for making the sheet, a module and a cassette.

5 [0028] Referring to Figure 1, a sheet 7 is made of a piece of a non-woven textile. The sheet 7 that has been pressed into a shape having a series of parallel semi-cylindrical depressions 6 spaced at predetermined intervals and separated by flat connectors 5. The outer depressions are bordered by two edge flanges 4. The radius of the semi-cylindrical depressions 6 may be, for example, between
10 0.3 mm and 50 mm depending on the application.

[0029] Referring to Figures 2 to 4, a mold 10 comprising a bottom cavity 9, a top cavity 11, and a plurality of inserts 8 (only one shown) is used for the forming process. The bottom cavity 9 matches the outer shape of the final molded sheet 7. The inserts 8, may be metallic and are used in conjunction with the
15 cavities 9, 11 to form the semi-cylindrical depressions 6. The inserts 8 can be separate components of the mold 10 or built into the top cavity 11 of the mold 10. When the mold has built in inserts 8, they can be fixed or have the capability of freely rotating. Rotating or detached inserts 8 allows for sliding of the non-woven substrate material during a mold closing step. Highly polished (mirror finish)
20 materials are used for the two cavities 9, 11 of the mold and the inserts 8. A piece of initially flat non-woven substrate is loaded onto the bottom cavity 9 of the mold (figure 2). This piece is initially cut to pre-determined dimensions. After loading the piece of substrate, the inserts 8 are placed on the piece of substrate (if they are not built into the top cavity 11) and the top cavity 11 is placed over the inserts 8.
25 The mold 10 is then closed and pressure is applied between the cavities 9, 11, for example by clamping them together. The top cavity 11 and inserts 8 thereby press the sheet 7 into the bottom cavity 9.

[0030] The top cavity 11 of the prototype mold 10 has the same interior shape as the bottom cavity 9. The mold 10 shown in Figures 2 to 4 is capable of
30 molding 2 sheets at the same time by inserting another piece of substrate between the inserts 8 and the top cavity 11 before closing the mold 10. Each mold cavity is preferably well machined within tight tolerances to provide good

control over the thickness and the shape of the final sheet 7. In particular, over compaction of any part of the sheet 7 is undesirable. Heat is applied during the molding process. After the heating phase, the mold is cooled in a closed position until the sheet (or sheets) is capable of maintaining its shape. In this way, a sheet
5 7 is initially heated and then cooled both while being pressed against the inside surface of a cavity 9. The sheet 7 is preferably heated to its heat deflection temperature (HDT) or more while it is pressed against the inner surface of the cavity 9. The sheet 7 is also preferably cooled to below its HDT, and more preferably below its glass transition temperature (T_g), while it is pressed against
10 the inner surface of the cavity 9. The sheet 7 thereby takes on a permanent shape having an outer surface corresponding to the inner surface of the cavity.

[0031] A non-woven fabric, for example a polyester based fabric normally used as a substrate for flat sheet UF membranes, may be used for the substrate material. Samples from different suppliers were tested using a prototype mold,
15 including a sample from Hirose (05TH-80W), 3 grades from 3M Powell, and multiple grades from Crane Nonwovens, AWA Paper, and Ahlstrom. The substrate materials had thicknesses ranging from 80 to 120 microns, and air permeability of 5 to 15 cc per square centimeter per second. Substrate materials were dried prior to molding. The substrate materials generally have a matrix of
20 thermally bonded short fibers and longer reinforcing fibers. All of the samples tested produced acceptable sheets 7.

[0032] Depending on the composition of the substrate, the molding temperature is at least 100F (38 degrees Celcius) and varied in tests between 300 and 500 F (149 and 260 degrees Celcius). In comparison, the T_g of polyester is
25 about 60 to 75 degrees Celcius, the HDT of polyester is about 170 to 177 degrees Celcius and the melting point (T_m) of polyester may be about 255 degrees Celcius, all of these temperatures being subject to variation depending on the form of the polyester. The temperature is preferably above the HDT of the matrix fibers and the reinforcing fibers, and optionally also above the melting point of the
30 matrix fibers, but preferably below the melting point of the reinforcing fibers. The mold is heated for long enough for the substrate to assume a shape corresponding to the inner surface of the cavity 9, 11, but at a combination of time

and temperature that maintains a substantial portion of the air permeability of the substrate such that a membrane dope may still penetrate and anchor to the substrate. Heat was provided by placing the mold 10 in a temperature-controlled oven. Cycle time varied between 5 and 10 minutes for heating and over 30 minutes for cooling. For production, a mold with built-in water (or other cooling agent) lines (similar to injection molding) can be expected to significantly shorten the cooling process. The mold components 9, 8, 11 are sized to produce a desired final sheet 7 thickness, for example between 0.05 to 0.1 mm. The formed sheet 7 was 0.075 mm thick when made in a first prototype mold. Some compaction is acceptable, and possibly preferable, to reduce wall thickness and increase the ability of the sheet 7 to hold a molded shape. The mold closing and holding pressures were in the range of 15 to 20 psi. A mold for a very large sheet 7 may require a higher closing pressure but can use the same holding pressure. Two sheets 7 were molded simultaneously in the first prototype mold using removable cylindrical metal inserts 8. The molded sheets 7 maintained an inner and outer radius matching the inserts 8 and cavities 9, 11 used in the mold. The radius of the inner surfaces of the depressions in the cavities 9, 11 in the prototype mold 10 was about 1.5 mm. In a second prototype mold, the radius of the inner surfaces of the depressions in the cavities was about 0.6 mm. An optimal diameter for microfiltration or ultrafiltration of water may be closer to 0.7 mm in order to maximize packing density with acceptable lumen pressure drop.

[0033] Referring to Figures 5 and 6, after molding the sheets 7 are trimmed to final dimensions and a pair of sheets 7 are assembled into a permeate sheet 20. The sheets 7 are attached together at bonding areas 12. Sheets 7 made in the prototype mold as described above were bonded together using several types of adhesives including epoxy, water-based adhesives, and polyurethanes. The same mold 10 that was used to form the sheets 7 was used for fusing together two sheets 7. In order to eliminate sticking of the bonding areas 12 to the mold 10, and contamination of the surface that will subsequently be coated with a membrane, due to full penetration of the bonding agent through the substrate material, higher viscosity adhesives are preferred. Two sheets 7 made in the first prototype mold as described above, when fused together, created a permeate

sheet 20 with cylindrical channels having a 3 mm outer diameter and a spacing between the outside diameters of about 2 mm. The overall dimension of the permeate sheet 20 were about 10 inches (25 cm) by 1 1/2 inches (37 cm), although larger sheets 7 may be made. Two sheets 7 made in the second
5 prototype mold created a permeate sheet 20 with cylindrical channels having a 1.2 mm outer diameter and a spacing between the outside diameters of about 1 mm. These sheets 20 were about 125 mm by 120 mm. The formed permeate sheets 20 from both prototype molds were self-supporting and maintained their shape with crisp transitions between the depressions 6 and the connectors 5.

10 [0034] In general, two sheets 7 can be attached together using thermoset materials like polyurethanes, epoxies or silicones or by using hot melts (thermoplastics) or other adhesives 19. The gluing process can take place in a separate gluing mold similar to the mold 10 used to form the sheets 7. First, the bottom sheet is loaded in the mold. The glue is applied using a dispenser, for
15 example a roller or a glue printing head moved by servos controlled by a computer. Next, cylindrical inserts may be placed inside the previously molded semi-circular shapes. The outside diameter of these inserts will match the intended ID of the newly formed channels. Using the inserts is optional, but the inserts help ensure a good roundness of the permeate channels. However, the
20 assembly process was also done in the prototype forming mold 10 without the use of its inserts 8. In this case, the process steps related to loading and removing of the inserts are obviously eliminated. A bottom sheet 7 is loaded into a bottom cavity of the mold and a top sheet 7 is loaded in a top cavity of the mold 10. After closing the mold, the two sheets will touch each other only in the bonding area.

25 With the mold closed pressure and heat may be applied to the newly created structure if required for the adhesive used. The contact surface will be glued together forming a permeate sheet 20. Once the cycle is complete the mold is opened and the inserts are removed. The permeate sheet 20 will be removed from the gluing mold, trimmed to final dimensions if necessary and transferred to a
30 casting machine. The sheets 7 can comprise low surface energy fibers, for example of polyethylene terephthalate (PET), which may make it difficult to achieve a strong bond. Particularly strong bonds are provided even in PET

based sheets 7 by using methyl methacrylate adhesive systems (MMA), epoxies and polyurethane (PUR) hot melt adhesives.

[0035] Another option for bonding is to use thermoplastic (hot melt) wires. The wires are positioned on top of the bottom sheet centered in the bonding areas 12. The other sheet 7, loaded in the other side of the mold, will be placed on top of the first sheet. Pressure and temperature is applied until the wires melt, penetrate superficially the two sheets 7 and fuses them together. As described before the process can be done with or without the use of inserts.

[0036] A third assembly method that can be used is sonic, friction or laser welding. Continuity of the bond along the connector is not paramount for the process since permeate flowing from one channel to another does not create contamination. Laser welding with a black PTFE backing plate behind the bonding areas 12, or with a near infrared absorbing welding material such as Clearweld™ system sold by Gentex Corporation between the sheets 7, provides a particularly strong bond.

[0037] For increased permeate sheet active surface and structural strength of the permeate sheet 20 a different assembly method can be used. A thin porous material may be placed between the two sheets prior to the assembly process. This permeate carrier media will allow the liquid permeating through the membrane in the connectors 6 area to flow between the two sheets 7 in the binding area 12 into the permeate channels and into the permeate headers. Welding or an adhesive can secure the two sheets together (via the porous material) and give structural strength to the permeate sheet 20 during the backwashing process. However, such a porous material is merely optional. It is not necessary for permeate to flow between one permeate channel and another, and some permeate may flow from the connector area into a permeate channel even in the absence of a porous material. Optionally, particularly if the membrane sheet will not be backwashed but possibly even if it will be backwashed, a welded or adhesive attachment between sheets 7 or between sheets 7 and an intermediate material may be discontinuous, for example in the form of a series of adhesive dots along the connectors 5, to allow the area of the connectors 5 to pass more permeate.

[0038] For additional strength, a permeate sheet 20 may optionally have a rigid insert sandwiched between the two sheets 7 on the edges 4 or on one or more of the connector areas 5, or both. The reinforcement is added during the assembly process previously described. The rigid inserts are made of very thin, high tensile strength materials, preferable plastic materials with or without reinforcement. They will compensate for stresses generated by weight increase during field operations when the permeate sheet is installed with the permeate channels in a horizontal position. The orientation of the sheets in a module will be determined by the type of application, hydraulic calculations and the type of process used for fouling protection and cleaning protocols. Additional reinforcements can be placed in the center of the permeate sheet 20 or in other locations throughout the permeate sheet 20.

[0039] As shown in Figure 15, another option is to provide an intermediate material or insert by way of a sheet form insert 50 between the entire area of two sheets 7, thus creating two semi-cylindrical permeate channels for every one cylindrical permeate channel that would be formed without the insert 50. This insert 50 may be rigid to reinforce the sheets 7 as described above, or may be permeable to increase the activity of the connector 5 area of the sheets 7 as described above. The insert 50 may also be used, whether rigid or not and whether porous or not, to enable attaching the sheets 7 together. An adhesive or weld enhancing material may be applied, for example sprayed in a thin layer or printed as lines or a grid of dots, on both sides of the insert 50. Placing the insert 50 between two sheets 7 thus provides an alternate method for applying an adhesive or weld enhancing material to the connectors 5. Whether or not an adhesive is pre-applied, the insert 50 may also help provide a secure bond between sheets 7 if there is not a crisp distinction between the depressions 6 and the connectors 5, for example if the sheets 7 have an undulating shape as shown in Figure 16. The insert 50 may be, for example, a solid film, for example of mylar, or a non-woven sheet such as a three dimensional matrix of polyamide (PA, nylon) fibers.

[0040] After the permeate sheet 20 is formed, a polymeric membrane dope is cast on both faces. This can be done simultaneously for both sides or

sequenced (one side at a time). The permeate sheet 20 is passed through a casting device that applies the dope. The casting device has a die, analogous to the spinneret of a hollow fiber coating device, with a shape corresponding to the outer shape of the permeate sheet 20. The dope is brought to the casting device when the permeate sheet 20 is present using gas pressure or a metering gear pump. The speed and the thickness of dope layer applied is controlled. Other process parameters like dope viscosity, temperature, and internal pressures inside the casting device are also controlled. The casting device has a shape matching the outside shape of the permeate sheet 20. The permeate sheet 20 is fed to the casting device vertically or horizontally, however vertical feeding reduces the tendency of dope to flow towards the binding areas 12. The exit of the casting device leads to a gap to allow the dispersion of the dope on to the permeate sheet 20 at a generally constant thickness. Subsequently the coated permeate sheet 20 passes through coagulation and rinse baths. This process will form a solid membrane layer 23 on top of the permeate sheet 20 by way of a phase inversion membrane formation process as shown in Figure 7 to produce a membrane sheet 24. Membrane sheets 24 are then rinsed, impregnated (UF only) and dried in an offline process. Membrane sheets 20 made in the first prototype mold were coated with polysulfone in a layer of about 140 microns thick. The polysulfone impregnated the permeate sheet 20 but did not fill the interior permeate channels of the membrane sheet 24.

[0041] Alternately, a membrane sheet 24 can also be made by forming a membrane on a substrate sheet before making a sheet 7. A flat sheet membrane can be cast on a regular casting machine. The flat sheet membrane is then formed in the mold 10 into a molded membrane sheet and assembled together with another such sheet into a membrane sheet 24. The molding process will have a different cycle time and use different process parameters.

[0042] Referring to Figures 8, 9 and 10 several membrane sheets 24 can be combined to form a bundle 26. While any number of membrane sheets 24 can be used, a preferred range is 15-50 based on desired inter-sheet spacing gaps and limits on plastic header molding. A bundle 26 can be potted in a plastic header molding 28 using a resin such as polyurethane according to conventional

methods such as fugitive static potting or centrifuge potting with cutting to open the channel ends. An alternate potting method, as shown in Figures 8, 9 and 10 is to use plastic inserts 31, 32 to attach the membrane sheets 24 together into a potting block or brick 25 that can then be inserted into a seat in a header molding 5 28. Optionally, a plurality of membrane sheets 24 may be laid in series between two inserts 31, 32. For example, inserts 31, 32 that are about 1 m long may hold 4 membrane sheets 24, each of which is about 25 mm high. Further optionally, a porous divider 34 may define a bottom of the seat. The block 25 is potted into place by pouring a resin 36 into the header seat over the block 25. Permeate 10 flows through the channels, exits the block 25 through open ends of the channels, flows through the divider 34 if any, and into a permeate receptacle 37 in the header 28. Permeate can be removed from the permeate receptacle 37 through a permeate spigot 25.

[0043] Figure 11 shows a module 40. The black area between the two permeate headers 40 represents a bundle 26 of membrane sheets 24 spaced by 15 gaps 27 as shown in more detail in Figure 10. The membrane sheets may be separated by a center to center distance of, for example, between 0.5 cm and 5 cm. Optionally, the membrane sheets 24 may be staggered relative to each other, with the ripples of one located across from the connectors of another. Figure 12 20 shows a top view of a cassette 42 having several modules 40 contained within a frame 44. A permeate header (not shown) is connected to the permeate spigots 35 of the modules 40. The frame 44, headers 28 and, optional permeate pipes if any, are located at the sides of the cassette 42 so that fluids can travel upwards through the gaps 27. Modules 40 can be stacked with the permeate spigot 25 of 25 one module 40 plugging into the permeate receptacle 37 of an upper or lower module 40. In Figure 14, for example, three modules 40 are stacked together in a vertical column. Referring to Figure 13, the frame 44 of the cassette 42 holds sliders 31 that correspond in shape and size to the alignment grooves 30 of the headers 28 to assist in placing the modules 40 in position in the cassette 42.

30 [0044] Another option is to not use a molded plastic header but to use the block as a finished element, potentially with a plastic guide attached to its perimeter, for direct insertion into a permeate cavity of a header or the cassette.

A removable seal between the block and the permeate cavity is made by compressing the block into the permeate cavity, or by a sealing means such as an O-ring. Advantages of this method include less active fiber blocked by urethane, less manufacturing scrap from potting, increased cassette packing density, reduced raw material cost (header plastic and urethane), easy repair of channels in the field by pinning open channel ends after releasing them from the permeate cavity, and reduced replacement module costs.

[0045] Under the no-header design, fiber bundle blocks will be directly inserted into a cassette composed of a steel frame with molded plastic ends that serve both as headers with double o-rings and permeate collection channels. 1 meter high elements could be stacked in any number in order to fill up any size tank. Bundles would be tapered by having an increasingly thin layer of thermoplastic at the end where there are minimal stresses and channels are non-permeating to allow for an easier fit into headers and to allow for bundles to be spaced together more closely. The thermoplastic would be thicker near the top to allow for a restrainer bar to be placed across all modules for security. The system will be adjustable in case of shrinkage.

[0046] By providing molded permeate channels inside a permeate sheet, the distribution of active surface inside the filtration tank can be precisely controlled. Further, the precision molded permeate channels allow for a membrane wall thickness of 0.3 mm or less, or 0.15 mm or less, which is less than for a reinforced hollow fiber membrane. The outer diameter of the permeate channels may be 1 mm or less, or 0.5 mm or less. In a calculated example, the channels have an outside diameter of 0.7 mm, and a membrane wall thickness of 0.15 mm. The permeate channels would have an internal diameter of 0.4 mm, which would be sufficient for high volume permeate flow without significant pressure drop to permeate flow through the permeate channels in a membrane sheet that is 1 m wide.

[0047] The membrane sheet has a significantly increased surface area relative to a typical flat sheet membrane, avoids the frame components and spacers that are necessary in typical flat sheet modules, and the rigidity of the membrane sheets allows for a larger area (referring to the external dimensions

of the sheet rather than its membrane surface area) per sheet. The membrane sheets 24 may undulate or vibrate when aerated, but there is little or no abrasion between adjacent membranes as in hollow fiber systems. All permeate channels are precision placed within a sheet and sheets can be precision placed with respect to each other, allowing a packing density of up to 50%. Tank and module packing density are at least comparable to hollow fiber systems.

[0048] Vertically oriented sheets, with headers at the sides of the sheets, allow for an aeration grid to channel air between sheets with no top or bottom header to block flow. Because air is directed between each sheet and forced to travel upward, the issue of fouling in dead zones within hollow fiber bundles is removed. However, unlike typical flat sheet membranes, having only two headers allows some vibration of the membrane sheets to help prevent sludging that may occur at the membrane surface. Yet the well-defined vertical gaps between membranes fosters plug-flow through the gaps, which reduces average solids exposure and creates well defined paths for solids drainage during tanks drains.

[0049] While hollow fiber membranes are limited to polymers that can be extruded with the right flexibility, strength, and casting properties, flat sheet casting allows for more rigid, pH resistance polymers such as polysulfone to be used without suffering disadvantages due to polysulfone rigidity. The permeate sheets may also be coated with thin-film composites such as NF membrane materials, which allows for an immersed NF filter and bioreactor. New nanostructured membrane materials, for example using carbon nanotubes, aquaporins, masked etching, or other novel processes, may also be suitable for being formed on a permeate sheet.

[0050] US provisional patent application number 61/325,972 is incorporated herein by this reference to it.

CLAIMS:

1. A device comprising,
two sheets of a substrate material, at least one of the sheets of substrate
5 material having one or more depressions extending to an edge of the at least one
of the sheets of substrate material, the two sheets of substrate material bonded
together along their outer edges except where the one or more depressions
extend to the outer edges,
whereby the one or more depressions form one or more internal channels
10 between the two sheets of substrate material, the one or more internal channels
being open to at least one of the outer edges.
2. The device of claim 1 further comprising a filtration membrane material pre-
coated on each of the two sheets of substrate material before they are bonded
15 together or coated on outer surfaces of the two sheets of substrate material after
they are bonded together.
3. The device of claim 1 wherein the membrane material has a pore size in the
microfiltration range or smaller.
20
4. The device of claim 3 wherein the membrane material has a pore size in the
nanofiltration range or smaller.
5. The device of claim 1 wherein the one or more depressions are generally free-
25 standing and permanent features of the at least one sheet of substrate material.
6. The device of any of claims 1 to 5 wherein the substrate material is a non-
woven textile.
- 30 7. The device of any of claims 1 to 6 wherein the one or more depressions are
free-standing features of shape molded into the at least one of the sheets of
substrate material having one or more depressions.

8. The device of any of claims 1 to 7 wherein the one or more internal channels are generally cylindrical and have an inside diameter of between 0.1 mm and 50 mm.
- 5 9. The device of any of claims 1 to 8 wherein the two sheets of substrate material are bonded together between the one or more internal channels directly or through an insert .
- 10 10. The device of any of claims 1 to 9 wherein the two sheets of a substrate material are bonded together by a thermoplastic or a resin such as an MMA, epoxy or a PUR hot melt adhesive, or by welding such as laser welding.
11. A filtration module comprising a bundle of the device of any of claims 1 to 10.
- 15 12. The filtration module of claim 11 wherein edges of the device that are open to the one or more internal channels are potted into a header.
13. The filtration module of claim 11 wherein adjacent devices in the bundle are separated by a spacer, by a potting material, or both.
- 20 14. The filtration module of claim 13 wherein the adjacent devices in the bundle are separated by spacers pre-made with surfaces corresponding to the shape of a gap between adjacent devices.
- 25 15. The filtration module of claim 14 wherein the ends of the devices in the bundle and the spacers are bonded together to form a block.
16. The filtration module of claim 15 wherein the block is removably sealed to a header cavity.
- 30 17. The filtration module of claim 15 wherein the block is attached to a header cavity by a solidified sealing material.

18. The filtration device of claims 12, 16 or 17 wherein the internal channels are generally parallel to each other and generally perpendicular to the header.
19. The filtration device of claim 18 wherein the header is mounted in a cassette
5 frame adapted to hold the filtration device in a tank with the header oriented vertically, the internal channels oriented horizontally, and with vertical gaps between adjacent devices.
20. A process for making a membrane comprising steps of,
10 a) inserting a piece of a substrate material into a cavity,
b) heating and cooling the piece of substrate material while pressing the piece of substrate material against an inner surface of the cavity to shape the piece of substrate material; and,
c) removing the substrate material from the die, wherein the removed
15 substrate material has a shape corresponding to the die.
21. The process of claim 20 wherein the substrate material is a porous non-woven textile.
22. The process of claim 20 or 21 wherein the cavity has a series of parallel spaced depressions.
- 20 23. The process of any of claims 20 to 22 further comprising bonding two of the shaped sheets together to provide a structure having one or more internal channels open to at least one edge of the structure.
24. The process of any of claims 20 to 23 further comprising a step of coating a
25 membrane material on the structure by passing the structure in a generally downward direction through a coating die having a shape generally matching that of the structure.
25. The process of any of claims 20 to 23 further comprising a step of coating the piece of substrate material with a membrane material while the substrate material is a flat sheet before inserting the piece of substrate material into the die.

26. The process of any of claims 20 to 25 wherein the piece of substrate material is heated to a temperature above its heat deflection temperature and cooled to below its heat deflection temperature while the substrate material is pressed against the inner surface of the cavity.