

Method of forming dielectric films, new precursors and their use in the semi-conductor manufacturing

The invention relates to a method of forming high-k dielectric films such as hafnium or zirconium oxides or oxynitrides and their use for manufacturing semi-conductors.

With the shrink of the critical dimensions of the future generation of semi-conductor devices, the introduction of new materials, especially having high dielectric constant, is required. In CMOS architectures, high-k dielectrics are required to replace SiO₂ which reaches its physical limits, having typically a SiO₂ equivalent thickness of about 1nm.

Similarly, high-k dielectrics are required in Metal-Insulator-Metal architectures for RAM applications. Various metal compositions have been considered to fulfill both the materials requirements (dielectric constant, leakage current, crystallization temperature, charge trapping) and the integration requirements (thermal stability at the interface, dry etching feasibility...).

The Group IV based materials, such as HfO₂, HfSiO₄, ZrO₂, ZrSiO₄, HfZrO₄, HfLnO_x (Ln being selected from the group comprising scandium, yttrium and rare-earth elements) and more generally HfMO_x and ZrMO_x, M being an element selected from Group II, Group IIIa and Group IIIb, or a transition metal, are among most promising materials. Furthermore, Group IV metals composition can also be considered for electrode and/or Cu diffusion barrier applications, such as TiN for mid-gap metal gate and HfN, ZrN, HfSi, ZrSi, HfSiN, ZrSiN, TiSiN for MIM electrodes.

The main industrial options to enable the deposition of such thin films with a reasonable throughput and an acceptable purity are vapor phase deposition techniques, such as MOCVD (Metal-organic Chemical Vapor Deposition) or ALD (Atomic Layer Deposition). Such deposition processes require metal precursors that must fulfill drastic requirements for a proper industrial use. Metal-organic or metal-halide precursors are required for those processes. Various hafnium and zirconium metal-organic compounds have been considered as precursors to enable such a deposition.

Halides such as HfCl₄, ZrCl₄ are the most common Hf/Zr precursors and have been widely described. Kim et al. disclosed the use of HfCl₄ for the

deposition of HfO_2 by ALD (Kim et al., Electrochem Soc Proceedings 2005-05, 397, 2005). However, some by-products generated during the deposition process, such as HCl or Cl_2 , can cause surface/interface roughness that can be detrimental to the final properties. Other possible byproducts, depending on the oxygen source used, may be hazardous. For instance, OCl_2 , through the OCl fragment by QMS, has been detected as a byproduct of the reaction between HfCl_4 and O_3 . Moreover, in the case of high-k oxide, Cl or F impurities are highly detrimental to the final electrical properties.

Triyoso et al. and Chang et al. studied the use of $\text{Hf}(\text{OtBu})_4$ for HfO_2 MOCVD and ALD, respectively [Triyoso et al.; J. Electrochem. Soc., 152(3), G203 - G209 (2005); Chang et al.; Electrochem. Solid. State Let., 7(6), F42-F44 (2004)]. Williams et al. have evaluated $\text{Hf}(\text{mmp})_4$ and $\text{Hf}(\text{OtBu})_2(\text{mmp})_2$ for MOCVD of HfO_2 . In WO2003035926, Jones et al. disclose solid Ti, Hf, Zr and La precursors improved with donor functionalized alkoxy ligand (1-methoxy-2-methyl-2-propanolate [$\text{OCMe}_2\text{CH}_2\text{OMe}$, mmp]) which helps inhibiting oligomerization of Zr and Hf alkoxide compounds and increasing their stability towards moisture. However, all those alkoxide precursors have the drawback not to enable self-limited deposition in ALD process as suggested by Potter et al. (R.J.Potter, P.R.Chalker, T.D.Manning, H.C.Aspinall, Y.F.Loo, A.C.Jones, L.M.Smith, G.W.Critchlow, M.Schumacher, Chem. Vap. Deposition, 2005, 11, N°3, 159-167).

Alkylamides precursors such as $\text{Hf}(\text{NEtMe})_4$, $\text{Hf}(\text{NMe}_2)_4$, $\text{Hf}(\text{NEt}_2)_4$ have been widely disclosed in the literature [Senzaki et al, J. Vac. Sci. Technol. A 22(4) Jul/Aug 2004; Haussmann et al, Chem. Mater. 2002, 14, 4350-4353; Kawahara et al., J. Appl. Phys., Vol 43, N°7A, 2004, pp 4129-4134; Hideaki et al., JP 2002-093804; Metzner et al. US 6,858,547; Dip et al. US 2005/0056219 A1]. Group IV alkylamides are both suitable for ALD and MOCVD processes. Furthermore, some are liquid at room temperature ($\text{Hf}(\text{NEt}_2)_4$ and $\text{Hf}(\text{NEtMe})_4$) and of sufficient volatility, and they allow self-limited ALD at low temperature for a limited thermal budget process. However, Group IV alkylamides, alkylamides in particular Zr compounds, have several drawbacks, among which they may decompose during the distribution to some extent leading to a possible clogging of the feeding line or the vaporizer, they may generate particles during deposition,

they may entail non-uniform compositions during deep trenches deposition processes, and they only allow a narrow self-limited ALD temperature window, hence reducing the process window. In particular, $\text{Zr}(\text{NEtMe})_4$ may decompose in the distribution lines and generate particles above 170°C which is a common distribution temperature. $\text{Hf}(\text{NEtMe})_4$ is more thermally stable yet do not afford self-limited atomic layer deposition above 300°C due to thermal decomposition.

In WO 2007/055088, Thenappan et al. disclose hafnium and zirconium guanidates complexes and their application for vapor phase deposition. $\text{Hf}(\text{NEt}_2)_2[(\text{NiPr-CNEt}_2)_2]$ is given as example. Hafnium and zirconium guanidates are however generally solids with a very limited volatility. As exemplified in thermal gravimetric analysis, one may not obtain $\text{Hf}(\text{NEt}_2)_2[(\text{NiPr-CNEt}_2)_2]$ in vapour phase, without a risk of thermal decomposition and a subsequent particle generation.

Lehn et al. (Chem. Vap. Deposition, 2006, 12, 280-284) disclose tetrakis(trimethylhydrazido) zirconium $[\text{Zr}(\text{NMeNMe}_2)_4]$ and hafnium and their use for low temperature CVD. The exemplified compounds have an acceptable volatility (sublimation at 0.06 Torr, 90°C reported) but they are solid at room temperature.

Carta et al. disclose the use of bis(cyclopentadienyl)bisdimethyl hafnium, $[\text{HfCp}_2\text{Me}_2]$ (Carta et al. discloses in Electrochem Soc Proceedings, 260, 2005-09, 2005) and several authors (Codato et al., Chem Vapor Deposition, 159, 5, 1995 ; Putkonen et al., J Mater Chem, 3141, 11, 2001 ; Niinisto et al., Langmuir, 7321, 21, 2005) proposed a new family of Zr and Hf compounds as alternatives to hafnium and zirconium alkylamides: Bis(cyclopentadienyl) bisdimethyl hafnium, bis(cyclopentadienyl) bisdimethyl zirconium, which allow an efficient ALD deposition process with an ALD window up to 400°C and an achievement of films with less than 0.2% C in optimized conditions with H_2O as co-reactant. However, HfCp_2Me_2 and ZrCp_2Me_2 both have the drawback of being solid products at room temperature (HfCp_2Me_2 melting point is 57.5°C). This prevents IC makers to use those precursors in an industrial manner, that is using delocalized containers filling, and entail both facilitation and process issues.

In US 6,743,473, Parkhe et al. disclose the use of $(\text{Cp}(\text{R})_n)_x\text{MH}_{y-x}$, to make a metal and/or a metal nitride layer, where M is selected from tantalum, vanadium,

niobium and hafnium, Cp is cyclopentadienyl, R is an organic group. Only examples of tantalum and niobium cyclopentadienyl compounds are disclosed. However, no liquid precursor or a precursor having a melting point lower than 50°C is disclosed.

5 Liquid bis(cyclopentadienyl) derivatives have recently been proposed by Heys et al. in WO 2006/131751 A1. However, they still present the disadvantage of limited volatility and also present large steric hindrance that may limit the achieved growth rate.

10 Today, there is a need for providing liquid or low melting point (<50°C) group IV precursor compounds, and in particular Hf and Zr compounds, that would allow simultaneously a proper distribution (physical state, thermal stability at distribution temperatures), a wide self-limited ALD window, and a deposition of pure films either by ALD or MOCVD.

15 According to the invention, certain cyclopentadienyl or pentadienyl based group IV metal-organic precursors have been found suitable for the deposition of Group IV metal containing thin films by either ALD or MOCVD processes and to have the following advantages:

- They are liquid at room temperature or having a melting point lower than 50°C,
 - 20 - They are thermally stable to enable proper distribution (gas phase or direct liquid injection) without particles generation,
 - They are thermally stable to allow wide self-limited ALD window,
- 4) allowing deposition of a variety of Group IV metals containing films, including ternary or quaternary materials, by using one or a combination of co-reactants
- 25 (selected from the group comprising of H₂, NH₃, O₂, H₂O, O₃, SiH₄, Si₂H₆, Si₃H₈, TriDMAS, BDMAS, BDEAS, TDEAS, TDMAS, TEMAS, (SiH₃)₃N, (SiH₃)₂O, TMA or an aluminum-containing precursor, TBTDET, TAT-DMAE, PET, TBTDEN, PEN, lanthanide-containing precursors such as Ln(tmhd)₃...).

30 According to a first embodiment, the invention relates to a method of deposition on a substrate, of at least one metal containing dielectric film comprising a compound of the formula (I):



wherein:

$$0 \leq a < 1,$$

$$0 < b \leq 3, \text{ preferably } 1.5 \leq b \leq 2.5;$$

$$0 \leq c \leq 1,$$

M^1 represents a metal selected from hafnium (Hf), zirconium (Zr) and
5 titanium (Ti); and

M^2 represents a metal atom selected from magnesium (Mg), calcium (Ca), zinc (Zn), bore (B), aluminum (Al), indium (In), silicon (Si), germanium (Ge), tin (Sn), hafnium (Hf), zirconium (Zr), titanium (Ti), vanadium (V), niobium (Nb), tantalum (Ta); and the Lanthanides atoms, more particularly scandium (Sc),
10 yttrium (Y) and lanthanum (La) and rare-earth metal atoms,
which comprises the following steps:

- A step a) of providing a substrate into a reaction chamber;

- A step (b) of vaporizing at least one M^1 metal containing precursor of the
15 formula (II):



wherein:

M^1 is as hereinabove defined;

$$0 \leq x \leq 3, \text{ preferably } x = 0 \text{ or } 1;$$

20 $0 \leq z \leq 3, \text{ preferably } z = 1 \text{ or } 2;$

$$1 \leq (x + z) \leq 4;$$

$$0 \leq y \leq 7, \text{ preferably } y=2 \quad 0 \leq t \leq 5, \text{ preferably } t=1;$$

(R^1_yOp) represents a pentadienyl (Op) ligand, which is either unsubstituted or substituted by one or more R^1 groups, y representing the
25 number of substituting R^1 groups on said pentadienyl ligand;

(R^2_tCp) represents a cyclopentadienyl (Cp) ligand, which is either unsubstituted or substituted by one or more R^2 groups, t representing the number of substituting R^1 groups on said cyclopentadienyl ligand;

R^1 and R^2 , are identical or different and are independently selected from
30 the group consisting of the chloro group, the linear or branched, alkyl groups having from one to four carbon atoms, the N-alkyl amino groups, wherein the alkyl group is linear or branched and has from one to four carbon atoms, the N,N - dialkyl amino groups, wherein each alkyl group, identical or different from the

other, is linear or branched and has from one to four carbon atoms, the linear or branched alkoxy groups, having from one to four carbon atoms, the alkylsilylamides groups, the amidinates groups and the carbonyl group;

R' represents a ligand independently selected from the group consisting of the hydrogen, fluoro, chloro, bromo or iodo atoms, the linear or branched, alkyl groups having from one to four carbon atoms, the N-alkyl amino groups, wherein the alkyl group is linear or branched and has from one to four carbon atoms, the N,N-dialkyl amino groups, wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms, the linear or branched alkoxy groups, having from one to four carbon atoms, the alkylsilyl amino groups wherein the alkyl group is linear or branched and has from one to four carbon atoms, the dialkylsilyl amino groups wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms, the trialkylsilyl amino groups wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms, the amidinates groups and the carbonyl, being understood that, if said formula (II) comprises more than one R' groups, each R' may be identical or different one from another, to form a first gas phase metal source;

20

- Optionally a step b') of vaporizing at least one M^2 metal containing precursor, M^2 being as hereinabove defined; to form an optional second gas phase metal source;

25

- A step c) of introducing said first gas phase metal source and said optional second gas phase metal source, in the reaction chamber, in order to provoke their contact with said substrate, to generate the deposition of a metal containing dielectric film comprising a compound of the formula (I) as hereinbefore defined, on said substrate;


30

provided that, if the at least one metal containing dielectric film to be formed comprises the compound of the formula (I'):



corresponding to the formula (I), as hereinbefore defined wherein, $a = 0$, $b = 2$,

and $c=0$, and if the M^1 metal containing precursor, which is involved in step b), is a compound of the formula (II'):



corresponding to the formula (II) as hereinabove defined wherein $x=0$, and $z=2$,
 5 in said formula (II'), $t > 0$ in at least one of the two (R^2_tCp) ligands.

In the method as hereinabove defined, the at least one metal containing precursor of the formula (II) and if necessary, the least one M^2 metal containing precursor, have a melting point generally below 50°C , preferably below 35°C and they are preferably liquid at room temperature.

10 According to a particular embodiment of the method as hereinbefore defined, the vaporization step b) and if necessary, the vaporization step b') are achieved by introducing a carrier gas into a heated container containing the at least one M^1 metal containing precursor of the formula (II):



15 and if necessary, both the at least one M^2 metal containing precursor. The container is preferably heated at a temperature allowing to get the said metal sources in liquid phase and at a sufficient vapor pressure. If necessary, one or both metal precursors may be mixed to a solvent or to a mixture of solvents and/or to a stabilizer. The said solvent is for example selected from octane,
 20 hexane, pentane or tetramethylsilane. The concentration of the metal precursors in the solvent or in the mixture of solvents is usually between 0.01M and 0.5M and is more particularly around 0.05M. The carrier gas is selected, without limitation, from Ar, He, H_2 , N_2 or mixtures of thereof. If necessary, the container may be heated at temperatures in the range of $80-110^\circ\text{C}$. Those skilled in the art
 25 will consider that the temperature of the container can be adjusted to control the amount of precursor to be vaporized.

The carrier gas flow is usually comprised between 10 sccm (standard cubic centimeter) and 500 sccm. Preferably, the carrier gas flow is comprised between 50 sccm and 200 sccm.

30 According to another particular embodiment of the method as hereinbefore defined, the vaporization step b) and if necessary, the vaporization step b') are achieved by introducing in a liquid form, the M^1 metal containing precursor of the formula (II):



and if necessary both the M^2 metal containing precursor to a vaporizer where it is vaporized. If necessary, one or both metal precursors may be mixed to a solvent or to a mixture of solvents and/or to a stabilizer. The said solvent is for example
 5 selected from octane, hexane, pentane or tetramethylsilane. The concentration of the metal precursors in the solvent or in the mixture of solvents is usually between 0.01M and 0.5M and is more particularly around 0.05M.

According to a more particular embodiment, the vaporization step b) and the vaporization step b') are combined in one vaporization step b'') of both
 10 sources.

During the step c) of the method as hereinbefore defined, the vaporized metal containing precursor is introduced into a reaction chamber where it is contacted to a substrate.

In the context of the present invention, substrate means any substrate
 15 used in the semiconductors manufacturing, which, because of their technical function, requires to be coated by metal containing films. Such substrates are for example not only selected from silicon substrates (Si), silica substrates (SiO_2), silicon nitride substrates (SiN) or silicon oxy nitride substrates (SiON), but also from tungsten substrates (W) or noble metal substrates such as for example,
 20 Platinum substrates (Pt), Palladium substrates (Pd), Rhodium substrates (Rh) or gold substrates (Au).

The substrate is heated until the required temperature to obtain the desired film with a sufficient growth rate and with the desired physical state and composition.

25 The temperature during step c), usually ranges from 150°C to 600°C. Preferably the temperature is lower or equal to 450°C.

The pressure in the reaction chamber is controlled to obtain the desired metal containing film with a sufficient growth rate. The pressure during step c) usually ranges from around 1mTorr (0.1333224 Pa) to around 100Torr (13332.24
 30 Pa).

In the context of the present invention, the M^2 metal containing precursor, is selected from the group consisting of:

Silicon derivatives or their Germanium homologues, such as:


disiloxane, trisilylamine, disilane, trisilane, alkoxysilane of the formula:

(III₁)




wherein: $0 \leq x \leq 3$ and R^3 represents a linear or branched hydrocarbon group having 1 to 6 carbon atoms;

silanol derivative of the formula (III₂):



wherein: $1 \leq x \leq 3$ and R^4 represents a linear or branched alkyl group, having 1 to 6 carbon atoms, preferably $\text{Si}(\text{OH})(\text{OR}^4)_3$ and more preferably $\text{Si}(\text{OH})(\text{OtBu})_3$;

aminosilane derivative of the formula (III₃):




wherein: $0 \leq x \leq 3$ and R^5 and R^6 are identical or different and independently represents an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably $\text{SiH}(\text{NMe}_2)_3$ (TriDMAS); $\text{SiH}_2(\text{NHtBu})_2$ (BTBAS); $\text{SiH}_2(\text{NEt}_2)_2$ (BDEAS)) and mixtures thereof;

Aluminum derivatives, such as trimethylaluminum $[\text{Al}(\text{CH}_3)_3]$, dimethyl aluminum hydride $[\text{AlH}(\text{CH}_3)_2]$, alkoxyalane of the formula (IV₁):




wherein: $0 \leq x \leq 3$ and R^7 represents a linear or branched alkyl having 1 to 6 carbon atom, and R^8 , identical to or different from R^7 , represents an hydrogen atom, or preferably $\text{AlR}^9\text{R}^{10}(\text{OR}^7)$, with R^9 and R^{10} identical or different, which independently represent an linear or branched alkyl having 1 to 6 carbon atoms, most preferably $\text{AlMe}_2(\text{OiPr})$;

amidoalane of the formula (IV₂):




wherein: $0 \leq x \leq 3$ and R^{12} and R^{13} identical or different, represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, and R^{11} , identical to or different from R^7 and , represents an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;

Tantalum derivatives, such as: $\text{Ta}(\text{OMe})_5$, $\text{Ta}(\text{OEt})_5$, $\text{Ta}(\text{NMe}_2)_5$, $\text{Ta}(\text{NEt}_2)_5$, $\text{Ta}(\text{NEt}_2)_5$, a tantalum derivative of the formula (V₁):




wherein R^{14} , R^{15} , R^{16} and R^{17} , identical or different, independently represent an

hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably Ta(OEt)₄(OCMe₂CH₂-OMe) (TAT-DMAE), a tantalum derivative of the formula (V₂):




5 wherein R¹⁸, R¹⁹, R²⁰, R²¹ and R²², identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, a tantalum derivative of the formula (V₃):




wherein R²⁴, R²⁵ and R²⁶, identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;


10 Niobium derivatives, such as Nb(OMe)₅, Nb(OEt)₅, Nb(NMe₂)₅, Nb(NEt₂)₄, Nb(NEt₂)₅, a niobium derivative of the formula (VI₁):



wherein R²⁷, R²⁸, R²⁹ and R³⁰, identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably Nb(OEt)₄(OCMe₂CH₂-OMe) (NBT-DMAE), a niobium derivative of the formula (VI₂):



wherein R³¹, R³², R³³, R³⁴ and R³⁵, identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, a niobium derivative of the formula (VI₃):



wherein R³⁶, R³⁷ and R³⁸, identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;

25 lanthanide derivatives, such as scandium derivatives, yttrium derivatives, cerium derivatives, praseodinium derivatives, gadolinium derivatives, dysprosium derivatives, erbium derivatives, lanthanum derivatives, a derivative with at least one β-diketonate ligand or at least a cyclopentadienyl ligand optionally substituted with one or several linear or branched alkyl groups having 1 to 6 carbon atoms;

30 divalent metal derivatives, such as strontium (Sr), barium (Ba), magnesium (Mg), calcium (Ca) or zinc (Zn) derivatives, with at least one β-diketonate ligand or at least a cyclopentadienyl ligand optionally substituted

with one or several linear or branched alkyl groups having 1 to 6 carbon atoms;
other metal derivatives such as tungsten(W), molybdenum (Mo), hafnium
 (Hf) or zirconium (Zr) derivatives, for example the alkoxy derivatives, the amino
 derivatives or adducts containing these species, being understood that said
 5 derivatives are not compounds of the formula (II) as hereinbefore defined.

According to another particular embodiment, the method as hereinbefore
 defined, comprise:

- A step d), wherein the at least one M^1 metal containing precursor of the
 formula (II), and if necessary, the at least one M^2 metal containing precursor, is
 10 mixed to at least one reactant specie prior to step c).

In the context of the invention, the at least one reactant specie is chosen in
 relation to the targeted metal based film, which is expected

According to another embodiment, the reactant specie is an oxygen
 source and more particularly oxygen (O_2), oxygen containing radicals $O^\bullet$ or $OH^\bullet$,
 15 for instance generated by a remote plasma, ozone (O_3), moisture (H_2O) and
 H_2O_2 and mixture thereof.

According to another embodiment, the reactant specie is a nitrogen
 source and more particularly nitrogen (N_2), nitrogen-containing radicals such as
 $N^\bullet$, $NH^\bullet$, $NH_2^\bullet$, ammonia (NH_3), hydrazine (NH_2NH_2) and its alkyl or aryl
 20 derivatives, and mixtures thereof.

According to another embodiment, the reactant specie is both a nitrogen
 and an oxygen source and more particularly, NO, NO_2 , N_2O , N_2O_5 , N_2O_4 and
 mixtures thereof.

Depending on the ratio N/O, which is required, the reactant specie which is,
 25 if necessary, used in the method as hereinbefore defined, may be either an
 oxygen source, either a mixture of an oxygen source and of a nitrogen source
 either both an oxygen and a nitrogen source or a mixture thereof.

According to another embodiment of the invention, if the targeted metal
 based film contains carbon, such as for example without limitation metal carbide
 30 or metal carbonitride, at least one reactant specie is a carbon source more
 particularly, methane, ethane, propane, butane, ethylene, propylene, t-butylene,

According to another embodiment of the invention if the targeted metal
 based film contains silicon, such as for example without limitation metal silicide,

silico-nitride, silicate or silico-carbo-nitride, at least on reactant specie is a silicon source such as:

disiloxane, trisilylamine, disilane (Si_2H_6), trisilane (Si_3H_8), alkoxysilane of the formulas (III₁), (III₂) or (III₃), as hereinbefore defined, for example $\text{SiH}(\text{NMe}_2)_3$ (TriDMAS); $\text{SiH}_2(\text{NHtBu})_2$ (BTBAS); $\text{SiH}_2(\text{NEt}_2)_2$ (BDEAS)) and mixtures thereof.

According to another particular embodiment, the method as hereinbefore defined, comprise:

- a step d') wherein the at least one M^1 metal containing precursor of the formula (II) and if necessary, the at least one M^2 metal containing precursor, is mixed to at least one reactant specie in the reaction chamber.

The mode of introduction of the at least one M^1 metal containing precursor of the formula (II) and if necessary, the at least one M^2 metal containing precursor, and the at least one reactant specie in the reaction chamber generally depends on the mode of deposition of the film on the substrate. The metal containing precursors and the reactant species are generally introduced simultaneously in a chemical vapor deposition process, or sequentially in an atomic layer deposition process or according to several combinations, as for example in a pulsed modified atomic layer deposition process wherein the at least one M^1 metal containing precursor of the formula (II) and if necessary, the at least one M^2 metal containing precursor, are introduced together in one pulse and the at least one reactant specie is introduced in a separate pulse; or in a pulsed chemical vapor deposition process wherein the at least one M^1 metal containing precursor of the formula (II) and if necessary, the at least one M^2 metal containing precursor, are introduced by pulse and the at least one reactant specie is introduced continuously.

According to another of the invention, the at least one reactant specie is passed through a plasma system localized remotely from the reaction chamber, and decomposed to radicals.

According to another embodiment, the step (b) of the method as hereinabove defined, consists of a step (b₁) of mixing at least one first metal containing precursor of the formula (II) together with at least a second of the following precursors: $\text{M}^1(\text{NMe}_2)_4$, $\text{M}^1(\text{NEt}_2)_4$, $\text{M}^1(\text{NMeEt})_4$, $\text{M}^1(\text{mmp})_4$, $\text{M}^1(\text{OtBu})_4$, $\text{M}^1(\text{OtBu})_2(\text{mmp})_2$ and mixtures thereof and a step (b₂) of vaporizing said mixture.

According to a more particular embodiment, the invention concerns a method as hereinbefore defined, of deposition of a metal containing dielectric film comprising a compound of the formula (I), wherein the M¹ metal containing precursor is of the formula (II₁):



corresponding to the formula (II), wherein x = 0, z = 1 and R' represents the group N(R³⁹)(R⁴⁰), wherein R³⁹ and R⁴⁰, identical or different, independently represent an hydrogen atom, a linear or branched alkyl group having from one to four carbon atoms, an alkylsilyl group, wherein the alkyl group is linear or branched and has from one to four carbon atoms, a dialkylsilyl group, wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms or a trialkylsilyl group wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms

According to a more particular embodiment, the invention concerns a method as hereinbefore defined, of deposition of a metal containing dielectric film comprising a compound of the formula (I₁):




corresponding to the formula (I), wherein a=0, b = 2 and c = 0, wherein the metal containing precursor of the formula (II) is selected from the group consisting of:
 HfCp₂Cl₂, Hf(MeCp)₂Me₂, HfCp(MeCp)Cl₂, Hf(MeCp)₂Cl₂, HfCp(MeCp)Me₂, Hf(EtCp)(MeCp)Me₂, Hf(EtCp)₂Me₂, Hf(MeCp)₂(CO)₂, ZrCp₂Cl₂, Zr(MeCp)₂Me₂, ZrCp(MeCp)Cl₂, Zr(MeCp)₂Cl₂, ZrCp(MeCp)Me₂, Zr(EtCp)(MeCp)Me₂, Zr(EtCp)₂Me₂, Zr(MeCp)₂(CO)₂, Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃
 and mixtures thereof.

According to a more particular embodiment, the invention concerns a method as hereinbefore defined, of deposition of a metal containing dielectric film comprising a compound of the formula (I₂):



corresponding to the formula (I), wherein $a=0$, $1.5 \leq b \leq 2.5$ and $0 < c \leq 0.5$, wherein the metal containing precursor of the formula (II) is selected from the group consisting of: HfCp₂Cl₂, Hf(MeCp)₂Me₂, HfCp(MeCp)Cl₂, Hf(MeCp)₂Cl₂,
 5 HfCp(MeCp)Me₂, Hf(EtCp)(MeCp)Me₂, Hf(EtCp)₂Me₂, Hf(MeCp)₂(CO)₂,
 ZrCp₂Cl₂, Zr(MeCp)₂Me₂, Zr(MeCp)₂Cl₂, ZrCp(MeCp)Me₂, Zr(EtCp)(MeCp)Me₂,
 Zr(EtCp)₂Me₂, Zr(MeCp)₂(CO)₂, Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃,
 ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃,
 Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃,
 10 Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃,
 Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃,
 Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃ and
 mixture thereof.

According to a more particular embodiment, the invention concerns a
 15 method as hereinbefore defined, of deposition of a metal containing dielectric
 film comprising a compound of the formula (I₃):



corresponding to the formula (I), wherein $0 \leq a < 1$ and $c=0$, wherein the metal
 containing precursor of the formula (II) is selected from the group consisting of:
 20 HfCp₂Cl₂, Hf(MeCp)₂Me₂, HfCp(MeCp)Cl₂, Hf(MeCp)₂Cl₂, HfCp(MeCp)Me₂,
 Hf(EtCp)(MeCp)Me₂, Hf(EtCp)₂Me₂, Hf(MeCp)₂(CO)₂, ZrCp₂Cl₂, Zr(MeCp)₂Me₂,
 ZrCp(MeCp)Cl₂, Zr(MeCp)₂Cl₂, ZrCp(MeCp)Me₂, Zr(EtCp)(MeCp)Me₂,
 Zr(EtCp)₂Me₂, Zr(MeCp)₂(CO)₂, Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃,
 ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃,
 25 Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃,
 Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃,
 Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃,
 Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃ and the M²
 metal containing precursor is preferably selected from the silicon derivatives or
 30 their germanium homologues, the tantalum derivatives, lanthanide derivatives,
 and the magnesium derivatives as hereinabove defined.

According to a more particular embodiment, the invention concerns a
 method as hereinbefore defined, of deposition of a metal containing dielectric

film comprising a compound of the formula (I₄):



corresponding to the formula (I), wherein $0 \leq a < 1$ and $0 < c \leq 0.5$, wherein the metal containing precursor of the formula (II) is selected from the group consisting of HfCp₂Cl₂, Hf(MeCp)₂Me₂, HfCp(MeCp)Cl₂, Hf(MeCp)₂Cl₂, HfCp(MeCp)Me₂, Hf(EtCp)(MeCp)Me₂, Hf(EtCp)₂Me₂, Hf(MeCp)₂(CO)₂, ZrCp₂Cl₂, Zr(MeCp)₂Me₂, ZrCp(MeCp)Cl₂, Zr(MeCp)₂Cl₂, ZrCp(MeCp)Me₂, Zr(EtCp)(MeCp)Me₂, Zr(EtCp)₂Me₂, Zr(MeCp)₂(CO)₂, Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃, the M² metal containing precursor is preferably selected from the silicon derivatives or their germanium homologues, the tantalum derivatives, lanthanide derivatives, and the magnesium derivatives as hereabove defined, and at least one oxygen containing precursor and at least one nitrogen containing precursor is introduced into the reactor.

According to another embodiment the invention concerns the use of the compounds of the formula (II) as hereinbefore defined, to make dielectric films more particularly for integrated circuits or in the preparation of Metal Insulator Metal (MIM) architectures for Random Access Memories.

According to another embodiment, the invention concerns a compound the formula (II₁):



corresponding to the formula (II), wherein $x = 0$, $z = 1$ and R' represents the group N(R³⁹)(R⁴⁰), wherein R³⁹ and R⁴⁰, identical or different, independently represent an hydrogen atom, a linear or branched alkyl group having from one to four carbon atoms, an alkylsilyl group, wherein the alkyl group is linear or branched and has from one to four carbon atoms, a dialkylsilyl group, wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon atoms or a trialkylsilyl group wherein each alkyl group, identical or different from the other, is linear or branched and has from one to four carbon

atoms.

According to a particular embodiment, the invention relates to a compound of the formula (II₁) as hereinbefore defined, wherein R², R³⁹ and R⁴⁰, identical or different, independently represent a radical selected from the methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl and tert-butyl groups, and more specifically the following compounds:

Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃,
 Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃,
 ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃,
 Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃,
 HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃,
 Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃.


According to a more specific embodiment, the invention relates to the following compounds:

Zr(EtCp)(NMe₂)₃, Zr(MeCp)(NMe₂)₃, ZrCp(NMe₂)₃, Hf(EtCp)(NMe₂)₃,
 Hf(MeCp)(NMe₂)₃ and HfCp(NMe₂)₃.

Those skilled in the art will recognize that the hereinabove metal-organic compounds could be used for any other applications than vapour phase deposition processes, such as catalysts or any other industrial process or application requiring the use of metal-organic compounds...

According to another embodiment, the invention concerns a process for the preparation of a compound of the formula (II₁) as hereinabove defined, which comprises:

a step 1, consisting of the preparation of the compound of the formula (VII₁):



wherein M¹, R² and t are as hereinabove defined for the formula (II), by the reaction of M¹Cl₄ with (R²)_tCp)Na ;

a step 2, consisting of the reaction of the compound of the formula (VII₁) prepared in step 1, with NH(R³⁹)(R⁴⁰), to produce the compound of the formula (II₁).

According to a last embodiment, the invention concerns the following compounds of the formula (II) as hereinabove defined:

Hf(EtCp)₂Me₂, Zr(MeCp)₂Me₂ or Zr(EtCp)₂Me₂.

The following examples are an illustration of the various embodiments of the present invention, without being a limitation.

5

Example I: Deposition of metal oxide film M¹O₂ with M¹ being preferably hafnium and zirconium

The film to be deposited comprises a compound of the formula (I) wherein a = 0, b = 2 and c = 0.

10

To make the deposition of such film on the surface of a wafer or in a deep trench to manufacture MIM structures for DRAM, one need to vaporize the M¹ metal source as defined in step (b) and to introduce it into the reactor (preferably Hafnium or Zirconium), to inject an oxygen source, preferably moisture, oxygen or ozone into said reactor, react the products at appropriate temperature (preferably between 150°C and 350°C) and pressure (preferably between 25 Pa and 1000 Pa) for the duration necessary to achieve either a thin film deposition on the substrate or to fill out deep trenches by ALD or pulse CVD process (sequential pulse injection of metal sources are necessary in order to allow regular deposition of the oxide in the trench to progressively fill out this trench and provide no voids in the dielectric film and therefore no defect in the capacitor dielectric film).

15

20

The dielectric film shall have the desired final composition (here essentially variations of the b value around 2 modifying the ratio of precursor to oxygen source).

25

Three examples of types of compounds of the formula (II) were chosen according to the three following options a, b or c:

a) The compound of the formula (II) is chosen from Zr(MeCp)₂Me₂, Zr(EtCp)₂Me₂, Hf(MeCp)₂Me₂ and Hf(EtCp)₂Me₂.

30

Delivery of molecules in liquid form is usually carried out by bubbling an inert gas (N₂, He, Ar, ...) into the liquid and providing the inert gas plus liquid gas mixture to the reactor.

b) The compound of the formula (II) is chosen from Zr(2,4-Me₂Op)₂Me₂ and Hf(2,4-Me₂Op)₂Me₂.

c) The compound of the formula (II) is chosen from $\text{Zr}(\text{MeCp})(2,4\text{-Me}_2\text{Op})\text{Me}_2$ and $\text{Hf}(\text{MeCp})(2,4\text{-Me}_2\text{Op})\text{Me}_2$.

The oxygen source shall be preferably, without limitations, oxygen (O_2), oxygen radicals (for instance $\text{O}^\cdot$ or $\text{OH}^\cdot$), such as radicals generated by a remote plasma system, ozone, NO , N_2O , NO_2 , moisture (H_2O) and H_2O_2 .

Regarding the deposition process by itself, the reactants can be introduced into the reactor simultaneously (chemical vapor deposition), sequentially (atomic layer deposition) or different combinations (one example is to introduce metal source and the other metal source together in one pulse and oxygen in a separate pulse [modified atomic layer deposition]; another option is to introduce oxygen continuously and/or to introduce the metal source by pulse (pulsed-chemical vapor deposition).

Example II: Deposition of metal oxynitride films M^1ON with M^1 being preferably Hafnium and Zirconium

The film to be deposited comprises a compound of the formula (I) wherein $a=0$ and b and c are different from zero.

All the information given in Example I, is applicable in this Example II, except that nitrogen needs to be introduced into the reactor.

The nitrogen shall be selected from a nitrogen source selected from the group comprising nitrogen (N_2), ammonia, hydrazine and alkyl derivatives, N-containing radicals (for instance $\text{N}^\cdot$, $\text{NH}^\cdot$, $\text{NH}_2^\cdot$), NO , N_2O , NO_2 or the like.

Example III: Deposition of M^1M^2 metal oxide films with M^1 being preferably Hf or Zr and M^2 being preferably Si or Al

The film to be deposited comprises a compound of the formula (I) wherein $a \neq 0$, $b \neq 0$ and $c=0$.

All the information given in Example I, is applicable in this Example III, except that a M^2 metal source is additionally needed.

The M^2 containing precursor is also introduced into the reactor to create the M^2 source of metal. This M^2 containing precursor source shall be preferably:

a) a silicon (or germanium) source, for example $\text{Si}(\text{OH})(\text{OtBu})_3$,

SiH(NMe₂)₃ (TriDMAS); SiH₂(NHtBu)₂ (BTBAS) and SiH₂(NEt₂)₂ (BDEAS)

b) an aluminum source, for example AlMe₂(OiPr); or

c) a tantalum (or niobium) source, for example Ta(OMe)₅, Ta(OEt)₅ and Ta(OEt)(OCMe₂CH₂-OMe) (TATDMAE);

5 The invention is directed to the deposition of dielectric films of the formula I, onto a support such as a wafer, in a reactor using ALD, CVD, MOCVD, pulse CVD processes.

10 **Example IV: Deposition of M¹M² metal oxynitride films with M¹ being preferably Hf or Zr and M² being preferably Si or Al**

The film to be deposited comprises a compound of the formula (I) wherein a≠0, b≠0 and c≠0.

All the information given in Example III, is applicable in this case, except that nitrogen needs to be introduced into the reactor.

15 The nitrogen source shall be selected from the group comprising nitrogen (N₂), ammonia, hydrazine and alkyl derivatives, N-containing radicals (for instance N[•], NH[•], NH₂[•]), NO, N₂O, NO₂.

20 **Example V: Synthesis of (ethylcyclopentadienyl) tris(dimethylamino) zirconium, Zr(EtCp)(NMe₂)₃**

Zr(EtCp)(NMe₂)₃ is prepared in 3 steps.

The first step is the preparation of Zr(EtCp)Cl₃ by the reaction of (EtCp)Na over ZrCl₄;

25 The second step is the reaction LiNMe₂ with Zr(EtCp)Cl₃ to produce Zr(EtCp)(NMe₂)₃. The resulting compound is purified by distillation. Overall yield was 35%.

(Ethylcyclopentadienyl)tris(dimethylamino)zirconium has been found to be a stable liquid pale yellow compound.

TGA analysis of Zr(EtCp)(NMe₂)₃

30 The thermal gravimetric apparatus was stored in an argon glove box with moisture and oxygen content maintained below 1ppmv. Thermal gravimetric analysis was performed by placing a 35mg sample in an aluminum crucible. The sample was then heated at a 10°C/min temperature ramp from 35°C to 400°C.

The mass loss was monitored as a function of the crucible temperature. The residue level was 2.6% with full evaporation temperatures of 260°C. The resulting graph is on Figure 1.

5 **Example VI: Atomic Layer Deposition of ZrO₂ thin films using Zr(EtCp)(NMe₂)₃**

 Zr(EtCp)(NMe₂)₃ is stored into a container. The container is heated at 90°C and N₂ is used as carrier gas at a flow of 50sccm. The pressure the container is controlled at 50Torr. O₃ is used as oxygen source. The substrate is
10 heated at 350°C. During a first step, Zr(EtCp)(NMe₂)₃ is introduced into the reaction chamber during 2s. A N₂ purge of 5s is performed afterwards as second step. As third step, a pulse of O₃ is then introduced into the reaction chamber during 2s, followed by a 2s N₂ purge as fourth step. All four steps are repeated 100 times to obtain a ZrO₂ film. Self-limited atomic layer deposition is obtained.

15 Similar experiments can be performed with Hf analogs. Similar experiments can be conducted with H₂O as oxygen source.

Example VII: Metal-Organic Chemical Vapor Deposition of ZrO₂ using Zr(EtCp)(NMe₂)₃

20 Zr(EtCp)(NMe₂)₃ is stored into a container. The container is heated at 90°C and N₂ is used as carrier gas at a flow of 50sccm. The pressure in the container is controlled at 50Torr. Zr(EtCp)(NMe₂)₃ is mixed to an O₂/N₂ gas mixture into the reaction chamber. The substrate is heated at 500°C. The pressure inside the reaction chamber is set at 10Torr. A film of zirconium oxide is
25 obtained.

 Similar experiments can be performed with Hf analogs.


Example VIII: Comparison of Zr(EtCp)(NMe₂)₃ and Zr(NEtMe)₄ thermal behavior

30 Thermal gravimetric analysis is performed on Zr(EtCp)(NMe₂)₃ and Zr(NEtMe)₄ in similar conditions. Thermal gravimetric apparatus was stored in an argon glove box with moisture and oxygen content maintained below 1ppmv. Thermal gravimetric analysis was performed by placing a 35mg sample in an

aluminum crucible. The sample was then heated at a 10°C/min temperature ramp from 35°C to 400°C. The mass loss was monitored as a function of the crucible temperature. In closed cup configuration, a pierced pan (0.8 mm) is placed over the crucible containing the metal-organic compound to slow down the evaporation. This indicates the thermal stability at higher temperature. The results indicates that $\text{Zr}(\text{EtCp})(\text{NMe}_2)_3$ is much more thermally stable than $\text{Zr}(\text{NEtMe})_4$, making it further attractive for use as vapor phase precursor. The results are shown on Figure 2.

CLAIMS

1. Method of deposition on a substrate, of at least one metal containing dielectric film comprising a compound of the formula (I):



wherein:

$$0 \leq a < 1,$$

$$0 < b \leq 3, \text{ preferably } 1.5 \leq b \leq 2.5;$$

$$0 \leq c \leq 1,$$

M^1 represents a metal selected from hafnium (Hf) and zirconium (Zr); and

M^2 represents a metal atom selected from magnesium (Mg), calcium (Ca), zinc (Zn), bore (B), aluminum (Al), indium (In), silicon (Si), germanium (Ge), tin (Sn), hafnium (Hf), zirconium (Zr), titanium (Ti), vanadium (V), niobium (Nb), tantalum (Ta); and the Lanthanides atoms, more particularly scandium (Sc), yttrium (Y) and lanthanum (La) and rare-earth metal atoms,

which comprises the following steps:

- A step a) of providing a substrate into a reaction chamber;
- A step (b) of vaporizing at least one M^1 metal containing precursor selected from: $Zr(MeCp)(NMe_2)_3$, $Zr(EtCp)(NMe_2)_3$, $ZrCp(NMe_2)_3$, $Zr(MeCp)(NEtMe)_3$, $Zr(EtCp)(NEtMe)_3$, $ZrCp(NEtMe)_3$, $Zr(MeCp)(NEt_2)_3$, $Zr(EtCp)(NEt_2)_3$, $ZrCp(NEt_2)_3$, $Zr(iPr_2Cp)(NMe_2)_3$, $Zr(tBu_2Cp)(NMe_2)_3$, $Hf(MeCp)(NMe_2)_3$, $Hf(EtCp)(NMe_2)_3$, $HfCp(NMe_2)_3$, $Hf(MeCp)(NEtMe)_3$, $Hf(EtCp)(NEtMe)_3$, $HfCp(NEtMe)_3$, $Hf(MeCp)(NEt_2)_3$, $Hf(EtCp)(NEt_2)_3$, $HfCp(NEt_2)_3$, $Hf(iPr_2Cp)(NMe_2)_3$, $Hf(tBu_2Cp)(NMe_2)_3$, to form a first gas phase metal source;

- Optionally a step b') of vaporizing at least one M^2 metal containing precursor, M^2 being as hereinabove defined; to form an optional second gas phase metal source;

- A step c) of introducing said first gas phase metal source and said optional second gas phase metal source, in the reaction chamber, in order to provoke their contact with said substrate, to generate the deposition of a metal containing

dielectric film comprising a compound of the formula (I) as hereinbefore defined, on said substrate.

2. Method according to claim 1, wherein the vaporization step b) and the
5 vaporization step b') are combined in one vaporization step b'') of both sources.

3. Method according to one of claim 1 or 2 wherein the M^2 metal containing precursor, is selected from the group consisting of:


Silicon derivatives or their Germanium homologues, such as:

10 disiloxane, trisilylamine, disilane, trisilane, alkoxysilane of the formula:
(III₁)



wherein: $0 \leq x \leq 3$ and R^3 represents a linear or branched hydrocarbon group having 1 to 6 carbon atoms;

15 silanol derivative of the formula (III₂):



wherein: $1 \leq x \leq 3$ and R^4 represents a linear or branched alkyl group, having 1 to 6 carbon atoms, preferably $\text{Si}(\text{OH})(\text{OR}^4)_3$ and more preferably $\text{Si}(\text{OH})(\text{OtBu})_3$;

aminosilane derivative of the formula (III₃):




wherein: $0 \leq x \leq 3$ and R^5 and R^6 are identical or different and independently represents an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably $\text{SiH}(\text{NMe}_2)_3$ (TriDMAS); $\text{SiH}_2(\text{NHtBu})_2$ (BTBAS); $\text{SiH}_2(\text{NEt}_2)_2$ (BDEAS)) and mixtures thereof;

25 Aluminum derivatives, such as trimethylaluminum $[\text{Al}(\text{CH}_3)_3]$, dimethyl aluminum hydride $[\text{AlH}(\text{CH}_3)_2]$, alkoxyalane of the formula (IV₁):




wherein: $0 \leq x \leq 3$ and R^7 represents a linear or branched alkyl having 1 to 6 carbon atom, and R^8 , identical to or different from R^7 , represents an hydrogen atom, or preferably $\text{AlR}^9\text{R}^{10}(\text{OR}^7)$, with R^9 and R^{10} identical or different, which
30 independently represent an linear or branched alkyl having 1 to 6 carbon atoms, most preferably $\text{AlMe}_2(\text{OiPr})$;

amidoalane of the formula (IV₂):




wherein: $0 \leq x \leq 3$ and R^{12} and R^{13} identical or different, represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, and R^{11} , identical to or different from R^7 and , represents an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;


Tantalum derivatives, such as: $\text{Ta}(\text{OMe})_5$, $\text{Ta}(\text{OEt})_5$, $\text{Ta}(\text{NMe}_2)_5$, $\text{Ta}(\text{NEt}_2)_5$, $\text{Ta}(\text{NEt}_2)_5$, a tantalum derivative of the formula (V_1):



wherein R^{14} , R^{15} , R^{16} and R^{17} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably $\text{Ta}(\text{OEt})_4(\text{OCMe}_2\text{CH}_2-\text{OMe})$ (TAT-DMAE), a tantalum derivative of the formula (V_2):




wherein R^{18} , R^{19} , R^{20} , R^{21} and R^{22} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, a tantalum derivative of the formula (V_3):




wherein R^{24} , R^{25} and R^{26} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;


Niobium derivatives, such as $\text{Nb}(\text{OMe})_5$, $\text{Nb}(\text{OEt})_5$, $\text{Nb}(\text{NMe}_2)_5$, $\text{Nb}(\text{NEt}_2)_4$, $\text{Nb}(\text{NEt}_2)_5$, a niobium derivative of the formula (VI_1):



wherein R^{27} , R^{28} , R^{29} and R^{30} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, preferably $\text{Nb}(\text{OEt})_4(\text{OCMe}_2\text{CH}_2-\text{OMe})$ (NBT-DMAE), a niobium derivative of the formula (VI_2):



wherein R^{31} , R^{32} , R^{33} , R^{34} and R^{35} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms, a niobium derivative of the formula (VI_3):



wherein R^{36} , R^{37} and R^{38} , identical or different, independently represent an hydrogen atom or a linear or branched alkyl having 1 to 6 carbon atoms;

lanthanide derivatives, such as scandium derivatives, yttrium derivatives, cerium derivatives, praeisidium derivatives, gadolinium derivatives or Nd derivatives, a derivative with at least one β -diketonate ligand or at least a cyclopentadienyl ligand optionally substituted with one or several linear or
 5 branched alkyl groups having 1 to 6 carbon atoms;

divalent metal derivatives, such as strontium (Sr), barium (Ba), magnesium (Mg), calcium (Ca) or zinc (Zn) derivatives, with at least one β -diketonate ligand or at least a cyclopentadienyl ligand optionally substituted with one or several linear or branched alkyl groups having 1 to 6 carbon atoms;

10 other metal derivatives such as tungsten (W), molybdenum (Mo), hafnium (Hf) or zirconium (Zr) derivatives, for example the alkoxy derivatives, the amino derivatives or adducts containing these species.

4. Method of Claim 3, wherein the M^2 metal containing precursor is an
 15 hafnium (Hf) derivative.

5. Method according to one of Claim 1 to 4, which further comprises:

- A step d), wherein the at least one M^1 metal containing precursor, and if necessary, the at least one M^2 metal containing precursor, is mixed to at least
 20 one reactant specie prior to step c).

6. Method according to one of Claim 1 to 5, which further comprises:

- a step d') wherein the at least one M^1 metal containing precursor and if necessary, the at least one M^2 metal containing precursor, is mixed to at least
 25 one reactant specie in the reaction chamber.

7. Method according to one of Claim 1 to 6, of deposition of a metal containing dielectric film comprising a compound of the formula (I₁):



30 corresponding to the formula (I), wherein $a=0$, $b=2$ and $c=0$, wherein the metal containing precursor is selected from the group consisting of: $Zr(MeCp)(NMe_2)_3$, $Zr(EtCp)(NMe_2)_3$, $ZrCp(NMe_2)_3$, $Zr(MeCp)(NEtMe)_3$, $Zr(EtCp)(NEtMe)_3$, $ZrCp(NEtMe)_3$, $Zr(MeCp)(NEt_2)_3$, $Zr(EtCp)(NEt_2)_3$, $ZrCp(NEt_2)_3$,

Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃ and mixtures thereof.

5

8. Method according to one of Claim 1 to 6, of deposition of a metal containing dielectric film comprising a compound of the formula (I₂):




corresponding to the formula (I), wherein a=0, 1.5 ≤ b ≤ 2.5 and 0 < c ≤ 0.5,

10 wherein the metal containing precursor is selected from the group consisting of:

Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃,
 15 HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃ and mixture thereof.


9. Method according to one of Claim 1 to 6, of deposition of a metal containing dielectric film comprising a compound of the formula (I₃):



20 corresponding to the formula (I), wherein 0 ≤ a < 1 and c=0, wherein the metal containing precursor is selected from the group consisting of

Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃, Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃, ZrCp(NEt₂)₃,
 25 Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃, Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃, HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃, Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃ and the M² metal containing precursor is preferably selected from the silicon derivatives or their germanium homologues, the tantalum
 30 derivatives, lanthanide derivatives, and the magnesium derivatives as hereabove defined.

10. Method according to one of Claim 1 to 6, of deposition of a metal containing dielectric film comprising a compound of the formula (I₄):



corresponding to the formula (I), wherein $0 \leq a < 1$ and $0 < c \leq 0.5$, wherein the
 5 metal containing precursor is selected from the group consisting of
 Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃,
 Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃,
 ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃,
 Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃,
 10 HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃,
 Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃, the M² metal containing precursor is
 preferably selected from the silicon derivatives or their germanium homologues,
 the tantalum derivatives, lanthanide derivatives, and the magnesium derivatives
 as hereabove defined, and at least one oxygen containing precursor and at least
 15 one nitrogen containing precursor is introduced into the reactor.

11. Method according to one of Claim 1 to 10, wherein said M¹ metal containing precursor is ZrCp(NMe₂)₃.

20 12. The use of the compounds selected from the group consisting of
 Zr(MeCp)(NMe₂)₃, Zr(EtCp)(NMe₂)₃, ZrCp(NMe₂)₃, Zr(MeCp)(NEtMe)₃,
 Zr(EtCp)(NEtMe)₃, ZrCp(NEtMe)₃, Zr(MeCp)(NEt₂)₃, Zr(EtCp)(NEt₂)₃,
 ZrCp(NEt₂)₃, Zr(iPr₂Cp)(NMe₂)₃, Zr(tBu₂Cp)(NMe₂)₃, Hf(MeCp)(NMe₂)₃,
 Hf(EtCp)(NMe₂)₃, HfCp(NMe₂)₃, Hf(MeCp)(NEtMe)₃, Hf(EtCp)(NEtMe)₃,
 25 HfCp(NEtMe)₃, Hf(MeCp)(NEt₂)₃, Hf(EtCp)(NEt₂)₃, HfCp(NEt₂)₃,
 Hf(iPr₂Cp)(NMe₂)₃, Hf(tBu₂Cp)(NMe₂)₃, to make dielectric films more particularly
 for integrated circuits or in the preparation of Metal Insulator Metal (MIM)
 architectures for Random Access Memories.