

Optical array converting UV

This invention is an optical array converting UV radiation, especially contained in sunlight.

- 5 The spectral characteristic of the transmission of the filter is similar to the sensitivity of human skin to sun burning. That sensitivity is described by the widely recognized Diffey Standard.

By now there are a few UV measuring devices based on an optical absorptive filter:

- 10 CASIO Computer Ltd. manufactures a device called "CASIO UC-120 UV", which has an optical array containing absorptive filter made of material similar to Schott UG-11 and a photodiode. The spectral characteristic of the device doesn't match the Diffey Standard. The device illuminated by sunlight is too sensitive to UV-A, that has low burning power. US patent 5.196.705 describes a device measuring the intensity and dose of UV. The device
- 15 has an optical array containing: an absorptive filter made of material similar to Schott UG-11, a photo-luminescentive material and a photodiode. The spectral characteristic of the device doesn't match the Diffey Standard. The device is too sensitive to UV-A comparing to its sensitivity to UV-B.

20

Description of the invention

- The invention solves the problem of constructing a device equipped with an optical array converting UV, visible and IR. radiation that has the spectral characteristic of the
- 25 transmission similar to the Diffey Standard.

Definition of the relative internal transmission of a set of filters:

$$T_{int}^{rel}(\lambda) = T_{int}(\lambda) / T_{int}(310) \quad (1)$$

- 30 where:

λ	wavelength in nano-meters
$T_{int}^{rel}(\lambda)$	relative internal transmission for λ wavelength
$T_{int}(\lambda)$	internal transmission for λ wavelength
$T_{int}(310)$	internal transmission for 310nm wavelength

35

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

REPLACED SHEETS		SG
☒ Description	: paged 1 to paged 6	
☒ Claim(s)	: paged 2 to paged 8	
☐ Drawing(s)	: paged to paged	
☐ Abstract	: paged to paged	
DATE OF RECEIPT		

Note that the total internal transmission of the set of absorptive filters is equal to the product of internal transmissions of each consecutive filter.

Definition of the relative transmission of a set of filters:

$$T^{rel}(\lambda) = T(\lambda)/T(310) \quad (2)$$

where:

λ	wavelength in nano-meters
$T^{rel}(\lambda)$	relative transmission for λ wavelength
$T(\lambda)$	transmission for λ wavelength
$T(310)$	transmission for 310nm wavelength

The Diffey spectral characteristics will be denoted as $D(\lambda)$ (3)

where:

λ	wavelength in nano-meters
-----------	---------------------------

This Sheet Has Been Replaced



In the first solution the array contains a system of absorptive filters to block visible and IR. radiation, a system of interference filters modifying transmission of UV and/or blocking visible and IR. radiation, scattering elements, elements forming the light beam. Interference filter/filters is/are made of layers of materials having high and low UV refractive indexes.

According to the invention one of the system of interference filters has layers made of Hafnium oxide and/or Zirconium oxide. A collimator placed in the optical path forms the light beam. The collimator can have surfaces highly absorbing light. At the beginning of the optical path a scatterer is placed to achieve non-directional characteristic of the array. The scatterer can be made of PTFE.

In the second solution the array contains the first system of absorptive filters to partly block UV-A, the second system of absorptive filters to block visible and IR. radiation and may contain scattering elements and/or system/systems of interference filter/filters.

The first system of absorptive filters has internal relative transmission $T^{rel}_{int}(\lambda)$: between 0 and 0.2 for $\lambda=290\text{nm}$, between 0.34 and 0.7 for $\lambda=300\text{nm}$, between 0.5 and 0.8 for $\lambda=320\text{nm}$, between 0.04 and 0.36 for $\lambda=330\text{nm}$, between $10\text{E-}3$ and 0.1 for $\lambda=340\text{nm}$, between $7*10\text{E-}6$ and 0.02 for $\lambda=350\text{nm}$, between $2*10\text{E-}7$ and $7*10\text{E-}3$ for $\lambda=360\text{nm}$, between $2*10\text{E-}7$ and $7*10\text{E-}3$ for $\lambda=370\text{nm}$, between $2*10\text{E-}5$ and 0.03 for $\lambda=380\text{nm}$,



70 between 2×10^{-3} and 0.14 for $\lambda=390\text{nm}$. The total optical thickness of the first system of absorptive filters is between 0.5 and 2mm.

The second system of absorptive filters has internal relative transmission $T_{\text{rel}}^{\text{rel}}(\lambda)$: between 0 and 0.3 for $\lambda=290\text{nm}$, between 0.7 and 0.8 for $\lambda=300\text{nm}$, between 1 and 1.3 for $\lambda=320\text{nm}$, between 1 and 1.4 for $\lambda=330\text{nm}$, between 1 and 1.3 for $\lambda=340\text{nm}$, between 1 and 1.12 for
75 $\lambda=350\text{nm}$, between 0.6 and 0.8 for $\lambda=360\text{nm}$, between 0.14 and 0.3 for $\lambda=370\text{nm}$, between 10^{-3} and 0.015 for $\lambda=380\text{nm}$, between 10^{-10} and 10^{-6} for $\lambda=390\text{nm}$. The total optical thickness of the first system of absorptive filters is between 0.5 and 10mm.


At the beginning of the optical path a scatterer is placed to achieve non-directional characteristic of the array. The scatterer can be made of PTFE. In the optical path
80 additional system/systems of interference filters can be placed to block visible and IR. radiation and/or to modify transmission in UV range.

This invention allows producing a cheap and simple optical array with a spectral characteristics in the UV-A and UV-B range following the human skin sensitivity described
85 by Diffey Standard. The scatterer ensures non-directional characteristics of the array. Other standards of skin sensitivity to UV-A and UV-B burning can also be easily followed.

The invention is presented on the block diagrams where Fig1 presents the construction of the version 1 of the optical array, Fig2 presents the construction of another variant of the
90 invention presented on Fig1, Fig3 presents the construction of the version 2 of the optical array, Fig4 presents the construction of the of the version 3 of the optical array. Fig. 5 presents $T^{\text{rel}}(\lambda) \cdot D(310) / T^{\text{rel}}(310)$ for optical array from Fig 2 in comparison with the Diffey Standard $D(\lambda)$. Fig. 6 presents $T^{\text{rel}}(\lambda) \cdot D(310) / T^{\text{rel}}(310)$ for optical array from Fig 3 in comparison with the Diffey Standard $D(\lambda)$, Fig. 7 presents $T^{\text{rel}}(\lambda) \cdot D(310) / T^{\text{rel}}(310)$ for
95 optical array from Fig 4 in comparison with the Diffey Standard $D(\lambda)$.

Description of the version 1.

The array contains: the layer 1 that scatters light, a collimator 2, an absorptive filter 3 that makes a system of absorptive filters, a set of interference filters 4 that makes a system of
100 interference filters. The absorptive filter 3 is made of material transparent to UV and blocking visible and IR. radiation. That property has M1 material, with a characteristics presented in the table below.



In that example a scatterer 1 is made of PTFE, and the absorptive filter 3 is a plano-parallel plate, 8mm thick, made of M1 material Schott UG-11 like. The set of interference filters 4 that is placed on the absorptive filter's 3 surface consists of 38 layers of Hafnium oxide and/or Zirconium oxide and Silica oxide.

The scatterer 1 ensures non-directional characteristics of the array. The collimator 2 forms the light beam. To achieve desired spectral characteristics the light beam passes through the absorptive filter 3 and the interference filter 4.

110

In the other variant of the version 1, that is shown on the Fig 2, the array contains: the layer 5 that scatters light, a collimator 6, absorptive filter 7 that makes a system of absorptive filters and a first set of interference filters 8 and a second set of interference filters 9 that both make a system of interference filters. The absorptive filter 7 is made of material transparent to UV and blocking visible and IR. radiation. That property has M1 material, with a characteristics presented in the table below.

In that example a scatterer 5 is made of PTFE, and absorptive filter 7 is a plano-parallel plate, 8mm thick, made of M1 material. Schott UG-11 like. The first set of interference filters 8 and the second set of interference filters 9 are placed on the absorptive filter's 7 surfaces and together consists of 62 layers of Hafnium oxide and/or Zirconium oxide and Silica oxide.

The scatterer 5 ensures non-directional characteristics of the array. The collimator 6 forms the light beam. To achieve desired spectral characteristics the light beam passes through the first interference filter 8, the absorptive filter 7 and the second interference filter 9.

On the Fig 5 chart the $T^{rel}(\lambda) \cdot D(310)/T^{rel}(310)$ characteristics of the array is plotted as a broken line, the Diffey Standard is plotted as a solid line. On the chart these two curves are close to each other in the 310-325nm range.

Description of the version 2.

The array contains: the layer 10 that scatters light, a first absorptive filter 11 that makes a first system of absorptive filters, a second absorptive filter 12 that makes a second system of absorptive filters. The first absorptive filter 11 is made of material transparent to UV with decreasing transmission when the wavelength is changed from 320 to 350nm, the second absorptive filter 12 is made of material transparent to UV and blocking visible and IR. radiation. That property have materials M2 and M1 respectively, with characteristics presented in the table below.

In that example a scatterer 10 is made of PTFE, the first absorptive filter 11 is a plano-parallel plate, 1.5mm thick, made of M2 material, Schott GG-19 like, the second absorptive filter 12 is a plano-parallel plate, 8 mm thick, made of M1 material, Schott UG-11 like.

The scatterer 10 ensures non-directional characteristics of the array. To achieve desired spectral characteristics the light beam passes through the first absorptive filter 11 and the second absorptive filter 12.

On the Fig 6 chart $T^{rel}(\lambda)*D(310)/T^{rel}(310)$ characteristics of the array is plotted as a broken line, the Diffey Standard is plotted as a solid line.

Description of the version 3.

The array contains: a first absorptive filter 13 that makes a first system of absorptive filters, a second absorptive filter 14 that makes a second system of absorptive filters and a first set of interference filters 15 and a second set of interference filters 16 that both make a system of interference filters. The first absorptive filter 13 is made of material transparent to UV with decreasing transmission when wavelength is changed from 320 to 350nm, the second absorptive filter 14 is made of material transparent to UV and blocking visible and IR radiation. That property have materials M2 and M1 respectively, with characteristics presented in the table below. Interference filters are constructed to block visible and IR radiation and/or to modify transmission characteristics in UV.

In that example the first absorptive filter 13 is a plano-parallel plate, 1.5mm thick, made of M2 material, Schott GG-19 like. The second absorptive filter 14 with interference filters 15, 16 placed on the filter 14 surfaces are made together by Schott as Schott DUG-11 filter.

To achieve desired spectral characteristics the light beam passes through the first absorptive filter 13, the first interference filter 15, the second absorptive filter 14 and the second interference filter 16.

On the Fig 7 chart $T^{rel}(\lambda)*D(310)/T^{rel}(310)$ characteristics of the array is plotted as a broken line, the Diffey Standard is plotted as a solid line.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

TABLE of relative internal transmission $T_{int}^{rel}(\lambda)$

170

λ [nm]		290	300	310	320	330	340	350
M1 glass, 8 mm thick	minimal value	0	0.7	1	1.0	1.0	1.0	1.0
	maximal value	0.3	0.8	1	1.3	1.4	1.3	1.12
M2 glass, 1.5 mm thick	minimal value	0	0.34	1	0.5	0.04	10E-3	7*10E-6
	maximal value	0.2	0.7	1	0.8	0.36	0.1	0.02

λ [nm]		360	370	380	390
M1 glass, 8 mm thick	minimal value	0.6	0.14	10E-3	10E-10
	maximal value	0.8	0.3	0.015	10E-6
M2 glass, 1.5 mm thick	minimal value	2*10E-7	2*10E-7	2*10E-5	2*10E-3
	maximal value	7*10E-3	7*10E-3	0.03	0.14

175 Data in tables above are $T_{int}^{rel}(\lambda)$ characteristics of plano-parallel plates made of M1, M2 with given thickness.

The exact values of $T_{int}^{rel}(\lambda)$ are described in the example constructions. These data are example values and it is obvious that the invention is not restricted to them.

180 The optical array in the example constructions has the spectral characteristics similar to human skin sensitivity to UV contained in sunlight. Fig. 5 presents $T^{rel}(\lambda)*D(310)/T^{rel}(310)$ chart for optical array from Fig 2 in comparison with the Diffey Standard $D(\lambda)$, Fig. 6 presents $T^{rel}(\lambda)*D(310)/T^{rel}(310)$ chart for optical array from Fig 3 in comparison with the Diffey Standard $D(\lambda)$, Fig. 7 presents $T^{rel}(\lambda)*D(310)/T^{rel}(310)$ chart for optical array from Fig 4 in comparison with the Diffey Standard $D(\lambda)$. The biggest discrepancies between the characteristics and the Diffey Standard are for UV-C that is absent in sunlight and UV-A

185 that has a minimal burning power comparing with total burning power of sun UV.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Claims

What is claimed is:



1. The optical array converting UV, visible and IR. radiation, especially contained in
 190 sunlight, with a spectral characteristics following the Diffey Standard comprising a
 system of absorptive filters to block visible and IR. radiation, a system of interference
 filters to modify transmission characteristics in the UV range and/or to block visible and
 IR. radiation, scattering elements and elements to form light beam. The interference
 filter is made of layers of high and low refractive indexes for UV light and some
 195 interference layers in the systems of interference filters (4), (8), (9) are made of
 Hafnium oxide and/or Zirconium oxide.
2. The array in claim 1 with the system of absorptive filters (3), (7) which internal
 , transmission for a given wavelength divided by the internal transmission of that second
 system for 310nm light are: between 0 and 0.3 for $\lambda=290\text{nm}$, between 0.7 and 0.8 for
 200 $\lambda=300\text{nm}$, between 1 and 1.3 for $\lambda=320\text{nm}$, between 1 and 1.4 for $\lambda=330\text{nm}$, between 1
 and 1.3 for $\lambda=340\text{nm}$, between 1 and 1.12 for $\lambda=350\text{nm}$, between 0.6 and 0.8 for
 $\lambda=360\text{nm}$, between 0.14 and 0.3 for $\lambda=370\text{nm}$, between $10\text{E}-3$ and 0.0015 for
 $\lambda=380\text{nm}$, between $10\text{E}-10$ and $10\text{E}-6$ for $\lambda=390\text{nm}$.
3. The array in claim 1 comprising a scatterer (1), (5) at the beginning of the optical path
 205 to achieve non-directional characteristics of the array.
4. The array in claim 3 comprising the scatterer made of PTFE.
5. The array in claim 1 comprising a collimator (2), (6) placed in the optical path to form
 the light beam passing through the array. The collimator surface could be highly
 absorptive to the light.
- 210 6. The optical array converting UV, visible and IR. radiation, especially contained in
 sunlight, with a spectral characteristics following the Diffey Standard comprising a first
 system of absorptive filters to partly block UV-A light, a second system of absorptive
 filters to block visible and IR. radiation and optionally scattering elements and/or
 system/systems of interference filters. The internal transmission of the first system of
 215 absorptive filters divided by the internal transmission of that first system for 310nm
 light are: between 0 and 0.2 for $\lambda=290\text{nm}$, between 0.34 and 0.7 for $\lambda=300\text{nm}$, between
 0.5 and 0.8 for $\lambda=320\text{nm}$, between 0.04 and 0.36 for $\lambda=330\text{nm}$, between $10\text{E}-3$ and 0.1
 for $\lambda=340\text{nm}$, between $7*10\text{E}-6$ and 0.02 for $\lambda=350\text{nm}$, between $2*10\text{E}-7$ and $7*10\text{E}-3$

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



- for $\lambda=360\text{nm}$, between $2 \cdot 10^{-7}$ and $7 \cdot 10^{-3}$ for $\lambda=370\text{nm}$, between $2 \cdot 10^{-5}$ and 0.03
220 for $\lambda=380\text{nm}$, between $2 \cdot 10^{-3}$ and 0.14 for $\lambda=390\text{nm}$.
7. The array in claim 6 with total optical thickness of the first system of absorptive filters (11), (13) between 0.5 and 2mm.
8. The array in claim 6 with the second system of absorptive filters (12), (14) which
225 internal transmission for a given wavelength divided by the internal transmission of that second system for 310nm light are: between 0 and 0.3 for $\lambda=290\text{nm}$, between 0.7 and 0.8 for $\lambda=300\text{nm}$, between 1 and 1.3 for $\lambda=320\text{nm}$, between 1 and 1.4 for $\lambda=330\text{nm}$, between 1 and 1.3 for $\lambda=340\text{nm}$, between 1 and 1.12 for $\lambda=350\text{nm}$, between 0.6 and 0.8 for $\lambda=360\text{nm}$, between 0.14 and 0.3 for $\lambda=370\text{nm}$, between 10^{-3} and 0.015 for $\lambda=380\text{nm}$, between 10^{-10} and 10^{-6} for $\lambda=390\text{nm}$.
- 230 9. The array in claim 6 with total optical thickness of the second system of absorptive filters (12), (14) between 0.5 and 10mm.
10. The array in claim 6 comprising a scatterer at the beginning of the optical path to achieve non-directional characteristics of the array.
11. The array in claim 10 comprising the scatterer made of PTFE.
- 235 12. The array in claim 6 comprising additional interference filter/filters (15), (16) to block visible and IR. radiation and/or to modify a transmission characteristics in the UV range.
13. The array in claim 12 comprising layers made of Hafnium oxide and/or Zirconium oxide as elements of the set of interference filters (15), (16).

This Sheet Has Been Replaced

