THIS SHEET HAS BEEN REPLACED

ABSTRACT

The invention relates to a solarization-stable aluminosilicate glass which has the following composition (in % by weight, based on oxide):
SiO_2 45-68; Al_2O_3 > 5-18; Na_2O 0-5; K_2O > 9-15; where $Na_2O + K_2O \geq 10$; CaO 0-10; SrO 0.5-18; BaO 0-10; where CaO + SrO + BaO 8- < 17; ZrO_2 1-6; TiO_2 0.2-5.
The glass is particularly suitable as substrate glass in display technology, in particular for plasma display panels.

This Sheet Has Been Replaced