

PROBE CARDS INCLUDING NANOTUBE PROBES AND METHODS OF FABRICATING

BACKGROUND

5 1. Field:

[0001] The disclosed subject matter relates to a probe cards for testing the performance of integrated circuits and more particularly to probe cards including nanotube probes and methods of manufacturing probe cards including nanotube probes.

2. Description of the Related Art:

10 [0002] In the computer chip manufacturing industry, it is necessary to test the performance of integrated circuits (IC's) at various points in the manufacturing process, in order to weed out defective components and to monitor the manufacturing process. Various technologies have been employed for this purpose, though all are challenged due to the increasing demands of the IC manufacturing process.

15 [0003] In order to electrically test the circuitry, it is necessary to make contact with pads on the IC, i.e. to "probe" the IC. The probes must be able to align very accurately with the IC pads to be tested, and to provide sufficient current to power the IC as well as provide reliable, low resistance electrical contact at low inductance such that the test signals are not distorted. As IC manufacturing progresses to increasingly smaller
20 geometries, increasing number of transistors, and higher clock frequencies, it challenges the abilities of existing technologies to probe the IC. The smaller geometries result in reduced test pad dimensions, which then require the probes to be better aligned to insure that they do not miss the pads. The increasing number of transistors and higher clock frequencies require that the probes be able to provide an increasing amount of current
25 without burning up or "fusing" the probe, or reducing the probes physical characteristics such as spring force and fatigue life.

[0004] IC manufacturers increasingly desire that the IC's be tested at elevated ambient temperature to better simulate worst-case environmental conditions or to perform accelerated life testing. This places an increasing burden on the probe to be able to
30 provide the high current levels at elevated temperatures of 150 degrees Celsius. The increased processing speed of the IC's further requires that the probes have low inductance

so as not to distort the clock and signal waveforms that are fed to the IC, and to accurately transfer the waveforms from the IC to the monitoring test equipment.

SUMMARY

[0005] One aspect of the disclosed subject matter is a method of fabricating a plurality of carbon nanotube-bundle probes on a substrate. In some embodiments, the method includes the following: providing a substrate having a top surface and a bottom surface; forming an array of electrically conductive pads on the top surface, the array of electrically conductive pads being formed to mirror an array of pads on an integrated circuit that is to be tested; applying a catalyst for promoting growth of carbon nanotubes on each of the array of electrically conductive pads; heating the substrate in a carbon-rich environment thereby growing nanotubes extending upwardly from each of the array of electrically conductive pads and above the top surface of the substrate thereby forming a plurality of carbon nanotube-bundle probes extending upwardly above the top surface of the substrate; and capping each of the plurality of carbon nanotube-bundle probes with an electrically conductive material.

[0006] Another aspect of the disclosed subject matter is a method of fabricating a plurality of carbon nanotube-bundle probes on a substrate. In some embodiments, the method includes the following: providing a substrate having a top surface, a bottom surface, and an array of micro-holes drilled through and connecting the top and bottom surfaces; providing a metal foil having top and bottom surfaces, the metal foil being configured for joining with the bottom surface of the substrate; applying a catalyst for promoting growth of carbon nanotubes; joining the top surface of the metal foil to the bottom surface of the substrate; heating the metal foil and the substrate in a carbon-rich environment thereby causing each of the array of micro-holes in the substrate to expand thereby forming an array of expanded micro-holes in the substrate; growing nanotubes extending upwardly from the top surface of the metal foil through each of the array of expanded micro-holes in the substrate and above the top surface of the substrate thereby forming a plurality of carbon nanotube-bundle probes extending upwardly above the top surface of the substrate, each of the plurality of carbon nanotube-bundle probes substantially filling a respective one of the array of expanded micro-holes; cooling the metal foil and the substrate thereby causing each of the array of expanded micro-holes in the substrate to contract thereby forming an array of contracted micro-holes in the

substrate, each one of the array of contracted micro-holes providing a shrink fit around a
respective one of the plurality of carbon nanotube-bundle probes contained therein so as to
substantially secure the respective one of the plurality of carbon nanotube-bundle probes
contained therein to the substrate; removing the metal foil from the bottom surface of the
5 substrate; and plating or solder bumping each of the plurality of carbon nanotube-bundle
probes adjacent the bottom surface of the substrate.

[0007] Another aspect of the disclosed subject matter is a method of fabricating a
plurality of carbon nanotube-bundle probes extending from opposing surfaces of a
substrate. In some embodiments, the method includes the following: providing a substrate
10 having a top surface, a bottom surface, and an array of micro-holes drilled through and
connecting the top and bottom surfaces; providing a first metal foil having top and bottom
surfaces and an array of holes drilled through and connecting the top and bottom surfaces,
the array of holes being arranged to align with the array of micro-holes in the substrate;
providing a second metal foil having top and bottom surfaces, the metal foil being
15 configured for joining with the bottom surface of the first metal foil; applying a catalyst
for promoting growth of carbon nanotubes; joining the top surface of the first metal foil to
the bottom surface of the substrate so that the array of holes is substantially aligned with
the array of micro-holes in the substrate; joining the top surface of the second metal foil to
the bottom surface of the first metal foil; heating the second metal foil and the substrate in
20 a carbon-rich environment thereby causing each of the array of micro-holes in the
substrate to expand thereby forming an array of expanded micro-holes in the substrate;
growing nanotubes extending upwardly from the top surface of the second metal foil
through each of the array of holes in the first metal foil and the array of expanded micro-
holes in the substrate and above the top surface of the substrate thereby forming a plurality
25 of carbon nanotube-bundle probes extending upwardly above the top surface of the
substrate, each of the plurality of carbon nanotube-bundle probes substantially filling a
respective one of the array of expanded micro-holes; cooling the second metal foil and the
substrate thereby causing each of the array of expanded micro-holes in the substrate to
contract thereby forming an array of contracted micro-holes in the substrate, each one of
30 the array of contracted micro-holes providing a shrink fit around a respective one of the
plurality of carbon nanotube-bundle probes contained therein so as to substantially secure
the respective one of the plurality of carbon nanotube-bundle probes contained therein to

the substrate; and removing the first and second metal foils from the bottom surface of the substrate.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] For the purpose of illustrating the invention, the drawings show a form of the disclosed subject matter that is presently preferred. However, it should be understood that
5 the disclosed subject matter is not limited to the precise arrangements and instrumentalities shown in the drawings, wherein:

FIG. 1 is a diagram of a method of fabricating a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

10 FIG. 2 is a side elevation view of a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

FIG. 3 is a diagram of a method of fabricating a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

15 FIGS. 5A and 5B are side elevation views of an assembly including probe cards having nanotube probes according to some embodiments of the disclosed subject matter;

... FIG. 6 is a diagram of a method of fabricating a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

FIGS. 7A and 7B are side elevation views of a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

20 FIGS. 8A and 8B are side elevation views of a probe card including nanotube probes according to some embodiments of the disclosed subject matter;

FIG. 9 is a side elevation views of a probe card including nanotube probes according to some embodiments of the disclosed subject matter; and

25 FIG. 10 is a top plan view of an array of nanotubes according to some embodiments of the disclosed subject matter.

DETAILED DESCRIPTION

[0009] The disclosed subject matter includes probe cards and methods of fabricating probe cards that include arrays of carbon nanotubes being used as probes to bridge the gap
30 between a substrate and the IC under test.

[0010] Referring now to FIGS. 1 and 2, some embodiments of the disclosed subject matter include a method 100 of fabricating a plurality of carbon nanotube-bundle probes 102 on a substrate 104. At 106, method 100 includes first providing substrate 104 having a top surface 108 and a bottom surface 110. Substrate 104 can be a patterned silicon wafer, a multi-layer ceramic, glass, or other similar device. Substrate 104 can also contain traces that route from electrically conductive pads 112, which are discussed further below, to connection points, spaced further apart, which serve as an interface to electrical test equipment. The traces can be buried inside the multi-layer substrate 104 so as not to be exposed to the nanotube processing environment, and to provide additional room on the substrate to facilitate the routing of the signals for high density applications.

[0011] Next, at 114, an array of electrically conductive pads 112 is formed on top surface 108 of substrate 104. The array of electrically conductive pads 112 is formed to mirror an array of pads on an integrated circuit (not shown) that is to be tested. Pads 112 are typically formed photo-lithographically on substrate 104, which allows for tight pad spacing.

[0012] Then, at 116, a catalyst 118, such as gold, iron, etc., for promoting growth of carbon nanotubes is applied to each of the array of electrically conductive pads 112. Catalyst 118 induces the growth of carbon nanotubes at the pad locations.

[0013] Next, at 120, substrate 104 is heated in a carbon-rich environment thereby growing nanotubes extending upwardly from each of the array of electrically conductive pads 112 and above top surface 108 of the substrate thereby forming a plurality of carbon nanotube-bundle probes 102 extending upwardly above the top surface of the substrate. Substrate 104 is processed in a way that induces the nanotube formation and growth.

[0014] Several methods are known that will induce the growth of nanotubes, such as Chemical vapor Deposition (CVD), Plasma Enhanced Chemical Vapor Deposition (PECVD), Laser Ablation, Arc discharge, etc. In some embodiments, method 100 for inducing nanotube formation and growth is CVD or PECVD, as both provide a controlled process whereby the overall length of the nanotubes can be controlled by controlling the processing time. The substrate is typically heated to temperatures around 700 degrees Celsius in a furnace with a carbon-rich environment such as propane, acetylene, ferrocene, xylene, methane, etc, and possibly in the presence of hydrogen, argon and/or oxygen.

Under these conditions, the array of carbon nanotubes would "grow" from the pad surface and fill the entire area of the exposed pads, extending perpendicularly from the pad surface to create a "forest" of aligned nanotubes. The array would be attached to the pad at its base, and each "probe" would then consist of an array of thousands of aligned nanotubes.

5 The array would consist of a variety of nanotube types, some metallic and some semiconducting. However, there would be more than enough of the metallic type to serve as electrical contacts to bridge the space between the substrate and IC under test.

[0015] Referring again to FIG. 1, at 122, each of plurality of carbon nanotube-bundle probes 102 is capped with an electrically conductive material such as gold, palladium, etc.

10 [0016] Alternatively, the probe array can be "grown" on a high temperature-capable substrate, and then transferred to a less expensive substrate, such as a printed circuit board. This would allow for a less expensive probe card for applications where elevated temperature testing was not required. Referring now to FIGS. 3, 4A, and 4B, some embodiments of the disclosed subject matter include a method 200 of fabricating a

15 plurality of carbon nanotube-bundle probes 202 on a substrate 204 using a metal foil 206 coated with an appropriate catalyst 208 that is bonded to the underside 210 of the substrate. At 212, method 200 includes first providing substrate 204 having a top surface 214, bottom surface 210, and an array of micro-holes 216 drilled through and connecting the top and bottom surfaces. Substrate 204 is typically prepared by pre-drilling, either

20 mechanically or with a laser, a pattern of micro-holes in a thin substrate, such as ceramic. The hole locations generally correspond to the desired probe locations and the hole diameter to the desired probe bundle diameter.

[0017] Next, at 218, metal foil 206 having top and bottom surfaces 220 and 222, respectively, is provided. Metal foil 206 is configured for joining with the bottom

25 surface 222 of substrate 204. Then, at 224, catalyst 208, such as gold, iron, etc., for promoting growth of carbon nanotubes is applied to top surface 220 of metal foil 206. At 226, top surface 220 of metal foil 206 is joined to bottom surface 210 of substrate 204.

[0018] At 228, metal foil 206 and substrate 204 are heated in a carbon-rich environment thereby causing each of the micro-holes in the substrate to expand due to

30 thermal expansion thereby forming array of expanded micro-holes 216 in the substrate. At 230, nanotubes are grown so as to extend upwardly from top surface 220 of metal foil 206

through each of array of expanded micro-holes 216 in substrate 204 and above top surface 214 of the substrate thereby forming plurality of carbon nanotube-bundle probes 202 extending upwardly above the top surface of the substrate. Each of plurality of carbon nanotube-bundle probes 202 substantially fills a respective one of array of expanded
5 micro-holes 216. Typically, substrate 204 and foil 206 are placed in a CVD chamber and processed so as to induce nanotube growth. The CVD reaction occurs at temperatures that are typically greater than 700 degrees Celsius. The CVD reaction gasses enter the micro-holes and induce nanotube growth at the hole locations. As mentioned above, the nanotubes pass through the thickness of the substrate and extend several mils past the front
10 substrate surface.

[0019] At 232, metal foil 206 and substrate 204 are cooled thereby causing each of array of expanded micro-holes 216 in the substrate to contract thereby forming array of contracted micro-holes in the substrate 216. Each one of array of contracted micro-holes 216 provides a shrink fit around a respective one of plurality of carbon nanotube-bundle
15 probes 202 contained therein so as to substantially secure the respective one of the plurality of carbon nanotube-bundle probes contained therein to substrate 204. At 234, metal foil 206 is removed from bottom surface 210 of substrate 204. Typically, metal foil 206 is removed using etching processes to form an assembly 235 (excluding foil 206). Referring now to FIGS. 3 and 4B, at 236, each of plurality of carbon nanotube-bundle
20 probes 202 is plated or provided with solder bumps 238 adjacent bottom surface 210 of substrate 204 to form an assembly 240.

[0020] The substrate/probe assembly can then be aligned with a space transformer having a corresponding set of contact pads and electrically connected to the pads to complete the probe card assembly.

25 [0021] Referring now to FIGS. 5A and 5B, method 200 described above with respect to FIGS. 3, 4A, and 4B can include additional process steps to develop an assembly 300 that serves as an interface between a space transformer 302 and a printed circuit board 304 in order to make them easily separable for replacement. Assembly 300 generally can be developed by pairing assemblies 235 and 240 in FIGS. 4A and 4B with mirrored hole
30 patterns aligned back-to-back.

[0022] Referring now to FIGS. 6, 7A, and 7B, some embodiments include a method 400 of fabricating a plurality of carbon nanotube-bundle probes 402 extending from opposing surfaces of a substrate 404. At 405, method 200 first includes providing substrate 404 having a top surface 406, a bottom surface 408, and an array of micro-holes 410 drilled through and connecting the top and bottom surfaces.

[0023] At 412, a first metal foil 414 having top and bottom surfaces 416 and 418, respectively, and an array of holes 420 drilled through and connecting the top and bottom surfaces is provided. Array of holes 420 is arranged to align with array of micro-holes 410 in substrate 404. Still at 412, a second metal foil 422 having top and bottom surfaces 424 and 426, respectively, is provided. Second metal foil 422 is configured for joining with bottom surface 418 of first metal foil 414.

[0024] At 428, a catalyst 430 for promoting growth of carbon nanotubes is applied to top surface 424 of second metal foil 422. At 430, top surface 416 of first metal foil 414 is joined to bottom surface 408 of substrate 204 so that array of holes 420 is substantially aligned with array of micro-holes 410 in the substrate and top surface 424 of second metal foil 422 is joined to bottom surface 418 of the first metal foil.

[0025] At 432, second metal foil 422 and substrate 404 are heated in a carbon-rich environment thereby causing each of micro-holes 410 in the substrate to expand thereby forming an array of expanded micro-holes 410 in the substrate. At 434, nanotubes are grown so as to extend upwardly from top surface 424 of second metal foil 422 through each of array of holes 420 in first metal foil 414 and array of expanded micro-holes 410 in substrate 404 and above top surface 406 of the substrate thereby forming plurality of carbon nanotube-bundle probes 402 extending upwardly above the top surface of the substrate. Each of plurality of carbon nanotube-bundle probes 402 substantially fills a respective one of array of expanded micro-holes 410.

[0026] At 436, second metal foil 422 and substrate 404 are cooled thereby causing each of array of expanded micro-holes 410 in the substrate to contract thereby forming an array of contracted micro-holes 410 in the substrate. Each one of array of contracted micro-holes 410 provides a shrink fit around a respective one of plurality of carbon nanotube-bundle probes 402 contained therein so as to substantially secure the respective one of the plurality of carbon nanotube-bundle probes contained therein to the substrate.

Referring to FIG. 7B, at 438, first and second metal foils 414 and 422, respectively, are removed from bottom surface 408 of substrate 404 to form an assembly 440.

[0027] Variations on embodiments of the disclosed subject matter are possible. For example, referring now to FIGS. 8A and 8B, some embodiments are directed to methods that include forming an assembly 500, which includes a tapered micro-hole 502 in a substrate 504 having a foil 506 backing so as to induce a tighter packing density in a nanotube bundle 508 as it grows up through the micro-hole, and therefore a tighter “shrink” fit as well as modification of the “stiffness” of the compliant nanotube bundle. As shown in FIG. 8B, a back side 510 of tapered micro-hole 502 is typically filled with a solder or conductive epoxy 512 after nanotube growth to form attachment bumps 514 and form a “plug” to secure nanotube bundle 508 to substrate 504.

[0028] Referring now to FIG. 9, some embodiments are directed to methods to form an assembly 600 that include drilling slanted micro-holes 602 to induce nanotube bundles 604 to emerge at an angle to a top surface 606 of a substrate 608 having a foil 610 backing, in order to obtain a different force-deflection characteristic for the probe and/or a different scrubbing action.

[0029] Each of the embodiments described in Fig 3-9 can employ known methods to assist with transferring the nanotube/substrate assembly. One known method includes pouring a poly(dimethylsiloxane) (PDMS) liquid over the nanotubes and curing it until it forms a polymer. In this case, the polymer is used to help adhere the nanotube bundle to the substrate. The foil is then peeled off the polymer, substrate and nanotubes assembly and the assembly transferred to a space transformer. Incorporating the rigid substrate in the assembly facilitates handling and alignment of the substrate assembly with the space transformer. It also provides rigidity and support when interfacing with flexible or fragile space transformers such as polymer films or silicon wafers.

[0030] Referring now to FIGS. 1, 2, and 10, in some embodiments, pads 112 on substrate 104 can be patterned so as to create a co-axial arrangement of nanotubes, with an inner ring 700 of nanotubes forming signal pads and an outer ring 702 of nanotubes routed to a ground plane, further limiting cross-talk between probes.

[0031] In some embodiments, the electron-emitting properties of nanotubes can be utilized to make a non-contacting probe in a vacuum environment. This property is currently being explored as a display technology. In certain test applications involving low current requirements, electrons are transferred through the small gap between the probe and the IC pad without actually making physical contact with the pad. This avoids the risk of damaging or contaminating the pad or probe through physical contact.

[0032] In some embodiments, telescoping probes are developed from multi-walled nanotubes by removing the cap on the outer tube to allow the inner tube to telescope outwards. It has been shown that applying a different charge to the inner and outer tubes can cause the inner tube to extend and bridge the gap between two contacts.

[0033] In some embodiments, the formation of so-called “colossal carbon nanotubes” is induced using a CVD process involving ethylene and paraffin oil.

[0034] The disclosed subject matter offers a plurality of benefits and advantages over prior art designs. Probe cards developed with nanotube probes allow for testing of ICs with tighter pitch, higher current capacity, improved planarity, elimination of mechanical assembly and handling operations, very low inductance, potential for full wafer probing at elevated temperatures, and easier cleaning of probes.

[0035] As mentioned above, in some embodiments, a probe card can be constructed by inducing the growth of nanotube arrays perpendicular to a substrate. The nanotube arrays act as electrical contacts or “probes” to bridge the space between the substrate and a device under test. By “growing” the contacts directly on a substrate, the contacts may be placed closer together than would be possible with conventional buckling beam technology. The unique physical characteristics of nanotubes (very high strength, very high current capacity, and elastic buckling) provide significant advantages over conventional technologies.

[0036] By “growing” the contacts directly on a substrate, the contacts may be placed closer together than would be possible with conventional probing technology, allowing for tight pitch probing. Since the individual nanotubes that make up the array are so tiny, there is no practical limit to the size of the substrate pad, as hundreds of thousands of nanotubes would fit on the pad. In addition, the “stiffness” of the probe array could be

controlled by varying the diameter of the pad on which the array is grown. Since the probe is "grown" rather than assembled conventionally, the alignment is limited only by the placement tolerance of the photo-lithographically defined array of pads, which is very good and comparable to the location tolerance of the IC pads themselves. In contrast,
5 conventional probing technology is an assembly of components, all having their own tolerances, and the tolerance accumulation limits the alignment accuracy capability of the probe.

[0037] Despite their small size, nanotubes can handle large amounts of current due to the "ballistic" nature of the electron flow. The individual nanotubes are largely defect-
10 free, allowing for very low resistance to electron flow. As a result, the nanotube array can handle significantly larger currents than could be passed through a conventional probe made of bulk material, such as beryllium-copper, of the same total cross-sectional area. They are also compatible with elevated temperature testing.

[0038] Nanotubes also exhibit good mechanical characteristics. Due to the lack of
15 defects, it has been demonstrated that individual nanotubes can be bent to extreme angles, yet return elastically to their original shape. Their tensile strengths are ten times greater than steel. Arrays of nanotubes have shown the capacity to be repeatedly compressed to 15% of their original length. These unique physical characteristics make them ideal probes and provide significant advantages over conventional technologies. Their high
20 strength and elastic properties allow the nanotubes to be significantly shorter than is possible with conventional probes, while still providing sufficient compliance to allow for the pad height variation of the IC's under test. Typically, at least 3 mils of compliance would be necessary due to pad height and wafer thickness variations. The nanotube probes can be grown as short as 4 mils, allowing for very low electrical inductance
25 suitable for ultra-high frequency testing.

[0039] Cleaning of the nanotube bundle probe can be accomplished by taking advantage of the relative surface roughness of the bundle tip. As there are no dangling covalent bonds on the nanotube, the nanotube probe is chemically non-reactive so non-conductive oxides do not tend to form on the probe tips. The lower surface area in contact
30 with the contaminant tends to reduce the van der Waals attraction between a nanotube probe and contaminants. Bringing a nanotube probe array in contact with a smooth

surface, such as quartz, ruthenium, tantalum oxynitride, etc., tends to transfer contaminants from the nanotube probe onto the smoother surface due to its greater van der Waals attractive force.

[0040] Although the disclosed subject matter has been described and illustrated with
5 respect to embodiments thereof, it should be understood by those skilled in the art that features of the disclosed embodiments can be combined, rearranged, etc., to produce additional embodiments within the scope of the invention, and that various other changes, omissions, and additions may be made therein and thereto, without parting from the spirit and scope of the present application.

Claims

What is claimed is:

1. A method of fabricating a plurality of carbon nano-tube-bundle probes (202) on a substrate (204), said method comprising:

providing a substrate (204) having a top surface (214), a bottom surface (210) and an array of microholes (216) drilled through and connecting said top and bottom surfaces (210);

providing a metal foil (206) having top (220) and bottom surfaces (222);

applying a catalyst (208) for promoting growth of carbon nanotubes to said top surface (220) of said metal foil (206);

joining said top surface (220) of said metal foil (206) to said bottom surface (210) of said substrate (204); heating said metal foil (206) and said substrate (204) in a carbon-rich environment thereby causing each of said array of micro-holes (216) in said substrate (204) to expand thereby forming an array of expanded micro-holes (216) in said substrate (204);

growing nanotubes extending upwardly from said top surface (220) of said metal foil (206) through each of said array of expanded micro-holes (216) in said substrate (204) to form a plurality of carbon nanotube-bundle probes (202); cooling said metal foil (206) and said substrate (204) thereby causing each of said array of expanded micro-holes (216) in said substrate (204) to contract thereby forming an array of contracted micro-holes (216) in said substrate; and

removing said metal foil (206) from said bottom surface (210) of said substrate (204).
2. The method according to claim 1, wherein said metal foil (206) being configured for joining with said bottom surface (210) of said substrate (204).
3. The method according to claim 1, wherein said carbon nanotubes are grown above said top surface (214) of said substrate (204) thereby forming a plurality of carbon nanotube-bundle probes (202) extending upwardly above said top surface (214) of said substrate (204), and wherein preferably each of said plurality of carbon nanotube-bundle probes (202) substantially fills a respective one of said array of expanded micro-holes (216).
4. The method according to claim 1, wherein each one of said array of contracted micro-holes (216) provides a shrink fit around a respective one of said plurality of carbon nanotube-bundle probes (202) contained therein so as to substantially secure said respective one of said plurality of carbon nanotube-bundle probes (202) contained therein to said substrate (204).
5. The method according to claim 1, wherein said array of micro-holes (216) are drilled at an angle not perpendicular to said top surface (214) of said substrate (204) thereby

causing said nanotubes to grow at an angle not perpendicular to said top surface (214) of said substrate (204).

6. The method according to claim 1, wherein each one of said array of micro-holes (216) is tapered, and preferably further comprising providing a solder or epoxy backfill to said array of micro-holes (216).
7. The method according to claim 1, further comprising plating or solder bumping each of said plurality of carbon nanotube-bundle probes (202) adjacent said bottom surface (210) of said substrate (204).
8. A method of fabricating a plurality of carbon nano-tube-bundle probes (402) extending from opposing surfaces of a substrate (404), said method comprising:

providing a substrate (404) having a top surface (406), a bottom surface (408), and an array of micro-holes (410) drilled through and connecting said top (406) and bottom surfaces (408);

providing a first metal foil (414) having top (416) and bottom surfaces (418) and an array of holes (420) drilled through and connecting said top (416) and bottom surfaces (418);

providing a second metal foil (422) having top (424) and bottom surfaces (426);

applying a catalyst (430) for promoting growth of carbon nanotubes;

joining said top surface (416) of said first metal foil (414) to said bottom surface (408) of said substrate (404);

joining said top surface (424) of said second metal foil (422) to said bottom surface (418) of said first metal foil (414);

heating said second metal foil (422) and said substrate (404) in a carbon-rich environment thereby causing each of said array of micro-holes (410) in said substrate (404) to expand thereby forming an array of expanded micro-holes (410) in said substrate (404);

growing nanotubes extending upwardly from said top surface (424) of said second metal foil (422) through each of said array of holes (420) in said first metal foil (414) and said array of expanded micro-holes (410) in said substrate (404) and above said top surface (406) of said substrate (404) thereby forming a plurality of carbon nanotube-bundle probes (402) extending upwardly above said top surface (406) of said substrate (404), each of said plurality of carbon nanotube-bundle probes (402) substantially filling a respective one of said array of expanded micro-holes (410); and

cooling said second metal foil (422) and said substrate (404), removing said first (414) and second metal foils (422) from said bottom surface (408) of said substrate (404).

9. The method according to claim 8, wherein said metal foil (422) is configured for joining with said bottom surface (418) of said first metal foil (414).
10. The method according to claim 8, wherein said array of holes (420) are arranged to align with said array of micro-holes (410) in said substrate (404), or wherein said array of holes (420) in said first metal foil (414) is substantially aligned with said array of micro-holes (410) in said substrate (404).
11. The method according to claim 8, wherein cooling causes each of said array of expanded micro-holes (410) in said substrate (404) to contract thereby forming an array of contracted micro-holes (410) in said substrate (404), each one of said array of contracted micro-holes (410) providing a shrink fit around a respective one of said plurality of carbon nanotube-bundle probes (402) contained therein so as to substantially secure said respective one of said plurality of carbon nanotube-bundle probes (402) contained therein to said substrate (404).