

METHOD FOR PRODUCING SURFACE-MODIFIED SILICA
NANOPARTICLES, AND SURFACE-MODIFIED SILICA
NANOPARTICLES

5

TECHNICAL FIELD

[0001] The present invention relates to a method for
producing surface-modified silica nanoparticles and also
10 relates to the surface-modified silica nanoparticles. The
invention further relates to a dispersion of the surface-
modified silica nanoparticles.

15

BACKGROUND ART

[0002] According as nanotechnology has been developed,
colloidal silica materials comprising nanosized silica
particles have been getting widely used. Colloidal silica
is generally known to improve the thermal and
20 mechanical properties of materials mixed therewith, and
hence is employed as an additive in various resins and
dispersion media. However, commercially available
colloidal silica is generally in the form of aqueous
colloidal solution or powder, and is accordingly poor in
25 dispersibility when added in organic dispersion media or
resins. In view of that, in order to solve the problem of
dispersibility, it has been desired to provide non-aqueous
colloid (which is also referred to as "organosol").

[0003] Heretofore, many attempts have been made to
30 produce non-aqueous colloid. In those attempts,
surface of colloidal silica is modified (to be hydrophobic)
so as to manufacture organosol materials homogene-
ously dispersible in organic dispersion media (for
example, see, Patent documents 1 to 4).

35

PRIOR ART DOCUMENTS

PATENT DOCUMENTS

[0004] [Patent document 1] Japanese Patent Laid-Open No.
H11(1999)-43319

5 [Patent document 2] Japanese Patent Laid-Open No.
2009-155138

[Patent document 3] Japanese Patent Laid-Open No.
2012-214554

[Patent document 4] Japanese Patent Laid-Open No.
2001-213617

10

DISCLOSURE OF INVENTION

PROBLEM TO BE SOLVED BY THE INVENTION

[0005] However, although the methods disclosed above
15 can provide colloidal silica materials dispersed in organic
dispersion media or resins, there is still room for
improvement in view of transparency of the dispersion.
The present inventors have studied and researched the
method for solving this problem, and consequently found
20 that surface-modified silica nanoparticles can show high
dispersibility, transparency and storage stability when
dispersed in organic dispersion media if they are
obtained in a manner in which: a dispersion containing
silica nanoparticles and an aqueous dispersion medium
25 is treated to replace the aqueous dispersion medium
with an organic dispersion medium comprising at least
one selected from cyclic esters or cyclic amides, and
then the silica nanoparticles are subjected to
surface-modification with a particular silane coupling
30 agent. The present invention has been achieved on the
basis of this finding.

[0006] It is thus an object of the present invention to
provide a method for producing surface-modified silica
nanoparticles showing high dispersibility, transparency
35 and storage stability in organic dispersion media, and
also to provide the surface-modified silica nanoparticles.

[0007] Further, it is another object of the present invention to provide a dispersion in which the surface-modified silica nanoparticles produced according to the method of the present invention are dispersed in an organic dispersion medium.


MEANS FOR SOLVING PROBLEM

[0008] An embodiment of the present invention provides a method for producing surface-modified silica nanoparticles comprises:

preparing a first silica nanoparticle dispersion containing silica nanoparticles and an aqueous dispersion medium;


replacing said aqueous dispersion medium in said first silica nanoparticle dispersion with an organic dispersion medium comprising at least one selected from cyclic esters or cyclic amides, to obtain a second silica nanoparticle dispersion; and

mixing said second silica nanoparticle dispersion with a silane coupling agent represented by the formula (1):



in which each R^1 is independently a hydrocarbon group of C_1 to C_{20} and R^2 is a hydrocarbon group of C_1 to C_3 , to modify the surface of the silica nanoparticles.

[0009] In a preferred embodiment, the above organic dispersion medium comprises at least one selected from cyclic esters or amides represented by the formula (2):



in which X is O or NR^3 where R^3 is H or a hydrocarbon

group of C_1 to C_3 , and n is an integer of 2 to 5.

[0010] Another embodiment of the present invention provides the surface-modified silica nanoparticles obtained by the above method and also provides a surface-modified silica nanoparticle dispersion obtained by dispersing said surface-modified silica nanoparticles in an organic dispersion medium.

EFFECT OF THE INVENTION

10 [0011] The present invention provides surface-modified silica nanoparticles capable of being favorably dispersed in various organic dispersion media to form highly transparent silica nanoparticle dispersions, and also provides a producing method thereof.

DETAILED DESCRIPTION

[0012] [method for producing surface-modified silica nanoparticles]

20 The method of the present invention for manufacturing surface-modified silica nanoparticles will be concretely described below. The method for producing surface-modified silica nanoparticles of the present invention comprises the steps of: preparing a first silica nanoparticle dispersion containing silica nanoparticles and an aqueous dispersion medium; replacing the aqueous dispersion medium in the first silica nanoparticle dispersion with an organic dispersion medium comprising at least one selected from cyclic esters or cyclic amides, to obtain a second silica nanoparticle dispersion (replacement step); and mixing said second silica nanoparticle dispersion with a particular silane coupling agent, to modify the surface of the silica nanoparticles (surface modification step). Each step will be explained below in detail.

35 [0013] <step of preparing a first silica nanoparticle dispersion>
First, in the method of the present invention for

producing surface-modified silica nanoparticles, a first silica nanoparticle dispersion is prepared which contains silica nanoparticles and an aqueous dispersion medium. The first silica nanoparticle dispersion can be prepared by adding and stirring silica nanoparticles in an aqueous dispersion medium. It is also possible to prepare a commercially available silica nanoparticle dispersion, such as, colloidal silica.

[0014] Examples of the silica nanoparticles usable in the present invention include: dry silica (which is also referred to as "fumed silica") obtained by a dry process, such as combustion method, and wet silica obtained by a wet process, such as precipitation method, gel method or sol-gel method. As the silica nanoparticles, it is also possible to adopt commercially available ones, such as, dry silica of REOLOSIL series ([trademark], manufactured by Tokuyama Corporation). The silica nanoparticles employed in the present invention have a volume mean particle size of preferably 100 nm or less, more preferably 50 nm or less. The volume mean particle size can be measured according to dynamic light scattering (DLS) method by means of an analyzer, such as Nanotracer particle size distribution analyzer ([trademark], manufactured by Nikkiso Co., Ltd.).

[0015] The aqueous dispersion medium used in the present invention mainly comprises water. If necessary, it may contain other components in small amounts. However, the amounts of the components other than water are preferably 30 wt% or less based on the whole weight.

[0016] The amount of the silica nanoparticles in the first silica nanoparticle dispersion can be appropriately selected, but is preferably 10 to 60 wt%, more preferably 20 to 50 wt%.


[0017] Examples of the commercially available silica nanoparticle dispersion usable in the present invention

include: Klebosol series ([trademark], manufactured by AZ electronic materials K.K.), Snowtex series ([trademark], manufactured by NISSAN CHEMICAL INDUSTRIES, LTD), Quartron PLEASE series ([trademark], manufactured by FUSO CHEMICAL CO, LTD), ADELITE AT series ([trademark], manufactured by ADEKA CORPORATION). However, those by no means restrict the present invention.

[0018] <replacement step>

Subsequently, in the method for producing surface-modified silica nanoparticles of the present invention, the aqueous dispersion medium in the first silica nanoparticle dispersion is replaced with an organic dispersion medium comprising at least one selected from cyclic esters or cyclic amides, to obtain a second silica nanoparticle dispersion containing the silica nanoparticles dispersed in the organic dispersion medium.

[0019] The organic dispersion medium, which is used for converting the aqueous dispersion medium in the first silica nanoparticle dispersion into an organic dispersion medium, comprises at least one selected from cyclic esters or cyclic amides. Without wishing to be bound by any theory, it is presumed that, since serving as a dispersion medium, the organic dispersion medium coats the surface of the nanoparticles and thereby keeps the dispersion state and also provides effects of improving the reactivity and of reducing side reactions when the nanoparticles react with the silane coupling agent. There are no particular limitations on the cyclic esters or amides as long as they are in liquid state at room temperature, but it is preferred to adopt the cyclic esters or amides represented by the following formula (2):



in which X is O or NR³ where R³ is H or a hydrocarbon group of C₁ to C₃, and n is an integer of 2 to 5.

Examples of the cyclic esters represented by the formula (2) include: β-propiolactone (n=2: 4-membered ring), γ-butyrolactone (n=3: 5-membered ring), δ-valerolactone (n=4: 6-membered ring), and ε-caprolactone (n=5: 7-membered ring). Examples of the cyclic amides represented by the formula (2) include: β-lactam (n=2: 4-membered ring), γ-lactam (n=3: 5-membered ring) and δ-lactam (n=4: 6-membered ring), in which R³ is H; and 1-methyl-2-pyrrolidone (n=3: 5-membered ring) and 1-methyl-2-piperidone (n=4: 6-membered ring), in which R³ is a hydrocarbon group of C₁ to C₃. Among them, γ-butyrolactone (boiling point: 205°C) is particularly preferred in view of availability (because it is not desirable for the cyclic esters or amides to cost too much) and of operatability (because it is not desirable for the cyclic esters or amides to have boiling points much lower or higher than that of water). In the present specification, the term "room temperature" means a temperature of 20 to 30°C.

[0020] In addition to the above organic dispersion medium, the second silica nanoparticle dispersion may further comprise another dispersion medium selected from ethers, non-cyclic esters, non-cyclic amides or mixtures thereof. Examples of the ethers include: tetrahydrofuran (THF), 1,4-dioxane, 1,2-dimethoxyethane, and bis(2-methoxyethyl)ether. Examples of the non-cyclic esters include: ethyl acetate and propylene-glycol-1-monomethylether-2-acetate (PGMEA). Examples of the non-cyclic amides include: N,N-dimethylformamide (DMF) and N,N-dimethylacetamide (DMAC). However, they by no means restrict the present invention. Those optional dispersion media may be contained in an amount of at most about 15 wt% based on the weight of the organic dispersion medium

comprising at least one selected from cyclic esters or cyclic amides.

[0021] The replacement of the dispersion medium can be carried out in any known manner. Specifically, for example, the aqueous dispersion medium is removed by centrifugation and then the organic dispersion medium is added to replace the dispersion medium. It is also possible to remove the aqueous dispersion medium by distillation under reduced pressure with a rotary evaporator or the like or otherwise by use of a separation membrane such as an ultrafiltration membrane. According to necessity, the dispersion medium may be replaced either at room temperature or under heating. As a result of the dispersion medium replacement, the dispersion medium in the second silica nanoparticle dispersion preferably consists of substantially only the organic dispersion medium so that the content of the aqueous dispersion medium may be 1% or less.


[0022] Before replaced with the organic dispersion medium, the aqueous dispersion medium may be mixed with one or more alcohols having boiling points lower than that of the organic dispersion medium by 30°C or more. If the alcohols are thus added, the time for the replacement step can be shortened by azeotropic distillation. The alcohols having such relatively low boiling points as to be employable here depend on what organic dispersion medium is used, but examples thereof include methanol, ethanol, 1-propanol, 2-propanol (or isopropyl alcohol (IPA)), and 1-methoxy-2-propanol (or propyleneglycol monomethyl ether (PGME)). However, they by no means restrict the present invention. Those alcohols are used in an amount preferably 3 to 10 times, further preferably 5 to 8 times as large in weight as the aqueous dispersion medium.

[0023] The amount of the silica nanoparticles in the

second silica nanoparticle dispersion can be appropriately selected, but is preferably 1 to 45 wt%, more preferably 10 to 30 wt%. If the second silica nanoparticle dispersion is controlled to contain the silica nanoparticles in an amount within the above range, the viscosity thereof can be prevented from increasing excessively so that the operatability can be kept favorable.

[0024] <surface modification step>

In the surface modification step of the producing method according to the present invention, the second silica nanoparticle dispersion obtained by the replacement step is mixed with a silane coupling agent represented by the following formula (1):



in which each R^1 is independently a hydrocarbon group of C_1 to C_{20} and R^2 is a hydrocarbon group of C_1 to C_3 . Examples of the silane coupling agent represented by the formula (1) include: methoxytrimethylsilane, methoxytriethylsilane, methoxytripropylsilane, methoxytributylsilane, ethoxytripropylsilane, ethoxytributylsilane, propoxytrimethylsilane, allyloxytrimethylsilane, methoxymethyldiethylsilane, methoxy(dimethyl)butylsilane, methoxy(dimethyl)octylsilane, methoxy(dimethyl)decylsilane, methoxy(dimethyl)tetradecylsilane, and methoxy(dimethyl)octadecylsilane. However, they by no means restrict the present invention.

[0025] The amount of the silane coupling agent adopted in the surface modification step can be appropriately selected. However, the silane coupling agent is preferably added in an amount about twice to 5 times as large in molar ratio as the number of silanol groups existing on the surface of the silica nanoparticles. Here,

the number of silanol groups existing on the silica nanoparticle surface can be determined according to the method described in "The chemistry of Silica: Solubility, Polymerization, Colloid and Surface Properties and Biochemistry of Silica; written by Ralph K. Iler (1979), published by John Wiley & Sons, Inc.", in which it is also described that there are 4 to 5 hydroxyl groups per 1 nm² (100 square angstrom) on the silica surface. This means that, if spherical silica having 25 nm diameter (radius: $r=25/2$ nm) is adopted, the number of hydroxyl (silanol) groups can be estimated to be a value 4 to 5 times as large as the surface area calculated according to the formula ($S=4\pi r^2$) on the basis of the method described in the above literature. It is still also described in the literature that about 4.6 hydroxyl groups per 1 nm² are generally observed on the amorphous silica surface treated at a high temperature. Accordingly, in the present invention, the number of hydroxyl (silanol) groups is considered to be a value 4.6 times as large as the surface area of spherical silica.

[0026] The surface modification step may be carried out either at room temperature or under heating according to necessity. The above silane coupling agent is added to the second silica nanoparticle dispersion and then preferably stirred with a magnetic stirrer or the like so that the reaction can proceed smoothly and homogeneously. The time for the surface modification step can be appropriately controlled according to the temperature and the amount of the adopted silica nanoparticles.

[0027] As a result of the surface modification step, the silica nanoparticles dispersed in the dispersion medium are surface-modified. Without wishing to be bound by any theory, it is presumed that the silanol groups existing on the silica nanoparticle surface are at least partly made to react with the silane coupling agent of the formula (1) to form $-\text{OSiR}^1_3$ groups on the nano-

particle surface and consequently to change the silica nanoparticle surface in affinities to aqueous and organic dispersion media. This surface-modification enables the silica nanoparticles to show high transparency when they are dispersed in an organic dispersion medium.

[0028] After subjected to the surface-modification, the silica nanoparticles can be surface-analyzed with a FT-IR (FT/IR-4000, [trademark], manufactured by JASCO Corporation) according to the method described in Japanese Patent Laid-Open No. H6(1994)-92621. Specifically, the FT-IR absorption spectra of the silica nanoparticles are compared between before and after the surface-modification to observe change of the peak (in 3400 to 3500 cm^{-1}) attributed to Si-OH, and thereby it can be judged whether or not the silica nanoparticles are surface-modified with the silane coupling agent.

[0029] The surface-modified silica nanoparticles in a dispersion can be subjected to visual sensory evaluation so as to evaluate the transparency. The dispersibility thereof can be also visually evaluated.

[0030] Surprisingly, the present inventors have found an unexpected fact that the silane coupling agent can be so changed as to select an organic dispersion medium in which the surface-modified silica nanoparticles are dispersed to form a dispersion having high transparency. Specifically, if the adopted silane coupling agent is represented by the formula (1) in which all R^1 s are hydrocarbon groups of C_1 to C_7 , the surface-modified silica nanoparticles exhibit high dispersibility, transparency and storage stability in a hydrophilic organic dispersion medium. Examples of that silane coupling agent include: methoxytrimethylsilane, methoxytriethylsilane, methoxytripropylsilane, methoxytributylsilane, ethoxytripropylsilane, ethoxytributylsilane, propoxytrimethylsilane, allyloxytrimethylsilane, methoxymethyldiethylsilane, and methoxy(dimethyl)-

butylsilane. Also, examples of the hydrophilic organic dispersion medium include: alcohols, such as, methanol, ethanol, propanol and butanol; polyalcohols, such as, ethylene glycol, propylene glycol, and glycerin; ethers, such as, dimethyl ether, ethylmethyl ether, and tetrahydrofuran; ketones, such as, acetone, methylethyl ketone, and diethyl ketone; lactones (cyclic esters), such as, β -propiolactone, γ -butyrolactone and δ -valerolactone; and lactams (cyclic amides), such as, 2-pyrrolidone and N-methyl- 2-pyrrolidone.

[0031] On the other hand, if the employed silane coupling agent is represented by the formula (1) in which at least one R^1 is a hydrocarbon group of C_8 to C_{20} , the surface-modified silica nanoparticles exhibit high dispersibility, transparency and storage stability in a hydrophobic organic dispersion medium. Examples of that silane coupling agent include: methoxy(dimethyl)octylsilane, methoxy(dimethyl)decylsilane, methoxy(dimethyl)tetradecylsilane, and methoxy(dimethyl)octadecylsilane. Also, examples of the hydrophobic organic dispersion medium include: straight-chain aliphatic hydrocarbons, such as, pentane, hexane and heptane; cyclic aliphatic hydrocarbons, such as, cyclohexane, cycloheptane, and decalin (decahydronaphthalene); and aromatic hydrocarbons, such as, benzene, toluene and xylene. As the hydrophilic organic dispersion medium, γ -butyrolactone or N-methyl-2-pyrrolidone is preferred. As the hydrophobic organic dispersion medium, hexane, decalin or toluene is preferred. The above effect of dispersion medium-selectivity appears remarkably when the used silane coupling agent is represented by the formula (1) in which two of the three R^1 s are short-chain hydrocarbon groups (e.g., hydrocarbon groups of C_1 to C_3).

35 [0032] <optional steps>

After the above surface modification step, the

surface-modified silica nanoparticles of the present invention may be directly used for practical application. However, they may be further subjected to filtration and drying before practical use. As a result of the filtration and drying steps, the surface-modified silica nanoparticles can be obtained in the form of powder. In view of the storage and transportation, the silica nanoparticles in the form of powder are more favorable than those in the form of a dispersion. Accordingly, the method for producing surface-modified silica nanoparticles of the present invention preferably further comprises the steps of filtrating the second silica nanoparticle dispersion and of drying the collected precipitates after the step of surface-modifying the silica nanoparticles. If the precipitates are not formed in the dispersion after the surface modification step, the dispersion may be poured into water to form precipitates and then filtrated. After the filtration step, the surface-modified silica nanoparticles may be dispersed again in an organic dispersion medium to obtain a surface-modified silica nanoparticle dispersion.

[0033] In addition, the method for producing surface-modified silica nanoparticles of the present invention furthermore comprises the step of washing the surface-modified silica nanoparticles between the steps of filtration and drying. The nanoparticles can be washed with any cleaning solvent, such as, alcohols. The washing step makes it possible to remove residues, such as, the silane coupling agent and cyclic ester or amide remaining after the surface modification step. The surface-modified silica nanoparticles thus obtained can be dispersed in a desired organic dispersion medium to produce a surface-modified silica nanoparticle dispersion less contaminated with impurities.

35 [0034] <surface-modified silica nanoparticles>

The surface-modified silica nanoparticles obtained

by the producing method according to the present invention can exhibit high dispersibility, transparency and storage stability when dispersed in an organic dispersion medium. They have a volume mean particle size of preferably 100 nm or less, more preferably 50 nm or less. The volume mean particle size can be measured according to dynamic light scattering (DLS) method by means of an analyzer, such as, Nanotrac particle size distribution analyzer ([trademark], manufactured by Nikkiso Co., Ltd.).

[0035] <surface-modified silica nanoparticle dispersion>

The above surface-modified silica nanoparticles can be dispersed in a desired organic dispersion medium to produce a surface-modified silica nanoparticle dispersion. The amount of the silica nanoparticles in the dispersion can be appropriately selected, but is preferably 3 to 40 wt%, more preferably 5 to 30 wt%. If contained in an amount within the above range, the surface-modified silica nanoparticles of the present invention can exhibit favorable dispersibility, transparency and storage stability in the dispersion.

EXAMPLES

[0036] The present invention will be further explained below in detail by Examples.

[0037] [Example 1]

(1) Preparation of second silica nanoparticle dispersion containing GBL

An aqueous dispersion (30.0 g) of silica sol (SiO₂ content: 30 wt%, mean particle size: 25 nm; Klebosol 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was mixed with γ -butyrolactone (GBL) as the cyclic ester in an amount of 13.5 g (which corresponds to a weight 0.45 times as large as the weight of the silica sol aqueous dispersion). The mixture was stirred and then distilled under reduced pressure with a

rotary evaporator, so that the aqueous dispersion medium of the silica sol was replaced with γ -butyrolactone to prepare a silica nanoparticle-GBL dispersion (22.5 g), in which the contents of SiO_2 and water were 40 wt% and 1 wt% or less, respectively.

(2) surface-modification of silica nanoparticles

After the above step of replacing the dispersion medium, the silica nanoparticle-GBL dispersion (9.275 g) was placed in a reaction vessel equipped with a stirrer. Successively, methoxytrimethylsilane (1.69 g) and γ -butyrolactone (38.16 g) were added thereto and then the mixture was stirred. Subsequently, after the reaction was conducted at room temperature for 48 hours, the reaction dispersion was poured into water (300 g, which corresponds to a weight about 5 times as large as the weight of the reaction dispersion). The formed precipitates were collected by filtration, washed with isopropyl alcohol and dried in vacuum at 40°C, to obtain the product (surface-modified silica nanoparticles) in a yield of 85%.

[0038] The dispersibility and transparency of the product were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both γ -butyrolactone and N-methyl-2-pyrrolidone, which are hydrophilic organic dispersion media, in amounts of 5 wt%, 15 wt% and 30 wt%. The prepared γ -butyrolactone and NMP dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a micro-filter having a pore diameter of 0.20 μm (Millex [trade-mark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0039] [Example 2]

(1) Preparation of second silica nanoparticle dispersion containing GBL

The procedure of Example 1 was repeated to prepare a second nanoparticle dispersion.

(2) surface-modification of silica nanoparticles

5 After the above step of replacing the dispersion medium, the silica nanoparticle-GBL dispersion (9.275 g) was placed in a reaction vessel equipped with a stirrer. Successively, methoxy(dimethyl)octylsilane (3.29 g) and γ -butyrolactone (38.16 g) were added thereto and then the mixture was stirred. Subsequently, after the
10 reaction was conducted at room temperature for 48 hours, the formed precipitates were collected by filtration, washed with isopropyl alcohol and dried in vacuum at 40°C, to obtain the product (surface-modified silica nanoparticles) in a yield of 83%.

15 [0040] The dispersibility and transparency of the product were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in
20 amounts of 5 wt%, 15 wt% and 30 wt%. The prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a microfilter having a pore diameter of 0.20 μm (Millex [trademark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0041] [Example 3]

30 (1) Preparation of second silica nanoparticle dispersion containing GBL

The procedure of Example 1 was repeated to prepare a second nanoparticle dispersion.

(2) surface-modification of silica nanoparticles

35 After the above step of replacing the dispersion medium, the silica nanoparticle-GBL dispersion (9.275 g) was placed in a reaction vessel equipped with a stirrer.

Successively, methoxy(dimethyl)octylsilane (5.565 g) and GBL (38.16 g) were added thereto and then the mixture was stirred. Subsequently, after the reaction was conducted at room temperature for 48 hours, the formed precipitates were collected by filtration, washed with isopropyl alcohol and dried in vacuum at 40°C, to obtain the product (surface-modified silica nanoparticles) in a yield of 87%.

[0042] The dispersibility and transparency of the product were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in amounts of 5 wt%, 15 wt% and 30 wt%. The prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a microfilter having a pore diameter of 0.20 μm (Millex [trademark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0043] [Example 4]

(1) Preparation of second silica nanoparticle dispersion containing IPA and GBL

An aqueous dispersion (30.0 g) of silica sol (SiO_2 content: 30 wt%, mean particle size: 25 nm; Klebosol 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was mixed with isopropanol (IPA) in an amount of 180 g (which corresponds to a weight 6 times as large as the weight of the silica sol aqueous dispersion) and γ -butyrolactone (GBL) as the cyclic ester in an amount of 13.5 g (which corresponds to a weight 0.45 times as large as the weight of the silica sol aqueous dispersion). The mixture was stirred and then distilled under reduced pressure with a rotary evaporator, so that the aqueous dispersion medium of the silica sol was

replaced with γ -butyrolactone to prepare a silica nanoparticle-GBL dispersion (22.5 g), which contained SiO_2 in a content of 40 wt% and water and IPA in a total content of 1 wt% or less.

5 (2) surface-modification of silica nanoparticles

The procedure of Example 3 was repeated to surface-modify the silica nanoparticles, to obtain surface-modified silica nanoparticles.

[0044] The dispersibility and transparency of the
10 produced surface-modified silica nanoparticles were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in amounts of 5
15 wt%, 15 wt% and 30 wt%. The 30 wt% dispersions were very slightly clouded, but the degrees thereof were practically negligible. The prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a micro-
20 filter having a pore diameter of 0.20 μm (Millex [trade-mark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0045] [Example 5]

25 (1) Preparation of second silica nanoparticle dispersion containing DVL

An aqueous dispersion (30.0 g) of silica sol (SiO_2 content: 30 wt%, mean particle size: 25 nm; Klebosol 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was mixed with δ -valerolactone (DVL) as
30 the cyclic ester in an amount of 13.5 g (which corresponds to a weight 0.45 times as large as the weight of the silica sol aqueous dispersion). The mixture was stirred and then distilled under reduced pressure with a
35 rotary evaporator, so that the aqueous dispersion medium of the silica sol was replaced with δ -valero-

lactone to prepare a silica nanoparticle-DVL dispersion (22.5 g), in which the contents of SiO₂ and water were 40 wt% and 1 wt% or less, respectively.

(2) surface-modification of silica nanoparticles

5 The procedure of Example 3 was repeated except for adding DVL in place of GBL, to surface-modify the silica nanoparticles and thereby to obtain surface-modified silica nanoparticles.

10 [0046] The dispersibility and transparency of the produced surface-modified silica nanoparticles were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in amounts of 5
15 wt%, 15 wt% and 30 wt%. The 30 wt% dispersions were very slightly clouded, but the degrees thereof were practically negligible. The prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a micro-
20 filter having a pore diameter of 0.20 μm (Millex [trade-mark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0047] [Example 6]

25 (1) Preparation of second silica nanoparticle dispersion containing EHL

 An aqueous dispersion (30.0 g) of silica sol (SiO₂ content: 30 wt%, mean particle size: 25 nm; Klebosol 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was mixed with ε-caprolactone (EHL) as
30 the cyclic ester in an amount of 13.5 g (which corresponds to a weight 0.45 times as large as the weight % of the silica sol aqueous dispersion). The mixture was stirred and then distilled under reduced pressure with a
35 rotary evaporator, so that the aqueous dispersion medium of the silica sol was replaced with ε-capro-

lactone to prepare a silica nanoparticle-EHL dispersion (22.5 g), in which the contents of SiO₂ and water were 40 wt% and 1 wt% or less, respectively.

(2) surface-modification of silica nanoparticles

5 The procedure of Example 3 was repeated except for adding EHL in place of GBL, to surface-modify the silica nanoparticles and thereby to obtain surface-modified silica nanoparticles.

10 [0048] The dispersibility and transparency of the produced surface-modified silica nanoparticles were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in amounts of 5
15 wt%, 15 wt% and 30 wt%. The 30 wt% dispersions were very slightly clouded, but the degrees thereof were practically negligible. The prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a micro-
20 filter having a pore diameter of 0.20 μm (Millex [trade-mark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

[0049] [Example 7]

25 (1) Preparation of second silica nanoparticle dispersion containing NMP

 An aqueous dispersion (30.0 g) of silica sol (SiO₂ content: 30 wt%, mean particle size: 25 nm; Klebosol 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was mixed with 1-methyl-2-pyrrolidone (NMP) as the cyclic amide in an amount of 13.5 g (which corresponds to a weight 0.45 times as large as the weight % of the silica sol aqueous dispersion). The mixture was stirred and then distilled under reduced
30 pressure with a rotary evaporator, so that the aqueous dispersion medium of the silica sol was replaced with
35

1-methyl-2-pyrrolidone to prepare a silica nanoparticle-NMP dispersion (22.5 g), in which the contents of SiO₂ and water were 40 wt% and 1 wt% or less, respectively.

5 (2) surface-modification of silica nanoparticles

The procedure of Example 3 was repeated except for adding NMP in place of GBL, to surface-modify the silica nanoparticles and thereby to obtain surface-modified silica nanoparticles.

10 [0050] The dispersibility and transparency of the produced surface-modified silica nanoparticles were confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility and transparency when dispersed in both decalin and toluene, which are

15 hydrophobic organic dispersion media, in amounts of 5 wt%, 15 wt% and 30 wt%. The 30 wt% dispersions were very slightly clouded, but the degrees thereof were practically negligible. The prepared decalin and toluene

20 dispersions of the surface-modified silica nanoparticles were individually successfully filtrated through a micro-filter having a pore diameter of 0.20 μm (Millex [trade-

 mark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE).

25 [0051] [Comparative example 1]

Surface-modification of silica nanoparticles in water/alcohol dispersion

 An aqueous dispersion (7.64 g) of silica sol (SiO₂ content: 30 wt%, mean particle size: 25 nm; Klebosol

30 30HB 25K [trademark], manufactured by AZ electronic materials K.K.) was placed in a reaction vessel equipped with a stirrer. Successively, methoxy(dimethyl)n-octadecylsilane (3.44 g), pure water (0.05 g) and isopropyl

 alcohol (21.61 g) were added thereto and then the

35 mixture was stirred. Subsequently, after the reaction was conducted at room temperature for 48 hours, the

formed precipitates were collected by filtration, washed with isopropyl alcohol and dried in vacuum at 40°C, to obtain the product (surface-modified silica nanoparticles) in a yield of 88%.

5 [0052] The dispersibility of the product was confirmed. As a result, the produced nanoparticles exhibited favorable dispersibility when dispersed in both decalin and toluene, which are hydrophobic organic dispersion media, in an amount of 5 wt%. On the other hand,
10 however, the dispersions were clouded and hence found to be poor in transparency. Further, the prepared decalin and toluene dispersions of the surface-modified silica nanoparticles were individually attempted to be filtrated through a microfilter having a pore diameter of
15 0.20 µm (Millex [trademark] FG (Syring-driven Filter Unit) Hydrophobic Fluoropore™ (PTFE) Membrane for Fine Particle Removal from Organic Solution, manufactured by MILLIPORE), but the attempts resulted in failure and the silica nanoparticles were observed to
20 agglomerate.

[0053] [Comparative example 2]

Surface-modification of silica nanoparticles with trialkoxylmonoalkylsilane coupling agent

After the step of replacing the dispersion medium
25 was carried out in the manner described in Example 1, the silica nanoparticle-GBL dispersion (3.01 g) was placed in a reaction vessel equipped with a stirrer. Successively, γ-butyrolactone (31.39 g) and n-octadecyltrimethoxysilane (1.57 g) were added thereto and then
30 the mixture was stirred. Subsequently, after the reaction was conducted at room temperature for 48 hours, the formed precipitates were collected by filtration, washed with isopropyl alcohol and dried in vacuum at 40°C, to obtain the product (surface-modified
35 silica nanoparticles) in a yield of 90%.

[0054] The dispersibility of the product was confirmed.

As a result, the produced nanoparticles exhibited poor dispersibility when dispersed in any of decalin and toluene, which are hydrophobic organic dispersion media, and N-methyl-2-pyrrolidone and γ -butyrolactone, which are hydrophilic organic dispersion media.

[0055] <measurement of mean particle size>

The mean particle sizes of the surface-modified silica nanoparticles obtained in Examples 1 to 7 were measured according to dynamic light scattering method (by means of Nanotracs particle size distribution analyzer [trademark], manufactured by Nikkiso Co., Ltd.). The silica nanoparticles of each Example were dispersed in each dispersion medium to prepare a 1 wt% organosol dispersion, which was then subjected to the measurement. Each mean particle size was represented by the median diameter (D50). On the other hand, however, the mean particle size of the nanoparticles obtained in Comparative example 1 could not be measured by dynamic light scattering method. Since not penetrating the filter having a pore diameter of 0.20 μm , the surface-modified silica nanoparticles of Comparative example 1 were considered to have a mean particle size of more than 0.2 μm .

[0056] <evaluation of transparency>

As for the transparency, the surface-modified silica nanoparticle dispersions obtained in Examples 1 to 7 and Comparative example 1 and 2 were evaluated and classified into the following grades:

A: highly transparent and very clear without any cloud,
B: negligibly clouded,
C: clouded,
D: very clouded.

[0057] <evaluation of dispersibility>

As for the dispersibility, the surface-modified silica nanoparticle dispersions obtained in Examples 1 to 7 and Comparative example 1 and 2 were evaluated and

classified into the following grades:

A: precipitates were not observed,

B: precipitates were observed.

[0058] <evaluation of storage stability>

5 The surface-modified silica nanoparticle disper-
sions obtained in Examples 1 to 7 and Comparative
example 1 and 2 were stored at room temperature for 3
months in sealed containers, and thereafter the storage
stability of each dispersion was evaluated by visually
10 observing whether the transparency changed or not and
also by observing, according to dynamic light scattering
method, whether the particle size increased or not and
whether the nanoparticles precipitated or not.

[0059] The following Tables 1 to 3 show the results of the
15 evaluations on the surface-modified silica nanoparticle
dispersions obtained in Examples 1 to 7 and Compara-
tive example 1 and 2.

Table 1

		Example 1		Example 2		Example 3	
Dispersion medium adopted in the replacement step		GBL		GBL		GBL	
Silane coupling agent		methoxytrimethylsilane (C1)		methoxy(dimethyl)octylsilane (C8)		methoxy(dimethyl)octa-decylsilane (C18)	
Dispersion medium		GBL	NMP	decalin	toluene	decalin	toluene
Silica content (wt%)		5 to 30	5 to 30	5 to 30	5 to 30	5 to 30	5 to 30
Mean particle size		26.5 nm	27.1 nm	28.4 nm	28.9 nm	30.9 nm	31.2 nm
Transparency (5 wt%)		A	A	A	A	A	A
Transparency (15 wt%)		A	A	A	A	A	A
Transparency (30 wt%)		A	A	A	A	A	A
Dispersibility		A	A	A	A	A	A
Storage stability after 3 months	Change of transparency	not found	not found	not found	not found	not found	not found
	Increase of particle size	not found	not found	not found	not found	not found	not found
	Precipitation of particles	not found	not found	not found	not found	not found	not found

Table 2

[illegible]

Table 3

		Comparative example 1		Comparative example 2			
Dispersion medium adopted in the replacement step		water + IPA		GBL			
Silane coupling agent		methoxy(dimethyl)n-octadecylsilane		n-octadecyltrimethoxysilane			
Dispersion medium		decalin	toluene	decalin	toluene	GBL	NMP
Silica content (wt%)		5	5	5	5	5	5
Mean particle size		$> 0.2 \mu\text{m}$	$> 0.2 \mu\text{m}$	–	–	–	–
Transparency (5 wt%)		C	C	D	D	D	D
Transparency (15 wt%)		–	–	–	–	–	–
Transparency (30 wt%)		–	–	–	–	–	–
Dispersibility		A	A	B	B	B	B
Storage stability after 3 months	Change of transparency	found	found	found	found	found	found
	Increase of particle size	found	found	–	–	–	–
	Precipitation of particles	found	found	found	found	found	found


CLAIMS

[1] A method for producing surface-modified silica nanoparticles, comprises:

preparing a first silica nanoparticle dispersion containing silica nanoparticles and an aqueous dispersion medium;

replacing said aqueous dispersion medium in said first silica nanoparticle dispersion with an organic dispersion medium comprising at least one selected from cyclic esters or cyclic amides, to obtain a second silica nanoparticle dispersion; and

mixing said second silica nanoparticle dispersion with a silane coupling agent represented by the formula (1):




in which each R^1 is independently a hydrocarbon group of C_1 to C_{20} and R^2 is a hydrocarbon group of C_1 to C_3 , to modify the surface of the silica nanoparticles.

[2] The method according to claim 1, wherein all the R^1 s in said silane coupling agent are hydrocarbon groups of C_1 to C_7 .

[3] The method according to claim 1, wherein at least one of the R^1 s in said silane coupling agent is a hydrocarbon group of C_8 to C_{20} .

[4] The method according to any of claims 1 to 3, wherein said organic dispersion medium comprises at least one selected from cyclic esters or amides represented by the formula (2):



in which X is O or NR^3 where R^3 is H or a hydrocarbon group of C_1 to C_3 , and n is an integer of 2 to 5.

[5] The method according to any of claims 1 to 4, wherein said second silica nanoparticle dispersion further comprises another dispersion medium selected from ethers, non-cyclic esters, non-cyclic amides or mixtures thereof.

[6] The method according to any of claims 1 to 5, wherein said aqueous dispersion medium is mixed with one or more alcohols having boiling points lower than that of said organic dispersion medium by 30°C or more before replaced with said organic dispersion medium.

[7] The method according to any of claims 1 to 6, wherein said surface-modified silica nanoparticles have a mean particle size of 100 nm or less.

[8] The method according to any of claims 1 to 7, which further comprises the steps of filtrating and then drying said second silica nanoparticle dispersion after the step of surface-modifying said silica nanoparticles.

[9] Surface-modified silica nanoparticles obtained by the method according to any of claims 1 to 8.

[10] A surface-modified silica nanoparticle dispersion obtained by dispersing the surface-modified silica nanoparticles according to claim 9 in an organic dispersion medium.