

6

-1-

REPLACED SHEETS SG

- ☒ Description : paged ...1... to paged ...23...
- ☒ Claim(s) : paged ...24... to paged ...26...
- ☐ Drawing(s) : paged to paged
.....
- ☒ Abstract : paged ...27... to paged
.....

PROCESS FOR PREPARATION OF SYNDIOTACTIC
VINYL AROMATIC POLYMERS


The present invention relates to a process for polymerizing vinyl aromatic monomers, such as styrene, to produce polymers having a high degree of syndiotacticity, and more particularly to a process for preparing polymers of vinyl aromatic monomers having a high degree of syndiotacticity using an alkyl-aluminoxane-free catalyst. Such polymers may be usefully employed in the preparation of solid objects and articles such as a moldings, films, sheets and foamed objects by molding, casting or the like process.

In USP 4,680,353 there is disclosed a process for the preparation of polymers of vinyl aromatic monomers having a stereoregular structure of high syndiotacticity by the use of certain coordination catalysts. Particularly disclosed were the reaction products of a titanium compound and an organoaluminum compound, especially polymethylaluminoxane. The process disclosed in this patent, however, requires the use of large amounts of the polymethylaluminoxane which is very expensive and difficult to make due to its very complex structure. Also, this process requires an expensive polymer purification system to remove remaining catalyst

C-38,253B-F

-1-


This Sheet Has Been Replaced



components due to the use of large amounts of the polymethylaluminoxane.

In EP 277,004 there are disclosed certain bis(cyclopentadienyl) metal compounds formed by reacting a bis(cyclopentadienyl) metal complex with salts of Bronsted acids containing a non-coordinating compatible anion. The reference discloses the fact that such complexes are usefully employed as catalysts in the polymerization of olefins.

According to the present invention there is now provided a process for preparing a syndiotactic polymer of a vinyl aromatic monomer said process comprising contacting at least one polymerizable vinyl aromatic monomer under polymerization conditions with a catalyst characterized in that the catalyst comprises a metal complex of the formula:



wherein:

Cp is a single η^5 -cyclopentadienyl group or a η^5 -substituted cyclopentadienyl group which may optionally also be bonded to M through a substituent;

M is a metal of Group 3, 4, 5, 6, 8, 9, 10 or the Lanthanide Series of the Periodic Table;

each X independently is an inert anionic ligand or a group of formula R, with the proviso that at least one X is R;

X' is an inert, neutral donor ligand;

each R independently is hydride, or is hydrocarbyl or silyl, optionally substituted with one or



more halogen atoms or alkoxy groups, and having up to 20 carbon and/or silicon atoms;

m and p are independently 0 or 1;

n is an integer greater than or equal to 1; and

5 the sum of m and n is one less than the valence of M, or when Cp is optionally bonded to M through a substituent, the sum of m and n is two less than the valence of M; and

10 A⁻ is a noncoordinating, compatible anion of a Bronsted acid salt.

As used herein, the term "syndiotactic" when used to refer to a polymer, indicates a polymer of which greater than 50 percent and preferably greater than 75 percent of the triads present are syndiotactic, as determined by C¹³ nuclear magnetic resonance spectroscopy. Such polymers may be usefully employed in the preparation of articles and objects (e.g., via compression molding, injection molding or other suitable technique) having an extremely high resistance to deformation due to the effects of temperature.

25 Examples of R include aralkyl, alkaryl, haloalkyl, silylalkyl, haloalkyl, haloaryl, haloalkaryl, halosilyl, haloalkarylsilyl, alkoxyalkyl, and so forth.

30 The term "inert" means noninterfering with the desired catalyst preparation or with the use of the resulting metal complex containing compound as a polymerization catalyst.

Illustrative but nonlimiting examples of X include R, halo, NR₂, PR₂, OR, SR, BR₂, etc.

Illustrative but nonlimiting examples of X' include ROR, RSR, NR₃, PR₃, C₂₋₂₀ olefin or diolefins,



etc. Such donor ligands are able to form shared electron bonds but not a formal covalent bond.

5 The catalytically effective ingredients of the catalysts used in the present invention are prepared by combining at least two components as hereinafter disclosed. The first component is a derivative of a metal of Group 3, 4, 5, 6, 8, 9, 10 or the Lanthanide Series of the Periodic Table of the Elements containing at least one substituent which will combine with the cation of a second component (described hereinafter) or alternatively which is subject to oxidative activation as hereinafter described. The first component additionally must be capable of forming a cation formally having a coordination number that is one less than its valence. The second component is a salt of a Bronsted acid and a noncoordinating compatible anion or alternatively a salt of an oxidizing cation and a noncoordinating, compatible anion.


10 20 All reference to the Periodic Table of the Elements herein shall refer to the Periodic Table of the Elements, published and copyrighted by CRC Press, Inc., 1989. Also, any reference to a Group or Series shall be 25 to the Group or Series as reflected in this Periodic Table of the Elements, utilizing the IUPAC system for numbering groups.

30 As used herein, the recitation "noncoordinating, compatible anion" means an anion which either does not coordinate with the first component or a derivative thereof; or which is only weakly coordinated to said component thereby remaining sufficiently labile to be displaced by the vinyl aromatic monomer to be polymerized. The recitation "noncoordinating,



compatible anion" specifically refers to an anion which when functioning as a charge balancing anion in the catalyst system of this invention does not transfer an anionic substituent or fragment thereof to the cationic portion of the catalyst. Compatible anions are also
5 anions which are not degraded to neutrality under the reaction conditions of the present invention.

Cyclopentadienyl and substituted
10 cyclopentadienyl groups for use according to the present invention are more specifically depicted by the formula:



wherein:

20 each R' independently is hydrogen, halogen, R, N-R₂, P-R₂; OR; SR or BR₂, wherein R is as previously defined; and

25 R'' is a group of the formula R' as defined above or a divalent group of from 2 to 7 nonhydrogen atoms that is covalently bonded to M.

30 Preferably, R' is alkyl or haloalkyl of up to 6 carbons, and preferably R'' is alkyl haloalkyl of up to 6 carbons or C₂₋₅ oxyalkylene or alkylene.

Illustrative, but not limiting examples of metal derivatives (first components) which may be used in the preparation of the compounds of this invention



are derivatives of titanium, zirconium, hafnium, chromium, lanthanum, etc.

- More preferably such metal derivative compounds are those having organyl substituents that are either
- 5 devoid of reactive hydrogens or wherein potentially reactive hydrogens are protected by bulky protecting groups. Illustrative, but not limiting examples of suitable metal derivative compounds include:
- 10 tetranorborenyl titanium, tetrabenzyl zirconium, tetraneopentyl titanium, (cyclopentadienyl)dimethyl- (isopropoxy)titanium, (cyclopentadienyl)dibenzyl- (isopropoxy)titanium, (cyclopentadienyl)dibenzyl- (phenoxy)zirconium, (cyclopentadienyl)dibenzyl-
- 15 (isopropoxy)hafnium, (cyclopentadienyl)dimethylzirconium chloride, (cyclopentadienyl)methylium chloride, bis(phenoxy)di(trimethylsilyl)zirconium, phenoxytrimethylzirconium, bis(2,6-diisopropyl-4-methyl)phenoxy)dibenzyltitanium, bis(2,4,6-
- 20 trimethylphenoxy)dibenzyltitanium, tri(tertiary butyl)siloxytrimethyl zirconium, bismethoxy-di(phenylmethyl)titanium, bis(2,4,6-trimethylphenoxy)dibenzyltitanium, triphenoxybenzyltitanium, bis(2,4,6-trimethylphenoxy)propylscandium,
- 25 butoxytris((trimethylsilyl)methyl)zirconium, dimethoxydimethylzirconium, 4-(1-methyl-1-(4-methoxyphenyl)ethyl)phenoxy tribenzyl titanium, dinorborneyldichlorotitanium, tribenzyltitanium hydride,
- 30 cyclopentadienyltribenzylzirconium, cyclopentadienyltribenzyltitanium, cyclopentadienyltrimethyltitanium, cyclopentadienyltrimethylzirconium, cyclopentadienyltrineopentyltitanium, cyclopentadienyltri(diphenylmethyl)zirconium, cyclopentadienyltriphenylzirconium, cyclopentadienyltrineopentylzirconium, cyclo-



pentadienyldi(m-tolyl)zirconium, cyclopentadienyldi(p-tolyl)zirconium, cyclopentadienyltrimethyltitanium hydride, cyclopentadienyltridiphenylmethylzirconium, and the like; hydrocarbyl-substituted cyclopentadienyl compounds such as pentamethylcyclopentadienyl-

5 trimethylzirconium, ethylcyclopentadienyltrimethylzirconium, pentamethylcyclopentadienyltribenzylzirconium, n-butylcyclopentadienyltrineopentyltitanium, (t-butylcyclopentadienyl)tri(trimethylsilyl)zirconium,

10 cyclohexylcyclopentadienyldimethylzirconium, (pentamethylcyclopentadienyl)dimethylzirconium chloride, indenyl dibenzyltitanium chloride, (pentamethylcyclopentadienyl)diisopropoxyhafnium chloride,

15 (benzylcyclopentadienyl)di(m-tolyl) titanium chloride, (diphenylcyclopentadienyl)dinorborneylzirconium chloride, methylcyclopentadienyltriphenylzirconium, tetraethylcyclopentadienyltribenzylzirconium, propylcyclopentadienyltrimethylzirconium, propylcyclopentadienyltrimethylzirconium, (n-butylcyclopentadienyl)

20 dimethyl(n-butoxy)titanium, cyclopentadienyldiphenylisopropoxyzirconium, cyclohexylmethylcyclopentadienyltribenzylzirconium, cyclohexylmethylcyclopentadienyltrimethylzirconium, cyclopentadienylzirconium dihydride, benzylcyclopentadienyldimethylhafnium,

25 indenyltribenzylzirconium, trimethylsilylcyclopentadienyltrimethylzirconium, trimethylgermylcyclopentadienyl)trimethyltitanium, trimethylstannylcyclopentadienyltribenzylzirconium, (penta-

30 trimethylsilyl)cyclopentadienyltrimethylzirconium, trimethylsilylcyclopentadienyltrimethylzirconium, penta(trimethylsilyl)cyclopentadienyltribenzyltitanium, trimethylgermylcyclopentadienyltriphenylhafnium, cyclopentadienylbis(p-tolyl)scandium, cyclopentadienyl-dibenzylchromium, pentamethylcyclopentadienylbis-



(trimethylsilylmethyl)yttrium, pentamethylcyclopentadienylbis(trimethylsilylmethyl)scandium, pentamethylcyclopentadienylbis(trimethylsilyl)lanthanum, and the like; halogen-substituted cyclopentadienyl compounds such as trifluoromethylcyclopentadienyltri-
5 methylzirconium, trifluoromethylcyclopentadienyltrinorbornylzirconium, trifluoromethylcyclopentadienyltribenzylzirconium, and the like; silyl-substituted (cyclopentadienyl)metal compounds such
10 as cyclopentadienyltrimethylsilylzirconium, cyclopentadienyltri(phenyldimethylsilyl)zirconium, and the like.

Other compounds which are useful in the
15 catalyst compositions of this invention especially compounds containing other Group 3, 4, 5, 6, 8, 9, 10 or Lanthanide metals will, of course, be apparent to those skilled in the art.

20 Preferred components are titanium or zirconium compounds.


Compounds useful as a second component in the preparation of the catalyst used in this invention may,
25 in one embodiment, comprise a cation, which is a Bronsted acid capable of donating a proton, and a compatible, noncoordinating anion. In another embodiment such compounds comprise an oxidizing cation and a compatible, noncoordinating anion. Preferred
30 anions are those containing a single coordination complex comprising a charge-bearing metal or metalloid core which anion is relatively large (bulky), capable of stabilizing the active catalyst species (the Group 3, 4, 5, 6, 8, 9, 10 or Lanthanide Series cation) formed when the two components are combined, and which will be



sufficiently labile to be displaced by the polymerizable vinyl aromatic monomer.

5 The term "metalloid", as used herein, includes non-metals such as boron, phosphorus and the like which exhibit semi-metallic characteristics. Suitable metals, include, but are not limited to, aluminum, gold, platinum and the like. Suitable metalloids include, but are not limited to, boron, phosphorus, silicon and the like. Compounds containing anions which comprise
10 coordination complexes containing a single metal or metalloid atom are, of course, well known. In light of this, salts containing anions comprising a coordination complex containing a single boron atom are preferred.

15 Preferably, second components useful in the preparation of the catalysts used in this invention may be represented by the following general formulas:



wherein:

L is a neutral Lewis base;

25 $(L-H)^+$ is a Bronsted acid;

$[A]^-$ is a compatible, noncoordinating anion;

Ox^+ is an organic or metallic oxidizing cation;

30 and


$[A^*]^-$ is a compatible, noncoordinating, inert, anion.

By the term "inert" as employed above is meant that A^* of formula (II) comprises an anion which is a



single coordination complex comprising a plurality of lipophilic radicals covalently coordinated to and shielding a central formally charge-bearing metal or metalloid atom, which anion is bulky and stable under the oxidation and subsequent polymerization conditions, and which anion is compatible with and noncoordinating towards the resulting polymerization catalyst. The anion is employed only to provide charge balance without interfering with the oxidizing ability of Ox^+ .

Anions comprising boron which are particularly useful as $[A^*]^-$ may be represented by the following general formula:




wherein:

B is boron in a valence state of 3;

X_1 to X_4 are the same or different nonreactive, organyl or silyl radicals containing from 1 to 20 carbon or silicon atoms. In addition two or more of X_1 to X_4 may be linked to each other through a stable bridging group. Preferably X_1 to X_4 lack reactive hydrogen moieties. That is, the radicals are either devoid of hydrogen, contain only hydrogen in nonactivated positions or contain sufficient steric hinderence to protect potentially active hydrogen sites. Examples of suitable radicals for X_1 to X_4 are perfluorinated hydrocarbyl radicals containing from 1 to 20 carbon atoms, 3,4,5-trifluorophenyl, 3,4-di(trifluoromethyl)phenyl, etc.

A most highly preferred compatible, non-coordinating, inert, anion for use in compounds


This Sheet Has Been Replaced



corresponding to formula (II) is tetra(pentafluorophenyl)borate.


Suitable oxidizing cations include organic and inorganic cations having sufficient electronegativity to oxidize the metal derivatives. Organic oxidizing cations for use in the compounds corresponding to formula (II) include ferrocenium ions, indenium ions and cationic derivatives of substituted ferrocene, indene, and the like molecules. Suitable metallic oxidizing cations include Ag^{+1} , Pd^{+2} , Pt^{+2} , Hg^{+2} , Hg_2^{+2} , Au^{+} and Cu^{+} . The process of the invention involves a molecular oxidation. The Group 3, 4, 5, 6, 8, 9, 10 or Lanthanide metal is previously fully oxidized. Highly preferred oxidizing cations have an oxidation potential of at least +0.20 volt and preferably at least +0.25 volt. Most highly preferred oxidizing cations are ferrocenium and Ag^{+1} cations.

Without wishing to be bound by any particular theory of operation it is believed that the oxidizing cation causes the molecular oxidation of the metal derivative, and in the process becomes a neutral species. The oxidized metal derivative loses a hydrogen or hydrocarbyl radical ($\cdot\text{R}$) by a unimolecular elimination reaction. Two or more such radicals form a hydrogen molecule or a neutral organic species of the formula $\text{R}(\text{R}_x)$ where x is an integer. These byproducts are neutral or noninterfering with any subsequent polymerization reaction and may also be removed from the reaction mixture. The preparation technique is analogous to that previously disclosed by R. Jordan, et al., J. A. C. S., 109, 4111-4113 (1987).



Illustrative, but not limiting, examples of oxidizing agents according to formula (II) are ferrocenium tetra(pentafluorophenyl)borate, gold (I) tetrakis 3,4,5-trifluorophenyl borate, silver tetra(pentafluorophenyl)borate, 1,1'-dimethylferrocenium tetrakis 3,5-bistrifluoromethylphenyl borate and the like.

Returning to above formula (I), preferably A⁻ corresponds to the formula:



wherein:


M' is a metal or metalloid selected from Groups 5-15 of the Periodic Table of the Elements;

each Q independently is hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl; or substituted hydrocarbyl containing up to 20 carbon atoms with the proviso that in not more than one occurrence is Q halide;

n' is an integer from 2 to 8; and

n-m = 1;

Second components comprising boron are particularly useful in the preparation of catalysts of formula (I) and may be represented by the following general formula:



wherein:



L is a neutral Lewis base;

$[L-H]^+$ is a Bronsted acid;

B is boron in a valence state of 3; and

5 Q is as previously defined.

Illustrative, but not limiting, examples of boron compounds which may be used as a second component in formula (I) are trialkyl-substituted ammonium salts
10 such as triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tri(n-butyl)ammonium tetraphenylborate, trimethylammonium tetra(p-tolylborate), tributylammonium tetrakis-
15 pentafluorophenylborate, tripropylammonium tetrakis-2,4-dimethylphenylborate, tributylammonium tetrakis-3,5-dimethylphenylborate, triethylammonium tetrakis-(3,5-di-trifluoromethylphenyl)borate and the like. Also
suitable are N,N-dialkyl anilinium salts such as N,N-
20 dimethylanilinium tetraphenylborate, N,N-diethylanilinium tetraphenylborate, N,N-2,4,6-pentamethylanilinium tetraphenylborate and the like; dialkyl ammonium salts such as di-(i-propyl)ammonium tetrakis-
25 pentafluorophenylborate, dicyclohexylammonium tetraphenylborate and the like; and triaryl phosphonium salts such as triphenylphosphonium tetraphenylborate, tri(methylphenyl)phosphonium tetrakis-pentafluorophenylborate, tri(dimethylphenyl)phosphonium tetraphenylborate
30 and the like.

Similar lists of suitable compounds containing other metals and metalloids which are useful as second components could be made, but such lists are not deemed necessary to a complete disclosure. In this regard, it should be noted that the foregoing list is not intended



to be exhaustive and other boron compounds that would be useful as well as useful components containing other metals or metalloids would be readily apparent from the foregoing general formula and examples to those skilled in the art.

5

In general, the catalyst can be prepared by combining the two components in a suitable solvent at a temperature of from -100°C to 300°C . The catalyst system can also form *in situ* if the components thereof are added
10 directly to the polymerization process and a suitable solvent or diluent, including condensed monomer, is used in said polymerization process. It is, however, preferred to form the catalyst in a separate step in a
15 suitable solvent prior to adding the same to the polymerization step. The catalysts' components are generally sensitive to both moisture and oxygen and should be handled and transferred in an inert atmosphere such as nitrogen, argon or helium.

20

As previously indicated, the improved catalyst of the present invention will, preferably, be prepared in a suitable solvent or diluent. Suitable solvents or diluents include any of the solvents known in the prior
25 art including, but not necessarily limited to, straight and branched-chain hydrocarbons such as $\text{C}_6\text{-}_{12}$ alkanes (hexane, heptane, octane and the like); $\text{C}_6\text{-}_{12}$ cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane and
30 the like and $\text{C}_6\text{-}_{12}$ aromatic and alkyl-substituted aromatic compounds such as benzene, toluene, xylene, decalin, and the like, and mixtures thereof.




The catalysts may be employed as homogeneous catalysts or supported on the surface of a suitable support such as alumina or silica.

5 In general, catalysts according to the present invention can be selected so as to produce polymer products that will be free of certain trace metals generally found in polymers produced with Ziegler-Natta type catalysts containing cocatalysts such as aluminum or magnesium based compounds.

10 In a highly preferred embodiment of the present invention C_p is pentamethylcyclopentadiene, m is zero or one, M is titanium or zirconium, n is two or three, p is zero, X is R or OR , and A is tetrakis-pentafluorophenyl borate. In a most preferred embodiment X is C_{1-20} alkyl, aryl, aralkyl, phenoxyalkoxy and m is 0 or 1.

15 Suitable vinyl aromatic monomers which can be polymerized in the process of the present invention include those represented by the formula:




30 wherein each R is independently hydrogen; an aliphatic, cycloaliphatic or aromatic hydrocarbon group having from 1 to 10, more suitably from 1 to 6, most suitably from 1 to 4, carbon atoms; or a halogen atom. Examples of such monomers include, styrene, chlorostyrene, n-butyl



styrene, p-vinyl toluene etc. with styrene being especially suitable. Copolymers of styrene and the above vinyl aromatic monomers other than styrene can also be prepared.

5 The polymerization may be conducted under
slurry, bulk or suspension polymerization conditions or
other suitable reaction conditions including solid,
powdered reaction conditions. The polymerization can be
10 conducted at temperatures of from 0°C to 160°C,
preferably from 25°C to 100°C, more preferably from 30°C
to 80°C, for a time sufficient to produce the desired
polymer. Typical reaction times are from one minute to
100 hours, preferably from 1 to 10 hours. The optimum
15 reaction time or reactor residence time will vary
depending upon the temperature, solvent and other
reaction conditions employed. The polymerization can be
conducted at subatmospheric pressure as well as
superatmospheric pressure, suitably at a pressure within
20 the range of 1 to 500 psig (100 kPa-3,400 kPa). The use
of ambient or low pressures, e.g., 1-5 psig (100-130
kPa) is preferred in view of lower capital and equipment
costs.

25 The polymerization may be conducted in the
presence of an inert diluent or solvent or in the
absence thereof, i.e., in the presence of excess
monomer. Examples of suitable diluents or solvents
include C₆₋₂₀ aliphatic, cycloaliphatic, aromatic and
30 halogenated aliphatic or aromatic hydrocarbons, as well
as mixtures thereof. Preferred diluents comprise the
C₆₋₁₀ alkanes, toluene and mixtures thereof. A
particularly desirable diluent for the polymerization is
iso-octane, iso-nonane or blends thereof such as Isopar-
E®, available from Exxon Chemical Company. Suitable



amounts of solvent are employed to provide a monomer concentration from 5 percent to 100 percent by weight.

The molar ratio of the vinyl aromatic monomer to the catalyst (in terms of metal) may range from 100:1 to 500,000:1, preferably from 3,500:1 to 200,000:1. In the case of using a solvent, the catalyst may be used at a concentration with the range from 10^{-7} to 10^{-1} moles per liter of solvent.

As in other similar polymerizations it is highly desirable that the monomers and solvents employed be of sufficiently high purity that catalyst deactivation does not occur. Any suitable technique for monomer purification such as devolatilization at reduced pressures, contacting with molecular sieves or high surface area alumina, deaeration, etc. may be employed. In addition a small amount of an aluminum trialkyl compound or similar scavenger may be added to the reaction mixture to protect the catalyst from deactivation by contaminants in the reaction mixture.

Purification of the resulting polymer to remove entrained catalyst may also be desired by the practitioner. Purification of the resulting polymer prepared by the process of this invention is much easier than a conventional process since the process of this invention does not use polyalkylaluminum which is used in large quantities as cocatalyst in the conventional process. Entrained catalyst may generally be identified by residues of ash on pyrolysis of the polymer that are attributable to catalyst metal values. A suitable technique for removing such compounds is by solvent extraction, e.g., extraction utilizing hot, high




boiling chlorinated solvents, acids or bases such as caustic followed by filtration.

Having described the invention, the following examples are provided as further illustrative and are not to be construed as limiting. Unless stated to the contrary, all parts and percentages are based on weight.

Example 1


10 Preparation of Catalyst

In a flask, 0.10 gm of pentamethylcyclopentadienyltitanium trimethyl was added to a suspension of 0.343 gm of tri(ethyl)ammonium tetra(pentafluorophenyl)borate in 10 ml of toluene at room temperature. The obtained mixture was allowed to stir for 10 hours, and then heated to 45°C for one hour. No precipitate was observed since the mixture was a very dark solution. The toluene solvent was stripped off *in-vacuo* thereby leaving a black solid. This solid was washed 3 times with 5 ml of petroleum ether and dried *in-vacuo*. The product comprised a composition having a structure as identified by ¹³C NMR of the formula:



Preparation of Syndiotactic Polystyrene

A dry 20 ml vial was charged with 0.025 gm (28 umole) of the above catalyst and then 10.0 gm (102.9 mmol) of styrene was added. The vial was capped with a PTFE coated septum and a metal crimp cap, and shaken until most of the catalyst was dissolved. The vial was placed in a 70°C water bath for 3 hours and then the vial was taken out from the water bath and the



polymerization was stopped by the addition of methanol. The off-white, insoluble product was washed with methanol and dried *in-vacuo* to obtain 3.32 gm of a resultant polymer. The resultant polymer was insoluble in methylene chloride or other common solvents for atactic polystyrene.

The resultant polystyrene had a melting point of 268°C (by DSC) and syndiotacticity of greater than 95 percent by ^{13}C analysis. The polymer had a weight average molecular weight (M_w) of 382,000.

Examples 2-11

The reaction conditions of Example 1 were substantially repeated excepting that various catalysts and reactant ratios were employed. Accordingly, a dry 20 ml vial was charged with the catalyst further described in Table I. Styrene was added, the vial was capped with a PTFE coated septum and a metal crimp cap, and shaken until the mixture had mostly dissolved or the mixture gelled, rendering further mixing impossible. The vial was placed in a 70°C water bath for 3 hours and then the vial was taken out from the water bath and the polymerization stopped by the addition of methanol. The off white, insoluble polymer was washed with methanol and dried *in-vacuo*. In all cases the polymer was insoluble in methylene chloride and other common solvents for atactic polystyrene. Crystalline melting points were determined by differential scanning calorimetry, DSC. Syndiotacticities were determined by ^{13}C NMR analysis. Results are contained in Table I.



Table I

Example	Complex ^a	Mole Ratio Sty:Ti	Temp °C	Time h	% Yield	% Syndio	DSC °C	Mw x 10 ³
2	CMTTB	3700:1	RT	4.0	10.4	>95	263	544
3	CBTTB	7500:1	70	1.5	24.1	>95	270	---
4	CBTTB	7500:1	70	4.0	38.0	>95	269	---
5	CBTTB ^b	7500:1	70	4.0	4.5	--	260	---
6	CBTTB ^c	7500:1	70	4.0	1.4	--	267	---
7	CBTTB	10000:1	70	2.0	20.9	--	270	584
8	CSTTB	7500:1	70	1.5	8.6	--	270	340
9	CTBOMB	10000:1	70	2.0	10.0	--	270	---
10	CBTTB ^d	10000:1	70	2.0	49.8	--	266	---
11	CBTTB ^{de}	10000:1	70	2.0	32.9	--	265	---

a) CDTTB= cyclopentadienyldimethyltitanium tetra(pentafluorophenyl)borate, (Cp*Ti(CH₃)₂⁺TB⁻), CBTTB= cyclopentadienyldibenzyltitanium tetra(pentafluorophenyl)borate (Cp*Ti(CH₂C₆H₅)₂⁺TB⁻), CSTTB= cyclopentadienylditrimethylsilylmethyltitanium tetra(pentafluorophenyl)borate (Cp*Ti(CH₂Si(CH₃)₃)₂⁺TB⁻), CTBOMB= cyclopentadienyldibenzylmethoxytitanium tetra(pentafluorophenyl)borate (Cp*Ti(CH₂C₆H₅)(OCH₃)⁺TB⁻)

b) 2 ml of o-dichlorobenzene added

c) 2 ml of chloroform added

d) prepared from diisopropylethylammonium tetra(pentafluoro)boron

e) unwashed catalyst

Examples 12-15

The reaction conditions of Example 1 were substantially repeated excepting that an aluminum trialkyl compound was also present in the reaction mixture. Accordingly, a dry 20 ml vial was charged with the catalyst further described in Table II. (The catalysts were prepared according to the technique of Example 1 or (in Example 15) by contacting in equimolar quantities monocyclopentadienylyltitaniumtribenzyl with



- ferrocenium tetra(pentafluorophenyl)borate in toluene.) To a second vial styrene and an aluminum trialkyl compound (in 1M toluene solution) were combined. This solution was added to the vial containing the titanium complex, capped with a PTFE coated septum and a metal crimp cap, and shaken until the mixture had mostly dissolved or the mixture gelled rendering further mixing impossible. The vial was placed in a 70°C water bath for .2 hours and then the vial was taken out from the water bath and the polymerization stopped by the addition of methanol. The off white, insoluble polymer was washed with methanol and dried *in-vacuo*. In all cases the polymer was insoluble in methylene chloride and other common solvents for atactic polystyrene.
- Crystalline melting points were determined by differential scanning calorimetry, DSC. Syndiotacticities were determined by C¹³ NMR analysis. Results are contained in Table II.

Table II

Example	Complex ^a	Mole Ratio Styrene:Al:Ti	Temp °C	Time h	% Yield	% Syndio	DSC °C	Mw x 10 ³
12	CTBB ^b	10000:20:1	70	2	29.4	---	266	287
13	CTBB ^c	10000:18:1	70	1.5	76.2	---	269	92
14	CTBB ^d	65000:9:1	70	1.5	26.6	---	270	690
15	CTBB ^d	39000:20:1	70	1.5	67.2	---	269	604

a) CTBB= cyclopentadienyltitaniumdibenzyl tetra(pentafluorophenyl)borate

b) trimethylaluminum added to reaction

c) triethylaluminum added to reaction

d) triisobutylaluminum added to reaction




Example 16

In an argon atmosphere dry box, a dry 20 ml vial was charged with 2.2 mg (4.4 μ mol) of bis(2,4,6 trimethylphenoxy)dibenzyltitanium and 3.8 mg (4.4 μ mol) of ferrocenium tetra(pentafluorophenyl) boron. To this was added 1 ml of dry, degassed toluene. The mixture was allowed to interact while being stirred for ~30 minutes, after which time a dark insoluble, oily product had formed. Styrene was added to the flask (10 ml, 87.4 mmol) the vial was capped with a PTFE coated septum and a metal crimp cap, shaken until most of the complex had dissolved and then placed in a 70°C water bath for 1.5 hours. The vial was removed from the water bath and the polymerization stopped by the addition of 2 ml of methanol. The off white, insoluble polymer was dried *in-vacuo* to obtain 0.34 gms of a resultant polymer. The polymer was insoluble in methylene chloride, MEK or other common solvents for atactic polystyrene, and had a crystalline melting point of 259°C, which is consistent with a polymer having >90 percent syndiotacticity.

Examples 17-22

25 Pentamethylcyclopentadienyltribenzyltitanium
Tetra(pentafluorophenyl)borate catalyzed polymerization
of p-methylstyrene and t-butylstyrene

30 In an argon atmosphere dry box, a dry 20 ml vial was charged with a calculated amount of dried, degassed monomer to provide the monomer molar ratios indicated in Table III. The vial was capped with PTFE coated septum and a metal crimp clamp, then removed from the dry box. To this vial was added via syringe, 205 μ l of a 0.0055 M catalyst solution consisting of the



reaction product derived from pentamethylcyclopentadienetriphenyl titanium, decamethylferrocenium tetra(pentafluorophenyl) borate and 5 equivalents of triisobutyl aluminum in toluene at room temperature. The vial was then placed in a 70°C water bath for 1 hour. Polymerization was stopped by the addition of methanol. The polymer was washed with methanol and dried under reduced pressure.

Crystalline melting points were determined by differential scanning calorimetry, DSC. Results are contained in Table III.

Table III

Ex.	Monomer	Ratio pMeSt:Al:Ti	Percent conv	DSC °C
17	p-methylstyrene	67,400:5:1	50.3	169, 198
18	p-methylstyrene	120,200:5:1	14.1	167, 196
19	p-methylstyrene/-styrene (9.5/90.5)	78,000:5:1	55.0	238
20	t-butylstyrene	49,100:5:1	69.4	310
21	t-butylstyrene	125,700:5:1	64.8	310
22	t-butylstyrene/-styrene (10.1/89.9)	76,000:5:1	56.6	---






2

CLAIMS:

1. A process for preparing a syndiotactic polymer of a vinyl aromatic monomer said process comprising contacting a polymerizable vinyl aromatic monomer under polymerization conditions with a catalyst characterized in that the catalyst comprises a metal complex of the formula:

5



wherein:

10

Cp is a single η^5 -cyclopentadienyl group which may optionally also be bonded to M through a substituent;

15

M is a metal of Group 3, 4, 5, 6, 8, 9, 10 or the Lanthanide Series of the Periodic Table;

each X independently is an inert anionic ligand or a group of formula R, with the proviso that at least one X is R;

20

X' is an inert, neutral donor ligand;
each R independently is hydride, or is hydrocarbyl or silyl, optionally substituted with one or more halogen atoms or alkoxy groups, and having up to 20 carbon and/or silicon atoms;

25





m and p are independently 0 or 1;


n is an integer greater than or equal to 1, the sum of m and n is one less than the valence of M, or when Cp is optionally bonded to M through the substituent, the sum of m and n is two less than the valence of M; and

A⁻ is a noncoordinating, compatible anion of a Bronsted acid salt.

2. The process according to Claim 1 wherein the monomer is contacted with the catalyst at a temperature from 0°C to 160°C.

3. The process according to any of claims 1 or 2, wherein the molar ratio of the vinyl aromatic monomer to the catalyst ranges from 100:1 to 500,000:1.

4. The process according to any of claims 1 to 3 wherein the vinyl aromatic polymer is represented by the formula:



wherein each R is independently hydrogen; an aliphatic, cycloaliphatic or aromatic hydrocarbon group having from 1 to 10 carbon atoms; or a halogen atom.





5. The process according to Claim 4 wherein the vinyl aromatic monomer is styrene.

6. The process according to any of claims 1 to 5 wherein M is titanium or zirconium.

5 7. The process according to any of claims 1 to 6 wherein Cp is pentamethylcyclopentadiene.

8. The process according to any of claims 1 to 7 wherein each X independently is R or OR.

10 ✓9. The process according to any of claims 1 to 8 wherein A is tetrakis-pentafluorophenyl borate.

15

20

25

30


This Sheet Has Been Replaced



8

ABSTRACT

A process for preparing syndiotactic vinyl aromatic polymers comprising contacting one or more aromatic monomers under polymerization conditions with a catalyst corresponding to the formula:



wherein:

- 10 Cp is a single η^5 -cyclopentadienyl or η^5 -substituted cyclopentadienyl group;
 M is a metal of Group 3, 4, 5, 6, 8, 9, 10 or the Lanthanide Series of the Periodic Table;
 X each occurrence is an inert anionic ligand, with the proviso that at least one X is R;
 15 X' is an inert, neutral, donor ligand;
 R is hydrocarbyl, silyl, a combination thereof or a substituted derivative thereof having up to 20 carbon, silicon or carbon and silicon atoms;
 m and p are independently 0 or 1;
 20 n is an integer greater than or equal to 1;
 the sum of m and n is equal to the valence of M; and
 A⁻ is a noncoordinating, compatible anion of a Bronsted acid salt.

25



REPLACED SHEETS	SG
☒ Description : paged <u>2</u> to paged <u>.....</u>	
☒ Claim(s) : paged <u>24</u> to paged <u>25</u>	
☐ Drawing(s) : paged <u>.....</u> to paged <u>.....</u>	
☒ Abstract : paged <u>26</u> to paged <u>.....</u>	

- 2 -

REPLACEMENT SHEETS	SG
☒ Description : paged <u>2</u> to paged <u>.....</u>	
☒ Claim(s) : paged <u>24</u> to paged <u>25</u>	
☐ Drawing(s) : paged <u>.....</u> to paged <u>.....</u>	
☒ Abstract : paged <u>26</u> to paged <u>.....</u>	
DATE OF RECEIPT <u>17-7-1996</u>	

components due to the use of large amounts of the polymethylaluminoxane.

5

In EP 277,004 there are disclosed certain bis(cyclopentadienyl) metal compounds formed by reacting a bis(cyclopentadienyl) metal complex with salts of Bronsted acids containing a non-coordinating compatible anion. The reference discloses the fact that such complexes are usefully employed as catalysts in the polymerization of olefins.

10

According to the present invention there is now provided a process for preparing a polymer of a vinyl aromatic monomer having a stereoregular structure of greater than 50 percent syndiotactic of a racemic triad said process comprising contacting a polymerizable vinyl aromatic monomer under polymerization conditions with a catalyst characterized in that the catalyst comprises a metal complex of the formula:

15



20

wherein:

Cp is a single η^5 -cyclopentadienyl group or a η^5 -substituted cyclopentadienyl group which may optionally also be bonded to M through a substituent;


M is a metal of Group 4 or the Lanthanide Series of the Periodic Table;


25

each X independently is an inert anionic ligand or a group of formula R, with the proviso that at least one X is R;

X' is an inert, neutral donor ligand; each R independently is hydride, or is hydrocarbyl or silyl, optionally substituted with on or

This Sheet Has Been Replaced





- 24 -



Claims:

1. A process for preparing a polymer of a vinyl aromatic monomer having a stereoregular structure of greater than 50 percent syndiotactic of a racemic triad said process comprising contacting a polymerizable vinyl aromatic monomer under polymerization conditions with a catalyst characterized in that the catalyst comprises a metal complex of the formula:



wherein:

- Cp is a single η^5 -cyclopentadienyl group or a η^5 -substituted cyclopentadienyl group which may optionally also be bonded to M through a substituent;

M is a metal of Group 4 or the Lanthanide Series of the Periodic Table;

each X independently is an inert anionic ligand or a group of formula R, with the proviso that at least one X is R;

- X' is an inert, neutral donor ligand;

each R independently is hydride, or is hydrocarbyl or silyl, optionally substituted with one or more halogen atoms or alkoxy groups, and having up to 20 carbon and/or silicon atoms;

m and p are independently 0 or 1;

- n is an integer greater than or equal to 1, the sum of m and n is one less than the valence of M, or when Cp is optionally bonded to M through the substituent, the sum of m and n is two less than the valence of M; and

A⁻ is a noncoordinating, compatible anion of a Bronsted acid salt.


2. The process according to Claim 1 wherein the monomer is contacted with the catalyst at a temperature from 0°C to 160°C.

3. The process according to any of claims 1 or 2, wherein the molar ratio of the vinyl aromatic monomer to the catalyst ranges from 100:1 to 500,000:1.


4. The process according to any of claims 1 to 3 wherein the vinyl aromatic polymer is represented by the formula:

This Sheet Has Been Replaced





- 25 -




wherein each R is independently hydrogen; an aliphatic, cycloaliphatic or aromatic hydrocarbon group having from 1 to 10 carbon atoms; or a halogen atom.

- 5 5. The process according to Claim 4 wherein the vinyl aromatic monomer is styrene.
6. The process according to any of claims 1 to 5 wherein M is titanium or zirconium.
7. The process according to any of claims 1 to 6 wherein Cp is pentamethylcyclopentadiene.
- 10 8. The process according to any of claims 1 to 7 wherein each X independently is R or OR.
9. The process according to any of claims 1 to 8 wherein A is tetrakis-pentafluorophenyl borate.
- 15 10. A process according to claim 1 substantially as hereinbefore described with reference to any one of the Examples.

This Sheet Has Been Replaced






PROCESS FOR PREPARATION OF SYNDIOTACTIC VINYL AROMATIC POLYMERS

ABSTRACT

A process for preparing syndiotactic vinyl aromatic polymers comprising contacting one or more aromatic monomers under polymerization conditions with a catalyst corresponding to the formula:



wherein:

Cp is a single η^5 -cyclopentadienyl or η^5 -substituted cyclopentadienyl group;

M is a metal of Group 3, 4, 5, 6, 8, 9, 10 or the Lanthanide Series of the Periodic Table;

X each occurrence is an inert anionic lignd, with the proviso that at least one X is R;

X' is an inert, neutral, donor ligand;

R is hydrocarbyl, silyl, a combination thereof or a substituted derivative thereof having up to 20 carbon, silicon or carbon and silicon atoms;

m and p are independently 0 or 1;

n is an integer greater than or equal to 1;

the sum of m and n is equal to the valence of

M; and

A⁻ is a noncoordinating, compatible anion of a Bronsted acid salt.

This Sheet Has Been Replaced

