

Description

The present invention concerns dielectric materials, and in particular low dielectric constant dielectric materials suitable for use, without limitation, in multilayer printed circuit boards.

The principal conventional dielectric material in present use for printed circuit boards is a laminated composite comprised of fiberglass fabric impregnated with a thermosetting epoxy resin, referred to by the National Electronic Manufacturers Association (NEMA) classification as FR₄. FR₄ is produced by impregnating fiberglass fabric with a liquid, thermosetting epoxy resin. The resin in the impregnated fabric is partially cured with heat to form a dry, flexible sheet in which the resin is in an intermediate cure state, termed "B"-stage or "pre-preg" sheet. One or more sheets of pre-preg are then stacked together to a desired thickness and laminated together by further curing under heat and pressure to form a laminated composite in which the resin is in a fully-cured state, termed the "C"-stage state.

During the lamination process, the B-stage epoxy resin of the pre-preg sheet is converted to fully-cured C-stage resin. Normally, the sheets of pre-preg are bonded to one or two sheets of copper foil during the lamination process so that the laminated composite consists of dielectric material clad on one or both sides with copper foil. This composite material is referred to as the FR₄ copper clad laminate and is fabricated into single and double sided printed circuit boards.

Where very high circuit densities are required printed circuit boards with more than two layers of circuitry have been developed, called multilayer printed circuit boards. Thin dielectric FR₄ copper clad laminate is fabricated into single or double sided circuit patterns called innerlayers. One or more of these innerlayers are interleaved with one or more sheets of B-stage pre-preg and laminated together under heat and pressure to form a homogeneous, void free multilayer structure. The lamination process converts the B-stage epoxy resin of the pre-preg into C-stage resin, bonding the innerlayers together and providing insulation between the circuit layers. The multilayered structure is further processed into a multilayer printed circuit board.

The thermosetting resin is essential to the fabrication of multilayer printed circuit boards in which the resin is uniform throughout. The B-stage resin in the pre-preg is converted to a fully-cured C-stage state without melting or materially altering the C-stage dielectric material in the innerlayers. Because the intermediately cured pre-preg is essentially the same composition as the C-stage resin in the innerlayers, the multilayer composite is dimensionally stable and easily processed.

There is a need in the electronics industry for dielectric materials having lower dielectric constants than that of conventional materials because signal speeds and operating frequencies of electronic systems have increased

dramatically. Lower dielectric constant dielectric materials both decrease capacitive coupling and increase the speed of the electronic signal so that electronic systems can process data at greater speeds.

FR₄ laminate has a relatively high dielectric constant, approximately 5.0 at 1 megahertz. This is a result of the high dielectric constant contribution of the fiberglass, 6.11, averaged with the lower dielectric constant of the epoxy resin, 3.4. To achieve a lower dielectric constant dielectric material, the electronics industry has turned to laminated composites comprised of fiberglass fabric impregnated with fluorocarbon resins. These laminated composites have a dielectric constant of approximately 2.5 at 1 megahertz. However, fluorocarbons are not thermosetting resins and are extremely difficult to fabricate into multilayer printed circuit boards. At temperatures at which the fluorocarbon pre-preg sheets will bond the package together, the innerlayers can melt or lose their dimensional stability. If FR₄ pre-pregs are used to bond the fluorocarbon innerlayers together, the resulting multilayer composite is non-homogeneous and the dielectric constant is raised as a result of the higher dielectric constant of the pre-preg.

Other specialty dielectric materials have been developed which utilize fibers other than fiberglass in combination with thermosetting resins. Laminated composites of polyaramide fibers and epoxy resins have a dielectric constant of 3.8, which is considerably higher than the fluorocarbon composites. Quartz fibers have been used in composites, but quartz fibers have nearly the same dielectric constant as polyaramide fibers.

It is known from GB-A-2061989 to provide an insulating board which comprises one or more layers of polymeric fibrous material, such as P.T.F.E., having a predetermined dielectric constant impregnated with a thermosetting polymer having a dielectric constant which is close to that of the dielectric constant of said fibrous material.

According to the present invention there is provided a dielectric material comprising a fabric having fibers and interstices between said fibers, in which at least a portion of the fibers in said fabric are fluorocarbon fibers which have been treated to make the fluorocarbon fibers wettable by an uncured thermosetting resin, the fabric being impregnated within said interstices between said fibers with a thermosetting resin cured to at least the semi-cured, B-stage state, the dielectric constant of said dielectric material being less than 3.5.

Preferably the dielectric constant of the material is less than 3.0. The thermosetting resin may be cured to the fully-cured, C-stage state and the dielectric material may have electrically conductive foil bonded to at least one surface thereof.

The present invention also provides a laminated composite structure comprising one or more sheets of this dielectric material in which the thermosetting resin is cured to the fully-cured, C-stage state, and one or more sheets of the

dielectric material in which the thermosetting resin is cured to the semi-cured, B-stage state, oriented such that, wherever a layer of material in the C-stage state contacts another layer, the other layer is of material in the B-stage state.

In a laminated composite structure comprising one or more sheets of this dielectric material in which the thermosetting resin is cured to the fully-cured, C-stage state, and having an electrically conductive foil bonded to at least one side of at least one of the sheets, and one or more sheets of the dielectric material in which the thermosetting resin is cured to the semi-cured, B-stage state, the layers are oriented such that, wherever a layer of material in the C-stage state contacts another layer, and wherever an electrically conductive foil contacts another layer, the other layer is of material in the B-stage state.

The composite structure may have at least one additional layer of a material other than the dielectric material of this invention. This additional layer may be a layer of epoxy/fiberglass, fluorocarbon/fiberglass, polyimide/fiberglass, epoxy/polyaramide fiber, epoxy/quartz fiber and polyimide/quartz fiber composites. The thermosetting resin may be an epoxy, polyimide, polyamide, polyester, phenolic or an acrylic thermosetting resin. It is preferably an epoxy resin. All fibers in the fabric can be fluorocarbon fibers or combinations of fluorocarbon fibers with fiberglass fibers, polyaramide fibers, or quartz fibers. The fabric may be a woven fabric or a non-woven felt or mat. The fluorocarbon fibers are preferably PTFE fibers which may be drawn, non-porous, sintered PTFE fibers or expanded, porous PTFE fibers. The fluorocarbon fibers may contain a filler which can be a dielectric insulator material such as ceramic or glass, or it may be electrically conductive such as electrically conductive or semi-conductive metals, metal oxides or carbon. The dielectric material is useful in a printed circuit laminated composite, as a dielectric insulator for submicrowave or microwave signals. It may be used in a microwave printed circuit board and in a microwave radome.

The invention also provides a process for making the dielectric material comprising: (a) treating fluorocarbon fibers to render them wettable by an uncured thermosetting resin, the fibers being held under longitudinal tension during such treatment, thereby preventing longitudinal shrinkage of the fibers during treatment, (b) weaving the fabric containing at least a portion of the treated fluorocarbon fibers, (c) impregnating the fabric with an uncured thermosetting resin, and (d) heating and drying the resin-impregnated-fabric to cure the resin to at least the semi-cured, B-stage state. Alternatively the process for making the dielectric material may comprise the steps of: (a) treating a fabric containing at least a portion of fluorocarbon fibers to render the fluorocarbon fibers wettable by an uncured thermosetting resin, the fabric being restrained from shrinkage during such treatment or, alternatively, the fabric being allowed to shrink during treatment and

stretched to nearly its original dimensions after treatment, (b) impregnating the fabric with an uncured thermosetting resin, and (c) heating and drying the resin-impregnated-fabric to cure the resin to at least the semi-cured, B-stage state. The process may include the step of calendering the fabric to reduce its thickness. The treatment to make the fluorocarbon fibers wettable may include applying an alkali naphthanate solution to the fluorocarbon fibers or fabric. The process may include napping the fluorocarbon fibers to improve wettability and adhesion between fibers and resin.

The fibers or fabric can be bleached subsequent to the treatment to make them wettable, in order to lighten the colour of the fibers.

The invention will now be particularly described by way of example with reference to the accompanying drawings, in which:—

Figure 1A is a schematic diagram of a process for making a dielectric material according to the invention;

Figure 1B is a schematic diagram of a process for treating a fluorocarbon fiber which can be woven into a fabric, shown in Figure 1C, and which can be processed in a similar manner to that of Figure 1 to make the dielectric material;

Figure 2 shows a stack of pre-preg sheets of the dielectric material having sheets of metal foil above and below the pre-preg sheets;

Figure 3 shows the result of applying heat and pressure to the sheets of Figure 2, to produce a composite having fully-cured, C-stage resin and the copper foil bonded thereto on both top and bottom;

Figure 4 shows a fabric for use in the invention having all fluorocarbon fibers;

Figure 5 shows a fabric for use in the invention having fluorocarbon fibers and fiberglass fibers;

Figure 6 shows a dielectric material according to the invention having a printed circuit bonded thereto;

Figure 7 shows a stack of metal foils, dielectric sheets and a central printed circuit board just prior to lamination and bonding, and

Figure 8 is a diagram of the stack shown in Figure 7 after being bonded by application of heat and pressure.

By means of this invention dielectric materials can be provided having a dielectric constant below 3.5 and 1 megahertz while exhibiting the desirable handling and fabricating characteristics of structures fabricated from thermosetting resins. Moreover, a system of pre-preg sheets and innerlayer printed circuit laminates can be provided having a dielectric constant below 3.5 at 1 megahertz which can be fabricated into a homogeneous, void free, multilayer printed circuit.

The dielectric materials in accordance with the present invention are comprised of thermosetting resins reinforced with fluorocarbon fibers. In the process of the present invention fluorocarbon fibers are treated under longitudinal tension, preferably with an alkali naphthanate solution, to

provide a wettable surface. The longitudinal tensioning of the fiber during treatment with an alkali naphthanate is utilised because, surprisingly, the fluorocarbon fiber shrinks up to approximately 20% during the treatment process if left unrestrained. The treated fiber is woven into a fabric using conventional weaving practices.

Treated fluorocarbon fabric can be impregnated with a liquid thermosetting resin and partially cured to a dry, flexible sheet of B-stage pre-preg. One or more of the B-stage pre-preg sheets can be stacked together to a desired thickness and laminated under heat and pressure to form a laminated composite of thermosetting resin and fluorocarbon fabric. If epoxy is used as the thermosetting resin, then the fluorocarbon fabric laminated composite has a dielectric constant at 35 volume % epoxy of approximately 2.6 at 1 megahertz. The sheet of fluorocarbon fiber pre-preg can be bonded to one or two sheets of copper foil during the lamination process so that the laminated composite consists of dielectric material clad on one or both sides with copper foil. If epoxy is used as the thermosetting resin, then the resulting fluorocarbon fiber, copper clad laminate has a dielectric constant at 35 volume % of epoxy of 2.6 at 1 megahertz. The fluorocarbon fiber, copper clad laminate can be fabricated into a single- or double-sided printed circuit board.

One or more innerlayers made from the fluorocarbon fiber, copper clad laminate can be interleaved with one or more fluorocarbon fiber pre-preg sheets and laminated together under heat and pressure to form a homogeneous, void free, multilayer structure. If epoxy is used as the thermosetting resin, then the multilayer structure has a nearly homogeneous resin composition when further processed into a multilayered printed circuit board.

This process of impregnating specially treated fluorocarbon fabrics with thermosetting resin has resulted in unique products which exhibit a dielectric constant below 3.5 and retain the processing and handling advantages of thermosetting resins. It is the only known method of fabricating homogeneous, void free, multilayer printed circuit boards having a uniform dielectric constant, being always below 3.5 at 1 megahertz.

Specific fluorocarbon fibers impart desirable physical properties to the laminated composite. Fluorocarbon fibers of drawn, sintered polytetrafluoroethylene (PTFE) made according to the teachings of U.S. Patent 2,772,444 can be utilized in the present invention. However, the preferred fluorocarbon fiber for this invention is expanded, porous PTFE fiber made according to the teachings of U.S. Patents 3,953,566 and 4,187,390. Laminated composites comprised of expanded PTFE fibers have higher flexural strength, higher tensile strength and a lower shrinkage after processing than laminates of drawn, sintered PTFE fiber.

It has also been found that very thin laminated composites can be prepared by calendering the fluorocarbon fabrics to a reduced thickness. Fab-

ric woven from expanded PTFE fibers can be calendered to thicknesses of less than .0025 inch (.0064 cms) and two sheets of epoxy pre-preg from this fabric can yield a thin laminate with a dielectric core of .005 inch (.0127 cms) thickness. Dielectric cores of this thickness are very desirable for innerlayers and flexible circuits.

If it is desirable to increase the laminated composites tensile strength, flexural strength, shrinkage after processing, or thermal coefficient of expansion, then other fibers than fluorocarbon fibers can be included in the composite structure. For example, fiberglass and treated fluorocarbon fibers can be woven into the same fabric and used as reinforcement for the thermosetting resins. Laminated composites composed of epoxy resin and expanded PTFE fabric containing less than 10 wt. % fiberglass have exhibited a dielectric constant of 2.8 at 1 megahertz while significantly improving the laminate's flexural strength, tensile strength, shrinkage after processing and thermal coefficient of expansion. A second method of including other fibers than fluorocarbon fibers into the fluorocarbon composite is to interleave sheets of fiberglass pre-preg with sheets of treated fluorocarbon fiber pre-preg. While this method can also yield a low dielectric constant laminated composite, it does not have the same desirable homogeneous structure.

An unexpected additional benefit of the fluorocarbon fiber laminated composites is their high flexibility. A laminated composite .008 inch (.02 cms) thick, for example, of two sheets of expanded PTFE fabric impregnated with epoxy resin, can be bent around a 0.1 inch (0.24 cm) radius mandrel without breaking the PTFE fibers, while fiberglass fibers in an equivalent thickness FR-4 laminate will break when the laminate is bent over an equivalent diameter mandrel). The fluorocarbon fiber laminated composites can, therefore, be excellent dielectrics for flexible printed circuit boards.

When the fluorocarbon fibers are treated with an alkali naphthanate, the surface of the fibers turns dark brown. In applications where this colour is not desirable, the fibers can be bleached to lighter colour using heat or an oxidizing agent such as chlorine bleach. The lightening process must be controlled to insure that a wettable surface remains.

In the process illustrated in Figure 1A, fabric 10 containing at least a portion of polytetrafluoroethylene fibers is fed from a feed roll over guide roll 12 into bath 14 containing the alkali naphthanate treatment solution 16. Pinned guides 13 pierce the fabric and prevent its shrinkage in both the longitudinal and transverse directions during passage through the treatment solution 16. The treated fabric 10 emerges from the bath 16 and passes over guide roll 12 in the direction indicated by the arrow and enters water wash 18 wherein excess treatment solution is washed away. The fabric is then optionally bleached in chamber 19, using, for example, a chlorine bleach solution. The treated fabric then passes between optional

compression rolls 20 wherein it may be reduced in thickness if desired. Liquid resin 22 is applied to the fabric from container 22 which wets the fabric and penetrates into its interstices. The coated fabric is heated in heater 26 to cure the resin to at least the B-stage cured or pre-preg sheet 29, and this sheet is cut into individual pre-preg sheets 30 by cutter 28.

Figure 1B shows an alternative process for treating fibers for use in a fabric to make the pre-preg sheets of the invention. A PTFE fiber 40 is passed around first tension roll 42, over and around guide rolls 44 which guide the fiber through the treatment solution 48 in bath 46. The fiber emerges from the bath and passes around a second tension roll 50, rotating at substantially the same speed as the first tension roll 42, thereby preventing the fiber from shrinkage during treatment. The treated fiber is then formed into a fabric 52 as depicted in Figure 1C to be used in making the pre-preg sheets according to the invention.

Figure 2 shows a stack of the pre-preg sheets 30 of the invention with a metal foil 32, preferably copper, placed above and below the sheets 30. On application of heat and pressure as depicted in Figure 3 the resin in pre-preg sheets 30 is cured to a homogeneous, C-stage cured state to form the composite 34 and the metal foils 32 are firmly bonded to the composite 34.

Figure 4 shows a portion of a woven fabric in which all fibers 40 are porous PTFE fibers, and Figure 5 shows a portion of a fabric in which a portion of the fibers 40 are porous PTFE and a portion are glass fibers 38.

Figure 6 depicts a composite 34 from which a portion of the metal from metal foil 32 has been removed leaving electrical circuitry 60.

Figure 7 shows the composite of Figure 6 sandwiched between two pre-preg sheets 30 and having metal foils 32 above and below the pre-preg sheets 30. Wherever a layer of material in which the resin is in the C-stage state, i.e. layer 34, and wherever an electrically conductive foil or circuit, i.e. 32 or 60, contacts another layer, i.e. layers 30, the other layer is of material in the B-stage state.

Figure 8 shows a composite of this invention 80 obtained by applying heat and pressure to the stack shown in Figure 7. The resin in the centre portion 36 has become homogeneous and fully cured to the C-stage state. The foils 32 are securely bonded to both sides of the composite 36.

The following examples are intended to be illustrative of the invention but will not limit the scope of the claims in any way.

Example I

A fabric was woven using conventional procedures from fibers of expanded polytetrafluoroethylene (PTFE) available commercially as GORE-TEX (Trade Mark) expanded PTFE weaving fibers from W. L. Gore & Associates, Inc., Elkton, MD. The fabric construction had 52 (400 denier) fibers

per inch (20 per cm) in the longitudinal direction and 52 (400 denier) fibers per inch (20 per cm) in the transverse direction. The fabric was cut into six, 6 inch x 6 inch (15 cm x 15 cm) sheets and immersed unrestrained for 30 seconds in an alkali naphthanate solution, available commercially under the trademark TETRA-ETCH (Trade Mark), also available from W. L. Gore & Associates, Inc. Following this treatment, the fabric was washed in warm tap water and rinsed in acetone. The treatment with the TETRA-ETCH (Trade Mark) solution caused the fibers to develop a dark brown colour and resulted in the fabric shrinking approximately 20% in both the longitudinal and transverse directions. The fabric was stretched to nearly its original dimensions by grasping the fabric on its edges and manually stretching the fabric.

A liquid epoxy resin was prepared using the guidelines of Dow Chemical Company product brochure No. 296-396-783 for Dow epoxy resin 521-A80. When liquid epoxy resin was coated on untreated PTFE fabric, the resin beaded up and would not wet or penetrate the interstices between the fibers. Conversely, when the liquid epoxy resin was coated on the treated fabric, it wet the fabric and filled the interstices, between the fibers to form a level, even coating over the fabric surface.

The six epoxy-coated treated fabric sheets were placed one at a time in a convection oven at 160°C., each for 4 minutes. When the sheets were removed from the oven and cooled, the epoxy resin was observed to have completely wetted the fabric and had been converted into a dry, flexible, semi-cured state known as B-stage pre-preg. The average resin pickup for each pre-preg sheet was 5 gms and the average thickness was approximately 0.14 inch (0.36 cm).

The six pre-preg sheets were stacked one upon another and placed between FEP release sheets and stainless steel caul plates to form a lamination package. The package was placed in a Carver (Trade Mark) platen press which had been pre-heated to 175°C., and a pressure of 100 psi (690 kPa) was applied. After three minutes the pressure was increased to 800 psi (5516 kPa) and the package was cured for 30 minutes at 175°C. The heaters were turned off and the package was allowed to cool to room temperature while still under the 800 psi (5516 kPa) pressure. The package was removed from the press and the laminated composite was separated from the FEP release sheets and caul plates.

The laminated composite was fully cured to the C-stage state, was approximately 0.45 inch (1.14 cms) thick and exhibited excellent resin wetting throughout the composite. There was no evidence of air entrapment, blistering, resin voids or delamination between the layers of fabric. Microscopic examination of cross sections of the laminated composite showed a uniform distribution of epoxy resin around the fibers, within the interstices of the fabric and between the layers of fabric.

5

10

15

20

25

30

35

40

45

50

55

60

65

5

Example II

The same conditions and materials of Example I were used, except that the stack of pre-preg sheets was placed between sheets of .0014 inch (.0036 cm) thick copper foil instead of the FEP release sheets. After removing the cooled sample from the platen press, it was observed that the copper foil was intimately and securely bonded to the composite core of C-stage cured epoxy resin and GORE-TEX (Trade Mark) expanded PTFE fibers to form a structure known as a double-sided, copper clad laminate. The total laminate thickness was approximately .045 inch (1.14 cms) and the core thickness was approximately .042 inch (.107 cm). Using a capacitance bridge, the dielectric constant at 1 MHz of the laminate sample was determined to be approximately 2.8. The calculated weight percent fiber in the core was 63% and that of epoxy resin was 37%.

Example III

A double-sided copper clad laminate was prepared as detailed in Example II and fabricated into a double-sided, plated-through-hole circuit board using standard techniques familiar to those skilled in the art. The circuit board was electrically conductive along circuit lines and across the plated-through hole connections.

Example IV

Eight pre-preg sheets were prepared as described in Example I with the exception that the fabric construction had 64 fibers per inch of GORE-TEX (Trade Mark) expanded PTFE fiber in the longitudinal direction and 60 fibers per inch (24 per cm) in the transverse direction. Three sheets of commercially available pre-preg FR-4 made from B-stage epoxy resin reinforced with a 7628 fiberglass fabric (7628 being a recognised style number of fiberglass) were placed in the stack of expanded PTFE pre-preg sheets and copper foil in the following order:

A=.0014 inch (.0036 cm) copper foil.

B=epoxy/fiberglass pre-preg.

C=epoxy/expanded PTFE fiber pre-preg.

No. of sheets	Material
1	A
1	B
4	C
1	B
4	C
1	B
1	A

This package was placed between stainless steel caul plates and processed into a double-sided copper clad laminate using the conditions described in Example II.

The C-stage cured laminate was void free and exhibited excellent adhesion between layers of fabric, copper foil and resin. The dielectric core was .092 inch (.234 cm) thick and was composed

of 15 wt. % fiberglass, 54 wt. % GORE-TEX (Trade Mark) expanded PTFE fibers and 31% C-stage epoxy resin. The dielectric constant of the composite was 2.9 at 1 MHz.

The addition of 15 wt % fiberglass significantly improved the mechanical properties of the composite as shown below:

Core Composition A=55 wt % Epoxy/45 wt. % GORE-TEX (Trade Mark) expanded PTFE fiber.

Core Composition B=15 wt % Fiberglass/31 wt % Epoxy/54 wt % GORE-TEX (Trade Mark) expanded PTFE fiber.

	A	B
Flexural Strength $\times 10^3$ psi ($\times 6.9$ MPa)	12	20
Flexural Modulus $\times 10^3$ psi ($\times 6.9$ MPa)	250	930
Thermal Coefficient of Expansion ppm/ $^{\circ}$ C	52	16

Example V

A fabric was woven using conventional procedures from GORE-TEX (Trade Mark) expanded PTFE fibers and fiberglass fibers. The fabric construction had 64 expanded PTFE fibers per inch (25 per cm) in the longitudinal direction and 60, 150 1/0, fiberglass fibers per inch (24 per cm) in the transverse direction. (150 1/0 means 150 Denier one unplied or single fiberglass fiber per inch (per 2.54 cms) in the transverse direction. Ten, 5 inch $\times$ 6 inch (12.7 cm $\times$ 15.2 cm) sheets of the fabric were treated with TETRA-ETCH (Trade Mark) and converted into an epoxy B-stage pre-preg using the procedure described in Example I.

A double-sided copper clad laminate was prepared from the pre-preg sheets using the procedure described in Example II, with the exception that the pre-preg sheets were alternately stacked at right angles to one another so that fiberglass fibers were running in both the x and y axes of the finished, cured laminate.

The laminate had a core thickness, of .075 inch (.19 cm) and was composed of 36 wt. % epoxy, 40 wt % expanded PTFE fiber, and 24 wt % fiberglass. The dielectric constant at 1 MHz was 3.4 and the mechanical properties also improved to the same degree as the fiberglass-containing sample of Example IV, as demonstrated by the samples thermal coefficient of expansion of 14 ppm/ $^{\circ}$ C.

Example VI

A fabric was woven using conventional procedures from 400 denier drawn, solid PTFE fiber, available commercially from E. I. DuPont under product designation Teflon (Trade Mark) TFE-Fluorocarbon Fiber. These fibers are multifilament fibers and are not expanded. The fabric construction had 60 fibers per inch (24 per cm) in the longitudinal direction and 64 fibers per inch (25 per cm) in the transverse direction.

Liquid epoxy resin would not wet the untreated PTFE fabric, but when the fabric was treated with TETRA-ETCH (Trade Mark) it was able to be

processed by the methods described in Examples I and II. The DuPont PTFE fabric exhibited the same 20% shrinkage as the GORE-TEX (Trade Mark) expanded PTFE fiber fabric, but likewise could be stretched back to its near original size.

A double-sided copper clad laminate was fabricated using the methods described in Examples I and II. The laminate core was .088 inch (.224 cm) thick, had a dielectric constant at 1 MHz of 2.6 and was composed of 32 wt. % epoxy resin and 68 wt. % DuPont fiber. The mechanical properties were slightly lower than laminate fabricated from the GORE-TEX (Trade mark) expanded PTFE fiber.

Core Composition A=32 wt. % Epoxy/68 wt. % DuPont PTFE Fiber.

Core Composition B=55 wt. % Epoxy/45 Wt. % GORE-TEX (Trade Mark) expanded PTFE fiber.

	A	B
Flexural Strength $\times 10^3$ psi ($\times 6.9$ MPa)	7	12
Flexural Modulus $\times 10^3$ psi ($\times 6.9$ MPa)	250	250
Thermal Coefficient of Expansion ppm/ $^{\circ}$ C	58	52

Example VII

Four hundred denier fibers of GORE-TEX (Trade Mark) expanded PTFE were treated with TETRA-ETCH (Trade Mark) naphthanate solution before weaving into a fabric as opposed to treating the fabric after it was woven as described in Example I. The fiber was treated and washed in warm water while under longitudinal tension so as to prevent fiber shrinkage resulting in a more stable fabric construction. A fabric was woven from the fiber using a hand loom to minimize abrasion of the fibers. The fabric was then coated with liquid epoxy resin and converted into a pre-preg by the methods described in Example I. The pre-preg was well wetted by the epoxy resin and showed no evidence of voids or poor adhesion.

Example VIII

A fabric was woven from 100 denier GORE-TEX (Trade Mark) expanded PTFE fibers using conventional procedures. The fabric had 80 fibers per inch (31 per cm) in both the longitudinal and transverse directions. The fabric was treated with TETRA-ETCH (Trade Mark) alkali naphthante solution and stretched as described in Example I. The fabric at this point was approximately .005 inch (.013 cm) thick. The fabric was passed between stainless steel calendering rolls set at approximately a .002 inch (.005 cm) gap. After two passes through the calendering rolls, the fabric thickness was reduced to .0026 inch (.0066 cm) thick.

The fabric was converted into a pre-preg and double-sided copper clad laminate using the methods described in Examples I and II. The laminate containing the sheets of calendered fabric had a core thickness of .005 inch (.013 cm), which is a very desirable thickness for laminate

used for multiple layer printed circuit boards. The dielectric constant at 1 was 2.8.

Example IX

A fabric of 400 denier GORE-TEX (Trade Mark) expanded PTFE fiber was woven and treated with TETRA-ETCH (Trade Mark) alkali naphthanate as described in Example I. The fabric was bleached to nearly its original white colour by immersing the fabric for 5 minutes in Chlorox (Trade Mark) chlorine bleach at 175 $^{\circ}$ F—200 $^{\circ}$ F (79—93 $^{\circ}$ C). The bleached fabric was then converted into an epoxy pre-preg and unclad, cured laminate using the methods described in Example I.

The bleached fabric was wet by the liquid epoxy resin and the cured laminate was free of voids. Adhesion between the bleached fibers and cured epoxy resin was excellent.

Example X

A double-sided copper clad laminate was made using the methods described in Examples I and II except that two sheets of fabric woven from 100 denier GORE-TEX (Trade mark) expanded PTFE fibers were utilized. The core thickness was .008 inch (.02 cm) and the dielectric constant at 1 MHz was 2.6.

The laminate was tested for flexibility by folding it back on itself with a 0.1 inch (0.25 cm) radius. While the copper foil cracked at the bend, the dielectric core maintained its integrity and did not crack or separate with up to 10 flexures. A double-sided copper clad commercial grade epoxy/fiberglass laminate, with a .006 inch (.015 cm) thick core, was also bent with a 0.1 inch (0.25 cm) radius. The copper foil on the outside radius of the laminate cracked, but the epoxy/fiberglass core also cracked and after 2 flexures broke and separated into two parts.

Example XI

Double-sided copper clad laminate and pre-preg were produced using the methods and conditions described in Example VIII. Three of the copper clad laminates were fabricated into double-sided innerlayer printed circuits using standard procedures. The three innerlayer printed circuit were interleaved with two sheets of pre-preg between each two innerlayer circuits for a total of four sheets of pre-preg in the stack. The stack was laminated under heat and pressure, imaged and plated using conventional procedures for fabricating multilayer printed circuit boards.

The completed multilayer printed circuit board was free of voids and exhibited good intralayer adhesion.

Example XII

A fabric was woven using the materials and procedures described in Example I. The fabric was cut into 8 inch $\times$ 8 inch (20 cm $\times$ 20 cm) squares and placed over a 6 inch $\times$ 6 inch (15 cm $\times$ 15 cm) pin frame (tenter frame). The pin frame was a square, window frame type structure

which had 1/2 inch (1.27 cm) long pins placed on 1 inch (2.54 cm) centers around the perimeter of the frame. The fabric was pressed onto the pins on one edge of the frame and stretched under moderate tension to the pins on the other side of the frame. The other two sides of the fabric square were likewise stretched and placed on the pins on the remaining two sides of the pin frame. The fabric was thus restrained under moderate tension on all four sides.

The pin frame holding the fabric was immersed in an alkali naphthanate solution for 30 seconds, washed in warm water and rinsed in acetone. The fabric developed the characteristically dark brown colour, indicating effective treatment, but it did not shrink appreciably after being removed from the pin frame. The fabric was coated with epoxy resin and processed as described in Example I to a pre-preg and then into a laminated composite. The epoxy wetted the fabric acceptably and the fully cured laminated composite performed equivalently to the laminated composite of Example I.

Claims

1. A dielectric material comprising a fabric having fibers and interstices between said fibers, in which at least a portion of the fibers in said fabric are fluorocarbon fibers which have been treated to make the fluorocarbon fibers wettable by an uncured thermosetting resin, the fabric being impregnated within said interstices between said fibers with a thermosetting resin cured to at least the semi-cured, B-stage state, the dielectric constant of said dielectric material being less than 3.5.

2. A dielectric material according to claim 1 characterised in that it has a dielectric constant less than 3.0.

3. A dielectric material according to claim 1 or claim 2 characterised in that the thermosetting resin is cured to the fully-cured, C-stage state.

4. A dielectric material according to claim 3 characterised by an electrically conductive foil bonded to at least one surface of the impregnated fabric.

5. A dielectric material according to claim 3 or claim 4 characterised in that the impregnated fabric is in sheet form having an electrically conductive foil bonded to one side thereof.

6. A dielectric material according to claim 5 characterised in that the impregnated fabric has electrically conductive foil bonded to both sides thereof.

7. A dielectric material according to any one of claims 4 to 6 characterised in that said foil is copper foil.

8. A dielectric material according to claim 3 in the form of a laminated composite structure characterised by it comprising two or more sheets of the impregnated fabric and having an electrically conductive foil bonded to at least one side of at least one of said sheets.

9. A dielectric material according to claim 1 in the form of a laminated composite structure

characterised by one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the fully-cured, C-stage state, and one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the semi-cured, B-stage state, wherein, wherever a layer of material in said C-stage state contacts another layer, said other layer is of material in said B-stage state.

10. A dielectric material according to claim 1 in the form of a laminated composite structure characterised by one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the fully-cured, C-stage state, and having an electrically conductive foil bonded to at least one side of at least one of said sheets, and one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the semi-cured, B-stage state, wherein, wherever a layer of material in said C-stage state contacts another layer, and wherever an electrically conductive foil contacts another layer, said other layer is of material in said B-stage state.

11. A dielectric material according to any one of claims 8 to 10 characterised by at least one additional layer which is a layer of epoxy/fiberglass, fluorocarbon/fiberglass, polyimide/fiberglass, epoxy/polyaramide fiber, epoxy/quartz fiber or polyimide/quartz fiber composites.

12. A dielectric material according to any preceding claim characterised in that said thermosetting resin is an epoxy, polyimide, polyamide, polyester, phenolic or acrylic thermosetting resin.

13. A dielectric material according to any preceding claim characterised in that all said fibers in said fabric other than fluorocarbon fibers are fiberglass fibers or polyaramide fibers or quartz fibers.

14. A dielectric material according to any preceding claim characterised in that said fabric is a woven fabric or a non-woven felt or mat.

15. A dielectric material according to any preceding claim characterised in that said fluorocarbon fibers are drawn, non-porous, sintered PTFE fibers, or expanded, porous PTFE fibers, and said fluorocarbon fibers contain a dielectric insulator material or other material as a filler.

16. A dielectric material according to claim 15 characterised in that said filler is electrically conductive or semi-conductive, and is a metal, a metal oxide, carbon, ceramic or glass.

17. A process for making the dielectric material of claim 1 characterised by:

(a) treating fluorocarbon fibers to render them wettable by an uncured thermosetting resin, the fibers being held under longitudinal tension during such treatment, thereby preventing longitudinal shrinkage of said fibers during treatment.

(b) weaving said fabric containing at least a portion of said treated fluorocarbon fibers,

(c) impregnating said fabric with an uncured thermosetting resin, and

(d) heating and drying said resin-impregnated fabric to cure said resin to at least the semi-cured, B-stage state.

which had 1/2 inch (1.27 cm) long pins placed on 1 inch (2.54 cm) centers around the perimeter of the frame. The fabric was pressed onto the pins on one edge of the frame and stretched under moderate tension to the pins on the other side of the frame. The other two sides of the fabric square were likewise stretched and placed on the pins on the remaining two sides of the pin frame. The fabric was thus restrained under moderate tension on all four sides.

The pin frame holding the fabric was immersed in an alkali naphthanate solution for 30 seconds, washed in warm water and rinsed in acetone. The fabric developed the characteristically dark brown colour, indicating effective treatment, but it did not shrink appreciably after being removed from the pin frame. The fabric was coated with epoxy resin and processed as described in Example I to a pre-preg and then into a laminated composite. The epoxy wetted the fabric acceptably and the fully cured laminated composite performed equivalently to the laminated composite of Example I.

Claims

1. A dielectric material comprising a fabric having fibers and interstices between said fibers, in which at least a portion of the fibers in said fabric are fluorocarbon fibers which have been treated to make the fluorocarbon fibers wettable by an uncured thermosetting resin, the fabric being impregnated within said interstices between said fibers with a thermosetting resin cured to at least the semi-cured, B-stage state, the dielectric constant of said dielectric material being less than 3.5.

2. A dielectric material according to claim 1 characterised in that it has a dielectric constant less than 3.0.

3. A dielectric material according to claim 1 or claim 2 characterised in that the thermosetting resin is cured to the fully-cured, C-stage state.

4. A dielectric material according to claim 3 characterised by an electrically conductive foil bonded to at least one surface of the impregnated fabric.

5. A dielectric material according to claim 3 or claim 4 characterised in that the impregnated fabric is in sheet form having an electrically conductive foil bonded to one side thereof.

6. A dielectric material according to claim 5 characterised in that the impregnated fabric has electrically conductive foil bonded to both sides thereof.

7. A dielectric material according to any one of claims 4 to 6 characterised in that said foil is copper foil.

8. A dielectric material according to claim 3 in the form of a laminated composite structure characterised by it comprising two or more sheets of the impregnated fabric and having an electrically conductive foil bonded to at least one side of at least one of said sheets.

9. A dielectric material according to claim 1 in the form of a laminated composite structure

characterised by one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the fully-cured, C-stage state, and one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the semi-cured, B-stage state, wherein, wherever a layer of material in said C-stage state contacts another layer, said other layer is of material in said B-stage state.

10. A dielectric material according to claim 1 in the form of a laminated composite structure characterised by one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the fully-cured, C-stage state, and having an electrically conductive foil bonded to at least one side of at least one of said sheets, and one or more sheets of the impregnated fabric in which the thermosetting resin is cured to the semi-cured, B-stage state, wherein, wherever a layer of material in said C-stage state contacts another layer, and wherever an electrically conductive foil contacts another layer, said other layer is of material in said B-stage state.

11. A dielectric material according to any one of claims 8 to 10 characterised by at least one additional layer which is a layer of epoxy/fiberglass, fluorocarbon/fiberglass, polyimide/fiberglass, epoxy/polyaramide fiber, epoxy/quartz fiber or polyimide/quartz fiber composites.

12. A dielectric material according to any preceding claim characterised in that said thermosetting resin is an epoxy, polyimide, polyamide, polyester, phenolic or acrylic thermosetting resin.

13. A dielectric material according to any preceding claim characterised in that all said fibers in said fabric other than fluorocarbon fibers are fiberglass fibers or polyaramide fibers or quartz fibers.

14. A dielectric material according to any preceding claim characterised in that said fabric is a woven fabric or a non-woven felt or mat.

15. A dielectric material according to any preceding claim characterised in that said fluorocarbon fibers are drawn, non-porous, sintered PTFE fibers, or expanded, porous PTFE fibers, and said fluorocarbon fibers contain a dielectric insulator material or other material as a filler.

16. A dielectric material according to claim 15 characterised in that said filler is electrically conductive or semi-conductive, and is a metal, a metal oxide, carbon, ceramic or glass.

17. A process for making the dielectric material of claim 1 characterised by:

(a) treating fluorocarbon fibers to render them wettable by an uncured thermosetting resin, the fibers being held under longitudinal tension during such treatment, thereby preventing longitudinal shrinkage of said fibers during treatment.

(b) weaving said fabric containing at least a portion of said treated fluorocarbon fibers,

(c) impregnating said fabric with an uncured thermosetting resin, and

(d) heating and drying said resin-impregnated fabric to cure said resin to at least the semi-cured, B-stage state.



18. A process for making the dielectric material of claim 1, characterised by:

(a) treating a fabric containing at least a portion of fluorocarbon fibers to render said fluorocarbon fibers wettable by an uncured thermosetting resin,

(b) impregnating said fabric with an uncured thermosetting resin, and

(c) heating and drying said resin-impregnated fabric to cure said resin to at least the semi-cured, B-stage state.

19. A process according to claim 17 or claim 18 characterised by the step of calendering said fabric to reduce its thickness.

20. A process according to claim 17 or claim 18 characterised in that said treating includes applying an alkali naphthanate solution to said fluorocarbon fibers or fabric.

21. A process according to claim 20 characterised by napping the fluorocarbon fibers to improve wettability and adhesion between said fibers and resin.

22. A process according to claim 17 or claim 18 characterised in that said fibers or fabric are bleached subsequent to treating them to make them wettable.

23. A process according to claim 22 characterised by the use of an oxidizing agent to bleach the fibers or fabric.

24. A process according to claim 23 characterised in that the fibers or fabric are bleached by heating to a temperature in the range of about 500°F to about 675°F (260°C to 357°C).

25. A process according to claim 18 characterised in that said fabric is held in longitudinal and transverse tension during said treatment, thereby preventing shrinkage of said fabric in the longitudinal and transverse directions during treatment.

26. A process according to claim 18 characterised in that said fabric is unrestrained during said treatment and is allowed to shrink, following which the fabric is stretched to approximately its original dimensions prior to said treatment.

Patentansprüche

1. Dielektrisches Material, welches ein Textilmaterial enthält, welches Fasern und Zwischenräume zwischen diesen Fasern aufweist, und in welchem mindestens ein Teil der Fasern des Textilmaterials Fluorkohlenstofffasern sind, welche behandelt worden sind, um die Fluorkohlenstofffasern durch ein ungehärtetes thermohärtbares Harz benetzbar zu machen, welches Textilmaterial in den Zwischenräumen zwischen den Fasern mit einem thermoerhärtenden Harz, welches zumindestens bis zum halbausgehärteten, B-Stufen, Zustand gehärtet ist, imprägniert ist, wobei die Dielektrizitätskonstante dieses dielektrischen Materials kleiner als 3,5 ist.

2. Dielektrisches Material nach Anspruch 1, dadurch gekennzeichnet, daß es eine Dielektrizitätskonstante von weniger als 3,0 hat.

3. Dielektrisches Material nach Anspruch 1 oder

2, dadurch gekennzeichnet, daß das thermoerhärtende Harz bis zum voll ausgehärteten, C-Stufen, Zustand, gehärtet ist.

4. Dielektrisches Material nach Anspruch 3, dadurch gekennzeichnet, daß eine elektrisch leitfähige Folie mit mindestens einer Oberfläche des imprägnierten Textilmaterials verbunden ist.

5. Dielektrisches Material nach Anspruch 3 oder 4, dadurch gekennzeichnet, daß das imprägnierte Textilmaterial Blatt-Form hat und eine elektrisch leitfähige Folie aufweist, welche mit einer Seite desselben verbunden ist.

6. Dielektrisches Material nach Anspruch 5, dadurch gekennzeichnet, daß das imprägnierte Textilmaterial mit beiden Seiten verbundene elektrisch leitfähige Folien aufweist.

7. Dielektrisches Material nach einem der Ansprüche 4 bis 6, dadurch gekennzeichnet, daß die genannte Folie eine Kupferfolie ist.

8. Dielektrisches Material nach Anspruch 3 in Form einer laminierten zusammengesetzten Struktur, dadurch gekennzeichnet, daß es zwei oder mehr Blätter des imprägnierten Textilmaterials aufweist und mit einer elektrisch leitfähigen Folie versehen ist, welche mit mindestens einer Seite von mindestens einem der genannten Blätter verbunden ist.

9. Dielektrisches Material nach Anspruch 1, in Form einer laminierten zusammengesetzten Struktur, gekennzeichnet durch ein oder mehrere Blätter des imprägnierten Textilmaterials, in denen das thermoerhärtende Harz bis zum voll ausgehärteten, C-Stufen, Zustand gehärtet ist, und eine oder mehrere Blätter des imprägnierten Textilmaterials, in denen das thermoerhärtende Harz zum halb-ausgehärteten, B-Stufen, Zustand gehärtet ist, wobei überall dort, wo eine Schicht eines im C-Stufenzustand befindlichen Materials eine andere Schicht berührt, diese andere Schicht aus einem Material, welches sich im B-Stufenzustand befindet, besteht.

10. Dielektrisches Material nach Anspruch 1, in Form einer laminierten zusammengesetzten Struktur, gekennzeichnet durch ein oder mehrere Blätter des imprägnierten Textilmaterials, in dem das thermoerhärtende Harz zum voll ausgehärteten, C-Stufen, Zustand ausgehärtet ist und mit einer elektrisch leitfähigen Folie versehen ist, welche mit mindestens einer Seite von mindestens einem dieser Blätter verbunden ist, und durch eine oder mehrere Blätter des imprägnierten Textilmaterials, in denen das thermoerhärtende Harz bis zum halb-ausgehärteten, B-Stufen, Zustand gehärtet ist, wobei überall dort, wo eine Schicht des im C-Stufen-Zustand befindlichen Materials eine andere Schicht berührt, und wo immer eine elektrisch leitfähige Folie eine andere Schicht berührt, diese andere Schicht aus einem im B-Stufen-Zustand befindlichen Material besteht.

11. Dielektrisches Material nach einem der Ansprüche 8 bis 10, gekennzeichnet, durch mindestens eine zusätzliche Schicht, welche eine Schicht aus Epoxy/Glasfaser-, Fluorkohlenstoff/Glasfaser-, Polyimide/Glasfaser-, Epoxy/Polyara-



midfaser-, Epoxy/Quarzfaser- oder Polyimid/Quarzfaser Zusammensetzung ist.

12. Dielektrisches Material nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß das thermoerhärtende Harz eine thermoerhärtendes Epoxy-, Polimid-, Polyamid-, Polyester-, Phenol-, oder Acrylharz ist.

13. Dielektrisches Material nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß alle Fasern des Textilmaterials, welche keine Fluorkohlenstofffasern sind, Faserglasfasern oder Polyaramidfasern oder Quarzfasern sind.

14. Dielektrisches Material nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß das Textilmaterial ein nichtgewebter Filz oder Matte ist.

15. Dielektrisches Material nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß die Fluorkohlenstofffasern gereckte, nicht poröse, gesinterte PTFE-Fasern oder expandierte poröse PTFE-Fasern sind und daß diese Fluorkohlenstofffasern ein dielektrisches Isoliermaterial oder ein anderes Material als Füller enthalten.

16. Dielektrisches Material nach Anspruch 15, dadurch gekennzeichnet, daß der Füller elektrisch leitfähig oder halbleitend ist und ein Metall, ein Metalloxid, Kohlenstoff, Keramik oder Glas ist.

17. Verfahren zur Herstellung des dielektrischen Materials nach Anspruch 1, dadurch gekennzeichnet, daß:

(a) Fluorkohlenstofffasern einer Behandlung unterzogen werden, um sie durch ein ungehärtetes thermoerhärtbares Harz benetzbar zu machen, wobei die Fasern während dieser Behandlung unter Längsspannung gehalten werden, um so ein Längsschrumpfen dieser Fasern während der Behandlung zu verhüten,

(b) das Textilmaterial, welches mindestens einen Teil der genannten behandelten Fluorkohlenstofffasern enthält, gewebt wird,

(c) das Textilmaterial mit einem ungehärteten thermoerhärtenden Harz imprägniert wird, und

(d) das harzprägnierte Textilmaterial erhitzt und getrocknet wird, um das Harz mindestens bis zum halbausgehärteten, B-Stufen, Zustand zu härten.

18. Zur Herstellung des dielektrischen Materials nach Anspruch 1, dadurch gekennzeichnet, daß:

(a) ein Textilmaterial, welches zumindestens einen Anteil von Fluorkohlenstofffasern enthält, behandelt wird, um die Fluorkohlenstofffasern durch eine ungehärtetes thermoerhärtbares Harz benetzbar zu machen,

(b) dieses Textilmaterial mit einem ungehärteten thermoerhärtbaren Harz imprägniert wird, und

(c) das harzprägnierte Textilmaterial erhitzt und getrocknet wird, um das Harz bis mindestens zum halbausgehärteten, B-Stufen, Zustand zu härten.

19. Verfahren nach Anspruch 17 oder 18, dadurch gekennzeichnet, daß das Textilmaterial kalandert wird, um seine Dicke zu vermindern.

20. Verfahren nach Anspruch 17 oder 18, dadurch gekennzeichnet, daß die genannte

Behandlung die Anwendung einer Alkali-Naphthenat-Lösung auf die Fluorkohlenstofffasern oder das Textilmaterial einschließt.

21. Verfahren nach Anspruch 20, dadurch gekennzeichnet, daß die Fluorkohlenstofffasern aufgeraut werden um die Benetzbarkeit und die Adhäsion zwischen diesen Fasern und dem Harz zu verbessern.

22. Verfahren nach Anspruch 17 oder 18, dadurch gekennzeichnet, daß die Fasern oder das Textilmaterial auf die die Benetzbarkeit herbeiführende Behandlung folgend gebleicht werden.

23. Verfahren nach Anspruch 22, dadurch gekennzeichnet, daß zum Bleichen der Fasern oder des Textilmaterials ein Oxidationsmittel verwendet wird.

24. Verfahren nach Anspruch 23, dadurch gekennzeichnet, daß die Fasern oder das Textilmaterial unter Erhitzen auf eine Temperatur im Bereich von ungefähr 500°F bis ungefähr 675°F (260°C bis 357°C) gebleicht werden.

25. Verfahren nach Anspruch 18, dadurch gekennzeichnet, daß das Textilmaterial in Längsrichtung und in Querrichtung während der Behandlung unter Spannung gehalten wird und so ein Schrumpfen des Textilmaterials in der Längsrichtung und in der Querrichtung während der Behandlung verhindert wird.

26. Verfahren nach Anspruch 18, dadurch gekennzeichnet, daß das Textilmaterial während der Behandlung nicht eingespannt wird und schrumpfen gelassen wird, und daß das Textilmaterial nachfolgend auf annähernd seine ursprünglichen Abmessungen, welche es vor der Behandlung hatte, gestreckt wird.

Revendications

1. Matière diélectrique comprenant une toile comportant des fibres et des interstices entre ces fibres, au moins une partie des fibres de cette toile étant formées par des fibres fluorocarbonées qui ont été traitées pour les rendre mouillables, par une résine thermodurcissable non durcie, cette toile était imprégnée dans les interstices susdits compris entre les fibres par une résine thermodurcissable durcie au moins jusqu'à l'état B semi-durci, la constante diélectrique de cette matière diélectrique étant inférieure à 3,5.

2. Matière diélectrique suivant la revendication 1, caractérisée en ce qu'elle a une constante diélectrique inférieure à 3,0.

3. Matière diélectrique suivant la revendication 1 ou la revendication 2, caractérisée en ce que la résine thermodurcissable est durcie à l'état C totalement durci.

4. Matière diélectrique suivant la revendication 3, caractérisée en ce qu'elle comporte une feuille conductrice de l'électricité liée à au moins une surface de la toile imprégnée.

5. Matière diélectrique suivant la revendication 3 ou la revendication 4, caractérisée en ce que la toile imprégnée est sous forme d'une nappe comportant une feuille conductrice de l'électricité liée suivant l'un de ses côtés.



6. Matière diélectrique suivant la revendication 5, caractérisée en ce que la toile imprégnée comporte une feuille conductrice de l'électricité liée suivant ses deux côtés.

7. Matière diélectrique suivant l'une quelconque des revendications 4 à 6, caractérisée en ce que la feuille susdite est une feuille de cuivre.

8. Matière diélectrique suivant la revendication 3 sous forme d'une structure composite stratifiée, caractérisée en ce qu'elle comprend deux feuilles ou plus de la toile imprégnée et comporte une feuille conductrice de l'électricité liée à au moins un côté d'au moins l'une de ces feuilles.

9. Matière diélectrique suivant la revendication 1 sous la forme d'une structure composite stratifiée, caractérisée en ce qu'elle comporte une ou plusieurs feuilles de la toile imprégnée, dans lesquelles la résine thermoscurissable est durcie à l'état C pleinement durci, et une ou plusieurs feuilles de la toile imprégnée, dans lesquelles la résine thermoscurissable est durcie à l'état B semi-durci, et dans laquelle, lorsqu'une couche de matière à l'état C est en contact avec une autre couche, cette autre couche est faite de matière à l'état B.

10. Matière diélectrique suivant la revendication 1 sous la forme d'une structure composite stratifiée, caractérisée en ce qu'elle comporte une ou plusieurs feuilles de la toile imprégnée, dans lesquelles la résine thermoscurissable est durcie à l'état C pleinement durci, avec une feuille conductrice de l'électricité liée à au moins une face d'au moins l'une des feuilles susdites, et une ou plusieurs feuilles de la toile imprégnée, dans lesquelles la résine thermoscurissable est durcie à l'état B semi-durci, et dans laquelle, lorsqu'une couche de matière à l'état C entre en contact avec une autre couche et lorsqu'une feuille conductrice de l'électricité entre en contact avec une autre couche, cette autre couche est faite d'une matière à l'état B.

11. Matière diélectrique suivant l'une quelconque des revendications 8 à 10, caractérisée en ce qu'elle comporte au moins une couche supplémentaire qui est formée par une couche de composites époxyde/fibres de verre, fluorocarbone/fibres de verre, polyimide/fibres de verre, époxyde/fibres de polyamide, époxyde/fibres de quartz ou polyimide/fibres de quartz.

12. Matière diélectrique suivant l'une quelconque des revendications précédentes, caractérisée en ce que la résine thermoscurissable est une résine thermoscurissable époxyde, polyimide, polyamide, polyester, phénolique ou acrylique.

13. Matière diélectrique suivant l'une quelconque des revendications précédentes, caractérisée en ce que toutes les fibres susdites de la toile, autres que des fibres fluorocarbonées, sont des fibres de verre ou des fibres de polyaramide ou encore des fibres de quartz.

14. Matière diélectrique suivant l'une quelconque des revendications précédentes, caractérisée en ce que la toile est une toile tissée ou une matée ou feutre non tissé.

15. Matière diélectrique suivant l'une quelcon-

que des revendications précédentes, caractérisée en ce que les fibres fluorocarbonées sont des fibres de PTFE étirées, non poreuses, frittées, ou des fibres de PTFE poreuses dilatées, et ces fibres fluorocarbonées contiennent une matière isolante diélectrique ou autre matière à titre de charge.

16. Matière diélectrique suivant la revendication 15, caractérisée en ce que la charge est une charge conductrice ou semi-conductrice de l'électricité et est constituée par un métal, un oxyde de métal, du carbone, de la céramique ou du verre.

17. Procédé de fabrication de la matière diélectrique suivant la revendication 1, caractérisé en ce que:

(a) on traite des fibres fluorocarbonées pour les rendre mouillables par une résine thermoscurissable non durcie, ces fibres étant maintenues sous tension longitudinale durant ce traitement, en empêchant ainsi un rétrécissement longitudinal des fibres durant le traitement,

(b) on tisse la toile contenant au moins une certaine proportion des fibres fluorocarbonées traitées susdites,

(c) on imprègne cette toile par une résine thermoscurissable non durcie, et

(d) on chauffe et on sèche cette toile imprégnée de résine pour durcir ou cuire la résine au moins jusqu'à l'état B semi-durci.

18. Procédé de fabrication de la matière diélectrique suivant la revendication 1, caractérisé en ce que:

(a) on traite une toile comportant au moins une certaine proportion de fibres fluorocarbonées pour rendre celles-ci mouillables par une résine thermoscurissable non durcie,

(b) on imprègne cette toile par une résine thermoscurissable non durcie, et

(c) on chauffe et on sèche cette toile imprégnée de résine pour durcir celle-ci au moins jusqu'à l'état B semi-durci.

19. Procédé suivant la revendication 17 ou la revendication 18, caractérisé en ce qu'il comporte la phase de calandrage de cette toile pour réduire son épaisseur.

20. Procédé suivant la revendication 17 ou la revendication 18, caractérisé en ce que le traitement susdit comprend l'application d'une solution de naphatanate alcalin aux fibres fluorocarbonées ou à la toile comportant celles-ci.

21. Procédé suivant la revendication 20, caractérisé par le lainage des fibres fluorocarbonées pour améliorer la mouillabilité et l'adhérence entre les fibres susdites et la résine.

22. Procédé suivant la revendication 17 ou la revendication 18, caractérisé en ce que les fibres ou la toile sont blanchies après leur traitement pour les rendre mouillables.

23. Procédé suivant la revendication 22, caractérisé par l'utilisation d'un agent oxydant pour blanchir les fibres ou la toile.

24. Procédé suivant la revendication 23, caractérisé en ce que les fibres ou la toile sont blanchies par chauffage à une température de l'ordre d'environ 260 à environ 357°C (500 à 675°F).



25. Procédé suivant la revendication 18, caractérisé en ce que la toile est maintenue sous tension longitudinale et sous tension transversale durant le traitement susdit, pour empêcher ainsi un rétrécissement de cette toile dans la direction longitudinale et dans la direction transversale durant le traitement.

5

26. Procédé suivant la revendication 18, caractérisé en ce que la toile est laissée libre durant le traitement susdit et peut rétrécir, cette toile étant ensuite étirée à peu près jusqu'à ses dimensions initiales après le traitement précité.

10

15

20

25

30

35

40

45

50

55

60

65

12



* C L M S *