

ABSTRACT

Provided are a hollow sealing resin sheet which makes it possible to produce a hollow package with a high yield even when a gap in its hollow structure has a width of about 100 μm ; and a production method for a hollow package. The hollow sealing resin sheet of the present invention contains an inorganic filler in a content of 70 to 90% by volume both inclusive, wherein: in the particle diameter distribution of the inorganic filler that is measured by a laser diffraction scattering method, at least one frequency distribution peak is present in the particle diameter range of 1 to 10 μm both inclusive, and further at least one frequency distribution peak is present in the particle diameter range of more than 10 μm and not more than 100 μm ; and the inorganic filler has a BET specific surface area of 2 to 5 m^2/g both inclusive.