

DESCRIPTION

TITLE OF INVENTION

5 SPUTTERING TARGET AND PROCESS FOR PRODUCTION THEREOF

TECHNICAL FIELD

[0001]

 The present invention relates to a sputtering target and a
10 process for production thereof. More particularly, the present
invention relates to a sputtering target with which it is possible
to form a magnetic thin film having a high coercive force and to
a process for production thereof. Hereinafter, the sputtering
target may be referred to simply as a "target".

15

BACKGROUND ART

[0002]

 A magnetic disk in a hard disk drive utilizes a magnetic thin
film having a CoPtCr-oxide-based granular structure as a magnetic
20 recording film that records information signals (for example, see
Non-Patent Literature 1). In order to further improve the recording
density of this magnetic thin film, there is a need to micronize
magnetic crystal grains contained in the magnetic recording layer
(magnetic thin film).

25 [0003]

However, the progress of micronization of magnetic crystal grains has resulted in occurrence of the so-called thermal fluctuation phenomenon, in which the superparamagnetic phenomenon impairs the thermal stability of recorded signals and leads to loss of the recorded signals. This thermal fluctuation phenomenon has contributed a major obstacle to increasing the recording density of magnetic disks.

[0004]

In order to surmount this obstacle, the magnetic energy of each magnetic crystal grain needs to be increased such that the magnetic energy exceeds the thermal energy. The magnetic energy of each magnetic crystal grain is obtained by $v \times K_u$, which is a product of the volume v of the magnetic crystal grain and the magnetocrystalline anisotropy constant K_u . Therefore, the magnetocrystalline anisotropy constant K_u of the magnetic crystal grain needs to be increased in order to increase the magnetic energy (for example, see Non-Patent Literature 2).

[0005]

Current perpendicular magnetic recording films have a granular structure composed of columnar CoPtCr crystal grains and crystal grain boundaries formed of an oxide that surrounds the columnar CoPtCr crystal grains. In order to increase the magnetocrystalline anisotropy constant K_u of the CoPtCr-oxide film having this granular structure, an attempt to perform sputtering with the substrate temperature elevated has been made. Sputtering with the substrate

temperature elevated is intended to promote diffusion of metal atoms (Co atom, Pt atom, Cr atom) during film deposition and thus to obtain favorable magnetic crystal grains.

[0006]

5 However, when the CoPtCr-oxide film is formed by performing sputtering with the substrate temperature elevated, the CoPtCr magnetic crystal grains grow not in a columnar shape but in spherical shape, which generates a phenomenon in which the magnetic crystal grains have a low magnetic anisotropy and the obtained CoPtCr-oxide
10 film has a reduced magnetocrystalline anisotropy constant K_u (see Non-Patent Literature 3).

[0007]

 Therefore, the inventors of the present invention have attempted to improve the magnetocrystalline anisotropy constant
15 K_u by performing annealing after forming a CoPtCr-oxide film (at room temperature) without raising the temperature of the substrate. However, annealing has increased the diameter of the lower portions (portions near the substrate) of columnar CoPtCr magnetic crystal grains and has caused magnetic coupling in the lower portions of
20 the CoPtCr magnetic crystal grains. This has increased the interaction between the grains and has undesirably reduced the coercive force H_c .

CITATION LIST

25 Non-Patent Literature

[0008]

Non-Patent Literature 1: T. Oikawa et al., IEEE TRANSACTIONS
ON MAGNETICS, Sep 2002, VOL.38, NO.5, p.1976-1978

Non-Patent Literature 2: S. N. Piramanayagam, JOURNAL OF
5 APPLIED PHYSICS, 2007, 102, 011301

Non-Patent Literature 3: Shintaro Hinata and four others, the
37th annual conference on magnetism in Japan, Sep 2013, 5aA-1

SUMMARY OF INVENTION

10 Technical Problem

[0009]

In light of such circumstances, a first object of the present
invention is to provide a sputtering target with which it is possible
to form a magnetic thin film having a high coercive force H_c and
15 to provide a process for production thereof.

[0010]

A second object of the present invention is to provide a
sputtering target with which it is possible to form a magnetic thin
film whose coercive force H_c can be increased by annealing and to
20 provide a process for production thereof.

Solution to Problem

[0011]

The inventors of the present invention have diligently carried
25 out studies to solve the above-mentioned problem. As a result, the

inventors of the present invention have found that the magnetocrystalline anisotropy constant K_u can be improved by forming magnetic crystal grains in a magnetic thin film (perpendicular magnetic recording film) having a granular structure by using a CoPt alloy using no Cr instead of using a CoPtCr alloy, which is used in current magnetic thin films (perpendicular magnetic recording films).

[0012]

Furthermore, the inventors of the present invention have found that an oxide used when a CoPt-oxide film is formed by using magnetic crystal grains made of a CoPt alloy is preferably WO_3 and TiO_2 and particularly preferably WO_3 in order to obtain a high coercive force H_c of the film deposited at room temperature and to further increase the coercive force H_c by annealing the film deposited at room temperature.

[0013]

The present invention has been made on the basis of these new findings.

[0014]

Namely, a sputtering target according to the present invention is a sputtering target comprising metallic Co, metallic Pt, and an oxide, wherein the sputtering target does not contain metallic Cr, and the oxide has at least one of WO_3 and TiO_2 .

[0015]

In the above-described sputtering target, it is preferable

that the sputtering target comprises 20 to 90 at% of metallic Co relative to a total of metallic Co and metallic Pt.

[0016]

It is preferable that the oxide is at least one of WO_3 and TiO_2 .

[0017]

It is preferable that the oxide has WO_3 .

[0018]

It is preferable that the oxide is WO_3 .

10 [0019]

It is preferable that the sputtering target comprises 10 to 50 vol% of the oxide, and it is more preferable that the sputtering target comprises 25 to 35 vol% of the oxide.

[0020]

15 It is preferable that the sputtering target can be used for forming a magnetic thin film.

[0021]

Preferably, the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 6 kOe or higher, which is equal to or higher than the coercive force realized at the current technical level (hereinafter may be referred to as the "current technical level of coercive force"), by annealing the magnetic thin film in the temperature range of 300°C or higher and 550°C or lower.

25 [0022]

More preferably, the oxide has WO_3 and the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 9 kOe or higher, which is over the current technical level of coercive force, by annealing the magnetic thin film in the temperature range of 400°C or higher and 520°C or lower.

[0023]

Further preferably, the oxide has WO_3 and the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 10 kOe or higher, which is over the current technical level of coercive force, by annealing the magnetic thin film in the temperature range of 460°C or higher and 520°C or lower.

[0024]

It is preferable that the magnetic thin film after the annealing has a granular structure.

[0025]

A first aspect of a process for production of a sputtering target according to the present invention is a process for production of a sputtering target, comprising: a step of preparing a CoPt alloy powder that contains Co and Pt and does not contain Cr by an atomizing method; a step of preparing a powder mixture for pressure sintering by dispersedly mixing an oxide powder and the prepared CoPt alloy powder; and a step of pressure-sintering the prepared powder mixture for pressure sintering, wherein the oxide powder has at least one of WO_3 and TiO_2 .

[0026]

A second aspect of a process for production of a sputtering target according to the present invention is a process for production of a sputtering target, comprising: a step of obtaining a powder mixture for pressure sintering by dispersedly mixing a Co powder, a Pt powder, and an oxide powder; and a step of pressure-sintering the obtained powder mixture for pressure sintering, wherein the oxide powder has at least one of WO_3 and TiO_2 .

[0027]

It is preferable that the sputtering target obtained by the above-described process for production of a sputtering target contains 20 to 90 at% of metallic Co relative to a total of the metallic Co and metallic Pt.

[0028]

It is preferable that the oxide powder is at least one of WO_3 and TiO_2 .

[0029]

It is preferable that the oxide powder has WO_3 .

[0030]

It is preferable that the oxide powder is WO_3 .

[0031]

A volume fraction of the oxide powder in the entire powder mixture for pressure sintering is preferably 10 to 50 vol%, and is more preferably 25 to 35 vol%.

Advantageous Effects of Invention

[0032]

The present invention can provide a sputtering target with which it is possible to form a magnetic thin film having a high coercive force H_c and provide a process for production thereof.

5 [0033]

Also, the present invention can provide a sputtering target with which it is possible to form a magnetic thin film whose coercive force H_c can be increased by annealing and provide a process for production thereof.

10

BRIEF DESCRIPTION OF DRAWINGS

[0034]

FIG. 1 is a graph showing the percentage P_{fcc} of the fcc crystal structure present in the CoPt based alloy particles (magnetic crystal
15 grains).

FIG. 2 is a graph showing the measured results of the magnetocrystalline anisotropy constant K_u of a CoPt based alloy-SiO₂ magnetic thin film.

FIG. 3 is a metallurgical microscope photograph of the cross
20 section in the thickness direction of a sintered test piece according to Example 1 (an image taken at a magnification of 100x; a bar scale in the photograph represents 500 μm).

FIG. 4 is a metallurgical microscope photograph of the cross
section in the thickness direction of a sintered test piece according
25 to Example 1 (an image taken at a magnification of 500x; a bar scale

in the photograph represents 100 μm).

FIG. 5 is a graph showing the measured results of the coercive force H_c of magnetic thin films (CoPt alloy-oxide).

FIG. 6 is a graph showing the M-H loops (magnetization curves) of the magnetic thin films (CoPt alloy-oxide).

FIG. 7 illustrates TEM micrographs of a magnetic thin film of Example 1, where FIG. 7(a) illustrates a plane TEM micrograph of the CoPt-WO₃ magnetic thin film without annealing, FIG. 7(b) illustrates a plane TEM micrograph of the CoPt-WO₃ magnetic thin film with annealing at 500°C, and FIG. 7(c) illustrates a cross-sectional TEM micrograph of the CoPt-WO₃ magnetic thin film with annealing at 500°C.

FIG. 8 is a figure illustrating, as a graph, the magnetocrystalline anisotropy constant K_u^{grain} and the anisotropic magnetic field H_k^{grain} calculated for the CoPt alloy magnetic crystal grains in the magnetic thin film of Example 1.

DESCRIPTION OF EMBODIMENTS

[0035]

A sputtering target according to an embodiment of the present invention is a sputtering target comprising metallic Co, metallic Pt, and an oxide, wherein the sputtering target does not contain metallic Cr, and the oxide has at least one of WO₃ and TiO₂.

[0036]

1. Components of Target

The sputtering target according to this embodiment contains Co and Pt as metallic components and may further contain other metals (for example, Au, Ag, Ru, Rh, Pd, Ir, W, Ta, Cu, B, and Mo) unless these metals interfere with formation of the magnetic thin film.

5 As demonstrated in Reference Instance described below, the sputtering target cannot contain metallic Cr because the presence of metallic Cr has an adverse effect on the magnetocrystalline anisotropy constant K_u of the magnetic thin film.

[0037]

10 Metallic Co and metallic Pt are components of magnetic crystal grains (fine magnet) in the granular structure of the magnetic thin film formed by sputtering.

[0038]

Co is a ferromagnetic metal element and plays a central role
15 in the formation of the magnetic crystal grains (fine magnet) in the granular structure of the magnetic thin film. In order to increase the magnetocrystalline anisotropy constant of the CoPt alloy particles (magnetic crystal grains) in the magnetic thin film obtained by sputtering and to maintain the magnetism of the CoPt
20 alloy particles in the obtained magnetic thin film, the content percentage of metallic Co in the sputtering target according to this embodiment is preferably 20 to 90 at% and more preferably 25 to 85 at% relative to the total metallic components (the total of metallic Co and metallic Pt).

25 [0039]

Platinum, when alloying with Co in a predetermined composition range, has the function of reducing the magnetic moment of the alloy and thus has a role of adjusting the magnetic strength of the magnetic crystal grains. In order to increase the magnetocrystalline anisotropy constant of the CoPt alloy particles (magnetic crystal grains) in the magnetic thin film obtained by sputtering and to adjust the magnetism of the CoPt alloy particles (magnetic crystal grains) in the obtained magnetic thin film, the content percentage of metallic Pt in the sputtering target according to this embodiment is preferably 10 to 80 at% and more preferably 15 to 75 at% relative to the total metallic components.

[0040]

The sputtering target according to this embodiment contains at least one of WO_3 and TiO_2 as an oxide component. The oxide component serves as a non-magnetic matrix that separates the magnetic crystal grains (fine magnet) from each other in the granular structure of the magnetic thin film.

[0041]

The sputtering target according to this embodiment contains at least one of WO_3 and TiO_2 as an oxide and may further contain other oxides (for example, SiO_2 , Ti_2O_3 , Ta_2O_5 , Cr_2O_3 , CoO , Co_3O_4 , B_2O_3 , Fe_2O_3 , CuO , Y_2O_3 , MgO , Al_2O_3 , ZrO_2 , Nb_2O_5 , MoO_3 , CeO_2 , Sm_2O_3 , Gd_2O_3 , WO_2 , HfO_2 , and NiO_2) unless these oxides interfere with formation of the magnetic thin film. As demonstrated in Examples described below, WO_3 or TiO_2 is preferably used as an oxide because the use

of WO_3 or TiO_2 as an oxide can increase the coercive force H_c of the magnetic thin film deposited at room temperature and allows further improvement in the coercive force H_c by annealing the magnetic thin film deposited at room temperature. As demonstrated in Examples

5 described below, WO_3 is particularly preferably used as an oxide because the use of WO_3 as an oxide can significantly increase the coercive force H_c of the magnetic thin film formed.

[0042]

The content percentage of metallic components and the content

10 percentage of oxide components in the entire sputtering target depend on the composition of a desired magnetic thin film. Although not limited, the content percentage of metallic components in the entire sputtering target may be, for example, 88 to 94 mol%, and the content percentage of oxide components in the entire sputtering target may

15 be, for example, 6 to 12 mol%.

[0043]

As described above, the oxide component serves as a non-magnetic matrix that separates the magnetic crystal grains (fine magnet) from each other in the granular structure of the magnetic

20 thin film. Thus, a large oxide content in the magnetic thin film is preferred because it is easy to assuredly separate the magnetic crystal grains from each other and to make the magnetic crystal grains independent from each other. The oxide content in the sputtering target according to this embodiment is preferably 10

25 vol% or larger, and more preferably 20 vol% or larger, and still

more preferably 25 vol% or larger.

[0044]

However, an excessively large oxide content in the magnetic thin film has an adverse effect on the crystallinity of the CoPt alloy particles (magnetic crystal grains) because the CoPt alloy particles (magnetic crystal grains) are contaminated with the oxide, which may increase the proportion of structures other than the hcp structure in the CoPt alloy particles (magnetic crystal grains). This also reduces the number of the magnetic crystal grains per unit area of the magnetic thin film and thus makes it difficult to increase the recording density. In light of such views, the oxide content in the sputtering target according to this embodiment is preferably 50 vol% or less, more preferably 40 vol% or less, and still more preferably 35 vol% or less.

[0045]

Therefore, the oxide content in the sputtering target according to this embodiment relative to the entire sputtering target is preferably 10 to 50 vol%, more preferably 20 to 40 vol%, and still more preferably 25 to 35 vol%.

[0046]

2. Microstructure of Sputtering Target

The microstructure of the sputtering target according to this embodiment is not particularly limited, but is preferably a microstructure in which a metal phase and an oxide phase are finely dispersed in each other. Such a microstructure makes it difficult

to generate defects such as nodules and particles during sputtering.

[0047]

3. Process for Production of Sputtering Target

The sputtering target according to this embodiment can be produced, for example, in the following manner. An example production process in which WO_3 is used as an oxide will be described here.

[0048]

(1) Preparation of CoPt Alloy-Atomized Powder

Metallic Co and metallic Pt are weighed so as to obtain a prescribed composition (the atomic ratio of metallic Co to the total of the metallic Co and metallic Pt is 20 to 90 at%), and a molten CoPt alloy is produced. Subsequently, the molten CoPt alloy is gas-atomized to prepare a CoPt alloy-atomized powder having a prescribed composition (the atomic ratio of metallic Co to the total of the metallic Co and metallic Pt is preferably 20 to 90 at%). The produced CoPt alloy-atomized powder is classified so that the particle size becomes not larger than a predetermined particle size (for example, 106 μm or smaller).

[0049]

In order to increase the magnetism of the CoPt alloy-atomized powder, the atomic ratio of metallic Co to the total of the metallic Co and metallic Pt contained in the powder is preferably 25 at% or larger and more preferably 30 at% or larger.

[0050]

(2) Preparation of Powder Mixture for Pressure Sintering

AWO₃ powder is added to the CoPt alloy-atomized powder prepared in (1). The mixture is dispersedly mixed with a ball mill to prepare a powder mixture for pressure sintering. By dispersedly mixing the CoPt alloy-atomized powder and the WO₃ powder with the ball mill, a powder mixture for pressure sintering in which the CoPt alloy-atomized powder and the WO₃ powder are finely dispersed in each other can be prepared.

[0051]

In the magnetic thin film formed by using the obtained sputtering target, the volume fraction of the WO₃ powder in the entire powder mixture for pressure sintering is preferably 10 to 50 vol%, more preferably 15 to 40 vol%, and still more preferably 25 to 35 vol% in order to easily make the magnetic crystal grains independent from each other by assuredly separating the magnetic crystal grains from each other by WO₃, to makes it easy for the CoPt alloy particles (magnetic crystal grains) to have the hcp structure, and to increase the recording density.

[0052]

(3) Molding

The powder mixture for pressure sintering prepared in (2) is pressure-sintered and molded using, for example, a vacuum hot pressing method to produce a target. Since the powder mixture for pressure sintering prepared in (2) has been dispersedly mixed with a ball mill and the CoPt alloy-atomized powder and the WO₃ powder

are finely dispersed in each other, defects such as generation of nodules and particles are unlikely to occur during sputtering using the sputtering target obtained by this production process.

[0053]

5 The method for pressure-sintering the powder mixture for pressure sintering is not limited. The method may be a method other than a vacuum hot pressing method and may be, for example, a HIP method.

[0054]

10 (4) Modification

 The example production process described in (1) to (3) involves preparing the CoPt alloy-atomized powder by an atomizing method, adding the WO₃ powder to the prepared CoPt alloy-atomized powder, and dispersedly mixing the mixture with the ball mill to prepare
15 the powder mixture for pressure sintering. A Co single powder and a Pt single powder may be used instead of using the CoPt alloy-atomized powder. In such a case, three types of powder, which are a Co single powder, a Pt single powder, and a WO₃ powder, are dispersedly mixed with a ball mil to prepare a powder mixture for pressure sintering.

20

EXAMPLES

[0055]

 Hereinafter, the data that support the absence of metallic Cr in the sputtering target according to the present invention are
25 first shown in Reference Instance. Specifically, there are shown

the experimental results indicating that the magnetocrystalline anisotropy constant K_u is improved by forming magnetic crystal grains in a magnetic thin film having a granular structure by using a CoPt alloy that does not contain Cr instead of using a CoPtCr alloy, which is used in current perpendicular magnetic recording films. On the basis of the experimental results shown in Reference Instance, the sputtering target used for forming the magnetic thin film is free of metallic Cr in the present invention.

[0056]

In Examples and Comparative Examples, studies were carried out using four types of oxides, provided that the sputtering target used for forming the magnetic thin film was free of metallic Cr (the magnetic crystal grains in the magnetic thin film were formed of a CoPt alloy that does not contain Cr). The sputtering target that realized the magnetic thin film having a coercive force H_c over 10 kOe was obtained by selecting WO_3 as an oxide. The coercive force H_c of a magnetic thin film realized at the current technical level is about 6 to 7 kOe, and no magnetic thin film having a coercive force H_c over 10 kOe has been reported at present as long as the inventors of the present invention know.

[0057]

(Reference Instance)

A magnetic recording film was formed by sputtering with a DC sputtering apparatus. The magnetic recording film was formed on a glass substrate. The stacked structure of the formed magnetic

recording film includes, in order of increasing distance from the glass substrate, Ta (5 nm, 0.6 Pa) / Pt (6 nm, 0.6 Pa) / Ru (10 nm, 0.6 Pa) / Ru (10 nm, 8 Pa) / Co₆₀Cr₄₀-26 vol.% SiO₂ (2 nm, 4 Pa) / CoPt based alloy-SiO₂ (16 nm, 4 Pa) / C (7 nm, 0.6 Pa). The number on the left side in parenthesis indicates the film thickness, and the number on the right side indicates the pressure of an Ar atmosphere during sputtering.

[0058]

In the stacked structure of the formed magnetic recording film, CoPt based alloy-SiO₂ is a magnetic thin film that serves as the recording layer of a perpendicular magnetic recording medium. In Reference Instance, the following samples were prepared: a sample in which magnetic crystal grains in the magnetic thin film made of CoPt based alloy-SiO₂ were formed of a CoPtCr alloy that contained Cr (a sample in which the magnetic thin film had a composition of Co₇₄Pt₁₆Cr₁₀-25 vol.% SiO₂); and a sample in which magnetic crystal grains in the magnetic thin film made of CoPt based alloy-SiO₂ were formed of a CoPt alloy that did not contain Cr (a sample in which the magnetic thin film had a composition of Co_{82.4}Pt_{17.6}-27.7 vol.% SiO₂). Therefore, the term "CoPt based alloy" in the "CoPt based alloy-SiO₂" in the stacked structure of the magnetic recording film in Reference Instance refers to both a ternary CoPtCr alloy that contains Cr and a binary CoPt alloy that does not contain Cr. Hereinafter, the term "CoPt based alloy" also refers to both a ternary CoPtCr alloy that contains Cr and a binary CoPt alloy that does

not contain Cr.

[0059]

In addition, samples were prepared by forming the magnetic thin film made of CoPt based alloy-SiO₂ at different substrate temperatures during film deposition. Specifically, the following samples were prepared: a sample in which the magnetic thin film made of CoPt based alloy-SiO₂ was deposited on a substrate that was not heated but maintained at room temperature; and a sample in which the magnetic thin film made of CoPt based alloy-SiO₂ was deposited on a substrate that had been heated to a predetermined temperature until just before film deposition and had been transferred to a sputtering unit in the apparatus just before the start of film deposition.

[0060]

The prepared samples were analyzed for their crystal structures by in-plane X-ray diffraction. The analysis reveals that the crystal structure of the CoPt based alloy particles (magnetic crystal grains) in the CoPt based alloy-SiO₂ magnetic thin film formed in Reference Instance was composed mostly of the hcp structure and the remaining small part was composed of the fcc structure in all samples. FIG. 1 is a graph showing the results of the crystal structure analysis by in-plane X-ray diffraction. The graph shows the percentage P_{fcc} of the fcc crystal structure present in the CoPt based alloy particles (magnetic crystal grains). The horizontal axis of the graph shown in FIG. 1 represents the substrate temperature (°C) just before film

deposition. The vertical axis of the graph shown in FIG. 1 represents the percentage P_{fcc} (%) of the fcc crystal structure present in the CoPt based alloy particles (magnetic crystal grains).

[0061]

5 As shown in FIG. 1, in CoPtCr-SiO₂, which was a magnetic thin film that contained Cr, P_{fcc} was substantially constant at about 2.5% until the substrate temperature reached 200°C. The percentage P_{fcc} increased monotonously with increasing substrate temperature when the substrate temperature was in the temperature range of 200°C
10 to 470°C. The percentage P_{fcc} was about 5.5% when the substrate temperature was 470°C. In CoPt-SiO₂, which was a magnetic thin film that did not contain Cr, P_{fcc} was substantially constant at less than about 2% until the substrate temperature reached about 300°C. The percentage P_{fcc} started to increase with increasing substrate
15 temperature when the substrate temperature exceeded about 300°C. But, the percentage P_{fcc} was about 4.0% even when the substrate temperature was 470°C.

[0062]

Therefore, it is found that the absence of Cr in the CoPt based
20 alloy-SiO₂ magnetic thin film leads to a low percentage P_{fcc} of the fcc crystal structure present in the CoPt based alloy particles (magnetic crystal grains) and thus to a low percentage of stacking faults.

[0063]

25 The magnetocrystalline anisotropy constant K_u was determined

by using a torque magnetometer for the prepared samples. FIG. 2 is a graph showing the results of determination of the magnetocrystalline anisotropy constant K_u by using the torque magnetometer. The horizontal axis of the graph shown in FIG. 2 represents the substrate temperature ($^{\circ}\text{C}$) just before film deposition. The vertical axis of the graph shown in FIG. 2 represents the magnetocrystalline anisotropy constant K_u ($\times 10^6 \text{ erg/cm}^3$).

[0064]

As shown in FIG. 2, in CoPtCr-SiO_2 , which was a magnetic thin film that contained Cr, the magnetocrystalline anisotropy constant K_u was substantially constant at about $5.4 \times 10^6 \text{ erg/cm}^3$ until the substrate temperature reached 200°C . The magnetocrystalline anisotropy constant K_u decreased monotonously with increasing substrate temperature when the substrate temperature was in the temperature range of 200°C to 470°C . The magnetocrystalline anisotropy constant K_u was about 1.7 erg/cm^3 when the substrate temperature was 470°C . In CoPt-SiO_2 , which was a magnetic thin film that did not contain Cr, the magnetocrystalline anisotropy constant K_u was substantially constant at about 6.5 erg/cm^3 until the substrate temperature reached about 300°C . The magnetocrystalline anisotropy constant K_u started to decrease with increasing substrate temperature when the substrate temperature exceeded about 300°C . But, the magnetocrystalline anisotropy constant K_u was about 2.5 erg/cm^3 even when the substrate temperature was 470°C .

[0065]

Therefore, it is found that the absence of Cr in the CoPt based alloy-SiO₂ magnetic thin film leads to a large magnetocrystalline anisotropy constant K_u of the magnetic thin film. This is probably because the formation of the CoPt-SiO₂ magnetic thin film that does not contain Cr by eliminating Cr from the CoPtCr-SiO₂ magnetic thin film that contains Cr results in a low percentage P_{fcc} of the fcc crystal structure present in the CoPt based alloy particles (magnetic crystal grains) and thus in a small amount of stacking faults.

[0066]

(Example 1)

The composition of the entire target prepared as Example 1 is 91.4(80Co-20Pt)-8.6WO₃ in terms of molar ratio. The target was prepared and evaluated in the following manner. The composition of the entire target prepared in Example 1, when the content percentage of the oxide (WO₃) is expressed as the volume fraction in the entire target, is (80Co-20Pt)-30 vol% WO₃. The target prepared in Example 1 is within the scope of the target according to the present invention.

[0067]

To prepare the target according to Example 1, an 80Co-20Pt alloy-atomized powder was prepared first. Specifically, metals were weighed so as to obtain an alloy composition of Co: 80 at% and Pt: 20 at% and heated to 1500°C or higher to prepare a molten alloy. The molten alloy was gas-atomized to prepare an 80Co-20Pt alloy-atomized powder.

[0068]

The prepared 80Co-20Pt alloy-atomized powder was separately classified through 150 mesh sieves to obtain 80Co-20Pt alloy-atomized powder having a particle diameter of 106 μm or smaller. [0069]

5 To 610.00 g of the classified 80Co-20Pt alloy-atomized powder, 154.44 g of a WO_3 powder was added. Then, the mixture was mixed and dispersed by a ball mill to obtain a powder mixture for pressure sintering. The cumulative rotation number of a ball mill was 1,870,560.

10 [0070]

The obtained powder mixture (30 g) for pressure sintering was subjected to hot pressing under the conditions of sintering temperature: 900°C, pressure: 26 MPa, time: 30 min, and atmosphere: 5×10^{-2} Pa or lower to prepare a sintered test piece (ϕ 30 mm). 15 The relative density of the prepared sintered test piece was 101.641%. The calculated density is 10.64 g/cm³.

[0071]

FIG. 3 and FIG. 4 are metallurgical microscope photograph of the cross section in the thickness direction of the obtained sintered 20 test piece. FIG. 3 is a photograph at a photographing magnification of 100 times (a bar scale in the photograph represents 500 μm), and FIG. 4 is a photograph at a photographing magnification of 500 times (a bar scale in the photograph represents 100 μm).

[0072]

25 As can be seen from FIG. 3 and FIG. 4, the 80Co-20Pt-alloy

phase and the WO_3 phase were finely dispersed in and mixed with each other.

[0073]

Next, the prepared powder mixture for pressure sintering was subjected to hot pressing under the conditions of sintering temperature: 900°C , pressure: 26 MPa, time: 60 min, and atmosphere: 5×10^{-2} Pa or lower to prepare a target with $\phi 164.0$ mm and a thickness of 2.0 mm. The relative density of the prepared target was 99.7%.

[0074]

The prepared target was evaluated for leakage flux on the basis of ASTM F2086-01. As a result, the average magnetic leakage flux rate was 59.3%. This average magnetic leakage flux rate is sufficient for favorable magnetron sputtering.

[0075]

Next, a magnetic thin film made of (80Co-20Pt)-30 vol% WO_3 was deposited on a substrate by magnetron sputtering using the prepared target to produce a sample for determining magnetic properties. The stacked structure of this sample for determining magnetic properties includes glass/Ta (5 nm, 0.6 Pa) / Pt (6 nm, 0.6 Pa) / Ru (10 nm, 0.6 Pa) / Ru (10 nm, 8 Pa) / $\text{Co}_{60}\text{Cr}_{40}$ -26 vol.% SiO_2 (2 nm, 4 Pa) / CoPt alloy- WO_3 (16 nm, 8 Pa). The number on the left side in parenthesis indicates the film thickness, and the number on the right side indicates the pressure of an Ar atmosphere during sputtering.

[0076]

In the stacked structure of the sample for determining magnetic properties, CoPt alloy-WO₃ is a magnetic thin film deposited by using the target prepared in Example 1. This magnetic thin film was deposited at room temperature without heating the substrate during film deposition.

[0077]

Next, the obtained sample for determining magnetic properties was annealed in an annealing furnace (degree of vacuum: 5×10^{-4} or less). The heating rate and cooling rate of the annealing furnace were both constant at 200 °C/h. The annealing temperatures were 200°C, 300°C, 400°C, 450°C, 500°C, and 600°C. Different samples for determining magnetic properties were used at different annealing temperatures. There was one annealed sample for determining magnetic properties at each annealing temperature in Example 1, that is, there were total six samples. In the annealing, each sample was maintained at an annealing temperature for 0 hours and cooled to room temperature. That is, heating was terminated when a predetermined annealing temperature was reached, and the sample was cooled to room temperature.

[0078]

The M-H loops (magnetization curves) were obtained by using a magneto-optical Kerr effect apparatus for the samples (total six samples) for determining magnetic properties that had been annealed by heating to a target annealing temperature and cooled to room temperature and the sample (one sample) for determining magnetic

properties that had not been annealed after film deposition at room temperature. The coercive force H_c was read from each M-H loop (magnetization curve).

[0079]

5 The measured results of the coercive force H_c are shown in FIG. 5 together with the results in other Examples and Comparative Examples. The horizontal axis of FIG. 5 represents the annealing temperature ($^{\circ}\text{C}$), and the vertical axis represents the coercive force H_c (kOe).

10 [0080]

In Example 1, the coercive force H_c of the sample without annealing was 7.1 kOe. This coercive force is equal to or higher than the coercive force of a magnetic thin film realized at the current technical level. The magnetic thin film of Example 1, even
15 without annealing, has a coercive force sufficient for use as a current perpendicular magnetic recording medium.

[0081]

In Example 1, the coercive force H_c was further increased by annealing. As can be seen from FIG. 5, the coercive force H_c reached
20 the maximum when the annealing temperature was 500°C . The maximum coercive force H_c was 10.8 kOe, which was over 10 kOe. As described above, the coercive force H_c of a magnetic thin film realized at the current technical level is about 6 to 7 kOe, and no magnetic thin film having a coercive force H_c over 10 kOe has been reported
25 as long as the inventors of the present invention know. The magnetic

thin film of Example 1 (annealed at 500°C) is the first magnetic thin film having a coercive force H_c over 10 kOe.

[0082]

The M-H loop (magnetization curve) when the maximum coercive force H_c was obtained (when the annealing temperature was 500°C) is shown in FIG. 6 together with the results of other Examples and Comparative Examples. The horizontal axis of FIG. 6 represents the strength of the magnetic field applied. The vertical axis of FIG. 6 represents the value normalized by dividing the rotation angle (Kerr rotation angle) of the polarization axis of incident light by the saturation Kerr rotation angle.

[0083]

(Example 2)

The composition of the entire target prepared as Example 2 is (80Co-20Pt)-30 vol% TiO_2 . A target was prepared in the same manner as in Example 1 except that TiO_2 was used as an oxide. The target prepared in Example 2 is within the scope of the target according to the present invention. Samples for determining magnetic properties were also prepared in the same manner as in Example 1 using the prepared target.

[0084]

In the same manner as in Example 1, the M-H loops (magnetization curves) were obtained by using a magneto-optical Kerr effect apparatus for samples (total six samples) for determining magnetic properties that had been annealed at target annealing temperatures

(200°C, 300°C, 400°C, 450°C, 500°C, and 600°C) and cooled to room temperature and a sample (one sample) for determining magnetic properties that had not been annealed after film deposition at room temperature. The coercive force H_c was read from each M-H loop
5 (magnetization curve).

[0085]

The measured results of the coercive force H_c are shown in FIG. 5 together with the results in other Examples and Comparative Examples.

10 [0086]

In Example 2, the coercive force H_c of the sample without annealing was 5.8 kOe. The coercive force H_c of the samples with annealing reached the maximum when the annealing temperature was 500°C. The maximum coercive force H_c was 8.6 kOe. As described
15 above, the coercive force H_c of a magnetic thin film realized at the current technical level is about 6 to 7 kOe. The coercive force H_c of the magnetic thin film of Example 2 (annealed at 500°C) exceeds the coercive force H_c of a magnetic thin film realized at the current technical level.

20 [0087]

The M-H loop (magnetization curve) when the maximum coercive force H_c was obtained (when the annealing temperature was 500°C) is shown in FIG. 6 together with the results of other Examples and Comparative Examples.

25 [0088]

(Comparative Example 1)

The composition of the entire target prepared as Comparative Example 1 is (80Co-20Pt)-30 vol% SiO₂. A target was prepared in the same manner as in Example 1 except that SiO₂ was used as an oxide. Since the oxide used in the target prepared in Comparative Example 1 is SiO₂, the target prepared in Comparative Example 1 is out of the scope of the target according to the present invention. Samples for determining magnetic properties were also prepared in the same manner as in Example 1 using the prepared target.

[0089]

In the same manner as in Example 1, the M-H loops (magnetization curves) were obtained by using a magneto-optical Kerr effect apparatus for samples (total six samples) for determining magnetic properties that had been annealed at target annealing temperatures (200°C, 300°C, 400°C, 450°C, 500°C, and 600°C) and cooled to room temperature and a sample (one sample) for determining magnetic properties that had not been annealed after film deposition at room temperature. The coercive force H_c was read from each M-H loop (magnetization curve).

[0090]

The measured results of the coercive force H_c are shown in FIG. 5 together with the results in other Examples and Comparative Examples.

[0091]

In Comparative Example 1, the coercive force H_c of the sample

without annealing was 5.2 kOe. The coercive force H_c of the samples with annealing reached the maximum when the annealing temperature was 300°C. The maximum coercive force H_c was 5.5 kOe.

[0092]

5 The M-H loop (magnetization curve) when the maximum coercive force H_c was obtained (when the annealing temperature was 300°C) is shown in FIG. 6 together with the results of other Examples and Comparative Examples.

[0093]

10 (Comparative Example 2)

 The composition of the entire target prepared as Comparative Example 2 is (80Co-20Pt)-30 vol% Al_2O_3 . A target was prepared in the same manner as in Example 1 except that Al_2O_3 was used as an oxide. Since the oxide used in the target prepared in Comparative
15 Example 2 is Al_2O_3 , the target prepared in Comparative Example 2 is out of the scope of the target according to the present invention. Samples for determining magnetic properties were also prepared in the same manner as in Example 1 using the prepared target.

[0094]

20 In the same manner as in Example 1, the M-H loops (magnetization curves) were obtained by using a magneto-optical Kerr effect apparatus for samples (total six samples) for determining magnetic properties that had been annealed at target annealing temperatures (200°C, 300°C, 400°C, 450°C, 500°C, and 600°C) and cooled to room
25 temperature and a sample (one sample) for determining magnetic

properties that had not been annealed after film deposition at room temperature. The coercive force H_c was read from each M-H loop (magnetization curve).

[0095]

5 The measured results of the coercive force H_c are shown in FIG. 5 together with the results in other Examples and Comparative Examples.

[0096]

10 In Comparative Example 2, the coercive force H_c of the sample without annealing was 0.9 kOe. The coercive force H_c of the samples with annealing reached the maximum when the annealing temperature was 600°C. The maximum coercive force H_c was 2.3 kOe.

[0097]

15 The M-H loop (magnetization curve) when the maximum coercive force H_c was obtained (when the annealing temperature was 600°C) is shown in FIG. 6 together with the results of other Examples and Comparative Examples.

[0098]

(Studies about Oxide)

20 The oxide used in Example 1 is WO_3 , the oxide used in Example 2 is TiO_2 , the oxide used in Comparative Example 1 is SiO_2 , and the oxide used in Comparative Example 2 is Al_2O_3 .

[0099]

25 In order to further study how these four types of oxides affect the magnetic properties of the obtained magnetic thin film, the

nucleation magnetic field H_n (kOe) and the slope α of the M-H loops (magnetization curves) were calculated from the M-H loops shown in FIG. 6 (the M-H loops for the samples for determining magnetic properties that had been annealed at the annealing temperature at which the coercive force H_c reached the maximum). The slope α of the M-H loops (magnetization curves) was calculated in accordance with the formula of $4\pi \times |dM/dH|$ using the data in the region near the points indicating the coercive force H_c . The calculated results of the nucleation magnetic field H_n (kOe) and the slope α of the M-H loops are shown in Table 1 below together with the maximum coercive force H_c described above.

[0100]

[Table 1]

Oxide	Coercive force H_c (kOe)	Nucleation magnetic field H_n (kOe)	Slope α of the M-H loops
WO ₃ (Example 1)	10.8	5.5	1.6
TiO ₂ (Example 2)	8.6	4.9	2.2
SiO ₂ (Comparative Example 1)	5.5	0.4	1.8
Al ₂ O ₃ (Comparative Example 2)	2.3	1.8	14.5

[0101]

As can be seen from Table 1, the coercive force H_c and the nucleation magnetic field H_n of the magnetic thin film of Example

1 using WO_3 as an oxide are the highest, and 10.8 (kOe) and 5.5 (kOe),
respectively. As described above, the coercive force H_c of a magnetic
thin film realized at the current technical level is about 6 to
7 kOe, and no magnetic thin film having a coercive force H_c over
5 10 kOe has been reported as long as the inventors of the present
invention know. The magnetic thin film of Example 1 (annealed at
500°C) is the first magnetic thin film having a coercive force H_c
over 10 kOe.

[0102]

10 The slope α of the M-H loop of the magnetic thin film of Example
1 (after annealed at 500°C) using WO_3 as an oxide is as small as
1.6, which suggests that a rapid magnetic reversal is unlikely to
occur.

[0103]

15 Since the coercive force H_c and the nucleation magnetic field
 H_n are high and the slope α of the M-H loop is small for the magnetic
thin film of Example 1 (annealed at 500°C) using WO_3 as an oxide,
the thermal stability of record signals when the magnetic thin film
of Example 1 is used as a magnetic recording film is considered
20 significantly high.

[0104]

As can be seen from FIG. 5, the coercive force H_c of the magnetic
thin film of Example 1 using WO_3 as an oxide increases with increasing
annealing temperature when the annealing temperature is in the range
25 of 500°C or less. Thus, the magnetic thin film of Example 1 is also

characterized in that the coercive force H_c is improved by annealing at an annealing temperature of 500°C or less.

[0105]

As can be seen from FIG. 5, the coercive force H_c of the magnetic thin film of Example 1 using WO_3 as an oxide is 7.1 kOe even when the magnetic thin film is not annealed (in the state as it was deposited at room temperature). This coercive force is equal to or higher than the coercive force of a magnetic thin film realized at the current technical level. Therefore, the magnetic thin film of Example 1, even without annealing, has a coercive force sufficient for use as a current perpendicular magnetic recording medium.

[0106]

The coercive force H_c and the nucleation magnetic field H_n of the magnetic thin film of Example 2 (annealed at 500°C) using TiO_2 as an oxide are 8.6 (kOe) and 4.9 (kOe), respectively, which are below those of the magnetic thin film of Example 1. However, compared with current magnetic thin films, the magnetic thin film of Example 2 has a coercive force over the realized coercive force. The thermal stability of record signals when the magnetic thin film of Example 2 is used as a magnetic recording film is considered significantly high.

[0107]

As can be seen from FIG. 5, the coercive force H_c of the magnetic thin film of Example 2 using TiO_2 as an oxide increases with increasing annealing temperature when the annealing temperature is in the range

of 500°C or less. Thus, the magnetic thin film of Example 2 is also characterized in that the coercive force H_c is improved by annealing at an annealing temperature of 500°C or less.

[0108]

5 The coercive forces of the magnetic thin film of Comparative Example 1 using SiO_2 as an oxide and the magnetic thin film of Comparative Example 2 using Al_2O_3 as an oxide, regardless of whether annealing is performed, do not reach the coercive force (6 to 7 kOe) of a magnetic thin film realized at the current technical level.

10 The thermal stability of record signals when the magnetic thin films of Comparative Examples 1 and 2 are used as magnetic recording films cannot be considered high.

[0109]

(TEM Observation of Magnetic Thin Film of Example 1)

15 The microstructure of the magnetic thin film of Example 1 (magnetic thin film using WO_3 as an oxide) that attained very good magnetic properties was examined by using TEM. FIG. 7 illustrates TEM micrographs of the magnetic thin film of Example 1.

[0110]

20 FIG. 7(a) illustrates a plane TEM micrograph of the CoPt-WO_3 magnetic thin film without annealing (the TEM micrograph of the surface of the magnetic thin film in the plane direction). FIG. 7(b) illustrates a plane TEM micrograph of the CoPt-WO_3 magnetic thin film with annealing at 500°C.

25 [0111]

In the plane TEM micrographs of FIGs. 7(a) and 7(b), the deep gray regions indicate the CoPt alloy and the white regions indicate WO_3 . As can be seen from FIGs. 7(a) and 7(b), regardless of whether annealing is performed, the CoPt alloy magnetic crystal grains are separated by WO_3 at a distance of about 1 nm to form a favorable granular structure.

[0112]

The area of the region of each CoPt alloy magnetic crystal grain was determined at 100 points or more by using the plane TEM micrographs. Assuming that the shape of each CoPt alloy magnetic crystal grain is a cylinder, the crystal grain size (diameter of the cylinder) was calculated. As a result, the crystal grain size was 6.4 nm when annealing was not performed and 8 nm when annealing was performed at 500°C. This suggests that annealing causes the CoPt alloy magnetic crystal grains to grow in a cylindrical shape.

[0113]

FIG. 7(c) illustrates a cross-sectional TEM micrograph of the CoPt- WO_3 magnetic thin film with annealing at 500°C (the TEM micrograph of the cross-section in the direction perpendicular to the plane of the magnetic thin film). As can be seen from this cross-sectional TEM micrograph, the CoPt alloy magnetic crystal grains grow in a cylindrical shape in the CoPt- WO_3 magnetic thin film with annealing at 500°C.

[0114]

As described above, TEM observation reveals that the CoPt- WO_3

magnetic thin film has a good granular structure regardless of whether annealing is performed. It is also revealed that annealing the CoPt-WO₃ magnetic thin film at 500°C allows the CoPt alloy magnetic crystal grains to grow in a cylindrical shape.

5 [0115]

(Suitable Annealing Temperature)

Since the magnetic thin films of Examples 1 and 2 attain a good coercive force H_c, studies are carried out on the annealing temperature suitable for the magnetic thin films of Examples 1 and 2 on the basis of FIG. 5 (the graph indicating the relationship between the annealing temperature and the coercive force H_c).

[0116]

As can be seen from FIG. 5, when the annealing temperature is in the temperature range of 300°C or higher and 550°C or lower, the coercive forces H_c of the magnetic thin films of Examples 1 and 2 are about 6.5 kOe or higher, which are equal to or higher than the coercive force H_c of a magnetic thin film of the current technical level. Therefore, the annealing temperature for the magnetic thin films of Examples 1 and 2 is preferably in the temperature range of 300°C or higher and 550°C or lower.

[0117]

As can be seen from FIG. 5, when the annealing temperature is in the temperature range of 400°C or higher and 520°C or lower, the coercive force H_c of the magnetic thin film of Example 1 is about 9 kOe or higher, which is a coercive force H_c over the current

technical level. When the annealing temperature is in the temperature range of 400°C or higher and 520°C or lower, the coercive force Hc of the magnetic thin film of Example 2 is about 7.1 kOe or higher, which is a coercive force Hc equal to or higher than the coercive force Hc of a magnetic thin film of the current technical level. Therefore, the annealing temperature for the magnetic thin films of Examples 1 and 2 is more preferably in the temperature range of 400°C or higher and 520°C or lower.

[0118]

As can be seen from FIG. 5, when the annealing temperature is in the temperature range of 460°C or higher and 520°C or lower, the coercive force Hc of the magnetic thin film of Example 1 is about 10 kOe or higher, which is a coercive force Hc that a magnetic thin film of the current technical level does not achieve. When the annealing temperature is in the temperature range of 460°C or higher and 520°C or lower, the coercive force Hc of the magnetic thin film of Example 2 is about 8 kOe or higher, which is a coercive force Hc over the current technical level. Therefore, the annealing temperature for the magnetic thin films of Examples 1 and 2 is still more preferably in the temperature range of 460°C or higher and 520°C or lower.

[0119]

As can be seen from FIG. 5, when the annealing temperature is in the temperature range of 480°C or higher and 510°C or lower, the coercive forces Hc of the magnetic thin films of Examples 1

and 2 reach substantially the maximum. Therefore, the annealing temperature for the magnetic thin films of Examples 1 and 2 is particularly preferably in the temperature range of 480°C or higher and 510°C or lower.

5 [0120]

(Studies about Reason for Increase in Coercive Force H_c by Annealing)

A high coercive force H_c of 10.8 kOe was obtained by annealing the magnetic thin film of Example 1 at 500°C. To study the reason
10 for obtaining a high coercive force H_c by annealing, the magnetocrystalline anisotropy constant K_u^{grain} and the anisotropic magnetic field H_k^{grain} of the CoPt alloy magnetic crystal grains in the magnetic thin film of Example 1 were calculated. Specifically, the magnetocrystalline anisotropy constant K_u^{grain} and the anisotropic
15 magnetic field H_k^{grain} were calculated by subtracting the amount corresponding to the effect of 30 vol% of WO_3 from the average magnetic property values of the CoPt- WO_3 magnetic thin film.

[0121]

The magnetocrystalline anisotropy constant K_u^{grain} and the
20 anisotropic magnetic field H_k^{grain} have a relationship of $K_u^{\text{grain}} = (M_s^{\text{grain}} \times H_k^{\text{grain}})/2$, wherein M_s^{grain} is the saturation magnetization of each crystal grain and is calculated from the average saturation magnetization determined with a vibrating sample magnetometer. The saturation magnetization M_s^{grain} of each crystal grain was
25 substantially constant at about 990 emu/cm³ regardless of whether

annealing was performed and the annealing temperature.

[0122]

FIG. 8 is a figure illustrating, as a graph, the magnetocrystalline anisotropy constant K_u^{grain} and the anisotropic magnetic field H_k^{grain} calculated for the CoPt alloy magnetic crystal grains in the magnetic thin film of Example 1. In the graph shown in FIG. 8, the horizontal axis represents the annealing temperature ($^{\circ}\text{C}$), and the vertical axis represents the magnetocrystalline anisotropy constant K_u^{grain} ($\times 10^6 \text{ erg/cm}^3$) and the anisotropic magnetic field H_k^{grain} (kOe).

[0123]

As can be seen from FIG. 8, when the annealing temperature increases from room temperature to 500°C , the magnetocrystalline anisotropy constant K_u^{grain} increases from $7.8 \times 10^6 \text{ erg/cm}^3$ to $10.4 \times 10^6 \text{ erg/cm}^3$, and the anisotropic magnetic field H_k^{grain} increases from 15.7 kOe to 21 kOe. Since the ways the magnetocrystalline anisotropy constant K_u^{grain} and the anisotropic magnetic field H_k^{grain} change are the same as the way the coercive force H_c changes shown in FIG. 5, an increase in coercive force H_c by annealing is supposed to be on the basis of an increase in magnetocrystalline anisotropy constant K_u^{grain} .

[0124]

(Additional Studies about Composition of CoPt Alloy)

The results of Reference Instance, Examples 1 and 2, and Comparative Examples 1 and 2 as described above reveal that a magnetic

thin film having a coercive force H_c over 10 kOe is obtained by annealing, at 500°C, a magnetic thin film formed by using the sputtering target that contains Co, Pt, and an oxide, does not contain Cr, and has WO_3 as the oxide without heating the substrate.

5 [0125]

However, the chemical composition of Co and Pt in the sputtering targets used in Examples 1 and 2 and Comparative Examples 1 and 2 is 80Co-20Pt, only one type of composition.

[0126]

10 Then, magnetic thin films formed by using sputtering targets having different compositions of Co and Pt (and containing 30 vol% of WO_3 as an oxide) without heating the substrate were annealed at 500°C. The coercive force H_c and the nucleation magnetic field H_n of the annealed magnetic thin films were determined to study the
15 range of the composition of Co and Pt in the sputtering target that exhibits advantageous effects of the present invention.

[0127]

The compositions of Co and Pt in the sputtering targets in additional studies (Examples 3 to 7, Comparative Examples 3 and
20 4) were 90Co-10Pt in Example 3, 85Co-15Pt in Example 4, 50Co-50Pt in Example 5, 25Co-75Pt in Example 6, and 20Co-80Pt in Example 7. The metallic component in the sputtering target of Comparative Example 3 is only Co, and the metallic component in the sputtering target of Comparative Example 4 is only Pt. The targets were prepared
25 in the same manner as in Example 1 except that the composition of

Co and Pt was changed. The coercive force H_c and the nucleation magnetic field H_n of the magnetic thin films were determined in the same manner as in Example 1. The measured results are shown in Table 2 below together with the measured results of Example 1.

5 [0128]

[Table 2]

	Compositions of CoPt	WO ₃ content (vol%)	Coercive force H_c (kOe)	Nucleation magnetic field H_n (kOe)
Comparative Example 3	100Co	30	0.5	0.0
Example 3	90Co-10Pt	30	7.8	3.5
Example 4	85Co-15Pt	30	9.5	4.6
Example 1	80Co-20Pt	30	10.8	5.5
Example 5	50Co-50Pt	30	13.3	6.7
Example 6	25Co-75Pt	30	11.1	5.2
Example 7	20Co-80Pt	30	6.8	2.3
Comparative Example 4	100Pt	30	0.0	0.0

[0129]

As can be seen from Table 2, the coercive forces H_c , after
 10 annealing at 500°C, of the magnetic thin films formed by using the
 sputtering targets within the scope of the present invention (Example
 1, Examples 3 to 7) were all 6.8 kOe or higher, which were equal
 to or higher than the current technical level of coercive force.

In particular, the coercive forces H_c of the magnetic thin films of Examples 1, 5 and 6 were 10 kOe or higher, which were significantly high coercive forces.

[0130]

5 The coercive forces H_c , after annealing at 500°C, of the magnetic thin films formed by using the sputtering target of Comparative Example 3 out of the scope of the present invention in which the metallic component was only Co and the sputtering target of Comparative Example 4 out of the scope of the present invention
10 in which the metallic component was only Pt were as small as 0.5 kOe and 0.0 kOe, respectively.

[0131]

(Additional Studies about Oxide Content)

As described above, the coercive forces H_c , after annealing
15 at 500°C, of the magnetic thin films formed by using the sputtering targets within the scope of the present invention (Example 1, Examples 3 to 7) were all 6.8 kOe or higher, which were coercive forces equal to or higher than the current technical level of coercive force and showed favorable results.

20 [0132]

However, the WO_3 content in the sputtering targets used in Example 1 and Examples 3 to 7 was 30 vol%, only one type of content.

[0133]

Then, magnetic thin films formed by using sputtering targets
25 (the composition of Co and Pt was 80Co-20Pt) having different WO_3

contents without heating the substrate were annealed at 500°C. The coercive force H_c and the nucleation magnetic field H_n of the annealed magnetic thin films were determined to study the range of the WO_3 content in the sputtering target that exhibits advantageous effects of the present invention.

[0134]

The WO_3 contents in the sputtering targets in additional studies (Examples 8 to 13, Comparative Example 5) were 10 vol% in Example 8, 20 vol% in Example 9, 25 vol% in Example 10, 35 vol% in Example 11, 40 vol% in Example 12, 50 vol% in Example 13, and 0 vol% in Comparative Example 5. The targets were prepared in the same manner as in Example 1 except that the WO_3 content was changed. The coercive force H_c and the nucleation magnetic field H_n of the magnetic thin films were determined in the same manner as in Example 1. The measured results are shown in Table 3 below together with the measured results of Example 1.

[0135]

[Table 3]

	Compositions of CoPt	WO ₃ content (vol%)	Coercive force H _c (kOe)	Nucleation magnetic field H _n (kOe)
Example 8	80Co-20Pt	10	7.5	3.2
Example 9	80Co-20Pt	20	9.5	4.3
Example 10	80Co-20Pt	25	10.4	5.0
Example 1	80Co-20Pt	30	10.8	5.5
Example 11	80Co-20Pt	35	10.8	5.5
Example 12	80Co-20Pt	40	10.0	4.7
Example 13	80Co-20Pt	50	6.9	2.9
Comparative Examples 5	80Co-20Pt	0	0.7	-1.9

[0136]

5 As can be seen from Table 3, the coercive forces H_c, after annealing at 500°C, of the magnetic thin films formed by using the sputtering targets within the scope of the present invention (Example 1, Examples 8 to 13) were all 6.9 kOe or higher, which were equal to or higher than the current technical level of coercive force.

10 In particular, the coercive forces H_c of the magnetic thin films of Examples 1, 10, 11 and 12 were 10 kOe or higher, which were significantly high coercive forces.

[0137]

The coercive force H_c , after annealing at 500°C, of the magnetic thin film formed by using the sputtering target of Comparative Example 5 out of the scope of the present invention in which the WO_3 content was 0 was as small as 0.7 kOe.

CLAIMS

1. A sputtering target comprising metallic Co, metallic Pt, and an oxide,

wherein the sputtering target does not contain metallic Cr,

5 and

the oxide has at least one of WO_3 and TiO_2 .

2. The sputtering target according to claim 1, wherein the sputtering target comprises 20 to 90 at% of metallic Co relative

10 to a total of metallic Co and metallic Pt.

3. The sputtering target according to claim 1 or 2, wherein the oxide is at least one of WO_3 and TiO_2 .

15 4. The sputtering target according to claim 1 or 2, wherein the oxide has WO_3 .

5. The sputtering target according to claim 1 or 2, wherein the oxide is WO_3 .

20

6. The sputtering target according to any one of claims 1 to 5, wherein the sputtering target comprises 10 to 50 vol% of the oxide.

7. The sputtering target according to any one of claims 1 to 5,

25 wherein the sputtering target comprises 25 to 35 vol% of the oxide.

8. The sputtering target according to any one of claims 1 to 7, wherein the sputtering target can be used for forming a magnetic thin film.

5

9. The sputtering target according to claim 8, wherein the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 6 kOe or higher by annealing the magnetic thin film in a temperature range of 300°C or higher and 550°C or lower.

10

10. The sputtering target according to claim 8, wherein the oxide has WO_3 , and the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 9 kOe or higher by annealing the magnetic thin film in a temperature range of 400°C or higher and 520°C or lower.

15

11. The sputtering target according to claim 8, wherein the oxide has WO_3 , and the magnetic thin film formed by using the sputtering target is allowed to have a coercive force of 10 kOe or higher by annealing the magnetic thin film in a temperature range of 460°C or higher and 520°C or lower.

20

25

12. The sputtering target according to any one of claims 9 to 11, wherein the magnetic thin film after the annealing has a granular structure.

- 5 13. A process for production of a sputtering target, comprising:
a step of preparing a CoPt alloy powder that contains Co and Pt and does not contain Cr by an atomizing method;
a step of preparing a powder mixture for pressure sintering by dispersedly mixing an oxide powder and the prepared CoPt alloy
10 powder; and
a step of pressure-sintering the prepared powder mixture for pressure sintering,
wherein the oxide powder has at least one of WO_3 and TiO_2 .
- 15 14. A process for production of a sputtering target, comprising:
a step of obtaining a powder mixture for pressure sintering by dispersedly mixing a Co powder, a Pt powder, and an oxide powder;
and
a step of pressure-sintering the obtained powder mixture for
20 pressure sintering,
wherein the oxide powder has at least one of WO_3 and TiO_2 .

15. The process for production of a sputtering target according to claim 13 or 14, wherein the obtained sputtering target contains
25 20 to 90 at% of metallic Co relative to a total of the metallic

Co and metallic Pt.

16. The process for production of a sputtering target according to any one of claims 13 to 15, wherein the oxide powder is at least one of WO_3 and TiO_2 .

17. The process for production of a sputtering target according to any one of claims 13 to 15, wherein the oxide powder has WO_3 .

18. The process for production of a sputtering target according to any one of claims 13 to 15, wherein the oxide powder is WO_3 .

19. The process for production of a sputtering target according to any one of claims 13 to 18, wherein a volume fraction of the oxide powder in the entire powder mixture for pressure sintering is 10 to 50 vol%.

20. The process for production of a sputtering target according to any one of claims 13 to 18, wherein a volume fraction of the oxide powder in the entire powder mixture for pressure sintering is 25 to 35 vol%.