

Chemical products suitable as cocatalysts, their preparation and their use in catalyst systems for preparing polyolefins

- 5 The present invention relates to chemical products suitable as cocatalysts, to processes for preparing them and to their use in catalyst systems for preparing polyolefins. In particular, the invention relates to chemical products which are electrically neutral and in combination with an organic transition metal
10 compound can form a catalyst system which can advantageously be used for the polymerization of olefins. Here, the use of aluminoxanes such as methylaluminumoxane (MAO) as cocatalyst can be dispensed with while nevertheless achieving a high catalyst activity and good polymer morphology.

- 15 The role of cationic complexes in Ziegler-Natta polymerization using metallocenes is generally recognized (H.H. Brintzinger, D. Fischer, R. Mülhaupt, R. Rieger, R. Waymouth, Angew. Chem. 1995, 107, 1255-1283).

- 20 MAO as effective cocatalyst has the disadvantage that it has to be used in a large excess. Although modified MAO cocatalysts have been described, for example in WO99/30819, WO99/30820, WO99/30821 and JP-09-278817 A1, these systems display unsatisfactory
25 polymerization activities and have to be used in a large excess.

- The preparation of cationic transition metal alkyl complexes opens the way to MAO-free catalysts having comparable activity, in which the cocatalyst can be used in an almost stoichiometric
30 amount.

- The synthesis of "cation-like" metallocene polymerization catalysts is described in J. Am. Chem. Soc. 1991, 113, 3623. A process for preparing salts of the formula $LMX^+ XA^-$ according to
35 the above-described principle is described in EP-A-0 520 732.


- EP-A-0 558 158 describes zwitterionic catalyst systems which are prepared from dialkyl-metallocene compounds and salts of the formula $[R_3NH]^+ [B(C_6H_5)_4]^-$. Reaction of such a salt with, for
40 example, Cp_2ZrMe_2 results in protolysis with elimination of methane to give a methyl-zirconocene cation as intermediate. This reacts via C-H activation to form the zwitterion $Cp_2Zr^+-(\eta-C_6H_4)-BPh_3^-$. In this zwitterion, the Zr atom is covalently bound to a carbon atom of the phenyl ring and is
45 stabilized by a agostic hydrogen bonds.

- US-A-5,384,299 describes zwitterionic catalyst systems which are prepared from dialkyl-metallocene compounds and salts of the formula $[R_3NH]^+ [B(C_6F_5)_4]^-$ by protolysis. The C-H-activation as subsequent reaction does not occur. In EP-A-0 426 637, the Lewis-acid CPh_3^+ cation is used for abstraction of the methyl group from the metal center. $B(C_6F_5)_4^-$ functions as weakly coordinating anion.
- 10 To enable metallocene catalysts to be utilized industrially, the catalyst system has to be made heterogeneous in order to ensure appropriate morphology of the resulting polymer. The application of cationic metallocene catalysts based on the abovementioned borate anions to a support is described in WO 91/09882. Here, the catalyst system is formed by applying a dialkyl-metallocene
- 15 compound and a Brønsted-acid, quaternary ammonium compound having a noncoordinating anion such as tetrakis(pentafluorophenyl) borate to an inorganic support. The support material is modified beforehand using a trialkylaluminum compound.
- 20 A disadvantage of this method of application to a support is that only a small part of the metallocene used is fixed to the support material by physisorption. When the catalyst system is introduced into the reactor, the metallocene can easily be leached from the support surface. This leads to a partly homogeneous
- 25 polymerization, resulting in an unsatisfactory morphology of the polymer. WO 96/04319 describes a catalyst system in which the cocatalyst is covalently bound to the support material. However, this catalyst system has a low polymerization activity and, in addition, the high sensitivity of the supported cationic
- 30 metallocene catalysts can lead to problems during introduction into the polymerization system.

It is an object of the present invention to provide a chemical product which can be used as cocatalyst in catalyst systems and

35 displays the positive properties of MAO and can also be physisorbed on or covalently bound to a support material. The catalyst system formed therefrom should be able to be activated either before the introduction into the reactor or only in the polymerization autoclave.

40 We have found that this object is achieved by chemical products which are suitable as cocatalysts and are obtainable by reacting a compound of the formula (I),




3

where

- 5 R^1, R^2, R^3 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl or C_7-C_{40} -haloalkylaryl,
- 10 M^1 is an element of main group II or III of the Periodic Table of the Elements and
- 15 m is 0 or 1, with m being 1 when M^1 is an element of main group III and m being 0 when M^1 is an element of main group II,

with a compound of the formula (II),



in which heteroatom-containing substituents R^4X are located on a parent moiety G , where

- 25 R^4 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl, C_7-C_{40} -haloalkylaryl,
- 30 X is an element of main group VI of the Periodic Table of the Elements,
- 35 G is at least divalent C_1-C_{20} -haloalkylene, C_6-C_{40} -haloarylene, C_7-C_{40} -haloarylalkylene, C_7-C_{40} -haloalkylarylene,
- 40 M^2 is an element of main group VI of the Periodic Table of the Elements,
- 45 R^5, R^6 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{10} -alkoxy, C_2-C_{10} -alkenyl, C_7-C_{20} -arylalkyl, C_7-C_{20} -alkylaryl, C_6-C_{10} -aryloxy, C_1-C_{10} -haloalkyl,

4

g is an integer from 2 to 10 and

g is an integer from 1 to 10.

- 5 The present invention also provides a process for preparing this chemical product by reacting a compound of the formula (I),




10 where

15 R^1, R^2, R^3 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl or C_7-C_{40} -haloalkylaryl,

20 M^1 is an element of main group II or III of the Periodic Table of the Elements and

25 m is 0 or 1, with m being 1 when M^1 is an element of main group III and m being 0 when M^1 is an element of main group II,

with a compound of the formula (II),



in which heteroatom-containing substituents R^4X are located on a parent moiety G,

35 where

40 R^4 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl, C_7-C_{40} -haloalkylaryl,

45 X is an element of main group VI of the Periodic Table of the Elements,

G is at least divalent C_1-C_{20} -haloalkylene, C_6-C_{40} -haloarylene, C_7-C_{40} -haloarylalkylene,

5

C₇-C₄₀-haloalkylarylene,

M² is an element of main group VI of the Periodic Table of the Elements,

5

R⁵, R⁶ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₁₀-alkoxy, C₂-C₁₀-alkenyl, C₇-C₂₀-arylalkyl, C₇-C₂₀-alkylaryl, C₆-C₁₀-aryloxy, C₁-C₁₀-haloalkyl,

10

q is an integer from 2 to 10 and

g is an integer from 1 to 10.

15

According to the present invention, preference is given to using compounds of the formula (I) in which R¹, R² and R³ are C₁-C₆-alkyl groups. R¹, R² and R³ are particularly preferably C₁-C₄-alkyl groups. In the formula (I), M¹ is preferably an element of main group III of the Periodic Table of the Elements, in particular boron or aluminum. Very particular preference is given to aluminum.

20

Particularly preferred aluminum compounds of the formula (I) are trimethylaluminum, triethylaluminum, triisopropylaluminum, trihexylaluminum, trioctylaluminum, tri-n-butylaluminum, tri-n-propylaluminum and triisoprenylaluminum. Among these, trimethylaluminum, triethylaluminum and triisopropylaluminum are particularly preferred.

25

30

Particularly preferred boron compounds of the formula (I) are triethylborane and boranes having branched alkyl radicals.

In preferred compounds of the formula (II), the parent moiety G is preferably a partially or fully halogenated C₁-C₂₀-haloalkylene or C₆-C₄₀-haloarylene, where chlorine and/or fluorine are used as halogen. G is particularly preferably a partially or fully fluorinated C₆-C₄₀-arylene.

35

In formula (II), X is preferably oxygen or sulfur, particularly preferably oxygen. Furthermore, R⁴ in formula (II) is preferably hydrogen or C₁-C₂₀-alkyl, particularly preferably hydrogen.

40

In a very particularly preferred embodiment of the invention, q is 2.

45

6

In the compounds of the formula (II), M^2 is preferably oxygen or sulfur, in particular oxygen. R^5 and R^6 are preferably hydrogen or C_1 - C_{20} -alkyl, very particularly preferably hydrogen. The integer g preferably assumes values in the range from 1 to 5 and

5 particularly preferably 1 or 2. In a very particularly preferred embodiment of the invention, g is 1.

In the compounds of the formula (II), $(M^2R^5R^6)_g$ is preferably water or an alcohol. Particular preference is given to water,
10 methanol, ethanol and branched alcohols. Very particular preference is given to using water.

Particularly preferred compounds of the formula (II) in which G is a partially or fully fluorinated C_6 - C_{40} -arylene bear, as
15 substituents R^4X , from two to eight hydroxyl groups.

Nonlimiting examples of chemical compounds of the formula (II) are:

- 20 4,4'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 4,3'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 4,5'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 4,6'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 4,7'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 25 4,8'-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 1,2-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 1,3-dihydroxyoctafluorobiphenyl * $(s \cdot H_2O)$,
- 4,4'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 4,3'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 30 4,5'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 4,6'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 4,7'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 4,8'-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 35 1,2-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 1,3-dihydroxyheptafluorobiphenyl * $(s \cdot H_2O)$,
- 4,4'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 4,3'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 4,5'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 40 4,6'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 4,7'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 4,8'-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 1,2-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,
- 1,3-dihydroxyhexafluorobiphenyl * $(s \cdot H_2O)$,

45

- 4,4'-dihydroxypentafluorobiphenyl * (s*H₂O),
 4,3'-dihydroxypentafluorobiphenyl * (s*H₂O),
 4,5'-dihydroxypentafluorobiphenyl * (s*H₂O),
 5 4,6'-dihydroxypentafluorobiphenyl * (s*H₂O),
 4,7'-dihydroxypentafluorobiphenyl * (s*H₂O),
 4,8'-dihydroxypentafluorobiphenyl * (s*H₂O),
 1,2-dihydroxypentafluorobiphenyl * (s*H₂O),
 1,3-dihydroxypentafluorobiphenyl * (s*H₂O),
 10 4,4'-dihydroxyoctachlorobiphenyl * (s*H₂O),
 4,3'-dihydroxyoctachlorobiphenyl * (s*H₂O),

 4,5'-dihydroxyoctachlorobiphenyl * (s*H₂O),
 4,6'-dihydroxyoctachlorobiphenyl * (s*H₂O),
 15 4,7'-dihydroxyoctachlorobiphenyl * (s*H₂O),
 4,8'-dihydroxyoctachlorobiphenyl * (s*H₂O),
 1,2-dihydroxyoctachlorobiphenyl * (s*H₂O),
 1,3-dihydroxyoctachlorobiphenyl * (s*H₂O),
 4,4'-dihydroxyheptachlorobiphenyl * (s*H₂O),
 20 4,3'-dihydroxyheptachlorobiphenyl * (s*H₂O),

 4,5'-dihydroxyheptachlorobiphenyl * (s*H₂O),
 4,6'-dihydroxyheptachlorobiphenyl * (s*H₂O),
 4,7'-dihydroxyheptachlorobiphenyl * (s*H₂O),
 25 4,8'-dihydroxyheptachlorobiphenyl * (s*H₂O),
 1,2-dihydroxyheptachlorobiphenyl * (s*H₂O),
 1,3-dihydroxyheptachlorobiphenyl * (s*H₂O),
 4,4'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 4,3'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 30 4,5'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 4,6'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 4,7'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 4,8'-dihydroxyhexachlorobiphenyl * (s*H₂O),
 1,2-dihydroxyhexachlorobiphenyl * (s*H₂O),
 35 1,3-dihydroxyhexachlorobiphenyl * (s*H₂O),
 4,4'-dihydroxypentachlorobiphenyl * (s*H₂O),
 4,3'-dihydroxypentachlorobiphenyl * (s*H₂O),
 4,5'-dihydroxypentachlorobiphenyl * (s*H₂O),
 4,6'-dihydroxypentachlorobiphenyl * (s*H₂O),
 40
 4,7'-dihydroxypentachlorobiphenyl * (s*H₂O),
 4,8'-dihydroxypentachlorobiphenyl * (s*H₂O),
 1,2-dihydroxypentachlorobiphenyl * (s*H₂O),
 1,3-dihydroxypentachlorobiphenyl * (s*H₂O),
 45 1,8-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,7-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,6-dihydroxyhexafluoronaphthalene * (s*H₂O),

8

- 1,7-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,5-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,4-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,3-dihydroxyhexafluoronaphthalene * (s*H₂O),
 5 1,2-dihydroxyhexafluoronaphthalene * (s*H₂O),
 1,8-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,7-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,6-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,7-dihydroxyhexachloronaphthalene * (s*H₂O),
 10 1,5-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,4-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,3-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,2-dihydroxyhexachloronaphthalene * (s*H₂O),
 1,8-dihydroxypentafluoronaphthalene * (s*H₂O),
 15 1,7-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,6-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,7-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,5-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,4-dihydroxypentafluoronaphthalene * (s*H₂O),
 20 1,3-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,2-dihydroxypentafluoronaphthalene * (s*H₂O),
 1,8-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,7-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,6-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 25 1,7-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,5-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,4-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,3-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 1,2-dihydroxytetrakisfluoronaphthalene * (s*H₂O),
 30 1,2-dihydroxy-3,4,5,6,7,8,9,10,11,12-decafluoroterphenyl *
 (s*H₂O), 1,3-dihydroxy-2,4,5,6,7,8,9,10,11,12-decafluoroterphenyl
 * (s*H₂O),
 1,4-dihydroxy-2,3,5,6,7,8,9,10,11,12-decafluoroterphenyl *
 (s*H₂O), 1,5-dihydroxy-2,3,4,6,7,8,9,10,11,12-decafluoroterphenyl
 35 * (s*H₂O),
 1,6-dihydroxy-2,3,4,5,7,8,9,10,11,12-decafluoroterphenyl *
 (s*H₂O), 1,7-dihydroxy-2,3,4,5,6,8,9,10,11,12-decafluoroterphenyl
 * (s*H₂O),
 1,8-dihydroxy-2,3,4,5,6,7,9,10,11,12-decafluoroterphenyl *
 40 (s*H₂O), 1,9-dihydroxy-2,3,4,5,6,7,8,10,11,12-decafluoroterphenyl
 * (s*H₂O),
 1,10-dihydroxy-2,3,4,5,6,7,8,9,11,12-decafluoroterphenyl *
 (s*H₂O), 1,11-dihydroxy-2,3,4,5,6,7,8,9,10,12-decafluoroterphenyl
 * (s*H₂O),
 45 1,12-dihydroxy-2,3,4,5,6,7,8,9,10,11,12-decafluoroterphenyl *
 (s*H₂O), 1,9-dihydroxynonafluoroanthracene * (s*H₂O),
 1,2-dihydroxynonafluoroanthracene * (s*H₂O),

9

- 1,3-dihydroxynonafluoroanthracene * (s*H₂O),
 1,4-dihydroxynonafluoroanthracene * (s*H₂O),
 1,5-dihydroxynonafluoroanthracene * (s*H₂O),
 1,6-dihydroxynonafluoroanthracene * (s*H₂O),
 5 1,7-dihydroxynonafluoroanthracene * (s*H₂O),
 1,8-dihydroxynonafluoroanthracene * (s*H₂O),
 1,9-dihydroxynonachloroanthracene * (s*H₂O),
 1,3-dihydroxynonachloroanthracene * (s*H₂O),
 1,4-dihydroxynonachloroanthracene * (s*H₂O),
 10 1,5-dihydroxynonachloroanthracene * (s*H₂O),
 1,6-dihydroxynonachloroanthracene * (s*H₂O),
 1,7-dihydroxynonachloroanthracene * (s*H₂O),
 1,8-dihydroxynonachloroanthracene * (s*H₂O),
 1,9-dihydroxyoctafluoroanthracene * (s*H₂O),
 15 1,2-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,3-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,4-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,5-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,6-dihydroxyoctafluoroanthracene * (s*H₂O),
 20 1,7-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,8-dihydroxyoctafluoroanthracene * (s*H₂O),
 1,9-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,2-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,3-dihydroxyheptafluoroanthracene * (s*H₂O),
 25 1,4-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,5-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,6-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,7-dihydroxyheptafluoroanthracene * (s*H₂O),
 1,8-dihydroxyheptafluoroanthracene * (s*H₂O),
 30 1,9-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,2-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,3-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,4-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,5-dihydroxyhexafluoroanthracene * (s*H₂O),
 35 1,6-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,7-dihydroxyhexafluoroanthracene * (s*H₂O),
 1,8-dihydroxyhexafluoroanthracene * (s*H₂O),

 1,9-dihydroxynonafluorophenanthrene * (s*H₂O),
 40 1,2-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,3-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,4-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,5-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,6-dihydroxynonafluorophenanthrene * (s*H₂O),
 45 1,7-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,8-dihydroxynonafluorophenanthrene * (s*H₂O),
 1,9-dihydroxynonachlorophenanthrene * (s*H₂O),

- 1,3-dihydroxynonachlorophenanthrene * (s*H₂O),
 1,4-dihydroxynonachlorophenanthrene * (s*H₂O),
 1,5-dihydroxynonachlorophenanthrene * (s*H₂O),
 5 1,6-dihydroxynonachlorophenanthrene * (s*H₂O),
 1,7-dihydroxynonachlorophenanthrene * (s*H₂O),
 1,8-dihydroxynonachlorophenanthrene * (s*H₂O),
 1,9-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,2-dihydroxyoctafluorophenanthrene * (s*H₂O),
 10 1,3-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,4-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,5-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,6-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,7-dihydroxyoctafluorophenanthrene * (s*H₂O),
 15 1,8-dihydroxyoctafluorophenanthrene * (s*H₂O),
 1,9-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,2-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,3-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,4-dihydroxyheptafluorophenanthrene * (s*H₂O),
 20 1,5-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,6-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,7-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,8-dihydroxyheptafluorophenanthrene * (s*H₂O),
 1,9-dihydroxyhexafluorophenanthrene * (s*H₂O),
 25 1,2-dihydroxyhexafluorophenanthrene * (s*H₂O),
 1,3-dihydroxyhexafluorophenanthrene * (s*H₂O),
 1,4-dihydroxyhexafluorophenanthrene * (s*H₂O),
 1,5-dihydroxyhexafluorophenanthrene * (s*H₂O),
 1,6-dihydroxyhexafluorophenanthrene * (s*H₂O),
 30 1,7-dihydroxyhexafluorophenanthrene * (s*H₂O),
 1,8-dihydroxyhexafluorophenanthrene * (s*H₂O),

 4,5,4'-trihydroxyheptafluorobiphenyl * (s*H₂O),
 4,5,3'-trihydroxyheptafluorobiphenyl * (s*H₂O),
 35 4,5,5'-trihydroxyheptafluorobiphenyl * (s*H₂O),
 4,5,6'-trihydroxyheptafluorobiphenyl * (s*H₂O),
 3,4,5',7'-tetrahydroxyhexafluorobiphenyl * (s*H₂O),
 3,4,6',8'-tetrahydroxyhexafluorobiphenyl * (s*H₂O),
 3,5,5',7'-tetrahydroxyhexafluorobiphenyl * (s*H₂O),
 40 3,5,3',5'-tetrahydroxyhexafluorobiphenyl * (s*H₂O),

where s is preferably 1, 2, 3, 4, 5, 6, 7, 8, 9, 10.

The present invention also provides a supported catalyst system
 45 in which the chemical products obtainable by reacting compounds
 of the formula (I) with compounds of the formula (II) are used as
 cocatalysts, and provides a process for preparing this catalyst

11

system. In addition, the invention provides a process for preparing polyolefins by polymerization in the presence of the catalyst systems of the present invention.

- 5 The reaction according to the present invention of compounds of the formula (I) with compounds of the formula (II) to give the chemical product of the present invention is generally carried out using the following procedure.
- 10 Firstly, one or more compounds of the formula (I) can be placed in a reaction vessel. The compounds can either be dissolved or suspended in a solvent or can be present as such. Suitable solvents are aliphatic or aromatic hydrocarbons such as n-pentane, isopentane, n-hexane, n-heptane, cyclohexane, 15 isododecane, n-octane, n-nonane, n-decane, petroleum ether, toluene, benzene, o-xylene, m-xylene, p-xylene, 1,2,3-trimethylbenzene, 1,2,4-trimethylbenzene, 1,2,5-trimethylbenzene, 1,3,5-trimethylbenzene, ethylbenzene, propylbenzene, etc. and also ethers such as diethyl ether, methyl 20 tert-butyl ether, dimethoxyethane, diisopropyl ether, di-n-butyl ether, anisole or mixtures thereof. Among these, particular preference is given to aromatic hydrocarbons, in particular toluene, o-xylene, m-xylene, p-xylene, 1,2,3-trimethylbenzene, 1,2,4-trimethylbenzene, 1,2,5-trimethylbenzene and 25 1,3,5-trimethylbenzene. The compounds of the formula (I) and any solvents used are generally placed in the reaction vessel at from -100°C to 300°C, preferably from -80°C to 200°C, particularly preferably from 20°C to 150°C. The compound of the formula (I) is advantageously present in a liquid phase.
- 30 One or more compounds of the formula (II) can subsequently be added. The compounds of the formula (II) can likewise be dissolved or suspended in a solvent or be added as such. Suitable solvents are those described above; preference is given to using 35 the same solvent. The addition can be carried out over a period of from 1 minute to 96 hours. The addition is preferably carried out within a period of from 10 minutes to 8 hours. The temperature of the initial charge during the addition is in the range from -100°C to 200°C, preferably from -80°C to 150°C, 40 particularly preferably from 20°C to 150°C. The temperature is generally selected so that at least one reactant is present in a liquid phase. The subsequent reaction temperature is preferably in a range from 20°C to 150°C. The reaction can be carried out at atmospheric pressure or superatmospheric pressure, although the 45 latter requires appropriate reactors. The molar ratio in which the compounds of the formula (I) and those of the formula (II)

are combined is generally in the range from 1:1000 to 1:0.01, based on the amount of M^1 in the compounds of the formula (I).

5 The molar ratio of compounds of the formula (I) to those of the formula (II) is preferably from 1:100 to 1:0.1, based on the amount of M^1 in the compounds of the formula (I). Particular preference is given to stoichiometric reaction of the compounds of the formulae (I) and (II). The molar ratio here depends on the
10 number g of $((M^2R^5R^6))$ groups. The figures given here assume a value of 1 for g . In the case of higher values of g , a correspondingly smaller amount of compound (II) can be used.

The present invention also provides a process for preparing the
15 products suitable as cocatalysts, in which compounds of the formula (I) are reacted with compounds of the formula (II).

The present invention additionally provides a catalyst system which preferably comprises

20

A) at least one organic transition metal compound,

B) if desired, at least one main group alkyl,

25 C) if desired, at least one support component and

D) at least one chemical product which is obtainable by reacting compounds of the formula (I) with compounds of the formula (II) and preferably comprises compounds of the formula (III).

30


As organic transition metal compound A), preference is given to using metallocene compounds. These can be, for example, bridged or unbridged biscyclopentadienyl complexes as are described, for example, in EP-A-0 129 368, EP-A-0 561 479, EP-A-0 545 304 and
35 EP-A-0 576 970, monocyclopentadienyl complexes such as bridged amidocyclopentadienyl complexes as described, for example, in EP-A-0 416 815, multinuclear cyclopentadienyl complexes as described, for example, in EP-A-0 632 063, π -ligand-substituted tetrahydropentalenes as described, for example, in EP-A-0 659 758
40 or π -ligand-substituted tetrahydroindenes as described, for example, in EP-A-0 661 300. It is also possible to use organic metal compounds in which the complexing ligand contains no cyclopentadienyl units. Examples are diamine complexes of elements of transition groups III and IV of the Periodic Table of
45 the Elements, as are described, for example, in D.H. McConville, et al., Macromolecules, 1996, 29, 5241 and D.H. McConville, et al., J. Am. Chem. Soc., 1996, 118, 10008. Diimine complexes of

13

elements of transition group VIII of the Periodic Table of the Elements (e.g. Ni^{2+} or Pd^{2+} complexes) as described by Brookhart et al., J. Am. Chem. Soc. 1995, 117, 6414 and Brookhart et al., J. Am. Chem. Soc., 1996, 118, 267 can also be used. Furthermore, 2,6-bis(imino)pyridyl complexes of metals of transition group VIII of the Periodic Table of the Elements (e.g. Co^{2+} or Fe^{2+} complexes) as described in Brookhart et al., J. Am. Chem. Soc. 1998, 120, 4049 and Gibson et al., Chem. Commun. 1998, 849 can be used. It is also possible to use metallocene compounds whose complexing ligand contains heterocycles. Examples of such compounds are described in WO 98/22486.

Preferred metallocene compounds are unbridged or bridged compounds of the formula (IV),

15



30

where

M^4 is a metal of transition group III, IV, V or VI of the Periodic Table of the Elements, in particular Ti, Zr or Hf,

35

R^{15} are identical or different and are each a hydrogen atom or $\text{Si}(R^{17})_3$, where R^{17} are identical or different and are each a hydrogen atom or a C_1 - C_{40} group, preferably C_1 - C_{20} -alkyl, C_1 - C_{10} -fluoroalkyl, C_1 - C_{10} -alkoxy, C_6 - C_{20} -aryl, C_6 - C_{10} -fluoroaryl, C_6 - C_{10} -aryloxy, C_2 - C_{10} -alkenyl, C_7 - C_{40} -arylalkyl, C_7 - C_{40} -alkylaryl or C_8 - C_{40} -arylalkenyl, or R^{15} is a C_1 - C_{30} group, preferably C_1 - C_{25} -alkyl, such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C_2 - C_{25} -alkenyl, C_3 - C_{15} -alkylalkenyl, C_6 - C_{24} -aryl, C_5 - C_{24} -heteroaryl, C_7 - C_{30} -arylalkyl, C_7 - C_{30} -alkylaryl, fluorinated C_1 - C_{25} -alkyl, fluorinated C_6 - C_{24} -aryl, fluorinated C_7 - C_{30} -arylalkyl, fluorinated C_7 - C_{30} -alkylaryl or C_1 - C_{12} -alkoxy, or two or more

45

14

radicals R^{15} may be joined in such a way that the radicals R^{15} and the atoms of the cyclopentadienyl ring which connect them form a C_4-C_{24} -ring system which may in turn be substituted,

- 5 R^{16} are identical or different and are each a hydrogen atom or $Si(R^{18})_3$, where R^{18} are identical or different and are each a hydrogen atom or a C_1-C_{40} group, preferably C_1-C_{20} -alkyl, C_1-C_{10} -fluoroalkyl, C_1-C_{10} -alkoxy, C_6-C_{14} -aryl, C_6-C_{10} -fluoroaryl, C_6-C_{10} -aryloxy, C_2-C_{10} -alkenyl, C_7-C_{40} -arylalkyl, C_7-C_{40} -alkylaryl or C_8-C_{40} -arylalkenyl, or
- 10 R^{16} is a C_1-C_{30} group, preferably C_1-C_{25} -alkyl such as methyl, ethyl, tert-butyl, cyclohexyl or octyl, C_2-C_{25} -alkenyl, C_3-C_{15} -alkylalkenyl, C_6-C_{24} -aryl, C_5-C_{24} -heteroaryl, C_5-C_{24} -alkylheteroaryl, C_7-C_{30} -arylalkyl, C_7-C_{30} -alkylaryl, fluorinated C_1-C_{25} -alkyl, fluorinated C_6-C_{24} -aryl, fluorinated C_7-C_{30} -arylalkyl, fluorinated C_7-C_{30} -alkylaryl or
- 15 C_1-C_{12} -alkoxy, or two or more radicals R^{16} may be joined in such a way that the radicals R^{16} and the atoms of the cyclopentadienyl ring which connect them form a C_4-C_{24} -ring system which may in turn be substituted,
- 20

1 is 5 when $v = 0$, and 1 is 4 when $v = 1$,

m is 5 when $v = 0$, and m is 4 when $v = 1$,

25

L^1 may be identical or different and are each a hydrogen atom, a C_1-C_{10} -hydrocarbon group such as C_1-C_{10} -alkyl or C_6-C_{10} -aryl, a halogen atom or OR^{19} , SR^{19} , $OSi(R^{19})_3$, $Si(R^{19})_3$, $P(R^{19})_2$ or $N(R^{19})_2$, where R^{19} is a halogen atom, a C_1-C_{10} -alkyl group, a

30 halogenated C_1-C_{10} -alkyl group, a C_6-C_{20} -aryl group or a halogenated C_6-C_{20} -aryl group, or L^1 is a toluenesulfonyl, trifluoroacetyl, trifluoroacetoxyl, trifluoromethanesulfonyl, nonafluorobutanesulfonyl or 2,2,2-trifluoroethanesulfonyl group,

35

o is an integer from 1 to 4, preferably 2,

z is a bridging structural element between the two cyclopentadienyl rings and v is 0 or 1.

40

Examples of Z are $M^5R^{20}R^{21}$ groups, where M^5 is carbon, silicon, germanium, boron or tin and R^{20} and R^{21} are identical or different and are each a C_1-C_{20} -hydrocarbon-containing group such as C_1-C_{10} -alkyl, C_6-C_{14} -aryl or trimethylsilyl. Z is preferably CH_2 ,

- 45 CH_2CH_2 , $CH(CH_3)CH_2$, $CH(C_4H_9)C(CH_3)_2$, $C(CH_3)_2$, $(CH_3)_2Si$, $(CH_3)_2Ge$, $(CH_3)_2Sn$, $(C_6H_5)_2Si$, $(C_6H_5)(CH_3)Si$, $(C_6H_5)_2Ge$, $(CH_3)_3Si-Si(CH_3)(C_6H_5)_2Sn$, $(CH_2)_4Si$, $CH_2Si(CH_3)_2$, $MeSi-Si(Me)_3$,

15

o-C₆H₄ or 2,2'-(C₆H₄)₂, or a 1,2-(1-methylethanediy1),
 1,2-(1,1-dimethylethanediy1) or 1,2(1,2-dimethylethanediy1)
 bridge. It is also possible for Z together with one or more
 radicals R¹⁵ and/or R¹⁶ to form a monocyclic or polycyclic ring
 5 system.

Preference is given to chiral bridged metallocene compounds of
 the formula (IV), particularly those in which v is 1 and one or
 both cyclopentadienyl rings are substituted so that they form an
 10 indenyl ring. The indenyl ring is preferably substituted,
 particularly in the 2 position, the 4 position, the 2,4,5
 positions, the 2,4,6 positions, the 2,4,7 positions or the
 2,4,5,6 positions, by C₁-C₂₀ groups such as C₁-C₁₀-alkyl or
 C₆-C₂₀-aryl, where two or more substituents of the indenyl ring
 15 may also together form a ring system.

Chiral bridged metallocene compounds of the formula (IV) can be
 used as pure racemic or pure meso compounds. However, it is also
 possible to use mixtures of a racemic compound and a meso
 20 compound.

Examples of metallocene compounds are:

- dimethylsilanediy1bis(indenyl)zirconium dichloride
 25 dimethylsilanediy1bis(4-naphthylindenyl)zirconium dichloride
 dimethylsilanediy1bis(2-methylbenzoindenyl)zirconium dichloride
 30 dimethylsilanediy1bis(2-methylindenyl)zirconium dichloride
 dimethylsilanediy1bis(2-methyl-4-(1-naphthyl)indenyl)zirconium
 dichloride
 35 dimethylsilanediy1bis(2-methyl-4-(2-naphthyl)indenyl)zirconium
 dichloride
 dimethylsilanediy1bis(2-methyl-4-phenylindenyl)zirconium
 dichloride
 40 dimethylsilanediy1bis(2-methyl-4-tert-butylindenyl)zirconium
 dichloride
 dimethylsilanediy1bis(2-methyl-4-isopropylindenyl)zirconium
 45 dichloride

16

dimethylsilanediylbis(2-methyl-4-ethylindenyl)zirconium
dichloride

dimethylsilanediylbis(2-methyl-4- α -acenaphthindenyl)zirconium
5 dichloride

dimethylsilanediylbis(2,4-dimethylindenyl)zirconium dichloride

dimethylsilanediylbis(2-ethylindenyl)zirconium dichloride
10

dimethylsilanediylbis(2-ethyl-4-ethylindenyl)zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-phenylindenyl)zirconium
dichloride

15 dimethylsilanediylbis(2-methyl-4,5-benzindenyl)zirconium
dichloride

dimethylsilanediylbis(2-methyl-4,6-diisopropylindenyl)zirconium
20 dichloride

dimethylsilanediylbis(2-methyl-4,5-diisopropylindenyl)zirconium
dichloride

25 dimethylsilanediylbis(2,4,6-trimethylindenyl)zirconium dichloride

dimethylsilanediylbis(2,5,6-trimethylindenyl)zirconium dichloride

dimethylsilanediylbis(2,4,7-trimethylindenyl)zirconium dichloride
30

dimethylsilanediylbis(2-methyl-5-isobutylindenyl)zirconium
dichloride

dimethylsilanediylbis(2-methyl-5-t-butylindenyl)zirconium
35 dichloride

methyl(phenyl)silanediylbis(2-methyl-4-phenylindenyl)zirconium
dichloride

40 methyl(phenyl)silanediylbis(2-methyl-4,6-diisopropylindenyl)-
zirconium dichloride

methyl(phenyl)silanediylbis(2-methyl-4-isopropylindenyl)zirconium
dichloride

45

- methyl(phenyl)silanediyibis(2-methyl-4,5-benzoindenyl)zirconium dichloride
- methyl(phenyl)silanediyibis(2-methyl-4,5-(methylbenzo)indenyl)-
5 zirconium dichloride
- methyl(phenyl)silanediyibis(2-methyl-4,5-(tetramethylbenzo)-indenyl)zirconium dichloride
- 10 methyl(phenyl)silanediyibis(2-methyl-4- α -acenaphthindenyl)-zirconium dichloride
- methyl(phenyl)silanediyibis(2-methylindenyl)zirconium dichloride
- 15 methyl(phenyl)silanediyibis(2-methyl-5-isobutylindenyl)zirconium dichloride
- 1,2-ethanediyibis(2-methyl-4-phenylindenyl)zirconium dichloride
- 20 1,4-butanediyibis(2-methyl-4-phenylindenyl)zirconium dichloride
- 1,2-ethanediyibis(2-methyl-4,6-diisopropylindenyl)zirconium dichloride
- 25 1,4-butanediyibis(2-methyl-4-isopropylindenyl)zirconium dichloride
- 1,4-butanediyibis(2-methyl-4,5-benzoindenyl)zirconium dichloride
- 30 1,2-ethanediyibis(2-methyl-4,5-benzoindenyl)zirconium dichloride
- 1,2-ethanediyibis(2,4,7-trimethylindenyl)zirconium dichloride
- 1,2-ethanediyibis(2-methylindenyl)zirconium dichloride
- 35 1,4-butanediyibis(2-methylindenyl)zirconium dichloride
- [4-(η^5 -cyclopentadienyl)-4,6,6-trimethyl-(η^5 -4,5-tetrahydropentalene)]dichlorozirconium
- 40 [4-(η^5 -3'-trimethylsilylcyclopentadienyl)-4,6,6-trimethyl-(η^5 -4,5-tetrahydropentalene)]dichlorozirconium
- [4-(η^5 -3'-isopropylcyclopentadienyl)-4,6,6-trimethyl-(η^5 -4,5-tetrahydropentalene)]dichlorozirconium
- 45

18

{4-(η^5 -cyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorotitanium

{4-(η^5 -cyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorozirconium

{4-(η^5 -cyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorohafnium

10 {4-(η^5 -3'-tert-butylcyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorotitanium

4-(η^5 -3'-isopropylcyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorotitanium

15

4-(η^5 -3'-methylcyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorotitanium

20 4-(η^5 -3'-trimethylsilylcyclopentadienyl)-2-trimethylsilyl-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorotitanium

4-(η^5 -3'-tert-butylcyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)}dichlorozirconium

25 {tert-butylamido}{tetramethyl- η^5 -cyclopentadienyl}dimethylsilyl-dichlorotitanium

{tert-butylamido}{tetramethyl- η^5 -cyclopentadienyl)-1,2-ethanediyl-dichlorotitanium

30

{methylamido}{tetramethyl- η^5 -cyclopentadienyl}dimethylsilyl-dichlorotitanium

35 {methylamido}{tetramethyl- η^5 -cyclopentadienyl)-1,2-ethanediyl-dichlorotitanium

{tert-butylamido}-(2,4-dimethyl-2,4-pentadien-1-yl)-dimethylsilyl-dichlorotitanium

40 bis-(cyclopentadienyl)zirconium dichloride

bis-(n-butylcyclopentadienyl)zirconium dichloride

bis-(1,3-dimethylcyclopentadienyl)zirconium dichloride

45

19

tetrachloro-[1-[bis(η^5 -1H-inden-1-ylidene)methylsilyl]-3- η^5 -cyclopenta-2,4-dien-1-ylidene)-3- η^5 -9H-fluoren-9-ylidene]butane]-dizirconium

- 5 tetrachloro-[2-[bis(η^5 -2-methyl-1H-inden-1-ylidene)methoxysilyl]-5-(η^5 -2,3,4,5-tetramethylcyclopenta-2,4-dien-1-ylidene)-5-(η^5 -9H-fluoren-9-ylidene)hexane]dizirconium

- 10 tetrachloro-[1-[bis(η^5 -1H-inden-1-ylidene)methylsilyl]-6-(η^5 -cyclopenta-2,4-dien-1-ylidene)-6-(η^5 -9H-fluoren-9-ylidene)-3-oxaheptane]dizirconium

dimethylsilanediylbis(2-methyl-4-(tert-butylphenylindenyl))-zirconium dichloride

- 15 dimethylsilanediylbis(2-methyl-4-(4-methylphenylindenyl))zirconium dichloride

- 20 dimethylsilanediylbis(2-methyl-4-(4-ethylphenylindenyl))zirconium dichloride

dimethylsilanediylbis(2-methyl-4-(4-trifluoromethylphenylindenyl))-zirconium dichloride

- 25 dimethylsilanediylbis(2-methyl-4-(4-methoxyphenylindenyl))-zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4-tert-butylphenylindenyl))-zirconium dichloride

- 30 dimethylsilanediylbis(2-ethyl-4-(4-methylphenylindenyl))zirconium dichloride

- 35 dimethylsilanediylbis(2-ethyl-4-(4-ethylphenylindenyl))zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4-trifluoromethylphenylindenyl))-zirconium dichloride

- 40 dimethylsilanediylbis(2-ethyl-4-(4-methoxyphenylindenyl))zirconium dichloride

dimethylsilanediylbis(2-methyl-4-(4-tert-butylphenylindenyl))-dimethylzirconium

- 45

20

dimethylsilanediylbis(2-methyl-4-(4-methylphenylindenyl)dimethyl-
zirconium

dimethylsilanediylbis(2-methyl-4-(4-ethylphenylindenyl)dimethyl-
5 zirconium

dimethylsilanediylbis(2-methyl-4-(4-trifluoromethylphenylindenyl)
dimethylzirconium

10 dimethylsilanediylbis(2-methyl-4-(4-methoxyphenylindenyl)dimethyl
zirconium

dimethylsilanediylbis(2-ethyl-4-(4-tert-butylphenylindenyl)-
dimethylzirconium

15

dimethylsilanediylbis(2-ethyl-4-(4-methylphenylindenyl)dimethyl-
zirconium

dimethylsilanediylbis(2-ethyl-4-(4-ethylphenylindenyl)diethyl-
20 zirconium

dimethylsilanediylbis(2-ethyl-4-(4-trifluoromethylphenylindenyl)d
imethylzirconium

25 dimethylsilanediylbis(2-ethyl-4-(4-methoxyphenylindenyl)dimethyl-
zirconium

dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

30

dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
hafnium dichloride

dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
35 titanium dichloride

dimethylsilanediylbis(2-methyl-4-(4'-methylphenyl)indenyl)-
zirconium dichloride

40 dimethylsilanediylbis(2-methyl-4-(4'-n-propylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-methyl-4-(4'-n-butylphenyl)indenyl)-
zirconium dichloride

45

21

dimethylsilanediylbis(2-methyl-4-(4'-hexylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-methyl-4-(4'-sec-butylphenyl)indenyl)-
5 zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-phenyl)indenyl)zirconium
dichloride

10 dimethylsilanediylbis(2-ethyl-4-(4'-methylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4'-ethylphenyl)indenyl)-
zirconium dichloride

15

dimethylsilanediylbis(2-ethyl-4-(4'-n-propylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4'-n-butylphenyl)indenyl)-
20 zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4'-hexylphenyl)indenyl)zirconium
dichloride

25 dimethylsilanediylbis(2-ethyl-4-(4'-pentylphenyl)indenyl)
-zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4'-cyclohexylphenyl)indenyl)
-zirconium dichloride

30

dimethylsilanediylbis(2-ethyl-4-(4'-sec-butylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
35 zirconium dichloride

dimethylsilanediylbis(2-n-propyl-4-phenyl)indenyl)zirconium
dichloride

40 dimethylsilanediylbis(2-n-propyl-4-(4'-methylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-n-propyl-4-(4'-ethylphenyl)indenyl)-
zirconium dichloride

45

22

dimethylsilanediylbis(2-n-propyl-4-(4'-isopropylphenyl)indenyl)-
zirconium dichloride

5 dimethylsilanediylbis(2-n-propyl-4-(4'-n-butylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-n-propyl-4-(4'-hexylphenyl)indenyl)-
zirconium dichloride

10 dimethylsilanediylbis(2-n-propyl-4-(4'-cyclohexylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-n-propyl-4-(4'-sec-butylphenyl)indenyl)-
zirconium dichloride

15 dimethylsilanediylbis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

20 dimethylsilanediylbis(2-n-butyl-4-phenyl)indenyl)zirconium
dichloride

dimethylsilanediylbis(2-n-butyl-4-(4'-methylphenyl)indenyl)-
zirconium dichloride

25 dimethylsilanediylbis(2-n-butyl-4-(4'-ethylphenyl)indenyl)-
zirconium dichloride

30 dimethylsilanediylbis(2-n-butyl-4-(4'-n-propylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-n-butyl-4-(4'-isopropylphenyl)indenyl)-
zirconium dichloride

35 dimethylsilanediylbis(2-n-butyl-4-(4'-n-butylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-n-butyl-4-(4'-hexylphenyl)indenyl)-
zirconium dichloride

40 dimethylsilanediylbis(2-n-butyl-4-(4'-cyclohexylphenyl)indenyl)-
zirconium dichloride

45 dimethylsilanediylbis(2-n-butyl-4-(4'-sec-butylphenyl)indenyl)-
zirconium dichloride

23

dimethylsilanediylbis(2-n-butyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-hexyl-4-phenyl)indenyl)zirconium
5 dichloride

dimethylsilanediylbis(2-hexyl-4-(4'-methylphenyl)indenyl)-
zirconium dichloride

10 dimethylsilanediylbis(2-hexyl-4-(4'-ethylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-hexyl-4-(4'-n-propylphenyl)indenyl)-
zirconium dichloride

15

dimethylsilanediylbis(2-hexyl-4-(4'-isopropylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-hexyl-4-(4'-n-butylphenyl)indenyl)-
20 zirconium dichloride

dimethylsilanediylbis(2-hexyl-4-(4'-hexylphenyl)indenyl)zirconium
dichloride

25 dimethylsilanediylbis(2-hexyl-4-(4'-cyclohexylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-hexyl-4-(4'-sec-butylphenyl)indenyl)-
zirconium dichloride

30

dimethylsilanediylbis(2-hexyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
35 zirconium bis(dimethylamide)

dimethylsilanediylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
dibenzylzirconium

40 dimethylsilanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
dimethylzirconium

dimethylgermanediylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

45

24

dimethylgermanediylbis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
hafnium dichloride

dimethylgermanediylbis(2-propyl-4-(4'-tert-butylphenyl)indenyl)-
5 titanium dichloride

dimethylgermanediylbis(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

10 ethylidenebis(2-ethyl-4-phenyl)indenyl)zirconium dichloride

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium
dichloride

15 ethylidenebis(2-n-propyl-4-(4'-tert-butylphenyl)indenyl)zirconium
dichloride

ethylidenebis(2-n-butyl-4-(4'-tert-butylphenyl)indenyl)titanium
dichloride

20

ethylidenebis(2-hexyl-4-(4'-tert-butylphenyl)indenyl)dibenzyl-
zirconium

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)dibenzyl-
25 hafnium

ethylidenebis(2-methyl-4-(4'-tert-butylphenyl)indenyl)dibenzyl-
titanium

30 ethylidenebis(2-methyl-4-(4'-tert-butylphenyl)indenyl)zirconium
dichloride

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)dimethyl
hafnium

35

ethylidenebis(2-n-propyl-4- α -phenyl)indenyl)dimethyltitanium

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)zirconium
bis(dimethylamide)

40

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)hafnium
bis(dimethylamide)

ethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)titanium
45 bis(dimethylamide)

25

methylethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

methylethylidenebis(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
5 hafniumdichloride

phenylphosphinediyl(2-ethyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

10 phenylphosphinediyl(2-methyl-4-(4'-tert-butylphenyl)indenyl)-
zirconium dichloride

phenylphosphinediyl(2-ethyl-4-(4'-tert-butylphenyl)indenyl)
zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-
methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-
20 methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-
methylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-
(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-
(4'-methylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-
(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-
35 methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-
methylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-
methyl-4-(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-
methyl-4-(4'-methylphenylindenyl)zirconium dichloride

45

26

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

20

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-methylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

35

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

45

27

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

15 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

30 dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-ethylphenylindenyl)zirconium dichloride

45

28

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

45

29

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-n-propylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

45

30

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-isopropylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

45

31

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

20

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

35

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-n-butylphenylindenyl)zirconium dichloride

45

32

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

15 dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

30 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

45

33

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-s-butylphenylindenyl)zirconium dichloride

15 dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

30 dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

45

34

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

45

35

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-n-pentylphenylindenyl)zirconium dichloride

45

36

- dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 5 dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 10 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 15 dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 20 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 25 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 30 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 35 dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 40 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride
- 45

37

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-n-hexylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

45

38

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

15 dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-cyclohexylphenylindenyl)zirconium dichloride

30 dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

45

0732/00036

39

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-trimethylsilylphenylindenyl)zirconium dichloride

45

40

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

20 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride

45

41

- dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- 5 dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- 10 dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- 15 dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-adamantylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- 20 tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- 25 dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- 30 dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- 35 (4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- 40 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride
- dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium
- 45 dichloride

42

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

- 5 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

10

dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

- 15 dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

- 20 dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

25

dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

- 30 dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-tris(trifluoromethyl)methylphenylindenyl)zirconium dichloride

- 35 dimethylsilanediyl(2-methyl-4-azapentalene)(2-ethyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5,6-dihydro-4-azapentalene)(2-ethyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

40

dimethylsilanediyl(2-methyl-4-azapentalene)(2-ethyl-4-(4'-tert-butylphenyltetrahydroindenyl)zirconium dichloride

- 45 dimethylsilanediyl(2-methyl-5-azapentalene)(2-n-butyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

43

ethylidene(2-methyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-trimethylsilyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-tolyl-5-azapentalene)(2-n-propyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

10 dimethylgermanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

methylethylidene(2,5-dimethyl-4-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2,5-diisopropyl-6-azapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2,6-dimethyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

20

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(6'-tert-butylanthracenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-(6'-tert-butylanthracenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-4-phosphapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

30

diphenylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

dimethylphenylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

35

ethylidene(2,5-dimethyl-4-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

40 dimethylmethylidene(2,5-dimethyl-6-thiapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

diphenylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

45

44

diphenylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-(4'-tert-butylphenylindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-4-azapentalene)(2-methylindenyl)-zirconium dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(2-methylindenyl)-zirconium dichloride

10 dimethylsilanediyl(2-methyl-6-azapentalene)(2-methylindenyl)-zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methylindenyl)zirconium dichloride

15 dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methylindenyl)zirconium dichloride

20 dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methylindenyl)-zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methylindenyl)-zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methylindenyl)zirconium dichloride

30 dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methylindenyl)zirconium dichloride

35 dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methylindenyl)-zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methylindenyl)-zirconium dichloride

40 dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methylindenyl)-zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methylindenyl)zirconium dichloride

45

45

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methylindenyl)
zirconium dichloride

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methylindenyl)-
5 zirconium dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methylindenyl)-
zirconium dichloride

10 dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methylindenyl)-
zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methylindenyl)-
zirconium dichloride

15

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methylindenyl)-
zirconium dichloride

dimethylsilanediyl(2-methyl-4-azapentalene)(indenyl)zirconium
20 dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(indenyl)zirconium
dichloride

25 dimethylsilanediyl(2-methyl-6-azapentalene)(indenyl)zirconium
dichloride

dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(indenyl)-
zirconium dichloride

30

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(indenyl)-
zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(indenyl)-
35 zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(indenyl)zirconium
dichloride

40 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(indenyl)zirconium
dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(indenyl)
zirconium dichloride

45

46

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(indenyl)
zirconium dichloride

dimethylsilanediyl(2-methyl-4-thiapentalene)(indenyl)zirconium
5 dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(indenyl)zirconium
dichloride

10 dimethylsilanediyl(2-methyl-6-thiapentalene)(indenyl)zirconium
dichloride

dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(indenyl)-
zirconium dichloride

15

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(indenyl)-
zirconium dichloride

dimethylsilanediyl(2-methyl-4-oxapentalene)(indenyl)zirconium
20 dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(indenyl)zirconium
dichloride

25 dimethylsilanediyl(2-methyl-6-oxapentalene)(indenyl)zirconium
dichloride

dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(indenyl)zirconium
dichloride

30

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(indenyl)zirconium
dichloride

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4-phenyl-
35 indenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4-phenyl-
indenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4-phenyl-
indenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4-
phenylindenyl)zirconium dichloride

45

47

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

10 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

15

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

25 dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

30

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

35

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

45

48

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4-phenylindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-4-azapentalene)(2-methyl-4,5-benzo-5 indenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-azapentalene)(2-methyl-4,5-benzo-indenyl)zirconium dichloride

10 dimethylsilanediyl(2-methyl-6-azapentalene)(2-methyl-4,5-benzo-indenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-4-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

15

dimethylsilanediyl(2-methyl-N-phenyl-5-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-N-phenyl-6-azapentalene)(2-methyl-20 4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

25 dimethylsilanediyl(2,5-dimethyl-6-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-N-phenyl-4-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

30

dimethylsilanediyl(2,5-dimethyl-N-phenyl-6-azapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-4-thiapentalene)(2-methyl-4,5-35 benzoindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-thiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

40 dimethylsilanediyl(2-methyl-6-thiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-thiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

45

49

dimethylsilanediyl(2,5-dimethyl-6-thiapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

5 dimethylsilanediyl(2-methyl-4-oxapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2-methyl-5-oxapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

10 dimethylsilanediyl(2-methyl-6-oxapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

dimethylsilanediyl(2,5-dimethyl-4-oxapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

15

dimethylsilanediyl(2,5-dimethyl-6-oxapentalene)(2-methyl-4,5-benzoindenyl)zirconium dichloride

20 dimethylsilanediylbis(2-methyl-4-azapentalene)zirconium dichloride

dimethylsilanediylbis(2-methyl-5-azapentalene)zirconium dichloride

25 dimethylsilanediylbis(2-methyl-6-azapentalene)zirconium dichloride

dimethylsilanediylbis(2-methyl-N-phenyl-4-azapentalene)zirconium dichloride

30

dimethylsilanediylbis(2-methyl-N-phenyl-5-azapentalene)zirconium dichloride

35 dimethylsilanediylbis(2-methyl-N-phenyl-6-azapentalene)zirconium dichloride

dimethylsilanediylbis(2,5-dimethyl-4-azapentalene)zirconium dichloride

40 dimethylsilanediylbis(2,5-dimethyl-6-azapentalene)zirconium dichloride

dimethylsilanediylbis(2,5-dimethyl-N-phenyl-4-azapentalene)-zirconium dichloride

45

50

dimethylsilanediylbis(2,5-dimethyl-N-phenyl-6-azapentalene)-
zirconium dichloride

dimethylsilanediylbis(2-methyl-4-thiapentalene)zirconium
5 dichloride

dimethylsilanediylbis(2-methyl-5-thiapentalene)zirconium
dichloride

10 dimethylsilanediylbis(2-methyl-6-thiapentalene)zirconium
dichloride

dimethylsilanediylbis(2,5-dimethyl-4-thiapentalene)zirconium
dichloride

15
dimethylsilanediylbis(2,5-dimethyl-6-thiapentalene)zirconium
dichloride

dimethylsilanediylbis(2-methyl-4-oxapentalene)zirconium
20 dichloride

dimethylsilanediylbis(2-methyl-5-oxapentalene)zirconium
dichloride

25 dimethylsilanediylbis(2-methyl-6-oxapentalene)zirconium
dichloride

dimethylsilanediylbis(2,5-dimethyl-4-oxapentalene)zirconium
dichloride

30
dimethylsilanediylbis(2,5-dimethyl-6-oxapentalene)zirconium
dichloride

Further examples of metallocenes which can be used in the process
35 of the present invention are metallocenes from the above list in
which the zirconium fragment "-zirconium dichloride" is replaced
by

zirconium monochloride mono(2,4-di-tert-butylphenoxide)
40

zirconium monochloride mono(2,6-di-tert-butylphenoxide)

zirconium monochloride mono(3,5-di-tert-butylphenoxide)

45 zirconium monochloride mono(2,6-di-sec-butylphenoxide)

51

- zirconium monochloride mono(2,4-dimethylphenoxide)
- zirconium monochloride mono(2,3-dimethylphenoxide)
- 5 zirconium monochloride mono(2,5-dimethylphenoxide)
- zirconium monochloride mono(2,6-dimethylphenoxide)
- zirconium monochloride mono(3,4-dimethylphenoxide)
- 10 zirconium monochloride mono(3,5-dimethylphenoxide)
- zirconium monochloride monophenoxide
- 15 zirconium monochloride mono(2-methylphenoxide)
- zirconium monochloride mono(3-methylphenoxide)
- zirconium monochloride mono(4-methylphenoxide)
- 20 zirconium monochloride mono(2-ethylphenoxide)
- zirconium monochloride mono(3-ethylphenoxide)
- 25 zirconium monochloride mono(4-ethylphenoxide)
- zirconium monochloride mono(2-sec-butylphenoxide)
- zirconium monochloride mono(2-tert-butylphenoxide)
- 30 zirconium monochloride mono(3-tert-butylphenoxide)
- zirconium monochloride mono(4-sec-butylphenoxide)
- 35 zirconium monochloride mono(4-tert-butylphenoxide)
- zirconium monochloride mono(2-isopropyl-5-methylphenoxide)
- zirconium monochloride mono(4-isopropyl-3-methylphenoxide)
- 40 zirconium monochloride mono(5-isopropyl-2-methylphenoxide)
- zirconium monochloride mono(5-isopropyl-3-methylphenoxide)
- 45 zirconium monochloride mono(2,4-bis-(2-methyl-2-butyl)phenoxide)

52

zirconium monochloride mono(2,6-di-tert-butyl-4-methylphenoxide)

zirconium monochloride mono(4-nonylphenoxide)

5 zirconium monochloride mono(1-naphthoxide)

zirconium monochloride mono(2-naphthoxide)

zirconium monochloride mono(2-phenylphenoxide)

10

zirconium monochloride mono(tert-butoxide)

zirconium monochloride mono(N-methylanilide)

15 zirconium monochloride mono(2-tert-butylanilide)

zirconium monochloride mono(tert-butylamide)

zirconium monochloride mono(di-isopropylamide)

20

zirconium monochloride monomethyl


zirconium monochloride monobenzyl

25 zirconium monochloride mononeopentyl.

Also preferred are the corresponding dimethyl zirconium compounds and the corresponding zirconium- η^4 -butadiene compounds.

30 The preferred catalyst system of the present invention comprises at least one main group alkyl B), where B) is particularly preferably a compound of the formula (V), usually an organometallic compound, which can be reacted in any stoichiometric ratio with compounds of the formula (III) and

35 (IV).



45

(V)

53

The radicals R^{20} in formula (V) can be identical or different and are each a halogen atom, a hydrogen atom, a C_1-C_{40} group, preferably C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl or C_7-C_{40} -haloalkylaryl. R^{20} are preferably C_1-C_6 -alkyl groups, particularly preferably C_1-C_4 -alkyl groups.

For the reaction of compounds of the formula (III) and (IV) with compounds of the formula (V), the compounds can be dissolved or suspended in a solvent. However, the reaction can also be carried out in the absence of solvent or suspension medium. Suitable solvents are those described above; preference is given to using the same solvent. The reaction is generally carried out for from 1 minute to 96 hours, preferably from 10 minutes to 8 hours. The temperature of the initial charge during the addition is from -100°C to 200°C , preferably from -80°C to 150°C , particularly preferably from 20°C to 150°C . The temperature is selected so that at least one reactant is present in a liquid phase. The subsequent reaction temperature is preferably in a range from 20°C to 150°C . Furthermore, the reaction can be carried out under atmospheric pressure or under superatmospheric pressure, but the latter requires appropriate reactors. The molar ratio in which the compounds of the formula (III) and (IV) are combined with the chemical compound of the formula (V) is from 1000:1 to 0.01:1, based on the amount of M^3 or M^4 in the compounds of the formulae (III) and (IV) used.

Preference is given to a molar ratio of compounds of the formulae (III) and (IV) to the chemical compound of the formula (V) of from 100:1 to 1:1, based on the amount of M^3 or M^4 in the compounds of the formulae (III) and (IV) used.

In the preparation of the catalyst system of the present invention, a molar ratio of aluminum in the compounds of the formula (III) to M^4 in the compounds of the formula (IV) of from 10,000 to 0.01 is employed. Preference is given to using a molar ratio of from 1000 to 0.1, very particularly preferably from 100 to 1. For this purpose, a compound of the formula (V) can be additionally added in a molar ratio of $\text{Al}:M^4$ of from 10,000 to 0.01. Preference is given to using a molar ratio of from 1000 to 0.1, very particularly preferably from 100 to 1.

The compounds can be brought into contact with one another in any conceivable combination. One possible method is to dissolve or suspend an organic transition metal compound of the formula (IV) in an aliphatic or aromatic solvent such as toluene, heptane, tetrahydrofuran or diethyl ether. A compound of the formula (V)

54

is then added in dissolved or suspended form. The reaction time is from 1 minute to 24 hours, preferably from 5 minutes to 120 minutes. The reaction temperature is from -10°C to $+200^{\circ}\text{C}$, preferably from 0°C to 50°C . Subsequently, an organoaluminum compound of the formula (III) is added either as such or in dissolved or suspended form. The reaction time is from 1 minute to 24 hours, preferably from 5 minutes to 120 minutes. The reaction temperature is from -10°C to $+200^{\circ}\text{C}$, preferably from 0°C to 50°C . The individual components can also be introduced successively, in any order, into the polymerization vessel.

If desired, the catalyst system of the present invention can also be used in supported form. For this purpose, the catalyst system of the present invention can be reacted with a support component.

The preferred catalyst system of the present invention comprises a support component C) which may be any organic or inorganic, inert solid. Particular preference is given to porous supports such as talc, inorganic oxides, mixed oxides and finely divided polymer powders (e.g. polyolefins).

Suitable inorganic oxides may be found among the oxides of elements of main groups II-VI and transition groups III-IV of the Periodic Table of the Elements. Examples of oxides preferred as supports include silicon dioxide, aluminum oxide and also mixed oxides of the two elements and corresponding oxide mixtures. Other inorganic oxides which can be used either alone or in combination with the abovementioned preferred oxidic supports are, for example, MgO , ZrO_2 , TiO_2 or B_2O_3 .

The support materials used generally have a specific surface area in the range from 10 to $1000\text{ m}^2/\text{g}$, a pore volume in the range from 0.1 to 5 ml/g and a mean particle size of from 1 to 500 μm . Preference is given to supports having a specific surface area in the range from 50 to 500 μm , a pore volume in the range from 0.5 to 3.5 ml/g and a mean particle size in the range from 5 to 350 μm . Particular preference is given to supports having a specific surface area in the range from 200 to $400\text{ m}^2/\text{g}$, a pore volume in the range from 0.8 to 3.0 ml/g and a mean particle size of from 10 to 200 μm .

If the support material used naturally has a low moisture content or residual solvent content, dehydration or drying before use can be omitted. If this is not the case, for example when using silica gel as support material, dehydration or drying is advisable. Thermal dehydration or drying of the support material can be carried out under reduced pressure with simultaneous inert

55

gas blanketing (e.g. nitrogen). The drying temperature is in the range from 100 to 1000°C, preferably from 200 to 800°C. In this case, the parameter pressure is not critical. The duration of the drying process can be from 1 to 24 hours. Shorter or longer drying times are possible, provided that equilibrium with the hydroxyl groups on the support surface can be established under the conditions selected, which normally takes from 4 to 8 hours.

Dehydration or drying of the support material can also be carried out by chemical means, by reacting the adsorbed water and the hydroxyl groups on the surface with suitable passivating agents. The reaction with the passivating reagent can convert the hydroxyl groups fully or partly into a form which leads to no adverse interaction with the catalytically active centers.

Suitable passivating agents are, for example, silicon halides and silanes, e.g. silicon tetrachloride, chlorotrimethylsilane, dimethylaminotrichlorosilane, or organometallic compounds of aluminum, boron and magnesium, for example trimethylaluminum, triethylaluminum, triisobutylaluminum, triethylborane, dibutylmagnesium. Chemical dehydration or passivation of the support material is carried out, for example, by reacting a suspension of the support material in a suitable solvent with the passivating reagent in pure form or as a solution in a suitable solvent in the absence of air and moisture. Suitable solvents are, for example, aliphatic or aromatic hydrocarbons such as pentane, hexane, heptane, toluene or xylene. Passivation is generally carried out at from 25°C to 120°C, preferably from 50°C to 70°C. The reaction time is from 30 minutes to 20 hours, preferably from 1 to 5 hours. After chemical dehydration is complete, the support material can be isolated by filtration under inert conditions, washed one or more times with suitable inert solvents as described above and subsequently dried in a stream of inert gas or under reduced pressure.

Organic support materials such as finely divided polyolefin powders (e.g. polyethylene, polypropylene or polystyrene) can also be used and should likewise be free of adhering moisture, solvent residues or other impurities by appropriate purification and drying operations before use.

40

To apply the catalyst system of the present invention to a support, the catalyst mixture prepared above is mixed with a dehydrated or passivated support material, the solvent is removed and the resulting supported metallocene catalyst system is dried in order to ensure that all or most of the solvent is removed

56

from the pores of the support material. The supported catalyst is obtained as a free-flowing powder.

The present invention also provides a process for preparing a polyolefin by polymerization of one or more olefins in the presence of the catalyst system of the present invention, preferably comprising at least one organometallic component of the formula (V). For the purposes of the present invention, the term polymerization encompasses both homopolymerization and copolymerization.

Preference is given to polymerizing olefins of the formula $R_m-CH=CH-R_n$, where R_m and R_n are identical or different and are each a hydrogen atom or an organic radical having from 1 to 20 carbon atoms, in particular from 1 to 10 carbon atoms, and R_m and R_n together with the atoms connecting them may also form one or more rings.

Examples of such olefins are 1-olefins having 2 - 40, preferably 2 - 10, carbon atoms, e.g. ethene, propene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene or 1-octene, styrene, dienes such as 1,3-butadiene, 1,4-hexadiene, vinylnorbornene, norbornadiene or ethylnorbornadiene and cyclic olefins such as norbornene, tetracyclododecene or methylnorbornene. In the process of the present invention, preference is given to homopolymerizing propene or ethene or copolymerizing propene with ethene and/or with one or more 1-olefins having from 4 to 20 carbon atoms, e.g. hexene, and/or one or more dienes having from 4 to 20 carbon atoms, e.g. 1,4-butadiene, norbornadiene, ethylidenenorbornene or ethylnorbornadiene. Examples of corresponding copolymers are ethene-propene copolymers or ethene-propene-1,4-hexadiene terpolymers.

The polymerization is carried out at from -60°C to 300°C , preferably from 50°C to 200°C , very particularly preferably from 50°C - 80°C . The pressure is from 0.5 to 2000 bar, preferably from 5 to 64 bar.

The polymerization can be carried out in solution, in bulk, in suspension or in the gas phase, continuously or batchwise, in one or more stages.

The catalyst system prepared according to the present invention can be used as sole catalyst component for the polymerization of olefins having from 2 to 20 carbon atoms, or preferably in combination with at least one alkyl compound of elements of main groups I to III of the Periodic Table, e.g. an aluminum alkyl,

57

magnesium alkyl or lithium alkyl or an aluminoxane. The alkyl compound is added to the monomer or suspension medium and serves to purify the monomer of substances which can impair the catalyst activity. The amount of alkyl compound added depends on the quality of the monomers used.

As molar mass regulator and/or to increase the activity, hydrogen is added if necessary.

- 10 The supported catalyst system can be used directly for the polymerization. However, it is also possible to remove the solvent and then to resuspend the catalyst system for use in the polymerization. The advantage of this activation method is that it offers the option of forming the polymerization-active catalyst system only in the reactor. This prevents partial decomposition from occurring during introduction of the air-sensitive catalyst.

Furthermore, an additive such as an antistatic can be used according to the present invention, e.g. for improving the particle morphology of the polymer.

- It is generally possible to use all antistatics which are suitable for polymerization. Examples are salt mixtures of calcium salts of Medialan acid and chromium salts of N-stearylanthranilic acid, as described in DE-A-3,543,360. Further suitable antistatics are, for example, C₁₂- to C₂₂-fatty acid soaps of alkali metals or alkaline earth metals, salts of sulfonic esters, esters of polyethylene glycols with fatty acids, polyoxyethylene alkyl ethers, etc. An overview of antistatics is given in EP-A-0,107,127.

It is also possible to use a mixture of a metal salt of Medialan acid, a metal salt of anthranilic acid and a polyamine as antistatic, as described in EP-A-0,636,636.

Commercially available products such as Stadis® 450 from DuPont, namely a mixture of toluene, isopropanol, dodecylbenzenesulfonic acid, a polyamine, a copolymer of 1-decene and SO₂ and also 1-decene, or ASA®-3 from Shell and ARU5R® 163 from ICI can likewise be used.

The antistatic is preferably used as a solution; in the preferred case of Stadis® 450, preference is given to using from 1 to 50% by weight, more preferably from 5 to 25% by weight, of this solution, based on the mass of the supported catalyst used (support together with covalently bound metallocenium-forming

58

compound and one or more metallocene compounds, e.g. of the formula (IV)). However, the amounts of antistatic required fluctuate within a wide range depending on the type of antistatic used.

5

The polymers prepared using the catalyst system of the present invention display a uniform particle morphology and contain no fines. No deposits or cake material are formed in the polymerization using the catalyst system of the present invention.

The polymers prepared by the process of the present invention are particularly useful for producing hard and stiff shaped bodies having a good tensile strength, e.g. fibers, filaments, injection-molded parts, films, sheets or large hollow bodies (e.g. pipes).

The preparation, which has been described in general terms above, of a catalyst system according to the present invention can be carried out by two different methods based on either physisorption or covalent bonding to the support. The sequence of steps employed in the two methods is described below:

Method 1 (Physisorption):

25

In step 1, an inorganic support material (C) is reacted with a metal compound of the formula (V). The metal compound of the formula (V) is preferably added as a solution to a suspension of the support. Solvents or suspension media which can be used are those described under B. The amount of metal compounds of the formula (V) can vary within wide limits; the minimum amount depends on the number of hydroxyl groups on the support. Temperature, reaction times and pressures are not critical per se; preference is given to the temperatures and reaction times described under Method 2. After pretreatment of the support, it has been found to be useful to remove the excess metal compound of the formula (V) by washing, for example with hydrocarbons such as pentane, hexane, ethylbenzene or heptane, and to dry the support.

40

This material is then reacted in step 2 with a metallocene complex of the formula (IV) and one or more of the compounds of the present invention, which preferably comprise compounds of the formula III. It is also possible to use mixtures of various metallocene complexes.

59

The conditions for the reaction of the metallocene complex with the compound of the present invention are not critical per se; the reaction is preferably carried out in solution, especially in hydrocarbons as solvents, preferably aromatic hydrocarbons such as toluene.

An amount of from 0.1 to 10% by weight of metallocene complex, based on the inorganic support material, is particularly useful. The conditions for this reaction are likewise not critical.


10 Temperatures in the range from 20 to 80°C and reaction times in the range from 0.1 to 20 hours have been found to be particularly useful.

In a further step 3, the material obtained after step 2 is 15 reacted with a metal compound of the formula (V). This activation can be carried out at any point in time, i.e. before, during or after the material obtained in step 2 is introduced into the reactor. The activation is preferably carried out after the material obtained in step 2 has been introduced into the reactor.

20 The chemical products of the present invention, in particular those comprising compounds of the formula (III), display, in particular, a high activity when used as cocatalysts in the polymerization of olefins. In addition, they can be stored for a 25 long time; they are not pyrophoric and are readily soluble.

Method 2 (covalent bonding to a support)

The catalyst system of the present invention can further comprise 30 a Lewis base of the formula (VI)



where

35 M^6 is an element of main group V of the Periodic Table of the Elements,

40 R^{21} , R^{22} , R^{23} are identical or different and are each a hydrogen atom or a C_1 - C_{20} -alkyl, C_1 - C_{20} -haloalkyl, C_6 - C_{40} -aryl, C_6 - C_{40} -haloaryl, C_7 - C_{40} -alkylaryl or C_7 - C_{40} -arylalkyl group, where two radicals or all three radicals R^{21} , R^{22} and R^{23} may be joined via C_2 - C_{20} units, where at least one radical R^{21} , R^{22} or R^{23} is not a hydrogen 45 atom or a linear alkyl chain.

60

Preference is given to Lewis bases of the formula (VI) in which R^{21} , R^{22} and R^{23} are identical or different and are each a hydrogen atom or a C_1 - C_{20} -alkyl, C_1 - C_{20} -haloalkyl, C_6 - C_{40} -aryl, C_6 - C_{40} -haloaryl, C_7 - C_{40} -alkylaryl or C_7 - C_{40} -arylalkyl group, where
 5 two radicals or all three radicals R^{21} , R^{22} and R^{23} may be joined via C_2 - C_{20} units and at least one radical R^{21} , R^{22} and R^{23} is a radical having from 2 to 20 carbon atoms or an aromatic group, each of which may be substituted and/or contain heteroatoms selected from the group consisting of P, O, S, N. It is preferred
 10 that at least one radical R^{21} , R^{22} and R^{23} is an alkylaryl group, in particular a benzylic group.

M^6 is preferably nitrogen.

15 Nonlimiting examples of Lewis bases of the formula (VI) are:

- N,N-dimethylcyclohexylamine, N,N-diethylcyclohexylamine,
 N,N-dimethylisopropylamine, N,N-diethylbenzylamine,
 N,N-dimethyl-p-toluidine, N,N-diethyl-p-toluidine,
 20 N,N-dimethylbenzylamine, N,N-diethylisopropylamine,
 N,N-diisopropylmethylamine, N,N-diisopropylethylamine,
 N,N-dimethylcyclopentylamine, N,N-dimethylcycloheptenylamine,
 N,N-dimethylcyclooctanylamine, N,N-dimethylnonanoylamine,
 N,N-diethylcyclopentylamine, N,N-diethylcycloheptenylamine,
 25 N,N-diethylcyclooctanylamine, N,N-diethylnonanoylamine;

 N-benzyl dimethylamine, N-benzyl diethylamine, N-benzyl butylamine,
 N-benzyl-tert-butylamine, N'-benzyl-N,N-dimethylethylenediamine,
 N-benzylethylenediamine, N-benzylisopropylamine,
 30 N-benzylmethylamine, N-benzylethylamine,
 N-benzyl-1-phenylethylamine, N-benzyl-2-phenylethylamine, or
 N-benzylpiperazine;

 N,N-dimethylisopropylamine, N,N-dimethyl-2-butylamine,
 35 N,N-dimethylisobutylamine, N,N-dimethyl-2-pentylamine,
 N,N-dimethyl-3-pentylamine, N,N-dimethyl-2-methylbutylamine,
 N,N-dimethyl-3-methylbutylamine, N,N-dimethylcyclopentylamine,
 N,N-dimethyl-2-hexylamine, N,N-dimethyl-3-hexylamine,
 N,N-dimethyl-2-methylpentylamine,
 40 N,N-dimethyl-3-methylpentylamine,
 N,N-dimethyl-4-methylpentylamine, N,N-dimethyl-2-ethylbutylamine,
 N,N-dimethylcyclohexylamine, N,N-dimethyl-2-heptylamine,
 N,N-dimethyl-3-heptylamine, N,N-dimethyl-4-heptylamine,
 N,N-dimethyl-2-methylhexylamine, N,N-dimethyl-3-methylhexylamine,
 45 N,N-dimethyl-4-methylhexylamine, N,N-dimethyl-5-methylhexylamine,
 N,N-dimethyl-2-ethylpentylamine, N,N-dimethyl-3-ethylpentylamine,
 N,N-dimethyl-2-propylbutylamine, N,N-dimethylcycloheptylamine,

61

- N,N-dimethylmethylcyclohexylamine, N,N-dimethylbenzylamine,
N,N-dimethyl-2-octylamine, N,N-dimethyl-3-octylamine;
- N,N-dimethyl-4-octylamine, N,N-dimethyl-2-methylheptylamine,
5 N,N-dimethyl-3-methylheptylamine,
N,N-dimethyl-4-methylheptylamine,
N,N-dimethyl-5-methylheptylamine,
N,N-dimethyl-6-methylheptylamine, N,N-dimethyl-2-ethylhexylamine,
N,N-dimethyl-3-ethylhexylamine, N,N-dimethyl-4-ethylhexylamine,
10 N,N-dimethyl-2-propylpentylamine, N,N-dimethylcyclooctylamine,
N,N-dimethyldimethylcyclohexylamine, N,N-diethylisopropylamine,
N,N-diethyl-2-butylamine, N,N-diethylisobutylamine,
N,N-diethyl-2-pentylamine, N,N-diethyl-3-pentylamine,
N,N-diethyl-2-methylbutylamine, N,N-diethyl-3-methylbutylamine,
15 N,N-diethylcyclopentylamine, N,N-diethyl-2-hexylamine,
N,N-diethyl-3-hexylamine, N,N-diethyl-2-methylpentylamine,
N,N-diethyl-3-methylpentylamine, N,N-diethyl-4-methylpentylamine,
N,N-diethyl-2-ethylbutylamine, N,N-diethylcyclohexylamine,
N,N-diethyl-2-heptylamine, N,N-diethyl-3-heptylamine,
20 N,N-diethyl-4-heptylamine, N,N-diethyl-2-methylhexylamine,
N,N-diethyl-3-methylhexylamine, N,N-diethyl-4-methylhexylamine,
N,N-diethyl-5-methylhexylamine, N,N-diethyl-2-ethylpentylamine,
N,N-diethyl-3-ethylpentylamine, N,N-diethyl-2-propylbutylamine,
N,N-diethylcycloheptylamine, N,N-diethylmethylcyclohexylamine,
25 N,N-diethylbenzylamine, N,N-diethyl-2-octylamine,
N,N-diethyl-3-octylamine, N,N-diethyl-4-octylamine,
N,N-diethyl-2-methylheptylamine, N,N-diethyl-3-methylheptylamine,
N,N-diethyl-4-methylheptylamine, N,N-diethyl-5-methylheptylamine,
N,N-diethyl-6-methylheptylamine, N,N-diethyl-2-ethylhexylamine,
30 N,N-diethyl-3-ethylhexylamine, N,N-diethyl-4-ethylhexylamine,
N,N-diethyl-2-propylpentylamine, N,N-diethylcyclooctylamine,
N,N-diethyldimethylcyclohexylamine,
N-methyl-N-ethyl-isopropylamine, N-methyl-N-ethyl-2-butylamine,
N-methyl-N-ethylisobutylamine, N-methyl-N-ethyl-2-pentylamine,
35 N-methyl-N-ethyl-3-pentylamine,
N-methyl-N-ethyl-2-methylbutylamine,
N-methyl-N-ethyl-3-methylbutylamine,
N-methyl-N-ethylcyclopentylamine, N-methyl-N-ethyl-2-hexylamine,
N-methyl-N-ethyl-3-hexylamine,
40 N-methyl-N-ethyl-2-methylpentylamine,
N-methyl-N-ethyl-3-methylpentylamine,
N-methyl-N-ethyl-4-methylpentylamine,
N-methyl-N-ethyl-2-ethylbutylamine,
N-methyl-N-ethylcyclohexylamine, N-methyl-N-ethyl-2-heptylamine,
45 N-methyl-N-ethyl-3-heptylamine;

62

- N-methyl-N-ethyl-4-heptylamine,
N-methyl-N-ethyl-2-methylhexylamine;
- N-methyl-N-ethyl-3-methylhexylamine,
5 N-methyl-N-ethyl-4-methylhexylamine,
N-methyl-N-ethyl-5-methylhexylamine,
N-methyl-N-ethyl-2-ethylpentylamine,
N-methyl-N-ethyl-3-ethylpentylamine,
N-methyl-N-ethyl-2-propylbutylamine,
- 10 N-methyl-N-ethylcycloheptylamine,
N-methyl-N-ethylmethylcyclohexylamine,
N-methyl-N-ethylbenzylamine, N-methyl-N-ethyl-2-octylamine,
N-methyl-N-ethyl-3-octylamine, N-methyl-N-ethyl-4-octylamine,
N-methyl-N-ethyl-2-methylheptylamine,
- 15 N-methyl-N-ethyl-3-methylheptylamine,
N-methyl-N-ethyl-4-methylheptylamine,
N-methyl-N-ethyl-5-methylheptylamine,
N-methyl-N-ethyl-6-methylheptylamine,
N-methyl-N-ethyl-2-ethylhexylamine,
- 20 N-methyl-N-ethyl-3-ethylhexylamine,
N-methyl-N-ethyl-4-ethylhexylamine,
N-methyl-N-ethyl-2-propylpentylamine,
N-methyl-N-ethylcyclooctylamine,
N-methyl-N-ethyldimethylcyclohexylamine,
- 25 N-methyldiisopropylamine, N-methylbis(2-butyl)amine,
N-methylbis(isobutyl)amine, N-methylbis(2-pentyl)amine,
N-methylbis(3-pentyl)amine, N-methylbis(2-methylbutyl)amine,
N-methylbis(3-methylbutyl)amine, N-methyldicyclopentylamine,
N-methylbis(2-hexyl)amine, N-methylbis(3-hexyl)amine,
- 30 N-methylbis(2-methylpentyl)amine,
N-methylbis(3-methylpentyl)amine,
N-methylbis(4-methylpentyl)amine, N-methylbis(2-ethylbutyl)amine,
N-methyldicyclohexylamine, N-methylbis(2-heptyl)amine,
N-methylbis(3-heptyl)amine, N-methylbis(4-heptyl)amine,
- 35 N-methylbis(2-methylhexyl)amine, N-methylbis(3-methylhexyl)amine,
N-methylbis(4-methylhexyl)amine, N-methylbis(5-methylhexyl)amine,
N-methylbis(2-ethylpentyl)amine, N-methylbis(3-ethylpentyl)amine,
N-methylbis(2-propylbutyl)amine, N-methylbis(cycloheptyl)amine,
N-methylbis(methylcyclohexyl)amine, N-methyldibenzylamine,
- 40 N-methylbis(2-octyl)amine, N-methylbis(3-octyl)amine,
N-methylbis(4-octyl)amine, N-methylbis(2-methylheptyl)amine,
N-methylbis(3-methylheptyl)amine,
N-methylbis(4-methylheptyl)amine,
N-methylbis(5-methylheptyl)amine,
- 45 N-methylbis(6-methylheptyl)amine, N-methylbis(2-ethylhexyl)amine,
N-methylbis(3-ethylhexyl)amine, N-methylbis(4-ethylhexyl)amine,
N-methylbis(2-propylpentyl)amine, N-methylbis(cyclooctyl)amine,

63

- N-methylbis(dimethylcyclohexyl)amine, N-ethyldiisopropylamine,
 N-ethylbis(2-butyl)amine, N-ethylbis(isobutyl)amine,
 N-ethylbis(2-pentyl)amine, N-ethylbis(3-pentyl)amine,
 N-ethylbis(2-methylbutyl)amine, N-ethylbis(3-methylbutyl)amine,
 5 N-ethyldicyclopentylamine, N-ethylbis(2-hexyl)amine,
 N-ethylbis(3-hexyl)amine, N-ethylbis(2-methylpentyl)amine,
 N-ethylbis(3-methylpentyl)amine, N-ethylbis(4-methylpentyl)amine,
 N-ethylbis(2-ethylbutyl)amine, N-ethyldicyclohexylamine,
 N-ethylbis(2-heptyl)amine, N-ethylbis(3-heptyl)amine,
 10 N-ethylbis(4-heptyl)amine, N-ethylbis(2-methylhexyl)amine,
 N-ethylbis(3-methylhexyl)amine, N-ethylbis(4-methylhexyl)amine,
 N-ethylbis(5-methylhexyl)amine, N-ethylbis(2-ethylpentyl)amine,
 N-ethylbis(3-ethylpentyl)amine, N-ethylbis(2-propylbutyl)amine,
 N-ethylbis(cycloheptyl)amine, N-ethylbis(methylcyclohexyl)amine,
 15 N-ethyldi(benzyl)amine, N-ethylbis(2-octyl)amine,
 N-ethylbis(3-octyl)amine, N-ethylbis(4-octyl)amine,
 N-ethylbis(2-methylheptyl)amine, N-ethylbis(3-methylheptyl)amine,
 N-ethylbis(4-methylheptyl)amine, N-ethylbis(5-methylheptyl)amine,
 N-ethylbis(6-methylheptyl)amine, N-ethylbis(2-ethylhexyl)amine,
 20 N-ethylbis(3-ethylhexyl)amine, N-ethylbis(4-ethylhexyl)amine,
 N-ethylbis(2-propylpentyl)amine, N-ethylbis(cyclooctyl)amine,
 N-ethylbis(dimethylcyclohexyl)amine.

- In step 1 of Method 2, an inorganic support material (C) is
 25 reacted with a Lewis base of the formula (VI). The Lewis base of
 the formula (VI) is preferably added as a solution to a
 suspension of the support. Suitable solvents or suspension media
 are, in particular, hydrocarbons, preferably aromatic
 hydrocarbons such as toluene. The amount of Lewis base of the
 30 formula (VI) can vary within wide limits; the minimum amount
 depends on the number of hydroxyl groups on the support. It has
 also been found to be useful for, after the pretreatment of the
 support, the support material to be used moist in step 2.
 35 This material is then reacted in step 2 with one or more of the
 chemical compounds of the present invention, which preferably
 comprise compounds of the formula (III). It has been found to be
 useful, after step 2, to remove excess Lewis base of the formula
 (VI) by washing, for example with hydrocarbons such as pentane,
 40 hexane, ethylbenzene or heptane, and to dry the support.

The covalently supported cocatalyst prepared in this way is, in
 step 3, brought into contact with a reaction mixture comprising
 the organometallic compound of the formula (IV) and an aluminum
 45 alkyl of the formula (V). The reaction is preferably carried out

64

in solution, especially in hydrocarbons as solvents, preferably aromatic hydrocarbons such as toluene.

An amount of from 0.1 to 10% by weight of metallocene complex, 5 based on the inorganic support material, is particularly useful.

The conditions for the reactions in steps 1 to 3 are not critical; temperatures within the range from 20 to 150°C and reaction times in the range from 0.1 to 20 hours have been found 10 to be particularly suitable.

The catalyst material prepared in this way is filtered off, if desired washed with hydrocarbons such as pentane, hexane, ethylbenzene or heptane and dried to constant weight.

15

The following examples serve to illustrate the invention. In the examples, preparation and handling of the compounds was carried out in the absence of air and moisture under argon (Schlenk technique). All solvents required were dried before use by 20 boiling for a number of hours over suitable desiccants and subsequent distillation under argon. For characterization of the compounds, samples were taken from the individual reaction mixtures and dried in an oil pump vacuum.

25 Examples

A) Preparation of the novel chemical products suitable as cocatalysts and preparation/description of the cocatalysts used for comparison

30

Example 1: Cocatalyst (1)

5.0 ml of trimethylaluminum (2M in Exxol, viz. a hydrocarbon mixture from Exxon; 5.4 mmol) together with 100 ml of toluene 35 were placed in a reaction vessel. 3.65 g (5.4 mmol) of 4,4'-dihydroxyoctafluorobiphenyl monohydrate were added to this solution. The reaction solution was stirred at 60°C for one hour. The chemical product 1 obtained was subsequently used without purification for application to a support.

40

Example 2: Cocatalyst (2)

8.0 ml of triethylaluminum (2M in Exxol, 5.4 mmol) together with 100 ml of toluene were placed in a reaction vessel. 3.65 g 45 (5.4 mmol) of 4,4'-dihydroxyoctafluorobiphenyl monohydrate were added to this solution. The reaction solution was stirred at 60°C

65

for one hour. The chemical product 2 was subsequently used without purification for application to a support.

Example 3: Cocatalyst (3)

5

7.7 ml of triisobutylaluminum (2M in Varsol, viz. a hydrocarbon mixture from Exxon; 5.4 mmol) together with 100 ml of toluene were placed in a reaction vessel. 3.65 g (5.4 mmol) of 4,4'-dihydroxyoctafluorobiphenyl monohydrate were added to this solution. The reaction solution was stirred at 60°C for one hour. Chemical product 3 obtained was subsequently used without purification for application to a support.

Comparative Example 1: cocatalyst (4)

15

30% strength methylaluminoxane solution (Albemarle Corporation, Baton Rouge, Louisiana, USA)

Comparative Example 2: cocatalyst (5) (no prior art)

20

10 ml of a solution of trimethylaluminum (TMA) in toluene (2 mol/l) were added dropwise at room temperature to a suspension of 20 mmol of dihydroxyoctafluorobiphenyl. The mixture was subsequently stirred at room temperature for 3 hours. As reaction product, a 1:1 condensate of TMA and dihydroxyoctafluorobiphenyl was obtained.

B) Preparation of the supported cocatalysts

14.0 g of SiO₂ (XPO 2107, from Grace, dried at 600°C in a stream of argon) together with 20 ml of toluene were placed in a reaction vessel, 2.6 ml of N,N-dimethylaniline (20.80 mmol) were added dropwise and the mixture was stirred at room temperature for 2 hours. Subsequently, at 0°C, 20.80 mmol of the respective cocatalysts 1-3, in each case dissolved in 40 ml of toluene, were added. The suspension was allowed to warm to room temperature and was stirred for two hours at this temperature. The resulting bluish suspension was filtered and the residue was washed with 50 ml of toluene and subsequently with 3 x 100 ml of n-pentane. The residue was then dried in an oil pump vacuum. This in each case gave the supported cocatalyst system which was weighed.

C) Preparation of catalyst systems

Catalyst systems according to the present invention

66

0.30 ml of trimethylaluminum (20% strength in Exxol, 700 μmol) was added to a solution of 50 mg (80 μmol) of dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride in 50 ml of toluene and the solution was stirred at room temperature for 1.5 hours. 1920 $\mu\text{mol/g}$ [SiO_2] of the supported cocatalysts 1 to 3 from B were subsequently added a little at a time. The solution was stirred at room temperature for 60 minutes. The solvent was then removed in an oil pump vacuum, giving in each case a light-red free-flowing powder.

10

Comparison:

Dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride/MAO system

15

0.30 ml of trimethylaluminum (20% strength in Exxol, 700 μmol) was added to a solution of 50 mg (80 μmol) of dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride in 50 ml of toluene and the solution was stirred at room temperature for 1.5 hours. 1920 $\mu\text{mol/g}$ [SiO_2] of a 30% strength methylaluminoxane solution in toluene (Albermarle Corporation, Baton rouge, Louisiana, USA) supported as described in B were subsequently added as cocatalyst. The solution was stirred at room temperature for 60 minutes. The solvent was then removed in an oil pump vacuum, giving a light-red free-flowing powder.

Comparison:

Dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride/dihydroxyoctafluorobiphenyl

0.30 ml of trimethylaluminum (20% strength in Exxol, 700 μmol) was added to a solution of 50 mg (80 μmol) of dimethylsilanediylbis(2-methyl-4-phenylindenyl)zirconium dichloride in 50 ml of toluene and the solution was stirred at room temperature for 1.5 hours. 1920 $\mu\text{mol/g}$ [SiO_2] of cocatalyst (5) were subsequently added. The solution was stirred at room temperature for 60 minutes. The solvent was then removed in an oil pump vacuum, giving a light-red free-flowing powder.

D) Polymerization

For introduction into the polymerization system, the appropriate amount of the supported catalyst system prepared under B (16 μmol of metallocene) was resuspended in 30 ml of Exxol. In parallel thereto, a dry 16 dm³ reactor was flushed firstly with nitrogen

67

and subsequently with propylene and charged with 10 dm³ of liquid propene. 0.5 cm³ of a 20% strength triisobutylaluminum solution in Varsol, diluted with 30 cm³ of Exxol, were then introduced into the reactor and the mixture was stirred at 30°C for 15 minutes.

- 5 The catalyst suspension was subsequently introduced into the reactor. The reaction mixture was then heated to the polymerization temperature of 60°C (4°C/min) and the polymerization system was held at 60°C for 1 hour by cooling. The polymerization was stopped by venting the remaining propylene.
- 10 The polymer obtained was dried in a vacuum drying oven. The reactor displayed no deposits on the interior wall or stirrer. The results of the polymerization are summarized in the following table. These results demonstrate that a higher polymerization activity is found when using the chemical products of the present
- 15 invention as cocatalysts.

20	Supported catalyst system prepared using cocatalyst No.	1	2	3	4	5
	Amount of metallocene [mg]	50	50	50	50	50
25	Metallocene (μ mol)	80	80	80	80	80
	Cocatalyst (μ mol)	1920	1920	1920	1920	1920
30	Weight of catalyst system obtained [mg]	1000	1000	1000	1000	1000
35	Weight of catalyst system used for polymerization [mg] [16 μ mol of metallocene]	200	200	200	200	200
	Time (min)	60	60	60	60	60
	PP (kg)	0.62	0.78	0.58	0.41	0.18

40

45

We claim:

1. A chemical product suitable as cocatalyst which is obtainable
5 by reacting a compound of the formula (I),



where

10

R^1, R^2, R^3 are identical or different and are each hydrogen, C_1 - C_{20} -alkyl, C_1 - C_{20} -haloalkyl, C_6 - C_{20} -aryl, C_6 - C_{20} -haloaryl, C_7 - C_{40} -arylalkyl, C_7 - C_{40} -haloarylalkyl, C_7 - C_{40} -alkylaryl or C_7 - C_{40} -haloalkylaryl,

15


M^1 is an element of main group II or III of the Periodic Table of the Elements and

20

m is 0 or 1, with m being 1 when M^1 is an element of main group III and m being 0 when M^1 is an element of main group II,

with a compound of the formula (II),

25



in which heteroatom-containing substituents R^4X are located on a parent moiety G , where

30

R^4 are identical or different and are each hydrogen, C_1 - C_{20} -alkyl, C_1 - C_{20} -haloalkyl, C_6 - C_{20} -aryl, C_6 - C_{20} -haloaryl, C_7 - C_{40} -arylalkyl, C_7 - C_{40} -haloarylalkyl, C_7 - C_{40} -alkylaryl, C_7 - C_{40} -haloalkylaryl,

35

X is an element of main group VI of the Periodic Table of the Elements,

40

G is at least divalent C_1 - C_{20} -haloalkylene, C_6 - C_{40} -haloarylene, C_7 - C_{40} -haloarylalkylene, C_7 - C_{40} -haloalkylarylene,

45

M^2 is an element of main group VI of the Periodic Table of the Elements,

69

R⁵, R⁶ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₁₀-alkoxy, C₂-C₁₀-alkenyl, C₇-C₂₀-arylalkyl, C₇-C₂₀-alkylaryl, C₆-C₁₀-aryloxy, C₁-C₁₀-haloalkyl,

5

q is an integer from 2 to 10 and

g is an integer from 1 to 10.

10 2. A chemical product as claimed in claim 1, wherein

X and M² are each oxygen and

R⁴, R⁵ and R⁶ are each hydrogen.

15

3. A process for preparing a chemical product suitable as cocatalyst by reacting a compound of the formula (I),



20

where

R¹, R², R³ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₂₀-haloalkyl, C₆-C₂₀-aryl, C₆-C₂₀-haloaryl, C₇-C₄₀-arylalkyl, C₇-C₄₀-haloarylalkyl, C₇-C₄₀-alkylaryl or C₇-C₄₀-haloalkylaryl,

25


M¹ is an element of main group II or III of the Periodic Table of the Elements and

30

m is 0 or 1, with m being 1 when M¹ is an element of main group III and m being 0 when M¹ is an element of main group II,

35

with a compound of the formula (II),



40 in which heteroatom-containing substituents R⁴X are located on a parent moiety G, where

R⁴ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₂₀-haloalkyl, C₆-C₂₀-aryl, C₆-C₂₀-haloaryl, C₇-C₄₀-arylalkyl,

45

70

C₇-C₄₀-haloarylalkyl, C₇-C₄₀-alkylaryl,
C₇-C₄₀-haloalkylaryl,

- 5 X is an element of main group VI of the Periodic Table of the Elements,
- 10 G is at least divalent C₁-C₂₀-haloalkylene, C₆-C₄₀-haloarylene, C₇-C₄₀-haloarylalkylene, C₇-C₄₀-haloalkylarylene,
- 15 M² is an element of main group VI of the Periodic Table of the Elements,
- 15 R⁵, R⁶ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₁₀-alkoxy, C₂-C₁₀-alkenyl, C₇-C₂₀-arylalkyl, C₇-C₂₀-alkylaryl, C₆-C₁₀-aryloxy, C₁-C₁₀-haloalkyl,
- 20 q is an integer from 2 to 10 and
- g is an integer from 1 to 10.
- 25 4. A catalyst system comprising, as cocatalyst, a chemical product as claimed in claim 1 or 2 obtainable by reacting compounds of the formula (I) with compounds of the formula (II).
5. A catalyst system as claimed in claim 4 comprising
- 30 A) at least one organic transition metal compound,
- B) if desired, at least one main group alkyl,
- 35 C) if desired, at least one support component, and
- D) at least one chemical product obtainable by reacting compounds of the formula (I) with compounds of the formula (II).
- 40 6. A catalyst system as claimed in claim 4 or 5 comprising
- A) at least one metallocene, and
- 45 B) if desired, at least one Lewis base of the formula (VI),

71

 $M^6R^{21}R^{22}R^{23}$

(VI),

where

5 M^6 is an element of main group V of the Periodic Table
 of the Elements,

10 R^{21} , R^{22} , R^{23} are identical or different and are each
 hydrogen, C_1 - C_{20} -alkyl, C_1 - C_{20} -haloalkyl, C_6 - C_{40} -aryl,
 C_6 - C_{40} -haloaryl, C_7 - C_{40} -alkylaryl or C_7 - C_{40} -arylalkyl,
 where two radicals or all three radicals R^{21} , R^{22} and
 R^{23} may be joined to one another via C_2 - C_{20} units, and
 at least one radical R^{21} , R^{22} or R^{23} is not a hydrogen
 atom or a linear alkyl chain.

15

7. A process for preparing a polyolefin by polymerization of one
 or more olefins in the presence of a catalyst system as
 claimed in any of claims 4 to 6.

20

25

30

35


40

45

Chemical products suitable as cocatalysts, their preparation and their use in catalyst systems for preparing polyolefins

5 Abstract

Chemical products obtainable by reacting a compound of the formula (I),




where

15 R^1, R^2, R^3 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl or C_7-C_{40} -haloalkylaryl,

20 M^1 is an element of main group II or III of the Periodic Table of the Elements and

m is 0 or 1, with m being 1 when M^1 is an element of main group III and m being 0 when M^1 is an element of main group II,

25 with a compound of the formula (II),



30 in which heteroatom-containing substituents $R^4 X$ are located on a parent moiety G , where

35 R^4 are identical or different and are each hydrogen, C_1-C_{20} -alkyl, C_1-C_{20} -haloalkyl, C_6-C_{20} -aryl, C_6-C_{20} -haloaryl, C_7-C_{40} -arylalkyl, C_7-C_{40} -haloarylalkyl, C_7-C_{40} -alkylaryl, C_7-C_{40} -haloalkylaryl,

40 X is an element of main group IV, V or VI of the Periodic Table of the Elements,

45 G is at least divalent C_1-C_{20} -alkylene, C_1-C_{20} -haloalkylene, C_1-C_{10} -alkyleneoxy, C_6-C_{40} -arylene, C_6-C_{40} -haloarylene, C_6-C_{40} -aryleneoxy, C_7-C_{40} -arylalkylene, C_7-C_{40} -haloarylalkylene, C_7-C_{40} -alkylarylene, C_7-C_{40} -haloalkylarylene,

73

M² is an element of main group IV, V or VI of the Periodic Table of the Elements,

5 R⁵, R⁶ are identical or different and are each hydrogen, C₁-C₂₀-alkyl, C₁-C₁₀-alkoxy, C₂-C₁₀-alkenyl, C₇-C₂₀-arylalkyl, C₇-C₂₀-alkylaryl, C₆-C₁₀-aryloxy, C₁-C₁₀-haloalkyl,

10 q is an integer from 2 to 100 and

g is an integer from 1 to 100,

15 are suitable as cocatalysts in catalyst systems for the preparation of polyolefins.

20

25

30

35

40

45