

FABRICATION PROCESS OF A HYBRID SEMICONDUCTOR SUBSTRATE

The present invention relates to a fabrication process of a hybrid semiconductor substrate, and more particularly, relates to simultaneous fabrication of hybrid semiconductor substrate.

A semiconductor device, in which a Semiconductor-on-insulator (SeOI) region and a bulk semiconductor region are formed on the upper surface of a semiconductor base substrate, wherein the SeOI region comprises a buried insulating oxide layer (BOX) and a thin semiconductor layer, is known as a hybrid semiconductor device. Such a device can be used in memory cell.

FIG. 1 is a cross sectional view of a known hybrid semiconductor device 101, like for example disclosed in Yamaoka et. al., IEEE Journal of Solid-State Circuits, Volume 41, Number 11, page 2366 – 2372, November 2006.

As shown in the drawing, the hybrid semiconductor device 101 includes a SeOI region 113 comprising a BOX layer 105 and a SeOI layer 107 formed on a bulk substrate 103 and a bulk semiconductor region 111 formed on the same bulk substrate 103. The SeOI region 113 and the bulk semiconductor region 111 are usually separated from each other by a shallow trench isolation (STI) 123.

Devices comprising SeOI regions offer several advantages over more conventional semiconductor devices. For example, SeOI devices may have low parasitic capacitances, lower power consumption requirements than non-SeOI devices that perform similar tasks, and, hence provide faster switching times for the resultant circuits. Since the SeOI region can be provided with an ultra-thin BOX layer, threshold voltage (V_t) can be controlled by changing the voltage of the underlying well and hence it enables back gate control with low bias voltage. This back gate bias is applied through a well contact formed through the BOX layer, wherein the wells within the SeOI region and the bulk semiconductor region are separated from each other by STI.

However, the hybrid semiconductor devices such as the conventional device have the following drawbacks.

Unlike the bulk semiconductor region, the body of the SeOI region is usually not connected to a specific reference potential which may allow minority charge carriers to accumulate in that region, and, hence a floating body potential can exist in the SeOI region. This phenomenon leads to a variation in the threshold voltage (V_t) of the devices. In particular, for static random memory (SRAM) cells, the threshold voltage fluctuations may result in significant instabilities of the devices, which may not be tolerable in view of data integrity of the memory cells.

Further, it is known to implant three different concentrations of dopants (n- type or p-type) in a given region to form the channel of a MOSFET in a bulk substrate. The three different concentrations of dopants lead to three levels of doping: a shallow level called V_t -doping, a deeper level called Groundplane-doping (GP) and a deepest level called Well-doping. On the other hand, doping in the SeOI region is used to form the backside electrodes of the SeOI transistors. The formation of the backside electrodes is achieved with different implant conditions thus also with a different mask.

Thus, the fabrication of a hybrid semiconductor substrate, comprising a SeOI region and a bulk semiconductor region, requires different implant conditions for each region. The process cost and time for the said fabrication thus increases due to the need of a plurality of different masks to be able to carry out the implant steps in both the regions and thus a higher number of process steps.

It is therefore the object of the present invention to provide an improved manufacturing process of the hybrid semiconductor substrate.

This object is achieved with a method for manufacturing a hybrid semiconductor substrate comprising the steps of: (a) providing a hybrid semiconductor substrate comprising a semiconductor-on-insulator (SeOI) region, that comprises an insulating layer over a base substrate and a SeOI layer over the insulating layer, and a bulk semiconductor region, wherein the SeOI region and the bulk semiconductor region share the same base substrate; (b) providing a mask layer over the SeOI region, and (c) forming a first impurity level by doping the SeOI region and the bulk semiconductor region simultaneously such that the first impurity level in the SeOI region is contained within the mask layer.

With the afore-mentioned method for manufacturing according to the invention, both regions of the hybrid semiconductor substrate can be doped using the same implant conditions, which simplifies the manufacturing process of hybrid semiconductor substrates. As the implant profile is contained within the mask layer, a perturbation of this zone of the semiconductor material by the dopant can be prevented after mask removal.

Preferably, the method for manufacturing the hybrid semiconductor substrate can further comprise a step of: (d) forming a second impurity level by doping the SeOI region and the bulk semiconductor region simultaneously such that the second impurity level in the SeOI region is under the insulating layer and within the base substrate. Such an implant profile helps in suppressing the threshold voltage (V_t) fluctuations in transistors in the SeOI region and, in case the obtained hybrid substrate is used in SRAM applications, an improved SRAM stability can be achieved.

Advantageously, the method for manufacturing the hybrid semiconductor substrate can further comprise a step of: (e) forming a third impurity level by doping the SeOI region and the bulk semiconductor region simultaneously such that the third impurity level in the SeOI region is below the second impurity level within the base substrate and further away from the insulating layer. Such an implant profile helps in suppressing the threshold voltage (V_t) fluctuations in the SeOI regions and hence improves SRAM stability. Furthermore, a simultaneous creation of backside electrodes in the SeOI regions and the channels of the transistors in the bulk semiconductor regions in the hybrid semiconductor substrate can be achieved.

According to a preferred embodiment, the method for manufacturing the hybrid semiconductor substrate can further comprise the steps of: (g) providing a SeOI substrate; forming the mask layer on the SeOI substrate; and removing a predetermined area of the mask, the underlying SeOI layer and the underlying insulating layer to obtain the bulk semiconductor region. Thus, the bulk semiconductor region and the SeOI region can be formed starting from the same SeOI substrate. Compared to the prior art technique of the Epitaxial Layer Overgrowth that can be used to obtain SOI islands within Si bulk starting from a bulk substrates, the inventive method provides a simpler process and less crystal defects.

Preferably, the method for manufacturing the hybrid semiconductor substrate can further comprise a step (h) of providing a second mask with a predetermined pattern over the hybrid semiconductor substrate to prevent the formation of an impurity level in the area masked by the second mask during at least one of steps c), d) and e). Thus only one mask needs to be provided per transistor type (n- or p-type) in the bulk semiconductor region, while simultaneously the backside electrodes of transistors in the SeOI region can be formed. In addition, for the fabrication of the other type of transistors in the bulk semiconductor region also only one additional mask is necessary. Thus, the process can further be optimized such that a lower cost manufacturing can be achieved. The mask can be a standard photolithography mask (e.g. photoresist).

Preferably, the method for manufacturing a hybrid semiconductor substrate can further comprise a step (i) of removing the mask layer from the SeOI region after step c). By doing so the first impurity level can be removed which might not be useful for the formation of the electronic devices in the SeOI region. Indeed, the above introduced first impurity level present in the bulk semiconductor region should be kept away from the top layer of the SeOI region. Preferably, and according to this invention, the channel of devices formed in the SeOI region can thus be kept undoped.

According to a preferred embodiment, the mask layer and/or the insulating layer can be made of an oxide, in particular deposited by a chemical vapor deposition (CVD) process. Such a mask layer is thus easy to obtain and furthermore suitable to trap the dopants. A deposited silicon nitride layer or combination of deposited oxide and nitride layers can be used as a mask. A CVD oxide is, however, the most practical from a technology point of view.

Advantageously, the method for manufacturing the hybrid semiconductor substrate can comprise a step (j) of providing a spacer in an edge region of the SeOI region adjacent to the bulk semiconductor region such that the spacer extends at least from the surface of the base substrate till the SeOI layer. The spacer can protect the SeOI layer and the insulating layer of the SeOI region from damage while the mask layer is removed from the hybrid semiconductor substrate, e.g. by etching, during step (i). According to a variant the spacer can be removed after step (i), e.g. by a wet etch using phosphoric acid.

Preferably, the material of the spacer can be different than the one of the mask layer and/or the insulating layer, preferably a nitride. For materials having different etching properties, like nitride compared to an oxide, it is possible to protect the insulating layer during etching of the mask layer.

According to an advantageous embodiment, the mask layer can have a thickness of at least 20 nm. In particular, the thickness of the mask layer is not less than 20 nm and not more than 30 nm. By having a mask layer of such a thickness, the first impurity level in the bulk semiconductor region can form a shallow impurity region forming the so called V_t -doping level, whereas the second deeper level can form the Groundplane (GP) doping level and, if present, the third level can form the so called Well-doping level, so that the channel of a MOSFET transistor can be formed in the bulk semiconductor region of the hybrid semiconductor substrate.

Advantageously, the SeOI layer can have a thickness of at most 20 nm, in particular, the thickness of the SeOI layer is not less than 10 nm and not more than 20 nm, and/or the insulating layer can have a thickness of at most 20 nm, in particular, the thickness of the insulating layer is not less than 10 nm and not more than 20 nm. By having such a thin SeOI layer and thin insulating layer, the Groundplane and if present Well-doping level in the SeOI region of the hybrid semiconductor substrate can be positioned under the insulating layer, while at the same time those implant levels can be provided at correct depths within the bulk semiconductor region. Thus, characteristics such as suppression of threshold voltage fluctuations and hence SRAM stability can be achieved.

Preferably, the method for manufacturing the hybrid semiconductor substrate can further comprise a step of providing a shallow trench isolation (STI) to separate the SeOI region and the bulk semiconductor region. By having such a STI, the well regions of the SeOI region and the bulk semiconductor region can be separated and thus, the back-gate voltage of each region can be better controlled.

The object of the invention is also achieved with a hybrid semiconductor substrate according to claim 14 comprising: a semiconductor-on-insulator (SeOI) region, comprising a base substrate, an insulating layer over the base substrate, a SeOI layer over the insulating layer and a mask layer over the SeOI layer, a bulk semiconductor region provided adjacent

to the SeOI region, and a first impurity region in the SeOI region and the bulk semiconductor region wherein the first impurity region in the SeOI region is contained within the mask layer. With the afore-mentioned hybrid semiconductor substrate, the implant profile is contained within the mask layer and it becomes possible to simultaneously create backside electrodes on the SeOI region and channels of the transistors in the bulk semiconductor regions of the hybrid semiconductor substrate..

Advantageously, the hybrid semiconductor substrate can furthermore comprise: a second impurity region in the SeOI region and the bulk semiconductor region wherein the second impurity region in the SeOI region is under the insulating layer and within the base substrate. By having such an impurity region under the insulating layer, threshold voltage (V_t) fluctuations can be suppressed and hence SRAM stability can be achieved.

Preferably, the hybrid semiconductor substrate can comprise: a third impurity region in the SeOI region and the bulk semiconductor region wherein the third impurity region in the SeOI region is below the second impurity region within the base substrate and further away from the insulating layer. By having such an impurity region under the insulating layer, threshold voltage (V_t) fluctuations can be suppressed and hence SRAM stability can be achieved.

Advantageous embodiments of the inventive method will be described in the following by referring to the Figures. It is shown in:

FIG. 1 shows a cross-sectional view of a conventional hybrid semiconductor device known from the prior art;

FIG. 2 shows a cross-sectional view of the hybrid semiconductor substrate according to a first embodiment;

FIGs. 3a – 3h illustrates a method for manufacturing the hybrid semiconductor substrate 1 of the first embodiment of FIG. 2;

FIGs. 4a – 4h illustrates a method for manufacturing the hybrid semiconductor substrate 1 according to a second embodiment;

FIG. 5 illustrates the steps of providing impurity levels according to a variant of the first embodiment, wherein the two implantation steps illustrated in FIG. 3d and 3e, respectively are replaced by a single implantation step;

FIG. 6 illustrates a step of providing a spacer 29 according to a variant of the second embodiment as illustrated in FIG. 4c; and

FIG. 7 illustrates a further variant of the first embodiment.

In the following, features and advantageous embodiments of the method and the device according to the invention will be described in detail.

FIG. 2 illustrates a hybrid semiconductor substrate 1 according to a first embodiment of the invention. The fabrication method to manufacture the hybrid semiconductor substrate 1 will be described with respect to FIG. 3a to 3d.

The hybrid semiconductor substrate 1 comprises a base substrate 3 with a semiconductor-on-insulator (SeOI) region 13 that comprises an insulating layer 5, a semiconductor layer 7 also called SeOI layer, and a mask layer 9.

The hybrid semiconductor substrate 1 furthermore comprises a bulk semiconductor region 11 adjacent to the SeOI region 13 and which share the same base substrate 3.

In this embodiment, the base substrate 3 is a Si wafer, the insulating layer 5 is a silicon oxide layer also called buried oxide layer (BOX), and the SeOI layer 7 is a silicon containing layer. The material choice is nevertheless not limiting and other suitable materials, like germanium, gallium arsenide etc. could find their application for the substrate 3 and the SeOI layer 7. Concerning the insulating layer 5, other insulating materials than silicon oxide can also be used.

The thickness of the SeOI layer 7 in this embodiment has a value of at most 20 nm, in particular, a thickness from about 10 nm to about 20 nm. The insulating layer 5 has a thickness of at most 20 nm, in particular, a thickness from about 10 nm to about 20 nm.

According to the invention, the SeOI region 13 further comprises a mask layer 9 over the SeOI layer 7. The mask layer 9 in this embodiment is a silicon oxide. In this context, an oxide deposited by chemical vapour deposition is preferred. A deposited silicon nitride layer or combination of deposited oxide and nitride layers can also be used as the mask layer 9. The mask layer 9 has a thickness of at least 20 nm, in particular, with a thickness from about 20 nm to about 30 nm.

The hybrid semiconductor substrate 1 further comprises a first impurity level 17a in the SeOI region 13 and a first impurity level 17b in the bulk semiconductor region 11, wherein the first impurity level 17a in the SeOI region 13 is contained within the mask layer 9.

FIGs. 3a) through 3d) illustrate a method for manufacturing the hybrid semiconductor substrate 1 of the first embodiment illustrated in FIG. 2.

FIG. 3a illustrates a semiconductor-on-insulator (SeOI) substrate 1a. The SeOI substrate 1a, in this embodiment, comprises the base substrate 3, the insulating layer 5 over the base substrate 3 and the SeOI layer 7 over the insulating layer 5. The SeOI substrate 1a can, for example, be obtained by SmartCUTTM technology, or any other suitable semiconductor-on-insulator manufacturing method. The SeOI substrate 1a may have any suitable size or form such as, for example, 200 mm or 300 mm type wafer. The layers 3, 5 and 7 have the properties concerning material and thickness like already mentioned above with respect to FIG. 2.

Prior to the following process steps the surface 1b of the SeOI substrate 1a may be cleaned using for instance a Radio Corporation of America (RCA) cleaning.

Referring to FIG. 3b, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, comprises a step of providing a mask layer 9 over the surface 1b of the SeOI substrate 1a. The mask layer 9 is an oxide layer, in particular a silicon oxide layer. In this context, an oxide deposited by chemical vapour deposition is

preferred. A deposited silicon nitride layer or combination of deposited oxide and nitride layers can also be used as the mask layer 9 according to a variant. The mask layer 9 is deposited over the surface 1b of the SeOI substrate 1a, for example, by a chemical vapor deposition (CVD) process. The mask layer 9 has a thickness of at least 20 nm, in particular, with a thickness from about 20 nm to about 30 nm.

Referring to FIG. 3c, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of removing, for example, by plasma etching, a predetermined area of the mask layer 9, the underlying SeOI layer 7 and the underlying insulating layer 5 to obtain a bulk semiconductor region 11, like illustrated in FIG. 2. The region other than the bulk semiconductor region 11, thus without material removal, forms the SeOI region 13, like illustrated in FIG. 2. Thus, the bulk semiconductor region 11 and the SeOI region 13 are formed starting from the same SeOI substrate 1a. The dimensions of the predetermined area removed above is determined, for example, by the circuit design. The order of magnitude of the predetermined area can be, for example, several square micrometers.

According to a variant of the first embodiment, the steps illustrated in FIG. 3b and FIG. 3c can be exchanged. Thus, the bulk semiconductor region 11 can also be formed by removing only a predetermined area of the underlying SeOI layer 7 and the underlying insulating layer 5 and the mask layer 9 can then be formed independently over the SeOI region 13.

A step height h , as shown in FIG. 3c, of about 40 nm to 70 nm, can be observed between the bulk semiconductor region 11 and the SeOI region 13. This is, however, not an issue for the subsequent process steps, like photolithography.

Referring to FIG. 3d, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step (h) of providing a second mask 15 with a predetermined pattern over the hybrid semiconductor substrate 1. This second mask 15 provides the pattern for the doping steps. Indeed, the second mask 15 prevents the formation of an impurity level in the underlying area masked by the second mask 15.

The second mask 15 does not necessarily have to be in contact with the surface of the bulk semiconductor region 11 and/or SeOI region 13. According to a variant, a contact less mask 15b can also be used as the second mask 15, as illustrated in FIG. 7.

Subsequent to providing the second mask 15, still referring to FIG. 3d, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of forming a first impurity level 17a, 17b by doping the SeOI region 13 and the bulk semiconductor region 11 simultaneously using preferably ion implantation. The ion implantation 16 is performed such that the first impurity level 17a in the SeOI region 13 is contained within the mask layer 9. The doping levels are typically determined by the standard technology nodes. Preferred dopant species are P, B, As, etc., at energies between for example 10keV-500keV and with doses of e.g. 5×10^{12} - 5×10^{13} atoms per cm^2 . The doping is called a V_t -doping and creates a shallow impurity level 17a in the SeOI region 13 and a shallow impurity level 17b in the bulk semiconductor region 11 which can be used for suppressing the threshold voltage (V_t) variations..

Referring to FIG. 3e, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of forming a second impurity level 19a, 19b by doping the SeOI region 13 and the bulk semiconductor region 11 simultaneously again using ion implantation. The ion implantation 16 is performed such that the second impurity level 19a in the SeOI region 13 is under the insulating layer 5 and within the bulk semiconductor substrate 3. The doping is a so called Groundplane-doping (GP) and thus, creates an impurity level 19a, 19b that is deeper than the first impurity level 17a in the SeOI region 13 and the first impurity level 17b in the bulk semiconductor region 11.

Referring to FIG. 3f, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of forming a third impurity level 21a, 21b by doping the SeOI region 13 and the bulk semiconductor region 11 simultaneously again using ion implantation. The ion implantation is performed such that the third impurity level 21a in the SeOI region 13 is below the second impurity level 19a within the base substrate 3 and further away from the insulating layer 5. The doping is a so called Well-doping and thus, creates a deeper impurity level than the second impurity level

19a in the SeOI region 13 and the second impurity level 19b in the bulk semiconductor region 11.

According to variant, the sequence of the ion implantation steps illustrated in FIGs. 3d to 3f can be exchanged, thus performed in any order.

According to a further variant of the first embodiment, the step (d) and (e) can be replaced by a single doping step so as to form a single deeper doping level. That is, the inventive method for manufacturing the hybrid semiconductor substrate 1, according to a variant as shown in FIG. 5, can comprise two doping steps of (1): forming a first impurity level 17a, 17b by doping the SeOI region 13 and the bulk semiconductor region 11 simultaneously as illustrated in FIG. 3d and (2) forming another impurity level 18a, 18b by doping the SeOI region 13 and the bulk semiconductor region 11 simultaneously.

The simultaneous doping is done such that the said impurity level 18a in the SeOI region 13 is under the insulating layer 5 and within the base substrate 3. The said doping is a deeper level doping and thus, creates a deeper impurity level than the first impurity level 17a in the SeOI region 13 and the first impurity level 17b in the bulk semiconductor region 11. Thus, according to this variant, the bulk transistor in the bulk semiconductor region 11 may comprise just two impurity levels.

The second mask 15 is then removed after the above-mentioned implantation steps, e.g. by etching.

Referring to FIG. 3g, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of removing the mask layer 9 from the SeOI region 13. By doing so the first impurity level 17a is removed which is typically not useful for the formation of the electronic devices in the SeOI region 13. The mask layer 9 is typically removed by etching. For the oxide mask usually a HF dip and for nitride for example H_3PO_4 can be used. The dopants in the mask layer 9 have the positive side effect that the etching is achieved faster than in case of an undoped mask layer 9.

Thus, a hybrid semiconductor substrate is achieved in which SeOI transistors formed in the SeOI region 13 comprise two impurity levels 19a, 21a, whereas transistors in the bulk semiconductor region 11, comprise three impurity levels 17b, 19b, 21b.

Referring to FIG. 3h, the inventive method for manufacturing the hybrid semiconductor substrate 1, in the first embodiment, further comprises a step of providing a shallow trench isolation (STI) 23 between the bulk semiconductor region 11 and the SeOI region 13, in particular between electronic devices formed therein, to prevent current leakage between the regions 11 and 13. The regions above the implanted impurity levels 19a, 21a, 17b, 19b, 21b and between the STIs 23 are filled by an oxide layer, preferably CVD deposited silicon oxide, 25a, 25b and a nitride 27a, 27b. The STI densification is at the same time used as an implant activation anneal step.

With the above described manufacturing process, it becomes possible to obtain a hybrid semiconductor substrate 1 in a cost effective manner for the following reasons: both regions of the hybrid semiconductor substrate 1, the bulk semiconductor region 11 and the SeOI region 13 are doped under the same implant conditions using a single doping mask 15. Thus only one protective mask needs to be provided per transistor type (n- or p-type) in the bulk semiconductor region 11, while simultaneously creating the backside electrodes of transistors in the SeOI region 13. For the fabrication of the other type of transistors in the bulk semiconductor region 11 only one additional mask is necessary. Thus, the process for manufacturing a hybrid semiconductor substrate can further be optimized such that a lower cost manufacturing can be achieved.

As the first impurity level 17a, which is not needed for the devices, is contained within the mask layer 9, it can be removed together with the mask layer 9 after any one of the implantation steps illustrated in FIGs. 3d, 3e and 3f. Thus, the mask layer 9 may just be seen as a sacrificial layer.

Furthermore, the implantations conditions can be adjusted such that the deeper impurity level 18a or 19a in the SeOI region 13 is under the insulating layer 5 and within the base substrate 3. Such an implant profile helps in suppressing the threshold voltage (V_t) fluctuations in transistors in the SeOI region 13 and, in case the obtained hybrid

semiconductor substrate 1 is used in SRAM applications, an improved SRAM stability can also be achieved.

A second embodiment of the inventive method is illustrated in FIGs. 4a to 4h. Compared to the first embodiment, an additional spacer 29 is provided in an edge region of the SeOI region 13 adjacent to the bulk semiconductor region 11. The additional spacer 29 extends at least from the surface of the bulk semiconductor substrate 3 till the SeOI layer 7.

The second embodiment comprises essentially the same process steps as in the first embodiment, and therefore the description of the steps illustrated in FIGs. 4a, 4b, 4d – 4f and 4h is not repeated again but is incorporated herewith by reference. Elements having the same reference numerals in FIGs. 3a to 3h and FIGs. 4a to 4h correspond to each other, and their properties are therefore not repeated again in the description of this embodiment, but are incorporated herewith by reference.

According to the second embodiment the inventive method for manufacturing the hybrid semiconductor substrate 1 comprises a step of providing a spacer 29 in an edge region of the SeOI region 13 adjacent to the bulk semiconductor region 11, illustrated in FIG. 4c. The spacer 29 extends at least from the surface of the base substrate 3 till the interface 31 between the SeOI layer 7 and the mask layer 9.

The spacer 29 protects the SeOI layer 7 and the insulating layer 5 of the SeOI region 13 from damage while the mask layer 9 is removed from the hybrid semiconductor substrate 1, e.g. by etching, during the step (i) illustrated in FIG. 3g and FIG. 4g.

According to this embodiment, the spacer 29 is a nitride. A nitride is one example of a suitable material to protect the insulating layer 5 during etching of the mask layer 9, as it has different etching properties compared to the oxide used for the mask layer 9 and the insulating layer 5. This effect is thus achieved for any material choice for the spacer 29 and the mask layer 9 showing different etching properties.

According to a variant of the second embodiment, illustrated in FIG. 6, the spacer 29 extends at least from the surface of the base substrate 3 till the upper surface 33 of the mask layer 9.

Like illustrated in FIG. 4g, the spacer 29 is removed, e.g. by a wet etch using phosphoric acid after the removal of the second mask 15 and the mask layer 9.

The second embodiment of the manufacturing process according to the invention has the additional advantage, that an undercutting of the insulating layer 5 and the SeOI layer 7 during etching of the mask layer 9 can be prevented.

Thus, with the above disclosed embodiments and variants of the manufacturing process of the hybrid semiconductor substrate 1, it is possible to achieve a manufacturing process that is cheaper to carry out as for doping of both regions only one mask 15 needs to be provided. Furthermore it is at the same time possible to control the electrical characteristics of the devices formed on the hybrid semiconductor substrate 1.

CLAIMS

1. A method for manufacturing a hybrid semiconductor substrate comprising the steps of:
 - (a) providing a hybrid semiconductor substrate comprising a semiconductor-on insulator (SeOI) region (13), that comprises an insulating layer (5) over a base substrate (3) and a SeOI layer (7) over the insulating layer (5), and a bulk semiconductor region (11), wherein the SeOI region (13) and the bulk semiconductor region (11) share the same base substrate (3);
 - (b) providing a mask layer (9) over the SeOI region (13); and
 - (c) forming a first impurity level (17a, 17b) by doping the SeOI region (13) and the bulk semiconductor region (11) simultaneously such that the first impurity level (17a) in the SeOI region (13) is contained within the mask layer (9).
2. The method for manufacturing a hybrid semiconductor substrate according to claim 1 further comprising a step of:
 - (d) forming a second impurity level (19a, 19b) by doping the SeOI region (13) and the bulk semiconductor region (11) simultaneously such that the second impurity level (19a) in the SeOI region (13) is under the insulating layer (5) and within the base substrate (3).
3. The method for manufacturing a hybrid semiconductor substrate according to claim 2 further comprising a step of:
 - (e) forming a third impurity level (21a, 21b) by doping the SeOI region (13) and the bulk semiconductor region (11) simultaneously such that the third impurity level (21a) in the SeOI region (13) is below the second impurity level (19a) within the base substrate (3) and further away from the insulating layer (5).
4. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 3 further comprising the steps of,

- (g) providing a semiconductor-on-insulator (SeOI) substrate (1a);
forming the mask layer (9) on the SeOI substrate (1a); and
removing a predetermined area of the mask layer (9), the underlying SeOI layer (7) and the underlying insulating layer (5) to obtain the bulk semiconductor region (11).
5. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 4, comprising a step:
 - (h) providing a second mask (15) with a predetermined pattern over the hybrid semiconductor substrate to prevent the formation of an impurity level in the area masked by the second mask (15) during at least one of steps c), d) and e).
 6. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 5 comprising a step of
 - (i) removing the mask layer (9) from the SeOI region (13) after step c).
 7. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 6, wherein the mask layer (9) and/or the insulating layer (5) is made of an oxide.
 8. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 7 further comprising a step of:
 - (j) providing a spacer (29) in an edge region of the SeOI region (13) adjacent to the bulk semiconductor region (11) such that the spacer (29) extends at least from the surface of the base substrate (3) till the SeOI layer (7).
 9. The method for manufacturing a hybrid semiconductor substrate according to claim 8 further comprising a step of removing the spacer (29), in particular after step (j).

10. The method for manufacturing a hybrid semiconductor substrate according to one of claims 8 or 9, wherein the spacer (29) is made of a different material than the mask layer (9), in particular is a nitride.
11. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 10, wherein the mask layer (9) has a thickness of at least 20 nm, in particular, the thickness of the mask layer (9) is not less than 20 nm and not more than 30 nm.
12. The method for manufacturing a hybrid semiconductor substrate according to one of claims 1 to 11, wherein the SeOI layer (7) has a thickness of at most 20 nm, in particular, the thickness of the SeOI layer (7) is not less than 10 nm and not more than 20 nm, and/or

wherein the insulating layer (5) has a thickness of at most 20 nm, in particular, the thickness of the insulating layer (5) is not less than 10 nm and not more than 20 nm.

13. The method for manufacturing a hybrid semiconductor substrate according to claims 1 to 12, further comprising a step of providing a shallow trench isolation (STI) (23) to separate the SeOI region (13) and the bulk semiconductor region (11).
14. A hybrid semiconductor substrate comprising:
 - a semiconductor-on-insulator (SeOI) region (13), wherein the SeOI region (13) comprises a base substrate (3), an insulating layer (5) over the base substrate (3), a SeOI layer (7) over the insulating layer (5) and a mask layer (9) over the SeOI layer (7);
 - a bulk semiconductor region (11) provided adjacent to the SeOI region (13); and
 - a first impurity region (17a, 17b) in the SeOI region (13) and the bulk semiconductor region (11) wherein the first impurity region (17a) in the SeOI region (13) is contained within the mask layer (9).

15. The hybrid semiconductor substrate according to claim 14, wherein in the SeOI region (13) and the bulk semiconductor region (11) share the same base substrate (3).
16. The hybrid semiconductor device according to claim 15, further comprising a second impurity region (19a, 19b) in the SeOI region (13) and the bulk semiconductor region (11) wherein the second impurity region (19a) in the SeOI region (13) is under the insulating layer (5) and within the base substrate (3).
17. The hybrid semiconductor device according to claim 16, further comprising a third impurity region (21a, 21b) in the SeOI region (13) and the bulk semiconductor region (11) wherein the third impurity region (21a) in the SeOI region (13) is below the second impurity region (19a) within the base substrate (3) and further away from the insulating layer (5).