

SMALL-PORE CALCIUM HYDROXIDE PARTICLES
AND METHOD FOR MANUFACTURING SAME

5

Subject of the invention

[0001] The present invention relates to calcium hydroxide particles having a large number of small pores, making them particularly suitable for treating flue gases containing acid pollutants. It also relates to a method allowing the preparation of these calcium hydroxide particles having distinctive properties.

10

Technological background

[0002] Calcium hydroxide is known for its efficient treatment of flue gases containing acid pollutants, *inter alia* over a range of temperatures lower than 170°C. In general, one of the acids that is most difficult to capture in flue gases using reagents of calcium type is SO₂.

15

[0003] To capture acids contained in flue gases, the properties to be optimised are specific surface area, generally measured with the BET method (Brunauer-Emmett-Teller) i.e. the surface area of the particles accessible to acids, and pore volume generally measured with the BJH method (Barrett-Joyner-Halenda) i.e. the volume able to capture acids before they react with Ca(OH)₂. Hydrate producers have been continually striving for several decades to improve these characteristics. There are several generations of calcium hydrate that can be classified as follows.

20

[0004] Generation « 0 » is composed of an ordinary, dry Ca(OH)₂ hydrate having a residual H₂O percentage lower than 1 %. This hydrate is derived from a conventional hydration method followed by grinding to obtain an application-related particle size, and typically having a particle size of less than 150 µm.

25

[0005] Improved generation « 0 » differs from generation 0 in that the particles are subjected to selection to retain only the largest particles having greater pore volume and hence improved properties for flue gas treatment. The typical properties of this product are a specific surface area of 20 m²/g and pore volume 0.09 cm³/g.

30

[0006] Next, generation 1 was developed with the addition of an additive in the manufacturing process to increase specific surface area. This additive has the effect of delaying the hydration reaction, which imparts special properties to the hydrates. Excess water is generally used for hydration with 5 to 10 % residual water. Humidity must not be too high to allow optional grinding in a mill. This is the product described in patent EP 0 558 522. The specific surface area of this type of $\text{Ca}(\text{OH})_2$ is approximately 40-50 m^2/g , but the pore volume remains lower than 0.1 cm^3/g with values in the region of 0.08 cm^3/g .

[0007] Finally, generation « 2 » emerged with a two-step method:

- 10 - hydration in a hydrator with up to 20-30 % residual H_2O ;
- flash drying at over 350°C in a controlled atmosphere followed by grinding.

The $\text{Ca}(\text{OH})_2$ produced with this method has a large specific surface area in the region of 40 m^2/g and also a large pore volume of approximately 0.2 cm^3/g . This type of hydroxide is described in patent EP 0 861 209. The presence of a large specific surface area enables the acid molecules contained in flue gases to easily enter into the pores, and a large total pore volume allows the reaction between the acid molecules and $\text{Ca}(\text{OH})_2$ at the pore walls. It is therefore chiefly within the pores that acid capture takes place.

[0008] In the current state of knowledge, there is every reason to believe that the entire reaction occurs on the surface of the pores. Indeed, the diffusion of SO_2 through a layer of formed CaSO_3 or CaSO_4 takes a certain time, which is not compatible with some existing flue gas treatment equipment, hence the advantage of having the greatest volume of accessible pores.

[0009] Total pore volume is not the only determining factor. The diameter of these pores is of major importance too. For example, patent EP 0 861 209 recommends giving preference to pores having a diameter of between 100 and 400 Angströms. It therefore claims the majority presence of medium-size pores.

[0010] Yet, SO_2 molecules have a molecular diameter of about 3.8 Angströms. Pores of medium size between 100-400 Angströms are therefore much larger than the molecules to be captured. It could therefore prove to be more judicious to give preference to hydrates having smaller pores.

[0011] Document JP 2005350343 discloses a method for increasing pore volume using varied additives such as diethylene glycol, sorbitol and by coating the particles of hydrated lime with a silicone-based resin. The method uses a large excess of water in proportions of 1.5 to 5, preferably 3.2 times, the amounts theoretically required for the hydration reaction of lime. However, it only recommends a final residual humidity after two contacting steps with water of between 35 and 55 % after pressing, and a residual water value before drying of 35 to 45 % being preferred. The calcium hydroxide obtained has a BET specific surface area larger than 30 m²/g and a total pore volume (20-1000 Å) in the region of 0.30 cm³/g. However, this document does not mention either the CaO content in the starting lime or the pore volume contained in the fraction of pores of 20 to 100 Å. Solely the global pore volume for pores of 20 to 1000 Å is mentioned.

[0012] Document JP 2002029738 discloses a method intended to increase pore volume without reducing bulk density. For this purpose, the particles of calcium hydroxide are simultaneously subjected to grinding and compaction to reduce storage space. This document does not give any information on the residual humidity level of the calcium hydroxide produced, or on the characteristics of the starting reagent. It does not focus on the impact of the relationship between pore size and pore volume, in particular on the fraction of pores smaller than 100 Å, and on the absorption capacity of effluent gases.

[0013] Document EP 2 039 655 discloses a hydration method in the presence of an additive targeting residual humidity before drying of between 35 and 55 %. This document does not give information on the CaO content of the reagent.

Aims of the invention

[0014] The present invention aims to produce calcium hydrates having very small pores to improve acid capture. More specifically, the present invention aims to develop a new generation of calcium hydrates with a large proportion of pores having a diameter smaller than 200 Å, preferably smaller than 100 Å, whilst maintaining a high total pore volume.

Brief description of the figures

[0015] The characteristics and advantages of the present invention will become apparent on reading the detailed description below referring to Figures 1 to 5.

5 [0016] Figures 1 and 2 respectively illustrate the BJH volume distribution and surface area distribution of the pores as a function of their diameter per interval of 100 Å with the exception of the first range extending between 20 and 100 Å.

[0017] Figures 3 and 4 illustrate partial pore volume as a function of partial specific surface area for diameter ranges 20-100 Å and 20-200 Å, respectively.

10 [0018] Figure 5 illustrates the volume distribution of the pores as a function of their diameter per interval of 100 Å before and after SO₂ capture

Main characteristic elements of the invention

[0019] The present invention relates to calcium hydroxide particles having a total pore volume greater than 0.18 cm³/g, said total pore volume being calculated using the BJH method for a pore range having a diameter of between 20 and 1000 Å, said particles being characterized in that the BJH partial pore volume for the range of pores having a diameter of between 20 and 100 Å corresponds to more than 20 % of said BJH total pore volume.

20 [0020] In particular embodiments of the invention, the calcium hydroxide particles have at least one or a suitable combination of the following characteristics:

- the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å corresponds to more than 40 % of said BJH total pore volume;
 - the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å correspond to more than 50 % of said BNH total pore volume;
 - the BJH partial pore volume for the range of pores having a diameter of between 20 and 100 Å is greater than 0.04 cm³/g, and preferably greater than 0.05 cm³/g;
 - the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å is greater than 0.06 cm³/g, preferably greater than 0.09 cm³/g, and more preferably greater than 0.1 cm³/g;
- 30

- they have a BET specific surface area larger than 40 m²/g, preferably larger than 45 m²/g, and more preferably larger than 50 m²/g.

[0021] The present invention also relates to the method for preparing the above-described calcium hydroxide particles, comprising the steps of:

- 5 - mixing, with water and a hydration-delaying additive, a base material having a calcium oxide content determined as per standard EN 459-2 - paragraph 5.8, higher than 90 weight %, the water/base material weight ratio in said mixture is between 0.9 and 1.2, and said mixture having residual humidity higher than 20 weight % and lower than 30 weight %;
- 10 - drying said mixture to a form a hydrate having residual humidity lower than 2 % and preferably lower than 1 % by weight.

[0022] In some particular embodiments of the invention, the method comprises at least one or a suitable combination of the following characteristics:

- said calcium oxide content is higher than 93 %;
- 15 - the MgO content is 2 weight % or lower;
- the water/base material weight ratio in said mixture is between 1 and 1.05;
- the content of additive is 0.4 weight % or higher, preferably between 0.5 and 5 weight %, more preferably between 0.5 and 4.5 weight %, further preferably between 0.5 and 2.5 weight %, or from 0.5 to 1.5 weight % relative to the base
- 20 material;
- the hydration-delaying additive is selected from the list comprising ethylene glycol, diethylene glycol, triethylene glycol, monoethanolamine, diethanolamine, triethanolamine, monopropylene glycol, dipropylene glycol, the mixtures and derivative products thereof;
- 25 - the base material has a T₆₀ longer than 50s, preferably longer than 60s, and more preferably longer than 100s.

[0023] It also relates to the method for purifying flue gases, comprising the step of using the calcium hydroxide particles such as described above.

30 **Detailed description of the invention**

[0024] The present invention relates to calcium hydroxide particles combining a large specific surface area and large pore volume with a sizeable proportion of pores having a diameter smaller than 200 Å (<20 nm). More specifically, the calcium hydroxide particles of the invention have a BET specific surface area larger than 40 m²/g, preferably larger than 45 m²/g, more preferably larger than 50 m²/g. The BJH total pore volume of pores having a diameter of between 20 and 1000 Å (2 to 100 nm) is greater than 0.14 cm³/g, preferably greater than 0.16 cm³/g, and more preferably greater than 0.18 cm³/g and even 0.19 cm³/g. The partial pore volume for the range of pores having a diameter of between 20 and 200 Å is greater than 0.06 cm³/g, preferably greater than 0.08 cm³/g, more preferably greater than 0.1 cm³/g. Within this range of pore diameters smaller than 200 Å, the partial pore volume for pores of diameter between 20 and 100 Å is greater than 0.04 cm³/g, preferably greater than 0.045 cm³/g, and further preferably greater than 0.05 cm³/g. In percent terms, more than 18 % and preferably more than 20 % of the total pore volume is found in the range of pores having a diameter of between 20 and 100 Å (2 to 10 nm). For the 20 to 200 Å range (2 to 20 nm), more than 40 %, preferably more than 45 %, and more preferably more than 50 % of the total pore volume is found therein.

[0025] To manufacture Ca(OH)₂ particles having these properties, the method of the invention combines the following characteristics: use of a base lime having high CaO content, hydration thereof in the presence of a hydration-delaying additive to form a mixture having residual humidity higher than 20 weight % and preferably lower than 30 weight %. In the presence of lime with high CaO content, the additive allows the generation of small pores and the high level of residual humidity allows the pore volume in this range of small pores to be increased. As a result, this particular ratio of specific surface area/pore volume allows optimisation of the reactive surface area available for sorption of acid gases.

[0026] More specifically, the method of the invention comprises the following steps:

- Providing lime particles having an available CaO content higher than 90 %, and more preferably higher than 93 % by weight. By available CaO content, it is meant the content contained in the quicklime, and optionally in the hydrate in the event that

slight hydration of lime occurs at the inlet to the hydrator. This content does not include the CaO contained in the carbonate (CaCO_3) and in the sulphate (CaSO_4) which are not effective for subsequent capture of SO_2 in flue gases. The lime particles also have a sulphur content that is as low as possible, namely below 0.2 % and preferably between 0.01 and 0.07 % by weight. The MgO content thereof is lower than 8 %, and preferably lower than 3 % and even 2 % by weight, and the CO_2 content is 1.5 weight % or lower. As is conventional, the lime may also contain impurities such as aluminium oxide, iron, manganese or silicon.

The lime particles typically have a particle size distribution of between 0 and 2 mm, 0 and 10 mm, 2 and 10 mm or 5 and 25 mm. The lime can also be milled lime of micrometric size, for example having a particle size distribution of between 0 and 100 μm .

- Hydration is performed with a water/lime weight ratio of between 0.9 and 1.2 and preferably between 1 and 1.05, to obtain a mixture having residual humidity of 20 % or higher and preferably between 25 % et 30 % by weight. Typically, the temperature of the water is between 10 and 40 °C. Hydration is performed in the presence of a hydration-delaying additive comprising at least one alcohol chemical function (-O-H) and/or (NH_x , with $x = 1.2$ or 4) in a proportion of at least 0.4 weight % relative to the lime fed into the hydrator. Preferably, the content of additive is between 0.5 and 5 weight %, but for reasons of economy it is rather more limited to a range of 0.5 to 4.5 weight %, further preferably 0.5 to 3.5 weight %, even 0.5 to 2.5 % or even between 0.5 and 1.5 weight %. The additive is selected from the non-exhaustive list comprising ethylene glycol, diethylene glycol, triethylene glycol, monoethanolamine, diethanolamine, triethanolamine, monopropylene glycol, dipropylene glycol, the mixtures and derivative products thereof.
- The mixture thus obtained is then dried to reduce residual humidity to less than 2 % and preferably less than 1 % by weight. For drying hot air is used, previously heated through an exchanger in which a combustion gas circulates. Drying is conducted without direct contact between the combustion gas and the hydrate. Typically, drying is carried out in an ultra-rapid dryer. Drying takes place within a maximum of

2 or 3 seconds with hot air at a temperature of 300-400 °C. On leaving the dryer, the hydrate has a temperature of between about 85 and 90°C.

- Finally, the hydrate is ground to reduce the particle size to below 200 µm, and preferably below 150 µm.

5 **[0027]** To illustrate the invention, different powders of calcium hydroxide were prepared.

Examples

10 **[0028]** As raw materials, several limes having different CaO/MgO contents, different particle sizes and different reactivity were used. Tables 1 to 6 give the different samples tested. Samples 1 to 4 and 10 to 14 are comparative examples, and samples 5 to 9 and 15 to 18 are examples representing the invention. These Tables indicate the weight content of available lime which includes quicklime CaO and the hydrate Ca(OH)₂, determined according to standard EN 459-2 (September 2010 version), paragraph 5.8. They also indicate the MgO content determined according to 15 this same standard, paragraph 5.2. The reactivity of quicklime was evaluated in usual manner using T₆₀, a parameter corresponding to the time needed to raise the temperature of the lime/slaking water system up to 60°C, slaking of the lime being conducted following the protocol of paragraph 6.6 of above-mentioned standard 20 EN 459-2.

25 **[0029]** The parameters of the method given in Tables 2 and 5 were modulated by acting on the following parameters, taken alone or in combination, for the different samples: residual humidity before drying close to 20 % or in the region of 20-25 % by weight, without or with additive, and in the latter case two types of additive were tested (DEG for diethylene glycol or TEA for triethanolamine).

30 **[0030]** The hydrates obtained were characterized as follows. The BET specific surface area of the powders was measured in accordance with standard ISO9277, second Edition of September 1st, 2010. The total pore volume and pore distribution as a function of pore diameter were calculated based on the step-by-step analysis of the isotherm desorption branch using the BJH method of Barrett, Joyner and Halenda (1951), conventionally used with 77K nitrogen as adsorbent gas. The method is

described in standard DIN66134 (February 1998 version). It allows the calculation of pore volume distribution as a function of pore diameter on the assumption that the pores are cylindrical. Total pore volume and pore volume distribution were determined for the range of pores having a diameter ranging from 20 to 1000 Å. The results are given below per interval of 100 Å (20-100 Å, 100-200 Å, 200-300 Å, etc.). On the basis of pore volume distribution determined with the BJH method, the BJH surface area distribution of the pores was also calculated per interval of 100 Å again assuming the pores are cylindrical.

[0031] Figures 1 and 2 respectively illustrate the volume distribution and surface area distribution of the pores per interval of 100 Å for Examples 1 to 9. Figures 3 and 4 respectively illustrate the partial pore volume as a function of partial specific surface area for the intervals 20-100 and 20-200 Å, with a dotted line delimiting the results of comparative tests and the results of tests according to the invention. For the different samples, Table 3 gives the BET total specific surface area, BJH total pore volume, BJH partial pore volume and BJH partial specific surface area for the ranges 20-100 and 20-200 Å. The ratio expressed in percent between the partial pore volumes and total pore volume for these ranges is also given.

[0032] For samples 5 to 9 representing the invention, a distinct increase is observed in BJH total pore volume and BET specific surface area, compared with the comparative samples (Tables 3 and 6). The BET specific surface area is larger than 40 m²/g and even larger than 50 m²/g for samples 5 to 9. A smaller specific surface area of 43 m²/g is observed for comparative sample 10. This decrease is attributed to the MgO content, higher than 2 %, the corollary of which is a lower content of available CaO (Table 4). For the samples of the invention, the BJH total pore volume is greater than 0.14 cm³/g, even greater than 0.19 cm³/g for samples 5 to 9. Compared with the comparative samples, the partial pore volume is significantly increased in the 20-100 Å range with values greater than 0.04 cm³/g even greater than 0.05 cm³/g. In the 20-200 Å range, the partial pore volume increases to above 0.08 cm³/g and even above 0.09 cm³/g for samples 5 to 9. Within these samples 5 to 9 having close MgO contents, Figures 3 and 4 show that sample 8 having a lower T₆₀ i.e. stronger reactivity,

exhibits a less favourable balance between pore volume/specific surface area for the ranges 20-100 and 20-200 Å, compared with samples 5-7 and 9.

5

	Sample N°	MgO	Available CaO	T60	Particle size
		wt. %		s	mm
Comparative	1	0.58	96	125	0-10
	2	0.53	93.5	108	0-10
	3	0.55	94.2	70	0-10
	4	0.52	98	90	0-10
Invention	5	0.40	95	107	0-10
	6	0.53	95.1	98	0-10
	7	0.67	93.8	262	0-2
	8	0.59	95.5	57	2-10
	9	0.58	96.9	125	0-10

Table 1

	Sample N°	Additive		H ₂ O/lime	Residual H ₂ O after hydration/before drying
		wt. %	type	wt. %	
Comparative	1	0	/	0.6	0.6
	2	0	/	0.6	0.6
	3	0	/	1.05	22.9
	4	1	DEG	0.6	0.7
Invention	5	1	DEG	1.05	25
	6	1	TEA	1.05	22.2
	7	1	DEG	1.05	25
	8	1	DEG	1.05	25
	9	1	DEG	1.05	22.2

Table 2

10

	Sample N°	BET SSA (m ² :g)	BJH PV (cm ³ /g)					BJH SSA (m ² /g)	
			total	partial		partial		partial	
			20 - 1000 Å°	20 - 100 Å°	% of total	20 - 200 Å°	% of total	20 - 100 Å°	20 - 200 Å°
Com	1	23	0.100	0.018	18	0.038	38	13	17
	2	18	0.085	0.014	17	0.031	37	10	14

Invention	3	25	0.154	0.017	11	0.039	25	11	16
	4	31	0.111	0.032	29	0.055	50	21	26
	5	55	0.195	0.053	27	0.115	59	34	48
	6	55	0.196	0.057	29	0.097	50	38	47
	7	57	0.209	0.051	24	0.107	51	34	47
	8	53	0.218	0.045	21	0.104	48	29	42
	9	56	0.194	0.053	28	0.116	60	35	49

Table 3

- [0033]** The capacity of SO₂ sorption by the hydrated lime of the invention was measured statically for samples 1, 7, 8 and 9 as follows. A given quantity of sample, here approximately 0.5 to 1 g, was placed in a reactor between two beds of quartz wool. The assembly was placed in an oven at 150°C. Prior to the SO₂ sorption test, the reactor containing the sample was flushed with a stream of dry air to remove humidity from the sample, typically of between 0 and 1 %, which could impact results. The stream of dry air was then replaced by a mixture of humidified air and gas containing SO₂ and CO₂. The mixture thus generated comprised 358 ppmv of SO₂, 4.5 % of CO₂ by volume and 10 g/m³ of H₂O. The whole was injected into a loop bypassing the sample until a constant concentration was measured at the outlet of the circuit. Only then was the reactor containing the sample flushed with the mixture at a flow rate of 150 ml/min. The quantity of outgoing SO₂ was measured with a micro-chromatograph (μ -GC). The amount of SO₂ captured by the sample is equal to the difference between the amount of ingoing SO₂ at the inlet of the reactor and the amount of outgoing SO₂ at the outlet of the reactor, integrated over the entire flushing time of the sample with the gas mixture until the concentration of outgoing SO₂ is equal to 90 % of the starting concentration. For samples 1, 7, 8 and 9, the percent of captured mass i.e. the amount of captured SO₂ relative to the mass of the sample was respectively 4; 7; 5.7 and 6.2 %.
- Compared with reference 1, the SO₂ sorption capacity was 30 % to 42 % higher for the samples of the invention. Sample 8 exhibited lower sorption capacity than samples 7 and 9, which can be accounted for by the less favourable balance between pore volume and specific surface area for the ranges 20-100 and 20-200 Å as previously mentioned.
- [0034]** Analysis of pore volume distribution after SO₂ capture, performed on sample 9, showed that the pores having a diameter smaller than 200 Å and more

specifically those having a diameter smaller than 100 Å are most useful for capturing SO₂ (Figure 5). Therefore, in the 20-100 Å range, the pore volume was reduced by almost 50 % after SO₂ capture, and by almost 20 % in the 100-200 Å range. Over and above 200 Å, the reduction in pore volume was no longer significant. This confirms that very small pores having a diameter of less than 200 Å, and preferably less than 100 Å, are particularly useful for SO₂ capture.

Examples 10 to 18

These examples were performed to demonstrate the pertinence of the lime hydration method to obtain a significant pore volume within the fraction of pores between 20 and 100 Å.

Examples 10 to 14 are comparative examples, and examples 15 to 18 are examples of the invention.

Examples 10 and 11 have an available CaO concentration that is too low and lower than the concentration of the invention, and the total pore volume obtained is too small. Examples 12 and 13 were carried out outside the H₂O/lime concentration of 0.9 to 1.2 which led to a residual H₂O content after hydration and before drying of 9.7 % and 35 % respectively, which finally led to an insufficient total pore volume (20-1000 Å) or partial pore volume (20-100 Å). Example 14 only contained 0.25 % of hydration-delaying additive (diethylene glycol), which led to a partial pore volume percentage in the 20 à 100 Å fraction that was too low.

Sample N°	MgO	Available CaO	T60	Particle size
	wt. %		s	mm
10	2.25	91.9	105	0-20
11	4.72	89.9	150	0-10
12	0.53	95	95	0-10
13	0.53	95	95	0-10
14	0.53	95	95	0-10
15	0.53	95	95	0-10
16	0.53	95	95	0-10
17	0.53	95	95	0-10
18	0.53	95	95	0-10

Table 4

Sample N°	Additive		H ₂ O/lime	Residual H ₂ O after hydration/before drying
	wt. %	Type	wt. %	
10	1%	DEG	1.05	25.9
11	2%	DEG	1	24.1
12	1%	DEG	1.3	35
13	1%	DEG	0.8	9.7
14	0.25%	DEG	1.05	24.6
15	2%	DEG	1.05	23.5
16	2.50%	DEG	1.05	25.8
17	3.50%	DEG	1.05	25.9
18	4.50%	DEG	1.05	27.4

Table 5

Sample N°	BET SSA (m ² /g)	BJH PV (cm ³ /g)				
		total	partial		partial	
		20-1000 Å	20-100 Å	% total	20-200 Å	% total
10	43	0.14	0.047	34	0.08	57
11	44.6	0.132	0.017	13	0.038	29
12	37.43	0.222	0.023	10	0.081	36
13	44.2	0.132	0.034	26	0.049	37
14	33.64	0.195	0.024	12	0.078	40
15	50.22	0.227	0.064	28	0.138	61
16	52.67	0.225	0.054	24	0.123	55
17	52.51	0.219	0.056	26	0.125	57
18	56.56	0.222	0.058	26	0.117	53

Table 6

- 5 Examples 15 to 18 of the invention were performed with a concentration of available CaO of 95 %, with a water/lime proportion of 1.05 leading to residual humidity of between 23.5 and 27.4 %. The quantity of hydration-delaying additive (DEG) was in the range of 2 to 4.5 % by weight.

10 All these parameters allowed to obtain BJH pore volumes (20-1000 Å) that were greater than 0.219 cm³/g, a BET specific surface area larger than 50 m²/g and partial pore volume for the 20 à 100 Å pore range greater than 0.05 cm³/g.

CLAIMS

1. Calcium hydroxide particles having a total pore volume greater than 0.18 cm³/g, said total pore volume being calculated with the BJH method for a range of pores having a diameter of between 20 and 1000 Å, said particles being characterized
5 in that the BJH partial pore volume for the range of pores having a diameter of between 20 and 100 Å corresponds to more than 20 % of said BJH total pore volume calculated using the method described in standard DIN 66134 (February 1998 version).

2. The particles according to Claim 1, wherein the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å corresponds
10 to more than 40 % of said BJH total pore volume.

3. The particles according to Claim 2, wherein the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å corresponds to more than 50 % of said BJH total pore volume.

4. The particles according to any of the preceding claims, wherein the
15 BJH partial pore volume for the range of pores having a diameter of between 20 and 100 Å is greater than 0.04 and preferably greater than 0.05 cm³/g.

5. The particles according to any of the preceding claims, wherein the BJH partial pore volume for the range of pores having a diameter of between 20 and 200 Å is greater than 0.06 cm³/g, preferably greater than 0.09 cm³/g, more preferably
20 greater than 0.1 cm³/g.

6. The particles according to any of the preceding claims, having a BET specific surface area larger than 40 m²/g, preferably larger than 45 m²/g, more preferably larger than 50 m²/g measured according to standard ISO9277 (September 2010 version).

25 7. The particles according to any of the preceding claims, wherein said BJH total pore volume is greater than 0.19 cm³/g.

8. Method for preparing calcium hydroxide particles according to any of the preceding claims, comprising the steps of:

- mixing a base material, having a calcium oxide content higher than 93 weight %, this
30 content being determined according to standard EN 459-2 - paragraph 5.8 (September 2010 version), with water comprising a hydration-delaying additive

comprising at least one chemical function OH and/or NH_x (with x = 1, 2 or 4), the water/base material weight ratio of the mixture being between 0.9 and 1.2; said mixture having residual humidity after the hydration reaction of 20 weight % or higher and lower than 30 weight %;

- 5 - drying said mixture to form a hydrate having residual humidity lower than 2 % and preferably lower than 1 % by weight.

9. The method according to Claim 8, wherein the MgO content is lower than 8 % and preferably lower than 3 % by weight.

10 10. The method according to any of Claims 8 to 9, wherein the water/base material weight ratio in said mixture is between 1 and 1.05.

11. The method according to any of Claims 8 to 10, wherein the content of additive is 0.4 weight % or higher, preferably between 0.5 and 5 weight %, more preferably between 0.5 and 4.5 weight %, further preferably between 0.5 and 2.5 weight %, or between 0.5 and 1.5 weight % relative to the base material.

15 12. The method according to any of Claims 8 to 11, wherein the hydration-delaying additive comprising at least one chemical OH and/or NH_x function is selected from the list comprising ethylene glycol, diethylene glycol, triethylene glycol, monoethanolamine, diethanolamine, triethanolamine, monopropylene glycol, dipropylene glycol, the mixtures and derivative products thereof.

20 13. The method according to any of Claims 8 to 12, wherein the base material has a T₆₀ longer than 50 s, preferably longer than 60 s, and further preferably longer than 100 s, T₆₀ being measured according to standard EN 459-2, paragraph 6.6 (September 2010 version).

25 14. Method for treating flue gases, comprising a step to use the calcium hydroxide particles according to any of Claims 1 to 7.