

[DESCRIPTION]

[TITLE OF THE INVENTION]

METHOD OF ELECTROCHEMICALLY PRODUCING HYDROGEL,
METHOD OF PRODUCING HYDROGEL WITH PATTERN FORMED
5 OF CELLS, HYDROGEL PRODUCTION APPARATUS, AND
TRANSDUCER

[TECHNICAL FIELD]

[0001] The present invention relates to a method of electrochemically
10 producing a hydrogel by using electrolytic deposition, a method of
producing a hydrogel with a pattern formed of cells, a hydrogel production
apparatus, and a transducer.

[BACKGROUND ART]

15 [0002] A hydrogel is used as a scaffold for cell culture, for example. A
method of electrochemically producing a hydrogel by using electrolytic
deposition is known.

[0003] Non-patent Literature 1 and Non-patent Literature 2 disclose
methods of electrolytically depositing, on an indium tin oxide (ITO)
20 electrode with a pattern, a hydrogel corresponding to the pattern. Non-
patent Literature 3 and Non-patent Literature 4 disclose methods of
electrolytically depositing a hydrogel by using a Pt wire electrode or by
making a Pt wire electrode perform scanning in an electrolytic solution.
Non-patent Literature 5 and Non-patent Literature 6 disclose techniques of
25 electrolytically depositing a hydrogel or the like, by applying a voltage to

one electrode selected from two electrodes or from among one-dimensional array of electrodes or, on the electrode.

[PRIOR ART LITERATURE]

5 [NON-PATENT LITERATURE]

[0004] Non-patent Literature 1: F. Ozawa et al., "Cell Sheet Fabrication Using RGD Peptide-Coupled Alginate Hydrogels Fabricated by an Electrodeposition Method", Chemistry Letters, Vol. 46, No. 4, pp 605-608, Advance Publication on the web February 10, 2017.

10 <<http://www.journal.csj.jp/doi/pdf/10.1246/cl.170003>>

Non-patent Literature 2: F. Ozawa et al., "Alginate gel microwell arrays using electrodeposition for three-dimensional cell culture", Lab on a Chip, 2013, 13(15), pp 3128-3135.

<<http://pubs.rsc.org/en/Content/ArticleLanding/2013/LC/c3lc50455g#!div>

15 Abstract>

Non-patent Literature 3: F. Ozawa et al., "Electrochemical Hydrogel Lithography of Calcium-Alginate Hydrogels for Cell Culture", Materials, 2016, 9(9), 744. <<http://www.mdpi.com/1996-1944/9/9/744>>

Non-patent Literature 4: F. Ozawa et al., "Electrodeposition of
20 alginate gels for construction of vascular-like structures", Journal of Bioscience and Bioengineering, 2013, VOL 115, No. 4, pp 459-461.
<<http://www.sciencedirect.com/science/article/pii/S1389172312004409?via%3Dihub>>

Non-patent Literature 5: K. M. Gray et al., "Electrodeposition of a
25 Biopolymeric Hydrogel: Potential for One-Step Protein Electroaddressing",

Biomacromolecules, 2012, 13(4), pp 1181-1189.

<<http://pubs.acs.org/doi/abs/10.1021/bm3001155>>

Non-patent Literature 6: H. Yi et al., "Signal-Directed sequential
Assembly of Biomolecules on Patterned surfaces", Langmuir, 2005, 21(6),
5 pp 2104-2107. <<http://pubs.acs.org/doi/abs/10.1021/la047529k>>

[SUMMARY OF THE INVENTION]

[PROBLEMS TO BE SOLVED BY THE INVENTION]

[0005] Non-patent Literatures 1 to 6 disclose the methods of
10 electrolytically depositing a hydrogel. However, with the methods
disclosed in Non-patent Literatures 1 and 2, only two-dimensional
patterning can be performed. In addition, since the methods disclosed in
Non-patent Literatures 1 and 2 make it necessary to produce an electrode
for each pattern, the methods lack versatility. The methods disclosed in
15 Non-patent Literatures 3 and 4 are methods by which a pattern is formed
by using wire scanning, which is an extremely difficult and inefficient
means, and can only form a limited and specific three-dimensional shape
such as a tube. The techniques disclosed in Non-patent Literatures 5 and 6
are techniques of forming a hydrogel on one selected electrode and do not
20 aim to perform shaping.

[0006] The present invention provides a technique of electrochemically
producing a hydrogel, the technique that has a higher degree of flexibility
in shaping, has greater versatility, and can form a hydrogel with a two-
dimensional pattern or a three-dimensional pattern more efficiently than
25 ever before.

[MEANS TO SOLVE THE PROBLEMS]

[0007] According to an invention of Claim 1, a method of electrochemically producing a hydrogel by using electrolytic deposition of a hydrogel, the method by which a hydrogel is formed by a reaction which is induced in an electrolytic solution by an electrode product electrochemically generated by electrodes installed in the electrolytic solution, includes a step of preparing an apparatus including an electrolytic tank with a bottom surface on which a two-dimensional array of working electrodes is provided and a counter electrode which is installed in the electrolytic tank, housing an electrolytic solution containing a dissolved substance, which causes electrolytic deposition of the hydrogel, in the electrolytic tank, and, by applying a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes, forming, on the bottom surface, the hydrogel with a two-dimensionally defined pattern corresponding to the arrangement of the selected working electrodes.

[0008] In an invention of Claim 2, the invention of Claim 1 includes: a first step of forming a hydrogel with a two-dimensionally defined first pattern by applying a first voltage as the predetermined voltage to a first working electrode group as the one or more selected working electrodes; and a second step of forming a hydrogel with a two-dimensionally defined second pattern by applying a second voltage as the predetermined voltage to a second working electrode group as the one or more selected working electrodes. The second step is performed after the first step, and a

hydrogel with a three-dimensionally defined pattern including at least two layers formed of the first pattern and the second pattern, which is located under the first pattern on the side thereof closer to the bottom surface, is formed.

5 **[0009]** In an invention of Claim 3, in the invention of Claim 2, at least one of the first step and the second step includes a first sub-step and a second sub-step, a corresponding one of the first working electrode group and the second working electrode group includes a first working electrode sub-group and a second working electrode sub-group, a corresponding one
10 of the first voltage and the second voltage includes a first sub-voltage and a second sub-voltage, and a corresponding one of the first pattern and the second pattern includes a first sub-pattern and a second sub-pattern. The second working electrode sub-group consists of only the working electrode which does not belong to the first working electrode sub-group. A
15 hydrogel with the first sub-pattern is formed by applying the first sub-voltage to the first working electrode sub-group and a hydrogel with the second sub-pattern is formed by applying the second sub-voltage to the second working electrode sub-group.

20 **[0010]** In an invention of Claim 4, in the invention of Claim 3, in the second sub-step, a hydrogel which dissolves under a predetermined condition is formed. The invention of Claim 3 further includes, at least after the first sub-step and the second sub-step, a sub-pattern removal step of selectively removing the hydrogel with the second sub-pattern by dissolving the hydrogel with the second sub-pattern by providing the
25 hydrogel with the second sub-pattern with the predetermined condition.

[0011] In an invention of Claim 5, in the invention of any one of Claims 2 to 4, a Z stage that has an adhesion surface facing the bottom surface parallel thereto and is displaceable in a Z direction perpendicular to the bottom surface is further prepared. By performing the first step with the Z stage being located in the electrolytic solution such that the adhesion surface is apart from the bottom surface by a first distance, a hydrogel with the first pattern whose upper surface, of two surfaces perpendicular to the Z direction, on the side farther apart from the bottom surface adheres to the adhesion surface is formed. After that, by displacing the Z stage with the adhesion surface, to which the upper surface of the first pattern adheres, in a direction in which the Z stage moves away from the bottom surface, a lower surface, of the two surfaces perpendicular to the Z direction, of the first pattern on the side closer to the bottom surface is moved away from the bottom surface by a second distance. By performing the second step with the first pattern being located in the electrolytic solution such that the lower surface is apart from the bottom surface by the second distance, a hydrogel with the second pattern connecting to the lower surface of the first pattern is formed.

[0012] In an invention of Claim 6, in the invention of Claim 5, the adhesion surface is subjected to treatment that makes the adhesion surface have an affinity for water.

[0013] In an invention of Claim 7, in the invention of any one of Claims 2 to 6, all of the first working electrode groups are included in the second working electrode group and the three-dimensionally defined pattern has a structure in which the first pattern is supported from below by the second

pattern.

[0014] In an invention of Claim 8, in the invention of Claim 5 or 6, all of the second working electrode groups are included in the first working electrode group and the three-dimensionally defined pattern has a structure
5 in which the second pattern is supported from above, which is the side where the adhesion surface is located, by the first pattern so as to hang therefrom.

[0015] In an invention of Claim 9, in the invention of any one of Claims 1 to 8, all of the working electrodes which compose the two-dimensional
10 array protrude from the bottom surface and side faces of each protruding working electrode are surrounded with an insulating layer formed so as to protrude from the bottom surface along with the working electrode.

[0016] In an invention of Claim 10, in the invention of any one of Claims 1 to 9, a part of the bottom surface other than front surfaces of the working
15 electrodes is made water-repellent.

[0017] In an invention of Claim 11, the invention of any one of Claims 1 to 10 further includes a step of forming, on the bottom surface, a hydrogel with the two-dimensionally defined pattern corresponding to the arrangement of the selected working electrodes by applying the
20 predetermined voltage to the selected working electrodes, and after that, in a state in which the formed hydrogel is in contact with the selected working electrodes, promoting separation of the hydrogel from the selected working electrodes by dissolving a contact part of the hydrogel with the selected working electrodes by applying a voltage for hydrogel separation,
25 which is different from the predetermined voltage, to the selected working

electrodes.

[0018] According to an invention of Claim 12, in a method of producing a hydrogel patterned with cells, which is obtained by distributing predetermined cells over a hydrogel scaffold, by performing the invention
5 of any one of Claims 1 to 11 by using, as an electrolytic solution containing a dissolved substance which causes electrolytic deposition of the hydrogel, a suspension further containing the predetermined cells, a hydrogel with the distributed predetermined cells is formed on the bottom surface of the electrolytic tank.

10 **[0019]** In an invention of Claim 13, in the invention of Claim 12, the predetermined cells include one or more types of cells. The invention of Claim 12 includes a step of performing the invention of Claim 2 by using, as the electrolytic solution, a suspension containing one type of cell of the predetermined cells along with a dissolved substance, which causes
15 electrolytic deposition of the hydrogel, in any one of the first step and the second step.

[0020] In an invention of Claim 14, the invention of Claim 13 includes a step of performing the method by using, as the electrolytic solution, a suspension containing the other type of cell, which is different from the
20 one type of cell, of the predetermined cells along with a dissolved substance, which causes electrolytic deposition of the hydrogel, in the other of the first step and the second step.

[0021] In an invention of Claim 15, in the invention of Claim 12, the predetermined cells include one or more types of cells, and the invention of
25 Claim 3 is performed by using, as the electrolytic solution, a suspension

containing one type of cell of the predetermined cells along with a dissolved substance, which causes electrolytic deposition of the hydrogel, in any one of the first sub-step and the second sub-step.

[0022] In an invention of Claim 16, in the invention of Claim 15, the
5 method is performed by using, as the electrolytic solution, a suspension containing the other type of cell, which is different from the one type of cell, of the predetermined cells along with a dissolved substance, which causes electrolytic deposition of the hydrogel, in the other of the first sub-step and the second sub-step.

10 [0023] In an invention of Claim 17, the invention of any one of Claims 12 to 16 includes, before a step of forming a hydrogel by applying the predetermined voltage to the selected working electrodes in a state in which the suspension is housed in the electrolytic tank, a dielectrophoresis step of densely distributing the predetermined cells on the selected working
15 electrodes by dielectrophoresis by applying an alternating voltage of a predetermined frequency to the selected working electrodes.

[0024] In an invention of Claim 18, in the invention of Claim 17, in the dielectrophoresis step, an electrode with an electrode plane facing, parallel to the bottom surface, a region of the bottom surface in which the two-
20 dimensional array of the working electrodes is provided is used.

[0025] In an invention of Claim 19, in the invention of Claim 17, in the dielectrophoresis step, an electrode which is provided on the bottom surface so as to be located around each of the two-dimensional array of the working electrodes is used.

25 [0026] In an invention of Claim 20, the invention of any one of Claims

12 to 16 includes, before a step of forming a hydrogel by applying the predetermined voltage to the selected working electrodes in a state in which the suspension is housed in the electrolytic tank, an electrophoresis step of densely distributing the predetermined cells on the selected working electrodes by electrophoresis by applying a predetermined direct voltage to the selected working electrodes.

[0027] According to an invention of Claim 21, a hydrogel production apparatus that includes an electrolytic tank with a bottom surface on which a two-dimensional array of working electrodes is provided and a counter electrode, which is installed in the electrolytic tank, and can apply a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes includes a Z stage that has an adhesion surface facing the bottom surface parallel thereto and is displaceable in a Z direction perpendicular to the bottom surface.

[0028] In an invention of Claim 22, in the invention of Claim 21, the adhesion surface is subjected to treatment that makes the adhesion surface have an affinity for water.

[0029] According to an invention of Claim 23, in a hydrogel production apparatus that includes an electrolytic tank with a bottom surface on which a two-dimensional array of working electrodes is provided and a counter electrode, which is installed in the electrolytic tank, and can apply a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes, all of the working electrodes that make up the two-dimensional array protrude from the bottom surface and side faces of each protruding working electrode are

surrounded with an insulating layer formed so as to protrude from the bottom surface along with the working electrode.

[0030] In an invention of Claim 24, in the invention of Claim 21 or 22, all of the working electrodes that make up the two-dimensional array

5 protrude from the bottom surface and side faces of each protruding working electrode are surrounded with an insulating layer formed so as to protrude from the bottom surface along with the working electrode.

[0031] In an invention of Claim 25, in the invention of any one of Claims 21 to 24, a part of the bottom surface other than front surfaces of the

10 working electrodes is made water-repellent.

[0032] In an invention of Claim 26, the invention of any one of Claims 21 to 25 includes an oscillator that can apply an alternating voltage of a predetermined frequency to the selected working electrodes.

[0033] In an invention of Claim 27, the invention of Claim 26 further

15 includes an electrode for dielectrophoresis that is installed or can be installed in the electrolytic tank, and the electrode for dielectrophoresis is installed or can be installed in the electrolytic tank so that an electrode plane thereof faces, parallel to the bottom surface, a region of the bottom surface in which the two-dimensional array of the working electrodes is
20 provided.

[0034] In an invention of Claim 28, in the invention of Claim 26, the electrolytic tank further includes an electrode for dielectrophoresis and the electrode for dielectrophoresis is provided on the bottom surface so as to be located around each of the two-dimensional array of the working

25 electrodes.

[0035] According to an invention of Claim 29, in a transducer that includes an electrolytic tank, which can house an electrolytic solution and a hydrogel which is electrolytically deposited in the electrolytic solution, mounted on an LSI chip and is used for electrochemical production of a
5 patterned hydrogel, in a shaping area defined on a bottom surface of the electrolytic tank, first electrodes which are provided in the LSI chip in a two-dimensional array arrangement are located. The transducer includes a Z stage with an adhesion surface, which can be installed in the electrolytic tank. The Z stage can be installed in the electrolytic tank so as be
10 displaceable in a Z direction perpendicular to the bottom surface, in such a way that the adhesion surface faces the shaping area of the bottom surface parallel to the shaping area.

[0036] In an invention of Claim 30, in the invention of Claim 29, the adhesion surface is subjected to treatment that makes the adhesion surface
15 have an affinity for water.

[0037] According to an invention of Claim 31, in a transducer that includes an electrolytic tank, which can house an electrolytic solution and a hydrogel which is electrolytically deposited in the electrolytic solution, mounted on an LSI chip and is used for electrochemical production of a
20 patterned hydrogel, in a shaping area defined on a bottom surface of the electrolytic tank, first electrodes which are provided in the LSI chip in a two-dimensional array arrangement are located, and all of the first electrodes protrude from the bottom surface and side faces of each protruding first electrode are surrounded with an insulating layer formed so
25 as to protrude from the bottom surface along with the first electrode.

[0038] In an invention of Claim 32, in the invention of any one of Claims 29 to 31, a part of the shaping area other than front surfaces of the first electrodes is made water-repellent.

[0039] In an invention of Claim 33, in the invention of any one of Claims 29 to 31, in the shaping area, a second electrode which is provided in the LSI chip so as to be located around each of the first electrodes is further located.

[0040] In an invention of Claim 34, in the invention of Claim 33, the second electrode is formed over the entire surface of the shaping area without continuity between the first electrodes and the second electrode.

[0041] In an invention of Claim 35, in the invention of Claim 33 or 34, a part of the shaping area other than front surfaces of the first electrodes and a front surface of the second electrode is made water-repellent.

[0042] In an invention of Claim 36, the invention of any one of Claims 29 to 32 further includes a second electrode that is installed or can be installed in the electrolytic tank, and the second electrode is installed or can be installed in the electrolytic tank so that an electrode plane thereof faces the shaping area of the bottom surface parallel to the shaping area.

[EFFECTS OF THE INVENTION]

[0043] According to the present invention, it is possible to achieve a higher degree of flexibility in shaping, achieve greater versatility, and form a hydrogel with a two-dimensional pattern or a three-dimensional pattern more efficiently than ever before.

[BRIEF DESCRIPTION OF THE DRAWINGS]

[0044] Fig. 1 is a diagram for explaining the configuration of a hydrogel production apparatus of an embodiment.

Fig. 2 is a diagram for explaining the configuration of a transducer of an embodiment: (a) a plan view; (b) a sectional view; (c) a diagram
5 depicting the arrangement of cells of an LSI chip; and (d) a diagram depicting a working electrode provided in each cell.

Fig. 3 is a diagram for explaining electrochemical hydrogel production.

10 Fig. 4 is a diagram for explaining a method of electrochemically producing a hydrogel (an embodiment).

Fig. 5 is a photograph of a hydrogel actually produced by the method of electrochemically producing a hydrogel (an embodiment).

Fig. 6 is a diagram for explaining the method of electrochemically
15 producing a hydrogel (an embodiment).

Fig. 7A is a diagram for explaining a method of forming the working electrode protruding from a bottom surface of an electrolytic tank.

Fig. 7B is a diagram for explaining the formation and separation of a hydrogel which are performed when the working electrode depicted in Fig.
20 7A is used.

Fig. 8 is a diagram for explaining the method of electrochemically producing a hydrogel (an embodiment).

Fig. 9 is a diagram for explaining a method of producing a hydrogel with a pattern formed of cells (an embodiment).

25 Fig. 10 is a diagram for explaining dielectrophoresis which is

performed to concentrate cells on the working electrode.

Fig. 11 is a diagram depicting an example of an electrode for dielectrophoresis: (a) an example of an annular electrode; and (b) an example of a solid electrode.

5

[DETAILED DESCRIPTION OF THE EMBODIMENTS]

[0045] The principles and embodiments of a technique of electrochemically producing a hydrogel according to the present invention will be described with reference to the drawings.

10 **[0046]** First, the configuration of a hydrogel production apparatus will be described; then, the configuration of a transducer will be described.

[0047] <First embodiment>

Fig. 1 is a schematic diagram explaining the configuration of the hydrogel production apparatus. A hydrogel production apparatus 800
15 illustrated as an example includes an electrolytic tank 10, working electrodes 20, one counter electrode 30, one reference electrode 40, and a controller 85. The electrolytic tank 10 can house an electrolytic solution 11 and a hydrogel which is electrolytically deposited in the electrolytic solution 11. The working electrodes 20, the counter electrode 30, and the
20 reference electrode 40 are attached in the electrolytic tank 10 in this example. The working electrodes 20 are arranged on a bottom surface 10a of the electrolytic tank 10 with predetermined pitches in the form of a two-dimensional array (example: a two-dimensional grid-like arrangement; a detailed illustration thereof is omitted in Fig. 1). The controller 85 applies
25 a voltage between the counter electrode 30 and one or more selected

working electrodes 20 selected from among the working electrodes 20. The controller 85 includes a potentiostat 50 and switches 60. In Fig. 1, a reference numeral 70 denotes a salt bridge.

[0048] The counter electrode 30 and the reference electrode 40 are
5 connected to the potentiostat 50. Each of the working electrodes 20 is connected to the potentiostat 50 via a corresponding one of the switches 60. The potentiostat 50 functions as a constant-voltage power supply device and is depicted as an equivalent circuit including a variable power source 51 and a voltmeter 52 (see Fig. 1). The application of a voltage between
10 the counter electrode 30 and the working electrodes 20 is performed by the potentiostat 50.

[0049] The basic circuit configuration of the potentiostat 50 is the same as the basic circuit configuration of a potentiostat which is used for common electrochemical measurement. That is, a potentiostat which is
15 used for common electrochemical measurement can be used as part of the hydrogel production apparatus without any special change. For this reason, in the example of Fig. 1, the potentiostat 50 includes an ammeter 53 like a potentiostat which is used for common electrochemical measurement.

[0050] The controller 85 applies a predetermined voltage between the
20 working electrode 20 selected by operation (ON/OFF) performed on the switch 60 and the one counter electrode 30. The hydrogel production apparatus 800 can further have a configuration which is useful for production of a hydrogel (a detailed illustration thereof is omitted in Fig. 1). This useful configuration will be described later.

25 [0051] Next, the transducer will be described. The transducer includes

the hydrogel production apparatus and an integrated circuit. The bottom surface of the electrolytic tank is the front surface of the integrated circuit. The configuration of a transducer 900 will be described with reference to Fig. 2.

5 **[0052]** The transducer 900 has a configuration in which the electrolytic tank 10 covers an LSI chip 80. A hole 12 in the shape of a rectangle is formed in the center of the bottom of the electrolytic tank 10. The LSI chip 80 is disposed at the lower end of the hole 12 and closes the hole 12.

10 **[0053]** The LSI chip 80 and the electrolytic tank 10 are fixed on a substrate 90. A large number of wiring patterns 91 for connection with an external device (which is not depicted in the drawing) which performs control of the LSI chip 80 are formed on the substrate 90. In Fig. 2(b), a reference numeral 92 denotes bonding wires that connect the LSI chip 80 and the wiring patterns 91.

15 **[0054]** A shaping area 81 (a diagonally hatched portion in Fig. 2(a)) for producing a hydrogel with a pattern is set on the upper surface of the LSI chip 80. Specifically, the shaping area 81 is set in the position of the hole 12 of the electrolytic tank 10 and faces the electrolytic solution 11. In the position of the hole 12, the shaping area 81 is part of the bottom surface
20 10a of the electrolytic tank 10.

25 **[0055]** In this example, as depicted in Fig. 2(c), cells 82 are arranged in the shaping area 81 in the form of a two-dimensional grid array. One working electrode (a first electrode) 20 is formed in each cell 82 (see Figs. 2(c) and (d)). In this example, $20 \times 20 = 400$ cells 82 are arranged with 250- μm pitches in the form of a two-dimensional grid array. That is, the

LSI chip 80 has 400 working electrodes 20 arranged in the form of a two-dimensional grid array.

[0056] The LSI chip 80 has a function of applying a voltage between the counter electrode 30 and each working electrode 20, a switching function,
5 and so forth. The one counter electrode 30 and the one reference electrode 40 are installed in the electrolytic solution 11. The reference electrode 40 is located immediately above the shaping area 81, and the counter electrode 30 is located apart from the reference electrode 40 (see Fig. 2(b)). The transducer 900 can further have a configuration which is useful for
10 production of a hydrogel (a detailed illustration thereof is omitted in Fig. 2). This useful configuration will be described later.

[0057] Here, the principles of production of a hydrogel by an electrochemical method will be described.

[0058] A method of electrochemically producing a hydrogel is classified
15 into three types.

- 1) Gelation of dispersoids caused by cross-linking
- 2) Cohesion of charged polymers caused by electrostatic interaction
- 3) Transformation of monomers into polymers by polymerization

[0059] Fig. 3 depicts how a hydrogel is produced by a cross-linking
20 reaction, with chitosan being taken up as an example. When a voltage is applied between the counter electrode (an electrode) 30 and the working electrode (an electrode) 20 in an aqueous solution in which chitosan and chlorine ions are present, hypochlorous acid (HClO) is generated by an electrode reaction (see Fig. 3(b)). Chitosan is oxidized by hypochlorous
25 acid (see Fig. 3(a)). Then, a cross-linking reaction occurs between the

chitosan molecules, and a hydrogel 100, which is insoluble in a solvent, is deposited on the working electrode 20.

[0060] The example is not limited to chitosan; for example, a hydrogel of gelatin or sodium alginate can also be produced based on a cross-linking
5 reaction. Examples of specific conditions of aqueous solutions in cases where chitosan is used and gelatin is used are as follows.

- chitosan: 1% (w/v) solution (0.15 M NaCl, adjusted by acetic acid so as to be pH 5.5)

- gelatin: 10% (w/v) solution (4 M NaCl, 10 mM acetate buffer adjusted so
10 as to be pH 5.6)

[0061] A method of producing a hydrogel according to the present invention includes a process of producing a hydrogel by any one of reactions: 1) cross-linking between dispersoids, 2) electrostatic interaction, and 3) polymerization, which are started by an electrode reaction. The
15 method of producing a hydrogel uses electrolytic deposition of a hydrogel by which a hydrogel is generated by a reaction induced, in an electrolytic solution, by an electrode product electrochemically generated by electrodes installed in the electrolytic solution.

[0062] According to an embodiment of the present invention, in the
20 hydrogel production apparatus 800 and the transducer 900, an electrolytic solution containing a precursor (i.e., dispersoids, charged polymers, monomers) of a hydrogel as a dissolved substance is housed in the electrolytic tank (a housing step) and, by applying a predetermined voltage between one or more selected working electrodes of the working electrodes
25 arranged in the form of a two-dimensional array and the one counter

electrode 30, a hydrogel with a two-dimensional pattern or a three-dimensional pattern corresponding to the arrangement of the selected working electrodes is produced (a production step).

[0063] A method of producing a hydrogel with a three-dimensional
5 pattern includes a first step and a second step.

[0064] <First step>

By applying a first voltage, which is a predetermined voltage,
between all the working electrodes included in a first working electrode
group and one counter electrode, a hydrogel with a first pattern, which is a
10 two-dimensional pattern, is produced on the bottom surface of the
electrolytic tank. The first working electrode group is made up of one or
more selected working electrodes of the working electrodes 20.

[0065] <Second step>

By applying a second voltage, which is a predetermined voltage,
15 between all the working electrodes included in a second working electrode
group and one counter electrode, a hydrogel with a second pattern, which is
a two-dimensional pattern, is produced on the bottom surface of the
electrolytic tank. Since the second pattern connects to the bottom surface
of the first pattern, a hydrogel with a three-dimensional pattern as a whole
20 is produced on the bottom surface of the electrolytic tank. The second
working electrode group is made up of one or more selected working
electrodes of the working electrodes 20. At least one working electrode
included in the first working electrode group makes up the second working
electrode group.

25 **[0066]** By performing the second step after the first step, a hydrogel with

a three-dimensional pattern with a two-layer structure is produced. In the hydrogel with a three-dimensional pattern with a two-layer structure, the hydrogel with the second pattern directly connects to the bottom surface (a surface, of the two surfaces perpendicular to a Z direction, closer to the bottom surface of the electrolytic tank) of the hydrogel with the first pattern.

[0067] When all the working electrodes included in the first working electrode group are included in the second working electrode group, a three-dimensional pattern having a structure in which the first pattern is supported from below by the second pattern can be produced.

[0068] Fig. 4 is a schematic diagram explaining a process of producing a hydrogel having a structure in which the first pattern is supported from below by the second pattern. When a voltage is applied between the counter electrode 30 and a working electrode 20₂, a hydrogel 101 is produced on the working electrode 20₂ as depicted in Fig. 4(2). Next, when a voltage is applied between the counter electrode 30 and working electrodes 20₁, 20₂, and 20₃, a hydrogel 102 is produced on the working electrodes 20₁, 20₂, and 20₃ as depicted in Fig. 4(3). As a result, a hydrogel 103 with a three-dimensional pattern having a structure in which the hydrogel 101 with the first pattern is supported from below by the hydrogel 102 with the second pattern is produced.

[0069] Fig. 5 is a photograph of the actually produced hydrogel with a three-dimensional pattern. This hydrogel was produced by applying a voltage between the counter electrode 30 and the selected working electrodes 20 in a chitosan 1% (w/v) aqueous solution with the above-

described conditions by using the transducer 900 depicted in Fig. 2. Two voltage application modes (V1 mode, V2 mode) were started at the same time.

V1 mode: 0 V, 20 s $\rightarrow$ 0.95 V, 10 s

5 V2 mode: 0.95 V, 30 s

[0070] Specifically, a voltage in V1 mode was applied between the counter electrode 30 and the working electrodes 20 of the diagonally hatched cells 82 (see Fig. 2(c)) and a voltage in V2 mode was applied between the counter electrode 30 and the working electrodes 20 of the cells 10 82 with a dot pattern (see Fig. 2(c)). In other words, a voltage of 0.95 V was applied only between the counter electrode 30 and the working electrodes 20 of the cells 82 with a dot pattern for first 20 seconds and, for subsequent 10 seconds, a voltage of 0.95 V was applied between the counter electrode 30 and the working electrodes 20 of the diagonally 15 hatched cells 82 and between the counter electrode 30 and the cells 82 with a dot pattern.

[0071] It is understood from Fig. 5 that a hydrogel with a three-dimensional pattern was produced in accordance with the arrangement of the selected working electrodes 20 and the voltage application mode (V1 20 mode, V2 mode). In this experiment, the constituent materials of the working electrodes 20, the counter electrode 30, and the reference electrode 40 of the transducer 900 are as follows.

The working electrodes 20: Au

The counter electrode 30: Pt

25 The reference electrode 40: Ag/AgCl

[0072] When a hydrogel with a two-dimensional pattern is produced, the second step is unnecessary because a hydrogel with a two-dimensional pattern is produced only by the first step.

[0073] An embodiment is also admissible in which a step of discharging
5 the electrolytic solution used in the first step from the electrolytic tank 10 and housing an electrolytic solution which is used in the second step in the electrolytic tank 10 is executed between the first step and the second step. In this case, preferably, the electrolytic solution which is used in the second step is different from the electrolytic solution used in the first step
10 (at least one of the solvent and the dissolved substance of the electrolytic solution which is used in the second step is different from that of the electrolytic solution which is used in the first step). According to such an embodiment, it is possible to produce a hydrogel with a three-dimensional pattern with an alginate hydrogel on a chitosan hydrogel, for example.

15 [0074] <Second embodiment>

A hydrogel with a three-dimensional pattern with a layered structure such as the above-mentioned two-layer structure can be satisfactorily obtained by using a Z stage. The Z stage is a device that has an adhesion surface parallel to the bottom surface of the electrolytic tank and can move
20 the adhesion surface in the Z direction perpendicular to the bottom surface of the electrolytic tank.

[0075] A second embodiment of the hydrogel production apparatus includes the Z stage in addition to the configuration depicted in Fig. 1. A second embodiment of the transducer includes the Z stage in addition to the
25 configuration depicted in Fig. 2. The Z stage included in the hydrogel

production apparatus has a configuration in which the Z stage is independent of the hydrogel production apparatus or a configuration in which the Z stage is incorporated into the hydrogel production apparatus. In the hydrogel production apparatus, the adhesion surface of the Z stage is disposed parallel to the bottom surface 10a of the electrolytic tank 10. Likewise, the Z stage included in the transducer has a configuration in which the Z stage is independent of the transducer or a configuration in which the Z stage is incorporated into the transducer. In the transducer, the adhesion surface of the Z stage is disposed parallel to the shaping area 81.

10 [0076] The use of the Z stage makes it possible to produce a hydrogel with a desired three-dimensional pattern satisfactorily by the following procedure.

[0077] a) In the first step, in a state in which the adhesion surface of the Z stage is apart from the bottom surface of the electrolytic tank by a first distance in the electrolytic solution, a hydrogel with the first pattern, which is a two-dimensional pattern, is produced on the bottom surface of the electrolytic tank. The upper surface (a surface, of the two surfaces perpendicular to the Z direction, farther apart from the bottom surface) of the produced hydrogel adheres to the adhesion surface of the Z stage.

20 [0078] b) After the first step, the adhesion surface of the Z stage moves, with the hydrogel adhering to the adhesion surface of the Z stage, to a position apart from the bottom surface of the electrolytic tank by a predetermined distance, which is longer than the first distance, in the electrolytic solution. The lower surface (a surface, of the two surfaces perpendicular to the Z direction, closer to the bottom surface) of the

25

hydrogel is separated from the bottom surface of the electrolytic tank and apart from the bottom surface of the electrolytic tank by a second distance (a separation step).

[0079] c) After the separation step, in the second step, in a state in which
5 the lower surface of the hydrogel with the first pattern is apart from the bottom surface of the electrolytic tank by the second distance, a hydrogel with the second pattern, which is a two-dimensional pattern, is produced on the bottom surface of the electrolytic tank. Since the second pattern connects to the bottom surface of the first pattern, a hydrogel with a three-
10 dimensional pattern as a whole is produced on the bottom surface of the electrolytic tank.

[0080] A part, which is immersed in the electrolytic solution, of the Z stage is preferably made of glass, for example, from the viewpoint of preventing deterioration caused by an electrochemical reaction. Although
15 glass is a material having an affinity for water, it is preferable to perform additional treatment on the adhesion surface of the Z stage to enhance an affinity for water. Examples of this treatment include the application of polyethylene glycol, for instance.

[0081] Fig. 6 is a schematic diagram depicting a process of producing the
20 hydrogel depicted in Fig. 4 by using the Z stage.

[0082] An adhesion surface 110a of a Z stage 110 is apart from the bottom surface 10a of the electrolytic tank by a first distance Z_1 in the electrolytic solution. By applying a voltage between the counter electrode 30 and the working electrode 20₂ in this state, the hydrogel 101 with the
25 first pattern is formed on the working electrode 20₂. As depicted in Fig.

6(2), the upper surface of the hydrogel 101 adheres to the adhesion surface 110a. The separation step in which the hydrogel 101 is separated from the working electrode 20₂ (see Fig. 6(3)) will be described later in detail.

[0083] As depicted in Fig. 6(4), the adhesion surface 110a of the Z stage 110 moves to a position apart from the bottom surface 10a of the electrolytic tank by a predetermined distance, which is longer than the first distance Z_1 , in the electrolytic solution with the hydrogel 101 adhering to the adhesion surface 110a of the Z stage 110. A lower surface 101a of the hydrogel 101 is apart from the bottom surface 10a of the electrolytic tank by a second distance Z_2 . By applying a voltage between the counter electrode 30 and the working electrodes 20₁ to 20₃ in this state, the hydrogel 102 with the second pattern is produced on the working electrodes 20₁ to 20₃ as depicted in Fig. 6(5). The hydrogel 103 with a three-dimensional pattern, which is made up of the hydrogel 101 and the hydrogel 102, is satisfactorily produced.

[0084] When all the working electrodes included in the second working electrode group are included in the first working electrode group in the process of producing a hydrogel by using the Z stage, a three-dimensional pattern having a structure in which the first pattern has the second pattern, which is smaller than the first pattern, hanging therefrom (in other words, when the bottom surface 10a of the electrolytic tank 10 or the shaping area 81 is viewed squarely, a structure in which: a) the whole of the second pattern is included in the first pattern; b) the area of the second pattern is smaller than the area of the first pattern; and c) the first pattern is on the second pattern) is satisfactorily produced. That is, a hydrogel with an

inverted pyramid-shaped pattern is satisfactorily produced.

[0085] The following is an additional explanation of the hydrogel separation step (see Fig. 6(3)).

[0086] The separation step is performed in a state in which the hydrogel
5 101 with the first pattern is in contact with the working electrode 20₂. In
the separation step, a hydrogel separation voltage, which is different from
the voltage used in the production of the hydrogel 101, is applied between
the counter electrode 30 and the working electrode 20₂. As a result of the
application of the hydrogel separation voltage, a part of the hydrogel 101 in
10 which the hydrogel 101 is in contact with the working electrode 20₂ is
dissolved, and the hydrogel 101 is separated from the working electrode
20₂. The separation step allows the hydrogel 101 to move with the Z stage
110 while adhering to the adhesion surface 110a of the Z stage 110 (see Fig.
6(4)).

15 **[0087]** The separation step using the hydrogel separation voltage is
useful when a sodium alginate solution, for instance, is used for production
of a hydrogel. The reason is as follows: in the case of a sodium alginate
solution, when a voltage which causes an oxidation reaction is applied
between the counter electrode and the working electrode, an alginate
20 hydrogel is deposited and, when a voltage which causes a reduction
reaction is applied between the counter electrode and the working electrode,
the alginate hydrogel is dissolved.

[0088] However, the separation step using the hydrogel separation
voltage is not an indispensable step. Easy separation of the hydrogel from
25 the working electrode is made possible by, for example, reducing the

contact area between the hydrogel and the bottom surface 10a of the electrolytic tank. In this mode example, all the working electrodes arranged in the form of a two-dimensional array protrude from the bottom surface of the electrolytic tank. The side faces of the working electrodes
5 are surrounded with insulators protruding from the bottom surface of the electrolytic tank.

[0089] Figs. 7A(1)-(3) are schematic diagrams depicting an example of a method of producing the working electrodes and the insulators which protrude from the bottom surface of the electrolytic tank. As depicted in
10 Fig. 7A(2), insulators 25 which form micro wells are produced on the working electrodes 20 by photolithography. Then, electrodes are produced by filling the insides of the micro wells with plating. As a result, as depicted in Fig. 7A(3), working electrodes 20a which protrude from the bottom surface 10a of the electrolytic tank and have the side faces
15 surrounded with the insulators 25 are produced.

[0090] A hydrogel 104 produced by applying a voltage between the counter electrode 30 and the working electrodes 20a has a shape which does not make contact with the bottom surface 10a as depicted in Fig. 7B(2). Thus, the hydrogel 104 is easily separated from the working
20 electrodes 20a at the time of movement of the Z stage 110 depicted in Fig. 7B(3).

[0091] Alternatively, easy separation of the hydrogel from the working electrode is made possible by, for example, the bottom surface 10a, which is rendered water-repellent, of the electrolytic tank. In this mode example,
25 the bottom surface of the electrolytic tank other than the front surface of

the working electrode is rendered water-repellent. Rendering the bottom surface water-repellent is, for example, coating the bottom surface with a thin film of fluorocarbon resin such as polytetrafluoroethylene (PTFE).

[0092] The separation step using the hydrogel separation voltage can also
5 be applied to other embodiments.

[0093] <Third embodiment>

Next, a method of producing a hydrogel with a three-dimensional pattern with a layered structure, in which different types of hydrogel are present in the same layer, will be described.

10 [0094] At least one of the above-described first step and second step includes a first sub-step and a second sub-step.

When the first step includes the first sub-step and the second sub-step, the first working electrode group includes a first sub-group and a second sub-group, the first voltage includes a first sub-voltage and a second sub-
15 voltage, the first pattern includes a first sub-pattern and a second sub-pattern, and the second sub-group is made up of only the working electrode which does not belong to the first sub-group (in other words, the first sub-group and the second sub-group do not have a common working electrode).

When the second step includes the first sub-step and the second sub-
20 step, the second working electrode group includes a first sub-group and a second sub-group, the second voltage includes a first sub-voltage and a second sub-voltage, the second pattern includes a first sub-pattern and a second sub-pattern, and the second sub-group is made up of only the working electrode which does not belong to the first sub-group (in other
25 words, the first sub-group and the second sub-group do not have a common

working electrode).

[0095] In this case, by applying the first sub-voltage between each working electrode included in the first sub-group and one counter electrode, a hydrogel with the first sub-pattern, which is a two-dimensional pattern, is produced, and, by applying the second sub-voltage between each working electrode included in the second sub-group and the one counter electrode, a hydrogel with the second sub-pattern, which is a two-dimensional pattern, is produced. Thus, different types of hydrogel are present in the same layer.

[0096] In the first sub-step and the second sub-step, for example, an electrode reaction in the first sub-step is an electrode reaction of oxidation and an electrode reaction in the second sub-step is an electrode reaction of reduction.

[0097] In the case of sodium alginate, a hydrogel is produced by an oxidation reaction. In the case of chitosan, in accordance with pH adjustment, a hydrogel is produced by an oxidation reaction under certain pH conditions and a hydrogel is produced by a reduction reaction under other pH conditions. When pH is set at conditions under which a chitosan hydrogel is produced by a reduction reaction, two types of hydrogel (a chitosan hydrogel and an alginate hydrogel) are produced in the first sub-step and the second sub-step.

[0098] Fig. 8 depicts an example in which each of the first step and the second step includes the first sub-step and the second sub-step. Specifically, Fig. 8 is a schematic diagram explaining production of a hydrogel in which, in a hydrogel with a multi-layer structure, each layer is formed of two types of hydrogel and two types of hydrogel are alternately

located in the thickness direction (the Z direction) of the hydrogel. In Fig. 8, a reference numeral 105 denotes an alginate hydrogel and a reference numeral 106 denotes a chitosan hydrogel.

[0099] Fig. 8(2) depicts the first sub-step in the first step. The

5 electrolytic tank 10 is filled with a sodium alginate solution. By applying the first sub-voltage (V_{s1}) between the first sub-group (the working electrode 20₂) and the counter electrode 30, the alginate hydrogel 105 with the first sub-pattern is produced (the result of an oxidation reaction).

[0100] After the sodium alginate solution is removed from the

10 electrolytic tank 10, the electrolytic tank 10 is filled with a chitosan solution.

[0101] Fig. 8(3) depicts the second sub-step in the first step. The

electrolytic tank 10 is filled with the chitosan solution. By applying the second sub-voltage (V_{s2}) between the second sub-group (the working

15 electrodes 20₁ and 20₃) and the counter electrode 30, the chitosan hydrogel 106 with the second sub-pattern is produced (the result of a reduction reaction).

[0102] Furthermore, though not depicted in the drawing, the first sub-

step in the second step is executed. The electrolytic tank 10 is filled with

20 the chitosan solution. By applying the first sub-voltage (V_{s2}) between the first sub-group (the working electrode 20₂) and the counter electrode 30, the chitosan hydrogel 106 with the first sub-pattern is produced (the result of a reduction reaction). That is, the chitosan hydrogel 106 is produced under the alginate hydrogel 105 depicted in Fig. 8(3).

25 **[0103]** After the chitosan solution is removed from the electrolytic tank

10, the electrolytic tank 10 is filled with the sodium alginate solution.

[0104] Though not depicted in the drawing, the second sub-step in the second step is executed. The electrolytic tank 10 is filled with the sodium alginate solution. By applying the second sub-voltage (V_{s1}) between the
5 second sub-group (the working electrodes 20_1 and 20_3) and the counter electrode 30, the alginate hydrogel 105 with the second sub-pattern is produced (the result of an oxidation reaction). That is, the alginate hydrogel 105 is produced under the chitosan hydrogel 106 depicted in Fig. 8(3).

10 **[0105]** By repeating the above-described procedure, a hydrogel 107 with a multi-layer structure (a four-layer structure in the example depicted in Fig. 8(4)) is produced.

[0106] In addition, an embodiment in which the above-described sub-steps are performed is permitted to have a modification including a sub-
15 pattern removal step in which a selected hydrogel is removed. In the sub-pattern removal step, as one example, a hydrogel which is dissolved by predetermined treatment is produced in the second sub-step and, by performing the predetermined treatment after the first sub-step and the second sub-step, the hydrogel with the second sub-pattern is dissolved.

20 **[0107]** Specifically, for example, degradation of the alginate hydrogel by the addition of an alginate degrading enzyme is used. After the alginate hydrogel with the second sub-pattern is produced, the alginate degrading enzyme is diffused in the electrolytic solution. As a result, the second sub-pattern is selectively removed. The example is not limited to an enzyme;
25 cross-linking scission by light irradiation, dissolution of gel by control of

any one of pH and the temperature or both, and the like can also be used in the sub-pattern removal step.

[0108] When a hydrogel with a two-dimensional pattern is produced, as described earlier, only the first step is executed. In this case, a mode in
5 which the first step includes the first sub-step and the second sub-step is also included in the embodiments of the present invention.

[0109] <Fourth embodiment>

Next, a method of producing a hydrogel with a pattern formed of cells will be described. In this example, predetermined cells are distributed over
10 a hydrogel which is a scaffold.

[0110] In the method of producing a hydrogel with a pattern formed of cells, a suspension containing a precursor of a hydrogel and predetermined cells is used as the electrolytic solution. By using this suspension, it is possible to produce a hydrogel, in which the predetermined cells are
15 dispersed, on the bottom surface of the electrolytic tank.

[0111] The above-described method of producing a hydrogel is divided into the following four types.

- a) A method including only the first step
- b) A method including only the first step, which includes the first sub-step
20 and the second sub-step
- c) A method including the first step and the second step
- d) A method including the first step and the second step, at least one of which includes the first sub-step and the second sub-step

[0112] In the case of a), a suspension containing a precursor of a
25 hydrogel and predetermined cells is used as the electrolytic solution which

is used in the first step.

[0113] In the case of b), in at least one of the first sub-step and the second sub-step, a suspension containing a precursor of a hydrogel and one type of cell, for example, is used as the electrolytic solution. The

5 electrolytic solution which is used in the first sub-step and the electrolytic solution which is used in the second sub-step may be different from each other (at least one of the solvent and the dissolved substance of the electrolytic solution which is used in the first sub-step and that of the electrolytic solution which is used in the second sub-step are different from
10 each other). For instance, a suspension containing a precursor X of a hydrogel and one type of cell Y1 is used as the electrolytic solution which is used in the first sub-step and a suspension containing the precursor X of a hydrogel and one type of cell Y2 ($Y1 \neq Y2$) is used as the electrolytic solution which is used in the second sub-step.

15 **[0114]** In the case of c), in at least one of the first step and the second step, a suspension containing a precursor of a hydrogel and one type of cell, for example, is used as the electrolytic solution. By using this suspension, any one of a hydrogel with the cells dispersed therein and with the first pattern and a hydrogel with the cells dispersed therein and with the second
20 pattern or both is produced.

[0115] In the case of c), the electrolytic solution which is used in the first step and the electrolytic solution which is used in the second step may be different from each other (at least one of the solvent and the dissolved substance of the electrolytic solution which is used in the first step and that
25 of the electrolytic solution which is used in the second step are different

from each other). For instance, a suspension containing a precursor X of a hydrogel and one type of cell Y1 is used as the electrolytic solution which is used in the first step and a suspension containing the precursor X of a hydrogel and one type of cell Y2 ($Y1 \neq Y2$) is used as the electrolytic solution which is used in the second step. As a result, a hydrogel with the cells Y1 dispersed therein and with the first pattern and a hydrogel with the cells Y2 dispersed therein and with the second pattern are produced.

[0116] As in the case of c), in the case of d), in at least one of the first sub-step and the second sub-step, a suspension containing a hydrogel precursor and one type of cell, for example, is used as the electrolytic solution.

Furthermore, as in the case of c), in the case of d), the electrolytic solution which is used in the first sub-step and the electrolytic solution which is used in the second sub-step may be different from each other (at least one of the solvent and the dissolved substance of the electrolytic solution which is used in the first sub-step and that of the electrolytic solution which is used in the second sub-step are different from each other).

[0117] Fig. 9 is a schematic diagram depicting a process of production of a multi-layer structure formed of an alginate hydrogel in which cells A are dispersed and a chitosan hydrogel in which cells B are dispersed.

[0118] The electrolytic tank 10 is filled with a suspension containing sodium alginate and the cells A (see Fig. 9(1)).

[0119] Fig. 9(2) depicts the first sub-step in the first step. By applying the first sub-voltage (V_{s1}) between the first sub-group (the working electrode 20₂) and the counter electrode 30, an alginate hydrogel 105a with

the first sub-pattern and with the cells A dispersed therein is produced (the result of an oxidation reaction).

[0120] After the suspension containing sodium alginate and the cells A is removed from the electrolytic tank 10 (see Fig. 9(3)), the electrolytic tank
5 10 is filled with a suspension containing chitosan and the cells B (see Fig. 9(4)).

[0121] Fig. 9(5) depicts the second sub-step in the first step. The electrolytic tank 10 is filled with the suspension containing chitosan and the cells B. By applying the second sub-voltage (V_{s2}) between the second
10 sub-group (the working electrodes 20_1 and 20_3) and the counter electrode 30, a chitosan hydrogel 106a with the second sub-pattern and with the cells B dispersed therein is produced (the result of a reduction reaction).

[0122] Furthermore, though not depicted in the drawing, the first sub-step in the second step is executed. The electrolytic tank 10 is filled with
15 the suspension containing chitosan and the cells B. By applying the first sub-voltage (V_{s2}) between the first sub-group (the working electrode 20_2) and the counter electrode 30, the chitosan hydrogel 106a with the first sub-pattern and with the cells B dispersed therein is produced (the result of a reduction reaction). That is, the chitosan hydrogel 106a is produced under
20 the alginate hydrogel 105a depicted in Fig. 9(6).

[0123] After the suspension containing chitosan and the cells B is removed from the electrolytic tank 10, the electrolytic tank 10 is filled with the suspension containing sodium alginate and the cells A.

[0124] Though not depicted in the drawing, the second sub-step in the
25 second step is executed. The electrolytic tank 10 is filled with the

suspension containing sodium alginate and the cells A. By applying the second sub-voltage (V_{s1}) between the second sub-group (the working electrodes 20₁ and 20₃) and the counter electrode 30, the alginate hydrogel 105a with the second sub-pattern and with the cells A dispersed therein is produced (the result of an oxidation reaction). That is, the alginate hydrogel 105a is produced under the chitosan hydrogel 106a depicted in Fig. 9(6).

[0125] By repeating the above-described procedure, a hydrogel 107a with a multi-layer structure (a three-layer structure in the example depicted in Fig. 9(7)) is produced.

[0126] As described above, predetermined cells are dispersed in a hydrogel in a structural arrangement with a three-dimensional design. Thus, the present invention is useful for producing a desired cell culture structure.

[0127] An embodiment that produces a hydrogel in which predetermined cells are dispersed is permitted to have a modification including the above-described sub-pattern removal step. The above-described sub-pattern removal step is performed at the appropriate time in the process of producing a hydrogel in which predetermined cells are dispersed.

[0128] The type of cell which is used in the present invention is not limited to a particular type. For example, cells of any mammal, induced pluripotent stem (iPS) cells, embryonic stem (ES) cells, mesenchymal stem cells, hepatocytes, vascular endothelial cells, fibroblasts, and the like are used. For instance, in the case of vascular cells, by disposing vascular cells in a predetermined area of a hydrogel, it is possible to produce a blood

vessel having a predetermined shape.

[0129] When a hydrogel with a pattern formed of cells is produced, it is preferable to use the cells efficiently. For this reason, for instance, it is preferable to perform a dielectrophoresis step in a state in which a
5 suspension is housed in the electrolytic tank. The dielectrophoresis step is performed before a step of producing a hydrogel by applying a predetermined voltage between the selected working electrode and the counter electrode. In the dielectrophoresis step, an alternating voltage of a predetermined frequency is applied between the selected working electrode
10 and the counter electrode and cells are densely distributed on the selected working electrode by dielectrophoresis. The directivity of phoresis (an affinity of cells to the density of electrical flux lines) is controlled by a frequency. The working electrode and the counter electrode in the dielectrophoresis step serve as a positive electrode and a negative electrode
15 which alternate by an alternating voltage.

[0130] Fig. 10 is a schematic diagram depicting how dielectrophoresis of cells is performed. In this example, an electrode 120 with an electrode plane parallel to the bottom surface 10a of the electrolytic tank 10 is used. The electrode plane of the electrode 120 faces a region in which the two-
20 dimensional array of the working electrodes 20 is formed. In Fig. 10, a reference numeral 130 denotes an oscillator that applies an alternating voltage of a predetermined frequency between the working electrode 20 and the electrode 120. Moreover, a circle represents a cell and a dashed line represents an electrical flux line.

25 [0131] In the dielectrophoresis step, an electrode formed on the bottom

surface 10a may be used in place of the electrode 120.

In a first example, for each working electrode 20, one electrode 121 for dielectrophoresis, which surrounds the working electrode 20, is formed on the bottom surface 10a (see Fig. 11(a)). Each electrode 121 has a ring-
5 like shape. The electrode 121 and the working electrode 20 are not in contact with each other.

In a second example, one plate electrode 122 for dielectrophoresis is formed on the bottom surface 10a (see Fig. 11(b)). Holes corresponding to the positions of the working electrodes 20 are formed in the plate electrode
10 122. When the bottom surface 10a is viewed squarely, one working electrode 20 is located in one hole and the electrode 122 and the working electrode 20 are not in contact with each other.

[0132] When the dielectrophoresis step is performed, the hydrogel production apparatus 800 and the transducer 900 include the oscillator 130
15 in addition to the potentiostat 50. When the dielectrophoresis step is performed, the electrode 120 for dielectrophoresis, the electrode 121 for dielectrophoresis, or the electrode 122 for dielectrophoresis is a constituent element of the hydrogel production apparatus 800 or the transducer 900 or is a part which can be attached to the hydrogel production apparatus 800 or
20 the transducer 900. When the Z stage 110 is not used in the production of a hydrogel, the electrode 120 does not interfere with the Z stage 110. Thus, in this case, the electrode 120 can be used as the counter electrode and the counter electrode 30 is unnecessary.

In the case of the transducer, as in the case of the working electrode
25 20 as the first electrode, the electrode 121 or the electrode 122 as a second

electrode is formed in the shaping area 81 of the LSI chip 80. It is preferable to render a part of the shaping area 81 other than the front surface of the electrode water-repellent.

[0133] Since cells are negatively charged in general, in place of dielectrophoresis, electrophoresis can also be used to concentrate the cells densely on the selected working electrode. Electrophoresis is performed by applying a predetermined direct voltage between the selected working electrode and the counter electrode. In an electrophoresis step which is performed on the negatively charged cells, the working electrode serves as a positive electrode and the counter electrode serves as a negative electrode.

[0134] According to the present invention, it is possible to achieve a higher degree of flexibility in shaping, achieve greater versatility, and produce a hydrogel with a two-dimensional pattern or a three-dimensional pattern more efficiently than ever before. This makes it possible to produce a hydrogel of any shape accurately, easily, and quickly.

[0135] The present invention will be described as follows from a different perspective. It is to be noted that the following description is not contradictory to the disclosure described in the above-mentioned "MEANS TO SOLVE THE PROBLEMS" and it is possible to cross-reference the following description and the above-mentioned "MEANS TO SOLVE THE PROBLEMS" with each other.

[0136] - Item 1

A method of electrochemically producing a hydrogel by using electrolytic deposition, the method including:

a step of housing an electrolytic solution containing a precursor of the

hydrogel in an electrolytic tank, the electrolytic tank having a counter electrode therein and having a bottom surface with working electrodes arranged thereon; and

5 a first step of producing the hydrogel with a first two-dimensional pattern on the bottom surface by applying a first voltage between the counter electrode and all the working electrodes included in a first working electrode group, the first working electrode group consisting of one or more ones selected from among the working electrodes.

[0137] - Item 2

10 The electrochemical production method described in Item 1, further including a second step that is executed after the first step,

wherein the second step includes producing on the bottom surface, by applying a second voltage between the counter electrode and all the working electrodes included in a second working electrode group, the hydrogel with a three-dimensional pattern in which a second two-dimensional pattern connects to a bottom surface of the first two-dimensional pattern,

15 wherein the second working electrode group consists of one or more ones selected from among the working electrodes, and

20 wherein one or more ones included in the first working electrode group are included in the second working electrode group.

[0138] - Item 3

The electrochemical production method described in Item 2, including, between the first step and the second step, a step of discharging the electrolytic solution used in the first step from the electrolytic tank and

25

housing, in the electrolytic tank, the electrolytic solution which is to be used in the second step,

wherein the electrolytic solution used in the second step is different from the electrolytic solution used in the first step.

5 **[0139]** - Item 4

The electrochemical production method described in Item 2 or 3, wherein either or both of the first step and the second step include a first sub-step and a second sub-step,

wherein, when the first step includes the first sub-step and the second
10 sub-step, the first working electrode group includes a first sub-group and a second sub-group, the first voltage includes a first sub-voltage and a second sub-voltage, the first pattern includes a first sub-pattern and a second sub-pattern, and the first sub-group and the second sub-group do not have a common working electrode,

15 wherein, when the second step includes the first sub-step and the second sub-step, the second working electrode group includes a first sub-group and a second sub-group, the second voltage includes a first sub-voltage and a second sub-voltage, the second pattern includes a first sub-pattern and a second sub-pattern, and the first sub-group and the second
20 sub-group do not have a common working electrode,

wherein, by applying the first sub-voltage between the counter electrode and all the working electrodes included in the first sub-group, the hydrogel with the first sub-pattern is produced on the bottom surface, and

wherein, by applying the second sub-voltage between the counter
25 electrode and all the working electrodes included in the second sub-group,

the hydrogel with the second sub-pattern is produced on the bottom surface.

[0140] - Item 5

The electrochemical production method described in Item 4, including,
between the first sub-step and the second sub-step, a step of discharging
5 the electrolytic solution used in the first sub-step from the electrolytic tank
and housing, in the electrolytic tank, the electrolytic solution which is to be
used in the second sub-step,

wherein the electrolytic solution used in the second sub-step is
different from the electrolytic solution used in the first sub-step.

10 **[0141]** - Item 6

The electrochemical production method described in Item 4 or 5,
further including a sub-pattern removal step that is executed after the first
sub-step and the second sub-step,

wherein, in the first sub-step or the second sub-step, the hydrogel
15 which is dissolved by predetermined treatment is produced, and

wherein, in the sub-pattern removal step, the hydrogel with the first
sub-pattern or the second sub-pattern is dissolved by performing the
predetermined treatment.

[0142] - Item 7

20 The electrochemical production method described in any one of Items
2 to 6, further including a separation step that is performed after the first
step and before the second step,

wherein the first step and the second step are performed by using a Z
stage that has an adhesion surface parallel to the bottom surface of the
25 electrolytic tank and moves the adhesion surface in a direction

perpendicular to the bottom surface of the electrolytic tank,

wherein in the first step, the hydrogel with the first two-dimensional pattern is produced between the adhesion surface, which is located apart from the bottom surface of the electrolytic tank by a first distance in the electrolytic solution, and the bottom surface of the electrolytic tank and is
5 in contact with the adhesion surface,

wherein in the separation step, in a process whereby the adhesion surface is moved in the electrolytic solution by the Z stage to a position apart from the bottom surface of the electrolytic tank by a predetermined
10 distance, which is greater than the first distance, the hydrogel with the first two-dimensional pattern is separated from the bottom surface of the electrolytic tank while adhering to the adhesion surface, and

wherein in the second step, the hydrogel with the three-dimensional pattern is produced between the adhesion surface and the bottom surface of the electrolytic tank and the second two-dimensional pattern is in contact
15 with a bottom surface of the first two-dimensional pattern.

[0143] - Item 8

The electrochemical production method described in Item 7, wherein the adhesion surface has an affinity for water.

20 **[0144]** - Item 9

The electrochemical production method described in any one of Items 2 to 8,

wherein the number of working electrodes included in the second working electrode group is greater than the number of working electrodes
25 included in the first working electrode group, and

wherein all the working electrodes included in the first working electrode group are included in the second working electrode group.

- Item 10

5 The electrochemical production method described in Item 7 or 8,
wherein the number of working electrodes included in the first working electrode group is greater than the number of working electrodes included in the second working electrode group, and

wherein all the working electrodes included in the second working electrode group are included in the first working electrode group.

10 **[0145]** - Item 11

The electrochemical production method described in any one of Items 1 to 10,

wherein each of the working electrodes protrudes from the bottom surface, and

15 wherein side faces of each of the working electrodes are surrounded with insulators protruding from the bottom surface of the electrolytic tank.

[0146] - Item 12

The electrochemical production method described in any one of Items 1 to 11,

20 wherein the bottom surface of the electrolytic tank other than front surfaces of the working electrodes is water-repellent.

[0147] - Item 13

The electrochemical production method described in any one of Items 1 to 12, further including a step of dissolving, by applying a voltage, which
25 is different from the first voltage, between the counter electrode and all the

working electrodes included in the first working electrode group in a state in which the hydrogel with the first two-dimensional pattern is in contact with a working electrode included in the first working electrode group, a part of the hydrogel at which the hydrogel is in contact with the working
5 electrode included in the first working electrode group.

[0148] - Item 14

A method of producing a hydrogel with a pattern formed of cells, including a step of using an electrochemical production method that is the electrochemical production method described in any one of Items 1 to 13
10 and uses, as an electrolytic solution, a suspension containing a precursor of the hydrogel and the cells.

[0149] - Item 15

The production method described in Item 14, further including a step of concentrating the cells on the first working electrode group by
15 dielectrophoresis or electrophoresis before the first step or a step of concentrating the cells on the second working electrode group by dielectrophoresis or electrophoresis before the second step.

[0150] - Item 16

A hydrogel production apparatus for producing a hydrogel by using
20 electrolytic deposition, including:

an electrolytic tank with a counter electrode set therein, the electrolytic tank having a bottom surface with working electrodes arranged thereon;

a controller applying a voltage between the counter electrode and one
25 or more ones selected from among the working electrodes; and

a Z stage having an adhesion surface for the hydrogel's adhesion and moving the adhesion surface in a direction perpendicular to the bottom surface of the electrolytic tank while keeping the adhesion surface parallel to the bottom surface of the electrolytic tank.

5 **[0151]** - Item 17

The hydrogel production apparatus described in Item 16, wherein the adhesion surface has an affinity for water.

[0152] - Item 18

10 The hydrogel production apparatus described in Item 16 or 17,
 wherein each of the working electrodes protrudes from the bottom surface, and

 wherein side faces of the working electrodes are surrounded with insulators protruding from the bottom surface of the electrolytic tank.

[0153] - Item 18

15 A hydrogel production apparatus for producing a hydrogel by using electrolytic deposition, including:

 an electrolytic tank with a counter electrode set therein, the electrolytic tank having a bottom surface with working electrodes arranged thereon; and

20 a controller applying a voltage between the counter electrode and one or more ones selected from among the working electrodes,

 each of the working electrodes protruding from the bottom surface, and

25 side faces of the working electrodes being surrounded with insulators protruding from the bottom surface of the electrolytic tank.

[0154] - Item 19

The hydrogel production apparatus described in any one of Items 16 to 18,

wherein the bottom surface of the electrolytic tank other than front surfaces of the working electrodes is water-repellent.

[0155] - Item 20

The hydrogel production apparatus described in any one of Items 16 to 19, further including:

an electrode for phoresis; and
an oscillator that applies an alternating voltage of a predetermined frequency between the electrode for phoresis and one or more ones selected from among the working electrodes.

[0156] - Item 21

A transducer including:
the hydrogel production apparatus described in any one of Items 16 to 20; and
an integrated circuit,
the bottom surface of the electrolytic tank being a front surface of the integrated circuit.

20

[INDUSTRIAL APPLICABILITY]

[0157] The technique of producing a hydrogel according to the present invention is useful in, for example, assessment of drugs as an alternative to animal testing, production of operation practice equipment, production of medical supplies, and so forth.

25

WHAT IS CLAIMED IS:

1. A method of electrochemically producing a hydrogel by using electrolytic deposition of a hydrogel, the method by which a hydrogel is formed by a reaction which is induced in an electrolytic solution by an electrode product electrochemically generated by electrodes installed in the electrolytic solution, the method comprising

a step of preparing an apparatus including an electrolytic tank with a bottom surface on which a two-dimensional array of working electrodes is provided and a counter electrode which is installed in the electrolytic tank, housing an electrolytic solution containing a dissolved substance, which causes electrolytic deposition of the hydrogel, in the electrolytic tank, and, by applying a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes, forming, on the bottom surface, the hydrogel with a two-dimensionally defined pattern corresponding to an arrangement of the selected working electrodes.

2. The method of electrochemically producing a hydrogel according to Claim 1, comprising:

a first step of forming a hydrogel with a two-dimensionally defined first pattern by applying a first voltage as the predetermined voltage to a first working electrode group as the one or more selected working electrodes; and

a second step of forming a hydrogel with a two-dimensionally defined second pattern by applying a second voltage as the predetermined voltage to a second working electrode group as the one or more selected working

electrodes, wherein

the second step is performed after the first step, and

a hydrogel with a three-dimensionally defined pattern including at least two layers formed of the first pattern and the second pattern, which is
5 located under the first pattern on a side thereof closer to the bottom surface, is formed.

3. The method of electrochemically producing a hydrogel according to Claim 2, wherein

10 at least one of the first step and the second step includes a first sub-step and a second sub-step, a corresponding one of the first working electrode group and the second working electrode group includes a first working electrode sub-group and a second working electrode sub-group, a corresponding one of the first voltage and the second voltage includes a
15 first sub-voltage and a second sub-voltage, and a corresponding one of the first pattern and the second pattern includes a first sub-pattern and a second sub-pattern,

the second working electrode sub-group consists of only the working electrode which does not belong to the first working electrode sub-group,

20 and

a hydrogel with the first sub-pattern is formed by applying the first sub-voltage to the first working electrode sub-group and a hydrogel with the second sub-pattern is formed by applying the second sub-voltage to the second working electrode sub-group.

25

4. The method of electrochemically producing a hydrogel according to Claim 3, wherein

in the second sub-step, a hydrogel which dissolves under a predetermined condition is formed, and

5 the method further includes, at least after the first sub-step and the second sub-step, a sub-pattern removal step of selectively removing the hydrogel with the second sub-pattern by dissolving the hydrogel with the second sub-pattern by providing the hydrogel with the second sub-pattern with the predetermined condition.

10

5. The method of electrochemically producing a hydrogel according to any one of Claims 2 to 4, wherein

a Z stage that has an adhesion surface facing the bottom surface parallel thereto and is displaceable in a Z direction perpendicular to the

15 bottom surface is further prepared,

by performing the first step with the Z stage being located in the electrolytic solution such that the adhesion surface is apart from the bottom surface by a first distance, a hydrogel with the first pattern whose upper surface, of two surfaces perpendicular to the Z direction, on a side farther
20 apart from the bottom surface adheres to the adhesion surface is formed,

and after that, by displacing the Z stage with the adhesion surface, to which the upper surface of the first pattern adheres, in a direction in which the Z stage moves away from the bottom surface, a lower surface, of the two surfaces perpendicular to the Z direction, of the first pattern on a side
25 closer to the bottom surface is moved away from the bottom surface by a

second distance, and

by performing the second step with the first pattern being located in the electrolytic solution such that the lower surface is apart from the bottom surface by the second distance, a hydrogel with the second pattern
5 connecting to the lower surface of the first pattern is formed.

6. The method of electrochemically producing a hydrogel according to Claim 5, wherein

the adhesion surface is subjected to treatment that makes the adhesion
10 surface have an affinity for water.

7. The method of electrochemically producing a hydrogel according to any one of Claims 2 to 6, wherein

all of the first working electrode groups are included in the second
15 working electrode group, and

the three-dimensionally defined pattern has a structure in which the first pattern is supported from below by the second pattern.

8. The method of electrochemically producing a hydrogel according
20 to Claim 5 or 6, wherein

all of the second working electrode groups are included in the first working electrode group, and

the three-dimensionally defined pattern has a structure in which the second pattern is supported from above, which is a side where the adhesion
25 surface is located, by the first pattern so as to hang therefrom.

9. The method of electrochemically producing a hydrogel according to any one of Claims 1 to 8, wherein

all of the working electrodes which compose the two-dimensional
5 array protrude from the bottom surface and side faces of each protruding
working electrode are surrounded with an insulating layer formed so as to
protrude from the bottom surface along with the working electrode.

10. The method of electrochemically producing a hydrogel according
10 to any one of Claims 1 to 9, wherein

a part of the bottom surface other than front surfaces of the working
electrodes is made water-repellent.

11. The method of electrochemically producing a hydrogel according
15 to any one of Claims 1 to 10, further comprising

a step of forming, on the bottom surface, a hydrogel with the two-
dimensionally defined pattern corresponding to an arrangement of the
selected working electrodes by applying the predetermined voltage to the
selected working electrodes, and after that, in a state in which the formed
20 hydrogel is in contact with the selected working electrodes, promoting
separation of the hydrogel from the selected working electrodes by
dissolving a contact part of the hydrogel with the selected working
electrodes by applying a voltage for hydrogel separation, which is different
from the predetermined voltage, to the selected working electrodes.

12. A method of producing a hydrogel patterned with cells, which is obtained by distributing predetermined cells over a hydrogel scaffold, wherein

by performing the method of electrochemically producing a hydrogel according to any one of Claims 1 to 11 by using, as an electrolytic solution containing a dissolved substance which causes electrolytic deposition of the hydrogel, a suspension further containing the predetermined cells, a hydrogel with the distributed predetermined cells is formed on the bottom surface of the electrolytic tank.

10

13. The method of producing a hydrogel patterned with cells according to Claim 12, wherein

the predetermined cells include one or more types of cells, and the method includes a step of performing the method of electrochemically producing a hydrogel according to Claim 2 by using, as the electrolytic solution concerned, a suspension containing one type of cell of the predetermined cells along with a dissolved substance, which causes electrolytic deposition of the hydrogel concerned, in any one of the first step and the second step.

20

14. The method of producing a hydrogel patterned with cells according to Claim 13, comprising

a step of performing the method by using, as the electrolytic solution concerned, a suspension containing another type of cell, which is different from the one type of cell, of the predetermined cells along with a dissolved

25

substance, which causes electrolytic deposition of the hydrogel concerned, in another of the first step and the second step.

15. The method of producing a hydrogel patterned with cells
5 according to Claim 12, wherein
the predetermined cells include one or more types of cells, and
the method of electrochemically producing a hydrogel according to
Claim 3 is performed by using, as the electrolytic solution concerned, a
suspension containing one type of cell of the predetermined cells along
10 with a dissolved substance, which causes electrolytic deposition of the
hydrogel concerned, in any one of the first sub-step and the second sub-
step.

16. The method of producing a hydrogel patterned with cells
15 according to Claim 15, wherein
the method is performed by using, as the electrolytic solution
concerned, a suspension containing another type of cell, which is different
from the one type of cell, of the predetermined cells along with a dissolved
substance, which causes electrolytic deposition of the hydrogel concerned,
20 in another of the first sub-step and the second sub-step.

17. The method of producing a hydrogel patterned with cells
according to any one of Claims 12 to 16, comprising
before a step of forming a hydrogel by applying the predetermined
25 voltage to the selected working electrodes in a state in which the

suspension is housed in the electrolytic tank, a dielectrophoresis step of densely distributing the predetermined cells on the selected working electrodes by dielectrophoresis by applying an alternating voltage of a predetermined frequency to the selected working electrodes.

5

18. The method of producing a hydrogel patterned with cells according to Claim 17, wherein

in the dielectrophoresis step, an electrode with an electrode plane facing, parallel to the bottom surface, a region of the bottom surface in which the two-dimensional array of the working electrodes is provided is used.

10

19. The method of producing a hydrogel patterned with cells according to Claim 17, wherein

in the dielectrophoresis step, an electrode which is provided on the bottom surface so as to be located around each of the two-dimensional array of the working electrodes is used.

15

20. The method of producing a hydrogel patterned with cells according to any one of Claims 12 to 16, comprising

20

before a step of forming a hydrogel by applying the predetermined voltage to the selected working electrodes in a state in which the suspension is housed in the electrolytic tank, an electrophoresis step of densely distributing the predetermined cells on the selected working electrodes by electrophoresis by applying a predetermined direct voltage to

25

the selected working electrodes.

21. A hydrogel production apparatus that includes an electrolytic tank with a bottom surface on which a two-dimensional array of working
5 electrodes is provided and a counter electrode, which is installed in the electrolytic tank, and can apply a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes, the hydrogel production apparatus comprising:

a Z stage that has an adhesion surface facing the bottom surface
10 parallel thereto and is displaceable in a Z direction perpendicular to the bottom surface.

22. The hydrogel production apparatus according to Claim 21,
wherein
15 the adhesion surface is subjected to treatment that makes the adhesion surface have an affinity for water.

23. A hydrogel production apparatus that includes an electrolytic tank with a bottom surface on which a two-dimensional array of working
20 electrodes is provided and a counter electrode, which is installed in the electrolytic tank, and can apply a predetermined voltage to one or more selected working electrodes of the two-dimensional array of the working electrodes, wherein

all of the working electrodes that make up the two-dimensional array
25 protrude from the bottom surface and side faces of each protruding

working electrode are surrounded with an insulating layer formed so as to protrude from the bottom surface along with the working electrode.

24. The hydrogel production apparatus according to Claim 21 or 22,
5 wherein

all of the working electrodes that make up the two-dimensional array protrude from the bottom surface and side faces of each protruding working electrode are surrounded with an insulating layer formed so as to protrude from the bottom surface along with the working electrode.

10

25. The hydrogel production apparatus according to any one of Claims 21 to 24, wherein

a part of the bottom surface other than front surfaces of the working electrodes is made water-repellent.

15

26. The hydrogel production apparatus according to any one of Claims 21 to 25, comprising:

an oscillator that can apply an alternating voltage of a predetermined frequency to the selected working electrodes.

20

27. The hydrogel production apparatus according to Claim 26, further comprising

an electrode for dielectrophoresis that is installed or can be installed in the electrolytic tank, wherein

25 the electrode for dielectrophoresis is installed or can be installed in

the electrolytic tank so that an electrode plane thereof faces, parallel to the bottom surface, a region of the bottom surface in which the two-dimensional array of the working electrodes is provided.

5 28. The hydrogel production apparatus according to Claim 26,
wherein
 the electrolytic tank further includes an electrode for dielectrophoresis,
and
 the electrode for dielectrophoresis is provided on the bottom surface
10 so as to be located around each of the two-dimensional array of the
working electrodes.

 29. A transducer that includes an electrolytic tank, which can house
an electrolytic solution and a hydrogel which is electrolytically deposited
15 in the electrolytic solution, mounted on an LSI chip and is used for
electrochemical production of a patterned hydrogel, wherein
 in a shaping area defined on a bottom surface of the electrolytic tank,
first electrodes which are provided in the LSI chip in a two-dimensional
array arrangement are located,
20 the transducer includes a Z stage with an adhesion surface, which can
be installed in the electrolytic tank, and
 the Z stage can be installed in the electrolytic tank so as be
displaceable in a Z direction perpendicular to the bottom surface, in such a
way that the adhesion surface faces the shaping area of the bottom surface
25 parallel to the shaping area.

30. The transducer according to Claim 29, wherein
the adhesion surface is subjected to treatment that makes the adhesion
surface have an affinity for water.

5

31. A transducer that includes an electrolytic tank, which can house
an electrolytic solution and a hydrogel which is electrolytically deposited
in the electrolytic solution, mounted on an LSI chip and is used for
electrochemical production of a patterned hydrogel, wherein

10 in a shaping area defined on a bottom surface of the electrolytic tank,
first electrodes which are provided in the LSI chip in a two-dimensional
array arrangement are located, and

all of the first electrodes protrude from the bottom surface and side
faces of each protruding first electrode are surrounded with an insulating
15 layer formed so as to protrude from the bottom surface along with the first
electrode.

32. The transducer according to any one of Claims 29 to 31, wherein
a part of the shaping area other than front surfaces of the first
20 electrodes is made water-repellent.

33. The transducer according to any one of Claims 29 to 31, wherein
in the shaping area, a second electrode which is provided in the LSI
chip so as to be located around each of the first electrodes is further located.

25

34. The transducer according to Claim 33, wherein
the second electrode is formed over an entire surface of the shaping
area without continuity between the first electrodes and the second
electrode.

5

35. The transducer according to Claim 33 or 34, wherein
a part of the shaping area other than front surfaces of the first
electrodes and a front surface of the second electrode is made water-
repellent.

10

36. The transducer according to any one of Claims 29 to 32, further
comprising:

a second electrode that is installed or can be installed in the
electrolytic tank, wherein

15

the second electrode is installed or can be installed in the electrolytic
tank so that an electrode plane thereof faces the shaping area of the bottom
surface parallel to the shaping area.