

PATENT SPECIFICATION

(11) 1 434 038

1 434 038

- (21) Application No. 31775/73 (22) Filed 4 July 1973
 (31) Convention Application No. 269 648
 (32) Filed 7 July 1972 in
 (33) United States of America (US)
 (44) Complete Specification published 28 April 1976
 (51) INT CL² C21D 9/50
 (52) Index at acceptance C7N 4D1 4F 8



(54) HEAT TREATMENT OF WELDS

(71) We, HUGHES TOOL COMPANY, a Company organised and existing under the laws of the State of Delaware, United States of America, of 5425 Polk Avenue, Houston, Texas 77001, United States of America do hereby declare the invention for which we pray that a patent may be granted to us, and the method by which it is to be performed to be particularly described in and by the following statement:—

This invention relates in general to the post welding heat treatment of the welds of metal components and particularly tubular components. It is especially suitable for increasing the strength in the weld and the heat affected zone to produce an overall strength that at least matches that of the body of the tubular member.

It is common to use electrical resistance (flash-butt) welding to join tubular members such as drill pipes and their rotary connectors, called "tool joints", in the oil well drilling industry. It is important that the weld and the heat affected zone be able to carry as high a tensile load and be able to withstand fatigue stresses or impacts as well as the pipe used in the assembly. Otherwise, the weld or the heat affected zone may not have adequate load carrying capability and may fail when subjected to the severe stresses commonly encountered during oil well drilling.

As best seen in Figure 5 of the accompanying drawings, a drill pipe A usually has an area B of increased cross-section on each end called an upset, which is welded at C to a tool joint D. It is possible to have a lower yield strength of the metal in the heat affected zone of weld C than in the body A of the pipe and still have greater overall strength in the weld and heat affected zone. This is due to the larger cross-sectional area in upset B as compared with the smaller cross-sectional area of the non-upset portion or body A of the pipe. Typical ratios of an upset B cross-sectional area to the pipe body A cross-sectional areas may range from 1.38 to 2.10 for commercially available assemblies.

In some of the high strength pipe assemblies the load carrying capability of the heat affected zone around the weld C does not compare favourably with that of the pipe or tool joint when utilizing the prior art heat treatments such as normalizing and tempering the weld. In one prior art example, a 3-1/2 inch diameter 15.50 pound, S-135 drill pipe had a yield strength of 89,900 psi in the heat affected zone of upset B that was heat treated by normalizing and tempering, whereas the body A of the pipe had a yield strength of 140,000 psi. The ratio of the cross-sectional areas of the upset portion B of the pipe to the body A of the pipe was 1.42 to 1. With the pipe having a yield strength of 140,000 psi, a minimum yield strength of 99,000 psi is required in the heat affected zone of the upset B to essentially match the load carrying capability of the pipe. Using a safety factor of 10%, then the minimum yield strength of the heat affected zone should be at least 110,000 psi. The prior art method of normalizing and tempering the heat affected zone has been found incapable of producing such a yield strength in the heat affected zone.

The problem is more difficult than simply increasing the hardness of the weld and heat affected zone. Hardening too fast leads to the formation of cracks. Further, excessive hardness and brittleness leads to failures.

The invention may be summarized as method and apparatus for heat treating welds such that their overall strengths match those of the pipe bodies to which they are connected. To accomplish this result, a post welding heat treatment is provided comprising the steps of: heating the weld and heat affected zone to a temperature above critical; quenching the weld and heat affected zone at a rate to harden them across their cross-section without cracking, and to increase their overall strength to a value at least matching that of one of the components; and tempering the weld and heat affected zone. Too rapid cooling may result in cracking and too slow cooling will not provide the proper

55

60

65

70

75

80

85

90

95

100

hardness level. For the relatively thick sections of pipe to which tool joints are welded for oil well drilling, air quenching is preferably performed on the exterior, as well as in the interior, circumferential surfaces of the weld. As a consequence, the entire cross-sectional thickness of the weld and heat affected zone is hardened satisfactorily, without cracking. For best results, the post welding treatment includes first cooling the weld to a selected temperature, below the transformation temperature, reheating and quenching, and then tempering.

Apparatus for performing the method on a weld formed between a metal pipe and a metal connector may comprise: a generally ring shaped manifold; nozzle means carried by the manifold to direct flow inwardly; a mandrel; nozzle means carried by the mandrel to direct fluid flow outwardly; pumping means connected with the ring shaped manifold and the mandrel to supply fluid thereto.

The following is a more detailed description of one embodiment of the invention, reference being made to the accompanying drawings in which:

Figure 1 is a perspective view as seen obliquely from one end of a pipe and tool joint, with a ring shaped manifold and mandrel positioned to direct a flow of gaseous fluid against the heat affected zone of a weld;

Figure 2 is an end view of a ring shaped manifold, nozzle means and connections of the form also shown in Figure 1;

Figure 3 is a side elevation view of the mandrel shown in Figure 1;

Figure 4 is a schematic diagram of a pneumatic circuit for supplying gaseous fluid to the manifold and mandrel; and

Figure 5 (referred to earlier) is a fragmentary side elevation view in longitudinal section of one-half of a tool joint and the end of an upset drill pipe to which it has been welded.

Referring initially to Figure 1 of the drawing, a pipe 11 has secured to one end a connection member or tool joint 13 by means of a weld 15, generally formed by the electrical resistance (butt-flash weld) technique. This welding technique is well known, having been utilized for decades for such purposes as connecting tool joints to drill pipe used in rotary well drilling.

A ring shaped manifold 17 is shown positioned concentrically about the weld 15. A plurality of nozzle means 19 are secured to the inner periphery of the manifold, which has in this instance the geometric form known as the torus. Such nozzle means here is an element with a polygon shaped head through which extends an orifice 21. The lower end of each element is preferably

threaded for releasable attachment to a nozzle element pedestal 23 secured to the manifold. As shown, the nozzle elements are closely spaced along the inner periphery of the manifold such that the discharge of gaseous fluid from the orifices 21 tends to impinge against the entire circumferential area of the heat affected zone generated during welding.

Suitable connections 25 are utilized so that a gaseous fluid may be transmitted by a compressor 27 to the manifold, and also to a mandrel or probe 29 adapted for insertion within the tool joint 13 and end of pipe 11. The probe is preferably concentrically aligned with the tool joint such that its nozzle means or orifices 31 are equidistant from the tool joint. Here, as with the manifold, the number and spacing of the nozzle means is selected such that the gaseous fluid tends to flow against the entire circumferential area of the interior surface of the weld 15. The term "nozzle means" is used in its broadest sense to cover orifices, nozzles or any other form of openings through which a fluid may be directed.

For the purpose of controlling the axial position of the orifices 31 of mandrel 29 relative to the weld 15, a positioner means 33 is used. Here the positioner is in the form of a shoulder secured to a mid-region of the mandrel 29 to extend radially outward into engagement with the extremity of the tool joint 13.

The method of the invention may be practised by utilizing the pump 27, manifold 17, and mandrel 29 for pumping a fluid transversely against the exterior and interior circumferential surfaces of the weld 15.

The following is a specific example of one way in which the method was successfully practised:

A joint of the previously described 3½ inch, 15.50 pound, s—135 steel pipe, having a yield strength of approximately 140,000 psi, was welded to a tool joint of AISI 4137H steel by the flash-butt welding method. The ends of the pipe had an upset region B having a cross-sectional thickness greater than the cross-sectional thickness of the body A of the pipe by a ratio of 1.42 to 1.

Next, the heat affected zone was cooled to below 125°F.

Then, the assembly was heated in an induction coil to a temperature from about 1750° to 1800°F.

Thereafter, the manifold 17 and mandrel 29 were positioned approximately as shown in Figure 1 to pump a gaseous fluid, that in this instance was air at a temperature of about 100°F, transversely against the interior and exterior circumferential surfaces of the weld. The pressure above the mandrel and manifold was 53 psig and the time of cooling was 1½ minutes. The

manifold had a total of sixteen, drilled orifices for nozzle means, eight of which were 7/64 inch diameter and evenly spaced to direct fluid perpendicular with the pipe longitudinal axis. The other eight orifices were 1/8 inch diameter holes inclined at 7 1/2° relative to the longitudinal axis of the pipe. The mandrel was constructed of thin wall tubing of 1.050 inch outside diameter and 0.824 inch inside diameter. There were 56 drilled orifices, half of which were 7/64 inch diameter and half 1/8 inch diameter, all evenly spaced circumferentially and over a length of 4 1/4 inches in order to direct fluid uniformly and perpendicularly against the weld and inner pipe surface.

Finally, the assembly was tempered to a temperature of 1175°F.

As a result of using the above method and apparatus, the yield strength of the weld and heat affected zone increased from 89,900 to 120,500. Since the minimum yield strength acceptable in the upset area B is 110,000 psi after utilization of a safety factor of 10%, the treatment successfully increased the strength of the heat affected zone to a satisfactory value.

In the above described preferred embodiment, the weld must be initially cooled below the transformation temperature but need not be cooled to a temperature as low as 125°F for satisfactory results under all conditions. Such cooling may be accomplished by discharging water at normal hydrant temperatures in a stream that impinges on the pipe circumferentially about eight inches from the weld. After thus cooling, the weld and heat affected zone may be heated by suitable means such as an induction coil to a satisfactory pre-quenching temperature preferably above the upper critical such as that specified. This temperature must be above the lower critical to obtain any beneficial results. The quenching by air as described lowers the temperature to below about 600°F at a cooling rate that avoids the formation of extremely brittle structures that are likely to crack. Air is not the only fluid that will accomplish this result. Some liquids such as oils or other suitable quenchants, are capable of accomplishing a satisfactory result, although not with exactly the same cooling rate. After suitable tempering the metal in any instance must have a minimum yield strength that produces an overall strength in the weld area comparing favourably with that of the pipe.

It should be apparent from the foregoing that an invention has been provided having significant advantages. Through utilization of the method, the strength of the weld and heat affected zone may be increased to a level at least matching that of the body of the pipe. Further, the hardness of the heat

affected zone is obtained in a manner that avoids cracks and is easily controlled. It has been found that the time duration of the air quenching is not critical so long as a satisfactory minimum such as 1 1/4 minutes is used for the example given. This is especially advantageous in high production manufacturing since some variations in timing may be expected.

While the invention has been shown in only one of its forms, it should be apparent to those skilled in the art that it is not so limited, but is susceptible to various changes and modifications. The term fluid therefore encompasses liquids that meet the above requirements. The term gaseous fluid includes gases that may include a mist such as steam. Modifications to the method steps and to the specific manner of carrying out the method will become apparent to those skilled in the art in view of the previous description, as will modifications to the form of apparatus.

WHAT WE CLAIM IS:—

1. A method of heat treating a weld between metal components comprising the steps of: heating the weld and heat affected zone to a temperature above critical; quenching the weld and heat affected zone at a rate to harden them across their cross-section without cracking, and to increase their overall strength to a value at least matching that of one of the components; and tempering the weld and heat affected zone.

2. A method according to claim 1 wherein the weld and heat affected zone is cooled below the transformation temperature before being heated to above the critical temperature.

3. A method according to claim 1 or claim 2 wherein the weld and heat affected zone are quenched to a temperature of 600°F or less in 1 1/2 minutes.

4. A method according to any of claims 1 to 3 wherein said temperature above critical to which the weld and heat affected zone are heated is in the range of 1750°F to 1800°F.

5. A method according to any of claims 1 to 4 wherein the weld and heat affected zone are tempered to substantially 1175°F.

6. A method according to any of claims 1 to 5 wherein the quenching is effected by air.

7. A method according to any of claims 1 to 6 wherein the metal components welded together comprise a metal pipe and a metal connector, the connector being welded to one end of the pipe, and wherein the quenching increases the overall strength to at least the strength of the pipe.

8. A method according to claim 7 wherein the metal connector is welded to an end of



manifold had a total of sixteen, drilled orifices for nozzle means, eight of which were 7/64 inch diameter and evenly spaced to direct fluid perpendicular with the pipe longitudinal axis. The other eight orifices were 1/8 inch diameter holes inclined at 7 1/2° relative to the longitudinal axis of the pipe. The mandrel was constructed of thin wall tubing of 1.050 inch outside diameter and 0.824 inch inside diameter. There were 56 drilled orifices, half of which were 7/64 inch diameter and half 1/8 inch diameter, all evenly spaced circumferentially and over a length of 4 1/4 inches in order to direct fluid uniformly and perpendicularly against the weld and inner pipe surface.

Finally, the assembly was tempered to a temperature of 1175°F.

As a result of using the above method and apparatus, the yield strength of the weld and heat affected zone increased from 89,900 to 120,500. Since the minimum yield strength acceptable in the upset area B is 110,000 psi after utilization of a safety factor of 10%, the treatment successfully increased the strength of the heat affected zone to a satisfactory value.

In the above described preferred embodiment, the weld must be initially cooled below the transformation temperature but need not be cooled to a temperature as low as 125°F for satisfactory results under all conditions. Such cooling may be accomplished by discharging water at normal hydrant temperatures in a stream that impinges on the pipe circumferentially about eight inches from the weld. After thus cooling, the weld and heat affected zone may be heated by suitable means such as an induction coil to a satisfactory pre-quenching temperature preferably above the upper critical such as that specified. This temperature must be above the lower critical to obtain any beneficial results. The quenching by air as described lowers the temperature to below about 600°F at a cooling rate that avoids the formation of extremely brittle structures that are likely to crack. Air is not the only fluid that will accomplish this result. Some liquids such as oils or other suitable quenchants, are capable of accomplishing a satisfactory result, although not with exactly the same cooling rate. After suitable tempering the metal in any instance must have a minimum yield strength that produces an overall strength in the weld area comparing favourably with that of the pipe.

It should be apparent from the foregoing that an invention has been provided having significant advantages. Through utilization of the method, the strength of the weld and heat affected zone may be increased to a level at least matching that of the body of the pipe. Further, the hardness of the heat

affected zone is obtained in a manner that avoids cracks and is easily controlled. It has been found that the time duration of the air quenching is not critical so long as a satisfactory minimum such as 1 1/4 minutes is used for the example given. This is especially advantageous in high production manufacturing since some variations in timing may be expected.

While the invention has been shown in only one of its forms, it should be apparent to those skilled in the art that it is not so limited, but is susceptible to various changes and modifications. The term fluid therefore encompasses liquids that meet the above requirements. The term gaseous fluid includes gasses that may include a mist such as steam. Modifications to the method steps and to the specific manner of carrying out the method will become apparent to those skilled in the art in view of the previous description, as will modifications to the form of apparatus.

WHAT WE CLAIM IS:—

1. A method of heat treating a weld between metal components comprising the steps of: heating the weld and heat affected zone to a temperature above critical; quenching the weld and heat affected zone at a rate to harden them across their cross-section without cracking, and to increase their overall strength to a value at least matching that of one of the components; and tempering the weld and heat affected zone.

2. A method according to claim 1 wherein the weld and heat affected zone is cooled below the transformation temperature before being heated to above the critical temperature.

3. A method according to claim 1 or claim 2 wherein the weld and heat affected zone are quenched to a temperature of 600°F or less in 1 1/4 minutes.

4. A method according to any of claims 1 to 3 wherein said temperature above critical to which the weld and heat affected zone are heated is in the range of 1750°F to 1800°F.

5. A method according to any of claims 1 to 4 wherein the weld and heat affected zone are tempered to substantially 1175°F.

6. A method according to any of claims 1 to 5 wherein the quenching is effected by air.

7. A method according to any of claims 1 to 6 wherein the metal components welded together comprise a metal pipe and a metal connector, the connector being welded to one end of the pipe, and wherein the quenching increases the overall strength to at least the strength of the pipe.

8. A method according to claim 7 wherein the metal connector is welded to an end of



the pipe having a greater wall thickness than the main body of the pipe.

- 5 9. A method according to claim 7 or claim 8 wherein the exterior surfaces of the weld and heat affected zone are quenched by pumping a gaseous fluid against the exterior circumferential surface of the weld.

- 10 10. A method according to any of claims 7 to 9 wherein both the interior and exterior surfaces of the weld and heat affected zone are quenched.

11. A method according to claim 10 wherein the interior surfaces of the weld

and heat affected zone are quenched by pumping a gaseous fluid against the interior circumferential surface of the weld. 15

12. A method of heat treating a weld between a metal pipe and a metal connector substantially as hereinbefore described.

GERALD CARTER & COMPANY,
Chartered Patent Agents,
11 Altior Court,
Shepherds Hill,
London N.6.
Agents for the Applicants.

Printed for Her Majesty's Stationery Office by the Courier Press, Leamington Spa, 1976.
Published by the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from
which copies may be obtained.