

REPLACED SHEETS		SG
☒	Description : paged 1 to paged 3	
☒	Claim(s) : paged 4 to paged 6	
☐	Drawing(s) : paged to paged	
☒	Abstract : paged 10 to paged 1	
DATE OF RECEIPT		

7605919-1 1105

TITLE OF THE INVENTION

GROUTING LIQUID FOR INJECTION INTO A GROUND

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

The present invention relates to a suspension-type grouting liquid for injection into a ground containing, as a main ingredient, slag or water glass or sodium aluminate in addition to the slag, or, if necessary, cement and/or dispersant in addition to said mixture, and particularly, to such a suspension-type grouting liquid for injection into a ground which shows high strength of consolidation in spite that it shows low viscosity and long gellation time, and moreover, which is excellent in long duration strength of consolidation.

DESCRIPTION OF THE PRIOR ART

A water glass-type suspension grout, which is composed of adding cement into water glass, is well known in the past. In this case, if the grout is adjusted to a long gellation time for improving the penetrative property, the strength of consolidation lowered, and moreover, long duration strength of consolidation is also lacked.

Then, the grout of cement-water glass having low mol ratio is newly proposed, which is possible to be adjusted to a long gellation time.

But, it also shows the gellation time of merely several minutes to ten minutes, and thus, the penetrative property thereof

This Sheet Has Been Replaced



is not satisfied. Moreover, in this case, the cement and water glass can not be satisfactorily mixed, and thus, the reaction between them is not completely accomplished, and as a result thereof, the long stabilization of the consolidated material can not be obtained in the ground.

Accordingly, it is an object of the present invention to provide a grouting liquid for injection into a ground, which shows high strength of consolidation in spite of having a long gellation time and low viscosity, and which is excellent in penetration property and in long duration strength of consolidation, and moreover, which overcomes disadvantages associated with the above-described prior arts.

SUMMARY OF THE INVENTION

To achieve the above object, according to the present invention, there is provided a grouting liquid for injection into a ground which comprises water glass having mol ratio of 2.5 or less and slag, or sodium aluminate having mol ratio of 10 or more and slag, or, moreover, water glass, sodium aluminate and slag, or if necessary, cement and/or dispersant in addition to each of said mixtures.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention will be described by way of preferred embodiments.

The present grouting liquid comprises slag as a main ingredient, and is composed of the following conditions.

1. A grouting liquid for injection into a ground which comprises



slag and water glass having mol ratio of 2.5 or less, in which the mol ratio of the water glass indicates the value of molar concentration of SiO_2 /molar concentration of Na_2O in water glass.

2. A grouting liquid for injection into a ground which comprises slag and sodium aluminate having mol ratio of 10 or more, in which the mol ratio of sodium aluminate represents the value of molar concentration of Na_2O /molar concentration of Al_2O_3 in the liquid of sodium aluminate.

3. A grouting liquid for injection into a ground which comprises slag, water glass, and sodium aluminate, in which the value of molar concentration of SiO_2 in water glass/molar concentration of total Na_2O in water glass and sodium aluminate shows 2.5 or less.

4. A grouting liquid for injection into a ground which comprises, if necessary, cement and/or dispersant in addition to each of said mixtures 1, 2 and 3.

5. A grouting liquid for injection into a ground, wherein said slag or cement used in said 1, 2, 3 and 4 is fine grain slag or fine grain cement having, respectively, specific surface area of preferably $8000\text{cm}^2/\text{g}$ or more.

The amounts of said water glass, slag or sodium aluminate to be used are respectively variable, and thus, it is very difficult to determine the amounts, but the rough amounts are determined as follows.

1. Water glass

The amount of water glass to be used is, as molar



concentration, 0.3 to 4.0 mol, preferably 0.4 to 2.0 mol of SiO_2 in 1000g of the total blending amounts.

2. Slag

The amount of slag to be used is 100 to 500g, preferably 200 to 400g in 1000g of total blending amounts.

3. Sodium aluminate

The sodium aluminate is generally used as a liquid state. The amount thereof to be used is, as molar ratio, 0.002 to 0.1 mol, preferably, 0.0025 to 0.08 mol of Al_2O_3 in 1000g of total blending amounts.

When each of said amounts is out of said range, the viscosity of the obtained liquid becomes high, and as a result, the penetrative property becomes inferior, or the gellation time of the liquid becomes short, or abnormally long, and as a result, it can not be completely consolidated to show semi-consolidation state, and accordingly, the strength of the consolidated material becomes weak.

The functions of the present invention are considered as follows.

In the past, the grout of cement-water glass having low mol ratio is known, which is possible of prolonging the gellation time. But, the gellation time is merely in the range of several minutes to ten minutes.

The reason is considered that the amount of CaO in the cement is larger than the amount of SiO_2 in the water glass, and thus, the SiO_2 becomes easily reactive with the alkali.



On the other hand, however, in the present invention, the amount of CaO in slag is smaller than the amount of the cement, and thus, the reaction of SiO_2 with the alkali is comparatively slow. And accordingly, it is considered that the present liquid is gradually consolidated with a long gellation time, and shows high consolidation strength.

In addition, if the cement is added into said present liquid, the self curability resided in the cement is introduced in the present liquid.

Moreover, in the present invention, small amounts of the precipitation will be rarely appeared according to the blending ratio. To prevent the precipitation, the dispersant is used in the present invention to obtain a uniformly consolidated material.

EXAMPLES

The present invention will now be described in more detail by way of examples, but is not limited by these examples.

1. Material used

(1) Slag

The blast furnace slag (Trade name : BSMENT), which is commercially sold, and the ground slag having the specific surface area shown in Table 1, were used.



Table 1

slag	specific surface area (cm ² /g)
(1)	3 1 0 0 (not grinding)
(2)	5 5 0 0
(3)	8 1 0 0
(4)	1 1 3 0 0

(2) Sodium aluminate

3 kinds of sodium aluminate shown in Table 2 were used in these examples. (In the present invention, the potassium aluminate also shows the same result as the sodium aluminate.)

Table 2

liquid of sodium aluminate	density (20°C)	Al ₂ O ₃ (%)	Na ₂ O (%)	mol ratio
(1)	1.24	4.00	14.00	5.27
(2)	1.30	3.60	22.00	10.05
(3)	1.33	1.59	22.47	23.25

(3) Water glass

The water glasses shown in Table 3 were respectively used.



Table 3

water glass	density (20°C)	Na ₂ O (%)	SiO ₂ (%)	mol ratio
(1)	1.40	9.32	28.75	3.18
(2)	1.62	14.4	34.7	2.49
(3)	1.74	18.7	35.6	1.97
(4)	1.59	20.0	28.1	1.45

(4) Cement

The most popular portland cement with fine grain, having 8500cm²/g of specific surface area, was used in the examples, although various kinds of cements, such as alumina cement, portland cement, slag cement etc., can be used.

(5) Dispersant

Trade name : MAITY 150 was used.

2. Blending and results

(1) Water glass-slag type

The blending, gellation time, funnel viscosity, and unconfined compressive strength of the consolidated grout which is impregnated in water of the water glass-slag type were shown in Table 4.



Table 4

example No	blending									funnel viscosity after 10 min. (sec.)	gelation time (min.)	impregnation in water unconfined compressive strength (kgf/cm ²)	
	water glass				slag				water (g)				
	No. in Table 3 (g)				No. in Table 1 (g)								
	(1)	(2)	(3)	(4)	(1)	(2)	(3)	(4)					
1	1 7 0	—	—	—	2 7 0	—	—	—	5 6 0	gelation	2	5.6	6.9
2	1 7 0	—	—	—	—	—	—	2 7 0	5 6 0	gelation	1.3	6.2	7.4
3	—	1 7 0	—	—	2 7 0	—	—	—	5 6 0	4 5	3 0	2 9.8	3 2.7
4	—	1 7 0	—	—	—	2 7 0	—	—	5 6 0	4 1	2 7	3 1.0	3 3.1
5	—	1 7 0	—	—	—	—	2 7 0	—	5 6 0	3 4	2 5	3 5.1	3 8.0
6	—	1 7 0	—	—	—	—	—	2 7 0	5 6 0	3 0	2 2	3 7.4	4 0.7
7	—	—	1 7 0	—	2 7 0	—	—	—	5 6 0	3 2	6 0	3 3.5	3 6.0
8	—	—	1 7 0	—	—	—	2 7 0	—	5 6 0	2 6	4 8	3 9.7	4 2.0
9	—	—	—	1 7 0	2 7 0	—	—	—	5 6 0	3 0	7 7	3 7.0	3 9.0
10	—	—	—	1 7 0	—	2 7 0	—	—	5 6 0	2 7	7 0	3 8.6	4 1.5
11	—	—	—	1 7 0	—	—	2 7 0	—	5 6 0	2 1	6 6	4 1.2	4 4.8
12	—	—	—	1 7 0	—	—	—	2 7 0	5 6 0	2 0	6 1	4 1.7	4 5.1

(Temp. 20±1°C)

7A

In examples 1 and 2 shown in Table 4, No.3 water glass, having 3.18 of mol ratio, were used, respectively. It can be understood from Table 4 that the strength of the consolidated grout is not increased in spite that the gellation time is short.

In examples 3 to 12 shown in Table 4, the water glass having low mol ratio of the present invention are used, respectively.

It can be understood from Table 4 that when the mol ratio becomes 2.5 or less, the viscosity is suddenly lowered, and the strength of the consolidated grout is high in spite that the gellation time is long.

Moreover, it can be understood from Table 4 that the gellation time of the grout becomes a little shorter, and the strength of the grout becomes extremely higher, when the particle size of the slag becomes smaller, especially, the specific surface area of the slag becomes $8000\text{cm}^2/\text{g}$ or more.

(2) Sodium aluminate-slag type

The blending, gellation time, funnel viscosity, and unconfined compressive strength of the consolidated grout which is impregnated in water of the sodium aluminate-slag type were shown in Table 5.



Table 5

example No.	blending							water (g)	funnel viscosity after 10 min. (sec.)	gelation time (hour)	impregnation in water unconfined compressive strength (kgf/cm ²)	
	sodium aluminate			slag							7 days	30 days
	No. in Table 2 (g)			No. in Table 1 (g)								
	(1)	(2)	(3)	(1)	(2)	(3)	(4)					
13	140	—	—	370	—	—	—	490	100	1.5	10.1	16.5
14	140	—	—	—	—	—	370	490	80	1.2	13.2	19.9
15	—	140	—	370	—	—	—	490	43	7	21.5	24.1
16	—	140	—	—	370	—	—	490	39	6	23.2	26.6
17	—	140	—	—	—	370	—	490	33	4	26.3	29.5
18	—	140	—	—	—	—	370	490	30	3	28.0	31.8
19	—	—	140	370	—	—	—	490	29	9	27.7	32.0
20	—	—	140	—	370	—	—	490	26	8	30.1	34.9
21	—	—	140	—	—	370	—	490	21	7	38.8	43.0
22	—	—	140	—	—	—	370	490	18	6	40.4	45.7

(Temp. 20±1 °C)

In examples 13 and 14, sodium aluminate having 5.87 of mol ratio, and containing small amounts of alkali were used, respectively.

It can be understood from these examples of Table 5 that the strength of the consolidated grout shows 20 Kgf/cm² or less at the most, in spite that the gellation time is comparatively short, showing 1 to 2 hours, and the funnel viscosity is high, showing 1 minute or more.

In examples 15 to 22, sodium aluminate of the present invention were used, respectively.

It can be understood from these examples of Table 5 that when the mol ratio becomes 10 or more, the strength of the consolidated grout is extremely high in spite that the gellation time becomes longer and viscosity is lowered.

Moreover, it can be understood from examples 17, 18, 21, and 22 of Table 5 that the gellation time of the grout becomes a little shorter and the viscosity thereof is lowered, and further, the strength thereof becomes extremely higher, when the particle size of the slag becomes smaller, especially, the specific surface area of the slag becomes 8000cm²/g or more.

(3) Water glass-sodium aluminate-slag type

The blending, gellation time, funnel viscosity, and unconfined compressive strength of the consolidated grout which is impregnated in water of the water glass-sodium aluminate-slag type were shown in Table 6.



Table 6

example No	blending								funnel viscosity after 10 min. (sec.)	gelation time (min.)	impregnation in water unconfined compressive strength (kgf/cm ²)	
	water glass		sodium aluminate		slag		water (g)	molar cocentration rate $\frac{[SiO_2]}{[Na_2O]}$			7 days	30 days
	No. in Table 3 (g)		No. in Table 2 (g)		No. in Table 1 (g)							
	(1)	(2)	(1)	(2)	(1)	(3)						
23	145	—	21	—	285	—	549	2.62	76	17	8.1	10.9
24	136	—	28	—	290	—	546	2.43	40	43	23.8	30.5
25	102	—	56	—	310	—	232	1.75	42	60	28.7	36.0
26	102	—	56	—	—	310	232	1.75	32	50	29.7	40.0
27	—	145	—	21	285	—	549	2.04	38	70	26.9	35.4
28	—	145	—	21	—	285	549	2.04	30	55	28.0	38.8

(Temp. 20±1°C)

9A

This Sheet Has Been Replaced



It can be said from Tables 4 and 5 that the examples 1, 2, 13 and 14, in which water glass having high mol ratio (mol ratio : 3.18), or sodium aluminate having low mol ratio (mol ratio: 5.87) are separately mixed with slag, respectively show unpreferable results. On the other hand, it can be said from Tables 4 and 5 that when the water glass having low mol ratio, or sodium aluminate having high mol ratio are used in the examples, each of them shows preferable results concerning viscosity, gellation time, and strength, respectively.

It can be said from examples 27 and 28 on Table 6 that when both of the water glass having low mol ratio of 2.49 and sodium aluminate having high mol ratio of 10.05 are mixed with slag in combination, the obtained examples 27 and 28 show preferable results, respectively.

But, concerning examples 23 to 26, which are respectively prepared by mixing the both of water glass having high mol ratio (mol ratio: 3.18, No. 3 water glass) and sodium aluminate having low mol ratio (mol ratio: 5.87) with slag, examples 24 to 26 show preferable results except exampl 23. Thus, it is understood from Table 6 that when water glass having high mol ratio and sodium aluminate having low mol ratio are mixed with slag in combination, the obtained samples show preferable results in the case that the rate of the molar concentration of SiO_2 in water glass to the molar concentration of total Na_2O in water glass and sodium aluminate is 2.5 or less (examples 24, 25, 26), and show unpreferable results in the case that said rate is



more than 2.5 (example 23).

As a conclusion, it is said from Table 6 that when water glass having high mol ratio and sodium aluminate having low mol ratio, both of which are commercially sold, are mixed with slag to obtain the present liquid, the obtained samples show preferable results, if they are satisfied with the above conditions.

In Table 6, the non-grinding slag having specific surface area $3100\text{cm}^2/\text{g}$ of and the finely ground slag having specific surface area of $8100\text{cm}^2/\text{g}$ were used as a slag. It is said from Table 6 that examples 26 and 28, both, using finely ground slag show lower viscosity and higher strength though the gellation time is a little short, compared with examples 25, and 27.

(4) Use of cement and dispersant

Example 17 of Table 5 and example 26 of Table 6 were used as the examples. In these examples, a part of slag was substituted by cement, and moreover, the dispersant was added thereinto to obtain new examples. The test was carried out by using these new examples. The results were shown on Table 7.



Table 7

example No	blending						funnel viscosity after 10 min. (sec.)	gelation time (hour)	impregnation in water unconfined compressive strength (kgf/cm ²)	
	water glass	sodium aluminate	slag	cement (g)	dispersant (g)	water (g)				
	No in Table 3 (g)	No in Table 2 (g)	No in Table 1 (g)						7 days	30 days
29	—	140	300	70	—	490	38	4.5	24.6	27.5
30	—	(2) 140	(3) 300	70	10	480	41	4.2	25.2	29.0
31	102	56	250	60	—	532	39	1.3	27.5	36.0
32	(1) 102	(1) 56	(3) 250	60	10	522	44	1.1	28.3	39.1

(Temp. 20±1 °C)

11A

It is shown on table 7 that when a part of slag is substituted by cement as mentioned above, the viscosity becomes a little higher, gellation time becomes a little longer, and the strength is a little lowered. According, it is understood from the facts that when the grout having a long gellation time wants to be obtained, this sample is effective. The dispersant acts to prevent the precipitation of ingredients when the grout has a long gellation time. Thus, the grout is usually kept in homogeneous, suspension, and as a result, the strength of the consolidated grout is increased.

The effects of the present grouting liquid for injection into the a ground are as follows.

1. A mixture of slag and water glass having mol ratio of 2.5 or less, and a mixture of slag and sodium aluminate having mol ratio of 10 or more, respectively, can be gelled with a long gellation time, keeping low viscosity, and thus, they are very excellent in penetration property as suspension-type grouts. Also, they show very high strength of consolidation in spite that they have such a long gellation time, and thus, they are expected as a suspension type grout excellent in endurance.

2. In a mixture of slag and sodium aluminate, the water glass is not necessary to show mol ratio of 2.5 or less, and sodium aluminate is not necessary to show mol ratio of 10 or more. If the rate of molar concentration of SiO_2 in water glass and molar concentration of Na_2O in the mixture of water glass and



sodium aluminate is 2.5 or less, the mixture shows excellent effects same as afore-mentioned No.1. Accordingly, in this mixture, JIS No.3 water glass and sodium aluminate having low mol ratio, which are commercially sold, can be used.

3. In the mixtures of said No.1 and 2, the gellation time can be prolonged by substituting a part of slag with cement.

4. In the mixtures of said No.1, 2 and 3, the precipitation does not appear by adding dispersant thereinto, even though they have a long gellation time. Thus, the homogeneous and strong consolidation grout is obtained from the mixture.

5. The slag and cement to be used are preferably fine grain. The obtained mixtures show low viscosity and high strength of consolidation. Especially, this effect is excellent when they have the specific surface area of $8000\text{cm}^2/\text{g}$ or more.





What is claimed is:

1. A suspension-type grouting liquid for injection into a ground which comprises water glass having mol ratio of 2.5 or less and slag, in which the mol ratio of water glass shows molar concentration of SiO_2 /molar concentration of Na_2O .
2. The grouting liquid as claimed in claim 1, wherein cement and/or dispersant are further added into said grouting liquid.
3. The grouting liquid as claimed in claim 1, wherein said slag is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.
4. The grouting liquid as claimed in claim 2, wherein said cement is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.
5. A suspension-type liquid for injection into a ground which comprises sodium aluminate having mol ratio of 10 or more and slag, in which the mol ratio of sodium aluminate shows molar concentration of Na_2O /molar concentration of Al_2O_3 .
6. The grouting liquid as claimed in claim 5, wherein cement and/or dispersant are further added into said grouting liquid.
7. The grouting liquid as claimed in claim 5, wherein said slag is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.
8. The grouting liquid as claimed in claim 6, wherein said cement is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.
9. A suspension-type liquid for injection into a ground which





* C L H S *

.15

comprises water glass, sodium aluminate and slag, in which the value of molar concentration of SiO_2 in the water glass/total molar concentration of Na_2O in the water glass and sodium aluminate is 2.5 or less.

10. The grouting liquid as claimed in claim 9, wherein cement and/or dispersant are further added into said grouting liquid.
11. The grouting liquid as claimed in claim 9, wherein said slag is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.
12. The grouting liquid as claimed in claim 10, wherein said cement is fine grain having the specific surface area of $8000\text{cm}^2/\text{g}$ or more.

This Sheet Has Been Replaced

