

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 September 2002 (12.09.2002)

PCT

(10) International Publication Number
WO 02/070271 A2

(51) International Patent Classification⁷: **B41M 3/00**, 7/00

(21) International Application Number: PCT/US02/08164

(22) International Filing Date: 21 February 2002 (21.02.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/272,440 1 March 2001 (01.03.2001) US

(71) Applicant (for all designated States except US): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **BLANCHET-FINCHER, Graciela, Beatriz** [US/US]; 8 Pheasant's Ridge S., Greenville, DE 19807 (US).


(74) Agent: **WANG, Chen**; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: THERMAL IMAGING PROCESSES AND PRODUCTS OF ELECTROACTIVE ORGANIC MATERIAL



(57) Abstract: Processes for effecting thermal transfer of electroactive organic material are disclosed wherein unwanted portions of a layer of electro organic material supported by a donor element are removed or transferred from the layer by thermal transfer, particularly laser-induced thermal transfer, leaving a desired pattern of the electroactive organic material on the donor element. The electroactive organic material may be an organic material exhibiting electroluminescence, charge transport, charge injection, electrical conductivity, semiconductivity and/or exciton blocking. The layer of electroactive organic material may comprise more than one layer of different types of electroactive organic material. The exposure pattern is a negative image of the desired pattern. The electroactive organic material of the desired pattern is not, therefore, exposed to the heat which can cause decomposition. The desired pattern of electroactive organic material may then be gently transferred from the donor element to a desired substrate by lamination, for example, without damaging the electroactive organic material. The substrate may be used to form organic electronic devices, such as light emitting displays, photodetectors and photovoltaic cells. Donor elements for use in the processes are also disclosed.



Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.