

**POWDERS FOR RARE EARTH MAGNETS, RARE EARTH MAGNETS AND
METHODS FOR MANUFACTURING THE SAME**

TECHNICAL FIELD

5

[0001] The present invention relates to powders for rare earth-iron-boron-metal (R-Fe-B-M) permanent magnets and to methods of producing the powders and the magnets.

10 BACKGROUND

[0002] Permanent rare earth-iron-boron-metal (R-Fe-B-M) magnets are generally produced by powder metallurgical methods. Firstly, an ingot is produced by a casting method. The ingot
15 may be produced by casting the molten alloy into a mold, where it cools comparatively slowly. Alternatively, the ingot may be produced by a rapid solidification method such as strip casting. The solidified ingot is typically given an annealing heat treatment to homogenise the composition.

20

[0003] The ingot may then be given a hydrogenation treatment which is typically used to coarsely pulverise the solidified ingot due to the effects of hydrogen embrittlement of phases within the alloy. The ingot, or resulting coarsely
25 pulverised material, is then further pulverised to produce a powder.

[0004] A magnet is produced from the powder by powder metallurgy. The powder is compacted in a magnetic field to
30 form a textured green body which is then given a sintering heat treatment in order to produce a permanent magnet.

[0005] It is known that the magnetic properties, in particular the coercive force and the squareness of the J(H) curve, as well as the corrosion resistance and the temperature stability of the sintered magnet depend on the grain size as well as on the composition of the magnet. The composition and grain size of the sintered magnet are, in turn, dependent on the particle size and composition of the powder. R-Fe-B-M powders are, however, rather difficult to manufacture in large quantities and, consequently, the powders and the magnets produced using them are relatively expensive.

[0006] It is, therefore, desired to produce high-quality rare earth iron boron (R-Fe-B-M) sintered magnets more cost effectively so as to promote all kinds of applications in which they can be used. It is also desired to improve the corrosion stability and the temperature stability of such magnets.

SUMMARY

[0007] The invention seeks to provide (R-Fe-B-M) powder and (R-Fe-B-M) sintered magnets which have high quality magnetic properties, an improved temperature and corrosion stability and which can be more cost-effectively produced.

[0008] The invention also seeks to provide cost-effective methods of manufacturing (R-Fe-B-M) powder and permanent (R-Fe-B-M) sintered magnets.

[0009] The invention provides a powder for use in a R-Fe-M-B type permanent magnet and a R-Fe-M-B type permanent magnet consisting essentially by weight, of $28.00 \leq R \leq 32.00\%$, where

R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5, $0.50 \leq B \leq 2.00\%$, $0.50 \leq Co \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of the elements Ga, Cu and Al, $0.25 \text{ wt}\% < O \leq 0.5\text{wt}\%$, 0.15% or less of C, balance Fe.

5

[0010] The powder comprises an oxygen content of $0.25 \text{ wt}\% < O \leq 0.5\text{wt}\%$. Although, in principle, an increased oxygen content is undesirable as the fraction of the hard magnetic phase and the remnance of the magnet is reduced, an oxygen content in this range has been found to provide an improved powder for use in R-Fe-M-B type permanent magnets and an improvement in the properties of the magnets.

[0011] Magnets produced from a powder having a very low oxygen content, in this context a very low oxygen content is used to describe an oxygen content of less than 0.25 wt%, easily get a coarse grain structure which has two disadvantages. During the sintering process, the particle size of the powder having an oxygen content of less 0.25 wt% is observed to increase, generally speaking, by a factor of around three. Therefore, a powder with an average particle size of 4 μm produces a magnet with an average grain size of 12 μm . However, as the grain size of the magnet increases, the coercive field strength is reduced. Therefore, the properties of the magnet are limited by the particle size of the powder. This problem is avoided by increasing the oxygen content of the powder to provide a powder with an oxygen content in the range $0.25 \text{ wt}\% < O \leq 0.5\text{wt}\%$.

[0012] A further problem which is observed in magnets with an oxygen content of less than 0.25 wt% is the appearance of abnormal grain growth. Abnormal grain growth is used to

describe the phenomenon in where a few grains grow faster and reach a size of several hundred microns whereas the rest of the magnet has a normal grain size of, for example around 12 μm . Abnormal grain growth leads to a deterioration of the squareness of the B-H loop.

[0013] It has been found that, by providing the powder with an oxygen content in the range according to the invention, the sintering activity is reduced. Consequently, the average grain size in magnets sintered from powder according to the invention is approximately only double rather than treble the average particle size of the powder.

[0014] For example, for a powder according to the invention which has an oxygen content $0.25 \text{ wt}\% < O \leq 0.5 \text{ wt}\%$ and , a magnet produced from this powder with an average particle size of 4 μm has an average grain size of around 8 μm . This is in contrast to powders with an oxygen content outside of the range according to the invention which produce a magnet with an average grain size of 12 μm from a powder with an average particle size of 4 μm . Therefore, the coercive field strength of the magnet fabricated from powder of a particular particle size is increased as the grain size of the sintered magnet is reduced. For the same reason, abnormal grain growth is also reduced.

[0015] If the oxygen content is greater than 0.5 wt%, the remnance is more significantly reduced and the advantage provided by the increase in the coercive field strength is lost. In a further embodiment, the oxygen content is $0.3 \text{ wt}\% \leq O \leq 0.45 \text{ wt}\%$.

[0016] Powder for producing R-Fe-B-M magnets having a composition according to the invention also simplifies the manufacturing process. Since the grain size of the sintered magnet is only approximately double the particle size of the powder, the pulverisation process can be simplified as a magnet with a given grain size can be fabricated from powder with a larger particle size. Consequently, the pulverisation process may be simplified and the process time to carry out the pulverisation is reduced. The powder and magnets produced from the powder can, therefore, be manufactured more cost-effectively.

[0017] The use of gallium and copper additions in the powder for use in fabricating sintered R-Fe-B-M type magnets also provides advantages. Gallium and copper form molten phases with Nd and Co/Fe at the sintering temperature although they are not present in significant amounts in the hard magnetic phase.

[0018] Therefore, the advantage of the molten phase sintering, which produces a fast densification at relatively low sintering temperatures, is retained. Since only minor amounts of Ga and Cu can be dissolved in the hardmagnetic $R_2Fe_{14}B$ grains, rapid grain growth is slowed down substantially. Therefore, the grain growth by sintering is also reduced and, as previously described, abnormal grain growth is avoided. Therefore, the additions of gallium and/or copper also influence the relationship between powder particle size and the grain size of the sintered magnet and further reduce the increase in grain size of a magnet sintered from powder of a particular particle size.

[0019] In a further embodiment of the powder and permanent magnet, R is one or more of the elements Nd, Pr, Dy and Tb, $0.50\% < \text{Co} < 1.5\%$, $0.05\% < \text{Ga} < 0.25\%$ and $0.05\% < \text{Cu} < 0.20\%$.

5 [0020] The powder can have an average particle size according to FSSS (Fischer Sub-Sieve Size) in the range of around $4\text{ }\mu\text{m}$ to around $2.1\text{ }\mu\text{m}$ and contains no particles greater than around $20\text{ }\mu\text{m}$. In an alternative embodiment, the powder has an average particle size according to FSSS in the range of
10 around $2.5\text{ }\mu\text{m}$ to around $3\text{ }\mu\text{m}$ and contains no particles greater than around $15\text{ }\mu\text{m}$. This powder can be used to fabricate magnets with good magnetic properties, since, as previously described, the composition of the powder with a composition according to the invention, leads to a reduced grain size of
15 the magnet produced using the powder.

[0021] The permanent sintered magnet may have an average grain size of around $7.6\text{ }\mu\text{m}$ to around $4.2\text{ }\mu\text{m}$. This provides the magnet with magnetic properties, in particular a J(H)
20 curve and coercive force which are suitable for a wide range of applications and provides a magnet with good corrosion resistance.

[0022] In an embodiment, a magnet has an average grain size
25 of around $7.6\text{ }\mu\text{m}$ and in a HAST corrosion test has a mass loss of less than 1 mg/cm^2 after 10 days.

[0023] In an embodiment, a magnet has an average grain size of around $4.2\text{ }\mu\text{m}$ and in a HAST corrosion test has a mass loss
30 of less than 0.1 mg/cm^2 after 10 days.

[0024] In a further embodiment, a magnet has an average grain size of around $4.2\text{ }\mu\text{m}$ and in a HAST corrosion test has a mass loss of less than 1 mg/cm^2 after 100 days.

5 [0025] The invention also relates to methods of producing powder for use in R-Fe-B-M and to magnets fabricated from R-Fe-B-M powders.

[0026] In a method an alloy comprising by weight, of 28.00
10 $\leq R \leq 32.00\%$, where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5 , $0.50 \leq B \leq 2.00\%$, $0.50 \leq \text{Co} \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of the elements Ga, Cu and Al, $0.25\text{ wt}\% < \text{O} \leq 0.5\%$, 0.15% or less of C, balance Fe is melted. The alloy is then cast to form at
15 least one ingot, wherein the solidified ingot comprises finely dispersed α -Fe, and $\text{R}_2\text{Fe}_{14}\text{B}$ and R-rich constituents. The at least one ingot is annealed at a temperature in the range of approximately 800°C to approximately 1200°C under an inert atmosphere of Ar or under vacuum to form an ingot which is
20 free of the α -Fe phase. The at least one ingot is treated in hydrogen gas in order to hydrogenate the R-rich constituents. The at least one ingot is then coarsely pulverised and a fine pulverisation of the coarsely pulverised powder is performed in an atmosphere comprising oxygen, oxidizing the powder. The
25 finely pulverised powder comprises an oxygen content of $0.25\text{ wt}\% < \text{O} \leq 0.5\text{ wt}\%$.

[0027] It has been found that the ingots may be more easily pulverised and that powder having a smaller particle size
30 distribution can be produced using the method according to the invention. The casting conditions and homogenisation conditions of the invention produce an ingot or ingots which

are essentially free of the α -Fe phase. This has been found to lead to a more reliable pulverisation of the ingots.

[0028] It has also been found that the introduction of oxygen during the fine pulverisation process has the advantage that an oxide coating is formed on the outside of the pulverised powder particles. This improves distribution of the oxygen and the stability of the powder.

[0029] The alloy casting conditions and hydrogenation treatment of the invention also simplify the pulverisation process as the rare earth rich phases, formed during the casting process, are more easily and reliably hydrogenated. The hydrogenation conditions lead to a more uniform hydrogenation of the rare earth rich phases and to an improved cracking of the ingots. It is also possible to eliminate a coarse crushing step if sufficient cracking is achieved by the hydrogenation treatment.

[0030] In a further embodiment an alloy is melted in which R is one or more of the elements Nd, Pr, Dy and Tb, $0.50\% < \text{Co} < 1.5\%$, $0.05\% < \text{Ga} < 0.25\%$ and $0.05\% < \text{Cu} < 0.20\%$.

[0031] In an embodiment, the said ingot has smallest dimensions in the range of 5 mm to 30 mm.

[0032] In an embodiment, the powder has an average particle size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no particles greater than around 20 μm .

[0033] In an embodiment, the at least one ingot has dimensions in the range of 15 mm to 25 mm and said powder

after said fine pulverisation has an average particle size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no particles greater than around 20 μm .

5 [0034] In an embodiment, the hydrogenating is performed at a temperature between around 450°C and 600°C.

[0035] In an embodiment, the hydrogenating is performed at a temperature between around 500°C and 550°C.

10

[0036] In an embodiment, the hydrogenating is performed under 0.5 to 1.5 bars of hydrogen gas for between around 1 hour to around 10 hours.

15 [0037] In an embodiment, the hydrogenating is performed in 1 bar of hydrogen for around 5 hours.

[0038] In an embodiment, after said hydrogenating, said ingot is cooled to around 100°C under Ar gas.

20

[0039] It was found that the decomposition of the ingots is reduced by selecting a hydrogenation temperatures of greater than 450° C. By avoiding decomposition of the ingots, the ingots can be more easily removed from the furnace and the
25 composition of the final powder is more reliable as the ingots are less likely to absorb impurities such as O, C and N.

[0040] By selecting a hydrogenation temperature of less than around 600°C, the absorption of hydrogen is reduced to a
30 level at which decomposition of the hardmagnetic $\text{Nd}_2\text{Fe}_{14}\text{B}$ compound into NdH_2 , $\alpha\text{-Fe}$ and Fe_xB is avoided.

[0041] In a further embodiment, the fine pulverisation is performed in two steps. This embodiment has the advantage that a reduced average particle size, as well as a smaller particle size distribution can be provided by a simple re-pulverisation
5 of the finely pulverised powder.

[0042] A first fine pulverisation of the coarsely-pulverised powder is performed in an inert atmosphere. A second fine pulverisation of said finely pulverised powder is
10 then performed in an atmosphere comprising oxygen, oxidizing said finely pulverised powder. The finely pulverised powder comprises an oxygen content $0.25 \text{ wt}\% < O \leq 0.5 \text{ wt}\%$ after the second fine pulverisation.

15 [0043] In an embodiment, the first fine pulverisation and said second fine pulverisation is performed using a jet mill.

[0044] In an embodiment, after said first fine pulverisation, the powder has an average particle size
20 (FSSS) of around $4 \mu\text{m}$ and a particle size distribution in which 30% of particles have a diameter of more than around $10 \mu\text{m}$ and around 1% of the particles have a diameter of greater than between around $20 \mu\text{m}$ and around $25 \mu\text{m}$.

25 [0045] In an embodiment, after said second fine pulverisation, the powder has an average particle size (FSSS) in the range of around $4 \mu\text{m}$ to around $2.1 \mu\text{m}$ and contains no particles greater than around $20 \mu\text{m}$.

30 [0046] In an embodiment, the powder has an average particle size (FSSS) of around $4 \mu\text{m}$ and a particle size distribution in which 30% of particles have a particle diameter of more than

around 10 μm , and around 1% have a diameter of greater of between around 20 μm and around 25 μm after the first fine pulverisation. The powder has an particle grain size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no
5 particles greater than around 10 μm after the second fine pulverisation.

[0047] The invention also provides a method by which R-Fe-B-M powder is produced from a pre-cast ingot.

10

[0048] An alloy is provided which comprises by weight, of $28.00 \leq R \leq 32.00\%$, where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5, $0.50 \leq B \leq 2.00\%$, $0.50 \leq \text{Co} \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of
15 the elements Ga, Cu and Al, $0.25 \text{ wt}\% < \text{O} \leq 0.5\%$, 0.15% or less of C, balance Fe. The alloy has the form of an ingot.

[0049] Similarly, to the previous embodiment, the pre-cast ingot is annealed at a temperature in the range of
20 approximately 800°C to approximately 1200° C under an inert atmosphere of Ar or under vacuum to form an ingot which is free of the $\alpha\text{-Fe}$ phase. The ingot is then treated in hydrogen gas in order to hydrogenate the R-rich constituents and then coarsely pulverised. A fine pulverisation of the coarsely
25 pulverised powder is performed in an atmosphere comprising oxygen, oxidizing said powder. The finely pulverised powder comprises an oxygen content of $0.25 \text{ wt}\% < \text{O} \leq 0.5 \text{ wt}\%$.

[0050] In an embodiment, an alloy is provided in which R is
30 one or more of the elements Nd, Pr, Dy and Tb, $0.50\% < \text{Co} < 1.5\%$, $0.05\% < \text{Ga} < 0.25\%$ and $0.05\% < \text{Cu} < 0.20\%$.

[0051] In an embodiment, the powder has an average particle size (FSSS) in the range of around 2.5 μm to around 3 μm .

[0052] In an embodiment, the ingot has dimensions in the
5 range of 20 mm to 30 mm.

[0053] In an embodiment, the hydrogenating is performed at a temperature between around 450°C and 600°C.

10 [0054] In an embodiment, the hydrogenating is performed at a temperature of between around 500°C and 550°C.

[0055] In an embodiment, the hydrogenating is performed under 0.5 to 1.5 bars of hydrogen gas for between around 1
15 hour to around 10 hours.

[0056] In an embodiment, the hydrogenating is performed under 1 bar of hydrogen for around 5 hours.

20 [0057] In an embodiment, after the hydrogenation, the ingot is cooled to around 100°C under Ar gas.

[0058] The invention also relates to a method of producing a permanent R-Fe-B-M magnet. Powder is provided which consists
25 essentially by weight, of $28.00 \leq R \leq 32.00\%$, where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5, $0.50 \leq B \leq 2.00\%$, $0.50 \leq \text{Co} \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of the elements Ga, Cu and Al, 0.25 wt% < O $\leq 0.5\%$, 0.15% or less of C, balance Fe. The powder
30 is compacted in a magnetic field to form a textured compact. The compact is then sintered to produce a magnet.

[0059] In an embodiment, the powder has an average particle size according to FSSS and said magnet has an average grain size. The average grain size of said magnet is no more than 2.5 times the average particle size of said powder.

5

[0060] In an alternative embodiment, the average grain size of said magnet is no more than twice the average particle size of said powder.

10 [0061] In an embodiment, a sintered magnet having an average grain size in a range of about 7.6 μm to about 4.2 μm is produced in the step of sintering.

[0062] In a further embodiment, the powder is fabricated by
15 a two step fine pulverisation process. The powder after said second pulverisation has an average particle size according to FSSS of around 4.1 μm to around 2.6 μm and the magnet after sintering has an average grain size of around 7.6 μm to around 4.2 μm .

20

BRIEF DESCRIPTION OF THE DRAWINGS

[0063] The invention is now explained in detail in the following with reference to the drawings.

25

[0064] Fig. 1: Graph showing the percentage of H_2 -absorbed by ingots with a size of around 20 mm to 30 mm at 400 °C and a H_2 pressure of about 1 bar.

30 [0065] Fig. 2: Graph showing the percentage of H_2 -absorbed by ingots with a size of around 1 mm to 2 mm at 500 °C and a H_2 pressure of about 1 bar.

[0066] Fig. 3: Graph showing the percentage of H₂-absorbed by ingots with a size of around 20 mm to 30 mm at 550 °C and a H₂ pressure of about 1 bar.

5

[0067] Fig. 4: Graph showing the percentage of H₂-absorbed by ingots with a size of around 20 mm to 30 mm at 700 °C and a H₂ pressure of about 1 bar.

10 [0068] Fig. 5: Graph showing the effect of sifter rotation speed on average particle size according to FSSS of re-milled Nd-Fe-M-B alloy powder, where M is Al, Ga, Co, Cu.

[0069] Fig. 6: Graph showing the effect of sifter
15 rotation speed N on the particle size distribution of re-milled Nd-Fe-M-B alloy powder, where M is Al, Ga, Co, Cu.

[0070] Fig. 7: Graph showing the relationship between
20 grain size of the sintered magnet and particle size of the powder for different oxygen contents.

[0071] Fig. 8: Graph showing the temperature dependence of the coercivity field strength of Nd-Fe-M-B magnets, where M is Al, Ga, Co, Cu, fabricated from sintered powder with a
25 particle size of 4.1 µm and 2.6 µm.

[0072] Fig. 9: Demagnetisation curves J(H) of Nd-Fe-B magnets, fabricated from sintered remilled Nd-Fe-M-B powder, where M is Al, Ga, Co, Cu, with an average particle size of
30 2.6 µm.

[0073] Fig. 10: Graph showing the weight increase in a HAST test of Nd-Fe-M-B-magnets, where M is Al, Ga, Co, Cu, with an average grain size of 7.6 μm and 4.2 μm which were fabricated from sintered powder with an average particle size of 4.1 μm and 2.6 μm respectively.

[0074] Fig. 11: Graph showing the weight increase in a PCT test of Nd-Fe-M-B-magnets, where M is Al, Ga, Co, Cu, with an average grain size of 7.6 μm and 4.2 μm which were fabricated from sintered powder with an average particle size of 4.1 μm and 2.6 μm respectively.

[0075] Table 1: Hydrogenating conditions and results of hydrogenated alloys, where t_{knee} is the time after which saturation was reached, Δm is the weight gain, ΔV is the specific H_2 uptake, and $\Delta V/\Delta t_{\text{max}}$ is the maximum absorptions rate, each of which is calculated from the weight gain and/or the gas quantity added.

[0076] Table 2: Results showing the powdered decomposition product of hydrogenated and unhydrogenated ingots after storage in air under various conditions.

[0077] Table 3: Contamination uptake of hydrogenated and unhydrogenated alloys. The hydrogenated alloys were homogenised before the hydrogenation at 1060°C to 1120°C for 12h to 60 h.

[0078] Table 4: Surface damage of nickel -coated sintered Nd-Fe-B-M magnets with various grain sizes.

DETAILED DESCRIPTIONComposition

5 [0079] A powder for use in a R-Fe-M-B type permanent magnet was fabricated using powder metallurgical techniques. An alloy having a composition of 30% Nd, 0,1% Pr, 0,2% Dy, 0,5% Tb, 0,93% B, 0,25% Ga, 0,7% Co, 0,08% Cu, 0,10% Al was melted and cast to produce plates having a thickness of 20 mm which
10 comprise a finely dispersed α -Fe phase.

Casting and Homogenising

[0080] The cast plates were given a solid solution heat
15 treatment at around 1120°C for 12 hours. The ingots were then cooled to a temperature of between around 500°C to around 550°C under an atmosphere of argon in the furnace. After the homogenisation treatment, the ingots were essentially free from the α -Fe phase
20

Hydrogenation

[0081] A hydrogenation treatment was then performed on the homogenised ingots in order to enable the rare-earth rich
25 phases remaining in the alloy to form Nd-hydrides and hence to be more easily pulverised. The hydrogenation treatment was carried out at a temperature in the range 500 to 550°C.

[0082] The hydrogenation heat treatment was carried out by
30 replacing the argon by hydrogen and then maintaining the ingots under one bar of hydrogen at the desired temperature for around five hours.

[0083] After the hydrogenation heat treatment, the furnace was refilled with argon. The ingots were then cooled to around 100°C in argon and then transferred in air into a container
5 which was flushed with argon.

[0084] Results of experiments to determine the absorption rate are given in Table 1. The absorption rate was calculated from the weight gain and gas usage. The gas usage was 10 to 15
10 l/kg of hydrogen with a maximum absorption rate of 10 to 20 l/kg.

[0085] At hydrogenation temperatures of less than 500° C, the surface of the ingots was observed to decompose into a
15 powder. The results of these experiments are given in Table 2. The formation of a powdered decomposition product is not desired as, firstly, the ingots cannot be easily removed from the furnace. Secondly, the composition of the final powder is adversely affected as the decomposition product easily picks
20 up impurities such as O, C and N.

[0086] For hydrogenation temperatures of greater than around 550° C, an unexpectedly large amount of hydrogen was observed to be absorbed. It is thought that this is due to the
25 decomposition of the hardmagnetic $\text{Nd}_2\text{Fe}_{14}\text{B}$ compound into NdH_2 , $\alpha\text{-Fe}$ and Fe_xB which is also undesired.

[0087] The results of further experiments are given in Figures 1 to 4 in which the effect of the hydrogenation
30 temperature and size of the ingots on the maximum absorption rate was investigated. These results show that ingots with a

size of 20 to 30 mm can be fully hydrogenated in the desired temperature range.

[0088] After the hydrogenation heat treatment was been
5 carried out, the ingots were then further processed to produce a powder.

Stability of Ingots

10 [0089] The stability of hydrogenated alloy ingots was also investigated. The ingots were stored for 44 to 220 days in air and the percentage of the ingot which had decomposed was determined. The decomposition product has the form of a powder. Therefore, the percentage was determined by passing the sample
15 through a 500 μm sieve and weighing the portion of the sample which had a grain size of less than 500 μm .

[0090] The results of these experiments are given in Table 2 and results in which the values have been normalised for an
20 ingot size of 25mm and a storage time of 100 days are given in table 3. Table 3 also gives the results of experiments to determine the uptake of O, C and N contamination during storage.

25 [0091] These results show that the ingots hydrogenated at 500 to 550 °C can be reloaded from the furnace even at 100 °C without significant increase of the oxygen pickup. Therefore, the handling of the hydrogenated ingots is much easier and consequently cheaper compared to the standard process, as
30 disclosed in EP 0992309 B1.

Pulverisation

[0092] The ingots were then crushed to produce a coarse powder and then finely pulverised by milling the coarsely
5 pulverised powder in a jet mill to produce a powder with an average particle size (FSSS) of around 3 μm .

[0093] It is known that the magnetic properties of the magnets produced using the powder are dependent on the grain
10 size of the sintered magnet and on the particle size of the powder. In a further study the effects of performing a second fine pulverisation of the already finely pulverised powder was performed. The finely pulverised powder was milled for a second time in a jet mill and the effect of the second
15 treatment on the average particle size and particle size distribution was investigated.

[0094] A rare earth iron boron alloy powder with an average particle size of 4 μm was pulverised for a second time in a
20 jet mill with increased sifter rotation speed. As can be seen in figure 5, the average particle size decreases with increasing sifter speed.

[0095] The effect of sifter speed during the second
25 pulverisation on the particle size distribution was also investigated. As can be seen from the results shown in Figure 6, the width of the particle size distribution curve, which was measured by Fraunhofer diffraction, is reduced. It can be seen that the remilled powders contained essentially no
30 particles with a size greater than 10 μm .

Magnets

- [0096] Permanent magnets were fabricated from these powders. The powders were mixed with a lubricant, aligned in a magnetic field and isostatically pressed to form rods of diameter 40mm and length 195 mm. The green bodies were then sintered at 1060 °C or 1070 °C for 3 hours in vacuum and 1 hour in Ar. The blocks were then given a further annealing treatment at 480°C.
- 10 [0097] The relationship between the average grain size of the magnets in comparison with the average particle size of the powder from which it was fabricated was investigated, see Figure 7. A magnet fabricated from powder with an average FSSS particle size of 4.2 μm has an average grain size of 7.6 μm and a magnet fabricated from powder with an average FSSS particle size of 2.6 μm has an average grain size of 4.1 μm . The grain size of the magnets is, therefore, less than double the particle size of the alloy powder from which it was made.
- 20 [0098] Also, Figure 7 shows the relationship between the grain size of the sintered magnet and particle size (according to FSSS) of the powder for powders having different oxygen contents. A grain growth factor of 3.2 was observed for magnets produced from powders with an oxygen content of 0.22 wt%. A grain growth factor of 2.4 was observed for magnets produced from powders with an oxygen content of 0.29 wt%. A grain growth factor of 2.0 was observed for magnets produced from powders with an oxygen content of 0.43 wt%. A grain growth factor of 1.9 was observed for magnets produced from powders with an oxygen content of 0.62 wt%.
- 30

[0099] A reduced increase of the grain size is observed only for magnets with an oxygen content larger than 0.25 wt%. For magnets with an oxygen content of less than 0.25 wt%, there is a large tendency to form a very coarse and undesired
5 microstructure.

[00100] The effect of the powder particle size on the coercive force of sintered magnets fabricated using the powder can be seen in figure 8. The coercive field strength increases
10 from around 13kOe for alloy powder with a particle size of 4 μm to around 16.5 kOe for a magnet fabricated from an alloy powder with an average particle size of 2.1 μm . The J(H) curves for these magnets are shown in figure 9. Because of their higher coercivity, fine grained magnets can be applied
15 at higher temperatures.

Corrosion Resistance

[00101] The corrosion resistance of magnets fabricated from
20 powders of differing average particle size was also investigated. From the results of the highly accelerated stress test (HAST 130° C, 95% relative humidity, 2.6 bar pressure) and the pressure cooker test (PCT: 130° C, 100% humidity, 2.7 bar pressure) are shown in figures 10 and 11.
25 The magnets fabricated from alloy powders having a smaller average grain size have an improved corrosion resistance.

[00102] Table 4 shows the results from measurements of the surface damage to Ni coated magnets with a different average
30 grain size. These results confirm that magnets with a smaller grain size show a reduced surface deterioration during coating.

What is claimed:

1. A powder for use in a R-Fe-M-B type permanent magnet consisting essentially by weight, of $28.00 \leq R \leq 32.00\%$,
5 where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5 , $0.50 \leq B \leq 2.00\%$, $0.50 \leq Co \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of the elements Ga, Cu and Al, $0.25\% < O \leq 0.5\%$, 0.15% or less of C, 0.15% or less of N balance Fe wherein said powder has
10 an average particle size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no particles greater than around 20 μm .
2. A powder for use in a R-Fe-M-B type permanent magnet,
15 according to claim 1, wherein
R is one or more of the elements Nd, Pr, Dy and Tb, $0.50\% < Co < 1.5\%$, $0.05\% < Ga < 0.25\%$ and $0.05\% < Cu < 0.20\%$.
3. A powder for use in a R-Fe-M-B type permanent magnet,
20 according to claim 1, wherein
said powder has an average particle size (FSSS) in the range of around 2.5 μm to around 3 μm and no particles greater than around 15 μm .
- 25 4. A R-Fe-M-B type permanent magnet consisting essentially by weight, of $28.00 \leq R \leq 32.00\%$, where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5 , $0.50 \leq B \leq 2.00\%$, $0.50 \leq Co \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or more of the elements Ga, Cu and
30 Al, $0.25\text{ wt}\% < O \leq 0.5\%$, 0.15% or less of C, 0.15% or less of N, balance Fe, wherein said magnet has an average grain size of around 7.6 μm to around 4.2 μm .

5. A R-Fe-M-B type permanent magnet according to claim 4,
wherein
R is one or more of the elements Nd, Pr, Dy and Tb, $0.50\% <$
5 $\text{Co} < 1.5\%$, $0.05\% < \text{Ga} < 0.25\%$ and $0.05\% < \text{Cu} < 0.20\%$.
6. A R-Fe-M-B type permanent magnet according to claim 4,
wherein
said magnet has an average grain size of around $7.6\text{ }\mu\text{m}$ and
10 in a HAST corrosion test has a weight loss of less than 1 mg/cm^2 after 10 days.
7. A R-Fe-M-B type permanent magnet according to claim 4,
wherein
15 said magnet has an average grain size of around $4.2\text{ }\mu\text{m}$ and
in a HAST corrosion test has a weight loss of less than 0.1 mg/cm^2 after 10 days.
8. A R-Fe-M-B type permanent magnet according to claim 4,
20 wherein
said magnet has an average grain size of around $4.2\text{ }\mu\text{m}$ and
in a HAST corrosion test has a weight loss of less than 1 mg/cm^2 after 100 days.
- 25 9. A method to produce powders for use in R-Fe-B-M type
permanent magnets comprising:
- melting an alloy consisting essentially by weight, of
 $28.00 \leq \text{R} \leq 32.00\%$, where R is at least one rare earth
element including Y and the sum of $\text{Dy} + \text{Tb} > 0.5$, 0.50
30 $\leq \text{B} \leq 2.00\%$, $0.50 \leq \text{Co} \leq 3.50\%$, $0.050 \leq \text{M} \leq 0.5\%$, where
M is one or more of the elements Ga, Cu and Al, 0.25
 $\% < \text{O} \leq 0.5\%$, 0.15% or less of C, 0.15% or less of N,

balance Fe;

- casting said alloy to form at least one ingot, wherein the solidified ingot comprises finely dispersed α -Fe, and $R_2Fe_{14}B$ and R-rich constituents;
- 5 - annealing said ingot at a temperature in the range of approximately 800°C to approximately 1200° C under an inert atmosphere of Ar or under vacuum to form an ingot which is free of said α -Fe phase;
- treating said ingots in hydrogen gas in order to
- 10 hydrogenate the R-rich constituents;
- coarsely pulverising said ingot;
- performing a fine pulverisation of said coarsely pulverised powder in an atmosphere comprising oxygen, oxidizing said powder;
- 15 wherein said finely pulverised powder comprises an oxygen content of $0.25 \text{ wt}\% < O \leq 0.5 \text{ wt}\%$, and said ingot has smallest dimensions in the range of 15 mm to 25 mm and said powder after said fine pulverisation has an average particle size (FSSS) in the range of around 4 μm to around
- 20 2.1 μm and contains no particles greater than around 20 μm .

10. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 9, wherein R is one or more of the elements Nd, Pr, Dy and Tb, $0.50\% < \text{Co} < 1.5\%$, $0.05\% < \text{Ga} < 0.25\%$ and $0.05\% < \text{Cu} < 0.20\%$.

25

11. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 9, wherein said powder has an average particle size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no particles greater than around 20 μm .

30

12. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 9, wherein said powder has an average particle size (FSSS) in the range of around 2.5 μm to around 3 μm and no particles greater than around 15 μm .
13. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 9, wherein said hydrogenating is performed at a temperature between around 450°C and 600°C.
14. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 9, wherein said hydrogenating is performed at a temperature between around 500°C and 550°C.
15. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 13, wherein said hydrogenating is performed under 0.5 to 1.5 bars of hydrogen gas for between around 1 hour to around 10 hours.
16. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 15, wherein said hydrogenating is performed at around 1 bar of hydrogen for around 5 hours.
17. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 14, wherein said hydrogenating is performed under 0.5 to 1.5 bars of hydrogen gas for between around 1 hour to around 10 hours.
18. A method to produce powders for use in R-Fe-B-M type

permanent magnets according to claim 17, wherein
said hydrogenating is performed at around 1 bar of hydrogen
for around 5 hours.

- 5 19. A method to produce powders for use in R-Fe-B-M type
permanent magnets according to claim 9, wherein
after said hydrogenating, said ingot is cooled to around
100°C under Ar gas.
- 10 20. A method to produce powders for use in R-Fe-B-M type
permanent magnets according to claim 9, wherein
said fine pulverisation is performed in two steps.
21. A method to produce powders for use in R-Fe-B-M type
15 permanent magnets according to claim 20, wherein
a first fine pulverisation of said coarsely pulverised
powder is performed in an inert atmosphere and a second fine
pulverisation of said finely pulverised powder is performed
in an atmosphere comprising oxygen, oxidizing said finely
20 pulverised powder, wherein said finely pulverised powder
comprises an oxygen content $0.25 \text{ wt}\% < O \leq 0.5 \text{ wt}\%$ after the
second fine pulverisation.
22. A method to produce powders for use in R-Fe-B-M type
25 permanent magnets according to claim 20, wherein said first
fine pulverisation and said second fine pulverisation is
performed using a jet mill.
23. A method to produce powders for use in R-Fe-B-M type
30 permanent magnets according to claim 20, wherein after said
first fine pulverisation, said powder has an average
particle size (FSSS) of around 4 μm and a particle size

distribution, wherein 30% of grains have a diameter of more than around 10 μm , and around 1 % of grains have a diameter of greater than between around 20 μm and around 25 μm .

5 24. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 20, wherein after said second fine pulverisation, said powder has an average particle size (FSSS) in the range of around 4 μm to around 2.1 μm and contains no particles greater than around
10 20 μm .

25. A method to produce powders for use in R-Fe-B-M type permanent magnets according to claim 20, wherein said powder has an average particle size (FSSS) of around 4
15 μm and a particle size distribution, wherein 30% of grains have a particle diameter of more than around 10 μm , and around 1 % have a diameter of greater of between around 20 μm and around 25 μm after the first fine pulverisation and said powder has an particle grain size (FSSS) in the range
20 of around 4 μm to around 2.1 μm and contains no particles greater than around 10 μm after the second fine pulverisation.

26. A method of producing a powder for use in the
25 manufacture of R-Fe-B-M type permanent magnets, comprising - providing an alloy consisting essentially by weight, of $28.00 \leq R \leq 32.00\%$, where R is at least one rare earth element including Y and the sum of Dy + Tb > 0.5, $0.50 \leq B \leq 2.00\%$, $0.50 \leq \text{Co} \leq 3.50\%$, $0.050 \leq M \leq 0.5\%$, where M is one or
30 more of the elements Ga, Cu and Al, $0.25 \% < O \leq 0.5\%$, 0.15% or less of C, 0.15% or less of N, balance Fe, said alloy having the form of an ingot;

- annealing said ingot at a temperature in the range of approximately 800°C to approximately 1200° C under an inert atmosphere of Ar or under vacuum to form an ingot which is free of said α -Fe phase;
- 5 - treating said ingots in hydrogen gas in order to hydrogenate the R-rich constituents;
- coarsely pulverising said ingot;
- performing a fine pulverisation of said coarsely pulverised powder in an atmosphere comprising oxygen,
- 10 oxidizing said powder;
- wherein said finely pulverised powder comprises an oxygen content of 0.25 wt% < O $\leq$ 0.5 wt% R is one or more of the elements Nd, Pr, Dy and Tb, 0.50% < Co < 1.5%, 0.05% < Ga < 0.25% and 0.05% < Cu < 0.20% and said powder has an average
- 15 particle size (FSSS) in the range of around 2.5 μ m to around 3 μ m.

27. A method to produce powders for use in a rare earth magnet according to claim 26, wherein

20 said ingot has dimensions in the range of 15 mm to 25 mm.

28. A method to produce powders for use in a rare earth magnet according to claim 27, wherein

 said hydrogenating is performed at a temperature of between

25 around 450°C and 600°C.

29. A method to produce powders for use in a rare earth magnet according to claim 27, wherein

 said hydrogenating is performed at a temperature of between

30 around 500°C and 550°C.

30. A method to produce powders for use in a rare earth

- magnet according to claim 28, wherein
said hydrogenating is performed under 0.5 to 1.5 bars of
hydrogen gas for between around 1 hour to around 10 hours
- 5 31. A method to produce powders for use in a rare earth
magnet according to claim 30, wherein
said hydrogenating is performed at around 1 bar hydrogen for
around 5 hours.
- 10 32. A method to produce powders for use in a rare earth
magnet according to claim 29, wherein
said hydrogenating is performed under 0.5 to 1.5 bars of
hydrogen gas for between around 1 hour to around 10 hours.
- 15 33. A method to produce powders for use in a rare earth
magnet according to claim 32, wherein
said hydrogenating is performed at around 1 bar hydrogen for
around 5 hours.
- 20 34. A method to produce powders for use in a rare earth
magnet according to claim 26, wherein
after said hydrogenating, said ingot is cooled to around
100°C under Ar gas.
- 25 35. A method to produce a R-Fe-B-M type permanent magnet
comprising:
- providing powder consisting essentially by weight, of
28.00 ≤ R ≤ 32.00%, where R is at least one rare earth
element including Y and the sum of Dy + Tb > 0.5, 0.50
30 ≤ B ≤ 2.00%, 0.50 ≤ Co ≤ 3.50%, 0.050 ≤ M ≤ 0.5%, where
M is one or more of the elements Ga, Cu and Al, 0.25
wt% < O ≤ 0.5%, 0.15% or less of C, 0.15% or less of N,

balance Fe;

- compacting said powder in a magnetic field to form a textured compact;
- sintering said compact to produce a magnet.

5 wherein said powder has an average particle size according to FSSS and said magnet has a average grain size, wherein said average grain size of said magnet is no more than 2.5 times the average particle size of said powder.

10 36. A method to produce a R-Fe-B-M type permanent magnet according to claim 35, wherein in said step of sintering a sintered magnet having an average grain size in a range of about 7.6 μm to about 4.2 μm is produced.

15

37. A method to produce a R-Fe-B-M type permanent magnet according to claim 35, wherein said powder after said second pulverisation has an average particle size according to FSSS of around 4.1 μm to around 2.6 μm and said magnet after sintering has an average grain size of around 7.6 μm to around 4.2 μm .

20