

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : E04C 5/01	A1	(11) International Publication Number: WO 97/11239 (43) International Publication Date: 27 March 1997 (27.03.97)
(21) International Application Number: PCT/EP96/04080 (22) International Filing Date: 18 September 1996 (18.09.96) (30) Priority Data: 9500769 19 September 1995 (19.09.95) BE (71) Applicant (for all designated States except US): N.V. BEKAERT S.A. [BE/BE]; Bekaertstraat 2, B-8550 Zwevegem (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): LAMBRECHTS, Ann [BE/BE]; Koningsveld 31, B-2200 Herentals (BE). (74) Agents: DEMEESTER, Gabriël et al.; N.V. Bekaert S.A., Bekaertstraat 2, B-8550 Zwevegem (BE).	(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.	

(54) Title: STEEL WIRE ELEMENT FOR MIXING INTO SUBSEQUENTLY HARDENING MATERIALS



(57) Abstract

The invention relates to a steel wire element (1) for mixing into subsequently hardening soft materials, said element consisting of hook-shaped ends (3) and a middle portion (2) the length/diameter ratio of which is between 20 and 100, in which the middle portion (2) of the element (1) displays a substantially circular cross section over essentially its entire length and in which the hook-shaped ends (3) of the element (1) are deformed by flattening.