**CLAIMS**

1. An antifouling coating composition, comprising:


a copolymer P; and

an antifouling agent; wherein:

the copolymer P is a copolymer of a monomer (a), a monomer (b), a monomer (c), and an ethylenically unsaturated monomer (d) other than the monomers (a) to (c);

the monomer (a) is represented by general formula (1);

[chemical formula 1]



(1)

in the general formula (1), $R^1$ is a methyl group, each of $R^2$, $R^3$, and $R^4$ is a triisopropylsilyl group;

content of the monomer (a) is 25 to 50mass% with respect to a total mass of the monomers (a) to (d);

each of the monomer (b) and (c) is a monomer having a common logarithm log P of n-octanol/water partition coefficient P of 0.00 to 0.59 and 0.60 to 0.95;

the monomer (c) is a monomer having only one unsaturated bond.