

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 November 2001 (01.11.2001)

PCT

(10) International Publication Number
WO 01/81354 A2

(51) International Patent Classification⁷: **C07F 7/16**

(21) International Application Number: PCT/US01/05417

(22) International Filing Date: 20 February 2001 (20.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/553,912 20 April 2000 (20.04.2000) US

(71) Applicant: **GENERAL ELECTRIC COMPANY**
[US/US]; 1 River Road, Schenectady, NY 12345 (US).

(72) Inventors: **LEWIS, Larry, Neil**; 7 Harvest Drive, Scotia, NY 12302 (US). **WARD, William, Jessup, III**; 1924 Hexam Road, Schenectady, NY 12309 (US). **BABLIN, John, Matthew**; 36 Ellsworth Street, Amsterdam, NY 12010 (US).

(74) Agents: **WINTER, Catherine, J.** et al.; General Electric Company, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR PREPARING A CONTACT MASS

(57) Abstract: A method for making an alkylhalosilane is provided wherein the method comprises heat treating silicon and a form of copper at a temperature greater than about 500 °C to produce a contact mass and effecting reaction between an alkyl halide and silicon in the presence of the contact mass to produce alkylhalosilane.

WO 01/81354 A2